LEVEL II

AMMRC TR 79-6

AD

AD A0 67199

DDC FILE COPY

**SYNTHESIS OF A
THIOPHENE-CONTAINING BISBENZIL
AND A DERIVED POLYQUINOXALINE**

12

February 1979

Approved for public release; distribution unlimited.

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

79 04 11 009

The findings in this report are not to be construed as an official *Department of the Army position*, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.

AMMRC TR 79-6

SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZIL AND
A DERIVED POLYQUINOXALINE

Macaione and Wentworth

DEPARTMENT OF THE ARMY
ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD 314

OFFICIAL BUSINESS

THIRD CLASS MAIL

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER AMMRC-TR-79-6	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZIL AND A DERIVED POLYQUINOXALINE,	5. TYPE OF REPORT & PERIOD COVERED Final Report	6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Domenic P. Macaione and Stanley E. Wentworth	8. CONTRACT OR GRANT NUMBER(s)	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DRXMR-RA	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS D/A Project: 1L162105AH84 AMCMS Code: 612105.11.H84 Agency Accession: DA OG4691	
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Army Materiel Development and Readiness Command, Alexandria, Virginia 22333	12. REPORT DATE February 1979	13. NUMBER OF PAGES 8
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) (12/15p.)	15. SECURITY CLASS. (of this report) Unclassified	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Synthesis (chemical) High-temperature polymers Polyquinoxalines Crosslinking		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) (SEE REVERSE SIDE) 89 04 11 009		

DD FORM 1 JAN 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Block No. 20

ABSTRACT

The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxaloyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable.

This report deals with the synthesis of 1,4-bis(2-thienylglyoxaloyl)-benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.

ACCESSION for	
NTIS	White Section ☒
DDC	Buff Section ☐
UNANNOUNCED	☐
JUSTIFICATION.....	
BY.....	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. and/or SPECIAL
A	

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

INTRODUCTION

Since the initial report by Hergenrother and Levine¹ in 1967, polyphenylquinoxaline (PPQ) polymers have been regarded as a promising class of thermally resistant resins. The development of PPQ polymers has been hindered partly by the high cost of one resin component, 1,4-bis(phenylglyoxaloyl)benzene (PGB), I, which is prepared from expensive starting materials via a multistep synthesis.

The classical approach to aromatic α -diketones, the benzoin condensation and subsequent oxidation, is an obvious direct synthetic route. However, this method has not been generally extended to the synthesis of aromatic bis- α -diketones. Attempts to condense benzaldehyde with terephthalaldehyde in the presence of cyanide ion have not been successful² (Equation 1).

This reaction results in a mixture of products, apparently benzoin and unidentified oligomers undoubtedly arising from the self-condensation of terephthalaldehyde.

A report by Jones et al.,³ has shown that this synthetic approach can be successful with certain aldehydes as when furan-2-carboxaldehyde is condensed with terephthalaldehyde to produce, after oxidation, 1,4-bis(2-furylglyoxaloyl)-benzene (BFGB) (Equation 2).

Cherill and Wentworth⁴ reported the attempted condensation of terephthalaldehyde with the three isomeric monocarboxaldehydes of pyridine (II-IV). Although

1. HERGENROTHER, P. M., and LEVINE, H. H. *Phenyl-Substituted Polyquinoxalines*. J. Polymer Sci., v. 5, part A-1, 1967, p. 1453.
2. KRATZER, R. H., PACIOREK, K. L., and KARLE, D. W. *Modified Benzoin Condensation of Terephthalaldehyde with Benzaldehyde*. J. Organic Chem., v. 41, 1976, p. 2230. This report appeared while the present investigation was in progress.
3. JONES, R. J., VAUGHN, R. W., O'RELL, M. K., and SHEPPARD, C. H. *Development of Autoclavable Addition-Type Polyimides*. TRW Systems Group, Contract NAS 3-15834, Final Report, NASA CR-121251, 1974.
4. CHERILL, R. J., and WENTWORTH, S. E. *Attempted Synthesis of Pyridine Containing Bis- α -Diketones via the Benzoin Condensation*. Army Materials and Mechanics Research Center, AMMRC TR 76-13, April 1976.

they investigated a variety of conditions, none could be found for preparation of the desired bis-benzoin. This report describes a further extension of the benzoin route in pursuit of a low-cost replacement of PGB. Thiophene-2-carboxaldehyde has been successfully condensed with terephthalaldehyde in a classical benzoin condensation. Oxidation affords the corresponding bis- α -diketone by the cupric sulfate-hexamethylphosphoric triamide method which we previously reported for the conversion of labile benzoin to benzils.⁵ A review of the literature revealed no prior report of the synthesis of this bis- α -diketone.

EXPERIMENTAL

Materials

The thiophene-2-carboxaldehyde (Aldrich) was redistilled, in vacuo, prior to use and stored under argon with refrigeration. Terephthalaldehyde (Aldrich) was crystallized from water/ethanol prior to use. The 3,3'-diaminobenzidine (DAB) was obtained from Whittaker, R&D, San Diego, CA, recrystallized according to Hergenrother⁶ and stored under argon at -15 C. The m-cresol was distilled prior to use. All other materials were used as received.

Synthesis - 1,4-bis(2-thienylglyoxaloyl)benzene (THGB)

To a stirred solution of thiophene-2-carboxaldehyde, (6.7 g, 0.05 mole) and terephthalaldehyde (11.2 g, 0.1 mole) in ethanol was added a solution of potassium cyanide (3 g, 4.6×10^{-2} mole) in 20 ml of water. The mixture turned dark brown immediately. After refluxing with stirring for one hour, the reaction mixture was cooled to ambient temperature. With due caution, (HCN, HOOD!) 6 ml concentrated hydrochloric acid was added to the mixture which was stirred for an additional hour and chilled in an ice bath. The orange precipitate which formed was isolated, washed with ethanol, and dried in vacuo for 16 hours.

This bisbenzoin intermediate was not readily soluble in most common solvents, therefore the entire crude product was subjected to oxidation. Appropriate amounts of cupric sulfate pentahydrate and hexamethylphosphoric triamide were stirred in a flask while a stream of oxygen was bubbled through for a period of 30 minutes. The intermediate bisbenzoin was added to the mixture in one portion, and the contents of the flask turned reddish at once.

The reaction mixture was allowed to stir at ambient temperature, under oxygen, for 48 hours during which time the color changed to bright green and the solution viscosity increased. The mixture was poured into distilled water, stirred, and

5. MACAIONE, D. P., and WENTWORTH, S. E. *An Improved Method for the Synthesis of Benzils from Benzoin*. Synthesis, no. 10, October 1974, p. 716.

6. HERGENROTHER, P. M. *Poly(phenylquinoxalines)*. Macromolecular Syntheses, v. 5, 1974, p. 17.

the resulting precipitate was isolated, washed with water, air dried, and finally, dried in vacuo for 16 hours. To remove any oligomeric species present, the product was extracted for a minimum of 24 hours with chloroform and the solvent removed to yield a yellow product. Material of suitable purity for confirmation of structure was obtained by chromatography on an 18x1/2-inch column packed with silica gel with benzene/ethyl acetate (9:1) as the eluent. Such treatment resulted in a bright yellow crystalline product melting at 172 to 175 C, yield was 4.3 g (25%).

Polymerization - Poly(2-thienyl)quinoxaline (PTHQ)

Stoichiometric amounts of recrystallized 3,3'-diaminobenzidine (DAB) and 1,4-bis(2-thienylglyoxaloyl)benzene (THGB) were placed in a 3-neck flask and dissolved in sufficient distilled m-cresol to produce a 10% concentration of reactants. A stream of inert gas (argon or nitrogen) was admitted and the mixture was stirred at ambient temperature for 72 hours. Over the period of the reaction, the color of the mixture became more intense and the solution viscosity increased to such an extent that small volumes of m-cresol were added to the reaction flask periodically to maintain a fluid state. The final concentration of the reaction mixture was thus reduced to 2.5%. The reaction mixture was poured into an excess of stirred methanol and the resulting suspension gently stirred for 16 hours. The precipitated polymer was isolated by filtration through a medium glass frit, washed twice with hot methanol, extracted for 60 hours with fresh methanol to remove occluded m-cresol, and finally dried in vacuo at 85 C for 24 hours to yield a yellow-orange solid product.

RESULTS

Structural Confirmation of THGB

The structure of the presumed bis- α -diketone obtained from the oxidation of the intermediate bisbenzoin was confirmed by means of infrared spectroscopy, elemental analysis, and the proton nuclear magnetic resonance spectrum of the pure compound. The infrared spectrum was determined in KBr on a Perkin-Elmer Model 137 spectrophotometer. The bands of major interest are a doublet at 1739 cm^{-1} ($5.75\text{ }\mu$) and 1642 cm^{-1} ($6.09\text{ }\mu$) representative of the α -diketone structure. The bands at 1515 cm^{-1} ($6.60\text{ }\mu$), 1408 cm^{-1} ($7.10\text{ }\mu$), and 1348 cm^{-1} ($7.42\text{ }\mu$) are characteristic of the 2-thiophene ring-stretching vibrations.⁷ Elemental analysis was conducted by Galbraith Laboratories, Incorporated, Knoxville, TN.

Calculated for $\text{C}_{18}\text{H}_{10}\text{O}_4\text{S}_2$, molecular weight 354.4:

	%C	%H	%S
Calculated -	61.00	2.82	18.11
Found -	61.18	2.93	17.92

The proton nuclear magnetic resonance spectrum was determined with a Perkin-Elmer Model R-32 NMR spectrometer relative to TMS:

δ (ppm)

7.2	2 proton triplet
7.9	4 proton doublet
8.15	4 proton singlet

7. GRONOWITZ, S. *Recent Advances in the Chemistry of Thiophenes*. Adv. in Heterocyclic Chem., v. 1, 1963, p. 12.

In accord with spectra of known compounds, the following proton assignments were made:

H_a 7.2 ppm, $H_{b,c}$ 7.9 ppm, H_d 8.15 ppm

These results are consistent with the reaction sequence

Characterization of PTHQ

Several properties of poly(2-thienyl)quinoxaline (PTHQ) have been determined:

a. Polymer Decomposition Temperature (PDT)

The decomposition temperature of PTHQ was determined with a DuPont Model 951 thermogravimetric analyzer at a heating rate of 10 C/min in air at a flow rate of 50 cc/min. The PDT for PTHQ under these conditions is 585 C, taken as the intersection of the extrapolation of the two linear portions of the weight loss curve.

b. Isothermal Aging

Isothermal aging was conducted with the DuPont Model 951 thermogravimetric analyzer. A sample of PTHQ was held at 400 C in static air, and weight loss was measured as a function of time. Under these conditions the half-life (T_{50}) for PTHQ is approximately 10 hours.

c. Elemental Analysis

The elemental analysis of PTHQ was conducted by Galbraith Laboratories, calculated for $C_{30}H_{16}N_4S_2$:

	%C	%H	%N	%S
Calculated -	72.56	3.25	11.28	12.91
Found -	71.19	3.29	11.00	12.29

<p>Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172 SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZIL AND A DERIVED POLYQUINOXALINE — Domenic P. Macaione and Stanley E. Wentworth</p> <p>Technical Report AMMRC TR 79-6, February 1979, 8 pp — illus-table, D/A Project IL162105AH84, AMCMS Code 612105.11.H84</p> <p>The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxalyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable. This report deals with the synthesis of 1,4-bis(2-thienylglyoxalyl)benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.</p>	<p>AD</p> <p>UNCLASSIFIED UNLIMITED DISTRIBUTION</p> <p>Key Words Synthesis (chemical) High-temperature polymers Polyquinoxaline</p>
<p>Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172 SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZIL AND A DERIVED POLYQUINOXALINE — Domenic P. Macaione and Stanley E. Wentworth</p> <p>Technical Report AMMRC TR 79-6, February 1979, 8 pp — illus-table, D/A Project IL162105AH84, AMCMS Code 612105.11.H84</p> <p>The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxalyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable. This report deals with the synthesis of 1,4-bis(2-thienylglyoxalyl)benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.</p>	<p>AD</p> <p>UNCLASSIFIED UNLIMITED DISTRIBUTION</p> <p>Key Words Synthesis (chemical) High-temperature polymers Polyquinoxaline</p>
<p>Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172 SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZIL AND A DERIVED POLYQUINOXALINE — Domenic P. Macaione and Stanley E. Wentworth</p> <p>Technical Report AMMRC TR 79-6, February 1979, 8 pp — illus-table, D/A Project IL162105AH84, AMCMS Code 612105.11.H84</p> <p>The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxalyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable. This report deals with the synthesis of 1,4-bis(2-thienylglyoxalyl)benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.</p>	<p>AD</p> <p>UNCLASSIFIED UNLIMITED DISTRIBUTION</p> <p>Key Words Synthesis (chemical) High-temperature polymers Polyquinoxaline</p>

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZYL
AND A DERIVED POLYQUINOXALINE — Domenic P. Macaione
and Stanley E. Wentworth

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Technical Report AMMRC TR 79-6, February 1979, 8 pp —
illus-table, D/A Project IL162105AH84,
AMCMS Code 612105.11.H84

Synthesis (chemical)
High-temperature
polymers
Polyquinoxaline

The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxaloyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable. This report deals with the synthesis of 1,4-bis(2-thienylglyoxaloyl)benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZYL
AND A DERIVED POLYQUINOXALINE — Domenic P. Macaione
and Stanley E. Wentworth

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Technical Report AMMRC TR 79-6, February 1979, 8 pp —
illus-table, D/A Project IL162105AH84,
AMCMS Code 612105.11.H84

Synthesis (chemical)
High-temperature
polymers
Polyquinoxaline

The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxaloyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable. This report deals with the synthesis of 1,4-bis(2-thienylglyoxaloyl)benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZYL
AND A DERIVED POLYQUINOXALINE — Domenic P. Macaione
and Stanley E. Wentworth

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Technical Report AMMRC TR 79-6, February 1979, 8 pp —
illus-table, D/A Project IL162105AH84,
AMCMS Code 612105.11.H84

Synthesis (chemical)
High-temperature
polymers
Polyquinoxaline

The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxaloyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable. This report deals with the synthesis of 1,4-bis(2-thienylglyoxaloyl)benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
SYNTHESIS OF A THIOPHENE-CONTAINING BISBENZYL
AND A DERIVED POLYQUINOXALINE — Domenic P. Macaione
and Stanley E. Wentworth

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Technical Report AMMRC TR 79-6, February 1979, 8 pp —
illus-table, D/A Project IL162105AH84,
AMCMS Code 612105.11.H84

Synthesis (chemical)
High-temperature
polymers
Polyquinoxaline

The development of polyphenylquinoxaline (PPQ) polymers as high-temperature-resistant materials has been hindered, in part, by the high cost of one resin component, 1,4-bis(phenylglyoxaloyl)benzene (PGB). A low-cost synthesis of PGB or PGB-type compounds to be substituted for PGB in the synthesis of PPQ-type polymers is therefore desirable. This report deals with the synthesis of 1,4-bis(2-thienylglyoxaloyl)benzene (THGB) by the benzoin condensation route in the search for a low-cost replacement for PGB, and its reaction with 3,3'-diaminobenzidine (DAB) to prepare poly(2-thienyl)quinoxaline (PTHQ). Some of the properties of the polymer have been determined and are discussed.

d. Intrinsic Viscosity

The determination of intrinsic viscosity was conducted at 30 C in *m*-cresol solution with a Cannon-Ubbelohde dilution viscometer. An intrinsic viscosity value of 1.42 dl/g was obtained for PTHQ, indicative of a polymer of substantial molecular weight.

e. Thermal Crosslinking and Torsional Braid Analysis

The thermal crosslinking and torsional braid analysis study of PTHQ was conducted in a manner identical to work which we reported earlier.⁸ The results of measuring the change in glass transition temperature ΔT_g (defined in Reference 8) as a function of the conditioning temperature for PTHQ are shown in Table 1, and graphically in Figure 1, with standard PPQ for comparison. These results clearly indicate an enhanced crosslinkability for PTHQ relative to PPQ.

Table 1. EFFECT OF THERMAL CROSSLINKING ON GLASS TRANSITION TEMPERATURE

	Conditioning Temperature (°C)	T_g (°C)	ΔT_g (°C)
PTHQ ^a	Ambient	372	-
	250	373	1
	300	380	8
	350	393	21
	400	416	44
	450	>487	>115
PPQ [†]	Ambient	350	-
	350	370	20
	400	390	40
	450	414	64

^aThis study

[†]Wentworth and Macaione

Figure 1. Change of glass transition with temperature.

8. WENTWORTH, S. E., and MACIONE, D. P. *Synthesis and Thermal Crosslinking of p,p'-Divinylbenzyl Endcapped Phenylquinoxaline Oligomers*. J. Polymer Sci., Polymer Chemistry Edition, v. 14, 1976, p. 1301.

DISCUSSION

There are several points which should be stated regarding the results. First, it is to be understood that by the very nature of the benzoin condensation reaction one must postulate the formation of isomeric bisbenzoin species even though no attempt was made to isolate and identify individual isomers. Such an undertaking would be difficult under optimum conditions. The intrinsic simplicity of our synthetic approach resides in the fact that upon oxidation all isomeric forms are converted to the same tetraketone. However, the problems arising from the self-condensation of thiophene-2-aldehyde and terephthalaldehyde which can occur under the conditions of the reaction to form 2,2'-thenil and a series of oligomers, respectively, are not so easily solved. Application of the modified benzoin condensation after Kratzer et al.,² is being investigated as a means of circumventing these problems.

With regard to the characterization of the PTHQ polymer, a PDT of 585 C is slightly lower than the PDT of standard PPQ, and would indicate a somewhat lower thermo-oxidative stability for PTHQ. This is affirmed by the results of the isothermal aging experiments where the T_{50} of standard PPQ is nine times greater than that of PTHQ. Finally, although the change in T_g as a function of conditioning temperature is markedly greater for PTHQ than for PPQ, as shown in Figure 1, the results of the isothermal aging experiment indicate an insufficient thermal resistance to endow PTHQ with an extended service lifetime at elevated temperature.

ACKNOWLEDGMENT

The authors wish to thank R. Cherill, M. Humora, and D. Larsen for their technical assistance during the course of this investigation.

DISTRIBUTION LIST

No. of Copies	To
1	Office of the Under Secretary of Defense for Research and Engineering, The Pentagon, Washington, D. C. 20301
12	Commander, Defense Documentation Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, Virginia 22314
1	Metals and Ceramics Information Center, Battelle Columbus Laboratories, 505 King Avenue, Columbus, Ohio 43201
	Office of the Deputy Chief of Staff for Research, Development, and Acquisition, Washington, D. C. 20310
2	ATTN: DAMA-ARZ
	Commander, Army Research Office, P. O. Box 12211, Research Triangle Park, North Carolina 27709
1	ATTN: Information Processing Office
	Commander, U. S. Army Materiel Development and Readiness Command, 5001 Eisenhower Avenue, Alexandria, Virginia 22333
1	ATTN: DRCLDC, Mr. R. Zentner
	Commander, U. S. Army Electronics Research and Development Command, Fort Monmouth, New Jersey 07703
1	ATTN: DRDCO-GG-DD
1	DRDCO-GG-DM
	Commander, U. S. Army Armament Research and Development Command, Dover, New Jersey 07801
2	ATTN: Technical Library
1	DRDAR-SCM, Mr. J. D. Corrie
	Director, U. S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, Maryland 21005
1	ATTN: DRDAR-TSB-S (STINFO)
	Commander, U. S. Army Natick Research and Development Command, Natick, Massachusetts 01760
1	ATTN: Technical Library
	Commander, Harry Diamond Laboratories, 2800 Powder Mill Road, Adelphi, Maryland 20783
1	ATTN: Technical Information Office
	Commander, Picatinny Arsenal, Dover, New Jersey 07801
1	ATTN: SARPA-RT-S
1	SARPA-FR-M-D, Plastics Technical Evaluation Center (PLASTEC), A. M. Anzalone

No. of Copies	To
4	Commander, Redstone Scientific Information Center, U. S. Army Missile Research and Development Command, Redstone Arsenal, Alabama 35809 ATTN: DRDMI-TB
1	Commander, U. S. Army Foreign Science and Technology Center, 220 7th Street, N. E., Charlottesville, Virginia 22901 ATTN: Mr. Marley, Military Tech
1	Commander, U. S. Army Environmental Hygiene Agency, Edgewood Arsenal, Maryland 21010 ATTN: Chief, Library Branch
1	Naval Research Laboratory, Washington, D. C. 20375 ATTN: Dr. J. M. Krafft - Code 8430
1	Chief of Naval Research, Arlington, Virginia 22217 ATTN: Code 471
1	Commander, Naval Surface Weapons Center, Silver Spring, Maryland 20910 ATTN: Dr. J. M. Augl
2	Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio 45433 ATTN: AFML/MXE/E. Morrissey
1	AFML/LC
1	AFML/LLP/D. M. Forney, Jr.
1	AFML/MBC/Stanley Schulman
1	National Aeronautics and Space Administration, Washington, D. C. 20546 ATTN: Mr. B. G. Achhammer
1	Mr. G. C. Deutsch - Code RW
1	National Aeronautics and Space Administration, Marshall Space Flight Center, Huntsville, Alabama 35812 ATTN: R. J. Schwinghamer, EH01, Director, M&P Laboratory
1	Mr. W. A. Wilson, EH41, Building 4612
1	National Aeronautics and Space Administration, Lewis Research Center, 21000 Brookpark Road, Mail Stop 49-1, Cleveland, Ohio 44135 ATTN: W. B. Alston
1	National Aeronautics and Space Administration, Langley Research Center, Hampton, Virginia 23365 ATTN: Mr. P. M. Hergenrother
1	Materials Sciences Corporation, Blue Bell Office Campus, Merion Towle House, Blue Bell, Pennsylvania 19422
1	The Charles Stark Draper Laboratory, 68 Albany Street, Cambridge, Massachusetts 02139

No. of
Copies

To

	Lockheed-Georgia Company, 86 South Cobb Drive, Marietta, Georgia 30063
1	ATTN: Materials & Processes Engrg. Dept. 71-11, Zone 54
1	Dr. R. J. Jones, TRW Defense and Space Systems Group, Bldg. 01, One Space Park, Redondo Beach, California 90278
1	Dr. N. Bilow, Hughes Aircraft Company, Culver City, California 90230
1	Dr. C. Hughes, AVCO/Lowell, 2 Industrial Avenue, Lowell, Massachusetts 01851
	Lockheed Missile & Space Company, P. O. Box 504, Sunnyvale, California 94008
1	ATTN: D81-12B154, Dr. Kim Bailie
	Director, Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172
2	ATTN: DRXMR-PL
1	DRXMR-WD
2	Authors