

AD-A136 955

POLYMERIZATION OF 3-METHYL-25-DIBROMOTHIOPHENE
UTILIZING N-BUTYL LITHIUM A. (U) UTAH UNIV SALT LAKE
CITY DEPT OF CHEMISTRY A AMER ET AL. 06 JAN 84 TR-20

1/1

UNCLASSIFIED

N00014-83-K-0470

F/G 7/3

NL




END

DATE

FILMED

2-84

DTIC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS 1963 A

REPORT DOCUMENTATION PAGE


READ INSTRUCTIONS
BEFORE COMPLETING FORM

1. REPORT NUMBER 20		2. GOVT ACCESSION NO. AD-A136955	3. RECIPIENT'S CATALOG NUMBER (12)
4. TITLE (and Subtitle) Polymerization of 3-Methyl-2,5-Dibromothiophene Utilizing n-Butyl Lithium and Copper(II) Chloride		5. TYPE OF REPORT & PERIOD COVERED Technical Report # 20	
7. AUTHOR(s) Adel Amer, Hans Zimmer, Kevin J. Mulligan, Harry B. Mark, Jr., Stanley Pons, Jerome F. McAleer		6. CONTRACT OR GRANT NUMBER(s) N00014-S3-K-0470	
9. PERFORMING ORGANIZATION NAME AND ADDRESS University of Utah Department of Chemistry Salt Lake City, UT 84112		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Task No. NR 359-718	
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Chemistry Program - Chemistry Code 472 Arlington, Virginia 22217		12. REPORT DATE January 6, 1984	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES	
		15. SECURITY CLASS. (of this report) Unclassified	
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	

16. DISTRIBUTION STATEMENT (of this Report)
This document has been approved for public release and sale; its distribution unlimited.

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

18. SUPPLEMENTARY NOTES



19. KEY WORDS (Continue on reverse side if necessary and identify by block number)
Polymer Electrodes **A**

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)
Formation of conducting thiophene polymers formed by the use of n-butyl lithium as a dehalogenating agent is described.

AD A 136955
DTIC FILE COPY

OFFICE OF NAVAL RESEARCH

Contract N00014-83-K-0470

Task No. NR 359-718

TECHNICAL REPORT NO. 20

Polymerization of 3-Methyl-2,5-Dibromothiophene
Utilizing n-Butyl Lithium and Copper(II) Chloride

By

Adel Amer
Hans Zimmer
Kevin J. Mulligan
Harry B. Mark, Jr.
Stanley Pons*
Jerome F. McAleer

Prepared for Publication in
Journal of Polymer Science and Polymer Chemistry

University of Utah
Department of Chemistry
Salt Lake City, Utah 84112

January 6, 1984

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited.

Polymerization of 3-Methyl-2,5-Dibromothiophene
Utilizing n-Butyl Lithium and Copper(II) Chloride

Accession For	
GRAFI	<input checked="" type="checkbox"/>
IAE	<input type="checkbox"/>
Announced	<input type="checkbox"/>
Classification	
Distribution/	
Availability Codes	
Dist.	Avail. and/or Special
A-1	



2

2

PI

Introduction

In recent years, there have been extensive research activities focussed on macromolecules with extended π -electron system¹. Among the many macromolecules studied, conjugated olefinic compounds (polyenes), have been given much attention. Various methods for their synthesis have been reported.

In the heterocyclic category, there are four reports on the synthesis of poly(3-substituted-2,5-thienylene) (substituent = H, CH₃) via coupling of 3-substituted-2,5-dibromothiénylmagnesium by nickel salt promoters.²⁻⁵ Recently Afanas'ev, et al. reported also about the preparation of poly(2,5-thienylene) by an electrochemical method.⁶ *was studied. was used*

The ability for charge transport through the thiophene polymer chain is an important criterion for achieving high conductivity. For that reason ~~we began to study~~ the synthesis of polyenes. The present investigation was undertaken to improve the synthesis of poly(3-methyl-2,5-thienylene) and to obtain a magnesium free material. ~~Therefore, we chose to use~~ *n*-butyl lithium as dehalogenating agent. Cu(II) chloride was utilized to serve as catalyst.

Experimental

Instrumentation

¹H- and ¹³C-NMR spectra were recorded on a Nicolet NT300 narrow bore spectrometer with 1180 E data system. Chemical shifts are expressed in δ relative to tetramethylsilane as internal standard. Infrared spectra (IR) were recorded using a Perkin-Elmer Model 599 spectrometer calibrated against the 1601 cm⁻¹ band of polystyrene.

Materials

3-Methyl-2,5-dibromothiophene was prepared according to the procedure by O. M. Cohn and S. Gronowitz.⁷ *n*-Butyl lithium was obtained as a solution in *n*-hexane from

Lithium Corporation of America; the anhydrous cupric chloride (golden label), from Aldrich Chemical Company was used as received. Tetrahydrofuran (THF) was distilled from sodium and benzophenone under an argon atmosphere.

Polymer Synthesis

A solution of 7.952 gm (0.031 mole) of 3-methyl-2,5-dibromothiophene in 40 ml of dry THF was treated with 44.4 ml (0.062 mole) of 1.4 N n-butyl lithium in hexane at -55°C under N₂ atmosphere. The resulting colorless suspension was stirred for 10 min. at this temperature, then 8.354 gm of anhydrous cupric chloride followed by 7.952 gm of 3-methyl-2,5-dibromothiophene were added. The reaction mixture was allowed to warm up to -5 to 5°C. Stirring was continued for 20 min. while dry oxygen was bubbled through the suspension for 30 min. The reaction mixture was hydrolyzed with an aqueous solution of 5 gm potassium cyanide in 500 ml of water. The resulting precipitate was filtered off, washed with water and methanol to yield 4 gm of polymeric material. It was first extracted with methanol to remove the low molecular weight polymer, followed by extraction with CHCl₃, leaving an insoluble residue. Analysis found for CHCl₃-extractable fraction: %C, 51.07; %H, 3.62; %S, 27.26; %Br, 11.68; %Cl, 5.38; %Cu, 0.83 (total 99.86%).

Results and Discussion

n-Butyl lithium/cupric chloride proved successful as a polymerization agent of 3-methyl-2,5-dibromothiophene. The yield of the polymer was found to be dependent on the reaction temperature.

In order to get further information about the stereoselectivity of C-C coupling by the present method, we have prepared the poly(3-methyl-2,5 thienylene) exactly as reported by T. Yamamoto et al.⁵ using Mg and NiCl₂(bpy) and compared some physical properties of the polymer synthesized by these different methods.

Poly(3-methyl-2,5-thienylene) prepared by the present method is light brown whereas the one prepared by the previously reported method is dark brown.⁵ The UV-vis spectra for the CHCl_3 -extractable polymers (Fig. 1) showed difference in position of λ_{max} and magnitude of absorbance. The polymer synthesized by the present method showed a rather narrow UV absorption band at 415 nm which may be attributed to a fairly uniform range of molecular weight of this polymer. On the other hand, the polymer prepared by the known method⁵ exhibited a low absorbance broad band at 420 nm indicating a wide range of molecular weight. $^1\text{H-NMR}$ (CDCl_3) spectra (Fig. 2) showed two singlet at δ 2.192 and 2.369 (3H, CH_3), and a peak at δ 6.902 (1H, thiophene ring proton) (for the polymer synthesized by $n\text{-BuLi/CuCl}_2$, Fig. 2A). For the polymer synthesized by $\text{Mg/NiCl}_2(\text{bpy})$ Fig. 2 (B) two singlet at δ 2.216 and 2.382 (3H, CH_3) and a singlet at δ 6.944 (1H, thiophene ring proton) were observed. The methyl group protons resonated as two singlet in both cases, however the integration over the area showed that one singlet predominated over the other in the case of the polymer synthesized by the present method. A result which can be explained by the fact that under oxidative coupling of 3-methyl-2,5-dibromo-thiophene mixed with the corresponding di-lithium species, the probability of symmetrical coupling of the aryl species is much lower than the probability of unsymmetrical coupling.⁸ A plausible explanation of the $^1\text{H-NMR}$ spectrum (A) is the presence of a mixture of transoid and cisoid forms I and II.

However, $^{13}\text{C-NMR}$ (CDCl_3) (Fig. 3) of poly(3-methyl-2,5-thienylene) prepared by our method showed eight different methyl groups by exhibiting peaks at δ 14.763, 14.815, 15.014, 15.173, 15.347, 15.376, 15.531 and 15.669. The IR-spectrum has a strong absorption band at 800 cm^{-1} which is due to the characteristic out-of-plane C-H deformation of the thiophene ring; it also showed bands at 1420 and 1490 cm^{-1} which are caused by the ring stretching of substituted thiophene.³

The room temperature conductivity of a compressed pellet showed the polymer to be an insulator. A drastic change in conductivity, however, was observed upon doping with iodine. The polymer-iodine adduct shows electric conductivity of $3.2 \times 10^{-2} \text{ S cm}^{-1}$ for the CHCl_3 -extract (iodine/polymer = 30 wt percent) which is about equal to the reported value of $2.8 \times 10^{-2} \text{ S cm}^{-1}$ which, however, contains much more iodine, namely 94 wt percent.

It is interesting to note that the average polymer chain contains 8 monomer units (calculated on the basis of the amount of bromine which is assumed to ^{be} present on chain ends only). This seems to confirm recent suggestions that long chain^s of the polymer ^{is} not a necessary condition for good conductivity.⁹

In conclusion, our new method yields an excellent Mg-free polymer. An explorational investigation utilizing *n*-BuLi/transition metal complexes as polymerization agents of dibromoarylenes including structural studies and detailed electric properties are in progress.

Acknowledgement




This research was supported in part by the National Science Foundation, Grant No. CHE8205873. S.P. thanks the Office of Naval Research for support of part of this work.

REFERENCES

- 1) G. Wegner, *Angew. Chem. Int. Ed. Engl.*, 20, 361 (1981).
- 2) T. Yamamoto, K. Sanechika, and A. Yamamoto, *J. Polym. Sci. Polym. Lett. Ed.*, 18, 9 (1980).
- 3) J. W.-P. Lin and L. P. Dudek, *J. Polym. Sci. Polym. Chem. Ed.*, 18, 2869 (1980).
- 4) T. Yamamoto, K. Sanechika, and A. Yamamoto, *Chem. Lett.*, 1079 (1981).
- 5) T. Yamamoto, and K. Sanechika, *Chem. and Ind.*, 301 (1982).
- 6) V. L. Afanas'ev, I. B. Nazarova, and M. L. Khidekel, *Izv. Akad. Nauk SSR, Ser. Khim.*, 1687 (1980).
- 7) P. M. Cohn and S. Gronowitz, *Acta Chem. Scand.*, 20, 1577 (1966).
- 8) G. M. Whitesides, W. F. Fischer, J. S. Filippo, R. W. Basche, and H. O. House, *J. Am. Chem. Soc.*, 91, 4873 (1969).
- 9) A. G. MacDiarmid, 5th Biennial Carl S. Marvel Symposium, Tuscon, Arizona, March 1983.

Adel Amer, Hans Zimmer, Kevin J. Mulligan and Harry B. Mark, Jr.
Department of Chemistry
University of Cincinnati
Cincinnati, Ohio 45221

Stanley Pons and Jerome F. McAleer
Department of Chemistry
University of Alberta
Edmonton, Alberta



ULTRAVIOLET SPECTRA OF POLY(3-METHYL-2,5-THIENYLENE)

SYNTHESIZED BY

— N-BULI AND Cu(II)Cl_2
..... Mg AND $\text{NiCl}_2(\text{BPY})$





Fig. 1

¹H-NMR SPECTRA


PPM 7.28 TO 6.22 PPM
INTEGRAL = 1000.00
PPM 2.67 TO 2.71 PPM
INTEGRAL = 2784.40

n-BuLi + CuCl₂



DATA SET = AAA .010
PPM 3.14 TO 3.71 PPM
INTEGRAL = 300.00
PPM 0.65 TO 0.58 PPM
INTEGRAL = 88.34
PPM 0.94 TO 0.58 PPM
INTEGRAL = 91.21

Mg + NiCl₂(bpy)



Solvent = CDCl₃

Fig. 2

DECOUPLED ¹³C-NMR SPECTRUM





Fig. 3