UNCLASSIFIED AD 404 429

DEFENSE DOCUMENTATION CENTER

FCIR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA. VIRGINIA



UNCLASSIFIED

NOTICE: When government or other dravings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U.S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the rold drawings, specifications, or other data is not to be regarded by implication or othervise as in any manner licensing the holder or any other person or comporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.



28 March 1963

404429

de la

FILE

ł

OTS: 65-21442

FOR REFERENCE ONLY AT EACH OF THE DDC OFFICES. THIS REPORT CANNOT DE SATISFACTORILY REPRODUCED; DDC DOILS NOT FURNISH COPIES.

1. ···· , . .

۰.

ARTICLES ON SOVIET POWDER

(a)

<u>;</u>.

AST A APR 30 1963 TISIA

U. S. DEPARTMENT OF COMMERCE . . OFFICE OF TECHNICAL SERVICES JOINT PUBLICATIONS RESEARCH SERVICE • . . Building T-30 Ohio Dr. and Independence Ave.', S.W. Washington 25, D. C.

Price: \$.50

Best Available Copy

FOREWORD

This publication was prepared under contract for the Joint Publications Research Service as a translation or foreign-language research service to the various federal government departments.

÷ .

The contents of this material in no way represent the policies, views or attitudes of the U. S. Government or of the parties to any distribution arrangement.

PROCUREMENT OF JPRS REPORTS

All JPRS reports may be ordered from the Office of Technical Services. Reports published prior to 1 February 1963 can be provided, for the most part, only in photocopy (xerox). Those published after 1 February 1963 will be provided in printed form.

Details on special subscription arrangements for JPRS social science reports will be provided upon request.

No cumulative subject index or catalog of all JPRS reports has been compiled.

All JPRS report: are listed in the <u>Monthly Catalog of U. S.</u> <u>Government Publications</u>, evailable on subscription at \$4.50 per year (\$6.00 foreign), including an annual index, from the Superintendent of Documents, J. S. Government Printing Office, Washington 25, D. C.

All JPRS scientific and technical reports are cataloged and subject-indexed in <u>Technical Translations</u>, published semimonthly by the Office of Technical Services, and also available on subscription (\$12.00 per year domestic, \$16,00 foreign) from the Superintendent of Documents. Semiannual indexes to <u>Technical Translations</u> are available at additional cost.

JPR5: 18.407

ARTICLES ON SOVIET POWDER METALLURGY

[Following is a translation of several articles on powder metallurgy published in Doklady Akademy Neuk SSSR (Reports of the Academy of Sciences USSR), Izvestiya Akademii Hauk SSSR (News of the Academy of Sciences USSR), and Izvestiya Vysshikh Uchebayth Zavedeniy, Tsvetanaya Metallurgiya, Chernaya Metallurgiya (News of Higher Educational Institutions, Non-Ferrous Metallurgy and Ferrous Metallurgy series) and Vestnik Mashinostroyeniya (Herald of Machine Building). Bibliographic information is given with individual articles.]

TABLE OF CONTENTS

Page

Bal'shin, M. Yu. and Dubrovskiy, A. P. Some Aspects of the Hydrostatic Pressing of Powders	1
Zhabrova, G. M., Kadenatsi, V. M., Azizov, T. S., Gordeyeva, A. A., Glazunov, P. Ya. and Gazalov, A.A. A hadiation Method of Proparing Finely Divided	
Metals and Oxides	6
Beyling, L. V. and Kislyakov, I. P. Wetting and Impregnation of Briqueites of Titanium and Zirconium Nitrides by Molton Cobalt and Nickel	9
Nikolayev, A. N. Dauses of Easination Cracks in Pressings Made of Metal Powders	16
Plotkin, S. Ya. and Samsonov, G. V. Pressing of Metal Powders	19

---- 8 -----

SOME ASPECTS OF THE HYDROSTATIC PRESSING OF POWDERS M. Yu. Bal'shin and A. P. Dubrovskiy Presented by Academician Bochvar 3 August 1960

Moscow, Doklady Akademii Nauk SSSR (Reports of the Academy of Sciences, USSR), Vol 136, No 2, 11 January 1961, pr 332-335.

Hydrostatic (isostatic) pressing of powders /17 has so far been used only up to pressures of 10-12 kg/mm², which gives no proper basis for formulating the laws governing the behavior of powders in response to such pressing.

We have used pressures of 10-60 kg/mm² with powders of electrolytic copper (poured density 1.82 g/cm³, tamped density 2.86 g/cm³), vortex iron (1.72 and 2.56 g/cm³), electrolytic nickel (2.57 and 3.70 g/cm³), and reduced molybdenum (tamped density 3.22 g/cm³). The particle sizes were less than 10 μ , except for the iron (particles < 90 μ). The powders were pressed into rods within elastic sheaths (initial diameter 11 mm, length 65 mm; linear dimensions reduced by 25-30% by pressing). The specimens for use in determining the strength in compression were cut into cylinders having a ratio of height h to diameter D of about 0.7; preliminary tests on specimens cut in various orientations from large pressings showed that the strength in compression was the same in all directions. The pressure was applied perpendicular to the ends in the tests.

Conventional pressing in steel dies was used at the same pressures on the same powders for comparison. Specimens with $h/D \approx 0.7$ were used to measure the density as a function of pressure for both methods of pressing, the density being measured by weighing in air and in a liquid.

- 1



Fig. 1. Relation of 0 to p for a) hydrostatic pressing and b) ordinary pressing; 1) Cu; 2) Fe; 3) Ni; 4) Mo. The conventionally pressed specimens were tested in compression along the pressing axis (cylinders 15 mm in diameter having h/D # 0.7) and at right angles to that axis (rectangular blocks of side a perpendicular to the pressure of 6 mm).

Figure 1 shows the relative density 0 as a function of pressure p for both forms of pressing; hydrostatic pressing is clearly always the more effective. The reduction in the pressure needed is especially pronounced for fine and hard materials (nickel and molybdenum; hydrostatic pressures need be 30-50% less to give the same density), the reduc-

tion being some 20-30% for fine copper powder. The smallest effect occurs with the coarse iron powder (reduction of only 10-20%).

Figure 2 shows log Θ in relation to log p for both forms of pressing; the relation is linear, so 2 the relation of Θ to p may be put as

$$\frac{P}{Pmax} = \Phi^m, \qquad (1)$$

in which p_{max} is the maximum pressure (that giving $\Theta = 1$) and m is a constant. That is, the resistance to deformation is specified by p_{max} and m (see Fig. 2 for values of m), which are larger for hydrostatic pressing, except in the case of Mo. Table 1 gives p_{max} together with the hardness of the metals; the p_{max} for the softer metals (Cu and Fe) are almost the same for both methods, but those for the harder metals are less when hydrostatic pressing is used (by 24% for Ni and by 32% for Mo).

Table 2 gives σ (the strength in compression) for Cu (a typical soft metal) and Mo (a typical hard one). Ordinary pressings gives considerable anisotropy in ; the ratio of 11 to o1 is particularly large at low pressures, and it is larger

- 2



Fig. 2. delation of log p to log 0 for a) hydrostatic and b) ordinary pressing: 1) Cu; 2) Fe; 3) Ni; 4) No; m: 1a) 5.65; 2a) 5.26; 3a) 5.5; 4a) 5.4; 1b) 4.45; 2b) 4.66; 3b) 4.82; 4b) 5.33.

for Mo (hard) than for Cu (soft). A hydrostatically pressed material has the same strength in all directions, and this is roughly equal to the highest strength in ordinary pressing

tal	н _в ,	kg/mm ²	Pmax, kg/nm ²			
e X	Ann.	W. h.	Hydro	Ord.		
Cu	40	to 120	104	108		
Fe	60	" 180	111	112		
Ni	90	1 250	171	224		
Mo	150	" 270	244	360		

.....

Γ

(for Cu) or rather larger than it (by 20-130% for Mo).

In ordinary presering, the pressure p is reduced by an amount Δp as a result of friction at the walls of the die $\sqrt{2}$:

ŗ

¥=H#,

in which $\frac{1}{5}$ (= 0.3-0.4) is the lateral pressure coefficient, h/D is herew0.7, and μ (the coefficient of friction) is 0.15 to 0.35; then $\frac{4}{2}$ /p is 0.1 to 0.4 in our case, so the effective pressure is 10-40% less than the nominal pressure. This shows why p_{max} for hydrostatic pressing is less than that for ordinary

Material	Pressure,	e for ord kg	• pressing, /mm ²	5 1, /5,	€ for hydro.,	
	kg/mm-	11	1	41 ⁻ 11	kg/mm ²	
Cu	10 20 40 60	4.68 9.58 19.4 22.4	0.74 3.18 10.1 13.8	6.3 3.0 1.9 1.6	4.26 8.24 15.4 22.9	
Мо	10 20 40 60	0.28 0.84 4.35 12.2	- 1.0	12.2	0.33 1.94 7.5 18.1	

Table 2

pressing (by 1% for Fe, by 32% for Mc). Table 1 shows that p_{max} is determined mainly by the hardness (internal strength) of the particles, being between the hardness values for the annealed and maximally work-hardened states in most cases. Only in the case of molybdenum (the hardest metal) is p_{max} for ordinary pressing substantially greater than the hardness in the maximally work-hardened state; this is to be attributed to frictional losses. The difference between the p for a given degree of compression also corresponds with the p_{max} and m for hydrostatic and ordinary pressing.

There are two explanations for the differences between the hard and soft metals.

1. The friction and frictional losses in the dies are much larger for the hard metals, in which case the differences in the p_{max} and p would be larger for the harder metals. This was tested by reference to the ejection pressure for h/D = 0.7for these powders (the pressure is almost equal to the pressure loss at the wall). In every case the ejection pressure was about 40% of the total pressure (38% for Mo, 41% for Cu), so this possibility is eliminated.

2. Seisure of the particles of the softer metals /37appears more probable, for this greatly increases the adhesion between particles and hence the internal friction (e.e., the resistance to deformation). The effect is especially preminent in the hydrostatic pressing of soft metals, for it operates in all directions here, whereas in ordinary pressing it operates in one direction only. That is, p_{max} differs little between hydrostatic and ordinary pressing for soft metals (the absence of external friction is balanced by the higher internal friction) but differe greatly for the hard metals.

That is, hydrostatic pressing is especially effective for forming hard-metal powders to high density and strength.

> Baykov Institute of Netallurgy Received Academy of Sciences of the USSR 12 July 1960

THE TOORATEY

- 1. B. A. Borok. Coll.: Powder Metallurgy. Yaroslavl, 1956, p. 187.
- 2. N. Tu. Bal'shin. Science of Netal Powders. Moscow, 1948.
- 3. A. P. Semenov. Seisure of Metals. Moscow, 1958.

A RADIATION METHOD OF PREPARING FINELY DIVIDED METALS AND OXIDES

G. M. Zhabrova, V. M. Kadenatsi, T. S. Azizov, A. A.

Gordeyeva, P. Ya. Glazunov, and A. A. Gezalov

Moscow, Izvestim Akademii Nauk SSSR (News of the Academy of Sciences, USSR), Vol No 9, Sep 1962, pp 1,690-1,692.

Some problems in the use of active solids involve a decision on the conditions of preparation that give the maximum specific surface. The last stage of preparation is often a topochemical decomposition of some compound (salt or hydroxide, say) or a reduction; but such processes require high temperatures, at which sintering accompanies the formation of the new phase. This often causes difficulty in the preparation, especially for oxides.

Radiation-induced decomposition of a solid compound occurs at much lower temperatures 227 and so may not be associated with appreciable sintering. This makes it of interest to examine the radiolysis of salts and hydroxides for the preparation of metals and oxides as powders.

We have used the hydroxides of Zr, Fe, and Al, as well as nickel oxalate, copper oxalate, and basic copper carbonate; these were made in solution from the nitrates with ammonia (hydroxides) or oxalic acid (oxalates), apart from the copper carbonate, which was the commercial chemically pure grade. The gource was the electron beam from the linear accelerator at the Institute of Physical Chemistry, Academy of Sciences of the USSR. The specimen (1-2 g) was placed in an aluminium cell fitted with an external cooling jacket; this cell was closed with an aluminium foil (10 mg/cm²), The thickness of the layer is of powder corresponded roughly to the extreme range of the electrons. The cooling jacket was fed with water for dose rates up tow10⁴ rad/sec; liquid nitrogen was used instead for dose rates up tow10⁵ rad/sec. These measures ensured that the temperature of the powder did not exceed 40-50° (as read by a thin chromelalumel thermocouple placed in the middle of the layer). The irradiations were performed in air or with nitrogen flowing over the specimen.

The energy absorbed by the specimen was measured by placing between the window of the accelerator and the sample a menitor ionization chamber having walls of aluminium foil almost transparent to electrons /27. The chamber was calibrated by reference to the current reaching an electrode placed at the bottom of a glass cell. The ionization current was kept constant. The dose rate was calculated from the current reaching the electrode in the glass cell (without a specimen); in some cases it was checked by means of ferrous sulfate and cerium methods.

The irradiated specimens were subjected to kinetic and Xray analysis to determine the extent of conversion and the phase composition of the products. The specific surface of the oxide or metal was determined from the adsorption of n-pentame, bensene, or cyclohexane at 18° , and also with krypton at -196°.

Table 1

Initial :	Radi	olysis	. 5 .	Py	rolysis	
Compound	Cond.	Comp.	m ² /g	Cond.	Comp.	-1
Zr(OH)	6 x 10 ⁹ rad	2r0 ₂	300- 350	Air, 400°	2r0 ₂	100
Fe(OE)3*	10 ¹⁰ rad in air	F.203	50	Air, 450-500°	r.203	- 10
N1C204.2H20	10 ¹⁰ rad in No	N1 95% N10 5%	120	Vecuum, 280°	N1 95% N10 5%	10
CuC204.14H20	5 x 109 ² rad in air	Cu 98% Cu 0 2%	60	Vacuum, 280°	Cu 90% Cu ₂ 0 10%	. 9
CuC03.Cu(OH)2	7 x 10 ⁹ rad in air	CEO	40	Air	CLO	10

Specific Surface of Solids Formed by Radiolysis Pyrelysis from Inorganic Compounds

"X-ray analysis by M. Ya. Kushnerev indicates that the composition was FeOOH after drying.

All compounds showed appreciable decomposition after deses exceeding 10° rad, decomposition being extensive for ones of 109-

10¹⁰ rad. Radiolysis at low temperatures gave mainly the metals from the exalates even in air, whereas pyrolysis in air at 300-350° gives the exides.

The specific surface of a metal or oxide made by radiolysis was usually much larger than that of one made by pyrelysis, especially for the oxalates, where the ratio of the two was 10 or more. The hydroxides of Zr and Fe gave oxides of high specific surface, but A1(OH)₃ gave the same specific surface as by pyrolysis at 400-450°.

Conclusions

1. Radiolysis of solid hydroxides, oxalates, and carbonates at low temperatures produces finely divided metals and oxides.

2. Metals and oxides made by radiolysis have specific surfaces greatly exceeding those of the same materials as made by pyrolysis.

Institute of Physical Chemistry, 6 April 1962 Academy of Sciences of the USSR

BIBLIOGRAPHY

- V. A. Gordeyeva, Ye. V. Yegorov, G. M. Zhabrova, B. M. Kadenatsi, and S. Z. Roginskiy. <u>Dokl. Akad. Nauk SSER.</u> <u>136</u>, 1364 (1961).
- 2. P. Xa. Glazunov and T. B. Radziyevskiy. Action of Ionizing Radiations on Inorganic and Organic Systems. Izd. Akad. Nauk SSSR, Moscow, 1958, p. 395.

CBO: 1879-X

Construction of the second

WETTING AND IMPREGNATION OF BRIQUETTES OF TITANIUM AND ZIRCONIUM

NITRIDES BY MOLTEN COBALT AND NICKEL

L. V. Beylins and I. P. Kislyakov

(Department of Rare-Metal Metallurgy, Krasnodar Institute of

Nonferrous Metals)

Ordzhonikidze, Izvestiya Vysshikh Uchebnykh Zavedeniy, Tsvetnaya Metallurgiya (News of Higher Educational Teatitutions, Mon-ferrous Hetellurgy), No 3, 1952, pr 129-134

Combinations of the hard and refractory carbides, nitrides, borides, and silicides of metals of groups IV, V. and VI are of interest as new materials that are hard, heat-resistant, and wear-resistant /1-19/.

Carbides of these metals are now widely used in hard alloys, but little work has been done on the nitrides /117, so studies on methods of preparation and properties are of considerable interest. In particular, this applies to wetting and impregnation by metals of the iron group and also to sintering; these topics are considered here for the pewdered nitrides, nickel and iron being the metals used.

The nitrides were made from the metals:

or from the oxidas:

 $Me + \frac{1}{2}N_2 = MeN$ $MeO_2 + 2C + \frac{1}{2}N_2 = MeN + 2CO.$

The metals and oxides were standard commercial grades. The titanium powder was not less than 98% pure, the main impurities being hydrogen (about 0.5%), Ca (\neq 0.05%), and nitrogen (\geq 0.07%). The zirconium powder was not less than 98% pure, the main impurities being Ca, 0, Si, and Ti (0.3 - 0.5% each). The TiO₂ was of 99.5% purity, the impurities being oxides of iron, silicon, and sulfur (0.1 - 0.25% each) and P₂O₅ (\geq 0.05%). The ZrO₂ was not less than 98.85% pure, the main

impurities being SiO₂ ($\frac{1}{2}$ 0.35%), CaO ($\frac{1}{2}$ 0.28%), TiO₂ ($\frac{1}{2}$ 0.5%), and Pe₂O₃ ($\frac{1}{2}$ 0.55%).

The nitrides were made from the metals in a resistance furnace having an alundum tube and a silite heater; a furnace with a graphite tube as heater was used for the oxides. The nitrogen was purified by passage over heated copper turnings, then through a titanium tube, and through a column containing silicagel and phosphorus pentexide. Table 1 gives the compositions and lattice parameters of the products (the Kjehldahl method was used for nitrogen).

			Tabl	• 1		
		•		÷		
Compositions.	and	i.	ttice	Parameters	of	Nitrides

		X.	5	C.	\$	Paran	
# 1 ti	ride of	Stoich.	htp.	Total	Free	Theor.	Noas.
Ti,	from metal	22.65	21.6		-	4.230	4.2307
Ti,	from oxide	at the second se	20.2	1.17	0.22	Ħ	4.216
Zr,	from metal	13.31	12.97	-	-	4.567	4.557
Zr,	from oxide		9.77	2.18	0.14	11	-

Error 0.1 - 0.25 Error 0.2 - 0.5%

The metals were mitrided in two stages, the temperature being raised slowly to the maximum in each stage (1100 and 1150° respectively, first heating 3.5 hr, ascend 10 - 15 min., time at first maximum 1.5 km, at second 1 hr). The oxides (mixed with lamp black) were mitrided in three stages at 1600° for times of 1 hr, $\frac{1}{2}$ hr, and $\frac{1}{2}$ hr, the time to reach the maximum temperature being 1 hr. The mixture was broken up and ground after each heating.

Table 2

Métaride ef		S1	10, A	.	
NICTIGE OI	-2.4	2.4-3.6	3.6-4.8	4.8-5	Mean
Ti, from metal Ti, from oxide Zr, from metal Zr, from oxide	31.2 54.7 37.4 52.1	33.9 23.9 25.4 19.6	22.4 12:5 15.7 12.9	12.2 8.9 21.5 15.4	2.95 2.45 3.24 2.47

10

Grain-Size Distribution (%)

Table 1 shows that the motals mays much better approach to the theoretical composition; the products from the omides always of much carbon no matter what the semposition of the Birture. portion of carbon could be reduced only by making the estimat in initial mixture equal to the stelekionetric or less: but then the sucdust contained less mitregen, because some cargon remained. it is not possible to make mitrides approaching the theoretical composition from the oxides in the presence of carbon.

Table 2 gives grain-size assourements ande under the aisrescene. The oxides give much smaller grain sizes, as one would expect, for the earbon hinders the growth of the grains of nitride.

The powders were rendered convenient to handle by mixing them with a 55 solution of rubber in bensime (2 ac per 100 g); the mixture was dried for 12 hr at 80°, and cylinders 7.8 mm in dismeter and 6 mm hd were pressed in a steel die to give porosities not exceeding 305. mass of titanium mitride was 0.85 g and the pressure was 1 1/000; corresponding figures for sirconium mitride are 1.2 g and 1.2 t/on".

	TEDLO 3							
	St	storing	Conditio	ne	_ 1			
We have do	Heatir	Heating 1 Heating 2						
of	°c	min	°c	min	- t			
T1** E2#	500-600 #	45	1400 1450	60 60	Ti Ti O			

e specimens vere baked a vacuus even hevines a ass bulb and a molecul num heater to increase eir strength and remove e bonding agent (Table 3). ble 4 gives the limits variation of the poresity and density, as well as the compositions.

*res.pressure Hg col: 1-2.10-3 Table 4

Preparation of Briquettes from Mitrides

		Mitride		The proportion of
Property	Ti	Zr	Ti, from oxide	than theoretical,
Porosity, \$				sult of the resi-
pressed	23-38	39-42	42-45	dual axygen,
sintered	31-34	38-39	37-39	though there may
8. $q_{1} q/cm^{3}$				have been a ten-
การสุรุธป	3.2-3.3	4.0-4.1	2.8-3.0	dency for Mali-Me
sintered	3.4-3.6	4.2-4.3	3.2-3.3	solid solutions
¥. \$				to form as a re-
before	21.6	12.97	20.20	sult of decompo-
after	20.77	12.45	19.02	sition of the ni-
Tommile				tride under vac-
SVI MULOI	774 33	ZrN	TIN	uum. Both ef-
efter	M NO.96	2710.97	T1N0.89	fects can affect
WT COT.	1 **** 0.92	0.93	0.84	

the wetting by molten metals; the first tends to hinder it and the second to facilitate it, for oxides are usually less readily wetted than clean metals.



Fig. 1. Apparatus for impregnating briquettes: 1) drop of metal, 2) specimen, 3) molybdenum screen, 4) molybdenum heater, 5) Al₂O₃ support.

The specimens were tested for wetting and impregnation with nickel and cobalt in the furnace with the molybdenum heater, the residual pressure being 1-2 a Hg. A thin pressed disc of the powdered metal was placed on top of the specimen, which rested on an alumina plate. The temperature was measured (with an optical pyremeter) and the metal was observed via the glass bulb, there being holes in the heater and screen for this purpose (Fig. 1). This gave the temperature of the drop of metal to ± 20°C; the correction for absorption in the glass was taken as 50°. The cohalt powder had the following composition (%):

99.5 Co, 0.22 Ni, 0.10 **G**, 0.01 C, 0.06 Fe, 0.04 Si, and 0.07 water; the nickel: 99.56 Ni, 0.07 Co, 0.10 **O**, 0.01 C, 0.056 Fe, 0.04 Si, 0.016 C; 0.14 water. The specimens were brought up to temperature over a period of 45 min and were kept at temperature for 30 min; Table 5 gives the results, including the mean contact angles. Figure 2 shows the microstructure of impregnated titanium nitride.

	C	0			Li I		
90	Porosi	ty, \$	Angle,	00	on Porosity, \$		
-0	before	after	deg		before	after	deg
			TiN fro	m netal		·	
490	32	7.9	28	1450	34	20	36.5
560	31	8.4	-	1520	34	3.7	••
640	33	4-4	-	1600	33	9.8	
			TiN fro	m oxide			
490	37	37		1450	37	37	-
560	38	38	69.5	1520	37	37	47.5
610	37	37	-	1600	37	37	••

Table 5

15

			ZIN II	om metal		*	
1490	38	38	-	1450	38	38 🎂	_
1560	-	-	56	1520	39	39	22.5
1640	-		28	1600	39	39	~~;,
Fig. 2. Sections of TiN briquettes impregnated with a) Ni, x 600; b) Ni, x 1500; c) Co, x 1500		nilable pl suitable production	notografi for 17	bl an tu bu va ma nu po pr pl th oc co te pr th sc co te pr th sc fc ti re an sc fc ti th sc fc ti th sc fc co te pr th sc fc co te pr th sc fc co te pr th sc fc co te pr th sc fc co te pr th sc fc co te pr th sc fc co te pr th sc fc fc fc fc fc fc fc fc fc fc fc fc fc	It was e to mean gle at th res on ac bbling of lues give te, on ac mber of m rosity. egnation ete, and an 90°, : cur. The me more new mposition ontent is onded nit: ovement, ne reverse ontent dur cause a ormed. in itroge: nent dur cause a ormed. ing is as esidual of to the fit cause a ormed. ing is as esidual of to all the to all the type start the the spectrum ontact an	a not alwa sure the one count of the meta- en are only count of heasurement However, is reason the angle so wetting etals give and some still too riding give and some enitrogen oxygen the urnace. n is espec- ing vacuum solid solut the incomp sociated w rygen, for eadily we es also pro- al from py he pores. obalt began 20°; melt ed at the pecimen of somewhat completel gle fell g	ys possi- ontact tempera- pronounced 1. The y approxi- the small its and the the im- mably com- s are less a does e nitrides chiometric e nitrogen b low. Ex- ves no im- times even by because h is re- at leaks The loss chilly pro- a sintering, ition is blete wet- with the coxides tted. Ad- revent the enetrating an to melt the nickel ting al- contact (5/. The to wet after it by causel

1.3

from 90° to the value given in Table 5, thereafter remaining constant. The size of the drop decreased when the metal impregnated the sample, but the shape remained the same.

Complete improvation was attained only for titanium nitride made from the metal, the finely divided carbon and residual oxide hindered the impregnation of materials derived from oxides, and the very small grains also tended to interrupt the capillary channels.

The impregnation was hindered by external factors, not by lack of wetting, for a thin film of metal remained adhering to the surface of the specimen after cooling; this film was formed by the flowing away of the metal, and it would not be present if the material were not wetted.

The impregnated titanium nitride contained two very different phases, namely rounded and prominent grains of nitride (in places intergrown with loss of boundaries) and an extensive uniform network of metal between the grains. The pseudobinary combination of nitride with cobalt (or nickel) may be of eutectic type, as a result of limited solubility of the nitride in the metal. The reduction in the melting point of the metal at the contact with the grains also indicates that the product is a eutectio. The solubility of the nitride in the metal is also confirmed indirectly by the very much enlarged grains of nitride (relative to the inital grain size); this points to recrystallization via the liquid state, which would be impossible unless the nitride dissolves in the liquid but has a limited solubility in the solid The ratio of the volumes of the two phases as seen on the state. photomicrographs corresponds roughly with the residual porosity as calculated from the volume and weight of the impregnated specimen.

<u>Conclusions</u>

- 1. Titanium nitride is wetted by cobalt and nickel; the contact angles are much less than 90°.
- 2. Porous briquettes pressed from titanium nitride can be impregnated by moltan metals; the purity and grain size are the controlling factors.
- 3. Titanium nitride made from the high-purity metal can be impregnated reasonably completely by cobalt and nickel; the oxide gives a product that is wetted but not impregnated, which is attributed to contamination with free carbon and to the small grain size.
- 4. Zirconium nitride made from the metal is wetted by cobalt and nickel, but it was not impregnated under the conditions used. The reason is considered to be as above; some residual oxygen may also have an effect.

5. Some suppositions are made as to pseudobinary combinations of titanium nitride with nickel and cobult, which appear to be sutsctic, the nitride being of limited solubility in the metal in the solid and liquid states.

Received June 19, 1961.

BINLIOGRAFHT

- 1. Refractory and Corrosion-Resistant Cornet Materials [translated from English], Moscow, 1959.
- 2. F. Aisenkolb. Introduction to Powder Metallurgy [translated from German], Moscow, 1959.
- 3. High-Temperature Technology, edited by I. E. Campbell [translated from English], Moscow, 1959.
- 4. G. V. Sameonov and Ya. S. Umanakiy. Hard Compounds of Refractory Netals, Moscow, 1956.
- 5. Kiffer and Schwarzkopf. Hard Alloys [translated from German], Moscow, 1957.
- 6. V. I. Yeremenko. Titanium Carbide and Compounds Based on It. Kiev, 1957.
- 7. Hetzel and Skolnik. Components of Titanium Carbide made by Impregnation. In: Refractory Metallic Materials [translated from English], Izd-vo Inost. Lit., Moscow, 1955.
- 8. G. V. Samsonov, A. F. Zhigach, and others. Boron, its Compounds and Alloys. Kiev, 1960.
- 9. K. I. Portney and G. V. Samsonov. Beride Alloys. Izd-vo VINITI, Mescow, 1959.
- 10. Nook. Mechinery, 35, 5 (1959).
- 11. Kingery and Holden. Chemistry and Technology of Silicates, No 1. Ind-vo Inost. Lit., 1956.

15

CSO: 1879-N

CAUSES OF LAMINATION CRACKS IN PRESSINGS MADE OF METAL POWDERS-4. N. Nikolayov

Mosocry, Izvestiya Vysshikh Uchebnykh Zavedeniy, Chernaya Metallurgiya (News of higher Educational Institutions, Ferrous Metallurgy, No 2 13962, pp 101-103.

The formation of these cracks is usually represented as



follows. Expansion in the section a-a (Fig. 1) during ejection causes cracks to appear 217; the extent of the elastic aftereffect at right angles to the pressing direction is 0.15-, 0.30% for the best types of industrial powders and may be as much as 1% for powders of poor quality /1/. The elastic stretching of the cylindrical steel die is usually neglected, but ones having ratios of outside to inside diameters of 1.4-3.0 give [27 expansions of 0.039 to 0.676% in response to pressures of 500 to 4000 kg/cm², so the effect cannot be neglected. The following observations illustrate this.

Fig. 1. Formation of cracks [17.

Cylinders 10.25-10.65 mm high were pressed from grade Τ. 4M iron powder at a fixed pressure of 4 t/cm² [37, the dies having an internal diameter of 25.05 mm and an external one of 40 to 100 mm. All specimens from the 40 mm die showed cracks (Fig. 2).

Brash inserts of trolleybuses have been observed to 2. have laminated cracks after pressing; similar cracks are found when specimens 5 nm high were pressed in the same dis (internal hole 60 mm long, 20 mm wide) ". These cracks occur along the specimens on the sides (Fig. 3) at the point where the die was

* Pressings made by N. N. Letevich.

Available photograph not suitable

Fig. 2. Layered cracks in cylinders of iron powder. tereffect cannot explain cracks of this shape and position. 3. Two dies were made of grey cast iron; one of these was enclosed in a shroud made of St. 3 steel in the hot state.

These dies were used with AM powders to press cylinders of various heights at a fixed pressure of 4 t/cm². All specimens from the unsupported die showed cracks (Fig. 4a), but only the highest ones from the supported die (Fig. 4b).

These observations show that elastic stretching of the die is one of the main causes of cracking; the die expands during the pressing but contracts when the pressure is released. This contraction is opposed by the friction between specimen and die, and also by the resistance of the specimen.

Fig. 3. Layered cracks on a rectangular specimen.

reproduction7

Available photograph not suitable for

The clustic deformation may vanish as soon as the pressure is removed, before the specimen is ejected, or during the ejection; the specimen simultaneously expands (elastic aftereffect). The condition for the specimen to be free from cracks may be put as

in which ϵ is the elastic deformation of the plunger, d is the diameter or other dimension of the die perpendicular to the pressing direction, s is the total wall thickness of the specimen in the direction of d, y is the relative deformation of the specimen as a result of elastic expansion, and δ is the permissable deformation of the specimen. This δ is dependent on the mode of deformation as well as on the properties of the material; the δ for hydrostatic compression is larger than that for compression in a plane or along a line. The more nearly the stress distribution is to linear, the smaller δ [4].

> [Evailable photograph not suitable for reproduction]

Fig. 4. Specimens of iron powder pressed in cast-iron dies: a) without shroud; b) with shroud.

The above explanation of the cracks appears to agree closely with practical observations. Elastic stretching of the die and the elastic aftereffect in the specimen are the main causes of cracking. Stronger dies provide an effective means of minimizing cracking in powdered-metal specimens, for they show less elastic deformation.

BIBLIOGRAPHY

1. Yu. M. Bal'shin. Powder Metallurgy. Metallurgizdat, 1948.

2. I. M. Belyayev. Resistance of Materials. Gos. Izd. Tekh.-Teor. Lit., 1951.

 G. I. Aksenov and A. N. Nikolaya. Transactions of the Fourth All-Union Conference on Powder Metallurgy: Calculation of Dies Used to Press Metal Powders. NTO Mashprom. Taroslaw, 1956.

4. S. I. Gubin. Theory of Pressure-Working of Metals.

-18-

PRESSING OF METAL POWDERS

3. Ya. Plotkin and G. V. Samsonov

Moscow, Vesinik Machinostreyeniya (Herald of Machine Suilding) No 5, May 1959, pp 53-56

Bal'shin []7, Unckel [27, and others have made fundamental studies on the pressing of metal powders, but some aspects of considerable importance in practical powder metallurgy have been neglected. These include the effects

			of the time				
			on the density,				
tine.		2		4		6	effects, effect
min			Brique	ttes fr	om	<u></u>	of repeated pressing, and
. •	p•	ä	ą	8	p	8	of the forces
			Iro	n			Dreed ng
0	4.30	4.10	5.0	4.90	5.65	5.32	Time. Iron
0.5	4.35	4.06	5.00	4.92	5.75	5.68	powder (poured
3	4.4	5.25	5.39	4.88	6.74	5.83	density 2.06 g/cm ³) was pre-
			Tung	sten			pared by reduc-
0	8.55	9.95	10.40	11.00	11.00	11.80	tion from roll-
0.5	8.70	9.80	10.60	11.20	11.21	11.80	sieved (025B
1.5	8.84	9.95	10.25	11.50	11.50	12.40	sieve); tung-
3	9.03	9.70	11.21	10.40	11.56	14+20	sten powder

"p = pressing, s = sintering.

mean grain size 4.2 µ was also used. The powders were preseed in a cylindrical [steel die at 2, 4, or 6 t/cm², the density being measured as a

19 .

function of pressing time (times of 0.5, 1, 1.5, and 3 min were used). The iron samples were sintered in hydrogen at 1000-1150° and those of tungsten at 2100°, in both cases for 1 hr. Table 1 gives the densities in g/am^3 .

The density of an iron specimen generally increases with the pressing time, the increase itself tending to rise with the pressure. This is a result of liquidation of the state of stress (distribution of the stress throughout the volume). The loss of density on sintering indicates that the internal stresses are thereby relieved. On the other hand, the tungsten specimens became denser on sintering, which may mean that the forces resulting from sintering substantially exceed those of the stresses, which is sesociated with the high volatility and ready reduction of tungsten oxides, so sintering is activited.

Elastic Aftereffect. Here the dimensions of the specimens were measured under pressure and after pressing (a steel die 12.3 mm in diameter was used) for tungsten, tungsten carbide, iron, copper, and aluminium. Each powder was used in three different grain sizes (Table 2). Figure 1 shows the

Powder	Sep. method	Fraction, u				
		Large	Med.	Small		
W WC Cu F9 Al	Sedim. II Sieve II II	1.6 2.0 75-85 105-150 18-30	1.3 1.5 42-75 42-85 85-105	0.7 0.7 tc 42 42 42		

Table 2

Figure 1 shows the results. The large and medium fractions showed less effect; the maximum effect with WC moved to lower pressures as the grain size was reduced, which is evidently a result of brittle fracture of the particles. There is a fairly pronounced

trend in the effect with Fe, Cu, and Al; there is also an increase with the hardness of the powder, as has been observed previously /1/, but this extends only up to a certain pressure,

past which point there is a fall, which is caused by brittle fracture and hardening in the grains. The effect also varies with time; for example, copper specimens left in a nonoxidizing atmosphere for a week after pressing increased in diameter by C. 14-0.36% and in length by C. 36-0.48%.

Effects of Repeated Pressing. The powders





detailed in Table 3 were used here in a steel die 12 mm in diameter; after pressing, the specimens were ground up, sieved, and pressed again. Table 4 gives the results. The density of copper powder in all three forms increased steadily from

Grain	%, content					
aise, µ	Cu	W				
42	-	1				
42-25	-	1.5				
25-18	-	2.65				
18-15	-	17.35				
150-105	0.15	18.9				
105-85	1.3	34.1				
85-75	1.5	8.25				
75	97.05	16.15				
Note. Poured and tamped densities 1.63 and 2.33						
(Cu), an (W).	d 4.52 a	na 6.74				

Table 3

pressing I to pressing III, provided that the pressure used in pressing III was equal to or greater than that used in I and II; but if III was (say) 4 t/cm2 whereas I and II were 8 t/cm², the reverse occurred. The effects of repeated treatment on the much harder metal tungsten were very much less, though the trend in the density of the pressed specimens was as for iron powder (propounced fall if pressure III was below This method pressures I and II). enables one to produce the most favorable distribution of particle sizes and can be used to increase the density of the pressed materials.

Force Distribution. Unckel

[27 has used the die shown in Fig. 2 to measure the forces in pressing;

between the guide and the lower support there is a ring of copper or soft iron, which is indented by four steel balls held in recesses. A similar disc supported by three balls



Fig. 2. Unckel's die for determining the streas distribution in pressing: 1) plunger; 2) guide; 3) support for powder; 4) balls; 5) ring support under guide; 6) steel balls; 7) base of die.

records the force acting directly on the powder; the difference represents the frictional force N between the powder and the wall of the die. The indents are used to deduce the forces as follows: N is given by

 $N = \mu P_w F_w$

in which μ is the coefficient of friction, P_{ω} is the lateral pressure, and F_{ω} is the area of contact with the wall. Now

---- 21 -----

		III	P = 4		77.67	6.934 6.61 7.55		8 4 4 4 8 9 9 9 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0																				
		11	P = 8					0 = 4 D = 3 D = 9											22	68 4.06 4.80 7.82	•	5.9 31.7 35.4 4.08 6.15						
	(t/c ² 5	н	P = 8						8.3	91-2 3-9 2-89 2-49		227.8 27.8 4.35 6.26 6.26 9.82																
	res F	III	P = 4										τ 	+ 11 0.														
	pressu	11	P = 4		5.5	5. N N N N		75.58 28.0 28.0 28.0 8.51 8.51 8.51																				
	II at	н	P = 4	Cu		5.6	94.4 2.74 3.02 6.53		53.8 255.0 8.60 8.88 8.88																			
	I pue	III	P = 4			9	94 2.88 3.05 5.70		8.85 8.85 6.65 7.4 8.9 6.6 6.6 6.6 6.6 6.6 6.6 6.6 6																			
Table 4 Effects of pressings I, II,	II	с; н Д	n		5. 5. 5. 5. 5. 5. 5. 5. 5. 5. 5. 5. 5. 5	38	24 24 27 27 27 26 26 26 26																					
	н	сл 4 А,			= 0.5 P = 0.5 F = 4 P = 2	2.6	92.4 2.4 5.53		76.3 76.9 76.9 7.86 7.86 7.86																			
	111	F = 4				= 0.5 F = 0.5 F = 4	2.6	97.4 2.75 3.41 6.66		21.8 27.0 37.7 44.4 6.59 8.21																		
	11	P = 0.5					45.4	95-74 2-31 2-90 4-84		7.01 7.01 7.01 7.01																		
	H	= 0.5					= 0.5	9.35	90.65 1.74 2.4 4.77		×7.55 ×1.17 ×1.17 ×1.50 ×1.17 ×1.50																	
		- + vder	[F4		105 µ	1108 75 µ reà Z/cm ped " ssed "		705 k 85 k 75 k 75 k red g/cm3 seed a																				
		, od			Gra	Pre F		105 105 to Pres																				

- 22

Py is given (37 by

$P_{ij} = \frac{2}{3}P_{ij}$

in which $y = \frac{y}{(1 - y)}$ and $\frac{y}{1}$ is Poisson's ratio, P being the pressure applied to the plunger; $\frac{y}{1}$ is not affected by the porosity. Then we have that $\frac{W}{N_{B}} = \frac{45\mu H}{D}$ for the properties of the pressing force N_{p} lest by Triction. This increases with H, and so decreases as N_{p} is increased, as Upskel has shewn, his values for the ratio for iron powder being 70% at $2t/om^{2}$, 60% at 4, 50% at 12, and 50% at 18. A lubricant mixed with the powder reduces the ratio (to 41% at 12 and 18 t/em^{2} in Unckel's case).

We have used the same method, but with special attention to lubrication of the walls as a means of reducing the fric-The powders were of Cu, Fe, and W, which are metals tion. that differ greatly in plasticity. The Cu powder was made by reducing copper oxide with hydrogen (grain size 2-3 4, poured density 1.46 g/cm3); the Fe, by reduction of scale with hydrogen (2-3 μ , 2.0 g/cm³); and the W, by reduction of tungstic anhydride (5-6 µ 4.22 g/cm3). The lubricant was a 4% solution of paraffin wax in benaine (150 cc per 100 g of The powders were pressed without lubricant, with powder). the wall and ends lubricated, and with lubricant incorporated in the powder; the pressures ranged from 0.4 to 2.5 t/em2. Table 5 gives the results, which indicate a type of variation rather different from that reported by Unckel; the reason is that he used much higher pressures.

The proportion of the force lost by friction tends to increase with the pressure if the die is unlubricated, but it decreases if die or powder contains lubricant. The first effect may be caused by seisure and the second by leakage, which tends to increase with pressure. Unckel did not observe seisure, for the pressures he used were too high for the force to be important. Iron powder here gives a pronounced effect, which is greater than that for the Cu-Fe pair; the lubricant here decreases the proportion lost but does not affect the trend of the proportion with pressure.

The curve for $P_1f(P)/(P_1 + P_2)$, in which P is the pressure applied, has a maximum for tungsten powder when the wall is lubricated but decreases as P increases if the pewder contains lubricant, as for iron. The reason is that low pressures are insufficient to oversome the seisure of the powder with the wall of the die, especially when there is no lubricant. A lubricant within the powder tends to suppress seisure altogether, because the lubricant tends to be extruded along the wall as the pressure increases.

- 170		167	- 5
	•	La.	_

Lub. method	P, t/or2	kg		ک س لے	*	N	٩L
		P*	P2	P4/(P1 + 1	Res. por.	^H B, kg∕i	7 K
			(Ju			
None II II II	0.7 1.2 1.6 2.0	616 1275 1645 2240	776 1180 16 3 0 1 665	44.0 52.0 50.0 54.0	49.1 39.2 29.2 25.0	- 17.0 33.5 42.0	2.94 5. 54 9.60 12.6
die "" " " In powd. ""	0.7 1.1 1.5 2.1 0.7 1.0 1.5 2.0	470 585 755 960 468 610 735 894	1028 1282 2265 2840 812 1312 2240 3100	34.0 27.0 23.0 35.0 31.0 24.0 22.0	48.6 36.8 23.1 17.2 47.3 39.4 24.4 15.6	- 16.6 31.2 39.3 15.8 29.6 38.7	2.59 3.50 7.00 10.56 2.87 4.70 8.04 10.9
	8) - 1	: – ر ا	i (f e			
None M M H	0.4 1.1 1.6 1.9 2.3	412 1145 1763 2257 3290	470 978 1451 1510 1354	46.8 54.4 55.0 59.9 71.1	52.7 45.5 41.1 33.8 31.7	25.2 38.2 46.3 50.1	3.02 4.01 5.75 9.34 9.9
die H H H H H In powd. H H	0.4 0.9 1.4 1.7 2.1 0.5 1.1 1.4	207 518 1140 1477 2021 466 915 1319 1624	538 1367 1696 1990 2234 513 1309 1524 1486	27.8 27.5 40.4 42.6 47.5 47.6 41.5 46.2	51.7 41.3 35.2 32.9 25.9 50.1 41.4 36.2 31.8	21.2 30.3 46.3 71.5 18.1 26.7 34.6	0.59 4.07 4.4 8.7 11.8

, P₁ = Serce en peude:

*P. .

fores

.....

011

en pewder. (Cont. over)

- 24

Table 5 (Cont.)

Lub. method	P, t/cm ²	kg P*1 P2		/(P ₁ + P ₂) as %	Res. ror., %	B, kg/ ^{mm²}	ö, kg∕mm ²
				μ. Ι	,		
None H Wall of die H H T In powd. H H H	0.0 1.1 1.9 2.5 0.5 1.4 1.6 1.7 1.9 2.3	1110 997 1870 3010 495 975 1335 1610 447 1010 1280 1612 2500	723 1195 1940 1990 565 1178 1550 1710 660 1340 2120 2240 2142	58.2 45.5 49.5 60.0 46.5 40.5 48.5 48.5 39.0 37.7 47.0 53.6	47.1 46.9 40.0 48.0 47.8 47.8 47.8 47.8 47.9 47.5 59.5 59.5 59.5 44.3 8.6		0.83 0.83 2.34 0.28 0.28 0.28 0.28 0.28 0.28 0.38 0.28 0.38 0.38 0.48 0.51 0.63

The residual porosity falls steadily as P increases, the fall being most rapid for copper, as one would expect (by about a factor 2 for unlubricated powder and by a factor 3 for lubricated). The effect is less for iron (factors of 1.5 and 2 respectively) and least for tungsten (1.2 and 1.5).

The hardness and yield point of in compression both increase with P; the lubricant reduces of for Cu and W but has little effect for Fe, which may be a result of differences in the interaction between the lubricant and the powder (the lubricant is active with respect to iron but inert for Cu and W, where its presence enables the marticles to alide over one auother). The low strength of tungsten specimens occurs because the pressures were too low for use with this hard material.

The conclusions to be drawn are as follows.

The density increases with the pressing time; the internal stresses are thereby reduced. The elastic aftereffect in

the more plastic metals generally decreases as the grain size increases; with brittle materials of carbide type, it increases only up to pressures insufficient to cause brittle fracture.

Repeated pressing and powdering provides a substantial increase in the density of the pressed products without any great increases in the internal stress and elastic aftereffect.

The distribution of forces in the pressing of powders is very much dependent on the seizure between the die and the powder, especially for low pressures and low rates of pressing.

BIBLIOGRAPHY

- 1. Yu. M. Bal'shin. Powder Metallurgy. Metallurgisdat, 1948.
- 2. H. Unckel. Arch. Eisenhüttenwesen, 18, 161 (1945).
- 3. G. V. Samsonov and S. Ya. Plotkin. Production of Iron Fowder. Metallurgizdat, 1957, p. 137.

-END-

26

. 2187

CSU: 1879-N