

UNCLASSIFIED

AD 4 6 3 8 4 0

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

463840
CATERGED BY: DDC
463840

Research Laboratories

U
UNITED AIRCRAFT CORPORATION
A
EAST HARTFORD, CONNECTICUT

D910261-3

RESEARCH INVESTIGATION OF PHASE-REINFORCED
HIGH-TEMPERATURE ALLOYS PRODUCED DIRECTLY FROM A MELT

By

F. D. Lemkey
M. J. Salkind

AVAILABLE COPY WILL NOT PERMIT
FULLY LEGIBLE REPRODUCTION.
REPRODUCTION WILL BE MADE IF
REQUESTED BY USERS OF DDC.

April 15, 1965

United Aircraft Corporation Research Laboratories
East Hartford, Connecticut

Contract No. DA-19-020-AMC-00434(X)


Boston Procurement District

AMCMS CODE 5025.11.843

Department of the Army Project 1A024401A111

U. S. Army Materials Research Agency
Watertown, Massachusetts 02172

TECHNICAL REPORT NO. AMRA CR-64-05/1



TECHNICAL REPORT AMRA CR-64-05/1

The findings in this report are not to be construed
as an official Department of the Army position.

DDC AVAILABILITY NOTICE

Qualified requesters may obtain copies of this report from Commanding Officer,
Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314

DISPOSITION INSTRUCTIONS

Destroy; do not return

Reinforced Composites
High-Temperature Alloys
Eutectic Alloys
Unidirectional Solidification

RESEARCH INVESTIGATION OF PHASE-REINFORCED
HIGH-TEMPERATURE ALLOYS PRODUCED DIRECTLY FROM A MELT

By

F. D. Lemkey
M. J. Salkind

April 15, 1965

United Aircraft Corporation Research Laboratories
East Hartford, Connecticut

Contract No. DA-19-020-AMC-00434(X)
Boston Procurement District
AMCMS CODE 5025.11.843
Department of the Army Project 1A024401A111
U. S. Army Materials Research Agency
Watertown, Massachusetts 02172
TECHNICAL REPORT NO. AMRA CR-64-05/1

Research Investigation of Phase-Reinforced
High-Temperature Alloys Produced Directly From a Melt

ABSTRACT

The results of continued investigations on whisker-reinforced high temperature eutectic alloys are presented in this third quarterly report. Ingots of Ta-Ta₂C have been unidirectionally solidified at 15 cm/hr to produce a composite of aligned tantalum carbide rods and platelets within a matrix of tantalum using a modified electron beam zone melting apparatus.

A consistent crystallographic relationship between Ni and NiBe interpenetrating single crystal lamellae of a eutectic grain has been examined in detail using a hard sphere atomistic model of the interface.

The results of a study of cyclically loaded Ni-NiBe eutectic alloy has indicated that most of the deformation takes place within the nickel solid solution matrix. The yield strength increased with each cycle and reached a constant maximum value after four cycles.

Report D910261-3

Research Investigation of Phase-Reinforced
High-Temperature Alloys Produced Directly From a Melt

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
EXPERIMENTAL PROCEDURES	1
Master Heat Production and Controlled Solidification:	1
Crystallography	6
Mechanical Property Evaluation.	6
RESULTS AND DISCUSSION	7
Controlled Solidification	7
Crystallography	12
Mechanical Property Evaluation.	15
FUTURE WORK.	26
REFERENCES	27

ILLUSTRATIONS

<u>Figure</u>		<u>Page</u>
1.	Electron Beam Floating Zone Solidification Apparatus	3
2.	Modified Zone Scanner	4
3.	Swaged Microstructure of Ta-Ta ₂ C Eutectic (A65-030)	10
4.	Microstructure of Ta-Ta ₂ C Alloy (A65-033) Unidirectionally Solidified at 15 cm/hr	11
5.	Ni {111} Projection of Atom Positions	13
6.	NiBe {110} Projection of Atom Positions	14
7.	Stress-Strain Behavior of Unidirectionally Solidified Ta-Ta ₂ C Alloy (A65-027)	17
8.	Fracture Behavior in Ta-Ta ₂ C Eutectic Alloy (A65-027)	18
9.	Surface Cracks Developed in Tension Loaded Ni-NiBe Alloy Specimens	19
10.	Interrupted Tensile Test on Ni-NiBe Alloy (A65-008) Showing Change in Deformation Characteristics During Cyclic Loading	21
11.	Slip Lines in Ni-NiBe Alloy (A65-008) Stressed to Failure	22
12.	Yield Strength Limit Due to Cyclic Loading	23
13.	Fracture and Crack Path Through Ni ₃ B Platelets (A64-401)	25

INTRODUCTION

This is the third quarterly progress report for Contract No. DA-19-AMC-00434(X) entitled "Research Investigation of Phase-Reinforced High-Temperature Alloys Produced Directly From a Melt," covering the period from 31 December 1964 to 31 March 1965. The principle objective of this research is the production of whisker-reinforced high-temperature alloys directly from the melt by means of unidirectional solidification of eutectic alloys.

This report contains a discussion of results of experimental work carried out during the third quarter and of work to be conducted during the final report period.

EXPERIMENTAL PROCEDURES

Master Heat Production and Controlled Solidification

Ta-Ta₂C

A 25 lb master casting which was reprocessed by electron beam melting to bring up the carbon content to that of the eutectic value was re-examined for carbon content and homogeneity. A small amount of primary tantalum carbide was observed along the entire length of the master casting with a greater amount present at the bottom of the ingot. Fabrication of the top 2/3 of the master casting into 1/4 in. rod was then accomplished. Three billets were machined from this master casting and extruded at 2350 F at a 4:1 extrusion ratio. The resulting 1-1/2 in. diameter rod was annealed in argon at 2400 F for two hours and subsequently swaged to 1/4 in. stock at 800 F in several passes each consisting of 10% reduction. A typical analysis of the reprocessed master casting is presented in Table I.

The swaged rods were electron beam zone melted in the MRC apparatus illustrated in Fig. 1. This apparatus, designed primarily to zone refine high temperature materials has been modified to perform unidirectional solidification experiments as shown in Fig. 2. One specimen end clamp has been replaced by a large copper block (F) through which a cooling medium is passed (J). The cooled copper block acts as a heat sink to attain directional heat flow. The presence of the cooled block near the top of the bell jar also acts as a cold trap to lower the total pressure. Since thermal radiation losses are significant whenever high temperatures are involved, the radial loss of energy by radiation must be minimized to arrive at


TABLE I

Composition and Impurity Content of Ta-C Alloy


Master Heat (A65-030)

	<u>Top</u>	<u>Bottom</u>
Al	10 ppm	10 ppm
B	1	1
Cb	86	63
Cd	1	1
Co	5	5
Cr	10	10
Cu	2	2
Fe	15	15
H	3.5	2.4
Mg	10	10
Mn	10	10
Mo	10	10
N	35	40
Ni	10	10
O	160	120
Pb	5	5
Si	10	46
Sr	10	10
Ti	10	10
V	10	10
W	495	530
Zn	10	10
Zr	50	50
C	0.93 wt/o	0.87 wt/o
Ta	Balance	Balance

ELECTRON BEAM FLOATING ZONE SOLIDIFICATION APPARATUS



MODIFIED ZONE SCANNER



A-UPPER HALF OF SPECIMEN
 B-LOWER HALF OF SPECIMEN
 C-MOLTEN ZONE
 D-THERMIONIC EMITTER
 E-Mo PILL BOX

F-Cu COOLED BLOCK
 G-Ta RADIATION SHIELDS
 H-TRANSLATION SCREW
 I-SPECIMEN ROTATION DRIVE
 J-COOLENT ENTRANCE

the desired directional heat flow constraint. Tantalum sheets (G) in two thicknesses spaced 1/4 in. apart were used to radially shield the thermionic emitter (D) and molybdenum pill box (E). The pill box encloses the emitter and acts as a reflector for electrons. Total enclosure of the filament emitter and pill box was accomplished by shielding the top and bottom of the molten zone (C) with tantalum heat shields (not shown).

The energy required to melt the specimen is provided by the kinetic energy of the electrons, much of which is transformed into thermal energy. The flow of electrons is focused by the geometry of the filament and that of the enclosure. Several filament shapes were employed, including wire and ribbon. Because the wire filament does not close upon itself and allow the electrons to bombard the entire circumference of the specimen, rotational movement of the specimen is necessary for uniform heating of the molten zone. A provision for rotating the lower half of the specimen is located at the bottom specimen clamp and is adjustable from 10 to 200 rpm. Translation of the pill box and filament emitter along the length of the specimen is provided by a screw drive mechanism.

As previously described (Refs. 1 and 2) difficulty was encountered in using a thoriated tungsten wire filament which distorted on heating. A ribbon filament fabricated from thoriated tungsten sheet provided the desired rigidity and also enveloped the entire circumference of the specimen. However, its emission efficiency was low (Ref. 5) and a molten zone at 2800 C could not be attained using the present 2 kw electron beam unit. Currently a thoriated tungsten wire filament is being utilized which is uniformly seated to the electrical leads within a machined seat rather than held in place by two set screws. This has minimized distortion of the emitter when heated.

Ni-NiBe

Two eutectic alloy ingots were unidirectionally solidified at 2.1 and 3.3 cm/hr using the same procedure outlined in (Ref. 1). One of the resulting ingots (A65-008) was subsequently machined into a tensile coupon for step loading to failure in tension. A master heat of 50 atom percent Ni and 50 atom percent Be was prepared by consolidating 99.97 Ni rod and 99.7 Be rod and unidirectionally solidifying a 1/2-in. diameter ingot to produce a bulk specimen of NiBe. No effort was made to produce unidirectionally solidified ingots at steeper thermal gradients or at higher solidification rates since this system did not exhibit improvement in properties by unidirectional solidification (Ref. 2).

Crystallography

Ni-NiBe

One grain from the tail end of an ingot solidified at 2.1 cm/hr (A65-008) was analysed by the back reflection precession X-ray diffraction method developed by Kraft (Ref. 3). CoK_α radiation was used in place of FeK_α in order to obtain the separated families of planes for subsequent analysis. Use of CoK_α radiation instead of FeK_α allowed reduction of exposure time from 2 hours to 30 minutes, because the Co tube provided more intense radiation than the iron tube.

Ta-Ta₂C

A Debye-Scherrer pattern was obtained using CuK_α radiation to identify the carbide particles extracted from a eutectic alloy by an alcoholic bromine solution.

Ni₃B-Ni

Two grains from ingots solidified at 4.7 and 10.7 cm/hr were analysed by the back reflection precession X-ray diffraction method of Kraft (Ref. 3). FeK_α radiation and a specimen to film distance of 1.5 cm were used. The separated families of planes chosen for analysis were the same as those chosen by Shapiro and Ford (Ref. 4). Exposures of two hours duration were required to obtain the desired information for subsequent analysis.

Mechanical Property Evaluation

Ta-Ta₂C

A tensile specimen 0.125-in. diameter with a one inch long gage section was machined from a unidirectionally solidified specimen. The loading was applied parallel to the growth direction using a Tinius Olsen four-screw testing machine at a loading rate of 0.01 inches per minute.

Ni-NiBe

A 0.250-in. diameter, one inch long gage section tensile coupon was ground from a unidirectionally solidified specimen. Parallel flats 0.12 in. wide were ground on opposite sides of the tensile coupon along its length. The specimen was mechanically polished and etched with a solution of one part 20% potassium cyanide

in water and one part 20% ammonium persulfate in H₂O. The specimen was step loaded in the Tinius-Olsen testing machine at intervals of approximately 15,000 psi until considerable yielding occurred and then intervals of approximately 1.5% strain were employed. At the end of each of the nine steps, the polished flat was first examined optically along the gage length for deformation and then replicated at three indexed positions within the gage length for electron microscopic examination. Upon failure the fracture surface was replicated for fractographic analysis. The unidirectionally solidified ingot of NiBe could not be machined into a cylindrical tensile coupon because of grain boundary cracking. However a 1/16 x 1/16 x 1 in. microbend specimen has been machined for four point bend testing.

Ni₃B-Ni

Three specimens 3/4 of an in. long and 1/4 in. in diameter were loaded in compression to failure using a Tinius-Olsen four-screw testing machine at a strain rate of 0.01 in. per minute. A 1/2 in. gage length clip-on compressometer was used to measure strain. The specimen was mounted within a standard Tinius-Olsen compression fixture using flat TiB₂ bearing plates. An alloy steel specimen was used as a standard for calibrating the compressometer. The fractured specimen pieces were mounted in bakelite and mechanically polished and etched for light microscopic examination.

RESULTS AND DISCUSSION

Controlled Solidification

The results of solidification experiments performed during this quarter are presented and discussed below according to eutectic alloy system.

Ta-Ta₂C

Microscopic examination of the top, middle and bottom sections of the reprocessed master alloy indicated only a slight amount of primary carbide located chiefly in the bottom section. The carbon composition of the eutectic microstructure averaged 0.88 by weight which is approximately 10% greater than that previously reported (Ref. 6). The volume percent of Ta₂C within a matrix of Ta present at room temperature under equilibrium cooling conditions was approximately 35% based on this observed eutectic composition.

The results of the unidirectional solidification experiments performed during this quarter are shown in Table II. All of the experiments except that for specimen

TABLE II

Summary Ta-Ta₂C

Unidirectional Solidification Experiments

Identification Number	Charge Number	Traverse Rate (cm/hr)	End Quench	Voltage (kv)	Beam		Vacuum (mm Hg)	Microstructure	Comments
					Current (mA)	Filament Current (A)			
A65-027	A64-047	10	H ₂ O	2	300	21	2-3 x 10 ⁻⁵	Partial alignment of Ta ₂ C, L/d 10	Tensile coupon machined 25 rpm end rotation
A65-029	A65-030	10	H ₂ O	1.4	415	15	2-7 x 10 ⁻⁶	Spheroidized Ta ₂ C, L/d 1	
A65-031	A65-030	15	H ₂ O	1.65	360	16	4 x 10 ⁻⁵ 1 x 10 ⁻⁶	Partial axial alignment of Ta ₂ C phase	
A65-032	A65-030	20	H ₂ O	1.45	390	22	4-7 x 10 ⁻⁶	Small grains "as cast" appearance	
A65-033	A65-030	15	liq N ₂	1.5	390	23	1-2 x 10 ⁻⁶	Axial alignment of Ta ₂ C phase, banded	
A65-034	A65-030	15	liq N ₂	1.5	400	12.5	1-3 x 10 ⁻⁶	Partial axial alignment	Top and bottom shields added
A65-035	A65-030	10	liq N ₂	1.4	400	14	1-3 x 10 ⁻⁶	Partial axial alignment of Ta ₂ C	Top and bottom shields added
A65-036	A65-030	10	liq N ₂	1.5	400	15	1-2 x 10 ⁻⁶	Partial axial alignment of Ta ₂ C	Top and bottom shields added
A65-037	A65-030	15	liq N ₂	1.5	400	13	1-2 x 10 ⁻⁶	Axial alignment of Ta ₂ C phase, no bands	Top and bottom shields removed


A65-027 were performed using extruded and swaged alloy. The distribution of the carbide within the tantalum matrix of the starting material is indicated in Fig. 3. The alloy for specimen A65-027 was obtained from the carburizing experiments performed during the first quarter (Ref. 1).

In all the experiments performed to date approximately the same power, 0.6 kw, was required to stabilize a molten zone approximately 5/16 in. long above 2800 C. The first experiments, A65-027 through A65-032, Table II, were performed using water to quench the end of the specimen. Only partial alignment of a small number of eutectic grains parallel to the growth direction was observed at 15 cm/hr. At 10 cm/hr the Ta₂C phase was spherical in shape as determined by metallographic examination using a two surface technique. Increasing the solidification velocity to 20 cm/hr resulted in very small unoriented grains which looked very similar to that of the as-cast alloy. Attempts were made in the next series of experiments to increase the axial heat losses. Specimen A65-033 was solidified using liquid nitrogen at 3 psig to cool the solidified end. This experiment was successful in aligning the Ta₂C phase approximately parallel to the specimen axis. The microstructure produced is illustrated in Fig. 4. The morphology of the Ta₂C phase seems to be primarily ribbon or platelet, however the Ta₂C phase as revealed in some grains sectioned normal to the solidification direction is predominantly rod-like. Alignment of the carbide phase with the solidification direction is clearly evident in the longitudinal section. Banding was also present at irregular intervals which may have been associated with an interruption of liquid nitrogen flow necessary to refill the dewar during this experiment. The aspect ratio of the Ta₂C phase measured on longitudinal sections have exceeded 100 to 1. Aspect ratios thus measured are very conservative since the Ta₂C phase is not necessarily coplanar with the plane of examination.

Further experiments were performed using Ta shielding around the top and bottom of the pill box as well as the sides but were not successful in obtaining the desired directional heat flow. The top and bottom shields were removed and experiment A65-037 was performed. Axial alignment was accomplished without the presence of bands. The flow of liquid nitrogen was uninterrupted in this experiment. Only the last three inches of the six in. long specimen were entirely controlled, however, as evidenced by a longitudinal section taken along the specimens length.


NiBe

Further work in this system has been discontinued due to the lack of improved properties exhibited by the attainment of aligned NiBe lamellae within a nickel solid solution matrix. To conclude the study of the mechanical behavior, however, two eutectic specimens were unidirectionally solidified at 2.1 and 3.3 cm/hr. The resulting ingots contained a slight amount of primary NiBe phase. In


SWAGED MICROSTRUCTURE OF Ta-Ta₂C EUTECTIC (A65-030)

MAGNIFICATION: X200

MICROSTRUCTURE OF Ta-Ta₂C ALLOY (A65-033)
UNIDIRECTIONALLY SOLIDIFIED AT 15 CM/HR



TRANSVERSE SECTION: X200, MARGOLIN ENCE ECHANT



LONGITUDINAL SECTION: X1000, MARGOLIN ENCE ECHANT

addition a single ingot of NiBe was produced to determine its mechanical behavior. It was observed on handling and machining that NiBe grain boundaries were extremely weak and failure along these internal surfaces would invariably occur when the specimen was bent or machined.

Crystallography

Ni-NiBe

It has been shown that when a eutectic alloy containing Ni and NiBe is unidirectionally solidified a unique metallographic and crystallographic relationship between the interpenetrating single crystals is found (Ref. 2). This relationship has been summarized as:


$$\begin{array}{l} \text{Interface} \parallel \{111\}_{\text{Ni}} \parallel \{110\}_{\text{NiBe}} \\ \qquad \qquad \qquad \langle 110 \rangle_{\text{Ni}} \parallel \langle 111 \rangle_{\text{NiBe}} \end{array}$$

Further experimental confirmation of this relationship has been determined for another eutectic grain solidified at 2.1 cm/hr. This orientation is unique in that the close packed planes and the close packed directions in each phase are parallel to each other and to the metallographic interface. Since these are the planes of densest atomic packing, this observation supports the idea that the interfaces in unidirectionally solidified eutectics will consist of stable low energy planes (Ref. 7).


This unique orientation existing between B.C.C. and F.C.C. phases in equilibrium has been shown to exist for at least two other systems. Smith and Mehl (Ref. 8) have shown that the close packed planes and directions are parallel for austenite (F.C.C.) and ferrite (B.C.C.) in steel. In addition, Speich and Oriani (Ref. 9) have recently found a similar relationship for copper precipitates in an alpha iron matrix.

To examine the registry of the coincident phases in greater detail, constructions of the atom positions on the octahedral planes of nickel and the $\{110\}$ planes of NiBe were made (Figs. 5 and 6). The similarities in atomic positions and triangular symmetry can be readily observed. It can be assumed that the strain energy associated with this interface is low.

Ni {111} PROJECTION OF ATOM POSITIONS



NiBe {110} PROJECTION OF ATOM POSITIONS



Ni₃B-Ni

Two eutectic grains from specimens solidified at 4.7 and 10.7 cm/hr exhibited substructure which resulted in considerable broadening in the X-ray diffraction pattern. This broadening precluded determination of the crystallographic relationships between the two phases. The substructure consists of areas of angular misorientation between Ni₃B and Ni platelets. The areas which are free of substructure are too small to be examined by present X-ray diffraction techniques.

Ta-Ta₂C

Since the existence of a new hexagonal tantalum carbide phase has recently been determined by Villagrana and Thomas (Ref. 10) 1965, a confirmatory check was made on the existence of Ta₂C. The results of a Debye-Scherrer pattern on the extracted tantalum carbide phase are presented in Table III. Positive identification of hexagonal Ta₂C being the only phase present confirms the phase equilibrium diagram (Ref. 6) for the system Ta-C.

Mechanical Property Evaluation

Ta-Ta₂C

The stress-strain behavior of a unidirectionally solidified specimen (A65-027), the whisker aspect ratio for which was found to vary from 1 to 10 as measured by longitudinal sectioning, is presented in Fig. 7. The increase in ultimate tensile strength and corresponding decrease in total elongation compared with that for a specimen containing a random carbide dispersion (Ref. 1) indicate that some fiber reinforcement is obtained even for the relatively small aspect ratio. A longitudinal section through the fracture surface is shown in Fig. 8. No break-up of the Ta₂C phase is observed.

Ni-NiBe

As reported previously the results of tensile tests on specimens machined from unidirectionally solidified Ni-NiBe alloy indicate that strength enhancement by second phase reinforcement has not been achieved. An interesting phenomena was observed during the testing of this alloy in tension. Surface cracks formed along the gage length of the specimen but did not propagate through the sample although the stress concentration was high. Several of these cracks can be seen in Fig. 9 which is a longitudinal section of a specimen which was strained to failure with a total strain at failure of 9.4%.


TABLE III

Powder Pattern Data on Extracted Tantalum Carbide

Phase from Ta - 0.8 wt/o C Eutectic Alloy

Line	Diff. Angle θ Rad	Rel. Intensity I/I_1	$\sin^2 \theta$	Calculated $\sin^2 \theta$	Indices hkl
1	16.71	60	.0827	.0823	100
2	18.21	100	.0977	.0977	002
3	19.11	100	.1072	.1067	101
4	25.11	80	.1800	.1800	102
5	29.83	70	.2475	.2470	110
6	33.36	90	.3024	.3022	103
7	35.04	10	.3297	.3293	200
8	35.99	80	.3453	.3447	112
9	36.51	40	.3540	.3537	201
10	38.69	50	.3907	.3909	004
11	40.84	20	.4277	.4270	202
12	43.46	40	.4731	.4732	104
13	47.84	40	.5495	.5492	203
14	49.42	20	.5768	.5762	210
15 a ₁	50.79	50	.6003	.5996	211
15 a ₂		30			
16 a ₁	52.89	50	.6359	.6359	114
16 a ₂		30			
17 a ₁	55.14	30	.6733	.6727	212
17 a ₂		10			
18 a ₁	56.22	60	.6908	.6907	105
18 a ₂		40			
19 a ₁	57.92	20	.7179	.7181	204
19 a ₂		1			
20 a ₁	59.32	20	.7376	.7396	300
20 a ₂	59.62	1	.7442		
21 a ₁	63.02	60	.7942	.7944	213
21 a ₂	63.29	40	.7980		
22 a ₁	66.22	30	.8375	.8370	302
22 a ₂	66.54	10	.8415		
23 a ₁	69.40	50	.8762	.8762	006
23 a ₂	69.77	30	.8804		
24 a ₁	75.47	60	.9376	.9372	205
24 a ₂	76.07	40	.9420		
25 a ₁	78.17	60	.9580	.9584	106
25 a ₂	78.77	40			
26 a ₁	79.17	50	.9647	.9647	214
26 a ₂	79.90	30	.9692		
27 a ₁	83.25	50	.9862	.9862	220
27 a ₂	84.63	30	.9912		

STRESS - STRAIN BEHAVIOR OF UNIDIRECTIONALLY
SOLIDIFIED Ta - Ta₂C ALLOY (A65-U27)




FRACTURE BEHAVIOR IN Ta-Ta₂C
EUTECTIC ALLOY (A65-027)



MAGNIFICATION: 1000 X

**SURFACE CRACKS DEVELOPED IN TENSION
LOADED Ni - NiBe ALLOY SPECIMENS**



SPECIMEN STRAINED 9.4%

MAGNIFICATION: X500

The phenomenon of crack arrest and the micromechanics of deformation were studied in more detail by a cyclic loading experiment. The specimen was examined after predetermined increments of strain. The stress-strain behavior during a tensile test consisting of 9 loading increments is shown in Fig. 10. The specimen contained a slight amount of primary NiBe. Slip lines were first observed in the Ni phase after 0.6% elongation. After successive loadings, slip bands in the matrix became pronounced and severe plastic deformation near primary NiBe phase particles was noted. After the sample ruptured (7.3% elongation) light microscopic studies of longitudinal sections revealed cracks originating from the Ni-proeutectic particles and propagating into the lamellar eutectic region. These cracks generally traveled in a direction normal to the solidification direction. In a few instances when the cracks propagated parallel to the direction of applied stress interlamellar decohesion was noted. In no case was any deformation seen within the NiBe phase. The interaction of slip in the nickel solid solution matrix with the discontinuous NiBe lamellae is seen in Fig. 11. This specimen underwent 9 loading cycles. It appears that most of the deformation occurs in the matrix.


The changes in stress-strain behavior brought about by previous loading cycles were investigated. It was found that the yield stress increased during the first few cycles and then remained constant during the subsequent loading cycles. This behavior can be seen in Fig. 12 which indicates the variation in yield strength with the number of loading cycles. Similar behavior has been observed for aluminum (Ref. 11) and Udimet 600 (Ref. 12).

Ni₃B-Ni


The results of compression tests on unidirectionally solidified lamellar Ni₃B-Ni eutectic specimens loaded parallel to the growth direction are shown in Table IV. The elastic modulus in compression agreed with that determined in tension (Ref. 2). Since the fracture was catastrophic the compressometer detached at a stress level of approximately 100,000 psi. In two cases the cylindrical specimen failed by splitting in half.

The fracture path as observed in a section perpendicular to the load axis is shown in Fig. 13. Fracture propagated in the Ni₃B matrix and appeared to be deflected by the change in orientation of the Ni plates. No evidence of interfacial decohesion was noted.

INTERRUPTED TENSILE TEST ON Ni-NiBe ALLOY (A65-008) SHOWING
CHANGE IN DEFORMATION CHARACTERISTICS DURING
CYCLIC LOADING



SLIP LINES IN NI-NiBe ALLOY (A65-008)
STRESSED TO FAILURE



STRESS DIRECTION PARALLEL TO PLATELETS
MAGNIFICATION: X5000

YIELD STRENGTH LIMIT DUE TO CYCLIC LOADING





TABLE IV

Summary of Compression Tests Ni₃B-Ni

Traverse Rate R cm/hr	Sample	Diameter (in.)	Area (in. ²)	Length (in.)	Ultimate Load (lbs)	Ultimate Compressive Strength (psi)	Loading Rate (in/min)	Elastic Modulus (psi)	Strain*		Failure
									ε	%	
5.3	A64-371-02	0.2496	0.04890	0.750	14,000	286,000	0.01	---	0.86	0.86	Brittle
4.7	A64-401-2	0.2496	0.04890	0.748	12,500	256,000	0.01	34.0 x 10 ⁶	0.77	0.77	Brittle
4.7	A64-401-4	0.2494	0.04883	0.749	12,950	265,000	0.01	31.0 x 10 ⁶	0.80	0.80	Brittle

* Total strain based on Hookean behavior to failure E = 33 x 10⁶ psi

FRACTURE AND CRACK PATH THROUGH
 Ni_3B PLATELETS (A64 - 401)



MAGNIFICATION: 1000 X

FUTURE WORK

During the final report period continued efforts will be made to produce controlled microstructures in the Ta-Ta₂C eutectic system over a range of solidification velocities. In addition, an alloy of nickel beryllium solid solution will be prepared in order to evaluate its mechanical behavior.

X-ray crystallographic examination will be performed on single grains of Ta-Ta₂C. Tensile testing of specimens machined from controlled Ta-Ta₂C ingots to determine their strength and deformation characteristics will be continued.

REFERENCES

1. Ford, J. A., F. D. Lemkey, and B. J. Bayles: "Research Investigation of Phase Reinforced High Temperature Alloys Produced Directly from a Melt." Quarterly Progress Report No. 1, Department of the Army Project 1A024401A111, October 1964.
2. Salkind, M. J., F. D. Lemkey, B. J. Bayles and J. A. Ford: "Research Investigation of Phase Reinforced High Temperature Alloys Produced Directly from a Melt." Quarterly Progress Report No. 2, Department of the Army Project 1A024401A111, January 1965.
3. Kraft, R. W.: "Technique for Determining Orientation Relationship and Interfacial Planes in Polyphase Alloys: Application to Controlled Eutectic Specimen." Trans. Met. Soc. AIME, Vol. 221, pp. 704-711 (1961).
4. Shapiro, S. and J. A. Ford: "Crystallography of Unidirectionally Solidified Ni-Ni₃B Eutectic Alloys." Submitted to Trans. Met. Soc. AIME, August 1964.
5. Bakish, Editor: Introduction to Electron Beam Technology, John Wiley & Sons, 1962, p. 188.
6. English, J. J.: Binary and Ternary Phase Diagrams of Columbium, Molybdenum, Tantalum and Tungsten. DMIC Report 152, April 1961, p. 61.
7. Kraft, R. W.: "The Structure of the Mg-Mg₂Sn Eutectic." Trans. Met. Soc. AIME, 1963, Vol. 227, pp. 393-399.
8. Birchenall, C. E.: Smith and Mehl in Physical Metallurgy. McGraw-Hill, 1959, p. 295.
9. Speich, G. R. and R. A. Oriani: "Rate of Coarsening of Copper Precipitate in an Alpha-Iron Matrix." Paper presented at Annual Meeting AIME, Chicago, February 1965.
10. Villagrana, R. and G. Thomas: "Ordered Domains and the c/a Ratio of T₆C." Applied Physics Letters, Vol. 6, No. 4, February 1965, p. 61.
11. Sierakowski, R. L.: "Microstrain of Aluminum." Ph.D. dissertation, Yale University, June 1964.
12. Wells, C.: April 1965 Pratt & Whitney Advanced Materials Laboratory, United Aircraft Corp., North Haven, Conn.

AMRA DISTRIBUTION LISTMaterials for Army Weapons & Combat Mobility

AMC Code 5025.11.843

DA Project No. 1A024401A111

	<u>No. of Copies</u>
<u>A. Department of Defense</u>	
Office of the Director of Defense Research & Engineering Attn: Dr. Earl T. Hayes Assistant Director (Materials) The Pentagon Washington, D. C. 20315	1
Commander Defense Documentation Center Cameron Station, Bldg. 5 5010 Duke Street Alexandria, Virginia 22314	10
Defense Metals Information Center Battelle Memorial Institute Columbus, Ohio	1
<u>B. Department of the Army</u>	
Commanding Officer Boston Procurement District, U. S. Army Attn: R & D Branch, AMXBO-LD Army Base Boston, Mass., 02210	1
Commanding Officer Army Research Office Office Chief Research & Development Attn: Physical Sciences Division 3045 Columbia Pike Arlington, Virginia	2
Commanding General U. S. Army Material Command Attn: AMCRD-RC-M Washington, D. C. 20315	1

AMRA DISTRIBUTION LIST (Contd.)No. of CopiesB. Department of the Army (contd.)

Commanding General U. S. Army Missile Command Attn: E. J. Wheelahan, AMSML-RSM	1
R. E. Ely, AMSMI-RRS	1
R. Fink, AMSMI-RKK	1
K. Parr, AMSMI-RKK	1
Redstone Arsenal, Alabama 35809	
 Commanding General U. S. Army Tank-Automotive Center Attn: SMOTA-RCM	
Warren, Michigan 48090	1
 Commanding General U. S. Army Weapons Command Attn: G. Reinsmith, AMSWE-RDR	1
AMSWE-PP	1
Rock Island, Illinois	
 Commanding General U. S. Army Munitions Command Dover, New Jersey 07801	1
 Commanding Officer Aberdeen Proving Ground Attn: Tech Library, Bldg. 313	
Aberdeen Proving Ground, Maryland	3
 Commanding Officer U. S. Army Ballistic Research Laboratories Attn: Dr. D. Eichelberger	1
Dr. J. Sperrazza	1
Aberdeen Proving Ground, Maryland	
 Commanding Officer U. S. Army Engineer, R & D Labs Attn: STINFO Branch	
Fort Belvoir, Virginia 22060	2

AMRA DISTRIBUTION LIST (Contd.)

	<u>No. of Copies</u>
<u>B. Department of the Army (contd.)</u>	
Commanding Officer Frankford Arsenal Attention: Pitman-Dunn Labs Philadelphia, Pennsylvania 19137	2
Commanding Officer Harry Diamond Laboratories Attention: Library, AMXDO Washington, D. C. 20438	1
Commanding Officer Army Research Office (Durham) Box CM, Duke Station Durham, North Carolina	1
Commanding Officer Picatinny Arsenal Attention: Feltman Research Labs Dover, New Jersey 07801	1
Commanding Officer Rock Island Arsenal Attention: Laboratory, SWERI-RDL Rock Island, Illinois	1
Commanding Officer Springfield Armory Attention: SWESP-TX Springfield, Massachusetts 01101	1
Commanding Officer Watervliet Arsenal Attention: SWEWV-R Watervliet, New York 12189	1

AMRA DISTRIBUTION LIST (Contd.)

	<u>No. of Copies</u>
<u>C. Department of the Navy</u>	
Chief, Bureau of Ships Attn: Code 341 Department of the Navy Washington, D. C. 20315	1
Chief, Bureau of Naval Weapons Attn: RMMP Department of the Navy Room 2225, Munitions Bldg. Washington, D. C. 20315	1
Chief, Office of Naval Research Attn: Code 423 Department of the Navy Washington, D. C. 20315	1
Commander Naval Ordnance Laboratory Attn: Code WM White Oak, Silver Springs, Maryland	2
Commanding Officer and Director U. S. Naval Engineering Experimental Station Department of the Navy Annapolis, Maryland	1
Commander Naval Ordnance Test Station Attn: Code 5557 China Lake, California	1
Director Naval Research Laboratory Attn: Technical Information Officer Anacostia Station Washington, D. C.	1

AMRA DISTRIBUTION LIST (Contd.)

	<u>No. of Copies</u>
<u>C. Department of the Navy (contd.)</u>	
Commander Naval Weapons Laboratory Attn: A & P Lab Dahlgren, Virginia	1
Commanding Officer and Director U. S. Naval Engineering Experiment Station Attn: Metals Division Annapolis, Maryland	1
<u>D. Department of the Air Force</u>	
Headquarters, Aeronautical Systems Division Attn: AFML - MAAE Wright-Patterson Air Force Base, Ohio	5
<u>E. Other Government Agencies</u>	
Army Reactor Branch Division of Research Development Atomic Energy Commission Washington, D. C. 20315	1
U. S. Atomic Energy Commission Office of Technical Information Extension P. O. Box 62 Oak Ridge, Tennessee	1
The Director Jet Propulsion Laboratory California Institute of Technology Attn: Dr. L. Jaffe Pasadena 3, California	1
National Aeronautics & Space Administration Attn: R. V. Rhode	1
G. C. Deutech	1
B. G. Achhammer	1
Washington, D. C. 20546	1

AMRA DISTRIBUTION LIST (Contd.)

	<u>No. of Copies</u>
<u>E. Other Government Agencies (contd.)</u>	
Office of Scientific and Technical Information National Aeronautics and Space Administration Attn: Code AFSS-AD Washington, D. C. 20546	1
George C. Marshall Space Flight Center Attn: Dr. W. R. Lucas, M-S&M-M W. A. Wilson, M-F&AE-M, Bldg. 4720 Huntsville, Alabama	1 1
National Aeronautics and Space Administration Head, Operations Section Scientific and Technical Information Division (SAK/DL) P. O. Box 5700 Bethesda, Maryland 20014	2
Chief, Bureau of Mines Eastern Experiment Station College Park, Maryland	1
Commander British Army Staff Attn: Reports Officer 3100 Massachusetts Avenue, N.W. Washington 8, D. C.	4
Canadian Army Staff Attn: GSO-I, A&R Sec. 2450 Massachusetts Avenue, N.W. Washington 8, D. C.	3
<u>F. Non-Government Agencies</u>	
Materials Research Corporation Orangeburg New York 10962	1

<p>Fb AD Price Accession No. U. S. Army Materials Research Agency, Watertown, Mass., 02172 RESEARCH INVESTIGATION OF PHASE-REINFORCED HIGH-TEMPERATURE ALLOYS PRODUCED DIRECTLY FROM A MELT -</p> <p>F. D. Lemkey and M. J. Salkind United Aircraft Corporation Research Laboratories, East Hartford, Connecticut</p> <p>Report No. AMRA CR-64-05/1, Apr. 1965, 33 pp - tables - illus., (Contract DA-19-020-AMC-0043(X)), DA Project 1A024401ALL, Unclassified Report</p> <p>The results of continued investigations on whisker-reinforced high-temperature eutectic alloys are presented in this third quarterly report. Ingots of Ni-Ta₂C have been unidirectionally solidified at 15 cm/hr to produce a composite of aligned tantalum carbide rods and platelets within a matrix of tantalum using a modified electron beam zone melting apparatus.</p> <p>A consistent crystallographic relationship between Ni and NiBe interpenetrating single crystal lamellae of a eutectic grain has been examined in detail using a hard sphere atomistic model of the interface.</p> <p>The results of a study of cyclically loaded Ni-NiBe eutectic alloy has indicated that most of the deformation takes place within the nickel solid solution matrix. The yield strength increased with each cycle and reached a constant maximum value after four cycles.</p> <p>NO DISTRIBUTION LIMITATIONS</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Reinforced Composites 2. High Temperature Alloys 3. Eutectic Alloys 4. Unidirectional Solidification 5. Contract DA-19-020-AMC-0043(X) <p>I. UAC Research Laboratories</p>
---	---

<p>Fb AD Price Accession No. U. S. Army Materials Research Agency, Watertown, Mass., 02172 RESEARCH INVESTIGATION OF PHASE-REINFORCED HIGH-TEMPERATURE ALLOYS PRODUCED DIRECTLY FROM A MELT -</p> <p>F. D. Lemkey and M. J. Salkind United Aircraft Corporation Research Laboratories, East Hartford, Connecticut</p> <p>Report No. AMRA CR-64-05/1, Apr. 1965, 33 pp - tables - illus., (Contract DA-19-020-AMC-0043(X)), DA Project 1A024401ALL, Unclassified Report</p> <p>The results of continued investigations on whisker-reinforced high-temperature eutectic alloys are presented in this third quarterly report. Ingots of Ni-Ta₂C have been unidirectionally solidified at 15 cm/hr to produce a composite of aligned tantalum carbide rods and platelets within a matrix of tantalum using a modified electron beam zone melting apparatus.</p> <p>A consistent crystallographic relationship between Ni and NiBe interpenetrating single crystal lamellae of a eutectic grain has been examined in detail using a hard sphere atomistic model of the interface.</p> <p>The results of a study of cyclically loaded Ni-NiBe eutectic alloy has indicated that most of the deformation takes place within the nickel solid solution matrix. The yield strength increased with each cycle and reached a constant maximum value after four cycles.</p> <p>NO DISTRIBUTION LIMITATIONS</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Reinforced Composites 2. High Temperature Alloys 3. Eutectic Alloys 4. Unidirectional Solidification 5. Contract DA-19-020-AMC-0043(X) <p>I. UAC Research Laboratories</p>
---	---

<p>Fb AD Price Accession No. U. S. Army Materials Research Agency, Watertown, Mass., 02172 RESEARCH INVESTIGATION OF PHASE-REINFORCED HIGH-TEMPERATURE ALLOYS PRODUCED DIRECTLY FROM A MELT -</p> <p>F. D. Lemkey and M. J. Salkind United Aircraft Corporation Research Laboratories, East Hartford, Connecticut</p> <p>Report No. AMRA CR-64-05/1, Apr. 1965, 33 pp - tables - illus., (Contract DA-19-020-AMC-0043(X)), DA Project 1A024401ALL, Unclassified Report</p> <p>The results of continued investigations on whisker-reinforced high-temperature eutectic alloys are presented in this third quarterly report. Ingots of Ni-Ta₂C have been unidirectionally solidified at 15 cm/hr to produce a composite of aligned tantalum carbide rods and platelets within a matrix of tantalum using a modified electron beam zone melting apparatus.</p> <p>A consistent crystallographic relationship between Ni and NiBe interpenetrating single crystal lamellae of a eutectic grain has been examined in detail using a hard sphere atomistic model of the interface.</p> <p>The results of a study of cyclically loaded Ni-NiBe eutectic alloy has indicated that most of the deformation takes place within the nickel solid solution matrix. The yield strength increased with each cycle and reached a constant maximum value after four cycles.</p> <p>NO DISTRIBUTION LIMITATIONS</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Reinforced Composites 2. High Temperature Alloys 3. Eutectic Alloys 4. Unidirectional Solidification 5. Contract DA-19-020-AMC-0043(X) <p>I. UAC Research Laboratories</p>
---	---

<p>Fb AD Price Accession No. U. S. Army Materials Research Agency, Watertown, Mass., 02172 RESEARCH INVESTIGATION OF PHASE-REINFORCED HIGH-TEMPERATURE ALLOYS PRODUCED DIRECTLY FROM A MELT -</p> <p>F. D. Lemkey and M. J. Salkind United Aircraft Corporation Research Laboratories, East Hartford, Connecticut</p> <p>Report No. AMRA CR-64-05/1, Apr. 1965, 33 pp - tables - illus., (Contract DA-19-020-AMC-0043(X)), DA Project 1A024401ALL, Unclassified Report</p> <p>The results of continued investigations on whisker-reinforced high-temperature eutectic alloys are presented in this third quarterly report. Ingots of Ni-Ta₂C have been unidirectionally solidified at 15 cm/hr to produce a composite of aligned tantalum carbide rods and platelets within a matrix of tantalum using a modified electron beam zone melting apparatus.</p> <p>A consistent crystallographic relationship between Ni and NiBe interpenetrating single crystal lamellae of a eutectic grain has been examined in detail using a hard sphere atomistic model of the interface.</p> <p>The results of a study of cyclically loaded Ni-NiBe eutectic alloy has indicated that most of the deformation takes place within the nickel solid solution matrix. The yield strength increased with each cycle and reached a constant maximum value after four cycles.</p> <p>NO DISTRIBUTION LIMITATIONS</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Reinforced Composites 2. High Temperature Alloys 3. Eutectic Alloys 4. Unidirectional Solidification 5. Contract DA-19-020-AMC-0043(X) <p>I. UAC Research Laboratories</p>
---	---