

UNCLASSIFIED

AD NUMBER	
AD499509	
CLASSIFICATION CHANGES	
TO:	unclassified
FROM:	confidential
LIMITATION CHANGES	
TO:	Approved for public release, distribution unlimited
FROM:	Distribution authorized to DoD only; Administrative/Operational Use; 07 APR 1952. Other requests shall be referred to Naval Proving Ground, Dahlgren, VA. Pre-dates formal DoD distribution statements. Treat as DoD only.
AUTHORITY	
USNSWC ltr dtd 14 Aug 1975; USNSWC ltr dtd 14 Aug 1975	

THIS PAGE IS UNCLASSIFIED

THIS REPORT HAS BEEN DELIMITED
AND CLEARED FOR PUBLIC RELEASE
UNDER DOD DIRECTIVE 5200.20 AND
NO RESTRICTIONS ARE IMPOSED UPON
ITS USE AND DISCLOSURE.

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED.

AD499509

U. S. NAVAL PROVING GROUND
DAHLGREN, VIRGINIA

REPORT NO. 956

WARHEADS FOR AIR TARGET GUIDED MISSILES;
TESTING OF

41st Partial Report

INVESTMENT CAST STEEL TUBE
FOR AIR TARGET GUIDED MISSILES;
FRAGMENTATION TEST OF

FINAL Report

Copy No. 13

Task

Assignment NPG-Re3f-607-1-52

Classification CONFIDENTIAL

SECURITY INFORMATION

1952 APR 8 PM 2 36

~~CONFIDENTIAL~~
NPG REPORT NO. 956

U. S. NAVAL PROVING GROUND
DAHLGREN, VIRGINIA

RECEIVED
REFERENCE DEPARTMENT
LIBRARY OF CONGRESS

APR 22 1956

Forty-first Partial Report

on

Warheads for Air Target Guided Missiles; Testing of

Final Report

on

Investment Cast Steel Tube for Air

Target Guided Missiles; Fragmentation Test of

Project No.: NPG-Re3f-607-1-52
Copy No.: 13
No. of Pages: 7

Date: APR 6 1956

~~CONFIDENTIAL~~
~~SECRET~~

NP9-45618


4 DECEMBER 1951

CONFIDENTIAL

SECURITY INFORMATION


Investment Cast Steel Tube for Air Target Guided Missile, 2 1/2" x 2 1/2"
section of tube removed for Tensile Tests.

Figure 1



FRAG NO. 1415

NP9 46934



SCALE 1"

NP9-46934

4 DECEMBER 1951

CONFIDENTIAL
SECURITY INFORMATION

Mass Distribution of 4"6 diameter, 0.45 wall thickness, and 9"25 long.
Investment Cast Steel Tube Warhead, Composition C-3 loaded.

Figure 2

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

TABLE I

MASS DISTRIBUTION DATA

FRAGMENTATION OF INVESTMENT CAST STEEL TUBE WARHEAD: 4"6 O.D.; "45 WALL, 9'25 LONG, COMP C-3 LOADED																						
FUZE: SPECIAL ENGINEERS BLASTING CAP AND TETRYL BOOSTER FROM MK 44 AUX. DET.																						
NUMBER AND WEIGHT OF RECOVERED FRAGMENTS																						
Rd. No.	Comp. Wt. lb.	Filler Wt. lb.														TOTAL		Photo No, NP9	46934			
			0-5/8		5/8-1.25		1.25-2.5		2.5-5		5-10		10-20		20-40		40-80			Wt.	Gms. No.	
			Grams	Wt.	Grams	Wt.	Grams	Wt.	Grams	Wt.	Grams	Wt.	Grams	Wt.	Grams	Wt.	Grams					Wt.
			Gms.	No.	Gms.	No.	Gms.	No.	Gms.	No.	Gms.	No.	Gms.	No.	Gms.	No.	Gms.			No.	Gms.	No.
1	20.48	5.63	385	---	308	356	596	341	732	217	1185	174	1506	124	1582	57	330	7	6624	1276		

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

DISTRIBUTION

Bureau of Ordnance:

Ad3	1
Re2	1
Re3	2
Re3f	5

Chief of Ordnance Department of the Army Attn: OKDTA-AR	2
---	---

Navy Research Section Library of Congress Washington 25, D. C. (Via BUORD Re3)	2
---	---

Commanding General Aberdeen Proving Ground Aberdeen, Maryland Attn: Technical Information Section Development and Proof Services	1
--	---

Commander, Operational Development Force U. S. Atlantic Fleet, U. S. Naval Base Norfolk 11, Virginia	1
--	---

Naval Ordnance Laboratory	1
---------------------------	---

Naval Ordnance Laboratory Attn: Explosives Division Attn: Mr. H. W. Semon	1 1
---	--------

Picatinny Arsenal, Dover, N. J. Attn: Technical Division	1
---	---

Reports Office APL/JHU, Silver Spring, Maryland	1
--	---

APL/JHU, Silver Spring, Md. Attn: Mr. H. S. Morton (Via INSORD, Silver Spring, Md.)	1
---	---

~~SECRET~~
SECRET

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

DISTRIBUTION (Continued)

Bureau of Ordnance Technical Liaison Office	1
Bell Telephone Laboratories	
Whippany, New Jersey	1
USNOTS, Inyokern, China Lake, Calif.	
Inst. for Cooperative Research	
JHU/1315 St. Paul St.	
Via: (District Chief, Phila. Ord District	
1500 Chestnut St., Phila. 2, Pa.	1
Attn: Mr. Edward R. C. Niles)	
Director, Research and Development Division	
New Mexico Institute of Mining and Technology	
Socorro, New Mexico	
Via: Development Contract Officer	
New Mexico Institute of Mining and Technology	1
Socorro, New Mexico	
Boeing Airplane Company	
Seattle Division	1
Seattle, Washington	
Local:	1
OT	1
OTZ	1
OT-1	1
File	

UNCLASSIFIED

APPENDIX C

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

PART A

SYNOPSIS

1. This test was conducted to determine the fragment mass distribution of a Composition C-3 loaded investment cast steel tube.
2. a. Approximately 70% of the total weight of the warhead fragmented into fragments weighing more than 5 grams each.
b. The fragment mass distribution compared favorably with that obtained from similar steel tubes manufactured by other processes.

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

TABLE OF CONTENTS

	<u>Page</u>
SYNOPSIS	1
TABLE OF CONTENTS.	2
AUTHORITY.	3
REFERENCES	3
BACKGROUND	3
OBJECT OF TEST	3
PERIOD OF TEST	3
DESCRIPTION OF ITEM UNDER TEST	4
PROCEDURE.	5
RESULTS AND DISCUSSION	5
CONCLUSIONS.	6
APPENDIX A - WARHEAD, PHOTOGRAPH	FIGURE 1
APPENDIX B - MASS DISTRIBUTION DATA.	FIGURE 2 TABLE I
APPENDIX C - DISTRIBUTION.	1-2 (Incl)

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

PART B

INTRODUCTION

1. AUTHORITY:

This test was authorized by reference (a) and conducted under Task Assignment NPG-Re3f-607-1-52, reference (b).

2. REFERENCES:

- a. BUORD Conf ltr NP9 Re3f-EJHL:edb Ser 12896 of 26 Sep 1951
- b. BUORD Conf ltr NP9 Re3f-EJHL:edb Ser 25777 of 18 Sep 1951
- c. NPG Conf Report No. 705 of 16 Jan 1951
- d. NPG Conf Report No. 681 of 15 Nov 1950

3. BACKGROUND:

In the development of warhead cases for air target guided missiles, an investment cast steel tube was manufactured. The casting of steel tubes is a simple and expeditious method of manufacturing warhead cases.

4. OBJECT OF TEST:

This test was conducted to determine the fragment mass distribution of a Composition C-3 loaded investment cast steel tube.

5. PERIOD OF TEST:

- | | |
|-------------------------------------|-------------------|
| a. Date Project Letter | 26 September 1951 |
| b. Date Necessary Material Received | 24 September 1951 |
| c. Date Commenced Test | 4 December 1951 |
| d. Test Completed | 4 December 1951 |

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

- - - - -

PART C

DETAILS OF TEST

6. DESCRIPTION OF ITEM UNDER TEST:

From an investment cast steel tube, cylindrical, 4"6 outside diameter, .45 wall thickness, 9"25 long, manufactured by S. D. Hicks and Son Co., a 2 1/2" x 2 1/2" section from one end was removed for physical tests. The physical properties and chemical analysis of this tube were as follows:

Physical Properties: (Tests conducted at NPG)

<u>Test No.</u>	<u>Yield Strength at 0.2% offset (psi)</u>	<u>Tensile Strength (psi)</u>	<u>Elongation (% in 4d)</u>	<u>Reduction of Area (%)</u>
1	28,000	35,800	2.7	5.4
2	24,000	33,100	2.7	6.5
3	22,500	32,400	4.0	10.4
Average	24,800	33,800	3.1	7.4

Chemical Properties: (reported in reference (a))

<u>C</u>	<u>Si</u>	<u>Mn</u>
.10	.39	.69

The warhead was loaded with Composition C-3, and the weights were as follows:

<u>Empty</u>	<u>Comp. C-3</u>	<u>Total</u>
14.85 lbs.	5.63 lbs.	20.48 lbs.

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

7. PROCEDURE:

The warhead was initiated by a MK 44 auxiliary detonating fuze tetryl pellet and a special engineers blasting cap in a sawdust-filled chamber. After the detonation, the sawdust was sifted and the fragments recovered by the use of sieves and a magnetic separator.

8. RESULTS AND DISCUSSION:

The detailed mass distribution data are listed in Table I and the fragments are shown in Figure 2. The number of fragments in the various weight groups are summarized as follows:

<u>Wt. Group</u> <u>(grams)</u>	<u>No.</u> <u>Fragments</u>	<u>Wt. of</u> <u>Fragments (gm.)</u>	<u>% of Total</u> <u>Weight</u>
40-80	7	330	5
20-40	57	1582	24
10-20	124	1506	23
5-10	174	1185	18
2 1/2 - 5	217	732	11
1 1/4 - 2 1/2	341	596	9
5/8 - 1 1/4	356	308	4
0 - 5/8	---	385	6

Approximately 70% of the total warhead weight fragmented into fragments which were greater than 5 grams in weight. Comparing the fragment sizes with those recovered from similar size warheads manufactured by processes other than casting, references (c) and (d), indicate that the casting of cases may be a satisfactory method for producing warheads. It should be noted, however, that the results reported in references (c) and (d) are for warheads with substantially thinner walls, so that no exact comparison can be made.

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

PART D

CONCLUSIONS

9. a. Approximately 70% of the total weight of the warhead fragmented into fragments weighing more than 5 grams each.

b. The fragment mass distribution compared favorably with that obtained from similar steel tubes manufactured by other processes.

~~CONFIDENTIAL~~

NPG REPORT NO. 956

Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

The tests upon which this report is based were conducted by:
V. PHILIPCHUK, Fragmentation Battery Officer,
Fragmentation Division,
Terminal Ballistics Department
H. E. ROMINE, Head, Metallurgy Division,
Terminal Ballistics Department

This report was prepared by:
V. PHILIPCHUK, Fragmentation Battery Officer,
Fragmentation Division,
Terminal Ballistics Department

This report was reviewed by:
R. E. LYDDANE, Director of Research
Terminal Ballistics Department
W. B. ROBERTSON, Lieutenant Commander, USN
Terminal Ballistics Batteries Officer
Terminal Ballistics Department
R. T. RUBLE, Lieutenant Commander, USN
Terminal Ballistics Officer
Terminal Ballistics Department
C. C. BRAMBLE, Director of Research, Ordnance Group

APPROVED: IRVING T. DUKE
Rear Admiral, USN
Commander, Naval Proving Ground


C. T. MAURO
Captain, USN
Ordnance Officer
By direction

~~CONFIDENTIAL~~
~~UNCLASSIFIED~~