



Fatigue Properties of Nonferrous
Alloys for Heat Exchangers,
Pumps, and Piping

Assignment 86 108
MEL R&D Report 232/66
May 1966

By

M. R. Gross and R. C. Schwab

AD 633771

U. S. NAVY

MARINE ENGINEERING LABORATORY

code

CLEARINGHOUSE	
FEDERAL SCIENTIFIC AND TECHNICAL INFORMATION	
Hardcopy	
\$ 2.00	pp 70

Annapolis, Md. D D

JUN 15 1966

Dedicated To PROGRESS IN MARINE ENGINEERING

Best Available Copy

Distribution of this document is unlimited.

20040826008

Fatigue Properties of Nonferrous
Alloys for Heat Exchangers,
Pumps, and Piping

Assignment 86 108
MEL R&D Report 232/66
May 1966

By

M. R. Gross and R. C. Schwab

M. R. Gross
M. R. GROSS

R. C. Schwab
R. C. SCHWAB

Approved by:

W. L. Williams
W. L. WILLIAMS
Naval Alloys D

47763001

800 45804 005

ABSTRACT

The fatigue behavior of 13 nonferrous alloys used for corrosion-resistant heat exchangers, pumps, and piping systems was investigated over a broad life spectrum of 100 to 100-million cycles. Both cast and wrought copper-base and nickel-base alloys were studied. It is concluded that wrought Monel* and forged Ni-Al bronze have the highest fatigue strengths, whereas gun metal and valve bronze have the lowest. The effect of salt water on fatigue performance was not found to be highly significant. The use of Langer's equation to predict stress-cycle relationships gave satisfactory results for wrought alloys but appeared to be overly conservative for cast alloys.

*Registered trade name of the International Nickel Company, Incorporated.

TABLE OF CONTENTS

	<u>Page</u>
CONTRIBUTION LIST	ii
PREFACE	iii
INTRODUCTION	1
MATERIALS INVESTIGATED	2
METHOD OF TEST	2
FAILURE CRITERIA	4
RESULTS OF TESTS	5
COMPARISON OF FATIGUE STRENGTHS	6
CONCLUSIONS	7
REFERENCES	8
LIST OF FIGURES	
Figure 1 - Drawing, Rotating Cantilever Beam Fatigue Specimen	
Figure 2 - Drawing, Low-Cycle Fatigue Specimen	
Figure 3 - Curve, Flexural Fatigue Curves, Gun Metal (Cast)	
Figure 4 - Curve, Flexural Fatigue Curves, Valve Bronze (Cast)	
Figure 5 - Curve, Flexural Fatigue Curves, Ni-Al Bronze (Cast)	
Figure 6 - Curve, Flexural Fatigue Curves, Ni-Al Bronze (Forged)	
Figure 7 - Curve, Flexural Fatigue Curves, Superston 40 (Cast)	
Figure 8 - Curve, Flexural Fatigue Curves, 70-30 Cupronickel (Cast)	
Figure 9 - Curve, Flexural Fatigue Curves, 70-30 Cupronickel (Wrought)	
Figure 10 - Curve, Flexural Fatigue Curves, 90-10 Cupronickel (Hard)	
Figure 11 - Curve, Flexural Fatigue Curves, Cufenloy 40 (Annealed)	
Figure 12 - Curve, Flexural Fatigue Curves, Cufenloy 40 (DSR)	
Figure 13 - Curve, Flexural Fatigue Curves, Cupro- nickel 707 (Wrought)	
Figure 14 - Curve, Flexural Fatigue Curves, Monel "E" (Cast)	
Figure 15 - Curve, Flexural Fatigue Curves, Monel (Wrought)	

Introduction

Many copper-base and nickel-base alloys are used in the construction of heat exchangers, pumps, and piping systems designed to handle fresh or saline water. In the selection of materials for such applications, consideration is given primarily to corrosion resistance, erosion resistance, and heat transfer characteristics. In most applications the applied stress levels are low. Accordingly, the structural strength properties of the materials are relatively unimportant.

In recent years, more and more attention has been given to the structural properties of these alloys because of (1) cost and weight reduction programs, (2) conservation of strategic materials, (3) development of new high-strength alloys, and (4) new applications which impose high stress levels. Typical of the latter are sea-connected cooling systems for hydrospace vehicles.

One of the most likely modes of mechanical failure in systems undergoing cyclic pressurization or thermal shock loading is metal fatigue. The frequency of stress cycling in such systems may vary from that of an occasional start-up and shutdown to vibrational forces developed by the movement of the heat-exchanger fluids. Little or no published information on the alloys used in this type of service was found in reviewing the literature several years ago. Accordingly, tests were conducted at the U. S. Navy Marine Engineering Laboratory to establish the fatigue behavior of

ariety of corrosion-resistant nonferrous alloys. The results of these tests are presented in this paper.

Materials Investigated

The 13 alloys investigated are listed in Table 1, together with their chemical compositions and tensile properties.

Included are the strength coefficient, K, and strain-hardening exponent, n, contained in the true-stress/true-strain relationship:

$$\sigma = K \epsilon^n$$

There are some deficiencies in the tensile properties of the cast materials with respect to the governing specifications. This is to be expected inasmuch as the specification requirements are usually based on separately cast test coupons, whereas the values given in Table 1 were obtained on specimens removed from cast plates.

Method of Test

Two types of flexural fatigue specimens were used in the investigation. The high-cycle fatigue tests were performed with rotating cantilever-beam specimens having the dimensions shown in Figure 1. These were constant deadweight load tests with a cycle frequency of 1450 cpm. The smooth test lengths were circumferentially and longitudinally polished to a metallographic finish.

Table 1
Chemical Composition and Mechanical Properties of Alloys

Alloy	Type	Condition	Specification	Chemical Composition - %										Mechanical Properties							
				Chemical Composition - %										YS (0.2% Off- set) ksi	TS ksi	Elong % in 2 in.	RA %	K ksi	Hard- ness Rb	E x 10 ⁶ psi	
				Cu	Ni	Fe	Mn	Zn	Al	Sn	Si	Others									
Gun Metal (Comp G)	C	As-cast	MIL-M-16576	87.2	0.7	0.02	-	3.5	-	8.4	-	-	-	15.6	38.7	44	39	83	0.45	40	15
Valve Bronze (Comp M)	C	As-cast	MIL-B-16541	88.5	0.5	0.01	-	3.8	-	5.6	-	Pb-1.6 P-C.01	-	15.8	28.0	17	20	58	0.34	39	14
Ni-Al Bronze	C	As-cast	MIL-B-21230 Alloy 1	80.1	5.2	3.7	0.7	-	10.3	-	-	-	-	42.1	97.3	14	16	181	0.32	90	13
Ni-Al Bronze	F	Annealed	QC-B-679 Comp 2	81.2	4.5	2.8	0.9	-	10.6	Nil	-	-	-	51.8	103.3	16	15	206	0.28	99	17
Superston 40	C	As-cast	MIL-B-21230 Alloy 2	74.6	2.2	3.3	12.5	-	7.4	-	-	-	-	43.4	85.4	20	24	154	0.26	82	18
70-30 Cupro- nickel	C	As-cast	MIL-C-20159	66.8	30.4	0.5	1.25	-	-	-	0.5	Cb 0.5	-	48.1	79.2	23	39	151	0.27	73	18
70-30 Cupro- nickel	W	Annealed	MIL-C-15726	68.6	29.6	0.6	0.9	0.2	-	-	-	-	-	20.2	58.5	49	70	116	0.21	58	22
90-10 Cupro- nickel	W	Hard	MIL-C-15726	88.0	10.0	1.3	0.6	0.04	-	-	-	Pb	<0.02	49.6	53.8	33	77	73	0.09	69	20
Cu-ferro- 40	W	Annealed	-	55.0	Rem	2.2	1.4	0.06	0.01	0.01	0.01	-	Pb-0.01 As-0.01	22.4	70.3	50	78	174	0.48	59	24
Cu-ferro- 40	W	DSR*	-	55.0	Rem	2.2	1.4	0.06	0.01	0.01	0.01	-	Pb-0.01 As-0.01	68.4	79.0	26	72	110	0.10	90	20
Cupro- nickel - 707	W	Annealed	-	64.1	29.6	5.4	0.8	0.11	-	-	<0.05	0.02	Pb-0.01	51.0	81.6	33	48	148	0.25	83	22
Monel "E"	C	As-cast	QQ-N-288 Class "E"	30.3	63.1	2.2	0.9	-	-	-	1.6	C-0.1 Cb-1.6	-	27.0	59.5	23	24	128	0.36	70	23
Monel	W	Annealed	MIL-N-894 Class A	32.7	65.0	0.9	1.0	-	0.02	-	-	-	-	33.1	83.6	46	70	167	0.35	76	26

*Drawn and Stress relieved.
C - Cast; F - Forged; W - Wrought
YS - Yield Strength
TS - Tensile Strength
Elong - Elongation
RA - Reduction of Area

The low-cycle fatigue tests were performed with equipment described previously.¹ Flat flexure-type specimens having the dimensions shown in Figure 2 were used. The short end of the specimen was held stationary, while the long end was flexed between mechanical stops by a hydraulic piston. One or more strain gages (0.25-inch gage length) were attached to the narrowest section to record the longitudinal strain. The applied bending force was measured with a load cell. The total strain range, $\Delta\epsilon_T$, was obtained from strain gage readings, and the nominal bending-stress range was calculated from elastic stress-strain relations using the measured load range. Specimens were cycled at 1000 cpm.

All of the fatigue tests were of the completely reversed (Fatigue ratio = -1). Whereas most of the specimens were tested in air, a few were tested with Severn River water continuously wetting the test surface. Severn River water is a brackish estuary water containing 1/6 to 1/3 the salt content of natural seawater, depending on the season and the tide. Previous fatigue tests in both Severn River water and natural seawater have shown no significant differences in the effects of the two media.

Failure Criteria

Failure in the high-cycle, rotating cantilever-beam tests was defined as the onset of complete fracture. Failure in the low-cycle fatigue tests was defined as the onset of complete fracture.

tests was defined as one or more surface cracks 3/16 to 1/4 inch in length.

Results of Tests

The results of the tests are plotted in log-log form in Figures 3 through 15. Two methods have been used in analyzing the data. The top graph in each figure is the S_R vs N relationship for the data, where S_R is the nominal reversed bending stress and N is the number of cycles to failure. S_R was calculated from the elastic stress formula

$$S_R = \frac{\Delta M c}{2I} \quad \dots\dots (1)$$

where ΔM = bending moment range, in-lb.

c = distance from neutral axis to outermost fiber at minimum cross section, in.

I = moment of inertia of minimum cross section, in.⁴

The bottom graph in each figure is the S_{pE} vs N relationship for the data, where S_{pE} is the reversed pseudoelastic or apparent elastic stress calculated as follows:

$$S_{pE} = \frac{\Delta \epsilon_T \cdot E}{2} \quad \dots\dots (2)$$

where $\Delta \epsilon_T$ = total strain range as determined from strain gages on the test section, in/in.

E = modulus of elasticity (Table 1), psi.

curvilinear relationship between S_{PE} and N was obtained by fitting the following relationship to the data.

$$S_{PE} = \frac{C}{N^m} + S_E \quad \dots\dots (3)$$

C and m = best-fit constants

S_E = endurance limit or fatigue strength at 10^6 cycles, psi.

Best-fit equation for the S_{PE} vs N data is given in each

a.

Equation (3) is a generalization of the following equation used by Langer² for predicting the S_{PE} vs N fatigue curve tensile test data.

$$S_{PE} = \frac{E}{4N^{0.5}} \ln \left(\frac{100}{100-RA} \right) + S_E \quad \dots\dots (4)$$

RA = reduction of area, percent.

The dashed line in each figure is Langer's predicted curve on Equation (4) and the tensile data presented in Table 1.

The triangle symbols in graphs represent specimens which been continuously exposed to salt water during the fatigue

Comparison of Fatigue Strengths

Table 2 represents an attempt to rationalize the fatigue for the 13 alloys investigated. The S_R and S_{PE} values were from the curves in Figures 3 through 15. The values in column were then ranked in order of decreasing fatigue

strength. An average rank for each material is shown in the right hand column.

Table 2
Comparison of Fatigue Strengths
of Alloys Investigated

Alloy	Type	Condition	Fatigue Strength At.						Average Rank
			10 ³ Cycles		10 ⁵ Cycles		10 ⁸ Cycles		
			SR ksi	SPE ksi	SR ksi	SPE ksi	SR ksi	SPE ksi	
Gun Metal	Cast	As-cast	35(12)	96(12)	17(12)	25(12)	6(12.5)	8(12.5)	(12.2)
Valve Bronze	Cast	As-cast	32(13)	52(13)	16(13)	17(13)	6(12.5)	8(12.5)	(12.8)
Ni-Al Bronze	Cast	As-cast	78(6)	210(5)	46(4)	48(7)	29(3)	30(3)	(4.7)
Ni-Al Bronze	Forged	Annealed	110(1)	230(3)	65(1)	64(1)	35(1.5)	37(1)	(1.4)
Superston 40	Cast	As-cast	83(4)	230(3)	44(5)	50(5)	25(5.5)	25(5.5)	(4.7)
70-30 Cupronickel	Cast	As-cast	70(8)	130(11)	32(10)	27(11)	13(11)	14(11)	(10.3)
70-30 Cupronickel	Wrought	Annealed	57(11)	180(7)	29(11)	54(2)	25(5.5)	25(5.5)	(7.0)
90-10 Cupronickel	Wrought	Hard	74(7)	160(8.5)	38(7)	40(8)	21(8)	21(9)	(7.9)
Cufenloy 40	Wrought	Annealed	58(10)	230(3)	35(8)	38(9)	26(4)	26(4)	(6.3)
Cufenloy 40	Wrought	DSR	100(2)	160(8.5)	48(3)	50(5)	20(9)	23(7.5)	(5.8)
Cupronickel-707	Wrought	Annealed	90(3)	190(6)	50(2)	50(5)	22(7)	23(7.5)	(5.1)
Monel "E"	Cast	As-cast	62(9)	155(10)	34(9)	36(10)	16(10)	16(10)	(9.7)
Monel	Wrought	Annealed	80(5)	350(1)	40(6)	52(3)	35(1.5)	33(2)	(3.1)

Note: Numeral in () is rank of value.

Conclusions

From the data and curves presented in Figures 3 through 15, the following conclusions have been reached relative to the unnotched fatigue behavior of the materials investigated.

- Variations in fatigue strength or life are greater for cast alloys than for wrought alloys.

- The fatigue strength of a wrought alloy is superior to that of a cast alloy of comparable chemical composition.
- Wrought Monel and forged Ni-Al bronze have the highest fatigue strengths, whereas gun metal and valve bronze have the lowest.
- Stress-cycle relationships predicted by Langer's equation are generally satisfactory for wrought alloys but appear to be overly conservative for most cast alloys.
- Salt water does not have a highly significant effect on the fatigue behavior of the alloys investigated.

References

Gross, M. R., "Low-Cycle Fatigue of Materials for Submarine Construction," Naval Engineers Jour, Vol. 75, No. 5, Oct 1963, pp. 783-797

Langer, B. F., "Design of Pressure Vessels for Low-Cycle Fatigue," Jour of Basic Engineering, ASME Trans. Ser. D, Vol. 84, Series D, No. 3, Sep 1962, pp. 389-402




Figure 1

Rotating Cantilever Beam Fatigue Specimen




FIGURE 2 - LOW-CYCLE FATIGUE SPECIMEN

Title and Legend for Figures 3 Through 15

Title

Flexural Fatigue Curves

Legend

- O - Rotating Cantilever Fatigue Tests, Air
- Δ - Rotating Cantilever Fatigue Tests, Salt Water
- - Low-Cycle Fatigue Tests, Air
- ▲ - Low-Cycle Fatigue Tests, Salt Water




FIGURE 3 - GUN METAL (CAST) EQUATION: $S_{PE} = \frac{1.016 \times 10^6}{N^{0.35}} + 6,000$





FIGURE 4- VALVE BRONZE (CAST) EQUATION: $S_{PE} = \frac{4.03 \times 10^5}{N^{0.32}} + 6,000$



CYCLES TO FAILURE - N

FIGURE 5 - Ni-Al BRONZE (CAST) EQUATION: $S_{PE} = \frac{5.57 \times 10^6}{N^{0.49}} + 29,000$




FIGURE 6 - Ni-Al BRONZE (FORGED) EQUATION: $S_{PE} = \frac{3.53 \times 10^6}{N^{0.42}} + 35,000$




FIGURE 7 - SUPERSTON 40 (CAST) EQUATION: $S_{PE} = \frac{3.9 \times 10^6}{N^{0.44}} + 25,000$




FIGURE 8 - 70-30 CUPRONICKEL (CAST) EQUATION: $S_{PE} = \frac{2.8 \times 10^6}{N^{0.45}} + 13,000$




FIGURE 9 - 70-30 CUPRONICKEL (WROUGHT) EQUATION: $s_{PE} = \frac{1.90 \times 10^6}{N^{0.35}} + 20,000$




FIGURE 10 - 90-10 CUPRONICKEL (HARD) EQUATION: $S_{PE} = \frac{2.3 \times 10^6}{N^{0.42}} + 20,000$




FIGURE 11 - CUFENLOY 40 (ANNEALED) EQUATION: $S_{PE} = \frac{1.1 \times 10^7}{N^{0.58}} + 25,000$




FIGURE 12-CUFENLOY 40 (DSR) EQUATION: $S_{PE} = \frac{1.4 \times 10^6}{N^{0.34}} + 20,000$




FIGURE 13 - CUPRONICKEL 707 (WROUGHT) EQUATION: $S_{PE} = \frac{2.4 \times 10^6}{N^{0.39}} + 23,000$




FIGURE 14 - MONEL "E" (CAST) EQUATION: $S_{PE} = \frac{2.51 \times 10^6}{N^{0.42}} + 16,000$




FIGURE 15--MONEL (WROUGHT); EQUATION: $S_{PE} = 2.1 \times 10^7 N^{-0.61} + 33,000$

Security Classification

UNCLASSIFIED

DOCUMENT CONTROL DATA - R&D

Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

ORIGINATING ACTIVITY (Corporate author)

S. Navy Marine Engineering Laboratory
Annapolis, Maryland 21402

2a REPORT SECURITY CLASSIFICATION

UNCLASSIFIED

2b GROUP

SHORT TITLE

Fatigue Properties of Nonferrous Alloys for Heat Exchangers, Pumps,
Piping

DESCRIPTIVE NOTES (Type of report and inclusive dates)

AUTHOR(S) (Last name, first name, initial)

Goss, M. R. and Schwab, R. C.

SHORT DATE

May 1966

7a. TOTAL NO. OF PAGES

23

7b. NO. OF REFS

2

ABSTRACT OR GRANT NO.

9a. ORIGINATOR'S REPORT NUMBER(S)

232/66

SUBJECT NO.

9b. OTHER REPORT NO(S) (Any other numbers that may be assigned
this report)

MEL Assignment 86 108

AVAILABILITY/LIMITATION NOTICES

Distribution of this document is unlimited.

SUPPLEMENTARY NOTES

12. SPONSORING MILITARY ACTIVITY

ABSTRACT

The fatigue behavior of 13 nonferrous alloys used for corrosion-resistant heat exchangers, pumps, and piping systems was investigated over a broad life spectrum of 100 to 100-million cycles. Both cast and wrought copper-base and nickel-base alloys were studied. It is concluded that wrought Monel* and forged Ni-Al bronze have the highest fatigue strengths, whereas gun metal and valve bronze have the lowest. The effect of salt water on fatigue performance was not found to be highly significant. The use of Langer's equation to predict stress-cycle relationships gave satisfactory results for wrought alloys but appeared to be overly conservative for cast alloys.

(Authors)

Registered trade name of the International Nickel Co., Inc.

FORM 1473
JAN 64

UNCLASSIFIED

Security Classification

KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Nonferrous alloys Fatigue behavior, strength Piping systems Copper-base alloys Nickel-base alloys Cast and wrought alloys Salt water effect						

INSTRUCTIONS

ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter a group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. A meaningful title cannot be selected without classification. Show title classification in all capitals in parenthesis immediately following the title.

DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

AUTHOR(S): Enter the name(s) of author(s) as shown on in the report. Enter last name, first name, middle initial. Military, show rank and branch of service. The name of a principal author is an absolute minimum requirement.

REPORT DATE: Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

NUMBER OF REFERENCES: Enter the total number of references cited in the report.

CONTRACT OR GRANT NUMBER: If appropriate, enter applicable number of the contract or grant under which the report was written.

PROJECT NUMBER: Enter the appropriate military department identification, such as project number, project number, system numbers, task number, etc.

ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

OTHER REPORT NUMBER(S): If the report has been signed any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, roles, and weights is optional.