

AD640210

CHARACTERIZATION  
OF  
BERYLLIUM



CLEARINGHOUSE  
FOR FEDERAL SCIENTIFIC AND  
TECHNICAL INFORMATION

Hardcopy Microfiche  
\$ 1.00 \$ 0.50 19 1/2

ARCHIVE COPY

Code 1

RELEASABLE TO  
Clearinghouse for Federal Scientific and Technical  
Information (CFSTI)

National Academy of Sciences—  
National Research Council  
Washington, D. C.

**MATERIALS ADVISORY BOARD**  
**DIVISION OF ENGINEERING**  
**NATIONAL ACADEMY OF SCIENCES-NATIONAL RESEARCH COUNCIL**

**Chairman**

Dr. Walter L. Finlay (1968)  
Assistant Vice President, Research  
Copper Range Company  
630 Fifth Avenue  
New York, New York 10020

**Past Chairman**

Dr. Walter R. Hibbard, Jr., Director (1968)  
Bureau of Mines  
Department of Interior  
Room 4614  
Washington, D. C. 20240

**Members**

Mr. G. Mervin Ault (1970)  
Associate Chief  
Materials & Structure Division  
Lewis Research Center, NASA  
21000 Brookpark Road  
Cleveland, Ohio 44135

Dr. D. J. McPherson (1967)  
Vice President  
IIT Research Institute  
10 West 35th Street  
Chicago, Illinois 60616

Dr. J. H. Crawford, Jr. (1969)  
Associate Director  
Solid State Division  
Oak Ridge National Laboratory  
Oak Ridge, Tennessee 37831

Dr. E. F. Osborn (1969)  
Vice President for Research  
Pennsylvania State University  
207 Old Main Building  
University Park, Pennsylvania 16802

Dr. Morris E. Fine, Professor (1967)  
Department of Materials Science  
Materials Research Center  
Northwestern University  
Evanston, Illinois 60201

Professor Joseph A. Pask (1968)  
Professor of Ceramic Engineering  
Department of Mineral Technology  
University of California  
264 Hearst Mining Building  
Berkeley, California 94720

Dr. N. Bruce Hannay (1969)  
Chemical Director  
Bell Telephone Laboratories  
Murray Hill, New Jersey 07971

Dr. Malcolm M. Renfrew, Head (1967)  
Department of Physical Sciences  
University of Idaho  
Moscow, Idaho 83843

Dr. William J. Harris, Jr. (1970)  
Assistant to the Vice President  
Battelle Memorial Institute  
1755 Massachusetts Avenue, N.W.  
Washington, D. C. 20036

Dr. William Rostoker (1970)  
Professor of Metallurgy  
Department of Materials Engineering  
College of Engineering  
University of Illinois  
Box 4348  
Chicago, Illinois 60680

Mr. Abraham Hurlich (1970)  
Manager, Materials & Processes  
Department 572-0  
General Dynamics/Convair  
P. O. Box 1128  
San Diego, California 92112

Mr. Adolph O. Schaefer (1969)  
Consulting Engineer  
R. D. 4  
Norristown, Pennsylvania 19401

Mr. J. Harry Jackson (1968)  
General Director  
Metallurgical Research Division  
Reynolds Metals Company  
Fourth & Canal Streets  
Richmond, Virginia 23218

Dean Robert D. Stout (1968)  
Graduate School  
Lehigh University  
Bethlehem, Pennsylvania 18015

Mr. Humboldt W. Leverenz (1968)  
Staff Vice President  
Research & Business Evaluation  
RCA Laboratories  
David Sarnoff Research Center  
Princeton, New Jersey 08540

Dr. Morris Tanenbaum (1969)  
Director of Research and Development  
Western Electric Company  
P. O. Box 900  
Princeton, New Jersey 08540

Mr. Alan Levy, Manager (1967)  
Materials & Fabrication  
Research & Development Department  
Solid Rocket Operations  
Aerojet-General Corporation  
P. O. Box 1947  
Sacramento, California 95809

Mr. Alfred C. Webber (1968)  
Research Associate  
Plastics Department  
Experimental Station  
Building 323, Room 210  
E. I. duPont de Nemours & Co., Inc.  
Wilmington, Delaware 19898

Mr. Louis R. McCreight, Manager (1970)  
Materials Science Section  
Space Sciences Laboratory  
General Electric Company  
P. O. Box 8555  
Philadelphia, Pennsylvania 19101

Mr. F. Travers Wood, Jr., Director (1968)  
Engineering Laboratories and Services  
Missile & Space Systems Division  
Douglas Aircraft Company, Inc.  
3000 Ocean Park Blvd.  
Santa Monica, California 90406

**THE NATIONAL ACADEMY OF SCIENCES** is a private, honorary organization of more than 700 scientists and engineers elected on the basis of outstanding contributions to knowledge. Established by a Congressional Act of Incorporation signed by Abraham Lincoln on March 3, 1863, and supported by private and public funds, the Academy works to further science and its use for the general welfare by bringing together the most qualified individuals to deal with scientific and technological problems of broad significance.

Under the terms of its Congressional charter, the Academy is also called upon to act as official—yet independent—adviser to the Federal Government in any matter of science and technology. This provision accounts for the close ties that have always existed between the Academy and the Government, although the Academy is not a governmental agency and its activities are not limited to those on behalf of the Government.

**THE NATIONAL ACADEMY OF ENGINEERING** was established on December 5, 1964. On that date the Council of the National Academy of Sciences, under the authority of its Act of Incorporation, adopted Articles of Organization bringing the National Academy of Engineering into being, independent and autonomous in its organization and the election of its members, and closely coordinated with the National Academy of Sciences in its advisory activities. The two Academies join in the furtherance of science and engineering and share the responsibility of advising the Federal Government, upon request, on any subject of science or technology.

**THE NATIONAL RESEARCH COUNCIL** was organized as an agency of the National Academy of Sciences in 1916, at the request of President Wilson, to enable the broad community of U. S. scientists and engineers to associate their efforts with the limited membership of the Academy in service to science and the nation. Its members, who receive their appointments from the President of the National Academy of Sciences, are drawn from academic, industrial and government organizations throughout the country. The National Research Council serves both Academies in the discharge of their responsibilities.

Supported by private and public contributions, grants, and contracts, and voluntary contributions of time and effort by several thousand of the nation's leading scientists and engineers, the Academies and their Research Council thus work to serve the national interest, to foster the sound development of science and engineering, and to promote their effective application for the benefit of society.

**THE DIVISION OF ENGINEERING** is one of the eight major Divisions into which the National Research Council is organized for the conduct of its work. Its membership includes representatives of the nation's leading technical societies as well as a number of members-at-large. Its Chairman is appointed by the Council of the Academy of Sciences upon nomination by the Council of the Academy of Engineering.

**THE MATERIALS ADVISORY BOARD** is a unit of the Division of Engineering of the National Academy of Sciences-National Research Council. It was organized in 1951 under the name of the Metallurgical Advisory Board to provide to the Academy advisory services and studies in the broad field of metallurgical science and technology. Since the organization date, the scope has been expanded to include organic and inorganic nonmetallic materials, and the name has been changed to the Materials Advisory Board.

Under a contract between the Office of the Secretary of Defense and the National Academy of Sciences, the Board's present assignment is

"...to conduct studies, surveys, make critical analyses, and prepare and furnish to the Director of Defense Research and Engineering advisory and technical reports, with respect to the entire field of materials research, including the planning phases thereof."



**CHACTERIZATION  
OF  
BERYLLIUM**

**Prepared by the  
Materials Advisory Board  
Division of Engineering - National Research Council**

**as a service of  
The National Academy of Sciences  
The National Academy of Engineering  
to the  
Office of Defense Research and Engineering  
Department of Defense**

**RELEASABLE TO  
Clearinghouse for Federal Scientific and Technical  
Information (CFSTI)**

**National Research Council  
National Academy of Sciences - National Academy of Engineering  
Washington, D. C.  
August 1966**

The National Research Council, under the cognizance of both Academies, performs study, evaluation, or advisory functions through groups composed of individuals selected from academic, governmental, and industrial sources for their competence or interest in the subject under consideration. Members of these groups serve as individuals contributing their personal knowledge and judgments and not as representatives of any organization in which they are employed or with which they may be associated.

This report is one of a series in a study undertaken by the Materials Advisory Board for the National Academy of Sciences in execution of work under Defense Supply Service Contract No. DA-49-083 OSA 313 between the Department of Defense and the National Academy of Sciences.

No portion of this report may be published without prior approval of the contracting agency.

**MATERIALS ADVISORY BOARD**

**COMMITTEE ON BERYLLIUM METALLURGY**

**Chairman: Dr. T. L. Johnston**  
**Senior Scientist**  
**Ford Scientific Laboratory**  
**Dearborn, Michigan**

**Members**

**Mr. Wilfred H. Dukes**  
**Chief Engineer**  
**Vehicle Structure, D-32**  
**Bell Aerosystems Company**  
**Buffalo, New York**

**Dr. Stanley Gelles, Scientist**  
**Ledgemont Laboratory**  
**Kennecott Copper Corporation**  
**128 Spring Street**  
**Lexington, Massachusetts**

**Mr. A. G. Gross, Jr.**  
**Research Specialist**  
**Dept. 532-21, Bldg. 68**  
**Autonetics Division of N.A.A.**  
**Anaheim, California 92803**

**Dr. Marvin Herman, Section Chief**  
**Materials Sciences, Materials Lab.**  
**Allison Division**  
**General Motors Corporation**  
**Indianapolis, Indiana 46206**

**Dr. Martin I. Jacobson**  
**Research Scientist**  
**Department 52-30, Bldg. 201**  
**Materials Science Laboratory**  
**Research & Development Division**  
**Lockheed Missiles & Space Company**  
**3251 Hanover Street**  
**Palo Alto, California**

**Mr. Lee W. Roberts, Jr.**  
**Process & Materials Development Div.**  
**Chemistry Department**  
**Lawrence Radiation Laboratory**  
**P. O. Box 808**  
**Livermore, California 94551**

**Mr. Jack A. Yoblin**  
**General Manager**  
**Nuclear Metals Division**  
**Whittaker Corporation**  
**West Concord, Massachusetts 01781**

**Liaison Representatives**

**DOD Mr. John C. Barrett, Office of the Director of Defense, Research & Engineering, The Pentagon, Washington, D. C.**

**AF/RTD Mr. T. D. Cooper, Code MAMP, Wright-Patterson AFB, Ohio**

**Mr. K. L. Kojola, Code MAMP, Wright-Patterson AFB, Ohio**

**Army Mr. L. Croan, Materials Engineer, Army Material Command, Room 2504 Gravelly Point, Virginia**

**Mr. Jacob Greenspan, Army Materials Research Agency, Watertown Arsenal, Watertown, Massachusetts**

- Navy** Mr. Richard Schmidt, 2W96 W. Building, Naval Air Systems Command  
Department of the Navy, Washington, D. C. 20360
- AEC** Mr. Frank Kerze, Reactor Development & Technology Division, Atomic  
Energy Commission, Washington, D. C. 20545
- NASA** Mr. Richard Raring, Materials Research Program, National Aeronautics  
and Space Administration, Washington, D. C. 20546
- BuMines** Mr. J. Bilbrey, Staff Metallurgist, Room 4624, Bureau of Mines  
Washington, D. C. 20242

**Materials Advisory Board Staff:** Dr. Joseph R. Lane  
Staff Metallurgist  
Materials Advisory Board  
National Academy of Sciences-  
National Research Council  
2101 Constitution Avenue  
Washington, D. C. 20418

**COMMITTEE ON BERYLLIUM METALLURGY****TASK GROUP ON CHARACTERIZATION**

**Chairman: Mr. Jack A. Yoblin**  
**General Manager**  
**Nuclear Metals Division**  
**Whittaker Corporation**  
**West Concord, Massachusetts 01781**

**Members**

**Mr. A. G. Gross, Jr.**  
**Research Specialist**  
**Dept. 532-21, Bldg. 68**  
**Autonetics Division of N.A.A.**  
**Anaheim, California 92803**

**Mr. A. Hauser**  
**Senior Engineer**  
**Materials Development Lab.**  
**Pratt & Whitney Aircraft Division**  
**East Hartford, Connecticut**

**Mr. Arthur F. Hayes**  
**Senior Metallurgical Engineer**  
**The Ladish Company**  
**Cudahy, Wisconsin**

**Mr. Lee Roberts, Jr.**  
**University of California**  
**Lawrence Radiation Laboratory**  
**P. O. Box 808**  
**Livermore, California**



## ABSTRACT

Research and development projects involving beryllium have not always controlled or recorded all the significant variables. Applications have languished because of lack of reproducibility or the difficulty of relating unexpected behavior to prior processing. What has been lacking is an adequate characterizing of the metal. While this attempt at characterizing has fallen short of a complete scientific description, we have reached the stage where major correlations between processing, structure, and properties can be obtained if the data indicated in the report is collected.

This brief report has compiled the major process variables corresponding to the principal operations gone through in producing a beryllium mill product, and then a part. This compilation comprises a check list which should be reviewed at the start of a research or development effort to ensure that variables which might be significant are not being overlooked. The ultimate object of compiling and studying such data is to assure uniformity, and thus introduce reliability into manufactured parts.

CONTENTS

	<u>Page</u>
MEMBERSHIP, COMMITTEE ON BERYLLIUM METALLURGY . . . . .	iii
MEMBERSHIP, TASK GROUP ON CHARACTERIZATION . . . . .	v
ABSTRACT . . . . .	vii
CHARACTERIZATION OF BERYLLIUM . . . . .	1
FIGURE 1 . . . . .	3
TABLE I . . . . .	4

## CHARACTERIZATION OF BERYLLIUM

In a review of beryllium research<sup>\*</sup>, the statement was made, "It is the unanimous opinion of the Committee that future research support should place emphasis on the characterization of polycrystalline material.". The report went on to state, "Characterization is viewed broadly as a correlation of processing factors (such as casting, attritioning, and consolidation variables) and microstructure, (the latter being defined in terms of light and electron microscopy, microprobe analysis and texture determined by X-ray analysis) and a correlation between microstructural changes and those engineering properties that are used to predict performance."

A task group was established by the Committee on Beryllium Metallurgy in February 1966 to attempt to determine if the characterization of beryllium was possible, and if so, to suggest how this might be done. The members of this task group are shown on Page v of this report. Substantial agreement was obtained, as reported in the following pages.

It was considered that a full scientific characterization would be both extremely difficult and of little practical utility. It should be noted that this is, instead, an attempt to reconcile the most serious problems of beryllium with a practical approach to a better understanding of the relationship between process, structure, and properties. As such, this brief report represents an engineering approach (as contrasted to a purely scientific approach). It is strongly felt that improved intercourse among the users, fabricators, and producers of beryllium (under the guidance of the various sponsoring agencies) can and will result in substantially improved usage of this potentially valuable metal.

An MAB Ad Hoc Committee on Characterization of Materials has proposed the following definition:

Characterization describes those features of the composition and structure of a material that are significant for a particular preparation, study of properties, or use, and suffice for reproduction of the material.

---

<sup>\*</sup>Fifth Progress Report by the Committee on Beryllium Metallurgy of the Materials Advisory Board (MAB-199-M(5)), February 1966.

This report does not purport to characterize beryllium; rather it attempts to provide guidance to research directors and project sponsors, describing the measurements which should be made so that a true characterization can be performed later. The emphasis here is on those processing steps which probably have the greatest influence on structure, and thus on properties.

The approach used was to visualize the processing and fabrication of beryllium as a framework, beginning with the reduction to metal through to the manufacture of a part or component, as shown in Figure 1. The principal steps involved are shown on the chart, Table I. At each major operation, called a checkpoint, two classes of descriptors are listed. Under Roman numerals are the measurements which describe the structure or properties. Under Arabic numerals, the process variables which are measured or controlled are listed. In each class, typical measurements or variables which are believed to be important, are listed. This listing is not all-inclusive but is suggestive of major variables. The tabulation can be considered as a checklist of items to be reviewed when planning a research program. It is unlikely that funds would be available to measure or describe all the items listed, nor that all would be pertinent for any specific program.

In compiling these lists, consideration was given to the problem of specifying both processing and minimum level of properties when procuring materials. The point to be emphasized is that, at the least, as many as possible of these important variables should be measured and recorded (even if not controlled) to permit possible later correlation with structure and performance. The purchaser may wish to specify the processing, but may not then also expect a guaranteed level of properties.

As an example of how this scheme might work, let us suppose that an experimental program is to be planned with the goal of developing jet engine hardware.

Two specific vacuum hot pressed billets (two compositions) would be prepared (special material, special handling). The material from which they are made should be fully characterized, i.e., all process parameters




Figure 1. Flow chart for beryllium production. See Table I for description of process variables (Arabic numerals) and checkpoints for measurements (Roman numerals).

Table I

Processing Steps & Associated Measurements

<u>CHECKPOINT; MEASUREMENTS OF STRUCTURE AND/OR PROPERTIES</u>	<u>CORRESPONDING PROCESS VARIABLES</u>
<u>I. After Reduction, Before Ingot Casting</u> Chemical Composition	1. <u>Reduction</u>  2. <u>Ingot Casting</u> Crucible charge (virgin flake or pebble, remelt or revert scrap) Crucible composition and preparation Atmosphere (time, temperature, vacuum) Pour temperature and method Mold (material, preheat, configuration, hot-top) Solidification rate  2-3. <u>Atomization</u> Crucible material Atmosphere Temperature Atomization medium Collection medium
<u>II. After Ingot Casting, Before Attritioning or Hot Working</u> Chemical composition (average, local)  The following checkpoints apply to metal to be worked:  Soundness (cracks, inclusions, voids)  Morphology (size, shape distribution)  Macrostructure (etched slice)  Density  Inclusions and precipitates (fractography)  Texture	3. <u>Comminution</u> Atmosphere Grinding medium Mill materials Classification method (wet, dry, etc.) Temperature System to ensure detection of extraneous particles

**III. After Comminution, Before Hot Pressing**

Particle size, shape, distribution  
Chemical Composition  
Extraction of undesirables  
(liberation of second phases)  
Shelf life (date of manufacture)  
Tramp inclusions

**4. Hot Pressing**

Cycle parameters (time, temperature, atmosphere)  
Container and die materials and preparation  
Loading method (preconsolidation, vibration, etc.)  
Pressing size  
Sectioning plan  
Date of pressing  
Amount of skin removed  
Can material and billet density (for direct consolidation of powder)  
Reduction per pass  
Direction of working  
Deformation rate  
Cooling rate  
System for foreign particle avoidance

**IV, IVa, IVb. After Hot Pressing, After Mechanical Working**

Chemical composition (average, local)  
Soundness (cracks, inclusions, voids)  
Morphology (size, shape, distribution)  
Macrostructure (etched slice)  
Density  
Inclusions and precipitates (fractography)  
Texture  
Mechanical properties  
Physical properties (resistivity, conductivity, elastic constants)

**5,8. Mechanical Work**

Time  
Temperature  
Percent reduction  
Working directions and sequence  
Intermediate stress relief or anneal  
Atmosphere  
Container materials  
Lubrication  
Protection from contamination  
Die design  
Restraint or methods of hydrodynamic compression

**6,7,9. Final Use**

Failure analysis of overstressed part  
Fractography  
Metallography (grain size and shape, inclusions, microstructural constituents)  
Specific inclusions (size, shape, distribution, and composition)  
Radiography  
Ultrasonic examination

should be carefully documented and the material should have been known to possess adequate forgeability. For each of the two billets, two working processes would be utilized which are designed to give different degrees and types of texturing. The two working processes would be established to give extremes in texturing. For each of the two working processes, for each of the two billets, the following mechanical tests would be run and data gathered for the jet engine designer: tensile test results, low cycle fatigue, high frequency fatigue, impact, strain rate sensitivity, creep strength. The preceding properties should be obtained in both smooth and notched test bars. Fractography would be employed to establish the precipitates that are formed as a result of extremes of heat-treatment. The test forgings should be sufficiently large in size that post-forging heat treatments can be tried on a second series of test bars.

In contrast, a sheet rolling study might utilize a single starting material, particularly if funds are quite limited. Similarly, a single casting, comminution, and pressing practice might be adopted (with all pertinent measurements of these variables recorded and reported). The variables might principally be those of mechanical work, where the factors of temperature, reduction per pass, cross-rolling, annealing, etc. would be studied. After trials involving some of the variables shown in the Table as 5,8, a selection of the measurements (composition, soundness, etc.) shown as IV, IVa, IVb would be made and reported. If a good selection of the processing variables and of the structure and properties has been made, a step forward in the characterizing of beryllium will have been accomplished.

The use of standardized test procedures is highly recommended. Attention is called to the report of the Subcommittee on Test Methods of the Committee on Beryllium Metallurgy (MAB-205-M, "Evaluation Test Methods for Beryllium"). Only through the use of consistent methods can statistical data be generated from which correlations of processes, structures, and properties be obtained.

Even a cursory review of the numerous variables involved in the preparation of mill forms and the conversion of such forms to hardware



suggests the advisability of conducting research with metal especially prepared. Commercially available metal would inherently involve variability which might obscure the desired results from the experiments. In all probability, complete and accurate processing records are not made, nor would commercial policy permit them to be provided when buying a commercial product. For special research programs, it should be possible to specifically indicate the input material and the processing steps which are required to convert the raw material into a polycrystalline form suitable for subsequent fabrication and testing.

Existing knowledge does not permit one to list those processing variables which have the greatest influence on structure and those structural variations which have the greatest influence on mechanical properties. The items listed in this attempt to characterize probably include most such items. Only through research programs in which this kind of data is obtained will it be possible to establish a much smaller list of the truly significant variables. More uniform material with greater reproducibility could be the outcome. This could lead to the development of material.

## DOCUMENT CONTROL DATA - R&amp;D

*(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)*

1. ORIGINATING ACTIVITY (Corporate author) National Academy of Sciences-National Research Council -- Materials Advisory Board Washington, D. C.		2a. REPORT SECURITY CLASSIFICATION <b>Unclassified</b>	
		2b. GROUP	
3. REPORT TITLE <b>CHARACTERIZATION OF BERYLLIUM</b>			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates)			
5. AUTHOR(S) (Last name, first name, initial) Materials Advisory Board Subcommittee on Characterization of Beryllium			
6. REPORT DATE August 1966		7a. TOTAL NO. OF PAGES 14	7b. NO. OF REFS --
8a. CONTRACT OR GRANT NO. DA-49-083 OSA 313		8a. ORIGINATOR'S REPORT NUMBER(S) MAB-226-M	
b. PROJECT NO.		8b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
c.			
d.			
10. AVAILABILITY/LIMITATION NOTICES Qualified requesters may obtain copies from DDC. Releasable to CFSTI.			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY Assistant Director, (Materials) ODDR&E, Pentagon, Washington, D. C.	
13. ABSTRACT <p>Research and development projects involving beryllium have not always controlled or recorded all the significant variables. Applications have languished because of lack of reproducibility or the difficulty of relating unexpected behavior to prior processing. What has been lacking is an adequate characterizing of the metal. While this attempt at characterizing has fallen short of a complete scientific description, we have reached the stage where major correlations between processing, structure, and properties can be obtained if the data indicated in the report is collected.</p> <p>This <del>brief</del> report has compiled the major process variables corresponding to the principal operations gone through in producing a beryllium mill product, and then a part. This compilation comprises a check list which should be reviewed at the start of a research or development effort to ensure that variables which might be significant are not being overlooked. The ultimate object of compiling and studying such data is to assure uniformity, and thus introduce reliability into manufactured parts.</p>			

14 KEY WORDS  Characterization Beryllium Processing Structure Properties	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT

**INSTRUCTIONS**

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.
- 2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.
- 2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.
3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.
4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.
5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.
6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.
- 7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.
- 7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.
- 8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.
- 8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.
- 9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.
- 9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).
10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through \_\_\_\_\_."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through \_\_\_\_\_."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through \_\_\_\_\_."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.
12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.
13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, roles, and weights is optional.