

This document is a machine translation of Russian text which has been proc~ssed by the AN/GSQ-16(XW-2) Machine Translator, owned and operated by the United States Air Force. The machine output has been postedited to correct for major ambiguities of meaning, words missing from the machine's dictionary, and words out of the context of meaning. The sentence word order has been partially rearranged for readability. The content of this translation does not indicate editorial accuracy, nor does it indicate USAF approval or disapproval of the material translated.

177 N' TE SECTION FAF SECHON [T ... IT AVAILABILITY DEDE A-AIL SOFIE SPEEK ~

FTD-MT-24-262-67

EDITED MACHINE TRANSLATION

CORROSION OF CHROMIUM-NICKEL STAINLESS STEEL IN LITHIUM

By: N. M. Beskorovaynyy, V. K. Ivanov, and V. V. Petrashko

English pages: 7

SOURCE: Moscow. Inzhenerno-Fizicheskiy Institut. Metallurgiya i Metallovedeniye Chistykh Metallov. (Moscow. Institute of Engineering Physics. Process Metallurgy and Physical Metallurgy of Pure Metals). No. 5, 1966, pp. 163-172.

: 2

UR/2755-66-000-005

THIS TRANSLATION IS A RENDITION OF THE ORIGI-HAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT HECESSARILY REFLECT THE POSITION OR OPHNON OF THE POSISION TECHNOLOGY DI-VISION.

, 1

TT7501317

Dete13 Sept. 19 67

PREPARED BY:

TRANSLATION DIVISION FOREIGN TECHNOLOGY DIVISION WP-AFB, ONIO.

ITIS INDEX CONTROL FORM

Ol Acc Nr 68 Translation Nr TT7501317 FTD-MT-24-262-6					7	65 X Ref Acc Nr 76 Reel/Frame AT6023742 1881 0667			81 0667			
97	Header	Clas	63 CI	.4.5	64	Control M	arkings			94 B	xpansion	40 Ctry Info
U	ICL	+	UNCL	, 0	<u> </u>	0						UR
02	Ctry	103 R	ef FF	04	Yr 66	05 Vol	06		07 B. P	9. 45	E. Pg.	10 Date
	Tranclis	21	22	<u> </u>	00	000			0163		0172	NONE
ĸ	DRROZTYA	NER	CHAVE	viish	CHEY	KHROMONT	KET.EVOV	STALT	V T.T.TTT			
	9 Englis	h Tit	le CHROM	IUM-	NTCK	EL STAINI	ESS STE	EL TN 1				
4	3 Source	MOS	COW.	INZ	HENE	RNO-FIZIC	HESKIY	INSTITU	JT. MET	ALLUF	RGIYA I	
MI	ETALLOVE	DENI	YE CH	ISTY	<u>кн м</u>	ETALLOV	(RUS;	<u>JIAN)</u>				
4	2 Author						98 Docu	ment Lo	cation		_	
BI	ESKOROVA	YNYY	, N. 1	м							-	فسالة البزيان والكاري والكالب ومستنبيين
10	6 Co-Aut	hor					47 Subj	ect Cod	es			
I\	ANOV, V	<u>к.</u>						1	L		ويسترون ويسترك فيتك	
	6 Co-Aut	hor	77				39 Topi	c Tags:	stainl	ess s	teel, s	steel
- F1	Co Ant	/, V.	V .				chromi	um stee	el. nick	, cor el co	rosion ntainir	resistance,
T	o co-Aut	nor					lithiu	n				
NC	DNE	hor					1					
NC	DNE	nor					[
c m t o c	orrosion ens were anks mae f series nd the	n béh e tes de of s 3 s	navior sted i f 1Kh1	in .n 1: .8N9:	litr Lthiu C ste	nium at 70 um contain eel (serio	DOC for ning a s es 1) or	10 or mall a Armco	200 hr. mount of -iron (s	Ser C ¹⁴ Serie	ies 1 a isotop s 2).	nd 2 speci- e and in
ಕ ಶ g	ame pat radual	tanks tern disso	specim s were under olutic	ens; mac all on of	, the le of L the C chi	e lithium Armco-i. e conditie comium an	contain ron. Th ons test d nickel	ed 0.1 e corr ed, an from	% carbor osion wa d was ch the surf	n in as fo narac Cace	additio und to terized layer o	n the case n to C ¹⁴ follow the by a f the speci-

FTD FEB 67 0---90

and a support of the second support and and

ř |

U. S. BOARD ON GEOGRAPHIC NAMES TRANSLITERATION SYSTEM

Block	Italic	Transliteration	Block	Italic	Transliteration
A 1	A a	A. a.	Pp	Pp	R. r
5 6	5 6	R h	с. с.		с. а
		10 U			د و د س ب
DB	<i>b</i> •	V, V	1 1	1 m	Ty U
Гг	Γ 🕴	G, g	УУ	Уу	U, u
Дд	ДЭ	D, d	Φφ	Φφ	F.f
E é	Ë 4	Ye, ye; E, e [*]	XX	XX	Kh, kh
Жж	Ж ж	Zh, zh	Цц	Цц	Ts, ts
3 3	3 1	Z, z	મુષ	Ч ч	Ch, ch
КК	Ни	I, i .	Шш	Ш ш	Sh, sh
R R	Я 4	Y, y	Щщ	Щщ	Shch. shch
КК	K x	K, k	Ъъ	Ъъ	11
Лл	Л A	L, 1	Ыы	Ыы	Y, y
Мж	Мм	M, m	Бъ	Бъ	1
Ни	Нн	N, n	э >	Э ° э	E, e
0 0	0 0	0, 0	00 X	Юю	Yu. yu
Πn	17 N	P, p	ЯЯ	Я я	Ya, ya

* ye initially, after vowels, and after ъ, ь; e elsewhere. When written as ë in Russian, transliterate as yë or ë. The use of diacritical marks is preferred, but such marks may be omitted when expediency dictates.

FTD-MI-24-262-67

.

いたいことの

Ļ

1

•

いたの大学であ

CORROSION OF CHROMIUM-NICKEL STAINLESS STEEL IN LITHIUM

N. M. Beskorovaynyy, V. K. Ivanov, and V. V. Petrashko

Possibility of application of austenitic chromium-nickel steels as structural material for work in contact with liquid lithium is limited, since these steels possess unsatisfactory corresion resistance [1]. In connection with this it is expedient to study the cause of low corrosion resistance of chromium-nickel steels in lithium.

In this work there are brought out results of tests in lithium of [1Kh18N9T](1X18H9T) steel in reaction beakers from this steel and from Armco iron. Into lithium there was introduced radioactive isotope C^{14} , quantity of which did not essentially change the overall content of carbon in lithium; in a number of experiments there was used lithium with considerable additions of carbon (Table 1).

Table 1. Conditions of Testing of 1Kh18N9T Steel in

Variant of experiment	Material of reaction beakers	Additions to lithium
1 11 111	1Kh18K9T Armeo Iron 9 9	Radioactive isotope C ¹⁴ The same Radioactive isotope C ¹⁴ and U.1% C (gravite)

ちい

ł

A STREET

27.201

Corrosion tests were conducted in static conditions at temperature $700^{\circ}C$ for 10 and 200 h. Then samples were investigated by method of laminar analysis. Concentration of chromium was determined by method flame photometry [2], and concentration of nickel - by means of spectral analysis.

On Fig. 1 there are presented distribution curves of chromium and nickel in 1Kh18N9T steel after testing in lithium, which indicates lowering of chromium and nickel content in surface layer. In contrast to distribution curves of chromium, distribution curves of nickel have complicated character with maximum and minimum, position of which is changed depending upon time and testing conditions.

The least change of composition occurs when the sample and reaction beaker are from one material, since lithium is saturated with chromium and nickel simultaneously from the sample and beaker (Table 2).



1.11

Fig. 1. Distribution of chromium and nickel in 1Kh18N9T steel after testing in lithium at 700° C for 10 h (a) and 200 h (b) with respect to first (1) second (2) and third (3) variants.

Table	2.	Change of	Content	of	Chromium	and	Nickel	on	
CINNPOR	<u>, , , , , , , , , , , , , , , , , , , </u>	e 11/261 SMOM	94001						

	Content of Cr,	≸ by weight	Content of Ni, % by weight		
Variant of experiment	in 10 h	in 200 h	in 10 h	in 200 h	
1 11 111	0,9 0,85 0,3	. 0,9 0,5 0,5	0.8 0.7 0.6	0,7 0,55 0,5	

More significant changes in 1Kh18N9T steel occur after testing in reaction beakers from Armco iron (II and III variants). Chromium and nickel will form solid solutions with iron, therefore in the process of testing atoms of chromium and nickel, dissolved in lithium, can be transferred to iron, and their concentration in lithium will be reduced. This circumstance leads to acceleration of processes of dissolution of chromium and nickel from surface layer of samples (see Fig. 1), which is also indicated by change of increase of weight of samples positive in I variant of testing and negative in II and III variants (Fig. 2). Analogous results were observed during tests of chromium stainless steels [3].

Thus, testing conditions of 1Kh18N9T steel in II and III variants of experiment with the same character of corrosion process are more rigid as compared to I variant and due to mass transfer from sample to reaction beaker to a certain degree there are simulated actual work conditions of structural materials in liquid-metal heat-transfer agents, when because of temperature gradient there occurs mass transfer from hot zone to cold.

Results of tests indicate the significant effect of carbon on lowering of content of chromium and nickel in surface layer of 1Kh18N9T steel. With higher content of carbon in lithium the corrosion processes go more intensively.



Fig. 2. Change of weight of 1Kh18N9T steel after testing at 700° C in argon 1 - and in lithium according to first 2 - second 3and third 4 - variants. In II variant the carbon content in lithium composed approximately 0.1%, since carbon entered lithium from iron reaction beakers. In III variant lithium contained about 0.2% carbon, since 0.1% carbon was additionally introduced into it in the form of graphite.

Application of radioactive isotope C¹⁴ makes it possible to investigate the behavior of carbon during corrosion of chromium-nickel steel in lithium. After 10 h testing according to I variant (samples and beakers of 1Kh18N9T steel) the surface layer has high radioactivity (Fig. 3a and Table 3) with simultaneous significant increase of microhardness (Fig. 4a) and minimum change of composition of surface layer with respect to chromium and nickel. From this it follows that with small decrease of content of chromium the carbon is transferred from lithium to surface of sample, since chromium has higher chemical affinity to carbon than lithium, and microhardness of this layer is increased probably as a result of carbide formation (Fig. 5).



Fig. 3. Distribution of radiocarbon in 1Kh18N9T steel after testing in lithium, containing isotope C^{14} , at temperature 700°C for 10 h a) and 200 h b) according to first 1 second 2 - and third 3 - variants.



Table 3. Radioactivity of Surface of 1Kh18N9T Steel at Different Variants of Testing, Referred to Radioactivity of Surface of Sample Tested According 1 J Variant for 10 h

Diretion	\\	Variant of experiment						
of trating, h	I	11	111					
10 200	1,0 0,16	0,08 0,01	0,05 0,02					

3



Fig. 4. Distribution of microhardness in 1Kh18N9T steel after testing in lithium at 700° C for 10 h (a) and 200 h (b) according to first (1) second (2) and third (3) variants.

GRAPHIC NOT REPRODUCIBLE



5. Surface of Fig. 1Kh18N9T steel after testing in lithium at 700°C for 10 h accord-

ing to I variant (×1350).

With increase of duration of testing to 200 h both radioactivity and microhardness of surface are noticeably reduced (Fig. 3b and Table 3, Fig. 4b), which by analogy with chromium steels should indicate both some lowering of chromium content and decrease of quantity of Lowering of chromium content and decrease of quantity of carbide phase on surface [3]. Redistribution of carbon occurs simultaneously. Maximum radioactivity still is preserved on surface, but then there follows the zone where radiocarbon is absent. This zone is disposed at the same depth as maximum on distribution curve of nickel. Further, at a depth about 0.06 mm there is again marked maximum on distribution curve of carbon (Fig. 3b) and maximum on microhardness curve corresponds to it (Fig. 4b). At this depth the concentration of chromium is At this depth the concentration of chromium is approximately equal to initial, and on distribution curve of nickel there is minimum.

「たい」の「ない」の「いう」」

With contamination of lithium by carbon (II and III variants) lowering of content of chromium and nickel in surface layer of 1Kh18N9T steel goes more intensively, but form of distribution curves of chromium and nickel

(x1350). (see Fig. 1) is kept. However, distribution of carbon is changed significantly. On the surface the carbon content is reduced to small concentrations (see Table 3). In the zone where maximum is located on distribution curve of nickel, carbon is absent after 10 h and 200 h of testing. In the zone of minimum, conversely, concentration of carbon increases with increase of carbon content in lithium, especially with increase of duration of testing to 200 h. Redistribution of carbon is accompanied by change of microhardness. On the surface the microhardness is significiantly reduced, but increases in zone where there is noted maximum of concentration of carbon.

These date indicate that carbon, just as during test of chromium steels, shifts to deeper zones in proportion to how content of chromium is reduced on surface. Such shift is caused by higher chemical affinity of carbon to chromium as compared to nickel, iron, and lithium.

Change of composition of austentic chromium-nickel steel as a result of surface processes, developing at contact with lithium, is accompanied by change of structure. Layers of sample adjacent to surface do not contain carbides and have raised etchability (Fig. 6). If the structure of austenitic steel is usually revealed when etching in reagent 50% HC1 + 50% H₂O₂, then after testing in lithium the structure of subsurface layers is etched instantly in 5% solution HNO_3 in alchol, i.e., in this zone austenitic chromium-nickel steel loses its acid-resisting properties. In layers with raise pores, located basically along grain boundaries. In layers with raised etchability there are observed

With intense change of composition and structure of surface layers (II and III variants) the plasticity of 1Kh18N9T steel is noticeably reduced (Table 4).



Fig. 6. Microstructure of 1Kh18N9T steel after testing in lithium at 700° C for 200 h according to II variant at a depth of 0.06 mm. Etching agent - 5% solution HNO₃ in alchol (×1350). From given data it follows that the most significant process, which causes corrosional destruction of chromium-nickel steels at contact with lithium, is lowering of content of chromium and nickel in surface layer, accompanied by change of structure and appearance of microporosity.

When testing 1Kh18N9T steel in beakers from the same material (I variant) these processes are developed weakly. As a result the composition and structure of surface zone are changed little and, consequently, strength and plasticity of steel are preserved at the level of mechanical characteristics after testing in argon with these same temperature conditions.

After testing 1Kh18N9T steel in beakers from Armco iron and with additional introduction of carbon to lithium (II and III variants) the surface zone is significantly depleted by chromium and nickel, and depending upon degree of depletion the structure is changed and plastic properties of 1Kh18N9T steel are lost.

Lowering of plastic properties during test according to II and III variants is also possible due to carbides, which can be formed during diffusion of carbon from lithium into steel.

Table	4. C	hange o)f	Mechanical	Properties	oſ	1Kh18N9T
Steel	after	Testir	າຕ	in Lithium			

. Testing conditions	B. kg/ar.		8. %	
	10 h	200 h	in h	200 h
In atmosphere of argon Varient. I s II s III s III s III s III s	67,4 67,1 69,8 69,7	67,8 66,6 69,4 67,6	46.2 46.0 44.8 43.3	JR.2 47.1 26.4 21.4

However, main cause of impairment of mechanical characteristics of chromium-nickel steel should be considered those changes of structure, which are due to lowering of content of chromium and nickel in surface layer. Impurities of carbon in lithium only strengthen this process. This is indicated by the following experiment.

Samples of 1Kh18N9T steel were tested in reaction beakers from Armco iron, preliminarily decarbonized in lithium. In this case lowering of content of chromium and nickel occurs more intensively than in I variant, as a result of transfer of atoms of chromium and nickel to iron beaker, and at the same time the effect of carbon on processes of corrosion is excluded to a maximum degree. After 10 h of testing 1Kh18N9T steel had the following mechanical properties: $\sigma_{\rm B} = 67.3$ kg/mm², $\delta = 47.7\%$, i.e., plasticity was approximately the same value as during test according to I variant. After 200 h of testing the strength of steel composed $\sigma_{\rm B} = 68.1$ kg/mm², and plasticity - 31.8%. Thus, after 200 h of testing in preliminarily decarbonized iron beaker the plasticity of 1Kh18N9T steel has intermediate value between plasticity during test according to I variant and plasticity during test according to I variant and

It is possible to try to explain data obtained during test of chromium-nickel 1Kh18N9T steel in lithium on the basis of concepts on vacancy mechanism of diffusion in alloys based on iron [4], leading to development of pore formation and a number of processes accompanying it.

Dissolution in lithium of atoms of chromium and nickel, and also to some degree atoms of iron, should lead to formation of vacancies on surface of samples of 1Kh18N9T steel. Formed vacancies partially withdraw outside the sample, and partially diffuse deep. In subsurface layers there is possible supersaturation by vacancies above the equilibrium value determined by composition of alloy and temperature. In process of pore formation the alloy passes into more equilibrium state [5].

Presence in sample of a porous region, confirmed by raised etchability and microstructure, can significantly change the distribution of components of alloy with respect to depth of sample.

In porous region there is facilitated diffusion segregation of components of alloy: for example, in subsurface zone of 1Kh18N9T steel, tested in lithium, there is observed raised concentration of nickel, determined by maxima on distribution curves of nickel (see Fig. 1).

Inasmuch as nickel in contrast to chromium is a graphite forming element, then carbon is absent in zones enriched by atoms of nickel. It diffuses into deeper layers, from which nickel departed (minima on distribution curves of nickel). In these layers there is possible some supersaturation of steel by vacancies due to departed atoms of nickel, and in connection with this there are created favorable conditions for formation of chromium carbides. This is indicated by maxima on distribution curves of radiocarbon, and also on curves of microhardness (see Fig. 4). With increase of duration of testing to 200 h the redistribution of components of 1Kh18N9T steel is more considerable.

Intensification of corrosion processes with the presence of carbon in lithium is possible for the following reasons. There is known the inclination of chromium-nickel steels to intercrystallite corrosion after heating in temperature

range 500-800^oC. With such heating from γ -solid solution there are separated excess carbides, which are distributed along grain boundaries (Fig. 7). Diffusion mobility of chromium is several orders lower than carbon; therefore, for formation of carbides chromium enters basically from volumes adjacent to grain boundaries. As a result of this boundary zones are significantly depleted by chromium, and at intense carbide formation the appearance of vacancies in these zones is inevitable.



Fig. 7. Microstructure of 1Kh18N9T steel after aging in argon at 700°C for 200 h. Slide is not etched (×1350). Analgous process occurs at contact of chromiumnickel steel with lithium, containing carbon impurities. Carbon, possessing higher chemical affinity to chromium than to lithium, diffuses from lithium into steel, which is indicated by appearance of radioactive isotope C^{14} in surface layers of samples. With entrance of carbon from lithium in surface layers of steel the process of carbide formation is structured.

carbide formation is strengthened, and zones of γ -solid solution, depleted by chromium, are saturated by vacancies (in addition to those vacancies which will be formed with solution zones of chromium-nickel steel).

Thus, with the presence of carbon in lithium there is intensified pore formation in surface zones of chromium-nickel steel, which, on the one hand, should considerably facilitate diffusion of chromium and nickel at the surface and their dissolution in lithium, and on the other - should cause more intense reduction of plastic properties. Finally carbon, proceeding from lithium into chromium-nickel steel, will affect the speed of corrosion process of steel. Furthermore, it is not excluded that atoms of chromium dissolved in lithium can participate in the formation of carbides directly in unities of carbon in lithium should cause additional

lithium. In this case impurities of carbon in lithium should cause additional depletion of surface of sample by chromium with all the consequences emanating from this.

Conclusions

1. Corrosional destruction of austenitic chromium-nickel steel at contact with lithium at 700° C is connected with decrease of content of chromium and nickel in surface layer, as a result of which in this layer there appears porosity, lowering the plastic properties of steel.

2. Impurities of carbon in lithium significantly affect the degree of corrosion of 1Kh18N9T steel in lithium, causing more intense lowering of concentration of chromium and nickel in surface layers.

3. Testing of chromium-nickel steel in reaction beakers from other material intensifies the processes proceeding with corrosion of steel in lithium.

Literature

1. Beskorovaynyy N. M. and others. "<u>Metallurgiya i metallovedeniye chistykh</u>". (Metallurgy and metallography of pure metals). Vyp. IV. M., Gosatomizdat, 1963, str. 122.

2. Beskorovaynyy N. M. and others. In the collection: "<u>Metallurgiya i</u> metallovedeniye chistykh metallov". (Metallurgy and metallography of pure metal). Vyp. III. M., Gosatomizdat, 1961, str. 233.

3. Nevzorov B. A. and others. <u>Issledovaniye korrozionnoy stoykosti</u> <u>konstruktsionnykh materialov v shchelochnykh metallakh.</u> (Investigation of corrosion resistance of structural materials in alkali metals). Report No. 343 (USSR), presented at the 3rd International Conference on World Usage of Atomic Energy. Geneva, 1964.

4. Krishtal M. A. Diffuzionnyye protsessy v zheleznykh splavakh. (Diffusion processes in iron alloys). M., Metallurgizdat, 1963.

5. Geguzin Ya. Ye. <u>Makroskopicheskiye</u> defekty v metallakh. (Macroscopic defects in metals). M., Metallurgizdat, 1962.