

AD 680809

Department of Applied Mechanics  
STANFORD UNIVERSITY

dt

Technical Report No. 194  
Contract Report No. 16

ELASTIC-PLASTIC BOUNDARIES IN PLANE AND CYLINDRICAL  
WAVE PROPAGATION OF COMBINED STRESSES

By  
T.C.T. Ting

DDC  
RECEIVED  
JAN 23 1969  
RECEIVED  
B

Reproduced by the  
CLEARINGHOUSE  
for Federal Scientific & Technical  
Information Springfield Va. 22151

December 1968

Contract No. DA-04-200-AMC-659(X)  
Sponsored through Ballistic Research Laboratories  
Aberdeen Proving Ground, Maryland

This document has been approved  
for public release and sale; its  
distribution is unlimited

Department of Applied Mechanics

STANFORD UNIVERSITY

Technical Report No. 194

Contract Report No. 16

ELASTIC-PLASTIC BOUNDARIES IN PLANE AND CYLINDRICAL  
WAVE PROPAGATION OF COMBINED STRESSES

By

T.C.T. Ting

December 1968

Contract No. DA-04-200-AMC-659(X)  
Sponsored through Ballistic Research Laboratories  
Aberdeen Proving Ground, Maryland

ELASTIC-PLASTIC BOUNDARIES IN PLANE AND CYLINDRICAL  
WAVE PROPAGATION OF COMBINED STRESSES

By

T.C.T. Ting\*

ABSTRACT

A general study is given of plane and cylindrical wave propagation of combined stresses in an elastic-plastic medium. The coefficients of the governing differential equations, when written in matrix notation, are symmetric matrices and can be divided into sub-matrices each of which has a special form. The relations between the stresses on both sides of an elastic-plastic boundary are derived. Also presented are the restrictions on the speed of an elastic-plastic boundary.

---

\* Associate Professor of Applied Mechanics, Dept. of Materials Engineering, University of Illinois at Chicago Circle, Chicago, Illinois 60680.

1. Introduction.

The equations of motion for a continuum body are

$$\frac{\partial \sigma_{ij}}{\partial x_j} = \rho \frac{\partial v_i}{\partial t}, \quad (i, j=1, 2, 3) \quad (1)$$

where  $\sigma_{ij}$  is the stress,  $v_i$  the velocity and  $\rho$  is the mass density of the body, and summation is implied by repeated indices. The relation between the strain  $\epsilon_{ij}$  and the velocity  $v_i$  is

$$\frac{\partial \epsilon_{ij}}{\partial t} = \frac{1}{2} \left( \frac{\partial v_i}{\partial x_j} + \frac{\partial v_j}{\partial x_i} \right) \quad (2)$$

while the stress-strain relation for an elastic, isotropic work-hardening material is (see [1])

$$\frac{\partial \epsilon_{ij}}{\partial t} = \frac{1+\nu}{E} \frac{\partial \sigma_{ij}}{\partial t} - \frac{\nu}{E} \delta_{ij} \frac{\partial \sigma_{kk}}{\partial t} + G(k) \frac{\partial f}{\partial \sigma_{ij}} \frac{\partial f}{\partial \sigma_{kl}} \frac{\partial \sigma_{kl}}{\partial t} \quad (3)$$

$E$  is Young's modulus,  $\nu$  is Poisson's ratio.  $k$  is the yield stress and the yield condition can be written as

$$f(\sigma_{ij}) = k^2 \quad (4)$$

$G(k)$  in Eq. (3) is a given function of  $k$  which characterizes the work-hardening property. Equations (1) ~ (4) give a complete description of wave propagation in three-dimensional elastic-plastic media.

In this paper, we will restrict our attention to special cases in which the governing equations depend on only one space variable.

Plane wave propagation and cylindrical wave propagation are such special cases. The most general plane wave propagation is the one in which  $v_1$ ,  $v_2$ , and  $v_3$  are functions of  $x_1$  and  $t$  only. Using  $x$  instead of  $x_1$  for simplicity,  $\sigma_1$ ,  $\tau_2$ ,  $\tau_3$  for  $\sigma_{11}$ ,  $\sigma_{21}$ ,  $\sigma_{31}$  respectively, Eq. (1) gives

$$\sigma_{1,x} = \rho v_{1,t} \quad (5)$$

$$\tau_{2,x} = \rho v_{2,t} \quad (6)$$

$$\tau_{3,x} = \rho v_{3,t} \quad (7)$$

where the subscripts  $x$  and  $t$  denote partial differentiation with respect to these variables. If we use von Mises yield condition:

$$f = \frac{1}{2} s_{ij} s_{ij} = k^2$$

where

$$s_{ij} = \sigma_{ij} - \frac{1}{3} \delta_{ij} \sigma_{kk}$$

Eq. (3) gives, making use of Eq. (2) and the fact that  $\epsilon_{22} = \epsilon_{33} = 0$  leads to  $\sigma_{22} = \sigma_{33}$  in the present case,

$$v_{1,x} = \frac{1}{E} \sigma_{1,t} - \frac{2\nu}{E} \sigma_{2,t} + s_1 GQ \quad (8)$$

$$0 = -\frac{2\nu}{E} \sigma_{1,t} + \frac{2(1-\nu)}{E} \sigma_{2,t} + 2s_2 GQ \quad (9)$$

$$v_{2,x} = \frac{1}{\mu} \tau_{2,t} + 2\tau_2 GQ \quad (10)$$

$$v_{3,x} = \frac{1}{\mu} \tau_{3,t} + 2\tau_3 GQ \quad (11)$$

where  $s_1$ ,  $s_2$  and  $\sigma_2$  stand for  $s_{11}$ ,  $s_{22}$ , and  $\sigma_{22}$  respectively.  $\mu$  is the shear modulus and

$$Q = s_1 \sigma_{1,t} + 2s_2 \sigma_{2,t} + 2\tau_2 \tau_{2,t} + 2\tau_3 \tau_{3,t} \quad (12)$$

Equations (5 ~ 11) give a complete description of a general plane wave propagation in an elastic-plastic medium.

When  $v_2 \equiv 0$ , and hence  $\tau_2 \equiv 0$ , Eqs. (5), (7), (8), (9), and (11) reduce to the case of pressure-shear wave propagation considered in [2,3,4]. If  $v_2$ ,  $v_3$  are the only non-zero velocity components, then  $\tau_2$  and  $\tau_3$  are the only non-zero stresses and Eqs. (6), (7), (10) and (11) reduce to the case of two-shear waves studied in [3,5,6]. The equations derived in [7] for combined longitudinal and torsional waves in a thin-walled tube can also be reduced from Eqs. (5), (6), (8) and (10) by letting  $\sigma_2 \equiv 0$ .

If  $v_r$ ,  $v_\theta$ ,  $v_z$  are the velocity components of a particle in cylindrical coordinates  $(r, \theta, z)$ , the most general cylindrical wave propagation is the one in which  $v_r$ ,  $v_\theta$  and  $v_z$  are functions of  $r$  and  $t$  only. Then, the only non-zero strains are  $\epsilon_r$ ,  $\epsilon_\theta$ ,  $\gamma_\theta$ ,  $\gamma_z$  where  $\gamma_\theta$ ,  $\gamma_z$  stand for  $\epsilon_{r\theta}$ ,  $\epsilon_{rz}$  respectively. Consequently  $\sigma_r$ ,  $\sigma_\theta$ ,  $\sigma_z$ ,  $\tau_\theta$ ,  $\tau_z$  are the non-zero stresses where  $\tau_\theta = \sigma_{r\theta}$ ,  $\tau_z = \sigma_{rz}$ . Now, instead of writing the governing equations for cylindrical wave propagation in the form shown in Eqs. (5 ~ 11), we will use matrix

notation and write the governing equations, Eqs. (1~3) in a matrix differential equation which can be applied to both plane and cylindrical wave propagation.

## 2. The Matrix Differential Equation.

For wave propagation which involves only one space variable  $x$  or  $r$ , the equations of motion (1) can be written in matrix notation as

$$\underline{M} \underline{\sigma}_x + \underline{b}_1 = \rho \underline{v}_t \quad (13)$$

where  $\underline{g}$  and  $\underline{v}$  are column vectors whose elements are stress and velocity components respectively.  $\underline{b}_1$  is also a column vector whose elements are functions of stress  $\underline{g}$  and space variable  $x$  only. (In cylindrical waves,  $x$  becomes  $r$ ). If  $\underline{g}$  has  $m$  elements and  $\underline{v}$  has  $n$  elements, then  $\underline{M}$  is an  $n \times m$  matrix whose elements are constants. The continuity condition Eq. (2) can be written as

$$\underline{\epsilon}_t = \underline{N} \underline{v}_x + \underline{b}_2 \quad (14)$$

where  $\underline{\epsilon}$  is a column vector with strains as its elements while  $\underline{b}_2$  is a column vector whose elements are functions of velocity  $\underline{v}$  and space variable  $x$  only.  $\underline{N}$  is an  $m \times n$  matrix whose elements are constants. Finally, the stress-strain relation, Eq. (3) can be written as

$$\underline{\epsilon}_t = \underline{S} \underline{\sigma}_t \quad (15)$$

where  $\underline{S}$  is an  $m \times m$  square matrix. In the plastic region,  $\underline{S}$  can be written more precisely as

$$\underline{\underline{S}}^p = \underline{\underline{S}}^e + G(k)(\underline{\underline{\nabla}}f)(\underline{\underline{\nabla}}f)^T \quad (16)$$

$\underline{\underline{S}}^e$  is also an  $m \times m$  square matrix whose elements are functions of elastic constants only. Thus

$$\underline{\underline{\epsilon}}_t = \underline{\underline{S}}^e \underline{\underline{\sigma}}_t \quad (17)$$

gives the elastic stress-strain relation.  $\underline{\underline{\nabla}}f$  is the gradient of  $f(\underline{\underline{g}})$  with respect to the components of  $\underline{\underline{g}}$ . Hence, by (4)

$$(\underline{\underline{\nabla}}f)^T \underline{\underline{\sigma}}_t = 2kk_t \quad (18)$$

Now, by eliminating  $\underline{\underline{\epsilon}}_t$  between Eqs. (14) and (15), we can write Eqs. (13)~(15) in one matrix equation:

$$\underline{\underline{A}} \underline{\underline{w}}_t + \underline{\underline{B}} \underline{\underline{w}}_x = \underline{\underline{b}} \quad (19)$$

where

$$\underline{\underline{A}} = \begin{bmatrix} \rho \underline{\underline{I}} & \underline{\underline{Q}} \\ \underline{\underline{Q}} & \underline{\underline{S}} \end{bmatrix}, \quad \underline{\underline{w}} = \begin{bmatrix} \underline{\underline{v}} \\ \underline{\underline{\sigma}} \end{bmatrix} \quad (20)$$

$$\underline{\underline{B}} = \begin{bmatrix} \underline{\underline{Q}} & -\underline{\underline{M}} \\ -\underline{\underline{N}} & \underline{\underline{Q}} \end{bmatrix}, \quad \underline{\underline{b}} = \begin{bmatrix} \underline{\underline{b}}_1 \\ \underline{\underline{b}}_2 \end{bmatrix}$$

and  $\underline{\underline{I}}$  is a unit square matrix. It can be checked easily that the governing equations for general plane wave propagation derived in Eqs. (5~11) as well as the equations for other plane wave propagation reduced from Eqs. (5~11) can be written in the form of Eq. (19).

Moreover,  $\underline{\underline{A}}$  and  $\underline{\underline{B}}$  are both symmetric in all cases. In particular,



$\underline{N} = \underline{M}^T$  and the elements of  $\underline{N}$  and  $\underline{M}$  are either one or zero.

The same is true for all cylindrical waves. For the most general cylindrical wave propagation, it can be shown that, using von Mises yield condition:

$$\underline{v} = \begin{bmatrix} v_r \\ v_\theta \\ v_z \end{bmatrix}, \quad \underline{b}_1 = \begin{bmatrix} (\sigma_1 - \sigma_2)/r \\ 2\tau_\theta/r \\ \tau_z/r \end{bmatrix}, \quad \underline{M} = \begin{bmatrix} 1 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 1 & 0 \\ 0 & 0 & 0 & 0 & 1 \end{bmatrix}$$

$$\underline{\sigma} = \begin{bmatrix} \sigma_r \\ \sigma_\theta \\ \sigma_z \\ \tau_\theta \\ \tau_z \end{bmatrix}, \quad \underline{b}_2 = \begin{bmatrix} 0 \\ v_r/r \\ 0 \\ -v_\theta/r \\ 0 \end{bmatrix}, \quad \underline{N} = \underline{M}^T \quad (21)$$

$$\underline{S}^e = \begin{bmatrix} 1/E & -\nu/E & -\nu/E & 0 & 0 \\ -\nu/E & 1/E & -\nu/E & 0 & 0 \\ -\nu/E & -\nu/E & 1/E & 0 & 0 \\ 0 & 0 & 0 & 1/\mu & 0 \\ 0 & 0 & 0 & 0 & 1/\mu \end{bmatrix}, \quad \underline{\sigma}^e = \begin{bmatrix} s_r \\ s_\theta \\ s_z \\ 2\tau_\theta \\ 2\tau_z \end{bmatrix}$$

Cristescu [8] has studied an axially symmetric wave propagation in which  $v_r$  and  $v_\theta$  are the only non-vanishing velocities. The governing equations can be obtained from Eq. (21) by letting  $v_z \equiv \tau_z \equiv 0$ . The particular cases of two-shear cylindrical waves and pressure-shear cylindrical waves have also been derived earlier in [5] but the resulting coefficient matrices were not symmetric. The formulation presented here yields symmetric coefficient matrices for all cylindrical waves.

The analyses in the rest of this paper will be based on the matrix differential equation (19). Although for all plane waves and cylindrical waves the matrices  $\underline{A}$  and  $\underline{B}$  are symmetric, the analyses presented in the following do not require the symmetry property of  $\underline{A}$  and  $\underline{B}$ . The yield condition  $f$  of Eq. (4) is not restricted to von Mises yield condition.

### 3. An Identity.

In this section, we will derive an identity which is useful in the analyses of the present problem.

Let  $\underline{P}$  be a  $r \times r$  matrix and  $\underline{g}$  and  $\underline{h}$  are column vectors with  $r$  components. Then, if  $a$  is a scalar,

$$\|\underline{P} + a \underline{h} \underline{g}^T\| = \|\underline{P}\| + a \underline{h}^T \underline{P}^* \underline{g} \quad (22)$$

where  $\|\underline{P}\|$  denote the determinant of  $\underline{P}$ .  $\underline{P}^*$  is the adjoint of  $\underline{P}$ , i.e., the element  $P_{ij}^*$  in  $\underline{P}^*$  is the cofactor of the element  $P_{ij}$  in  $\underline{P}$ . Hence  $\underline{P}^*$  has the property:

$$(\underline{P}^*)^T \underline{P} = \|\underline{P}\| \underline{I} \quad (23)$$

To prove Eq. (22), we write  $\underline{P}$  in terms of its columns as

$$\underline{P} = [\underline{p}_1, \underline{p}_2, \dots, \underline{p}_r] \quad (24)$$

where  $\underline{p}_1, \underline{p}_2, \dots$  are column vectors. If  $g_1, g_2, \dots, g_r$  denote the components of  $\underline{g}$ , the left hand side of Eq. (22) can be written as

$$\|\underline{P} + a \underline{h} \underline{g}^T\| = \|\underline{p}_1 + a g_1 \underline{h}, \underline{p}_2 + a g_2 \underline{h}, \dots, \underline{p}_r + a g_r \underline{h}\| \quad (25)$$

Now, by the theory of determinants, it is known that

$$\|p_1 + a h, p_2, p_3, \dots, p_r\| = \|P\| + a \|h, p_2, p_3, \dots, p_r\|, \quad (26)$$

$$\|h, a h, p_3, p_4, \dots, p_r\| = 0 \quad (27)$$

By repeatedly applying Eqs. (26) and (27) to the right hand side of Eq. (25), we obtain:

$$\begin{aligned} \|z + a h g^T\| &= \|p_1, p_2, \dots, p_r\| + a g_1 \|h, p_2, p_3, \dots, p_r\| \\ &+ a g_2 \|p_1, h, p_3, \dots, p_r\| + \dots + a g_r \|p_1, p_2, \dots, h\| \end{aligned} \quad (28)$$

With this, it is not difficult to see that Eq. (28) can be written in the form of Eq. (22). This completes the proof.

For the particular case in which  $P$  is a unit matrix, Eq. (22) reduces to

$$\|I + a h g^T\| = 1 + a h^T g \quad (29)$$

### 3. The Characteristic Equation.

The characteristics  $c$  of Eq. (19) are the roots of the equation (see [9]):

$$\|cA - B\| = 0. \quad (30)$$

Since

$$cA - B = \begin{bmatrix} pcI & M \\ N & cS \end{bmatrix} = \begin{bmatrix} pcI & Q \\ N & D \end{bmatrix} \begin{bmatrix} I & \frac{1}{pc} M \\ Q & \frac{1}{pc} I \end{bmatrix},$$

where

$$D = \rho c^2 S - N M, \quad (31)$$

we have

$$\|cA - B\| = (\rho c)^{n-m} \|D\|. \quad (32)$$

Thus, instead of expanding the determinant  $\|cA - B\|$  which is of order  $m+n$ , we can expand the determinant  $\|D\|$  which is of order  $m$ .

If we define

$$D^e = \rho c^2 S^e - N M, \quad (33)$$

then by Eqs. (16) and (31), we have

$$D^p = D^e + \rho c^2 G(k)(\nabla f)(\nabla f)^T. \quad (34)$$

Using the identity derived in the previous section, we obtain

$$\|D^p\| = \|D^e\| + \rho c^2 G(k)(\nabla f)^T (\tilde{z}^e)^* (\nabla f). \quad (35)$$

Equation (35) can be used to study the relative positions of the roots of  $\|D^p\| = 0$  and  $\|D^e\| = 0$ . (see [4]).

#### 4. The Elastic-Plastic Boundary.

If  $c$  is the speed of an elastic-plastic boundary, then

$$\frac{d\tilde{w}}{dt} = \tilde{w}_x c + \tilde{w}_t \quad (36)$$

is the total derivative of  $\tilde{w}$  along the boundary. Elimination of  $\tilde{w}_x$  between Eqs. (19) and (36) yields

$$(c_A^p - B) \dot{w}_t = c_b - B \frac{dw}{dt} \quad (37)$$

Since  $w$  is continuous across an elastic-plastic boundary, Eq. (37) gives

$$(c_A^p - B) \dot{w}_t^p = (c_A^e - B) \dot{w}_t^e \quad (38)$$

where the superscripts  $e$  and  $p$  denote the values in elastic and plastic regions respectively. With Eq. (20), Eq. (38) is equivalent to:

$$\rho c \dot{v}_t^p + M \dot{\sigma}_t^p = \rho c \dot{v}_t^e + M \dot{\sigma}_t^e \quad (39)$$

$$N \dot{v}_t^p + c \dot{\xi}^p \sigma_t^p = N \dot{v}_t^e + c \dot{\xi}^e \sigma_t^e \quad (40)$$

It is more convenient to write Eqs. (39) and (40) in the following forms, using Eqs. (16) and (18):

$$\rho c (\dot{v}_t^e - \dot{v}_t^p) + M (\dot{\sigma}_t^e - \dot{\sigma}_t^p) = 0 \quad (41)$$

$$N (\dot{v}_t^e - \dot{v}_t^p) + c \dot{\xi}^e (\sigma_t^e - \sigma_t^p) = 2cG(k)k k_t^p (\nabla f) \quad (42a)$$

or

$$N (\dot{v}_t^e - \dot{v}_t^p) + c \dot{\xi}^p (\sigma_t^e - \sigma_t^p) = 2cG(k)k k_t^e (\nabla f) \quad (42b)$$

Equations (41) and (42a) yield

$$D^e (\sigma_t^e - \sigma_t^p) = 2\rho c^2 G(k)k k_t^p (\nabla f) \quad (43a)$$

while Eqs. (41) and (42b) yield

$$D^p (\sigma_t^e - \sigma_t^p) = 2\rho c^2 G(k)k k_t^e (\nabla f) \quad (43b)$$

Equation (43a) or (43b) gives a relation between  $\underline{\sigma}_t^e$  and  $\underline{\sigma}_t^p$  on both sides of an elastic-plastic boundary. For the case of combined longitudinal and torsional stresses in a tube,

$$\underline{D}^e = \begin{bmatrix} \frac{\rho c^2}{E} - 1 & 0 \\ 0 & \frac{\rho c^2}{\mu} - 1 \end{bmatrix}$$

and Eq. (43a) reduces to the result obtained in [10].

Equation (43a) can be solved for  $(\underline{\sigma}_t^e - \underline{\sigma}_t^p)$  by pre-multiplying both sides of equation by  $(\underline{D}^e)^{*T}$  and making use of Eq. (23). Hence

$$\underline{\sigma}_t^e - \underline{\sigma}_t^p = \frac{2\rho c^2 G(k)}{\|\underline{D}^e\|} k_t^p (\underline{D}^e)^{*T} (\underline{\nabla}f). \quad (44)$$

Pre-multiplying once more both sides of Eq. (44) by  $(\underline{\nabla}f)^T$  and making use of Eq. (18), we obtain

$$k_t^e - k_t^p = \frac{\rho c^2 G(k)}{\|\underline{D}^e\|} k_t^p (\underline{\nabla}f)^T (\underline{D}^e)^{*T} (\underline{\nabla}f) \quad (45)$$

Since the right hand side of the equation is a scalar,

$$(\underline{\nabla}f)^T (\underline{D}^e)^{*T} (\underline{\nabla}f) = (\underline{\nabla}f)^T (\underline{D}^e)^* (\underline{\nabla}f),$$

and by virtue of Eq. (35) we have finally

$$\frac{k_t^e}{k_t^p} = \frac{\|\underline{D}^p\|}{\|\underline{D}^e\|} \quad (46)$$

A simplest particular case of Eq. (46) is the case of longitudinal wave propagation in a thin rod studied in [13]. In the case of combined longitudinal and torsional stresses in a thin-walled tube,

$$\|D^e\| = \left(\frac{c_2^2}{c_0^2} - 1\right)\left(\frac{c_2^2}{c_2^2} - 1\right)$$

$$\|D^p\| = \left(\frac{c_2^2}{c_f^2} - 1\right)\left(\frac{c_2^2}{c_s^2} - 1\right)$$

where  $c_0^2 = E/\rho$ ,  $c_2^2 = \mu/\rho$ , and  $c_f, c_s$  are the roots of  $\|D^p\| = 0$ , Eq. (46) reduces to the result obtained in [10].

If  $k_t^p = 0$ , then by Eq. (43a) either  $\tilde{\sigma}_t^e = \tilde{\sigma}_t^p$  or  $\|D^e\| = 0$ . Similarly, if  $k_t^e = 0$ , then by Eq. (43b) either  $\tilde{\sigma}_t^e = \tilde{\sigma}_t^p$  or  $\|D^p\| = 0$ . Consequently, if  $k_t^e = k_t^p = 0$ ,  $\tilde{\sigma}_t^e = \tilde{\sigma}_t^p$ . Moreover,  $\tilde{w}_t^e = \tilde{w}_t^p$  by Eq. (41). Thus when  $k_t^e = k_t^p = 0$ ,  $\tilde{w}_t^e = \tilde{w}_t^p$ . To obtain relations between  $\tilde{\sigma}_{tt}^e$  and  $\tilde{\sigma}_{tt}^p$  on both sides of an elastic-plastic boundary when  $k_t^e = k_t^p = 0$ , we differentiate both sides of Eqs. (43) and noticing that  $\tilde{\sigma}_t^e = \tilde{\sigma}_t^p$ ,  $k_t^e = k_t^p = 0$ ,

$$D^e(\tilde{\sigma}_{tt}^e - \tilde{\sigma}_{tt}^p) = 2\rho c^2 G(k) k k_{tt}^p (\nabla f) \quad (47a)$$

$$D^p(\tilde{\sigma}_{tt}^e - \tilde{\sigma}_{tt}^p) = 2\rho c^2 G(k) k k_{tt}^e (\nabla f) . \quad (47b)$$

Similarly, if we differentiate both sides of Eq. (45), we obtain, after using Eq. (35),

$$\frac{k_{tt}^e}{k_{tt}^p} = \frac{\|D^p\|}{\|D^e\|} . \quad (48)$$

Equations (47) and (48) are identical to Eqs. (43) and (46) respectively with the exception that the order of derivatives is changed.

From the above derivations we can generalize the results and state as in the following:

If  $\partial^n k^e / \partial t^n = \partial^n k^p / \partial t^n = 0$  for  $n=1,2,\dots,\alpha-1$  but  $\partial^\alpha k^e / \partial t^\alpha$  and  $\partial^\alpha k^p / \partial t^\alpha$  are not both zero, we have

$$\frac{\partial^n \underline{w}^e}{\partial t^n} = \frac{\partial^n \underline{w}^p}{\partial t^n}, \quad n=1,2,\dots,\alpha-1 \quad (49)$$

$$\underline{D}^e \left( \frac{\partial^\alpha \underline{g}^e}{\partial t^\alpha} - \frac{\partial^\alpha \underline{g}^p}{\partial t^\alpha} \right) = 2\rho c^2 G(k) k \frac{\partial^\alpha k^p}{\partial t^\alpha} (\nabla f) \quad (50a)$$

or

$$\underline{D}^p \left( \frac{\partial^\alpha \underline{g}^e}{\partial t^\alpha} - \frac{\partial^\alpha \underline{g}^p}{\partial t^\alpha} \right) = 2\rho c^2 G(k) k \frac{\partial^\alpha k^e}{\partial t^\alpha} (\nabla f) \quad (50b)$$

and

$$\frac{\partial^\alpha k^e / \partial t^\alpha}{\partial^\alpha k^p / \partial t^\alpha} = \frac{\|\underline{D}^p\|}{\|\underline{D}^e\|}, \quad (51)$$

For a loading wave,

$$\frac{\partial^\alpha k^e / \partial t^\alpha}{\partial^\alpha k^p / \partial t^\alpha} \begin{cases} > 0 & \text{if } \alpha \text{ is an odd integer} \\ < 0 & \text{if } \alpha \text{ is an even integer} \end{cases} \quad (52a)$$

while for an unloading wave,

$$\frac{\partial^\alpha k^e / \partial t^\alpha}{\partial^\alpha k^p / \partial t^\alpha} \begin{cases} < 0 & \text{if } \alpha \text{ is an odd integer} \\ > 0 & \text{if } \alpha \text{ is an even integer} \end{cases} \quad (52b)$$



With this, Eq. (51) furnishes a restriction on the speed of an elastic-plastic boundary as in the particular cases considered in [10,11,13]. It would be noticed that Eq. (51) applies if  $\partial^e k / \partial t^n$  ( $n=1,2,\dots,\alpha-1$ ) are zero on both sides of an elastic-plastic boundary as well as along the boundary. If  $\partial^n k / \partial t^n$  ( $n=1,2,\dots,\alpha-1$ ) are zero on both sides of the boundary only at the point concerned but not at other points on the boundary, the right hand side of Eq. (51) should be modified. An example of this modification for the particular problem of wave propagation in a rod was given in [12].

#### Acknowledgements.

The work presented here was done at Stanford University during the author's visit in 1967-68 and was supported by the Ballistic Research Laboratories, Aberdeen Proving Ground, Maryland, through Contract DA-04-200-AMC-659(X) with Stanford University. The author is greatly indebted to Professor E.H. Lee for making the visit possible and for valuable discussions on many subjects, including the present work, during his stay at Stanford University.

### References

1. Hill, R., "The Mathematical Theory of Plasticity," Oxford, Clarendon Press, 1950.
2. Bleich, H.H., and Nelson, I., "Plane Waves in an Elastic-Plastic Half-Space Due to Combined Surface Pressure and Shear," J. Appl. Mech., Vol. 33, 1966. 149-158.
3. Nan, Ning, "Elastic-Plastic Waves for Combined Stresses," Tech. Rept. No. 184, Dept. of Appl. Mech., Stanford University, July, 1968.
4. Ting, T.C.T., and Nan, Ning, "Plane Waves Due to Combined Compressive and Shear Stresses in a Half-Space." To appear in J. Appl. Mech.
5. Fong, Jeffrey, T., "Elastic-Plastic Wave in a Half-Space of a Linearly Work-Hardening Material for Coupled Shear Loadings," Tech. Rept. No. 161, Div. of Eng. Mech., Stanford University, May 1966.
6. Ting, T.C.T., "Interaction of Shock Waves Due to Combined Two Shear-Loadings." To appear in Int. J. Solids Structures.
7. Clifton, R.J., "An Analysis of Combined Longitudinal and Torsional Plastic Waves in a Thin-Walled Tube," Fifth U.S. National Congress of Appl. Mech., June 1966, 465-480.
8. Cristescu, N., "Some Observations about the Case of Plane Axial-Symmetric Deformations in the Dynamic Problem of Plasticity (Prandtl-Reuss theory)," Com. Acad. R.P.R. 6, 1, 1956, 19-28.
9. Courant, R., and Hilbert, D., "Methods of Mathematical Physics," Vol. II, Interscience Publishers, N.Y., 1962.
10. Clifton, R.J., "Elastic-Plastic Boundaries in Combined Longitudinal and Torsional Plastic Wave Propagation." To appear in J. Appl. Mech.
11. Clifton, R.J., and Ting, T.C.T., "The Elastic-Plastic Boundary in One-Dimensional Wave Propagation." To appear in J. Appl. Mech.
12. Ting, T.C.T., "On the Initial Slope of Elastic-Plastic Boundaries in Longitudinal Wave Propagation in a Rod," Tech. Rept. No. 187, Dept. of Appl. Mech., Stanford University, Sept. 1968.
13. Lee, E.H., "A Boundary Value Problem in the Theory of Plastic Wave Propagation," Quarterly of Applied Mathematics, Vol. 10, 1953, 335-346.

## DOCUMENT CONTROL DATA - R &amp; D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Department of Applied Mechanics Stanford University Stanford, Calif. 94305		2a. REPORT SECURITY CLASSIFICATION Unclassified	
2b. GROUP			
3. REPORT TITLE Elastic-Plastic Boundaries in Plane and Cylindrical Wave Propagation of Combined Stresses			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Interim Technical Report			
5. AUTHOR(S) (First name, middle initial, last name) T. C. T. Ting			
6. REPORT DATE December 1968		7a. TOTAL NO. OF PAGES 16	7b. NO. OF REFS 13
8a. CONTRACT OR GRANT NO. DA-04-200-AMC-659(X)		9a. ORIGINATOR'S REPORT NUMBER(S) Technical Report No. 194	
b. PROJECT NO.		9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report) Contract Report No. 16	
10. DISTRIBUTION STATEMENT Qualified requesters may obtain copies of this report from DDC			
11. SUPPLEMENTARY NOTES None		12. SPONSORING MILITARY ACTIVITY U.S. Army, Ballistic Research Laboratories, Aberdeen Proving Ground, Maryland	
13. ABSTRACT A general study is given of plane and cylindrical wave propagation of combined stresses in an elastic-plastic medium. The coefficients of the governing differential equations, when written in matrix notation, are symmetric matrices and can be divided into sub-matrices each of which has a special form. The relations between the stresses on both sides of an elastic-plastic boundary are derived. Also presented are the restrictions on the speed of an elastic-plastic boundary.			

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Dynamic Plasticity						
Wave Propagation of Combined Stresses						
Elastic-Plastic Boundaries						
Unloading Boundaries						
Loading Boundaries						