D 68 0951

HEADQUARTERS QUARTERMASTER DESEARCH & ENGINEERING CONDUC Quartermuster Research & Engineering Center, U.S. Army Natick, Massachusetts

6

TEXTILE, CLOTHING AND FOOTWEAR DIVISION Textile Engineering Laboratory Report No. 266

SIMULATION OF SWEATING INTO CLOTHING WITH CONSTANT SKIN TEMPERATURE

by

Lyman Fourt

1.1156 3

TEL. 261

Project Reference 7-93-18-020A

THIS DOCUMENT HAS BEEN APPROVED FOR PUBLIC RELEASE AND SALE; ITS DISTRIBUTION IS UNUMITED.

> Reproduced by the CLEARINGHOUSE for Federal Scientific & Technical Information Springfield Va. 22151

1960

25

DISCLAIMER NOTICE



THIS DOCUMENT IS BEST QUALITY AVAILABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY. HEADQUARTERS QUARTERMASTER RESEARCH & ENGINEERING COMMAND Quartermaster Research & Engineering Center, U.S. Army Natick, Massachusetts

TEXTILE, CLOTHING AND FOOTMEAR DIVISION

Textile Engineering Laboratory Report No. 266

SIMULATION OF SWEATING INTO CLOTHING WITH CONSTANT SKIN TEMPERATURE

by

Lyman Fourt

Project Reference 7-93-18-020A

1.14

April 1960

FOREWORD

This is one of a series of reports in the general field of wool type fabrics and alternates to conserve wool, with special reference to the physical features by which clothing structures contribute to the protection and effectiveness of the soldier.

This report was prepared by Harris Research Laboratories under Contract No. DA 19-129 QM 1336, Headquarters Quartermaster Research and Engineering Command, Quartermaster Research and Engineering Center, U.S. Army, Natick, Massachusetts. The contract, entitled "Investigation of Properties of Synthetic Fibers in Blends with Wool," was initiated under Project No. 6-93-18-2-., Development of Alternate Fabrics to Conserve Wool: Task: Development of principles to improve the insulating characteristics and "comfort" of textile fabrics combinations, and was adminiatered under the direction of the Textile, Clothing and Foctwear Division, Headquarters Quartermaster Research and Development Center with Mr. Constantin J. Monego acting as project leader.

This material is contractor's Report No. 33, for the quarter ending Sept. 11, 1959, the third quarter of this contract. INVESTIGATION OF PROPERTIES OF SYNTHETIC FIEER IN BLENDS WITH WOOL

> Contract No. PA-19-129-QM 1336 O.T. No. 9075 Third Quarter Period ending Sept. 11, 1959

HARRIS RESEARCH LABORATORIES, INC. 6220 Kansas Avenue, N. E. Washington 11, D. C.

Contractor's Report No. 33

SIMULATION OF SWEATING INTO CLOTHING WITH CONSTANT SKIN TEMPERATURE

* * * * *

SURGARY

An improved simulation of sweating into clothing is obtained by maintaining constant skin temperature by means of an automatically regulating power supply. As in the previous report, an impermeable film, which can be removed which out disturbing the clothing assembly, permits establishment of lates. persoure gradient in dry clothing, followed by the sweating process.

With containt skin temperature, there is an initial pulse of temperature rise in the clothing at the start of soluting, followed by cooling to a new steady state in which the clothing temperatures are higher than in the dry condition.

The power increases at the start of the period of sweating, and quickly becomes constant at a higher level before the temperatures have reached new Steady values. The new constant rate can be used to calculate the ratio

- 1 -

of combined heat loss through the clothing during sweating to the loss through dry clothing without sweating, or an equivalent thermal resistance for the clothing during sweating. The equivalent resistance with sweating is about 50 percent of the dry resistance, for wool serge, polyurethane form and polyester fiber batt. Differences between these types of material in the ratio of equivalent resistance to dry resistance are much shalls than the difference caused by sweating in any one material. Although these materials are approximately similar in decrease of resistance while sweating is going on, they differ considerably in amount of \cdot for retained, with less retained by low density, low regain materials. This retained or accumulated water is important with respect to chill after heavy work and sweating, since it continues to evaporate after the man has ceased to sweat.

TFP/ B The chief suggestion for improvement of clothing arising from this work is to reduce the amount of water accumulating in the clothing, by such means as lower density or use of lower regain fibers.

EXPERIMENT . METHOD

A brass cylinder, two inches in diameter, and wind tunnel with air stream at 5 mph, were used, all in the cold box at about =3° C. air temperature, as in earlier reports.

Surface temperature controller:

A resistance wire grid on the evaporating surface of the test cylinder is used as one arm of a Wheatstone bridge, with a sensitive relay to detect off-balance. This relay, in which latching force is dependent not merely on the activating current, but also on tripments, is reset to center at intervals of about 7 seconds by an interrogating circuit. If power continues to be needed, it goes on again until the next intervogation, but if power is not needed, it will scay off, in center position, or go to the other pole.

Power Measur . ent:

The power supplied to the test cell was measured in two different ways, in different tests. In one, the "on" side of the relay was connected to a timer, so that the time on could be cumulated. This, with voltage and current, measured power supply. In the other method, a watt-hour meter was modified with a photoelectric counter to count the revolutions of the disc. This also could be used to cumulate the mover of ply in arbitrary units, and by calibration, in units of energy.

With each method of measuring power, the interrogation period provided a brief pause in which the instruments could be read. Charts of increments at various intervals, from 7 seconds, the base period, up could be made: a period of 5 minutes was found suitable for a smoothed average.

- 2 -

Initiation of sweating:

The system of starting sweating into the natural thermal gradient set up in dry clothing, by removing an impermeable layer made of polyester film, as described in Report 32, was continued. In most of these tests, this was done in the same way as in Report 32, by removing one of the end insulating blocks, pulling out the film, and replacing the block. This, however, may chill the test cell, and interfere with observations of power requirement close to the start of sweating.

In order to observe the start of sweating more closely, the end insulation was revised, as shown in Figure 1, to a doughnut like clock, fitting over insulation cemented to the end of the brass cell. The polyester film could thus be drawn out between the doughnut and the center, with minimum disturbance of the clothing or exposure of the end of the cell.

A layer of vapor permaable callophane was used between the wet chamois and the outer layers, just interior to the polyester film, and was left in place to limit moisture transfer to evaporation.

RESCLTS

Typical temperatura sequence:

Temperature was followed at three levels in the clothing, in these tests, instead of at two, as in Report 32, by resistance wire grids carried on polyester fiber fabrics. The arrangement of layers is disgrammed in Figure 2. The same general sequence, of a quick temperature rise in the clothing, followed by a slower cooling to a new steady state, is seen. The greatest range of change, however, is in the center of the clothing layers.

- 3 -

The inner layer remains close to the controlled surface temperature. One reason that the outer layer response is reduced in most of the examples in this report is that rather large thicknesses were used.

The final starty state temperatures in the present constant surface temperature tests are higher than in the dry fabrics, not lower as they were with the constant power tests of Report 32.

Variation with materials:

Figures 3 and 4 show results for 2 and 8 layers of wool serge, while Figure 5 shows 2 layers of poll aster foam, and Figures 6 and 7 show polyester fiber batt, in two densities. Corresponding numerical data are in Table 1. All follow the general pattern just described, but it can be seen that the wool layers are slower in reaching the peak, and show more rounding of the peak of temperature and slower cooling, than the less absorbent foam and polyester fiber. The change with thickness is greater for wool fiber also.

Water secondistion:

The effect of time on the socumulation of water was not examined but the result found for constant power conditions, that water continues to accumulate as sweating goes on, has been used to adjust observations somethat longer or shorter than 60 minutes, on the basis of proportionality to that. The smoonts accumulated, on a 60 minute basis, are shown in Table 2, as grams per square mater of evaporating surface. The grams per square mater of cloching are smaller, since the clothing surface increases with increasing radius.

- 4 -

The weighings involved in determining water losses and water contents vary in the degree to which they are affected by evaporation losses during the weighing period itself. The initial dry weights of clothing can be determined accurately, and the initial weight of the assembly, because evaporation is prevented by the impermeable film. The final weight of the whole assembly is also relatively accurate, since it is obtained immediately after the end of the test period. The weights of the impermeable film and the water removed on its inner surface are also obtained immediately, so the net loss from the whole assembly can be established relatively accurately.

The layers themselves are weighed quickly, as they are unwrapped from the assembly, but there are some losses by evaporation during this process. Hence weights of water accumulated in the clothing are minimum values. Since the wet cell is weighed last, the evaporation from the skin is probably a maximum value. The difference between loss from the system as a whole, and loss from the skin, is always larger than the accumulation in clothing and grid layers, leaving some water not accounted for. In the presentation of results in Table 2, these maximum and minimum relations are indicated.

Table 2 shows that the evaporation from the skin is in every case larger than the evaporation from the system as a whole. With two and eight thicknesses of wool, the evaporation from the skin was practically the same in each, but more escaped from the system as a whole with the thinner cover. The tests with low regain systems were with thicker assemblies than the wool, so that greater thickness may account for the lower evaporation from the skin, but the 1 regain and low density appear to be connected with the greater net evaporation from the system.

- 5 -

The accumulation of moisture in the clothing also appears related to regain, much more being retained by the wool layers than by the other materials. A possible additional effect, operating in the same direction as the higher regain of the wool, is the greater amount of fiber, and greater surface area, involved in wool fabrics as opposed to small amounts of polyester fiber in batt form. However, the firm polyester batt has nearly the same weight as the leaser thickness of wool, but thins much less water.

Comparison of evaporation and power supply:

The amount evaporated per hour can be expressed as the corresponding power in watts, and compared with the power supplied, in steady state dry or wet. The power supply has been corrected for end losses, by the calibrations of Report 31. The power supply figures are shown for tests made with the on time method of measuring power. Qualitatively similar results were obtained with the watt hour meter, but lack of calibration steps involving power losses in intermediate transformers provents direct comparison.

Comparing the increase in power due to sweating with the calculated power for evaporation, as shown in Table 2, one sees that the increase in overall power due to sweating is intermediate between the evaporation at the skin level and the evaporation from the system as a whole. This indicates, as was discussed in Report 32, that there is no clearcut separation into parallel processes of energy transfer by heat and by moisture, simultaneously but separately. Rather, there is a progressive interchange between energy transfer by evaporation, which is greatest at the skin, and energy transfer as sensible heat, which is sugmented within the clothing by the condensation of water.

- 6 -

Effect of start of sweating on power requirement:

The on-off characteristics of the regulating system, and variability and overshooting, prevent as detailed an approach to power measurement as was hoped for. However, as nearly as one can tell from five minute averages of power requirement, the power goes at once to a new level, when sweating is started at constant skin temperature, and continues at this level for a long time, through the cooling part of the transient temperature effect and into the steady temperature period as far as we have followed it. The power supply rate, for five minute intervals, is shown in Figure 6, in which one can also see how an excess of power in one interval produced an upward wave of temperature in all layers.

Combined heat loss ratio:

The power required to maintain the skin at constant temperature, corrected for losses through the ends in order to obtain the power flowing through the sides, is a measure of the combined heat loss rate by all machanisms. The ratio, (power with sweating)/(power dry) gives the increase of heat flow by all mechanisms, with sweating. This ranges from 1.5 times as much combined loss for sweating through wool, to 2.4 for a polyester batt. Heatvalent r distance during sweating:

Since the power becomes and remains constant, while sweating is going on, and while water is accumulating in the clothing, it is possible to calculate an equivalent resistance during sweating, in analogy to the thermal resistance under dry conditions. This equivalent resistance, Req, is:

$$\operatorname{Req} = \underbrace{\left(\mathbb{T}_{1}^{*} - \mathbb{T}_{0}^{*}\right)}_{W_{S}^{*}} A$$

- 7 -

where T_1 ' and T_0 ' are the temperatures on the two surfaces of the clothing in the steady condition, with sweating, W_5 ' is the watts dissipated through the sides of the test cylinder while sweating is going on and A is the area. We can concentrate our attention on the effect of sweating by considering the ratio of equivalent resistance with sweating to dry relistance. This ratio is:

$$\operatorname{Reg/R} = \underbrace{(\operatorname{T_1}^{!} - \operatorname{T_D}^{!})}_{W_{S}} \quad \underbrace{W_{S}}_{(\operatorname{T_1}^{!} - \operatorname{T_O})}$$

Since the saturation vapor pressure changes more rapidly than the temperature, one might expect a shift between the relative effects of vapor and direct heat transfer, with change of skin temperature. The method of test described in Report 32, in which power was kept constant and skin temperature was allowed to reach its own level, provides data at a range of lower temperatures. Table 3 lists the skin temperatures, the temperature differences in the clothing, and the power dissipled through the sides, and Figure 8 plots the ratio of equivalent resistance while sweeting to dry resistance, splingt skin temperature.

The date in Figure 8 show considerable scatter, and any trend with surface temperature is small, in this range. A trend toward lower equivalent rebistance while sweating, relative to resistance while dry, would be expected, for increase in skin temperature. The fact that any trend is small in this

- 8 -

range of temperature permits use of the equivalent resistance while sweating, or the ratio of this to dry resistance, as a characteristic of a clothing assembly.

The scatter of the data available is such as to suggest that all of the materials tested are similar, in undergoing a 50 percent loss of resistance to energy transfer, during sweating. This change is larger than any differences between the materials with respect to the amount of change.

DISCUSSION

Relation to clothing in use:

In the actual use of clothing, the dry condition, as used in these tests, corresponds well with clothing freshly put on, and more or less with clothing in constant wear without a period of high exertion and sweating. There will be some insensible perspiration from the cool dry skin into the clothing, but the changes due to this are probably small compared with the changes due to water vapor from a warm, wet skin. The prior effect of insensible perspiration may, however, take some of the peak off of the start of sweating.

If matches introduces heat production above what can be dissipated from the thermal gradient, sweating will begin, and conditions will correspoint to the sweating portion of the tests. Any given relatively thick encently will approximately double its heat dissipating rate, and continue to lat energy be transferred at some fixed rate, by a combination of vapor and cirect thermal transfer, while water accompliates in the clothing. For thick clothing assemblies, this to be independent of the water content over a wide range.

- 9 -

With lower activity after a high level of work and sweating, sweating from the skin will cease and skin temperature will fall. The water content of the clothing will then be the critical factor. Until the inner layers of a bave become dry, the vapor mechanism of energy transfer will be operative, adding to the heat drain.

Suggestions for improvement of clothing:

Such this suggestion for improvement of clothing for cold environments ari is from this work is to reduce the commulation of water in the clothing. This may be accomplished in several ways. With a given material, an impermeable membrane with spaced holes to permit vapor escape through only part of the area may reduce the accumulation of water more than it reduces the escape of water vapor, as suggested in Report 18 of this series.

One can also reduce the accumulation of water by using material of lower regain, if thickness can be kept at the same level. One can probably gain by using structures such as batts or foams, which have lower density and less material and fiber surface area for a given thickness than conventional to the fabrics. However, the other requirements of use and garment design are involved in the substitution of batts or foams for woven fabrics.

- 10 -

TABLE 1

COMPARISON OF MATERIALS AND TEXPERATURES

.

1.1.1.1.1

..

..

Material:	Wool Sc.e	Nool Sarge	Polyurethane Foam	Polyester Fiber Firm Batt	Polyater Fiber Light Batt
Radial thickness, cm	0.50	2.07	2.30	2.54	2.47
Density, g/cm ³	0.21	0.23	0.027	0.036	0.012
Temperature in center Dry, steady, °C. Peak, °C. Final, steady, °C.	18.0 26.9 20.4	13.2 20.8 17.2	13.3 19.2 25.8	11.3 17.0 15.0	11.6 16.4 14.0
Peak rise, °C. Time to peak, min.	8.9 2.0	7.6 7.5	5.9 2.0	5.7 2.0	4.8 1.5

TABLE 2

. .

EVAPORATION AND ACCUMULATION OF WATER, OBSERVED CO CALCULATED IN PROPORTION TO THAT, YOU GO MINULA PERIOD. AREA BASE IS THE EVAPORATING SURFACE

Materials:	Wool Serge	Wool Serge	Polyurothane Foim	Polyester Fiber Firm Batt	Polyester Fiber Light Batt
Radial thickness, cm Longth of sweating, min	0.50 76	2.07 41	2 10 61	2.54 60	2.47
Dry unterial, inter layers, g/m ²	430	2070	270	340	120
	220	2000	310	510	100
Evaporation from skin, maximum, s/m ²	265	268	176	140	194
Man an anna an faran					
systen, g/m ²	69	56	75	59	102
Accumulation, minimum					
inner layers, g/m ²	59	130	4	10	18
outer layers, g/m2	43	71	21	19	11
inner levers. %	14	6	1.5		15
outer luyers, %	8	3	7	4	7
Pover equivalent if ever	oration				
and skin watts/m ²	178	180	118	94	131
ite of the watts/m2	4:6	38	50	40	69
Power supply to sides (s	tesév co	mditions	c)		
dry, witte/n2	155		65	46	
swellting, watts/m ²	235		137	111	
increase, watts/m ²	80		71	65	
Power vatio, sweating/					
azy	1.5_		2.03	2.44	
Touperature difference a	cross el	othing			
sweating, °C.	17.5		25.3	24.9	
dry, C.	19.7		25.8	28.3	
Clothing resistance					
rutio diciv. sweat-					
ing/dry, 7.	59		45	36	

TABLE 3

. .

FQUIVALENT RESIMACE OF WHOL, FLOW OF ENERGY IN STEADY STATE WITH SWEATCHS, COLPARED WITH IN THERMAN RUSISIANCE, FOR TECHS WITH CONSIDUR POWER SUPPRY. (OTHER FEATURES OF THESE TESTS AND IN REPART 32.)

					•		
Material	Radial Thickness	Skin Temperatur, Sveeting	Temperatur through	e Difference c hing	Power three	cush eides	Resistance Ratio
	ยี		Dry C.	sting 'c.	Dry watts/m ²	Sweating watts/m ²	Sweat SIDE
Wool sc lo	0.27	22.2	9.6	7.0	166	186	65
	0.95	2.4.8	23.3	13.4	68.5	105	48
Polyeste:	0.49	22.1	15.1	8,9	181.	154	50
fiber batt	0.48	20.2	20.4	12.7	149	175	53
Polyuret hane	0.35	21.5	10.6	1.1	140	167	50
fosm	0.36	20.0	12.3	7.6	136	162	52
	0.36	20,8	16,3	10.5	164	185	50
	0.46	20.7	22.8	15.3	162	179	63
	0.46	20.6	18.8	11.4	165	181	55
	0.43	21.1	17.5	10.9	118	141	52
	0.76	21.6	17.6	10.8	101	123	50
	0.82	23.6	23.1	17.4	98	1.15	64
	0.89	22.8	17.6	11.5	67	115	55
	1.04	22.0	25.3	17.2	98	118	56

- 14-



Figure 1, Report 33.

Arrangement of test cylinder and insulated ends, to permit start of sweating by pulling an impermeable film out through the "hole in the doughnut" at the right, without disturbing the clothing or exposing the end of the cylinder.



Figure 2, Report 33.

Sequence of layers on side of test cylinder, with space between layers emaggerated. l is the brass shell

- CH Chambis
- Gs Grids for surface temperature and temperature control

- F_1 Film of vapor permeable cellophone F_2 Removable impermeable polyester film G_1 G_2 G_3 Inner, middle, and outer temperature measuring f_1 for the polyester fabric grids on polyester fabric
 - C1, C2 Clothing layers.



Figure 3, Report 33.

Temperature sequence, with two layers of wool serge, radial thickness 0.50 cm.







Pigure 5, Report 33.

Temperature sequence with polyurethane foam, radial thickness 2.30 cm.



Pagare 6, Report 33.

Temperature sequence with polyester fiber batt, density 0.036 g/cm^3 , radial thickness 2.54 cm. The power supply, averaged for 5 minute periods, is also shown (semi scale for watts and temperature). An excess of power at 15 minutes shows as a wave in the comperature sequences.



Ludre 7, Report 33.

Temperature sequence with polyester ... Ler butt, density 0.012 g/cm³, radial thickness 2.47 cm.

- L.



Pigure 8, Report 33.

Litio of equivalent residence while Overting to dry resistance, for a range of thicknesses of the second and corresponding skin temperatures. Open circles indicate polyurethane form; crosses, wool serge, x's, polyester fiber batts.