REPORT NC. FAA-NO-70-13

AN EXPERIMENTAL STUDY TO DETERMINE THE EFFECTS OF REPETITIVE SONIC BOOMS ON GLASS BREAKAGE

George C. Kao Wyle Laboratories 7800 Governors Drive, West Huntsville, Alabama 35807



JUNE 1970

FINAL REPORT

Availability is unlimited. Document may be released to the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151, for sale to the public.

Prepared for

FEDERAL AVIATION ADMINISTRATION

Office of Noise Abatement Washington, D. C. 20590

> Reproduced by NATIONAL IECHNICAL INFORMATION SERVICE Springfield, Va. 22131



DISCLAIMER NOTICE



THIS DOCUMENT IS BEST QUALITY AVAILABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY.



The contents of this report reflect the views of Wyle Laboratories which is responsible for the facts and the accuracy of the data presented herein. The contents do not necessarily reflect the official views or policy of the Department of Transportation. This report does not constitute a standard, specification or regulation. I

TECHNICAL REPORT STANDARD TITLE PAGE 1. Report No. 2. Government Accession No. 3. Recipient's Cotolog No. FAA-NO-70-13 4. Title and Subtitle 5. Report Date June 1970 AN EXPERIMENTAL STUDY TO DETERMINE THE EFFECTS OF 6. Performing Orgenization Code REPETITIVE SONIC BOOMS ON GLASS BREAKAGE Copy No. 45 7. Authodal 8. Performing Organization Report No. George C. Kao WR 70-11 9. Performing Organization Name and Address 10. Work Unit No. Wyle Laboratories - Research Staff 31. Contract or Grant No. 7800 Governors Drive, West FA69WA-2204 Huntsville, Alabama 35807 13. Type of Report and Period Covered 12. Sponsoring Agency Name and Address Department of Transportation **Final Report** Federal Aviation Administration Office of Noise Abatement 14. Sponsoring Agency Code Washington, D.C. 20590 15. Supplementary Notes Detaile of Diustrations in the document may be better studied on microfiche 16. Abstract A pneumatic pistonphone simulator, developed by Wyle Laboratories, was used under the present contract to experimentally determine damage potential to single strength glass specimens when exposed to repetitive sonic booms. The glass specimen dimensions were typically 48" x 48" x 3/32". In these experiments, particular emphasis was placed on the cumulative damage from a large number of booms. Preliminary static strength tests were conducted on two sizes of new (previously unused) single strength glass to determine mean values and probability distributions of incipient failure pressures, and a few such tests were also conducted for used (scratched and weathered) glass specimens. As a by-product, these tests yielded data regarding nonlinear stiffness characteristics of glass panes and the effects of boundary conditions on this stiffness. Although the test data are limited, results indicate that sonic boom overpressures required to cause incipient failure are nearly comparable to static failure pressures, and the probability of glass failure at realistic sonic boom overpressures is quite small for properly mounted new glass. Further experiments will be required to validate and extend these results. A preliminary glass neighborhood survey was conducted to determine breakage rates under natural environments; however, because of the small sample size, the glass breakage statistics obtained were of limited value in formulating a realistic breakage probability model. A more comprehensive, national alass neighborhood survey is required. 17. Key Words 18. Distribution Statement Simulation - Sonic Booms - Glass Breakage -Availability is unlimited. Document may be released to the Clearinghouse fcr. Federal Neighborhood Survey - Cumulative Damage Scientific and Technical Information, Springfield, Virginia 22151, for sale to the public. 21. No. of Pages 19. Security Clessif. (of this report) 20. Security Classif, (of this page) 22. Price 88 Unclassified Unclassified \$13.00

Form DOT F 1700.7 (8-85)

PREFACE

The development of the research study, implementation of the test program, and collection of the information and data presented in the report represent a team effort of the Wyle Laboratories Research Staff. The responsibilities of the participating personnel were as shown:

- Mr. R.W. White Program Manager: Static Test Program
- Dr. G.C. Kao Principal Investigator: Sonic Boom Test Program
- Mr. F.M. Murray Development of Sonic Boom Simulator Criteria
- Mr. J.A. Cockburn Structural Response Studies
- Mr. V.M. Conticelli Review of Sonic Boom Signatures
- Mr. R.C. Gray Glass Neighborhood Survey

Acknowledgements

.....

Thanks are extended to Mr. K.M. Eldred, Technical Director of Wyle Scientific Services and Systems (SSS) Group, for his criticisms and encouragement during various phases of the operations; to Mr. J.O. Bowman, Manager, Research Operations, for the management support; and Mr. N.E. Esslinger for implementing test programs.

Appreciation is also extended to Dr. J. Powers, Mr. K. Power, and Mr. S. Oleson of the Noise Abatment Office of FAA for many helpful discussions and guidance during the course of the program.

TABLE OF CONTENTS

			Page				
1.0	INTRO	RODUCTION					
2.0	DESCRIPTION OF WYLE SONIC BOOM SIMULATOR						
	2.1 2.2 2.3 2.4	Design Criteria Structural Configuration Airstream Modulation Valve Principles of Operation					
3.0	SONIC BOOM SIGNATURE CRITERIA						
	3.1 3.2 3.3	1 Introduction 2 Sonic Boom Signatures 3 Waveform Criteria					
4.0	EXPERIMENTAL PROGRAM						
	4.1 4.2	Introduction Static Strength and Nonlinear Stiffness Experiments	25 26				
		 4.2.1 General 4.2.2 Time to Failure 4.2.3 Failure Pressure Probability Curve 4.2.4 Non-linearity of Glass Behavior 	26 26 30 30				
	4.3	33					
		 4.3.1 Description of Test Specimen and Fixture 4.3.2 Test Procedures and Methods 4.3.3 Results of Sonic Boom Tests 	33 33 39				
	4.4	4.4 Discussion of Test Results					
5.0	EFFECT OF SONIC BOOMS ON GLASS BREAKAGE						
	 5.1 Introduction 5.2 Previous Experimental Results 5.3 Suggested Criteria for Glass Breakage 5.4 Design Guide for Evaluating the Effects of Sonic Booms 5.5 Glass Breakage Due to Normal Environments 5.6 Glass Breakage Probability Due to Sonic Booms 						
6.0	CONCLUSIONS						

vii

TABLE OF CONTENTS (Continued)

	Page
REFERENCES	68
BIBLIOGRAPHY	70

LIST OF FIGURES

Figure		Page
2-1	Side View of Interior of Sonic Boom Simulator	6
2-2	Cross-Section of Sonic Boom Simulator Showing Three Interior Cavities	7
2-3	Interior View of Sonic Boom Simulator Showing Inlet and Outlet Air Flow Valves	8
2-4	An Exploded View of the Air Stream Modulation Valve	9
2-5	Schematic Circuit of Glass Testing Facility	10
2-6	Instrumentation Block Diagram for the Electrical Control System	12
2-7	Instrumentation Equipment List	13
2-8	Input Signals for the Electrical Control System	14
2-9	Operation Sequence of the Wyle Sonic Boom Simulator	15
2-i0	Typical Sonic Boom Signatures Generated by Wyle Simulator	17
3-1	Typical Sonic Boom Signatures Generated by F-104, B-58, and XB-70 Supersonic Aircrafts (Reference 2)	19
3-2	Energy Spectra of Sonic Booms for Various Aircraft and a Hypothetical SST (from Reference 8)	21
3-3	Idealized Sonic Boom Signatures (Reference 6)	23
3-4	Comparison of Dynamic Amplification Functions for Five Different Types of Waveforms (Reference 6)	24
4-1	Arrangement of Plywood Box and Edge Support Conditions for Water Column Loading Experiments	28
4-2	Effect of Loading Rate on Normalized Breaking Stress	29

ix

LIST OF FIGURES (Continued)

Figure		Page
4-3	Probability Distributions for Failure of Single Strength Glass Under Standard Loading	31
4-4	Non-dimensional Load versus Non-dimensional Deflection for Single Strength Glass	32
4-5	Details of Wooden Mounting Frame	34
4-6	Method used to Fasten Wooden Frame to Steel Test Fixture	35
4-7	General View of Glass Testing Arrangement (Note Broken Glass Pane)	36
4-8	A Typical Acceleration Response Spectrum of a 48" x 48" x 3/32" Glass Specimen to Acoustic Sine Sweep Excitation	37
4-9	Sine Sweep Response Spectrum of a Test Specimen with Cracks in the Lower Right Corner	38
4-10	Acoustic and Accelerometer Responses of Sonic Boom Test Number 1	41
4-11	Acoustic and Accelerometer Responses of Sonic Boom Test Number 2	42
4-12	Acoustic and Accelerometer Responses of Sonic Boom Test Number 3	43
4-13	Acoustic and Accelerometer Responses of Sonic Boom Test Number 4	44
4-14	Acoustic and Accelerometer Responses of Sonic Boom Test Number 5	45
4-15	Acoustic Responses of Sonic Boom Test Number 6	46
4-16	Acoustic Responses of Sonic Boom Test Number 7	47
4-17	Acoustic Responses of Sonic Boom Test Number 8	48
4-18	Summary of Static Testing Data	50
4-19	Summary of Repetitive Sonic Boom Test Results	51
5-1	Measured Bending and Membrane Stresses at Center of Test Window Under Static Pressure Loading (Reference 12)	54

LIST OF FIGURES (Continued)

Figure		Page
5-2	Measured Peak Tensile Stresses at Center af Window as a Functian of the Saund-Pressure Level in a One-Third Octave Band Centered at 35 Hz (Reference 12)	54
5-3	Summary of Results from Window Breakage Tests (Data from Reference 16)	55
5-4	Summary af Window-Glass Breakage Experienced Due to Sanic Booms. Laad Specified by the Narmalized Parameter $p_0 (\alpha/h)^2$ where α/h is the Ratio of a Side Length (α) to Thickness (h). (Data fram a Summary in Reference 16)	57
5-5	Static Load – Deflection Curve far 3ft x 3 ft x 1/8 in. `/indow Pane (Data from Reference 16)	58
5-6	Maximum Safe Predicted ar Measured Average Ground Cverpressure for Plate and Window Glass (Reference 5)	60
5-7	Simplified DAF Envelapes for Sanic Booms (References 6 and 23)	62
5-8	Estimation af Probability af Test Result Versus Sample Papulation	66

xi

1.0 INTRODUCTION

Only limited information is available concerning the probability of glass or glass windows being damaged by sonic booms. Planned experiments and accidental booms have indicated that glass windows can be one of the more damage susceptible building materials in the sonic boom environment. Without conclusive valid data, one could suspect that overland supersonic flights would result in significant increases in glass damage. Further, the validity of any damage claim attributed to sonic booms would be extremely difficult to access. This is especially true concerning sonic boom created damage versus common glass damage due to accidents and natural environments such as wind, temperature fluctuations and general overloading.

The lack of information available concerning the above problem area shows that research is necessary to technically assist in planning flight patterns and operational procedures for superscnic aircraft. Overflight experiments are costly, time consuming, and disruptive to the general public; hence, it would be a significant step forward if the sonic boom environment could be confined to a laboratory and simulared by relatively inexpensive techniques. In this way, numerous windows could be exposed and statistically analyzed for their damage potential within such an environment. This approach requires the development of sonic boom simulators within which a test specimen can be mounted in a realistic manner and subjected to an N-wave overpressure pulse that is characteristic of sonic booms. Several such simulators are in existence, and each has its own peculiar advantages and disadvantages. In an attempt to further the state-of-the-art, Wyle Laboratories has developed a small inexpensive simulator which operates on a unique principle, and which can subject glass windows up to 4 feet by 6 feet to an unlimited number of sonic booms of various wave forms with a few seconds duration between booms. Details of the Wyle sonic boom simulator are presented in Section 2.0 so that its application to this program can be understood.

In order to determine acceptable waveforms for testing, a comprehensive literature survey was conducted to review available information on sonic boom signatures and the related structural response problems. From the result of the survey, it was concluded that the controlling factors affecting glass failure are the overpressure magnitude, the wave duration and rise time. The determination of sonic boom waveforms used in the test program is given in Section 3.0. In Section 4.0, the test program used to conduct exploratory static and sonic boom testing on glass specimens is described. The static testing was performed on 35 specimens with typical dimensions of $20" \times 20" \times 3/32"$ and 30 specimens with typical dimensions of $20" \times 20" \times 3/32"$ and 30 specimens with typical dimensions of $48" \times 48" \times 3/32"$. The objective here was to determine the distribution of failure strengths and to determine the correlation of static strengths and the overpressure levels used in the sonic boom testing. A total of six panes of used glass were also tested statically to evaluate the effect of aging on glass strengths. The sonic boom testing was performed on $48" \times 48" \times 3/32"$ specimens only. These tests were confined to specimens mounted on a wooden frame. A total of 8 successful tests were performed by employing repetitive N-wave loadings.

A local (Huntsville, Alabama) glass neighborhood survey has conducted and an extensive review made of existing published data on glass breakage. The results of these studies

have shown that it is not feasible to formulate valid statistical prediction techniques for normal glass breakage. Information concerning glass breakage is summarized in Section 5.0. Finally, the conclusion drawn from the results of the present study are summarized in Section 6.0.

ţ

2.0 DESCRIPTION OF WYLE SONIC BOOM SIMULATOR

2.1 Design Criteria

Although the Wyle simulator was designed and developed to expose large panels to various pressure fluctuations over a large range of frequencies (down to 0 Hz) the description presented here is applicable to use in producing transients. The following operational criteria were considered in design for sonic boom simulation mode:

- Internal fixturing for test specimen support should be variable so that test specimens may have arbitrary geometry, edge mounting conditions, and size (up to 4' x 8' rectangular window).
- Cavity stiffness of the closed volumes on either side of the test specimen should be small relative to the bending stiffness of the test specimen.
- Simulated overpressures should be reasonably uniform over the surface of one side of the test specimen.
- The overpressure time history for a single simulated sonic boom should consist of a symmetrical N-wave with rise times of less than 10-20 milliseconds.
- The amplitude and duration of a simulated N-wave should be variable throughout the ranges of 1.0-100 psf and 50-400 milliseconds, respectively.
- The system should be capable of generating a continuous train of N-waves having the same amplitude and period, and having a constant time between N-wave pulses.

2.2 Structural Configuration

The sonic boom simulator is contained within a steel pressure vessel that has a cylindrical main section with shallow spherical end caps. The cylindrical section has a length of 9.0', a diameter of 7.0', and is constructed of 1/4" steel. The rear end cap is permanently welded to the cylinder; while the hinged front end cap acts as a door and is attached to the cylinder through a reinforcing ring by means of 24 high strength steel bolts. Under normal operating conditions, ambient internal pressure levels may range between 3 to 10 psi; and hence the containment vessel was designed to ASME codes and was proof tested to 45 psi.

Internally, the simulator is divided into three cavities by means of two bulkheads that extend along the full length of the cylindrical tank. The largest of these three cavities, referred to as cavity number 1, is shown in the photograph in Figure 2-1, which is a view looking aft through the open front door. As shown in the photograph, the left-hand side of cavity number

1 is bounded by a heavy vertical steel bulkhead that contains a 4.5' x 6.5' rectangular opening for mounting of test specimens. The other two cavities, which are referred to as cavities number 2 and 3, are located behind the flat bulkhead. These cavities can be seen in the cross-section drawing in Figure 2-2, which is a view looking toward the door opening. The small 58 cubic foot central cavity number 2 is the active pressure cavity within which sonic boom overpressure signatures are generated. The large water-filled cavity number 3 was introduced for the sole propose of reducing the volume of number 2, and a water medium is employed to minimize vibration response of the 1/4-inch steel bulkhead which separates cavities 2 and 3.

The central bulkhead that supports the test specimens is designed to be very rigid so that vibrations of this bulkhead are minimized during sonic boom generation. This high lateral stiffness is achieved with shear plates that can be seen in Figure 2-1. With minor modifications, which do not effect the basic strength of the containment vessel, the rectangular opening in this bulkhead can be increased to 6' x 8' to accommodate larger test specimens. For smaller test specimens, the existing opening can be reduced in size by the addition of reinforced plywood panels. The fill-in panels used in the test program consisted of 2" thick plywood slabs bounded on both sides by 1/4-inch aluminum plates. These plywood panels, which are also used for calibrating sonic boom signatures, along with the test specimen frame are bolted to a steel angle that is welded to the interior periphery of the rectangular opening as shown in Figure 2-1.

When the panels and test specimen are in-plane, the central bulkhead provides a pressure seal between cavities 1 and 2. At the top of the simulator there are two pipe penetrations through the containment vessel. One of the pipes is connected to an air compressor which feeds high pressure air into the simulator; while the other pipe is used for exhausting air from the simulator into the outside atmosphere. Airstream modulation valves, which control the flow of air into and out of the simulator, are attached to the two pipe penetrations on the interior of the simulator. A photograph of these valves is shown in Figure 2-3.

During operations, the simulator is closed and cavities 1 and 2 are maintained at an ambient pressure level of about 3 psi. Ambient pressure equalization between cavities 1 and 2 is maintained by a small hand-valve. The flow rate through this valve is sufficiently small so that transient overpressures generated in cavity number 2 are not equalized in cavity number 1.

2.3 Airstream Modulation Valve

The Wyle patented airstream modulator valve is essentially a vibrating vane air valve which regulates large volumes of air at moderate pressure levels. The valve has a switching time capability within one or two m lliseconds. The device is normally operated with a continuous input air flow to produce high intensity acoustic energy. Modulation is accomplished through rapid interruption of the airstream by a moving coil and a valve having sufficient stiffness to assure constant displacement characteristics throughout the valve's operating range. The basic units of the valve are shown in Figure 2-4 which is an exploded view of the entire assembly without the aluminum supporting frames. This figure shows the entire armature with its voice

coil, modulation slots, suspension slots and finally a solid ring at the top which serves as an attachment surface. This entire unit, excluding the voice coil, is machined from a single piece of aluminum tubing. The modulation slots are cut around the periphery of the armature so that the axial motion of the voice coil against the suspension will vary the openings formed by the two sets of slots in the armature and stator. The width of each slot is chosen to match the maximum allowable displacement of the suspension. The suspension stiffness is chosen to properly load the capabilities of the voice coil Thus, all the elements of the armature are strongly interdependent.

It may be seen that air pressure applied to either the inside or the outside of the armature would cause air to pass through the various slots cut in it. The stator, mounted inside the armature, has no spring slots and therefore prevents air from flowing through, but it does have an identical set of modulation slots. The stator and armature are mounted such that the beams between the modulation slots of the armature cover exactly half of the slots of the stator and vice versa. This condition is permanently set at the factory so that no misalignment of these two sets of slots can occur in the field. Thus, it may be seen that motion of the voice coil causes the area of the modulation slots to increase or decrease depending upon the polarity of the input electrical signal to the voice coil. This action breaks the airstream into pulses of air. These pulses may then be translated into pressure pulses inside the simulator.

2.4 Principles of Operation

The shaping of N-waves in the simulator is achieved by modulating the airflow through the two airstream modulating valves (the inlet and outlet valves) under a constant compressor pressure. The arrangement of various mechanical and electrical elements employed in the operation are illustrated in Figure 2-5. The air supplied to the simulator is provided by the compressor and is regulated by the inlet valve, while the venting of the compressed air into outside atmosphere is controlled by the outlet valve.



Figure 2-1. Side View of Interior of Sonic Boom Simulator



Figure 2-2. Cross-Section of Sonic Boom Simulator Showing Three Interior Cavities

and the second second



Figure 2-3. Interior View of Sonic Boom Simulator Showing Inlet and Outlet Air Flow Valves



Figure 2-4. An Exploded View of the Air Stream Modulation Valve



.

A contribute

The second secon

- en-

An Auril 4

The essential part of the entire waveform synthesizing cycle is the shaping of the electrical control signals used to generate a series of rapid interruptions of airflow through the valves. The electrical system which controls the open-and-close sequence of the valves are shown in Figure 2-6, and the corresponding control signals used in the simulating process are shown in Figure 2-8. Figure 2-7 lists the instrumentation used throughout the test program.

The input signal, which controls the inlet valve, consists of two half-sine pulses (Figure 2-8 (a)). The pulse widths determine the total opening duration of the valve and therefore regulate the rate and the total amount of air to be supplied to the simulator. The input signal which controls the outlet valve (Figure 2-8 (b)) is shaped in a manner such that the combined operations of the two valves would render the desirable acoustic waveforms.

Generally, the sonic boom synthesizing operations involve four sequential stages described as follows:

- Stage 1 Generation of Steady State Pressure, P_a, in the Simulator
- Stage 2 Generation of Positive Overpressure, ΔP , Relative to P_{α}
- Stage 3 Generation of Negative Overpressure, ΔP , Relative to P_a
- Stage 4 Repressurization to P

The four-stage operation can be represented diagramatically as shown in Figure 2-9, and the details of the operations are described in the following paragraphs.

Stage 1: Generation of Steady State Pressure, $P_a - At$ the initial stage of the operation, the outlet value is completely open; the inlet value is partially closed to allow only a small amount of air leakage into the simulator; and the compressor is operating under a constant line pressure, P_L . The operations would permit the static pressure inside the simulator to maintain a very low level so that a very high pressure differential can be established across the inlet value to allow rapid build-up of various overpressure levels. Since airstream modulating values are designed to have 50 percent openings under no-load conditions, it is necessary to apply certain d.c. voltages to close and open the respective values to achieve the required initial condition. This is illustrated in Figure 2-9, in which the voltages $+V_1$ and $-V_2$ are applied to the inlet and outlet values, respectively.

Stage 2: Generation of Positive Overpressure, $+\Delta P$ – The operations required in this stage are (see Figures 2-9 and 2-10):

- a) to close the outlet valve completely, and
- b) to open the inlet valve with a half-sine pulse.

Both actions are initiated at time t_a.





12 .

.

DESCRIPTION	Provides from 10 to 100 individual and independent bits or incremental voltage levels, completely controlled in slope, amplitude and width.	Dual channel, 300 watt amplifier with frequency response – DC to 20 K Hz.	Single ended, high crurent amplifier + 100 MA output current with gains from 1,000 to 0.1 and continuous adjusiment.	Laboratory type instrument, generates sine, square, triangular and saw- tooth waves to cover the frequency spectrum from .0005 Hz to 1 M Hz.	A 5 psi, 60 dB dynamic range acoustic transducer. Frequency response- DC to 20 K Hz.	A radio frequency oscillator coupled to a diode detector circuit. Frequency response – DC to 20K Hz.	Voltage range - 100 microvolts to 320 volts in 13 ranges, total range of 130 dB. Frequency range 5 Hz to 500 K Hz.	A self contained portable unit for calibrating the sensitivity and linearity of microphone systems. Frequency set at 1 K Hz. Sound levels of 100 to 160 dB.	A dual trace, 200 K Hz bandwidth osci!loscope range 5μ s/cm to 200 ms/cm in 15 ranges.	A direct writing oscillographic recorder. Paper speeds from .05 ips to 120 ips and writing speeds in excess of 50,000 ips. Gal vanometer linearity is $\pm 2\%$ of full scale deflection which is 8 inches peak to peak.
MOD. NO.	200	DC-300	4550	9030	520	DG-60-5-D	320	PC-125	122/AR	1508-A
MFG.	Exact Electronics	Crown	Dynamics	Beckman	Photocon Research	Photocon Research	Ballatine	Photocon Research	Hewlett Packard	Honeywell
ITEM	Waveform Synthesizer	DC Power Amplifier	DC Amplifier	Function Generator	Microphone	Microphone Amplifier	True rms Voltmeter	Microphone Calibrator	Oscilloscope	Osci Il/vgraph Recorder

Figure 2-7. Instrumentation Equipment List



Figure 2-8. Input Signals for the Electrical Control System

i



Figure 2-9. Operation Sequence of the Wyle Sonic Boom Simulator

As a result, the pressure inside cavity number 1 rises. The rate of the pressurization and the final pressure intensity at t_1 is dependent on the pulse duration and the amplitude of the input half-sine pulse.

Stage 3: Generation of Negative Overpressure, $-\Delta P$ — The reduction of the pressure level in cavity number 1 requires:

- a) shut off the inlet valve completely to stop the airflow, and
- b) open up the outlet valve gradually to vent the compressed air into the atmosphere.

The rate of air venting is controlled by the input signal as shown in Figure 2-9(b), and the entire operation is designed to be completed within the time duration of $(t_2 - r_1)$.

Stage 4: Repressurization – After the $-\Delta P$ level is reached, it is necessary to close the outlet value so that the pressure level in cavity number 1 can be raised to its initial value, P_a . In order to achieve a faster recovery time, it is necessary to supply an additional volume of air from the compressor at time t_2 . This is accomplished by applying the half-sine pulse signal to the inlet value (Figure 2-9 (a)). The entire waveform synthesizing cycle is now complete.

Typical sonic boom signatures generated by the simulator are shown in Figures 2-10 (a) and 2-10 (b). These were obtained from tests using the rigid panel and a glass panel, respectively. The duration for both waveforms is 400 milliseconds, but the risetime is approximately 20 milliseconds for the rigid panel and 40 milliseconds for the glass panel. It is evident, as can be seen from the signatures, that a flexible panel yields a longer risetime.





NOT REPRODUCIBLE

(a) Sonic Boom Signature Obtained by a Rigid Calibration Panel





And the state of t

(b) Sonic Boom Signature Obtained by Glass Panel



3.0 SONIC BOOM SIGNATURE CRITERIA

3.1 Introduction

The prime concern of Wyle's sonic boom simulator is the creation of suitable environments to simulate the effect of sonic booms on structures. To achieve the objective, a careful evaluation on loading waveforms and the associated structural response phenomena would be required to insure that specific test requirements can be fulfilled by the simulator. Therefore, it is the purpose of this section to examine existing knowledge in the above stated areas and to define sonic boom signatures that are suitable for the study of structural effects under simulated conditions.

Assuming that the glass used in simulation tests are "perfect" specimens (so that the structural failure of glass is solely attributed either to overstress or to fatigue damage), the prime test parameters to be considered in the simulation tests are the sonic boom signatures, the dynamic characteristics of glass systems and the internal room acoustics. Recent investigations (Reference 1) have shown that the probability of Helmholtz resonance phenomena occurring in a room due to window response is quite low. Therefore, the influence of room acoustics or the response of window glass should be minimal under normal situations. Consequently, the parameters considered in the sonic boom signatures of window glass.

A review of sonic boom signatures obtained from overflight programs was performed, and the characteristics of these waveforms were compared based on their individual energy spectral density functions. After establishing the basic properties of sonic boom signatures and the dynamic characteristics of window glass, the criteria used to determine simulating waveforms for sonic boom tests were established.

3.2 Sonic Boom Signatures

The term "sonic boom signature" is used to designate the characteristics of the pressure disturbance generated by an aircraft flying at supersonic speed; it is characterized by its overpressure amplitude, risetime, and wave duration. The shape of a sonic boom is a function of aircraft configurations, atmospheric conditions, operating conditions and ground topology. Different aircrafts operating under various environments generate sonic boom signatures that are distinctively different from each other. Typical sonic boom signatures generated by F-104, B-58, and B-70 aircrafts are shown in Figure 3-1.

Efforts to gain a better understanding of the generation of sonic booms and their associated problems, such as effects on people and structures, have been attempted by numerous researchers and organizations. Excellent bibliographies on the above stated subjects can be found in References 2–7.







Figure 3–1. Typical Sonic Boom Signatures Generated by F–104, B–58, and XB–70 Supersonic Aircrafts (Reference 2)

and the second second second

To simplify the study of the effect of sonic booms on structural responses, the ordinary pressuretime history of the waveform can be converted into its corresponding energy spectra Jensity form which is defined as follows:

$$\left| P(\omega) \right|^2 = \left| \int_{-\infty}^{\infty} p(t) e^{-i\omega t} dt \right|^2$$

where

 $|P(\omega)| =$ energy spectral density p(t) = instantaneous pressure at time t $\omega =$ frequency in radians

The above quantity is used to express the spectral distribution of the input energy of the N-wave.

To illustrate the importance of the wave duration effect, the energy spectra of sonic booms for various aircrafts and a hypothetical SST (Reference 8) are shown in Figure 3-2, in which the same value of peak overpressure is assumed in each case. Since most of the input energies are contained in the low frequency range, it is expected that the dynamic responses caused by sonic boom disturbances on large windows would be pronounced. For smaller windows, whose fundamental periods are much shorter than that of the wave duration, the structural response to sonic booms is directly proportional to the magnitudes of the overpressures.

3.3 Waveform Criteria

The present Wyle sonic boom simulator could be used to serve two purposes:

- To determine the breaking strengths of glass specimens (static and dynamic), and
- To determine the cummulative damage effect on glass caused by repetitive sonic boom exposures.

Since there exists a variety of sonic boom signatures that could be utilized to excite test specimens in the simulator, the logical criterion for selecting a proper test waveform is that the waveform employed for testing must be able to produce the probable maximum structural responses. A convenient scale which is frequently used by engineers to compare structural responses subjected to different dynamic loadings is known as the dynamic amplification function (daf), which is a dimensionless quantity and is defined as the ratio of the maximum response of a single oscillator to its static response under uniform peak pressure loading.



Figure 3–2. Energy Spectra of Sonic Booms for Various Aircraft and a Hypothetical SST (from Reference 8)

and the second se

A comparative study on daf for simply supported uniform plates under five types of representative sonic boom signatures, as shown in Figure 3-3, has been recently reported by Cheng (Reference 6). He found that the response due to the pressure-pulse type loading is greater than that due to traveling-wave type loading; and the daf for different wave forms is dependent on the wave durations and the fundamental period of the plate. The latter results may be conveniently summarized in graphical form as shown in Figure 3-4, in which, the daf's for the five different waveforms are plotted agoinst the dimensionless quantity R, which is defined as the ratio of the sonic boom wave duration, τ , to the fundamental period, I, of a simply supported plate. Assuming that the wave duration of future SST's would be in the range of 300 to 400 miliseconds, it is obvious that the selection of simulation waveforms depends on the criteria described as follows:

- For smaller windows (R > 2), the daf's for the waveforms considered vary within the range of 1.5 to 2.5 and the generation of "exact" sonic boom signatures is not necessary. Adequate simulations could be achieved by employing either "C" or "Q" waves.
- For large windows (R < 2), the waveform characteristics have significant effects on respective daf's. Therefore, the knowledge of the approximate waveform would be required and the wave duration should be tuned to obtain the maximum dynamic response. If the information on the sonic boom signature is not available, the "R" wave should be used and tuned so as to obtain the probable lower bound overpressure level for test specimens.

Although the analysis performed for the above daf's did not include the effects of structural nonlinearity, participation of higher modes, and structural damping in the computation, it is considered that the omission of such factors would not alter significantly the overall characteristics of the computed daf's. For purposes of the Wyle experiments;

$$R = \frac{\tau}{T} = \frac{0.4 \text{ sec}}{0.033 \text{ sec}} \simeq 12$$



Figure 3-3. Idealized Sonic Boom Signatures (Reference 6)

and the strength of the streng





Dynamic Amplification Function, daf

4.0 EXPERIMENTAL PROGRAM

4.1 Introduction

The main objectives of the experimental program were to determine breaking strengths of new glass under static and sonic boom conditions and to evaluate the effect of different edge conditions on the nonlinear characteristics of glass specimens. In all, a total of 114 panes of new and used glass were tested. The type of glass specimens used are as follows:

- 35 panes of 20" x 20" x 3/32" new glass
- 73 panes of 48" x 48" x 3/32" new glass
- 6 panes of used glass (various sizes)

The criterion for the sonic boom tests was to establish cummulative damage limits for glass specimens under various overpressure levels. Obviously, testing too many types of glass would significantly reduce test sample sizes, and hence, lower the confidence limits of test results. Therefore, the optimum approach for the test program was to establish the lower bound cumulative damage limit by testing the weakest member of the glass family in which the single strength glass was considered as the candidate.* The dimensions of test specimens were determined primarily by the largest single strength glass available in local retail stores. The final dimensions chosen for the tests were $48" \times 48" \times 3/32"$.**

The $48" \times 48" \times 3/32"$ specimens were also used in the static testing to determine the breaking strength under three types of boundary conditions; namely, the rubber and putty; the simply supported; and the clamped supported. The objectives for the static testing were two-fold:

- To correlate the breaking strengths of sonic boom tests and static tests; and
- To compare test results with existing test data.

In order to study the effect of specimen size on glass breaking strengths, additional static tests were conducted on $20" \times 20" \times 3/32"$ specimens with the rubber and putty edge conditions. Furthermore, several panes of used glass mounted in their original wooden frames were also tested to study the effect of aging due to natural environments.

** For a given area, a square panel would experience a higher stress level as compared to rectangular panels subjected to identical loadings.

^{*} For a given area, the single strength glass sustains the least load as compared with glass of thicker gages, see References 9 and 10.

A summary of loading and edge conditions employed in the test program is presented in Table 1.

4.2 Static Strength and Nonlinear Stiffness Experiments

4.2.1 <u>General</u> – In order to verify the stotic behavior of glass samples and to assess the effects of proctical boundary conditions, experiments were conducted with 71 panes of single strength glass. The glass samples were divided into three groups, as follows:

- 30 panes of 48" x 48" new glass
- 35 panes of 20" x 20" new gloss
- 6 panes of 25" x 25" (approx.) used glass

The first group of glass samples was edge supported by three different types of mounts; as follows:

- Soft rubber and putty
- Simply supported by wood on one side
- Clamped by wood on both sides

The second group of glass samples was edge supported on neoprene rubber and putty, while the used glass panes were tested in their original wood fromes with putty on one side.

The static behavior of the glass somples was determined by pressure loading in the following manner:

- The 48" x 48" glass panes ond the 25" x 25" used gloss panes were loaded by a column of woter
- The 20" x 20" glass panes were loaded by oir pressure

The experiments utilizing water column loading were conducted in a plywood box as shown in Figure 4-1. Details of the three edge mounting conditions are also shown in this figure. To eliminate any air spring effect beneath the gloss pane due to gloss deflection under load, this volume was vented to atmosphere.

The experiments utilizing air pressure loading were conducted in a cylindricol pressure tonk, the glass sample being mounted in one of the stiff flot end bulkheods. The edge support conditions for the air pressure experiments was similar to the rubber-putty support shown in Figure 4-1.

4.2.2 Time to Failure – The time required for a glass panel to foil under o constant load varies inversely with the magnitude of the load, as shown in Figure 4-2 of Reference 11. Using this figure, stotic strength data presented in Reference 11 are normolized to a "oneminute-to-failure" load; most static strength glass tests are conducted so that failure occurs within approximately one minute.
TABLE I –	SUMMARY	OF	EXPERIMENTAL	PROGRAMS
-----------	---------	----	--------------	----------

Type of Test	Specimen Sizes (in.)	Edge Condition Total Number of Specimens		Type of Glass	
Static	20" × 20" × 3/32"	Rubber and Putty	35	New	
	48" x 48" x 3/32"	Rubber and Putty	31	New	
		Simply Support	4	New	
		Clamped-Clamped	2	New	
	25" × 25" × 3/32"	Wooden Window (Mounted Condition)	6	Used	
Sonic Boom	48" × 48" × 3/32"	Clamped-Clamped	36	New	





Partially Supported Edge Rubber and Putty One Side Only



Simply Supported Edge Wood One Side



Clamped Edge Wood Both Sides







And the second second

Loading rates for the experiments performed by Wyle were such that failure occurred within the following time durations:

- 1-2 minutes for the 20" x 20" glass panes
- 5-10 minutes for the 48" x 48" glass panes and the 25" x 25" used glass panes

Adjustments in failure pressure levels to the "one-minute-to-failure" pressure levels were insignificant in magnitude and were therefore not applied to the data obtained in the Wyle experiments.

4.2.3 <u>Failure Pressure Probability Curve</u> – Sufficient static strength experimental data were obtained from the 65 panes of new glass to allow construction of a failure pressure probability curve for each of the two pane sizes. These curves are shown in Figure 4-3 for pressure levels normalized to a common mean value and standard deviation. The table which is included in the figure defines the actual mean values and standard deviation for failure pressure level of the two sizes of glass panels.

Utilizing these two probability distributions, a reasonably smooth curve can be constructed for the (approximate) failure pressure probability for any size of glass panel; this curve is also shown in Figure 4-3.

4.2.4 <u>Non-linearity of Glass Behavior</u> – During static strength testing of the 48" x 48" single strength glass panes, it was observed that prior to failure the central deflection of the glass was approximately five to ten times its overall thickness (which varied from 0.087" to 0.1" over all glass samples).

From plate theory it is known that deflections of this magnitude cause the middle plane of the glass pane to stretch (i.e., the membrane effect), thereby causing the effective stiffness of the glass pane to behave non-linearly with respect to the applied load. Membrane stress may significantly alter the overall stress distribution at failure, thus influencing the actual failure mechanism; in addition, the associated non-linear stiffness may significantly effect the response levels of the glass panes when exposed to sonic boom overpressure.

Previous analytical and experimental studies, reported in Reference 11, have been conducted to evaluate the effects of non-linearity of glass behavior. Similar experiments were conducted during the present investigation to check the consistency of results for practical boundary conditions against the results of Reference 11. The clamped edge experiments were conducted to assess the influence of edge conditions on the degree of non-linearity. As a cross-check, different experiments were performed for constant edge conditions; the two sets of experiments produced consistent results. Load-versus-deflection curves obtained from these experiments are shown in Figure 4-3. The non-dimensional load parameter and non-dimensional deflection parameter are identical to those utilized in Reference 11, and thus the experimental results are directly comparable. Figure 4-4 shows the load versus deflection characteristics for clamped edges, simply supported edges, and the rubber-putty support. The curve presented in Reference 11 is also included in this figure for comparison.

	<u>.</u>	Static Failure Pressure			
Legend	Dimensions	Mean	Standard Deviation		
	48" × 48"	25.6 psf	σ = 4.5 psf		
	?0" × 20"	239.0 psf	σ = 72.5 psf		









) 32

it is observed in Figure 4-4 that clamped edges result in a greater non-linearity in stiffness behavior than the simply supported edges; the rubber-putty edge support is considerably more linear than the other two support conditions.

4.3 Sonic Boom Testing of Glass Specimens

The objective of the sonic boom test program was to evaluate the cummulative damage of glass subjected to repetitive sonic booms. A total of thirty-six tests were conducted. However, due to a high percentage of glass breakage which occurred during initial pressure calibration stages, only eight sets of sonic boom test data are considered usable.

In order to minimize the effect of test variables associated with edge support conditions on the test results, glass specimens were mounted in a standard wooden frame with smooth supporting surfaces on four sides. Details of the sonic boom operations and the descriptions on specimens and fixtures are presented in the following sections.

4.3.1 Description of Test Specimen an ⁴ Fixture – Test specimens used in the sonic boom test consisted of single strength glass with typical dimensions of $48" \times 48" \times 3/32"$. Each specimen was cut from an original sheet of glass which had a standard dimension of $54" \times 48" \times 3/32"$. Specimens were examined for surface and edge finish conditions. In general, most specimens exhibited no apparant surface flaws, but a few of the specimens showed certain edge imperfections which appeared in the forms of edge ripples. However, the specimens selected for testing consisted of those with no apparant defects on the surface or along the edges.

Each specimen was mounted in a rectangular wooden frame which had a net opening of 46 $1/2" \times 47"$. The details of the wooden frame is shown in Figure 4-5. Each specimen was held to the frame by 4 1/2" thick wooden strips which were bolted to the wooden frame by 3/8" diameter bolts, as shown by the typical sectional view in Figure 4-5(b). The wooden frame was, in turn, held against the steel fixture by tightening 3/8" diameter hex screws through corresponding steel anchoring plates as shown in Figure 4-6. The general arrangement of the test set-up is shown in Figure 4-7.

4.3.2 Test Procedures and Methods – The test procedures employed in the sonic boom test program included the sine sweep test and the sonic boom test. The sine sweep test was conducted at a relatively low pressure level and it was used to determine the resonant ^r equencies of the test specimens. (Such an acoustic test can be performed in the simulator in the same manner as a sonic boom test). The response signals of each specimen were monitored by a small accelerometer located at the center of the panel. In general, the measured fundamental frequencies were approximately 30 Hz and distinctive peak response amplitudes were observed at higher resonant frequencies. A typical sine sweep response curve is shown in Figure 4-8. Thus, the sine sweep signal provided a convenient check to examine the condition of a test specimen after it was mounted in the simulator. For example, Figure 4-9 shows the sine sweep response of a specimen which had a crack at the lower right corner. The early detection of flaws in specimens has significantly reduced the risk of obtaining invalid data.

33

State of the second second







Figure 4–6. Method used to Fasten Wooden Frame to Steel Test Fixture

States and a state of the state

35



Figure 4–7. General View of Glass Testing Arrangement (Note Broken Glass Pane)



Frequency, Hz





8b vesteration Responses ab

Two different sonic boom testing methods were used in the tests. The first method employed the "tuning" technique to tune the duration of an N-wave, which is a harmonic of the fundamental period of the test specimen, so that maximum responses of a test specimen could be achieved. The tuning process was carried cut at low excitation levels to minimize the possibility of accidental glass breakage. However, due to difficulties encouriered in stabilizing the line pressure and also the output signals of the waveform synthesizer, it was not possible to obtain satisfactory acoustic waveforms with durations less than 120 milliseconds. Therefore, only one test was performed under the "tuned" condition. The alternate method employed a fixed wave duration of 400 milliseconds. The complexities of frequency tuning were eliminated and clean N-waves were obtained for various overpressure levels. A total of seven tests were conducted in this manner.

4.3.3 <u>Results of Sonic Boom Tests</u> — The results of the sonic boom tests are summarized in Table II. Notice that the "tuning" method was used on test Number 1 only. Test Numbers 2 through 8 used a fixed wave duration of 400 milliseconds.

Test Number 1 employee the tuning technique to adjusi the acoustic wave form to approximately 162 milliseconds, which was five times the funcemental period of the test specimen. The net overpressure level was adjusted to 4 to 4.6 psf. A total of 1400 booms was applied to the test specimen. No visible damage was observed at the end of the test. The net overpressure level for Test Number 2 was set at 22.5 psf which was approximately equal to the mean static failure pressure (22.6 psf) obtained from the static test program. The test specimen failed after 40 booms. In Test Number 3, the overpressure level was adjusted between 13 to 16 psf. A total of 10,000 booms were applied but no visible damage to the specimen was observed at the end of the test. The same specimen was used in Test Number 4, but the overpressure level was increased to 24 psf and the specimen failed at the end of 87 booms.

From the test results obtained from test numbers 1 through 4, it was obvious that, for overpressures under 16 psf, test specimens probably would not fail within 10,000 booms. Hence the decision was made to select a pressure level that would cause a breakage in less than 1000 booms. Consequently, the overpressure was adjusted between 18 to 20 psf in test number 5, and the specimen failed at the end of 490 booms.

In Test Number 6, the coerpressure was adjusted between 18 to 20 psf and the specimen lasted for 435 booms. The specimen used in Test Number 7 broke at the substantially low overpressure of 13 psf. The failure occurred while attempts were made to increase the pressure to a higher level. A total of 37 booms was accounted for in this test. Test Number 8 was conducted at 19.5 psf level. The specimen failed after only two booms.

Typical acoustic and acceleration response signals for test numbers 1 through 8 are presented in Figures 4-10 through 4-17, respectively.

TABLE II - SONIC BOOM TEST DATA OF 48" × 48" × 3/32" GLASS SPECIMENS

Test Number	Net Overpressure ΔP, psf	Wave Duration Milliseconds	Number of Booms Applied	Figure Number Showing Partial Test Record	Remarks
-	4.0-4.6	162	1400	5	No Failure
7	22.5	400	40	Ŷ	Failure
ю	13-16	400	10,000	7	No Failure
ষ	24	400	87	œ	Failure
5	18-20	400	490	6	Failure
\$	18-20	400	435	0	Failure
7	13	400	37	-	Failure
8	19.5	400	2	12	Failure

i

۱











Figure 4-12. Acoustic and Accelerometer Responses of Sonic Boom Test Number 3

NOT REPRODUCIBLE





NOT REPRODUCIBLE

45

-XII COM



Vertical Scale: 1 cm = 11.7 psf Horizontal Scale: 1 cm = 100 m.s.

(a) Acoustic Response of Microphone Number 1

NOT REPRODUCIBLE



Vertical Scale: 1 cm = 1.17 psf Horizontal Scale: 1 cm = 100 m.s.

ł

(b) Acoustic Response of Microphone Number 2





Vertical Scale: 1 cm = 11.7 psf Horizontal Scale: 1 cm = 100 m.s.

(a) Acoustic Response of Microphone Number 1





Vertical Scale: 1 cm = 1.17 psf Horizontal Scale: 1 cm = 100 m.s.

I.

(b) Acoustic Response of Microphone Number 2





Vertical Scale: 1 cm = 11.7 psf Horizontal Scale: 1 cm = 100 m.s.

(a) Acoustic Response of Microphone Number 1

NCT REPRODUCIBLE



Vertical Scale: 1 cm = 1.17 psf Clorizontal Scale: 1 cm = 100 m.s.

١

ŧ

(b) Acoustic Response of Microphone Number 2



4.4 Discussion of Test Results

For the convenience of discussing the results obtained from the test program, the static and sonic boom data are summarized in Figures 4–18 and 4–19, respectively. The design criteria for single strength glass recommended by Pittsburgh Plate Glass Company (Reference 10) for both the static and sonic boom loadings are also presented in Figure 4–18 for the purpose of comparison. The conclusions drawn from the test results may be stated as follows:

Static Testing

- Edge support conditions have significant effects on the nonlinear stiffness of glass, thereby influencing the magnitude of static breaking pressures.
- Wyle static strength data appears to be low relative to the PPG curves. The phenomena might be attributed to the effect of rubber and putty edge conditions used in the majority of the tests and also the significant increase in the moisture content on glass surface due to water column loadings on the 48" x 48" x 3/32" specimens.
- The aging effect on used glass due to natural environments is quite apparant.

Sonic Boom Testing

- Under 4 psf overpressure level, the probability of failure of single strength glass under repetitive sonic boom exposure is extremely small.
- The strength endurance limit for the 48" x 48" x 3/32" specimens is estimated to be in the range of 14.5 to 16 psf. This value may be used as the lower bound for the glass family for all practical purposes.

Since the sample sizes used in the experimental program were extremely small, the above conclusions may bear little statistical significance as to be of practical application. There-fore, more tests would be required to improve the confidence level of the sonic boom test data. Nevertheless, valuable experience has been gained and can be utilized to provide guidelines for planning future test programs.



Figure 4.18. Summary of Static Testing Data





Figure 4–19. Summary of Repetitive Sonic Boom Test Results

5.0 EFFECT OF SONIC BOOMS ON GLASS BREAKAGE

5.1 Introduction

Glass breakage due to sonic booms, in general, may be grouped into two categories: incipient breakage; and cumulative fatigue damage. The incipient breakage occurs whenever stress levels in glass exceed their ultimate limits. Such overstressed conditions may be induced by three possible conditions described as follows:

- Direct Sonic Boom Loading Effects: Sonic booms with high overpressure levels would usually result in higher stresses in glass. However, certain critical stress levels could also be introduced due to the dynamic amplification effects caused by matching sonic boom waveforms.
- Effects of Mounting Systems: Distorted frames and the presence of stress raisers are the additional factors which would cause intensity stress levels under sonic boom excitations.
- Effects of Glass Aging: The prolong exposure to natural environments would lead to the reduction of glass breaking strength. The degree of strength reduction depends on the severity and the frequency of environmental variations. (Note, that existing old glass windows have survived natural environments and may therefore represent the higher strength members of the original old glass population).

Consequently, sonic booms are not solely responsible for all of the incipient failures occurring in glass; however, under certain circumstances, they are indirectly responsible for triggering failure mechanisms which initiate cracks. The cummulative damage failure is attributed to structural fatigue in glass. Unfortunately, present knowledge on the characteristics of glass fatigue under repetitive sonic boom loadings is quite limited. Adequate approaches towards solving this problem are still under various development stages and would require more effort and time before any workable techniques could be adopted for predicting fatigue damage in glass.

For the purpose of compiling present knowledge on solving glass breakage problems, attempts have been made in this section to review available test data obtained from previous overflight programs and to summarize results of existing analytical and statistical methods for potential application on glass related to the following areas:

- Design criteria for sonic booms
- Incipient glass damage criteria
- Glass breakage probabilities under normal and sonic boom environments

A brief discussion is also presented on the utilization of a statistical model to interpret test results obtained from limited number of experiments. The possibility of applying this method for planning future experimental programs is also outlined.

5.2 Previous Experimental Results

Previous sonic boom experimental programs have generally fallen into two major categories: full-scale supersonic overflight programs, and the development of sonic boom simulation techniques. Most of these programs have been concerned either with the responses of buildings as a whole, i.e., the structural responses of the walls, floors and the roof, etc., or with the community response and the nature of any damage claims. Relatively few studies have concentrated on the response of glass window panes to sonic boom overpressures.

One of the marliest systematic studies of the dynamic behavior of glass was performed by Freynik (keterence 12). A 3 foot square double strength glass pane of 1/8" thickness was mounted onto a test cubicle having a volume of 15 cubic feet. The fundamental frequencies of the glass pane, freely suspended, and mounted onto the test cubicle, were 21 Hz and 35 Hz, respectively. Strain gages were mounted on both sides of the glass to measure both membrane and bending strains, and the stresses were calculated using values of 1×10^7 lb/in² and 0.23 for the modulus of elasticity and Poisson's ratio, respectively. A typical result for static loading is shown in Figure 5-1 where the variations in membrane and bending stresses are plotted as a function of static pressure.

The dynamic stress resulting from window exposure to random noise concentrated in a one-third octave band is shown in Figure 5-2. For this series of experiments the one-third octave center frequency was 35 Hz, i.e., the input energy was concentrated at the fundamental resonance of the glass pane-cavity system. Figure 5-2 describes the variation in the peak tensile stress as a function of the overall sound pressure level in the one-third octave band. The horizontal ine at approximately 4,000 lb/in² represents the suggested peak stress level above which glass breakage is expected to occur (References 13 and 14). At low sound pressure levels it was concluded that the membrane stresses were negligible and the system responded in the fundamental mode. At high sound pressure levels however, the membrane stresses were found to be comparable in magnitude to the bending stresses, and higher modes of vibration were severe.

The inherent variability of the breaking strength of glass, coupled with random variations in the sonic boom N-wave for a given aircraft, resulted in an appreciable variation in sonic boom damage for a given type of window design. This is illustrated in Figure 5-3 by the data from one series of controlled tests of sonic boom damage for conventional 3' x 3' window panes employing double strength (1/8"), and single strength (approximately 0.09") (Reference 14). No failures were observed for overpressures less than 20 lb/sq.ft. Even at overpressures in the range of 80-100 lb/sq.ft., approximately 35 percent of the windows survived without failure. On the other hand, results from other tests have shown that windows which were intentionally cracked before exposure to a sonic boom would fail at overpressures as low as 7.6 lb/sq.ft. (Reference 15).



Figure 5-1. Measured Bending and Membrane Stresses at Center of Test Window Under Static Pressure Loading (Reference 12)



SPL, dB (in one-third octave band centered at 35 Hz)

Figure 5-2. Measured Peak Tensile Stresses at Center of Window as a Function of the Sound-Pressure Level in a One-Third Octave Band Centered at 35 Hz (Reference 12)

∆p _o , Ib∕sq ft	Number of Windows Exposed	Турі	Airplane cal Signa	A I tures _		B COSSO	
0-20	0						
0-20	24						
22.40	41	V////	[[[[[]]]]]]]]]]]]]]]]]]]]]]]]]]]]]]]]]]				
20-40	41						
40-60	22	V////					
40-00	35						
40.00	16				///		
00-80	11						
80-100	12	V///					
	12				3		
		L	20	40	60	80	J

Window Failures - Percent of Number Exposed

Figure 5–3. Summary of Results from Window Breakage Tests (Data from Reference 16)

Results from a number of different test programs on sonic boom damage of windows have been summarized in Reference 16. The results are shown in Figure 5-4 by a plot of a normalized loading parameter $p_0 (\alpha/h)^2$ as a function of the product $f_{1,1} \tau$ where α/h is the panel span to thickness ratio, $f_{1,1}$ is the fundamental natural frequency, and τ is the duration of the positive phase. A theoretically predicted value for the boundary between damage and no damage, derived in Reference 17, is also shown.

In a recent report summarizing the results of experiments conducted in Oklahoma City and White Sands (Reference 1), the possibility of Helmholtz resonance occurring when all doors and windows of the test houses were closed was examined. This was carried out in an attempt to explain an observed rapid decay of vibrations of a 5' x 10' window resulting from closed doors and windows. Experiments with a door open showed persistent vibration of the window for many cycles. Calculations showed that a Helmholtz type resonance had actually occurred but it was concluded that, in general, the probability of this resonance frequency coinciding with large window frequencies and causing damage was low.

5.3 Suggested Criteria for Glass Breakage

Revised criteria for sonic bcom damage of windows have recently been proposed by Sutherland (Reference 18) based upon the experiments described in Reference 16 and 17. Sutherland's revised criteria were formulated as follows:

A critical examination of the data and test procedures for the results shown in Figure 5-4 indicate that a more conservative value is desired for this damage criteria line. Based on the non-linear load-deflection curve, as shown in Figure 5-5, the stress at failure is estimated (Reference 19) to be about 8000 psi. The recommended design value for breaking strength for regular window and plate glass for sonic boom loads is about 6300 psi, (Reference 18). Thus, one reduction factor to be applied will involve reducing the criteria to allow for a more conservative breaking strength.

Further examination of the procedures employed for the sonic boom tests reveals that a 16 cubic foot sealed cavity was placed behind the panel to insure a positive pressure differential across the window pane. However, this has the effect of increasing the effective stiffness of the panel due to the added "acoustic stiffness". The computed relative change in effective panel stiffness with the cavity is 1.77. A similar stiffening effect was observed experimentally in Reference 12. The net effect of this added stiffness would have been to require a correspondingly higher overpressure to achieve the expected failure stress. This, then, provides a second correction factor which would tend to reduce the damage criteria level indicated in Figure 5-4.

Combining these two corrections, the original "no damage" criteria for the parameter $p_0 (\alpha/h)^2$ at 1.8 x 10⁶ lb/sq.ft (for values of $f_{1,1} \tau > 0.6$) is reduced to the following:

$$P_0\left(\frac{\alpha}{h}\right)^2 \le 0.8 \times 10^6 \text{ lb/sq.ft}$$



 $f_{1,1}$ τ - Fundamental Frequency times Duration of Positive Phase

Figure 5-4. Summary of Window-Glass Breakage Experienced due to Sonic Booms. Load specified by the normalized parameter $p_{n} (\alpha/h)^2$ where α/h is the ratio of a side Length (α) to thickness (h). Data from a summary in Reference 16.



Figure 5-5. Static Load - Deflection Curve for 3ft x 3ft x 1/8 in Window Pane (Data from Reference 16)

. **.** . . .

- A contraction overchescure + 10 sq 11
- c) = characteristic size of zoarcy/mately savarely/raaw
- s i gamerna, measurana, e ma
- surar an of positive prices

For verves of sonio poem overpressure within the proposed limits for the SST and for withows. Wrissellength to thickness conio meets standard building bode requirements. This criteric Indicates that normal quality withdows should not be damaged (Reference 10).

Based upph the CK phoma City and White Sanas test data. Wiggins (Reference 1) has suggested the maximum safe ground overpressures for plate and window glass as shown in Figure 340. This Figure , which shows the relation between glass area , glass thickness and safe overpressure is a modified version of the Pittsburgh Plate Glass Company's recommended practice (Reference 101).

5.4 Design Guide for Evaluating the Effects of Sonia Booms

In general, a window pane can be treated as a uniform rectangular plate having various boundary conditions. The dynamic response is considered to be due primarily to the application of the shockwave, i.e., the secondary effects arising from the interaction of the plate with the rest of the building are usually neglected. The dynamic response of uniform beams and rectangular plates having simply supported and clamped edge conditions and subjected to various types of pressure pulse has been studied exclusively by Cheng (References 6, 20 and 21). These studies include the effect of ideal N-shaped pressure pulses, traveling N-waves and traveling pressure waves of arbitrary shapes. Similar studies, including some experimental results have been presented by Crocker (Reference 22), and the agreement between Cheng's results and Crocker's results is remarkably good. In order to derive simplified methods, Cheng studied the theoretical damped dynamic responses of structural elements exposed to a group of typical sonic boom signatures (Reference 5). The essential results have been presented in terms of the dynamic amplification factor (DAF), defined as the ratio of the maximum dynamic moment to the static moment due to the uniform peak pressure developed at the same point in the structure.

It has been shown that the magnitude of the DAF depends upon the exact shape of the boom signature and upon the period ratio R. Since the DAF curves are asymptotic at large values of the period ratio R, the DAF can be assumed to be dependent only upon the fundamental period ratio (R_1) if the exact shape of the boom signature is known. However, in almost every practical case, the exact shape of the boom signature is difficult to determine accurately. In order to avoid the requirement that the boom signature shape be known, Cheng (Reference 6)

59

BEST AVAILABLE COPY



Figure 5–6. Maximum Safe Predicted or Measured Average Ground Overpressure for Plate and Window Glass (Reference 5)

1 million and

devised a design approach to predict the magnitude of the DAF. This design approach, although slightly inaccurate, leads to the determination of the DAF as a function of the fundamental period ratio (R_1) only. To utilize this method, only the magnitude of the peak pressure (p_0) is required.

The design curve resulting fram this method is shown in Figure 5-7. This figure describes the variation of the DAF far a beam at a square plate as a function af the fundamental period ratio R₁. To obtain the dynamic moment acting on the beam or plate, the corresponding daf is simply multiplied by the static moment (which is equal to $p_0 1^2/8$ for a beam or 0.0479 $p_0 a^2$ for a square plate, where $p_0 =$ the peak pressure).

For the purpases of comparison, a similar curve proposed by Crocker (Reference 23) is included in Figure 5-7. The DAF envelope proposed by Crocker (Reference 23) is for use in assessing the structural response due to supersonic transport overflight and is based upon a boam signature similar to the type shown in Figure 3-3(d). A wide variation between the envelopes prapased by Cheng (Reference 6) and Cracker (Reference 19) is abserved, this being due to the fact that Cheng's results include a boom signature having the shape of a sine pulse. If the results for the sine, pulse and the half-cosine pulse are ignored in the computation of Cheng's daf envelopes, then the resulting daf envelope is similar in magnitude to Crocker's results However, the two independent sets of DAF envelopes allow for the estimation of the structural respanse to a wide variety af sonic boom signatures.

5.5 Glass Breakage Due to Normal Environments

The determinatian of glass breakage probability under normal environmental conditians would require the knawledge of the distribution of glass population for regions where SST overflights are planned. Ta undertake this task in an efficient and economical manner, an adequate sampling method (Reference 24) is needed to acquire statistical information for a typical glass neighborhood. For example, one may choose a number of cities among several geographical areas, and select a certain number of households within each city to survey; or one may choose a state which is considered to be typical of all probable environmental conditions of those regions and carry out sample surveys in that state. In short, methods used to implement a survey objective are numerous, and the choice of a particular method depends entirely an the preference of the responsible individuals and the available fundings. Normally, a program with a large sample size would be very costly; but on the other hand, the data obtained from a small sample population may be biased and misleading. Hence the optimum approach is to define a reasonable objective and then design the survey program accordingly.

During the performance of this contract, a preliminary survey of the glass population in Huntsville, Alabama, was conducted. A total of twenty buildings were surveyed, and the distribution of these buildings surveyed is given as follows:




Type of Building	No. of Buildings
Commercial	10
Multiple Dwelling	3
Single Family Dwelling	7

The major causes of glass breakuge are summarized as follows:

•	Commercial Buildings:	a)	Burglary
		ь>	Winds
		c)	Walk-in
		d)	Shopping Cart
•	Multiple Dwellings:	a)	Winds
		b)	Accidental Slamming
		c)	Cold Weather
		d)	Accidents
•	Single Family Dwelling:	a)	Rocks thrown by Mower
		Ь)	Baseball
		c)	Accidents

However, it was considered that the sample size was not large enough to provide a fair description of glass breakage in the neighborhood. Additional effort would be required to define the glass distribution and the normal glass breakage probability of Huntsville.

A glass survey was made on a nationwide scole in 1964 (Reference 25). Twenty consumer panels, eaching consisting of 1000 families, were forwarded questionnaires by mail. The results of the survey obtained from the 21 percent respondent who purchased and used glass in that year are summarized as follows:

- Repairing 77 percent
- Replacement, Unbroken 6 percent
- New Additions 7 percent
- Alteration 6 percent
- No use
 4 percent

Recently, in Reference 26, an attempt was made to convert the above glass consumption rate to estimate the normal glass breakage rate for 1964. In the computation, the 4 percent "no use"

category was converted into that of the "repaired" and obtained the modified percentage of "repairing" at 80.2 percent. This value was multiplied by the percentage of respondents who used glass (21 percent), that gave 17 percent of U.S. households in which glass repairs were made in 1964. The information presented herein provides a gross picture of the glass breakage rate for that particular year. No known development has been reported in the "normal" breakage areas.

5.6 Glass Breakage Probability Due to Sonic Booms

Because of the brittle nature of the glass and other uncertain factors surrounding them, the prediction of glass damage to sonic booms could only be achieved by employing statistical approaches. In Reference 27, a study was made on the probability of glass failure under 2 psf overpressure. The analysis was based on two different assumptions that the strengths of window glass were either normally or log-normally distributed. The calculated probabilities were found to be 0.0002 and 10⁻⁹, respectively, for the two cases indicated above. However, claim data show that the probability of damage is in the order of 10⁻⁶. These values may suggest that the actual strength distribution of window glass might lie somewhere between the normal and log-normal. In Reference 5, attempts were made to fit available data on glass damage (References 28, 29, and 30) and the estimated overpressure levels with regression curves on log-normal papers. The final results have shown that these curves fit the test data satisfactorily at high overpressure levels, but no conclusive statement could be made on damage probability for overpressures under 3 psf.

Due to the lack of adequate test data from previous overflight programs, it is not feasible at this moment to formulate suitable statistical models for predicting cumulative damage on glass subjected to repetitive sonic booms. It is also unfortunate that the amount of test data taken during the present test program is limited in number; consequently, they could not be used to formulate the frequency distribution function for predicting failure. However, attempts have been made to utilize a non-parametric statistical model (Reference 31) to interpret test results in the future if more repetitive sonic boom test data becomes available.

Two basic assumptions are needed in applying the theorem; they are:

- Test specimens must be selected at random
- The frequency function of the basic test variables (i.e., the breaking strength of glass, number of booms to failure, etc.) must be continuous.

If N panes of glass were tested for a given overpressure level, and the maximum and minimum number of booms (designated here as the extreme values) required to break these test specimens have been obtained, then the probability, P, that a certain percentage of the total glass population (similar to the test specimens), H, would fall within the extreme values is given by the following equation:

$$P(H) = N(N-1)H^{N-2}(1-H)$$

A set of parametric curves used to represent the relationship among the three variables P(H), N and H is presented in Figure 5–8.

Far example, if 10 panes af $48" \times 48" \times 3/32"$ glass were tested at an overpressure level af 20 psf, and the extreme value in terms af number af booms to failure were found to be 400 and 500, respectively, then one may state that the probability is 95 percent, and that 65 percent of the glass population would fail between the extreme limits as indicated abave. Or, that the probability is 98.9 percent that 50 percent of the glass population would fail between the extreme limits, etc. It is important to note that the impravement in probability and population coverage can be achieved by employing more specimens in the tests.

and the second se



1

•

P. N. Statistics



6.0 CONCLUSIONS

The main objective of this program was to determine the cumulative damage effect of glass to repetitive sonic boom disturbances. In order to evaluate such phenomena experimentally, a pneumatic-pistonphone simulator was developed and used successfully to test glass specimens under simulated sonic boom overpressures. A limited amount of test data were obtained, however, preliminary understanding has been gained regarding the cumulative damage effect of glass to repetitive sonic boom loadings. The conclusions drawn from the research effort are summarized as follows:

- Sonic Boom Simulator It is feasible to apply the pneumatic pistonphone concept to generate pressure disturbances for simulating sonic booms. The pressure signatures can be controlled and reproduced reasonably well to synthesize various sonic boom waveforms. The simulator can be used efficiently to perform repetitive sonic boom testing of structural panels.
- Cumulative Damage Effects of Glass Specimens to Repetitive Sonic Boom Overpressures – From the results of the repetitive test data, it is clear that: the probability of glass damage to speciment subjected to overpressure levels of less than 4 psf is quite small; the endurance limit for the specimens tested is estimated between 14 to 16 psf. But the test results suffer from statistical accuracy due to a small number of glass specimens tested. Hence, these data could not be utilized to formulate a statistical model to predict glass damage.
- Effect of Aging on Glass Strengths From the results of static test data, it appears that the effects of natural environments have reduced the breaking strengths of the used glass as compared to that recommended by current design practices.
- Typical Glass Neighborhood Survey It is felt that such a neighborhood survey should be conducted on a larger scale to cover various parts of the nation, so that the glass distribution spectra of different environmental conditions can - properly defined, and the results of such a survey would provide more accurate information on glass damage probability.

REFERENCES

- Wiggins, J.H., "The Effects of Sonic Boom on Structural Behavior A Supplementary Analysis Report," Contract No. FA-SS-65-12, John Blume and Associates Res. Div., October 1965 (AD 475 662).
- Blume, J.A., et al., "Response of Structures to Sonic Booms Produced by XB-70, B-58 and F-104 Aircraft," J.A. Blume and Associates Research Division, October 1967 (AD 662 003).
- Schwartz, I.R., Editor, "Second Conference on Sonic Boom Research," NASA SP-180, May 1968.
- 4. Seebass, A.R., Editor, "Sonic Boom Research," NASA SP-147, pril 1967.
- 5. Wiggins, J.H., "Effects of Sonic Boom," J.H. Wiggins Company, Palos Verdes Estates, California, July 1969.
- 6. Cheng, D.H., and Benveniste, J.E., "Dynamic Response of Structural Elements Exposed to Sonic Booms," NASA CR-1281, March 1969.
- 7. Wadsworth, J., "Bibliography on Sonic Bangs," Royal Aircratt Establishment, Library Bibliography No. 287, January 1968, AD 837 824.
- Kryter, V.D., et al., "Definition of the Effects of Booms from the SST on Structures, People and Animals," Stanford Research Institute Report for the National Sonic Boom Evaluation Office, Department of Air Force, Under Contract AF49(638)-1690, June 1966.
- 9. Uniform Building Code, Vol. I, International Conference of Building Materials, Pasadena, California, 1964.
- 10. PPG Industries, "Glass Product Recommendations Structural," Technical Service Report No. 101.
- Iverson, J.H., "Summary of Existing Structures Evaluation, Part II: Window Glass and Applications," Stanford Research Institute, Menlo Park, California, December 1968, AD 687 294.
- 12. Freynik, H.S., "Response of Windows to Random Noise," Sound, Vol. 2, No. 3, June 1963.
- 13. Mayes, W.H. et al., "Application of a Blowdown Wind Tunnel for Large-Scale Acoustic Environmental Testing," Sound, Vol. 1, No. 4, 1962.
- Martin, C.W., "Fracture of Gypsum Plasters and Cement Mortars by Dynamic Loading," Air Force Weapons Laboratory, Tech. Report AFWL-TR-65-140, Dec. 1965.

- 15. "Preliminary Data, Sonic Boom Structural Response Program," White Sands Missile Range, New Mexico, March 1965.
- 16. Parrott, T.L., "Experimental Studies of Glass Breakage Due ta Sonic Baoms," Sound, May-June 1962.
- 17. ARDE Associates, "Response of Structures to Aircraft Generated Shack Wc WADC Tech. Report 58-169, U.S. Air Force, April 1959.
- Sutherland, L.C., "Sonic and Vibration Environments for Ground Fac Design Manual," NASA Contract NAS8-11217, Wyle Luborataries Res Report WR 68-2, March 1968.
- 19. Roark, R.J., "Formulas for Stress and Strain," McGraw-Hill Book Co., N.Y.
- Cheng, D.H., and Benveniste, J.E., "Transient Response af Structural Elements to Travelling Pressure Works of Arbitrary Shape," Presented at the 5th U.S. National Congress Applied Mech. 1966, Inst. J. Mech. Sci., 8, 1966.
- Cheng, D.H., and Benveniste, J.E., "Sanic Boom Effects on Structures A Simplified Approach," Trans. N.Y. Acad. Sci. Ser II, Vol, 30, Na.3, January 1968.
- 22. Crocker, M.J., "Multimode Response af Panels to Narmal and to Traveling Sonic Booms," J. Acoust. Soc. Am., Vol. 42, Na. 5, 1967.
- 23. Cracker, M.J. and Hudsan, R.R., "Structural Response to Sonic Baoms," J. Saund and Vibration, Val. 9, Na. 3, May 1969.
- 24. Hansen, M.H., et al., "Sample Survey Methads and Theary Vois. I and II," Jahn Wiley and Sans, Inc., New Yark 1962.
- 25. Plohr, G.W., "A Market Not to be Ignared," Glass Digest, Navember 1966.
- 26. Private Communication fram Mr. J.W. Reed ta Dr. E.F. Cax, March 11, 1970.
- 27. Seaman, L., "Respanse af Windows ta Sanic Booms," Interim Technical Report 7, Stanford Research Institute, Menia Park, Califarnia, June 1967.
- Maglieri, D.J., et al., "Graund Measurements of Shock Wave Pressure for Fighter Aircraft Flying at Very Law Altitudes and Camments an Associated Response Phenamena," AD 326 913 (December 1961).
- 29. Wiggins, J.H., "The Effects of Sanic Boom on Structural Behaviar," John A. Blume and Associates Research Division, AD 475 662, October 1965.

- Blume, J.A., et al., "Response of Structures to Sonic Booms Produced by XB-70, B-58 and F-104 Aircraft," Final Report to National Sonic Boom Evaluation Office, J.A. Blume and Associates, AD 662 003, October 1967.
- 31. Hoel, P.G., "Introduction to Mathematical Statistics," Second Edition, John Wiley and Sons, Inc., New York, 1960.

BIBLIOGRAPHY

Cox, E.F., et al., "Damaging Air Shocks at Large Distances from Explosions," Operation Buster-Jangle, Sanaia Corporation WT-303, April 1952.

Aleck, E.J., et al., "Response of Structures to Aircraft Generated Shock Waves," W.A.D.C. TR 58–169, April 1959.

Parrott, T.L., "Experimental Studies of Glass Breakage Due to Sonic Booms," Sound, 1, (3), pp. 18-21, May-June 1962.

"Experimental Determination of Gas Main Stresses from Sonic Booms," Brewer Eng. Labs. Report 249, August 1962.

Maglieri, D.J., and Morris, G.J., "Measurements of the Response of Two Light Airplanes to Sonic Booms," NASA TN D-1941, August 1963.

Hoover, J.W., and Ross, C.A., "Sonic Booms and Large Glass Windows," American Registered Architect, Convention Issue, 1963.

Cawthorn, J.M., "Some Sonic-Boom Induced Building Responses", (first presented at the sixtysixth meeting of the Acoustical Soc. America, Ann Arbor, Michigan, 6-8 November 1963), ARC Report 25949, May 1964.

Power, J.K., "Sonic Boom Effects on Light Aircraft, Helicopters, and Ground Structures," Fed. Aviat. Agency, Office of Supersonic Transport Div., ARC Report 25985, June 1964.

McKinley, R.W., "Response of Glass in Windows to Sonic Booms," Materials Research and Standards 4:594–9, ASTM Annual Meeting Sixty-Seventh Chicago, June 21–26, 1964.

Power, J.K., "Some Results of the Oklahoma City Sonic Boom Tests," Materials Research and Standards, <u>4</u>, (11) November 1964, 617–23. ASTM Annual Meeting, Sixty-Seventh Chicago, June <u>21</u>–26, 1964.

Mayes, W.H., and Edge, P.M., "Effects of Sonic Boom and Other Shock Waves on Buildings," Materials Res. and Standards, 4, (11) November 1964, 588–93. ASTM Annual Meeting, Sixty-Seventh Chicago June 21–26, 1964.

Cheng, D.H., "Some Dynamic Effects of Sonic Booms on Building Structural Elements," NASA LWP-25, Aug. 1964.

"Sonic Boom Structural Study."- Press Briefing. FAA Office of Deputy Adminstrator for Supersonic Transport Development, Nov. 1964.

"National Sonic Boom Study Program - Phase II, Structural Response Test," FAA Report ARC 26776, Nov. 1964.

Ramsay, W.A., "Damage ta Ottawa Air Terminal Building Produced by a Sanic Baam," Materials Res. and Standards, 4, (11) 612–6, Nov. 1964.

Newberry, C.W., "Measurement of Sonic Bangs and Their Effect an Typical Buildings," G.B. Building Research Station Note No. B180, Materials Research and Standards, <u>4</u>, (11) 601–11, November 1964.

Newberry, C.W., "Measuring the Sanic Boom and its Effect on Buildings," Building Res. Station, Watfard, Herts, U.K., DSIR BRS CP Res. 32, Nov. 1964.

Hilton, D.A., Huckel, V., Steiner, R., and Maglieri, D.J., "Sonic-Boom Expasures During FAA Cammunity-Respanse Studies Over a 6-Month Period in the Oklahoma City Area," NASA Tech. Note D-2539, Dec. 1964.

Hubbard, H.H., and Maglieri, D.J., "Noise and Sonic Boom Consideratians in the Operation of Supersonic Aircraft," AIAA Prep. (64–548), 1964.

Shuman, E.C., "Giant Sanic Boom Juses only Minar Damage to Houses," Mater. Res. and Strand., <u>5</u>, nr. 2, p. 79–80, Feb. 1965.

Andrews, D.K., et al., "Architectural and Engineering Services for Studies of Structural Response to Sonic Booms in Cannectian with the Supersonic Transport Research Program," Andrews Associates Inc., and Hudgins, Thampson, Ball and Associates, Inc., Okla, (Joint Venture). SST 65-1, Vol. 1, Feb. 1965.

"Sanic Boom Structural Response Test Pragram", White Sands Missile Range, New Mexico, Preliminary Data, Nov. 1964–Feb. 1965. Federal Aviation Agency SST–65–4.

"National Sonic Boom Study Pragram - Phase IIB," FAA, ARC Report 26777, March 1965.

"Cracking in Buildings," Building Research Station Note IC 20/65, ARC Report 26950, April 1965.

"Studies of Sanic Boom Induced Damage," NASA CR 227, ARC Report 28653, May 1965.

Parratt, T.L., "Summary of Results of Sonic-Boom Measurements Conducted During Joint FAA-USAF-USFS-NASA Snow-Avalanche Project in the Vicinity of Leadville, Colorado," March 18-20, 1965, NAS LWP-105, May 1965.

Revell, J.D., and Rogers, Thompson, J., "A Study of Mathads for Evaluating Sonic Boom Effects," Lockheed California Co., July 1965.

"Examination of Damage Alleged to have Been Caused by Sonic Booms Produced During Exercise Westminster," Building Research Station Note IC/31/65. ARC Report 28962, August 1965.

Lillard, D.C., Parrott, T.L., and Gallaghen, D.G., "Effect of Sonic Booms of Varying Overpressures an Snaw Avalanches," Tests canducted 18–20 March 1965. Federal Aviation Agency, Washington, D.C., Aug. 1965.

Cheng, D.H., "Dynamic Response of Structural Elements to Traveling N-Shaped Pressure Waves," NASA LWP-147, Sept. 1965.

Wiggins, J.H., "The Effects of Sonic Boom on Structural Behaviour – A Supplementary Analysis Report," FAA SST Report No. 65–18, Oct. 1965.

Weinroth, D.M., "Respanse af Buildings to Sonic Booms," Paper presented at the Acoustical Society of America Sonic Baam Symposium, St. Louis, Missouri, Nov. 3, 1965.

Kryter, K.D., "Labaratory Tests of Physiolagical-Psychological Reactions to Sonic Booms," Paper presented at the Acaustical Society of America Sonic Boom Symposium, St. Louis, Missouri, 3 Nov. 1965. Also published in J. of the Acoustical Soc. of America <u>39</u>, S65–S72 May 1966, Part 2.

Lowery, R.L. and Andrews, D.K., "Acoustical and Vibrational Studies Relating to an Occurrence of Sanic Boam Induced Damage to a Window Glas^e in a Store Front," NASA-CR-66170, 1966.

Kelley, H.L., "Sonic Booms – Ground Damage – Theories of Recovery," J. of Air Law and Cammerce, 32, 596–606, 1966.

Baron, M.L. and Bleich, H.H., "An Investigation of Ground Shock Effects Due to Rayleigh Waves Generated by Sonic Booms," NASA CR 451 Paul Weldlinger Consluting Engr. New York, May 1966.

Zumwalt, G.W., "Computation of the Pressure-Time History of a Sanic Boom Shock Wave Acting on a Window Glass in a Building," Andrews Associates, Inc. NASA-CR-66169, June 1966.

"Noise in Studios from Sonic Booms," British Broadcasting Corporation Research Dept. Engg. Div. RR-B-091. TIL/BR/10374, June 1966.

Kryter, K.D., et al., "Definition Study of the Effects of Booms from the SST on Structures, People and Animals," Stanford Research Institute Report No. 5897, AD 486 641, June 1966.

Maglieri, D.J., Huckel, V., and Parrott, T.L., "Ground Measurements of Shock-Wave Pressure for Fighter Airplanes Flying at Very Low Altitudes and Comments on Associated Response Phenomena," NASA TN D-3443, July 1966.

Cheng, D.H., and Benveniste, J.E., "Transient Response of Structural Elements to Traveling Pressure Waves of Aribitrary Shape," Intern. J. of Mech. Sciences 8, p.607–18, Oct. 1966. Annus, L., "Aircraft Noise and Sonic Boom," FAA Repart AD 801 370, Octaber 1966.

Wiggins, J.H., "Theoretical Study of Structural Respanse to Near-Field and Far-Field Sonic Baoms, Datacraft, Inc. Report Na. 3407–B, AD 66? 893, October 1966.

Richards, E.J., "Investigatian of Buildings Structure Response to Sonic Baoms," I.S.V.R. Memorandum ISAV 165, Dec. 1966.

Benveniste, J.E., and Cheng, D.H., "Dynamic Effects of Sonic Baams on a Beam Loosely Baund to its Supparts," A.I.A.A. Paper 67–14, January 1967.

Crocker, M.J., "Response of Panels to Oscillating and ta Maving Shack Waves," J. Sound and Vibratian, Val. 6, (1), July 1967.

Blume, J.A., et al., "Respanse of Structures to Sonic Baams Produced by XB-70, B-58 and F-104 Aircraft, Based on Sanic Boam Experiments at Edwards Air Force Base," AD 662-003, Oct. 1967.

Crocker, M.J., "Multimode Respanse of Panels to Normal and to Traveling Sanic Booms," JASA Val. 42, Na. 5, pp. 1070–1079, Nov. 1967.

Crandall, S.H., and Kurzweil, L., "On the Rattling of Windows by Sonic Boams," J. Acoust. Sac. Am., Val. 44, Na. 2, pp. 464–472, August 1968.

1 standards

Fillen in success 4

Nixon, C., et al., "Sonic Baoms Resulting trom Extremely Low Altitude Supersonic Flight: Measurements and Observations on Houses, Livestack and Peaple," Wright-Patterson Air Force Base, AMRL-TR-68-52, Oct. 1968.

Carden, H.D., and Mayes, N.H., "Experimental Farced Vibration Respanses of Two Test Houses Used During the Edwards Air Force Base Phase of the National Sonic Boom Test Program," Langley Warking Paper LWP-714, February 1969.

Chen, D.H., and Benveniste, J.E., "Dynamic Response of Structural Elements Exposes to Sonic Baoms," NASA CR-1281, March 1969.

Crocker, M.J., and Hudson, R.R., "Structural Response to Sonic Boams," J. Sound and Vibratian, Vol. 9 (3), May 1969.

Pretlove, A.J., "Acoustic-Elastic Effects in the Response of Large Windows to Sonic Bangs," J. Saund and Vibration, Val. 9, No. 3, pp. 487-500, May 1969.

Yeager, K.E., "Review of Sonic Boom Phenomenology," MTR-1192, The Mitre Corporation. Washingtan, D.C., May 1969.

Bailey, D., "A Sonic Boom Study for the Structural Engineer," Technical Report No. AFWL-TR-66-154, Air Force Weapons Laboratory, Kirtland Air Force Base, New Mexico, March 1967.

Runyan, H.L., and Maglieri, D.J., "Sonic Boom – Its Signature Characteristics," AD 827753, NASA Langley Research Center, Langley, Va., August 1967.

Federal Aviation Agency, "Some Considerations of Sonic Boom," May 1961.

Kane, J.E., et al., "Meteorological Aspects of the Sonic Boom," The Boeing Company, AD 610–463, September 1964.

"Sonic Boom Experiments at Edwards Air Force Base," Interim Report NSBEO-1-67, National Sonic Boom Evaluation Office, Arlington, Virginia, July 1967.

Maglieri, D.J., et al., "Variability in Sonic Boom Signatures Measured Along an 8000– Foot Linear Array," NASA TN D-5040, February 1969.

Powers, J.O., and Maglieri, D.J., "A Survey of Sonic Boom Experiments," Paper prepared for the 1968 Aviation and Space Conference of ASME, June 16–19, 1968, Beverly Hills, California.

Lyster, H.N.C., "A Review of Theoretical and Experimental Information Relating to the Sonic Boom," Aeronautica: Report LR-313, National Research Council of Canada, Ottawa, September 1961.

Maglieri, D.J., et al., "Lateral-Spread Sonic-Boom Ground-Pressure Measurements from Airplanes at Altitudes to 75,000 ft and at Mach Numbers to 2.0," NASA TN D-2021, November 1963.

Tombonlian, R., "Research and Development of a Sonic Boom Simulation Device," NASA CR-1378, July 1969.

Grubb, C.A., et al., "Report on Data Retrival and Analysis of U.S.A.F. Sonic Boom Claims Files," Technical Report No. 4, SRI Project No. ETU-5897, September 1967 (AD 691 496).

Cheng, D.H., and Benveniste, J.E., "Sonic Boom Effects on Beams Loosely Bound to their Supports," Presented at the AIAA 5th Aerospace Sciences Meeting, 1967, Journal of Aircraft, Vol. 4, No. 6, 1967.

Wiggins, J.H., and Kennedy, B., "Theoretical Study of Structural Response to Near-Field and Far-Field Sonic Booms," Final Report, Contract No. AF 49(638) – 1777, Datacraft, Inc., 1966.

Lowery, R.L., and Andrews, D.K., "Acoustical and Vibrational Studies Relating to an Occurrence of Sonic Boom Induced Damage to a Window Glass in a Store Front," NASA CR-66170, 1966.