



AD 748083

AD

CCL REPORT NO. 306

FINAL REPORT

CHLORIDE AND WATER PERMEABILITY OF
AUTOMOTIVE BRAKE HOSE

BY

JULES B. COUNTS

AND

ROBERT G. JAMISON

JULY 1972

DDC
RECEIVED
JUL 19 1972
RECEIVED

THIS DOCUMENT HAS BEEN APPROVED FOR PUBLIC RELEASE
AND SALE; ITS DISTRIBUTION IS UNLIMITED

U. S. ARMY
ABERDEEN RESEARCH & DEVELOPMENT CENTER
COATING & CHEMICAL LABORATORY

Aberdeen Proving Ground
Maryland

Reproduced by
NATIONAL TECHNICAL
INFORMATION SERVICE
U S Department of Commerce
Springfield VA 22151

132

DDC AVAILABILITY NOTICE

Qualified requesters may obtain copies of this report from Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314

THE FINDINGS IN THIS REPORT ARE NOT TO BE CONSTRUED AS AN OFFICIAL DEPARTMENT OF THE ARMY POSITION, UNLESS SO DESIGNATED BY OTHER AUTHORIZED DOCUMENTS.

DESTROY THIS REPORT WHEN IT IS NO LONGER NEEDED. DO NOT RETURN IT TO THE ORIGINATOR.

Accession for

NTIS	Section	<input checked="checked" type="checkbox"/>
GPO	Section	<input type="checkbox"/>
...	...	<input type="checkbox"/>

11

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) U.S. Army Aberdeen Research & Development Center Coating & Chemical Laboratory Aberdeen Proving Ground, Md. 21005		2a. REPORT SECURITY CLASSIFICATION Unclassified	
3. REPORT TITLE CHLORIDE AND WATER PERMEABILITY OF AUTOMOTIVE BRAKE HOSE		2b. GROUP	
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Final Report			
5. AUTHOR(S) (First name, middle initial, last name) Counts, Jules B. Jamison, Robert G.			
6. REPORT DATE July 1972	7a. TOTAL NO. OF PAGES 32	7b. NO. OF REFS 11	
8a. CONTRACT OR GRANT NO. AMCMS Code No. 502E.11.80200		8b. ORIGINATOR'S REPORT NUMBER(S) CCL #306	
b. PROJECT NO. 1T062105A108		9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
10. DISTRIBUTION STATEMENT This document has been approved for public release and sale; its distribution is unlimited. Qualified requesters may obtain copies of this report from Defense Documentation Center.			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY U.S. Army Materiel Command Washington, D. C. 20315	
13. ABSTRACT The object of this study was to determine the chloride and water permeability of hydraulic brake hoses. Permeability parameters measured were time interval, temperature, type of exposure, type of brake hose composition, type of brake fluid and the cation linked with the chloride ion. It was found that sufficient chloride and water will permeate brake hoses to initiate corrosion of metal parts in the conventional brake system. The extent of permeability is greatly reduced in systems containing silicone fluids. Details of illustrations in this document may be better studied on microfiche			

DD FORM 1473

REPLACES DD FORM 1473, 1 JAN 64, WHICH IS OBSOLETE FOR ARMY USE.

UNCLASSIFIED

Security Classification

UNCLASSIFIED

CCL REPORT NO. 306

FINAL REPORT

CHLORIDE AND WATER PERMEABILITY OF
AUTOMOTIVE BRAKE HOSE

BY

JULES B. COUNTS

AND

ROBERT G. JAMISON

AMCMS CODE NO. 502E.11.80200

DEPARTMENT OF THE ARMY PROJECT NO.
1T062105A108

U. S. ARMY
ABERDEEN RESEARCH AND DEVELOPMENT CENTER
COATING AND CHEMICAL LABORATORY
ABERDEEN PROVING GROUND
MARYLAND 21005

THIS DOCUMENT HAS BEEN APPROVED FOR PUBLIC RELEASE
AND SALE; ITS DISTRIBUTION IS UNLIMITED

UNCLASSIFIED

ib

ABSTRACT

The object of this study was to determine the chloride and water permeability of hydraulic brake hoses. Permeability parameters measured were time interval, temperature, type of exposure, type of brake hose composition, type of brake fluid and the cation linked with the chloride ion.

It was found that sufficient chloride and water will permeate brake hoses to initiate corrosion of metal parts in the conventional brake system. The extent of permeability is greatly reduced in systems containing silicone fluids.

TABLE OF CONTENTS

	<u>Page No.</u>
TITLE PAGE	i
ABSTRACT	ii
INTRODUCTION	1
DETAILS OF TEST	1 - 2
RESULTS AND DISCUSSION	2 - 4
CONCLUSIONS	4
RECOMMENDATIONS	4
ACKNOWLEDGEMENT	5
REFERENCES	5
APPENDIX A	6
Tables I - XII	7 - 14
APPENDIX B	15
Photographs 1 - 3	16 - 18
APPENDIX C ..	19
APPENDIX D	21
Figures I - VI	22 - 26
DISTRIBUTION LIST	27 - 28
DD FORM 1473	29

I. INTRODUCTION

Considerable investigative work is being carried on at the present time on water pick up in brake systems. Water pick up in brake systems is a matter of grave concern, since it increases vapor locking tendencies and affects low temperature viscosity (11). Permeability of brake hoses is an important factor in the entry of water into a brake system, so it is desirable to know the extent of permeability under various conditions. Further, since large concentrations of salt are used on the roads during winter months in the northern states, chloride permeability may be a concomittant factor in water pick up by brake fluids and should be investigated.

Accordingly, work was initiated to investigate the parameters of time, temperature, type of exposure and type of rubber affecting permeability of automotive brake hoses. It was also considered advisable to evaluate the deleterious effect of chloride content on the stroking and storage properties of the brake fluid and the type of brake fluids.

II. DETAILS OF TEST

1. Brake Hose Assembly.

Two brands of brake hoses used by the two leading auto manufacturers were selected for the test and designated as A and B. Each hose was filled with the SAE Compatibility Fluid (5), and closed with a brass couple. The couples were sealed with solder and both ends of the hose were triple dipped in paraffin wax.

2. Types of Exposure.

The packed brake hose assemblies were exposed to the following types of exposure:

- a) Water bath consisting of 3 gallon battery jar maintained at 36°F.
- b) Water bath consisting of 3 gallon battery jar maintained at 100°F.
- c) Five percent sodium chloride bath, 3 gallon battery jar, at 36°F.
- d) Five percent sodium chloride bath, 3 gallon battery jar, maintained at 100°F.
- e) Humidity cabinet conforming to Specifications JAN-H-31 and JAN-H-192 maintained at 100°F.
- f) Salt spray cabinet (5%) - manufactured by GS Equipment Co., Model No. 22, maintained at 95°F.

g) Salt spray cabinet (20%) - manufactured by GS Equipment Co., Model No. 22, maintained at 95°F.

The hoses in tests f) and g) were suspended as shown in Photo 1, Appendix B. The hoses in all other tests were completely immersed.

In order to determine if the cation affected the degree of chloride permeability, test c) was repeated using sodium chloride, calcium chloride and ammonium chloride. Three brake fluids were evaluated in these tests; one SAE Compatibility Fluid and two silicone fluids designated as Codes C and D.

3. Test Procedure.

One brake hose of each type was removed from each of the above exposures at weekly intervals, the ends scrupulously cleaned, dried, and then opened. The fluid was drained and the chloride and water contents were determined. The water content was determined by Karl Fischer analysis (ASTM Method D-1123). The chloride content was determined by a method based on that of Barney and Bertolacini using mercuric chloranilate. The modified procedure is contained in Appendix C (9 and 10).

4. Stroking Test.

Chloride was added to the SAE compatibility brake fluid at the rate of 100 ppm. The stroking properties of the resultant fluid were determined according to Method 361.3 of Federal Test Method Standard No. 791-13. The stroking properties of the SAE compatibility brake fluid without chloride added were also determined for purposes of reference and comparison.

5. Brake Wheel Cylinder Storage.

A standard chloride solution containing 1 mg per ml. was prepared by diluting 1.51 grams of ammonium chloride to one liter with distilled water. The SAE compatibility brake fluid was then contaminated with this chloride solution so that the final chloride content of the brake fluid was zero, 20 ppm, 100 ppm, 200 ppm and 400 ppm. SAE standard 1-1/8 inch brake wheel cylinders (Bendix 2227391-L) were disassembled, thoroughly washed and then packed in quadruplicate with each of the contaminated fluids. The twenty packed cylinders were stored in the open laboratory at 70-80°F. for 30, 90 and 180 days storage period.

III. RESULTS AND DISCUSSION

The results of the chloride and water content analysis of brake fluids taken from brake hoses after various types of exposure are shown in Appendix A, Tables I-VII. At the outset, it should be pointed out that the brake hoses tested were not uniform in fabrication. This fact should be considered in the analysis of statistical data. It was found in the

initial screening test that maximum contamination was obtained at about 35 days, and accordingly, this was the time chosen for the duration of the tests. In each test there was sufficient water permeability to seriously change the boiling point and viscosity of the brake fluid, and sufficient chloride permeability to initiate and accelerate the rate of corrosion of metal parts in the brake systems. The average test results of each exposure are listed in Table VIII.

1. Comparisons of Types of Hoses.

Analysis of the brake hoses designated as A and B showed that both types had an inner layer of neoprene and an outer layer of styrene butadiene. The hoses differed from each other in that the B hose had a thinner fiber layer which was milled with a polyester type compound as contrasted with the A hose that was milled with styrene butadiene rubber. From the averages listed in Table VIII, it will be seen that the average water permeability of the A hose was 9.65% compared with 8.10% for the B hose. The average chloride permeability of the two hoses was comparable: 68 ppm for the A hose, 66 ppm for the B hose.

2. Effect of Salt Concentration.

Examination of the values listed in Table VIII shows that the increased amount of salt concentration in the salt spray had little effect on the chloride permeability.

3. Effect of Cation on Magnitude of Chloride Permeability.

From Tables IX, X and XI it can be seen that within experimental error and the uncontrolled factor of hose uniformity, the chloride permeability is independent of the cation with which it was linked.

4. Effect of type of Brake Fluid on Water and Chloride Permeability.

From Tables IX, X and XI, it can be seen that the use of silicone fluids drastically reduce the chloride and water permeability.

5. Results of Stroking Evaluation.

After 90,000 strokes at 1000 psi. and 250°F. and 210,000 strokes at 500 psi. and 158°F. (total 300,000 strokes) the brake system containing the salt/water contaminated fluid was in the following condition:

a) Master cylinder: The brass piston was extremely darkened; interior of the cylinder was in satisfactory condition; the spring and check valve were in satisfactory condition; and the primary cup exhibited excessive chipping, while the secondary cup exhibited light to heavy chipping.

b) Wheel cylinders: The interior of the cylinder showed the normal wear while the four aluminum pistons showed excessive corrosive attack on the sides of the pistons (see Photo 2, Appendix B). The four wheel cylinders springs had areas of plating worn away. The interior of the cylinder was satisfactory. The wheel cylinder cups all showed excessive chipping.

The above test was repeated without chloride contamination. There was no excessive corrosion of metal parts and no excessive chipping of the rubber cups.

6. Brake Wheel Cylinder Storage.

At the end of six months storage at room temperature, the brake wheel cylinders were opened and the fluid collected. The condition of the cylinders is listed in Table IX. All cylinders containing chloride were considered inoperable and failing. The cylinders were cut in half and the corrosive effect of the chloride can be seen in Photo 3. The spectrograms of the drained fluids are shown in Appendix D. Except for the water band at 6.1 microns, no perceptible change in composition is noted.

IV. CONCLUSIONS

The chloride and water permeability in all the tests except those containing silicone fluids was sufficient to initiate and increase the rate of corrosion of metal parts in the brake system. The chloride and water permeability was drastically reduced when the system contained silicone fluids. It increased at elevated temperatures.

It appeared that the thicker the fiber layer of the brake hose the greater the permeability. Chloride permeability was essentially independent of the cation to which the chloride was originally linked.

V. RECOMMENDATIONS

1. On the basis of findings in this report, it is recommended that a permeability test requirement be considered in the next revision of Military Specification MIL-H-13719C, Hose Assembly, Rubber, Hydraulic Brake.

2. That this investigation be extended to include the chloride analysis of brake fluids from random vehicles which have been exposed to winter driving conditions involving "salted" roads.

3. That the brake wheel cylinder storage program be continued.

4. That the results of this study be given wide publicity in the various committees, both industrial and governmental, which are studying various aspects of brake system safety.

VI. ACKNOWLEDGEMENT

The assistance of Mr. B. Caudill in the stroking evaluation tests and Mr. H. R. Sheets in the preparation and packing of the brake wheel cylinders for the storage program is gratefully acknowledged.

VII. REFERENCES

1. Specification JAN-H-792, Humidity Cabinet.
2. Specification JAN-H-31, Humidity Cabinet.
3. Specification MIL-H-13719C, Hose Assembly, Rubber, Hydraulic Brake.
4. Federal Test Method Standard No. 791-13, Method 361.3 dated January 1969, Stroking Properties of Hydraulic Brake Fluids.
5. SAE Standard, J 1703, Hydraulic Brake Fluid.
6. Motor Vehicle Safety Standard No. 105, "Passenger Cars and Multi-purpose Passenger Vehicles, Trucks and Buses".
7. R. W. Radlins, J. L. Harvey, and R. J. Forthofer, "Operating Performance of Motor Vehicle Braking Systems as Affected by Fluid Water Content", SAE Paper 710253, Automotive Engineering Congress, Detroit, Michigan, 11 January 1971.
8. J. L. Harvey, L. J. Milliken, and R. J. Forthofer, "Trends in Motor Vehicle Brake Fluids and Their Standards", SAE Paper 710251, *ibid.*
9. J. Bertolacini, and J. Barney, "Colorimetric Determination of Chloride with Mercuric Chloranilate", *Analytical Chemistry*, 29:1787 (Aug 1957).
10. R. Bertolacini and J. Barney, "Ultraviolet Spectrophotometric Determination of Sulfate, Chloride and Fluoride with Chloranilic Acid", *Analytical Chemistry*, 30:202 (Feb 1958).
11. CCL Report No. 198, "Effect of Water on Hydraulic Brake Fluid", Coating and Chemical Laboratory, Aberdeen Proving Ground, Maryland, dated May 1966.

APPENDIX A

TABLE I

Chloride and Water Permeability of Brake Hoses
Brake Fluid Sampled After Exposure to 5% Salt Spray at 95°F.

Days	Chloride, ppm		% Water			
			Hose A		Hose B	
	Hose A	Hose B	Total Water	Permeability	Total Water	Permeability
0	Nil	Nil	0.46	--	0.46	--
7	5	5	7.11	6.65	8.67	8.21
14	18	25	12.66	12.14	8.10	7.64
21	200	170	10.90	10.44	8.60	8.14
28	50	116	7.90	7.44	7.30	6.84
35	12	12	8.04	7.58	8.50	8.04
Average	57	66		8.85		7.77

TABLE II

Chloride and Water Permeability of Brake Hoses
Brake Fluid Sampled After Exposure to 20% Salt Spray at 95°F.

Days	Chloride, ppm		% Water			
			Hose A		Hose B	
	Hose A	Hose B	Total Water	Permeability	Total Water	Permeability
0	Nil	Nil	0.44	--	0.44	--
7	9	5	14.15	13.71	11.55	11.11
14	46	58	12.20	11.76	9.10	8.66
21	90	--	11.87	11.43	6.88	6.44
28	80	98	8.05	7.61	7.50	7.06
35	12	12	8.70	8.26	--	--
Average	47	43		10.55		8.32

TABLE III

Chloride and Water Permeability of Brake Hoses

Brake Fluid Sampled After Exposure to 5% Salt Bath at 36°F.

Days	Chloride, ppm		% Water			
			Hose A		Hose B	
	Hose A	Hose B	Total Water	Permeability	Total Water	Permeability
0	Nil	Nil	0.46	--	0.46	--
7	5	5	3.95	3.49	3.35	2.89
14	5	5	9.22	8.76	10.40	9.94
21	23	60	8.40	7.94	9.30	8.84
28	25	50	5.30	4.84	7.00	6.54
35	275	400	7.80	7.34	15.95	15.49
Average	67	104		6.45		8.74

TABLE IV

Chloride and Water Permeability of Brake Hoses

Brake Fluid Sampled After Exposure to 5% Salt Bath at 100°F.

Days	Chloride, ppm		% Water			
			Hose A		Hose B	
	Hose A	Hose B	Total Water	Permeability	Total Water	Permeability
0	Nil	Nil	0.44	--	0.44	--
7	5	5	9.95	9.51	9.45	9.01
14	50	60	7.60	7.16	9.59	9.19
21	110	50	11.50	11.06	10.50	10.06
28	680*	50	11.30	10.86	10.50	10.06
35	240	43	6.74	6.30	4.44	4.00
Average	101	42		8.98		8.46

*Not included in average.

TABLE V

Chloride and Water Permeability of Brake Hoses

Brake Fluid Sampled After Exposure to Water Bath at 36°F.

Days	Chloride, ppm		% Water			
			Hose A		Hose B	
	Hose A	Hose B	Total Water	Permeability	Total Water	Permeability
0	Nil	Nil	0.46	--	0.46	--
7	Trace	Trace	11.50	11.04	10.60	10.14
14	Trace	Trace	7.04	6.58	5.94	5.48
21	Trace	Trace	7.89	7.43	7.53	7.07
28	Trace	Trace	10.49	10.03	9.49	9.03
35	Trace	Trace	9.84	9.38	5.58	5.12
Average	Trace	Trace		8.89		7.37

Table VI

Chloride and Water Permeability of Brake Hoses

Brake Fluids Sampled After Exposure to Water Bath at 100°F.

Days	Chloride, ppm		% Water			
			Hose A		Hose B	
	Hose A	Hose B	Total Water	Permeability	Total Water	Permeability
0	Nil	Nil	0.44	--	0.44	--
7	Trace	Trace	11.56	11.12	11.43	10.99
14	Trace	Trace	10.45	10.01	7.98	7.54
21	Trace	Trace	9.49	9.05	6.76	6.32
28	Trace	Trace	19.89	19.45	9.14	8.70
35	Trace	Trace	7.78	7.34	6.96	6.52
Average	Trace	Trace		11.39		8.01

TABLE VII

Chloride and Water Permeability of Brake Hoses
Brake Fluid Sampled After Exposure to Humidity Cabinet

Days	Chloride, ppm		% Water			
	Hose A	Hose B	Hose A		Hose B	
			Total Water	Permeability	Total Water	Permeability
0	Nil	Nil	0.46	--	0.46	--
7	Trace	Trace	0.78	0.32	0.76	0.30
14	Trace	Trace	8.17	7.71	6.04	5.58
21	Trace	Trace	8.89	8.43	8.46	8.00
28	Trace	Trace	24.80	24.34	14.60	14.14
35	Trace	Trace	24.00	23.54	12.74	12.28
Average	Trace	Trace		12.47		8.06

TABLE VIII

Summary of Average Chloride and Water Permeability
Of Brake Hoses After Various Exposures

Exposure	Chloride, ppm		% Water	
	Hose A	Hose B	Hose A	Hose B
5% Salt Bath (36°F.)	67	104	6.45	8.74
5% Salt Bath (100°F.)	101	42	8.98	8.46
5% Salt Spray	57	66	8.85	7.77
20% Salt Spray	47	43	10.55	8.32
Water Bath (36°F.)	--	--	8.89	7.37
Water Bath (100°F.)	--	--	11.39	8.01
Humidity Cabinet	--	--	12.47	8.06
Average	68	64	9.65	8.10

TABLE IX

Chloride and Water Content of SAE Brake Fluid from Brake Hose
After Exposure to Various Salt Baths for 21 Days at 36°F:

	<u>Cl (ppm)</u>	<u>H₂O (%)</u>
a) 5% Na Cl (Hose A)	349	5.94
b) 5% Na Cl (Hose A)	349	6.11
a) 5% Na Cl (Hose B)	214	0.93
b) 5% Na Cl (Hose B)	377	1.34
Average	330	3.58
a) 5% Ca Cl ₂ (Hose A)	368	3.99
b) 5% Ca Cl ₂ (Hose A)	428	5.80
a) 5% Ca Cl ₂ (Hose B)	133	0.88
b) 5% Ca Cl ₂ (Hose B)	139	5.19
Average	254	3.57
a) 5% NH ₄ Cl (Hose A)	158	3.30
b) 5% NH ₄ Cl (Hose A)	270	6.96
a) 5% NH ₄ Cl (Hose B)	158	8.49
b) 5% NH ₄ Cl (Hose B)	256	3.29
Average	211	5.41

TABLE X

Chloride and Water Content of Water Tolerant Silicone
Brake Fluid from Brake Hose After Exposure
To Various Salt Baths for 21 Days at 36°F.

	<u>Cl (ppm)</u>	<u>H₂O (%)</u>
a) 5% Na Cl (Hose A)	0	0.89
b) 5% Na Cl (Hose A)	0	1.20
a) 5% Na Cl (Hose B)	0	0.90
b) 5% Na Cl (Hose B)	0	0.63
Average	0	0.90
a) 5% Ca Cl ₂ (Hose A)	0	0.54
b) 5% Ca Cl ₂ (Hose A)	18	0.60
a) 5% Ca Cl ₂ (Hose B)	18	0.84
b) 5% Ca Cl ₂ (Hose B)	0	0.46
Average	9	0.61
a) 5% NH ₄ Cl (Hose A)	0	4.24
b) 5% NH ₄ Cl (Hose A)	0	1.47
a) 5% NH ₄ Cl (Hose B)	0	0.88
b) 5% NH ₄ Cl (Hose B)	0	0
Average	0	1.65

TABLE XI

Chloride and Water Content of Non-Hygroscopic Silicone
Brake Fluid From Brake Hose After Exposure to
Various Salt Baths for 21 Days at 36°F.


	<u>Cl (ppm)</u>	<u>H₂O (%)</u>
a) 5% Na Cl (Hose A)	Nil	N Nil
b) 5% Na Cl (Hose A)	Nil	Nil
a) 5% Na Cl (Hose B)	Nil	Nil
b) 5% Na Cl (Hose B)	Nil	Nil
Average		
a) 5% Ca Cl ₂ (Hose A)	*Contaminated	Nil
b) 5% Ca Cl ₂ (hose A)	Nil	Nil
a) 5% Ca Cl ₂ (Hose B)	Nil	Nil
b) 5% Ca Cl ₂ (Hose B)	Nil	Nil
Average		
a) 5% NH ₄ Cl (Hose A)	Nil	Nil
b) 5% NH ₄ Cl (Hose A)	Nil	Nil
a) 5% NH ₄ Cl (Hose B)	Nil	Nil
b) 5% NH ₄ Cl (Hose B)	Nil	Nil
Average		



TABLE XII

Condition of Wheel Cylinders after 6 Months Storage
With Brake Fluids Containing Chloride

<u>Chloride Content</u>	<u>Appearance</u>
0 ppm	Spring - OK. Right piston - Slight gum. Left piston - Slight gum and slight stain. Cylinder walls - Slight gum and slight stain.
20 ppm	Spring - OK. Right piston - Moderate gum and stain. Left piston - Moderate gum and stain; piston frozen. Cylinder walls - Moderate gum and stain.
100 ppm	Spring - OK. Right piston - Moderate gum and stain; piston frozen. Left piston - Moderate gum and stain; piston frozen. Cylinder walls - Moderate gum and stain; slight pitting.
200 ppm	Spring - OK. Right piston - Heavy gum and stain; piston frozen. Left piston - Heavy gum and stain; piston frozen. Cylinder walls - Heavy gum, stain and pitting.
400 ppm	Spring - OK. Right piston - Heavy gum buildup outside of piston, piston frozen. Left piston - Heavy gum buildup outside of piston, piston frozen. Cylinder walls - Heavy stain and pitting.

APPENDIX B















三

10
 11
 12
 13
 14
 15
 16
 17
 18
 19
 20
 21
 22
 23
 24
 25
 26
 27
 28
 29
 30
 31
 32
 33
 34
 35
 36
 37
 38
 39
 40
 41
 42
 43
 44
 45
 46
 47
 48
 49
 50
 51
 52
 53
 54
 55
 56
 57
 58
 59
 60
 61
 62
 63
 64
 65
 66
 67
 68
 69
 70
 71
 72
 73
 74
 75
 76
 77
 78
 79
 80
 81
 82
 83
 84
 85
 86
 87
 88
 89
 90
 91
 92
 93
 94
 95
 96
 97
 98
 99
 100
 101
 102
 103
 104
 105
 106
 107
 108
 109
 110
 111
 112
 113
 114
 115
 116
 117
 118
 119
 120
 121
 122
 123
 124
 125
 126
 127
 128
 129
 130
 131
 132
 133
 134
 135
 136
 137
 138
 139
 140
 141
 142
 143
 144
 145
 146
 147
 148
 149
 150
 151
 152
 153
 154
 155
 156
 157
 158
 159
 160
 161
 162
 163
 164
 165
 166
 167
 168
 169
 170
 171
 172
 173
 174
 175
 176
 177
 178
 179
 180
 181
 182
 183
 184
 185
 186
 187
 188
 189
 190
 191
 192
 193
 194
 195
 196
 197
 198
 199
 200
 201
 202
 203
 204
 205
 206
 207
 208
 209
 210
 211
 212
 213
 214
 215
 216
 217
 218
 219
 220
 221
 222
 223
 224
 225
 226
 227
 228
 229
 230
 231
 232
 233
 234
 235
 236
 237
 238
 239
 240
 241
 242
 243
 244
 245
 246
 247
 248
 249
 250
 251
 252
 253
 254
 255
 256
 257
 258
 259
 260
 261
 262
 263
 264
 265
 266
 267
 268
 269
 270
 271
 272
 273
 274
 275
 276
 277
 278
 279
 280
 281
 282
 283
 284
 285
 286
 287
 288
 289
 290
 291
 292
 293
 294
 295
 296
 297
 298
 299
 300
 301
 302
 303
 304
 305
 306
 307
 308
 309
 310
 311
 312
 313
 314
 315
 316
 317
 318
 319
 320
 321
 322
 323
 324
 325
 326
 327
 328
 329
 330
 331
 332
 333
 334
 335
 336
 337
 338
 339
 340
 341
 342
 343
 344
 345
 346
 347
 348
 349
 350
 351
 352
 353
 354
 355
 356
 357
 358
 359
 360
 361
 362
 363
 364
 365
 366
 367
 368
 369
 370
 371
 372
 373
 374
 375
 376
 377
 378
 379
 380
 381
 382
 383
 384
 385
 386
 387
 388
 389
 390
 391
 392
 393
 394
 395
 396
 397
 398
 399
 400
 401
 402
 403
 404
 405
 406
 407
 408
 409
 410
 411
 412
 413
 414
 415
 416
 417
 418
 419
 420
 421
 422
 423
 424
 425
 426
 427
 428
 429
 430
 431
 432
 433
 434
 435
 436
 437
 438
 439
 440
 441
 442
 443
 444
 445
 446
 447
 448
 449
 450
 451
 452
 453
 454
 455
 456
 457
 458
 459
 460
 461
 462
 463
 464
 465
 466
 467
 468
 469
 470
 471
 472
 473
 474
 475
 476
 477
 478
 479
 480
 481
 482
 483
 484
 485
 486
 487
 488
 489
 490
 491
 492
 493
 494
 495
 496
 497
 498
 499
 500
 501
 502
 503
 504
 505
 506
 507
 508
 509
 510
 511
 512
 513
 514
 515
 516
 517
 518
 519
 520
 521
 522
 523
 524
 525
 526
 527
 528
 529
 530
 531
 532

Reproduced from
best available copy.



APPENDIX C

Procedure for Ultraviolet Spectrophotometric Determination of Chloride in Brake Fluids with Mercuric Chloranilate


Reagents:

1N Nitric acid
Methyl cellosolve
Ammonium chloride (ACS)
Mercuric chloranilate (certified reagent grade)

Place 0.5 ml. of brake fluid in a 100 ml. volumetric flask. Add 5 ml. of 1N-nitric acid and 50 ml. of methyl cellosolve (ethylene glycol monoethyl ether). Add 0.2 gram of mercuric chloranilate. Dilute to the 100 ml. mark with distilled water and stopper the flask shake at least once a minute for fifteen minutes. Filter through Whatman #42 filter paper.

Read the absorbance of the filtrate on a Bechman "B" Spectrophotometer at 530 um. Compare to a standard curve constructed using a sample prepared by diluting 1.5105 grams of ammonium chloride to one liter with distilled water (see page 20). This gives a chloride standard of 1 mg per ml.

If the absorbance of the sample being tested exceeds the absorbance of the standard, the sample may be reduced accordingly. A 99% accuracy is obtained in the chloride range of 3 ppm to 400 ppm.



APPENDIX D




FIGURE 1 - SAE Compatibility Brake Fluid From Wheel Cylinder After Six Month's Storage.
(No Chloride Added).




FIGURE 11 - SAE Compatibility Brake Fluid From Wheel Cylinder After Six Month's Storage.
(20 ppm Chloride Added).




FIGURE III - SAE Compatibility Brake Fluid From Wheel Cylinder After Six Month's Storage.
(100 ppm Chloride Added).




FIGURE IV - SAE Compatibility Brake Fluid From Wheel Cylinder After Six Month's Storage.
(200 ppm Chloride Added).




FIGURE V - SAE Compatibility Brake Fluid From Wheel Cylinder After Six Month's Storage.
(400 ppm Chloride Added).