AD-775 818

DEVELOPMENT OF MANUFACTURING METHODS FOR BALLISTICALLY TOLERANT FIBERGLASS TUBULAR BELLCRANKS

I. E. Figge, Sr.

Army Air Mobility Research and Development Laboratory Fort Eustis, Virginia

January 1974

**DISTRIBUTED BY:** 

National Technical Information Service U. S. DEPARTMENT OF COMMERCE 5285 Port Royal Road, Springfield Va. 22151

DUCUMENT CONTROL DATA - R & D         (teachy classification of tills, body of barries and marking and scale			110	
Detrify Trice Activity (Compares and any provided in the second of th	DOCUME (Security classification of title, body of ebstract or	NT CONTROL DATA - R	& D	everall month is classified.
U.S. Army Air Mobility Research and Development Laboratory A. E. ANDER Pert Burkin, Virginia DEVEOPMENT OF MANUFACTURING METHODS FOR BALLISTICALLY TOLERANT FIBERGLASS TUBULAR BELLCRANKS DECEMPTIVE NOT XE (7)ppe of repeat and metastre dense) Technical Memo-andum AutorNMI (Normac, added industre dense) 1. E. Figge, St. PROTECT NO. PROJECT NO. PRO	ORIGINATING ACTIVITY (Corporate suther) Eustis Directorate		Unclassi	CURITY CLASSIFICATION
Alternative track DEVEOPMENT OF MANUFACTURING METHODS FOR BALLISTICALLY TOLERANT FIBERGLASS TUBULAR BELLCRANKS DEVENTIVE HOT TO THE OF THE BELLCRANKS DEVENTIVE HOT TO THE TOTAL HOT OF PARENT FIBERGLASS TUBULAR BELLCRANKS DEVENTIVE HOT TO THE DEVENTION BELLCRANKS DEVENTION OF THE DEVENTION DEVENTION OF THE DEVENT OF THE DEVENT OF THE DEVENTION OF THE DEVENT OF THE DE	U.S. Army Air Mobility Research and De Fort Eustis, Virginia	evelopment Laboratory	25. GROUP	
Deterministic for the former and um         AUTOMINI (Prot name, middle inflick, test name)         1. E. Figge, Sr.         MEFORT CARE January 1974	DEVEOPMENT OF MANUFACTURING N FIBERGLASS TUBULAR BELLCRANKS	METHODS FOR BALI	LISTICALLY	TOLERANT
Autoreniis (Print anne, niede initial, last name)  I. E. Figge, Sr.   APPORT DATE January 1974  - Source of the second s	DESCRIPTIVE NOTES (Type of report and inclusive dates Technical Memorandum	(		
ABPORT DATE January 1974       74. TOTAL NO. OF PASE 4       10. NO. OF REFS 2         CONTRACT ON STATEMENT       10. ONE NOT APPORT NUMBERIES         PROJECT NO.       10. ONE NATION STATEMENT         House Task 71-12       10. OTHER REPORT NOUSE (App other mambers dail may be conformed)         International and the statement       11. SPONSORING MILITARY ACTIVITY         Approved for public release; distribution unlimited.       11. SPONSORING MILITARY ACTIVITY         Exists Directorate, U.S. Army Air Mobility Research and Development Laboratory Fort Eustis, Virginia       11. SPONSORING MILITARY ACTIVITY         Asymact       11. SPONSORING MILITARY ACTIVITY       Exists Directorate, U.S. Army Air Mobility Research and Development Laboratory Fort Eustis, Virginia         The purpose of this investigation was to develop manufacturing methods for the ballistically tolera tubular/sandwich CH-47 forward bellerank with the goals of optimizing production costs and weigh while achieving structural repeatability. Complete fabrication details are presented. Ballistic, fatig and static tests, conducted at -65°F, 75°F, and 180°F, showed that the bellerank met the design requirements. The manufacturing technique that localized the ballistic damage on the exit face sheet and prevented gross delaminations was developed.         Reproduced by NATIONAL TECHNICAL INFORMATION SERVICE U.S. Department of Commerce Springfield VA 22131       Cotails of illustrations in this document may be better studied on microfiche.         D formation of the structure is Unclassified       Unclassified	I. E. Figge, Sr.			
EGNTMACT ON BRANT NO.       Is. ORIGINATON'S REPORT NUMBERIES         PROJECT NO.       USAAMRDL Technical Memorandum 3         House Task 71-12       Is. ORIGINATON'S REPORT NOUSE (Any other numbers that may be dealfor the major)         DISTRIBUTION STATEMENT       Approved for public release; distribution unlimited.         ISOFFLEMENTARY NOTES       Is. SPONSORING MILITARY ACTIVITY Eustis Directorate, U.S. Army Air Mobility Research and Development Laboratory Fort Eustis, Virginia         The purpose of this investigation was to develop manufacturing methods for the ballistically tolera tubular/sandwich CH-47 forward bellerank with the goals of optimizing production costs and weigi while achieving structural repeatability. Complete fabrication details are presented. Ballistic, fatig and static tests, conducted at -65°F, 75°F, and 180°F, showed that the bellerank met the design requirements. The manufacturing techniques developed resulted in both substantial weight savings \$135.00). A "slotting" technique that localized the ballistic damage on the exit face sheet and prevented gross delaminations was developed.         Neproduced by NATIONAL TECHNICAL INFORMATION SERVICE U S Department of Commerce Springfield VA 22151         Cotoils of illustrations in this document may be better studied on microfiche.         D reset.1473       Stateff SSA SERVICE, 'ARM MARCH 18	REPORT DATE January 1974	74. TOTAL NO. 0	34	76. NO. OF REFS
House Task 71-12      House Task 71-12      GistRisovion statement  Approved for public release; distribution unlimited.      If a sponsoning unlif a spo	CONTRACT OR GRANT NO.	Se. ORIGINATOR	S REPORT NUM	BER(#)
House Task 71-12  b. OTHER REPORT NO(19) (Any other numbers that may be acalged  stransurion statement Approved for public release; distribution unlimited.  Approved for public release; distribution apublic release; distribution approved forest for public release;	PROJECT NO.	USAAMRDL	Technical I	Memorandum 3
Approved for public release; distribution unlimited.	· House Task 71-12	6. OTHER REPO this report)	RT NO(S) (Any o	ther numbers that may be easigned
Approved for public release; distribution unlimited.  Approved for public release; distribution unlimi				
Approved for public release; distribution unlimited.	DISTRIBUTION STATEMENT			
INPPLEMENTARY NOTES       12. SPONSORING MILITARY ACTIVITY         Eustis Directorate, U.S. Army Air Mobility Research and Development Laboratory Fort Eustis, Virginia         ASSTRACT         The purpose of this investigation was to develop manufacturing methods for the ballistically tolera tubular/sandwich CH-47 forward bellcrank with the goals of optimizing production costs and weigi while achieving structural repeatability. Complete fabrication details are presented. Ballistic, fatigi and static tests, conducted at -65°F, 75°F, and 180°F, showed that the bellcrank met the design requirements. The manufacturing techniques developed resulted in both substantial weight savings (1.65 pounds compared to 3.4 pounds for a metal bellcrank) and cost savings (\$68.60 compared \$135.00). A "slotting" technique that localized the ballistic damage on the exit face sheet and prevented gross delaminations was developed.         Reproduced by NATIONAL TECHNICAL INFORMATION SERVICE U S Department of Commerce Springfield VA 22151         L'etails of illustrations in this document may be better studied on microfiche.         D	Approved for public release; distribution	unlimited.		
Asstract The purpose of this investigation was to develop manufacturing methods for the ballistically tolera tubular/sandwich CH-47 forward bellcrank with the goals of optimizing production costs and weigl while achieving structural repeatability. Complete fabrication details are presented. Ballistic, fatig and static tests, conducted at -65°F, 75°F, and 180°F, showed that the bellcrank met the design requirements. The manufacturing techniques developed resulted in booth substantial weight savings (1.65 pounds compared to 3.4 pounds for a metal bellcrank) and cost savings (\$68.60 compared \$135.00). A "slotting" technique that localized the ballistic damage on the exit face sheet and prevented gross delaminations was developed. Reproduced by NATIONAL TECHNICAL INFORMATION SERVICE U S Department of Commerce Springfield VA 22151	BUPPLEMENTARY NOTES	12. SPONSORING Eustis Direct	MILITARY ACTI	vity Army Air Mobility
The purpose of this investigation was to develop manufacturing methods for the ballistically tolera tubular/sandwich CH-47 forward bellcrank with the goals of optimizing production costs and weigh while achieving structural repeatability. Complete fabrication details are presented. Ballistic, fatig and static tests, conducted at -65°F, 75°F, and 180°F, showed that the bellcrank met the design requirements. The manufacturing techniques developed resulted in both substantial weight savings (1.65 pounds compared to 3.4 pounds for a metal bellcrank) and cost savings (\$68.60 compared \$135.00). A "slotting" technique that localized the ballistic damage on the exit face sheet and prevented gross delaminations was developed. Reproduced by NATIONAL TECHNICAL INFORMATION SERVICE U S Department of Commerce Springfield VA 22151 D forw1473 Stickett DEATSHLYCE. J can see white us Unclassified		Research and	Developme	nt Laboratory
The purpose of this investigation was to develop manufacturing methods for the ballistically tolera tubular/sandwich CH-47 forward bellcrank with the goals of optimizing production costs and weigl while achieving structural repeatability. Complete fabrication details are presented. Ballistic, fatig and static tests, conducted at -65°F, 75°F, and 180°F, showed that the bellcrank met the design requirements. The manufacturing techniques developed resulted in both substantial weight savings (1.65 pounds compared to 3.4 pounds for a metal bellcrank) and cost savings (\$68.60 compared \$135.00). A "slotting" technique that localized the ballistic damage on the exit face sheet and prevented gross delaminations was developed. Reproduced by NATIONAL TECHNICAL INFORMATION SERVICE U S Department of Commerce Springfield VA 22151 L'otails of illustrations in this document may be better studied on microfiche.		Fort Eustis	Virginia	,
Details of illustrations in this document may be better studied on microfiche.	The nurners of this investigation was to	develop manufacturia	most a de f	n also hallinai-alle a-1
D 1000 1473 REPLACES DE POR ANNY USE. JAN 66, WHICH IS Unclassified	The purpose of this investigation was to tubular/sandwich CH-47 forward bellcrank while achieving structural repeatability. C and static tests, conducted at -65°F, 75° requirements. The manufacturing techniq (1.65 pounds compared to 3.4 pounds fo \$135.00). A "slotting" technique that lo prevented gross delaminations was develop Reproduced NATION US Dep Spri	develop manufacturing with the goals of op Complete fabrication de F, and 180°F, showed ues developed resulted or a metal bellcrank) a ocalized the ballistic da oed. by NAL TECHNICAL MATION SERVICE martment of Commerce ingitield VA 22151	methods for timizing pro- etails are pro- l that the b in both sul nd cost savi mage on th	r the ballistically tolerar duction costs and weigh esented. Ballistic, fatigu ellcrank met the design ostantial weight savings ngs (\$68.60 compared to e exit face sheet and
	The purpose of this investigation was to tubular/sandwich CH-47 forward bellcrank while achieving structural repeatability. C and static tests, conducted at -65°F, 75° requirements. The manufacturing techniq (1.65 pounds compared to 3.4 pounds fo \$135.00). A "slotting" technique that lo prevented gross delaminations was develop Reproduced NATIOI INFORM U S Dep Spri	develop manufacturing with the goals of op Complete fabrication de 'F, and 180°F, showed ues developed resulted or a metal bellcrank) a boalized the ballistic da bed. by NAL TECHNICAL MATION SERVICE mathematication of Commerce ingfield VA 22151 Liet. this stud	methods for timizing pro- etails are pro- l that the b in both sul nd cost savi mage on th mage on th document i led on mici	r the ballistically tolerar duction costs and weigh sented. Ballistic, fatigu ellcrank met the design ostantial weight savings ngs (\$68.60 compared to e exit face sheet and rations in may be better rofiche.

	KEY WORDS	LINI	( A )	LIN	K 8	LIN	ĸc
D. 11:		ROLE	WT	ROLE	WT	ROLE	WT
Ballistically tol Fiberglass tubu	erant Iar bellcranks						
Toergiass tubu							
		1			:		
					'	1.1	
			1				
Ĭ							
			•				
				•			
					_		_
	c	· · · · · · · · · · · · · · · · · · ·	Unclass	ified			
	10	ι —	Security	Classific	ation		

### DISCLAIMERS

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission, to manufacture, use, or sell any patented invention that may in any way be related thereto.

Trade names cited in this report do not constitute an official endorsement or approval of the use of such commercial hardware or software.

### DISPOSITION INSTRUCTIONS

it

Destroy this report when no longer needed. Do not return it to the originator.

115	White Section (
	Buff Section
11	
11Cail00	l
ISTRIBUTIO	AVAILABILITY CODE
Biel.	AVAIL and/or SPECIA
-	
1	
$\square$	

House Task 71-12 USAAMRDL Technical Memorandum 3 January 1974

## DEVELOPMENT OF MANUFACTURING METHODS FOR BALLISTICALLY TOLERANT FIBERGLASS TUBULAR BELLCRANKS

By

I. E. Figge, Sr.

EUSTIS DIRECTORATE U.S. ARMY AIR MOBILITY RESEARCH AND DEVELOPMENT LABORATORY FORT EUSTIS, VIRGINIA

> Approved for public release; distribution unlimited.

> > ii

### SUMMARY

The purpose of this investigation was to develop manufacturing methods for the ballistically tolerant tubular/sandwich CH-47 forward bellcrank with the goals of optimizing production costs and weight, while achieving structural repeatability. Complete fabrication details are presented. Ballistic, fatigue, and static tests, conducted at  $-65^{\circ}F$ ,  $75^{\circ}F$ , and  $180^{\circ}F$ , showed that the bellcrank met the design requirements. The manufacturing techniques developed resulted in both substantial weight savings (1.65 pounds compared to 3.4 pounds for a metal bellcrank) and cost savings (\$68.60 compared to \$135.00). A "slotting" technique that localized the ballistic damage on the exit face sheet and prevented gross delaminations was developed.

## FOREWORD

The author acknowledges Messers. B. L. Karp, E. H. McIlwean, and particularly M. C. Dail (deceased), all of the Structures Area, Eustis Directorate, U. S. Army Air Mobility Research and Development Laboratory, for their significant contributions to this program. Without their ingenuity and resourcefulness, this program would not have been possible.

÷

# TABLE OF CONTENTS

÷

•

.

SUMMARY	iii
FOREWORD	v
LIST OF ILLUSTRATIONS	ix
INTRODUCTION	1
DEVELOPMENT OF FABRICATION PROCEDURES	2
Bellcrank Face Sheets Tubular Elements End Attachments Bearings Final Assembly	2 2 3 3 3 3
COST AND WEIGHT ESTIMATES	5
Cost Weight General Remarks	5 6 6
TEST EQUIPMENT AND PROCEDURES	7
General Ballistic Tests Static and Fatigue Tests	7 8 8
TEST RESULTS	9
Fiberglass Tubular Bellcrank Metal Bellcrank	9 9
CONCLUSIONS	12
LITERATURE CITED	13

Preceding page blank

Page

## APPENDIXES

I.	Detailed Drawing of Tubular Bellcrank	21
п.	Properties and Cure Cycles for 181-Style Prepreg Cloth	23
ш.	Properties and Cure Cycles for FM-1000 Structural Adhesive Film	25
DISTRIE	BUTION	26

Page

1

- 4 -

• •

ŗ

# LIST OF ILLUSTRATIONS

Figure		Page
1	Exploded View of Square Tube Bellcrank	14
2	Delamination of Exit Face Sheet Caused by Tumbled .30 Caliber Impact	14
3	Localized Delamination of Exit Face Sheet Resulting From "Slotting"	15
4	Edge View of Two .30 Caliber Impacts of Slotted Tubular Bellcrank (Note Minimal Delamination)	15
5	Aluminum Matched Metal Molds Used To Fabricate Face Sheets	16
6	Winding of Glass Cloth Tubular Elements	16
7	Aluminum Matched Metal Molds Used To Fabricate Tubular Elements	17
8	Jigging Used To Cut Tubular Elements to Final Dimensions	17
9	End Attachments	18
10	Aluminum Matched Metal Molds Used To Fabricate End Attachments	18
11	Exploded View of Aluminum Matched Metal Molds Used To Fabricate End Attachments	19
12	Final Assembly Jigging	19
13	Bellcrank Being Assembled	20
14	Completed Bellcrank	20
15	Typical Failure Mode	20

## INTRODUCTION

Reference 1 reports the development of a CH-47 forward bellcrank using fiberglass tubular/sandwich construction, which demonstrated improved ballistic tolerance, reduced weight, and potentially lower production costs as compared to metal bellcranks.

The primary purpose of this investigation was to develop manufacturing methods for the tubular/sandwich bellcrank concept with the goals of optimizing production costs and weight, while achieving structural repeatability.

Criteria for structural and ballistic impacts, which were developed in the previous investigation,<sup>1</sup> remained the same. In order to demonstrate that the structural objectives were met, static, dynamic, and ballistic tests were conducted at  $-65^{\circ}F$ ,  $75^{\circ}F$ , and  $180^{\circ}F$ .

### DEVELOPMENT OF FABRICATION PROCEDURES

#### BELLCRANK

The basic tubular concept developed in Reference 1 was selected for further study since it permitted straightforward use of existing low-cost fabrication techniques. A schematic of the tubular bellcrank is shown in Figure 1, and a detailed drawing of the bellcrank is presented in Appendix I. Prepreg cloth, 181-style, was used in the construction of all components of the bellcrank except the bearings and bearing sleeves. Complete material properties and cure cycles are presented in Appendix II. The bellcrank consisted of three major elements: face sheets, tubular members, and end attachments. In all cases, matched metal molds were used to fabricate the major elements. The elements were then assembled and bonded using FM-1000 adhesive (see Appendix III). The fabrication of each element is discussed in detail in the following sections.

2

### FACE SHEETS

Although research indicated that the concept developed in Reference 1 provided significant increases in ballistic tolerance, one deficiency was observed during ballistic testing in that investigation. It was found that when the projectile impacted the tubular portion of the bellcrank, it invariably caused gross delamination of the exit face sheet (see Figure 2). Numerous adhesive systems and overwrapping techniques were used in Reference 1 to no avail. No distinguishable differences in the extent of delamination were observed between ductile or brittle adhesive systems.

In the current program, it was found that preferential slotting of the exit face (see Figures 3 and 4) confined the delamination to the impact area. The slotting did not significantly reduce the undamaged structural strength, since the face sheets were designed as secondary load paths in the event of tube failure. The forward bellcrank is located close to the transmission housing and, as such, can be impacted only from one side. Since the delamination occurs only on the exit face, it was necessary to slot only that face for this application.

The spacing of the slots was selected as a function of the length of a fully tumbled round. In this case, the maximum threat was assumed to be a fully tumbled .30 caliber AP projectile that was 1.44 inches long. The slot spacing was slightly larger than onehalf the length of the projectile (.75 inch). In this manner, the maximum length that could be lost (delaminated) was 2.25 inches or approximately 1.6 times the tumbled length. The length of the slot (approximately 1-1/8 inches) was slightly larger than the width of the tubulat element.

The face sheets were fabricated in pairs using matched metal molds as shown in Figure 5. Three plies of prepreg 181 cloth were pattern cut to size and placed in the molds to form the stepped doublers for the attachment and pivot bearing areas. Four additional plies of 181 cloth were pattern cut and placed in the molds to complete the face sheet.

J. P. Steve's style-6 fiberglass peel ply was used on all surfaces that would later be bonded. The matched metal molds were placed in a press and the face sheets cured in accordance with Appendix II. The slots were cut in the exit face with a 100-grit diamond bandsaw after curing. This completed the fabrication of the face sheets, which were then ready for final assembly.

#### TUBULAR ELEMENTS

The tubular elements were wound with six plies of 181 cloth on a square mandrel, as shown in Figure 6. Again, peel ply was used. The uncured tube/mandrel was placed in the matched metal molds and placed in the press for curing (see Figure 7). After curing, the mandrels were removed and the angles on each tube were cut to final dimensions to allow assembly into a triangular platform, using the jigging shown in Figure 8. The slots to accept the end attachment were then cut, completing the operation.

#### END ATTACHMENTS

The end attachments shown in Figure 9 were fabricated in pairs in the matched metal mold shown in Figures 10 and 11. Eight-ply triangular-shaped doublers were integrally fabricated as part of the end attachments. These doublers served to align the tubular element during final assembly and to provide additional stiffening and bond area for the face sheet. The end attachments were four plies thick on the output attachment and twelve plies thick on the input attachment.

#### BEARINGS

Standard sleeve bearings as used in the existing metal bellcrank were used. The pivot bearing was designed to offset the bellcrank in order to permit fit and function in the CH-47 helicopter. Details of pivot bearing assembly are shown in Figure 1 and Appendix I. The internesting metallic sleeves holding the three pivot bearings were die formed (two step) from annealed 6061 aluminum. After forming, the sleeves were heat treated to the T6 condition. Ballistically tolerant bearings have been developed (see Reference 1). However, due to the fit and function requirement, they were not incorporated; rather, the existing metallic fitting was used.

#### FINAL ASSEMBLY

Final assembly was achieved by placing the elements in a precision positioning jig, as shown in Figures 12 and 13. FM-1000 adhesive was used in all bonded areas. The FM-1000 adhesive was cured in a hydraulic press at 350°F and with a nominal pressure on the bonded areas of 50 psi. After curing, the completed assembly was precision jig trimmed to final dimensions in a tensile cutter (high-speed router). Holes for the pivot and sleeve bearings were then jig drilled. The pivot bearing assembly was coated with Epon 828 resin/DTA catalyst and was inserted in the bellcrank, and the retainer sleeve was press-fit into place. The sleeve bearings for the input and output attachments were slip-fit into place. No adhesive was used since the bearings are designed to slide to accommodate and position the self-aligning rod end bearings. The completed bellcrank is shown in Figure 14.

•

. . .

: -

•

## COST AND WEIGHT ESTIMATES

## COST

The cost estimates are based on using high-volume production techniques, such as die-cutting the fiberglass cloth to shape, using jig positioning of material and cured elements, and using rapid-cure resin systems. Table I presents an estimate of the materials and man-hours required. Costs were estimated at \$8.00/hour, which includes overhead, G&A, and profit.

TABLE I. COST ES		
Materials		Cost (\$)
Prepreg 181-style fiberglass cloth, 2.5 sq yd		50.00
FM-1000 film adhesive, 120 sq in.		2.00
Aluminum alloy for pivot hearing sleeve		1.00
Bearings, 3 @ \$1.20		3.60
		56.00
Fabrication	Hours	Cost (\$)
Die cutting of fiberglass cloth (face sheets and end attachments)	.2	1.60
Placing fiberglass cloth in dies	.4	3.20
Curing (based on RF cure)	.05 Equip Time	•
Tube fabrication, including curing	.04	3.20
Cutting tubular elements to finished dimensions	.1	.80
Jig assembly of face sheets, tubular elements, and end attachments	.1	.80
Curing	1.0 Equip Time	
Final trim	.1	.80
Fabrication of pivot bearing sleave	.1	.80
Installation of bearing	.1	.80
	2.19	12.00
Total		68.60

5

The total estimated cost, \$68.60, compares favorably with the metal bellcrank cost, approximately \$135.00.

#### WEIGHT

The completed weight of the tubular/sandwich bellcrank was 1.65 pounds as compared to 3.4 pounds for the existing magnesium bellcrank, which amounts to a weight reduction of 52 percent. Nominal additional weight savings could be achieved if the pivot attachment fitting was modified to eliminate the need for the pivot bearing offset.

### GENERAL REMARKS

The fabrication procedures used for the fiberglass bellcrank show that both cost and weight savings are achievable using the tubular/sandwich construction. The remainder of this memorandum covers the testing that was conducted to demonstrate the structural adequacy of the bellcrank.

#### TEST EQUIPMENT AND PROCEDURES

### GENERAL

The existing CH-47 forward bellcrank is subjected to flight loads typically less than 100 pounds. The highest measured values have not exceeded 135 pounds. The maximum possible load that can be applied to the bellcrank is 562 pounds. However, the controlling factor is the parked load condition when the hydraulic boost has bled down. Under the worst conditions, the component can be subjected to a compressive load of approximately 2000 pounds.

In a contractual research program conducted by Boeing-Vertol, the proof loads have been set at 1860 pounds for static compression and  $\pm 350$  pounds for dynamic loading. Since strength is reduced about 40 to 50 percent at elevated temperature, the bellcrank studied in this program was designed for a load of -4000 pounds at room temperature and  $\pm 350$  pounds for dynamic loading. The design load of -4000 pounds at room temperature was selected to obtain a reasonable degree of assurance that the bellcrank could withstand a 2000-pound load at 180°F (operational requirement).

An elevated temperature of approximately 180°F was achieved by placing banks of heat lamps on both sides of the bellcrank being tested. Temperature probes indicated that the temperature was uniform to within ±5°F over the entire bellcrank. Each bellcrank was allowed to soak at temperature for approximately 2 hours prior to testing.

A low temperature of approximately  $-65^{\circ}F$  was achieved by surrounding the bellcrank with a sheet-metal container filled with a slurry of crushed dry ice and alcohol. Thermocouples placed inside the bellcrank indicated that the temperatures were uniform to within  $\pm 10^{\circ}F$ . Due to the difficulty of maintaining uniform temperatures for prolonged periods, testing was initiated as soon as the specimen reached the desired temperature.

Under combat conditions, the probability of a helicopter's receiving more than two ballistic hits in a single area is small. After a hit, an arbitrary requirement of 30 minutes of flight time was considered to be sufficient to get the damaged helicopter back to base, or at least into safe territory. Typically, 100 load cycles at  $\pm 100$ pounds might be experienced during this period. In this program, the specimens were subjected to fully tumbled impacts at 1800 feet per second, which has been shown to be the most damaging velocity. Following the ballistic tests, a minimum of 10,000 load cycles at  $\pm 350$  pounds were applied.

Environmental degradation of the bellcrank was not considered as an important design consideration, since the materials, i.e., fiberglass, epoxy, and film adhesives, used in construction have been subjected to environmental testing and have demonstrated

7

essentially no degradation. Seven fiberglass bellcranks were manufactured for testing; two metal bellcranks were tested as baselines. Static, fatigue, and ballistic tests were conducted on the bellcranks according to Table II.

Bellcrank	Test Temp (°F)	Ballistic (1)	Fatigue (2)	Static (3)
1	75			×
2	75			x
3	180			x
4	- 80*			x
5	75	x	x	x
6	180	x	x	x
7	- 65	x	x	×
8 (metal)	75	x	x	×
9 (metal)	75	×		

#### BALLISTIC TESTS

The bellcranks were impacted with fully tumbled .30 caliber armor-piercing ammunition at an approximate velocity of 1800 feet per second. Tumbling of the projectiles was achieved with a smooth-bore rifle with the barrel end cut at an angle. Projectile velocities were measured with electronic witness plates spaced 4 feet apart and with a high-speed digital counter. Photographs of each ballistic test were taken with a l6mm Fastex camera operating at 18,000 frames per second.

## STATIC AND FATIGUE TESTS

A 10,000-pound-capacity closed-loop hydraulic test machine was used to perform the static and fatigue tests. Loads were monitored with a Brush recorder, a recording oscilloscope, and an X-Y plotter. Cyclic frequency for all fatigue tests was 1 hertz. Static preloads for the ballistic tests were achieved by hanging weights on the ouput bearing of the bellcranks.

#### TEST RESULTS

#### FIBERGLASS TUBULAR BELLCRANK

In general, the fiberglass tubular bellcranks behaved as anticipated, based on the results in Reference 1. Test results are presented in Table III. The "slotting" technique limited the damage to only those "tabs" (material between slots) that were impacted. Temperatures of approximately  $-65^{\circ}F$  resulted in the highest failing loads. The results for both the undamaged and the ballistically damaged bellcrank at  $-65^{\circ}F$  were identical. The lowest failure loads were recorded at  $+180^{\circ}F$ . In the undamaged specimen at  $+180^{\circ}F$ , an FM-1000 adhesive failure was observed between the skin and the tubular elements. This was the only test in which the primary mode of failure was an adhesive failure. Typically, a shear failure of the skin and tube in the pivot area was observed (see Figure 15).

In the ballistically impacted specimens, an attempt was made to sever the tubular element between the pivot bearing and the output bearings. Although the bellcranks were capable of withstanding cyclic and static loads far in excess of flight load in the damaged condition without failure or signs of crack propagation, the deflections measured at the input bearing were more than desired (see Table III). In the case of bellcrank 7, in which the tubular element was not totally severed, the measured deflections were approximately 4.7 times smaller than those in bellcranks in which total severing of the tube occurred. Use of a rectangular tubular element, in which the frontal dimension is greater than the dimension of the fully tumbled threat, would prevent total severing of the element on ballistic impact and would thus reduce the deflections to a more acceptable range.

#### METAL BELLCRANK

A study conducted under contract, Reference 2, indicated that the existing metal forward bellcrank of the CH-47 was one of the four most vulnerable components in that flight control system. Limited tests conducted on the two standard metal bellcranks tested to provide baseline data for this program indicate that the metal bellcranks can survive a .30 caliber threat (see Table III, bellcranks 8 and 9). Impacts at approximately 1700 feet per second on the thinnest legs of the bellcranks were insufficient to cause complete failure. Muzzle velocity (-2750 feet per second) impacts were sufficient to cause through failure of the thinner legs, but only 80 percent failure of the thickest leg. Even with two nonthrough impacts and one through impact, the bellcrank was capable of operating at  $\pm 350$  pounds (approximately three times flight load) without appreciable deflections or indications of crack propagation. A second bellcrank (No. 8) failed at 8000 pounds after an 80 percent loss of the thickest leg. Impacts in the bearing areas, which represent a relatively small percentage of the total frontal area of the bellcrank, could, where the frontal area is less than the dimension of the tumbled threat, result in complete severing of that area. Impacts in the metallic bearings themselves normally result in bearing seizure.

Although the metal bellcranks demonstrated that they could continue to function after a .30 caliber impact, it was consistently observed that, upon impact, an extensive flash occurred. In an unpublished study, similar impacts on other magnesium components produced flashes that were more than adequate to ignite a fuel/vapor mixture. Obviously, the condition represents a serious safety threat. The fiberglass bellcranks, on the other hand, being designed to allow the projectile to pass with a minimum of resistance, did not cause any flash.

ę

•

						TAB	LE III. TES'	r results				
			Ballistic C	onditions			Fatigue			Failure		
Belicrank	Tento Official	Type	9 9	% Tumb	(fps)	Hertz	<b>be</b> (8)	Cycles	(in) Defi	(Input)	Remarks	
1 (without slotted exit face)	75					-	- 2070(1) + 700			-4300(2)	Slight local failure (bearing type) at input attachment due to fatigue loading. At 4100 pounds, loud pop occurred; load dropped to 3200 pounds, increased to failure; failed at pivot beering attachment.	
7	75									-4700	Failed at pivot bearing attachment.	
n	180									-2550	Adhesive failure between face sheet and tube in short leg.	
•	Ŗ									-4900	Failed at pivot bearing; pertial debond between face sheet and tube in short leg.	
ŝ	75	(1) AP (1)	-350	Full	1804	-	±200(2)	5000	10.15		Test terminated at end of step (6).	
						-	±400(3)	5000	14			
						۲.	-1250(4)	-	.15			_
						۰.	+600(5)	-	8			-
						-	(9)0067	830	1.53			
ω	180	(1) AP (1)	-360	Full	1820	-	1350	10, 000	±14	-1300(2)	Spec. overloaded at start of fattigue test, causing rips in each face sheet approx. 3 in. long. No crack propagation due to cycling; buckling failure of skins.	
7	8	.30 AP(1)	990-	Full	1756	-	±360(3)	10,000		-4900(4)	Two impacts did not sever tubular element. Failed	
		.30 AP(2)	-360	Full	1700				±03		in impect area.	_
8 (metal)	75	30 AP(1)	- 360	Full	2768	-	±350(2)	10,000		Approx. 8000(3)	Impacted thickest section approx. 80% penetration. Failed at impact area.	
9 (metal)	75	30 AP(1)	-350	75	1716						Shots 1 and 2 did not totally sever thin legs. Shot 3	
		30 AP(2)	99 j	75	1707						caused through tenue.	
		.30 AP(3)	985	Full	5082						والمنابعة والمنافعة والمستعملين والمنافعة المنافعة والمنافعة والمنافعة والمنافعة والمنافعة والمنافعة	-+
Numbers in part Sign convention:	-indicate	lenote test ser es push on inp	quence. sut bearing	I, + indicates p	oull on input l	bearing.						
												-

## CONCLUSIONS

It is concluded that:

- 1. Ballistically tolerant bellcranks, capable of satisfactory operation at -65° to 180°F after sustaining a fully tumbled .30 caliber impact, can be fabricated using fiberglass tubular element/sandwich construction at substantially less cost and weight than a metal bellcrank.
- 2. "Slotting" localizes ballistic damage to the impact area and eliminates gross delamination of the exit face sheet of a bellcrank.
- 3. Rectangular tubular elements having a frontal dimension greater than the length of a fully tumbled projectile must be used in future components to prevent total severing of the tubular elements, thus reducing the bellcrank deflections due to operational loads.
- 4. Based on limited data, the existing metal bellcrank can survive a .30 caliber impact, with the exception of the bearing attachment areas; however, flashing consistently occurs upor impact sufficient to cause ignition of a fuel/vapor mixture, thus increasing the threat of in-flight fires. No flashing occurs in the fiberglass bellcranks.

## LITERATURE CITED

- 1. Figge, I. E., Sr., EVALUATION OF TWO BALLISTICALLY TOLERANT FOR-WARD BELLCRANK CONCEPTS FOR THE CH-47 HELICOPTER, USAAMRDL Technical Report 71-63. Fustis Directorate, U. S. Army Air Mobility Research and Development Labora Fort Eustis, Virginia, November 1971, AD 893206L.
- 2. Gonsalves, J., FLIGHT CONTROLS SURVIVABILITY (U), Vertol Division, The Boeing Company; USAAVLABS Technical Report 67-54, U S. Army Aviation Materiel Laboratories, Fort Eustis, Virginia, December 1967, AD 391238L (Confidential).



Figure 1. Exploded View of Square Tube Bellcrank.



5 -

Figure 2. Delamination of Exit Face Sheet Caused by Tumbled .30 Caliber Impact.



Figure 3. Localized Delamination of Exit Face Sheet Resulting From "Slotting".



Figure 4. Edge View of Two .30 Caliber Impacts of Slotted Tubular Bellcrank (Note Minimal Delamination).





Figure 5. Aluminum Matched Metal Molds Used To Fabricate Face Sheets.



Figure 6. Winding of Glass Cloth Tubular Elements.



Figure 7. Aluminum Matched Metal Molds Used To Fabricate Tubular Elements.



Figure 8. Jigging Used To Cut Tubular Elements to Final Dimensions.



Figure 9. End Attachments.



1.1

Figure 10. Aluminum Matched Metal Molds Used To Fabricate End Attachments.



Figure 11. Exploded View of Aluminum Matched Metal Molds Used To Fabricate End Attachments.



Figure 12. Final Assembly Jigging.



Figure 13. Bellcrank Being Assembled.



Figure 14. Completed Bellcrank.



Figure 15. Typical Failure Mode.

APPENDIX I DETAILED DRAWING OF TUBULAR BELLCRANK



21



0

\_\_\_\_\_

## APPENDIX II PROPERTIES AND CURE CYCLES FOR 181-STYLE PREPREG CLOTH

### WBC 3201

### DESCRIPTION

WBC 3201 is an epoxy-novolac resin reinforced with fiberglass fabric.

POLYMER: Epoxy-novolac.

REINFORCEMENTS: Normally supplied on 181/Volan A glass but is available on various other types of reinforcements.

AVAILABILITY: Tapes and broadgoods.

## **RECOMMENDED APPLICATIONS**

WBC 3201 is a general-purpose epoxy-novolac based compound which produces excellent laminates for use at temperatures of up to 400°F. Laminates produced from WBC 3201 exhibit outstanding mechanical properties, including high interlaminar shear strength. This material is easily bonded to various substrates, including copper sheet, and has been used successfully in many electronic applications.

## **TYPICAL PHYSICAL PROPERTIES**

<b>Resin Solids Content</b>	%	WBC Method R <sub>3</sub>	36-44
Flow	%	WBC Method F <sub>1</sub>	12-20
Volatiles Content	%	WBC Method V <sub>3</sub>	3 Max
Tack (Minimum)		Seconds	30
Drape (Minimum)		Inches	8/32

#### TYPICAL PROPERTIES OF LAMINATES

. .

	ASTM METH	HOD
Flexural Strength (RT), psi Flexural Strength, psi (aged @	D-790-59T	90,000
300°F for ½ hr)	D-790-59T	60,000
Flexural Modulus (RT) × 10 <sup>6</sup>	D-790-59T	3.7
Flexural Modulus X 10 <sup>6</sup> (aged		
@ 300°F for 1/2 hr)	D-790-59T	3.0
Tensile Strength (RT), psi	D-638-61T	58,000
Tensile Strength, psi (aged @		
300°F for ½ hr)	D-638-61T	45,000

Preceding page blank

### 23

## TYPICAL PROPERTIES OF LAMINATES - Continued

# ASTM METHOD

Compressive Strength (RT)	D-695-54	55,000
(aged @ 300°F for ½ hr)	D-695-54	33,000
Dielectric Constant IMC	-	4.56
Arc Resistance, sec	-	100

## CURE CONDITIONS

WBC 3201 can be successfully cured under a wide range of conditions; the following cure cycle is typical and is adequate for most applications:

	Initial Cure		Post Cure	
Pressure (psi)	Temp (°F)	Time (hr)	Temp (°F)	Time (hr)
5-50	325	3	350	1

## APPENDIX III

## PROPERTIES AND CURE CYCLES FOR FM-1000 STRUCTURAL ADHESIVE FILM

#### PROPERTIES

FM-1000, an unsupported film, is designed for structural bonding of both sandwich and all-metal constructions.

Physical strengths (shear strength over 12,000 psi on steels and peel strengths up to 300 inch-pounds on metal sandwich) are obtainable under a wide variety of processing conditions. Proper design of aluminum structures allows the metal to be stressed to or near ultimate strength levels. Low-temperature peel strength is particularly note-worthy.

FM-1000 adhesive film has been completely evaluated against the requirements of MIL-A-5090D and found to surpass all requirements by an extremely wide margin.

FM-1000 adhesive film may be used for bonding of all metals (including copper), wood, most plastics, and all available sandwich combinations.

Primer is not required for either face or core. However, two primers are available for use where processing requires "tacking" of film in place or protection of cleaned details. A slight increase in all properties results. BR-1009-8 is used for "tack" assembly at room temperature, while BR-1009-49 is used for "heat tacking" at 175°F.

#### CURING PROCEDURE

- 1. Primer is unnecessary. Where desired, a single roller or sprayed cross coat is adequate.
- 2. FM-1000 adhesive film is placed between surfaces to be bonded. Colored separator may be removed at any time before closing the assembly.
- 3. In general, FM-1000 should be cured for 60 minutes at 315° to 350°F, under 5 to 50 psi pressure. A typical bonding cycle might use a 1-hour heat-up to 340° ± 10°F and a cure of 1 hour at top temperature. Bonding conditions may vary considerably, with heat-up rates ranging from 0 to 180 minutes and curing temperatures ranging from 315° to 400°F. Curing time, of course, is a function of cure temperature. In this program, a cure cycle of 60 minutes at 350°F and 50 psi was used in conjunction with BR-1009-8 tack primer.