UNCLASSIFIED

AD NUMBER

AD814417

NEW LIMITATION CHANGE

TO

Approved for public release, distribution unlimited

FROM

Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; Jan 1967. Other requests shall be referred to Air Force Aero Propulsion Laboratory, Attn: APFL, Wright-Patterson AFB, OH 45433.

AUTHORITY

AFAPL ltr, 12 Apr 1972

THIS PAGE IS UNCLASSIFIED

AD8144

FILE COPY

14121

त !

ġ

THE ROLE OF ADSORPTION IN THE CATALYTIC PARA-ORTHO HYDROGEN CONVERSION

HERBERT R. LANDER, JR.

TECHNICAL REPORT AFAPL-TR-06-142

JANUARY 1967

This document 's subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of the Air Force Aero Propulsion Laboratory (APFL), Wright-Patterson Air Force Base Ohio.

MAY 2 6 1967

AIR FORCE AERO PROPULSION LABORATORY RESEARCH AND TECHNOLOGY DIVISION AIR FORCE SYSTEMS COMMAND WRICHT-PATTERSON AIR FORCE BASE, OHIO

NOTICES

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely rela $\pm d$ Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.



Copies of this report should not be returned to the Research and Technology Division unless return is required by security considerations, centractual obligations, or notice on a specific document.

400 - April 1967 - CO192 - 28-646

THE ROLE OF ADSORPTION IN THE CATALYTIC PARA-ORTHO HYDROGEN CONVERSION

p. (11)

HERBERT R. LANDER, JR.

Ę

٠

This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of the Air Force Aero Propulsion Laboratory (APFL), Wright-Patterson Air Force Base, Ohio.

FOREWORD

1 112

This report was propared as part of the in-house research on unconventional aerospace fuels by the Fuels, Lubrication, and Hazards Branch, Support Technology Division of the Air Force Aero Propulsion Laboratory.

This analysis was performed under Project 3048, Aerospace Fuels, Task 304802, Un-

This report was submitted by the author 7 December 1966.

Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.

Arthur V. Churchill ARTHUR V. CHURCHILL,

ARTHUR V. CHURCHILL, Chief, Fuels, Lubrication and Hazards Branch Support Technology Division

AFAPL-7'R-66-142

. . .

ABSTRACT

44

Adsorption isotherms of the form

$$C_{A} = \frac{L'K'(P_{A})^{n}}{1+K'(P_{A})^{n}}$$

were determined for two para-ortho-hydrogen conversion catalysts, hydrous ferric oxide gel and nickel oxide silicate, at temperatures from 63° K to 196° K and at pressures from 1 to 10 atmospheres.

For the catalysts studied, Langmuir's isotherm holds at 194.6° K, while at lower temperatures (approximately $60-90^{\circ}$ K), the adsorption mechanism appears to be one where two molecules are adsorbed on five effective centers.

(Distribution of this abstract is unlimited)

9 XOT 1713 8 /

<u>a – Indersetter</u> Liter (* 1995)

÷

• • ±-

AFAPL-TR-66-142

TABLE OF CONTENTS

.- .-

SECTION	-	PAGE
I INTRODUCTION		. 1
General Information		1
Objectives of Report		2
II PROCEDURE FOR DETERMINING THE CONCENTRATION OF ADSORBED HYDROGEN AT VARIOUS TEMPERATURES AND FRESSURES		3
III. CONCLUSION		5
APPENDIX ILLUSTRATIONS AND TABLES		7
REFERENCES		27

同論の

ž

, - Janaa Jaar

*= _____

ILLUSTRATIONS

. . .

العربية الم معربية الإن معينها

The second se

. -

FIGURE		PAGE
1.	Equilibrium Para-Hydrogen Concentration As a Function of Temperature	9
2.	Enthalpy Vs. Temperature for Equilibrium, Para, and Normal Hydrogen at 1500 PSIA	10
3,	Reciprocal Plot of Isothermal Adsorption Data for Hydrogen on Hydrous Ferric Oxide Gel Catalyst	19
4.	Reciprocal Plot of Isothermal Adsorption Data for Hydrogen on Nickel Oxide Silicate Catalyst	20
5.	Correlation of Hydrogen on Hydrous Ferric Oxide Gel According to Equation (2)	21
6.	Correlation of Hydrogen on Nickel Oxide Silicate According to Equation (2)	22
7.	Effect of Temperature on the Constant K'	25

≓ _,

į.

1.1

andra andra Bergaria

LIST OF TABLES

÷

.

1410 1210 1200

TABLES	S	PAGE
I	Adsorption Data for Hydrogen at 63.16°K With Hydrous Ferric Oxide Gel as Catalyst	11
Ш	Adsorption Data for Hydrogen at 77°K With Hydrous Ferric Oxide Gel as Catalyst	12
ш	Adsorption Data for Hydrogen at 87.8°K With Hydrous Ferric Oxide Gel as Catalyst	13
IV	Adsorption Data for Hydrogen at 194.6°K With Hydrous Ferric Oxide Gel as Catalyst	14
v	Adsorption Data for Hydrogen at 63,16°K With Nickel Oxide Silicate as Catalyst	15
VI	Adsorption Data for Hydrogen at 77°F With Nickel Oxide Silicate as Catalyst	16
VII	Adsorption Data for Hydrogen at 87.8°K With Nickel Oxide Silicate as Catalyst	17
VШ	Adsorption Data for Hydrogen at 194.6°K With Nickel Oxide Silicate as Catalyst	18
IX	Values of L'and n	23
x	Values of K'	24
XI	Adsorption Isotherms for Hydrogen	26

¥11

115.5

SECTION I

INTRODUCTION

GENERAL INFORMATION

The existence of the para and ortho modifications of molecular hydrogen is a direct result of the orientation of the nuclear spins associated with the hydrogen atoms of the molecule. In molecular hydrogen, the nuclear spins of the individual atoms are oriented either in the same direction (parallel), which corresponds to the ortho modification, or in the opposite direction (antiparallel), which corresponds to the para modification. These two orientations of nuclear spins are responsible for the differences in the magnetic and the thermal properties of ortho and para modifications of molecular hydrogen. An equilibrium, which is a function of temperaturo, exists between the two forms.

Under equilibrium conditions, shown graphically in Figure *1, the para-hydrogen concentration in the pure hydrogen gas varies from essentially 100% para at 36°R to approximately 25% para at 270°R. Since the para to ortho-hydrogen conversion is endothermic in this temperature range (339 calories per mole), certain additional low temperature refrigeration is available from the conversion. Interest in the conversion of hydrogen stems from the heat of conversion when the reaction proceeds at low temperatures.

Many of the next generation of aerospace vehicles will use hydrogen as a fuel or propellant. At high flight speeds, the problems associated with cooling air-breathing aircraft engines and other parts will become critical. Problems will be encountered in cooling the walls of the combustion chamber and the exhaust nozzle. The hydrogen fuel will be the most logical reservior available to absorb brat and thereby provide the critically needed cooling capacity. In many engines under consideration, the hydrogen must be vaporized and superheated in order to obtain sufficient heat-absorbing capacities per pound of fuel. If the para-ortho shift of the hydrogen could be obtained below a temperature of 270°R, the effective heat sink capacity

*Illustrations and tables are in the appendix.

of hydrogen would be greatly increased, and the required size of the heat exchanger could be reduced.

The relative eathalpies of para, equilibrium, and normal hydrogen are shown in Figure 2. The differences in the enthalpies of hydrogen of the various compositions represent the enthalpy change due to conversion, if the hydrogen is used in a refrigeration circuit which does not contain a conversion catalyst, the temperatureenthalpy path will follow the para curve. However, if a conversion catalyst is included in the system, causing the temperatureenthalpy path to follow the equilibrium curve, significantly greater quantities of refrigeration can be provided by the hydrogen at low temperatures. The successful application of this conversion could increase payload because of reduction in the weights of heat exchangers. The strategic incorporation of this concept in heat exchanger equipment would alleviate "pinch-point" areas by increasing available refrigeration and, therefore, the driving force which causes the flow of heat.

Low-temperature heterogeneous catalysis was considered the most promising technique for effecting the para-ortho shift of hydrogen.

Early studies involved the characterization of the conversion catalysts for use in the production of a large quantity of liquid parahydrogen. In this process, normal hydrogen (equilibrium hydrogen at standard temperature contains approximately 25% parahydrogen and 75% ortho-hydrogen) is converted to the corresponding equilibrium hydrogen (approximately 100% para-hydrogen) at liquid hydrogen temperatures (approximately 36°R). This process step is included in the production of liquid hydrogen, since failure to convert the normal hydrogen to the equilibrium concentration would result in the conversion occurring slowly during storage. Since this particular reaction (normal to 99.79% para-hydrogen) is exothermic with a

heat release of 226 BTU/lb, the liquid hydrogen would boil away even if it were stored in a perfectly insulated container. For this reason, the conversion from orthohydrogen to para-hydrogen is made during the production cycle, and the liberated heat is taken away at this time. Chromium oxide supported on alumina was found to be effective for this conversion, however, a systematic study was undertaken to find materials which might be more effective.

Various metallic oxides such as cerium oxide, ferric oxide, neodymium oxide, and manganese dioxide, both supported and unsupported, were studied. Unsupported hydrous ferric oxide proved to be the most effective conversion catalyst of those studied. A space velocity of 330 STP/minute was achieved with 1/8-inch pellets of this material (Reference 3).

In early 1960, the U.S. Air Force, with its increasing interest in the use of hydrogen as an air-breathing engine propellant, recognized the intriguing possibilities of recovering the available refrigeration from parahyprogen fuel and initiated a program to develop catalysts (at Air Products and Chemical Inc.) to obtain additional cooling from the para-ortho shift. This work was carried out under contract AF33(616)-7506 and later under contracts AF33(657)-10333 and AF88(615)-1816. The objectives of the investigation were to determine the paramsters that effect the shift of para-hydrogen to ortho-hydrogen and to develop a catalyst for speeding the shift toward the equilibrium ratio at low temperatures. The hydrous ferric oxide gel developed for the ortho to para hydrogen shift in commerical plants was found to be effective also for the desired para to ortho hydrogen shift and was chosen as a baseline in the study.

According to theories formulated, there are two fundamental methods of inducing an orthoto-para or para-to-ortho transition. One method consists of dissociating the hydrogen molecules and allowing the atoms to recombine. When dissociated, the two atomic nuclei no longer are oriented with respect to nuclear spins. Upon reassociation, the molecules are formed according to the equilibrium energy distribution determined by the temperature. The other method involves the interaction between an inhomogeneous magnotic field and the magnetic field associated with the nuclear spin of the hydrogen nuclei. The dissociation or chemical mechanism is catalyzed by any method which is capable of producing hydrogen atoms or at least of destroying the molecular bond between the two nuclei. The magnetic or physical mechanism is catalyzed by any inhomogeneous magnetic field of molecular dimension.

Air Products and Chemicals Inc. developed a nickel oxide silicate catalyst which was 10.5 times more active on a weight basis than the standard hydrous ferric oxide gel.*

OBJECTIVES OF REPORT

In this report, the author will attempt to analyze the hydrogen adsorption date tabulated in Reference 5**, for both the advanced nickel oxide silicate catalysi and the commercial hydrous ferric oxide gel. The analyses will be directed toward determining the adsorption isotherm and gaining an understanding of the possible mechanism for the important adsorption step at the low temperatures of interest. The analyses will follow the approach of Koble and Corrigan (Reference 4) in conjunction with adsorption data for pure hydrocarbons. The author has taken the Koble-Corrigan approach to develop an expression for determining the concentration of hydrogen adsorbed at various temperatures and pressures.

**From Reference 5 the data used was equilibrium pressure in atmospheres and volume adsorbed (STP) ml/gm (ca') which are shown in Tables 1 through VIII in this technical report.

Recent efforts by the contractor have resulted in a nickel oxide catalyst that was 29 times more active, on a weight basis, than the standard.

SECTION II

FROCEDURE FOR DETERMINING THE CONCENTRATION OF ADSORBED HYDROGEN AT VARIOUS TEMPERATURES AND PRESSURES

In Reference 4 a general form for an adsorption isotherm was formulated and is

$$C_{A} = \frac{L'K'(p_{A})^{n}}{1 + K'(p_{A})^{n}} \qquad (1)$$

whera

- C_A = concentration of adsorbed gas moles per gram of catalyst
- L' = empirical adsorption constant related to the total number of active centers available on the adsorbent
- K' = empirical adsorption constant related to the equilibrium constant
- n = a constant
- p_A = equilibrium pressure of the adsorbed gas

Adsorption data for hydrogen on both the commercial hydrous ferric oxide gel catalyst and the advanced nickel oxide silicate inaterial will be used in conjunction with Equation (1), and the various constants will be detormined.

Equation (1.) is inverted and rearranged to give

$$\frac{1}{C_A} = \frac{1}{L'} = \frac{1}{L'K'} \left(\frac{1}{P_A}\right)^n \qquad (2)$$

The original data were reported in Reference 5 as volume of gas adsorbed, in milliliters at standard conditions, and the equilibrium pressure, in atmospheres, of the hydrogen in contact with the catalyst. The adsorption data for the two catalysts at four different temperatures are presented in Tables I through VIII, together with the manipulations necessary for the later treatment of the date.

The approximation of the constant L^2 for a given catalyst is given in Figures 3 and 4 for

the standard and advanced materials, respectively. L' is determined from the rectangular plot $1/C_A$ versus $1/p_A$.

Figure 3 is a plot of $1/C_A$ versus $1/p_A$ for

three of the four test temperatures for the hydrous ferric oxide gel. The intercept was determined to be 0.025; this value could have ranged from approximately 0.020 to 0.040according to the data reported. That L' is a constant independent of temperature is demonstrated by Figure 3, where the various isotherms converge on apparently the same intercept.

Figure 4 is a plot of $1/C_A$ versus $1/p_A$ for the hydrogen adsorption on the advanced nickel oxide silicate catalyst. Here, again, the isotherms converge on the same intercept which was determined to be 0.0105. This strengthens the concept that L' is a constant

and is independent of temperature.

The quantity $(1/C_A - 1/L')$, from Tables I through VIII, is plotted versus $1/p_A$ on logarithmic coordinates for the four temperatures studied. Figure 5 is the correlation for the commercial hydrous ferric oxide, and Figure 6 is a similar plot for the advanced nickel catalyst. Koble in Reference 4, recommended that the value of L' be corrected by trial and error until the plot of log $(1/C_A - 1/L')$ ersus $1/p_A$ gave a straight line. This procedure was not followed with this data since the adjustment of L' could not straighten out all of the curves, which indicates that mechanisms were changing with both pressure and temperature.

The isotherms for the adsorption on the catalysts studied are parallel for the 63.16, 77.0, and 87.8°K over a pressure range of approximately 1 to 10 atmospheres; data beyond this region were inconclusive and indicated possible changes in the slopes of the curves.

According to Koble's derivation of Equation (1), n should be either an integer or a fraction composed of small integers. Table IX presents the slopes of the isotherms from Figure 5 for the commercial catalyst and similar data from Figure 6 for the advanced catalyst. These data indicate that the adsorption mechanism changes from the lower temperatures to the higher one for both catalysts tested; in fact, the same type of adsorption seems to be taking place in both catalysts.

Hydrogen adsorption on both catriysts at 194.6°K follows the Langmuir Isotherm, which has been defined as a specific case of the general adsorption expression (Equation 1), where n is equal to unity. The mechanism for the hydrogen adsorption at this temperature is

$$H_{1} + \mathcal{L} = H_{1} \mathcal{L} \qquad (3)$$

where \mathcal{A} is an active center. The expression relating concentration of the adsorbed gas to its equilibrium partial pressure is

$$C_{H_{\frac{2}{2}}} = \frac{K' L' PH_{\frac{2}{2}}}{I + K' PH_{\frac{2}{2}}}$$
(4)

At lower temperatures (60-90°K) for both catalysts tested, the adsorption mechanism resemblos the following:

$$2H_{2} + 5\mathcal{A} = 2(H_{2})5\mathcal{A}$$
 (5)

which indicates that two molecules of hydrogen are adsorbed on five active centers. The expression relating the gas concentration adsorbed to the gas partial pressure for this mechanism is

$$C_{H_{2}} = \frac{K' L' (p_{H_{2}})^{2/5}}{1 + K' (p_{H_{2}})^{2/5}}$$
(6)

The author postulated that the true mechanism is, simply physical adsorption of two molecules on five active centers. It seems unlikely that the mechanism could be chemical dissociation because the near cryogenic temperatures are not compatible with activated adsorption associated with the molecular dissociation mechanisms.

The values of K' were determined from the intercepts of the isotherms with the ordinate at $1/p_A = 1$ from Figures 5 and 6 for the catalytic materials studied. The intercept gives the value of the quantity 1/L'K', so that K' can be calculated. These values for the catalysts of interest are given in Table X.

Since K'is related to the true thermodynamic equilibrium constant, a plot of log K'versus the recipiocal of the absolute temperature should be a reasonably straight line. Figure 7 is a plot of this information for the catalys's of interest. Since the lines are essentially straight, the slope should furnish a useful compirical constant that could be used to predict K'for temperatures other than those measured.

SECTION III CONCLUSIONS

The adsorption data on the commercially available hydrous ferric oxide gel and the advanced nickel oxide silicate material indicate that the adsorption mechanism is physical. This conclusion is reached primarily because the data were obtained at low temperatures. There are indications also that the adsorption mechanism changes with temperature and possibly with pressure; but, for the temperatures studied (63.16 to 194.6°K), the basic mechanism is physical adsorption. Table XI lists the expressions for the catalysts at the test temperatures.

References 6, 7, and 8 suggested that two mechanisms occurred with para-ortho conversion catalysts. One mechanism is increasingly effective as the temperature is lowered, and the other is increasingly effective as the temperature is raised. Taylor (Reference 9) showed that two types of adsorption occurs. Physical adsorption (Van der Waals) occurs at low temperatures and decreases as the temperature increases while activated, or chemisorption takes place above room temperature and increases as the temperature increases. These theories back the contention of this suthor that physical adsorption is occurring.

For the catalysis studied, Langmuir's Isotherm holds at 194.6°K, while at lower temperatures (approximately 60-90°K) the adsorption mechanism appears to be one where two molecules are adsorbed on five active centers.

The overall mechanism for the para-toortho (or ortho-to-para) shift of hydrogen consists of several consecutive steps, Before

the actual conversion can occur, a hydrogen molecule must diffuse out of the main gas stream to the surface of the catalytic particle and eventually into a small pore of the particle. The molecule must then adsorb onto the surface of the catalyst. We have determined that this step is physical adsorption. Once the molecule is adsorbed, it will migrate along the surface, perhaps passing near an active center. For the para-ortho hydrogen shift, active centers generally are associated with unshared electrons. In scrong, inhomogeneous, magnetic fields around such electrons, the restrictions against spontaneous conversion are removed, and the molecule may change to another modification. Finally, the converted molecule must evaporate (physical adsorption to physical desorption) from the adsorbed layer, diffuse along the pore to the outside surface of the particle, and then diffuse into the main gas stream that will carry it from the catalyst chamber. One of these steps, therefore, will control the rate of conversions. Current efforts are simed at getting sufficient data to determine the exact mechanism and the rate controlling step.

Since the catalytic material desired by the U. S. Air Force for application to possible future aircraft systems must be lightweight, and since the adsorption characteristics at the temperatures of interest are physical in nature, a good catalyst must exhibit certain qualities. Some of these characteristics would be low density, high surface area, high adsorptive capacity, high fraction of the surface area which contains active sites, high site activity, high porceity, and high thermal conductivity.

APPENDIX

ILLUSTRATIONS AND TABLES



÷

NOT TIMED

1911

¥.

سر. في ا

हेन्द्र-अन्स्





TABLE I

AUSORPTION DATA FOR HYDROGEN AT 63.16°K WITH HYDROUS FERRIC OXIDE GEL AS CATALYST

Equilibrium pressure (atms)	Volume adsorbed (STP) mal/gm (cat [*])	1/P atm ⁻¹	CA moles adsorbed moles/gm (cat) x 10 ⁴	1/C _A	1/c _A - 1/L'
0_221	11.6	4.52	5.18	0.193	0.167
1.16	19.1	0.56	8.53	C.117	160.0
2.62	23.4	0.38	10.43	0.096	0.070
3.94	25.7	0.254	11.40	0.086	0.062
<u>5.15</u>	27.3	0.194	12.15	0.082	0.056
6.16	28.3	0.162	12.63	0.079	0.053
6.03	30.9	0.111	13.75	0.073	0.047
11.30	33.3	0.083	14.85	0.067	0.041
15.60	36.7	0,064	16.30	0,061	0.035
19.0	39.0	0.053	17.40	Q.05/	0.031
22.1	41.2	0.045	18.43	0.054	0.028
24.6	42.9	0.041	19.10	0.052	0.026
26,6	43.5	0.038	19.40	130.0	0.025
28.0	45.3	0.036	20.20	0.050	0.024
Note: *cat	is used as abbreviati	on for catal	yst on all tables.		

H

ę

AFAPL-TR-66-142

11

ŧ

ς,

TABLE II

ADSORPTION DATA FOR HYDROGEN AT 77°K WITH ED.DROUS FERKIC OXIDE GEL AS CATALYST

Equilibrium prensure (atms)	Volume adsorbed (STP) mal/gm (cat)	1/P atm ⁻¹	CA moles adsorbed moles/gm (cat) x 10 ⁴	1/cA	1/C _A - 1/L'
0.408	6.53	2.45	2.93	0.342	0.316
1,16	11.1	0.86	4.95	0.201	0.175
2.08	14.0	0.48	6.25	0.160	0.134
2.98	15.8	0.335	7.08	0.142	0.116
4.12	17.4	0.243	7.78	0.129	0.103
5.46	19.0	0.184	8.50	0.118	0.092
6.90	20.3	0.145	9.08	0.110	0,084
8.47	21.4	0.118	9.56	0.104	0.078
10.10	22.6	0.099	10.10	0.099	0.073
11.80	23.6	0.085	10.55	0.095	0.60
13.40	24.9	0.075	11.10	060.0	0.064
15.0	26.0	0.067	11.60	0.086	0.060

.ż

TABLE III

	AZSORP BYD	TION DATA FOR ROUS FERRIC O	HYDROGEN AT 87.8°K WITH XIDE CEL AS CATALYST		
Equilibrium preasure (atma)	Volume Adsorbad (STP) al/gm (cat)	1/P atri-1	CA moles adsorbed moles/gm (cat) x 10 ⁴	1/CA	1/c _A - 1/L'
0.476 1.43	4.31 8.08	2.10 0.70	1.92	0.521	0.495
2.81	11.1	0.355	5.02 4.95	0.276	0.250
4.49	13.4	0.223	5.99	0.166	0.140
00 7.7 g	10.3	0,158	6.83	0.146	0.120
11.80	5 0 1 1	0,005	7.55	0.133	0,107
0.1		50°0	8.32	0.121	0.095
a 0.0		0,003	9.20	0.109	0.083
	2 4 5 7 5 7 5	0.048	10.01	0.100	0.674
		0.041	10.45	0.096	0.070
4/14	7.47	0.037	10.80	0.093	0.067

121.0

	NUYA	OUS FERRIC O.	XIDE GEL AS CATALYST		
Equilityrium pressure (stms)	Volume adsorbed (STP) ml/gm (cat)	1/P هن ت ًا	CA moles aúsorbed moles/gm (cat) x 10 ⁴	1/C _A	1/c _A - 1/L'
0.952	0.0123	8.13	0.055	18.20	18.17
2.84	0.494	2.03	0.219	4.56	4.53
4.69	0.742	1.35	0.331	3.01	2.98
6.46	0.998	1.00	0.446	2.24	2.21
B.20	1.23	0.613	0.549	1.82	1.79
10.7	1.58	0.535	0.703	1.42	1.39
15.2	2,19	0.456	0.975	1.025	1.00
20.7	2.96	0.338	1.325	0.755	0.725
27.1	2.98	0.335	1.328	0.751	0.721
. 30.1	3.79	0.264	1.695	0,590	0.560

1

: .=

TABLE IV

ALSORPTION DATA FOR HYDROGEN AT 194.6°K WITH

¥

	•				
Equilibrium pressure (atms)	Volumme adsorhed STP) mul/gm (cat)	1/P atm ⁻ i	C _A moles adsorbed moles/gm (cat) x 10 ⁴	1/5_A	1/C _A = 1/L'
0.0	20.4	1	9,10	0.110	660.0
0.306	57.0	3.65	25.40	0.0395	0.0290
1.28	83.4	0.78	37.10	0.0269	0.0164
3.84	106	0.26	47.40	0.0211	0.0106
6.70	117	0.15	52.30	0.0192	0.0087
1.28	84.4	0.78	37.50	0.0267	0,0162
6.00	117	0.167	52.30	0.0192	0.0087
11.2	130	0.089	58,00	0.0172	0.0067
15.7	138	0.064	61.50	0.0162	0.0057
19.3	144	0.052	64.20	0.0156	0.0051
22,1	149	0.045	66.30	0.0150	0.0045

त्र प्रस्तित स्**ते अन्**

ai :.

-

<u>i.,</u>,

TABLE V

ADSORPTION DATA FOR HYDROGEN AT 63.16°K WITH

::``

4

· so the control of the se

Rquilibrium precente (atme)	Volume adwrrhed (STP) nd/gm (cat)	1/P 8(=_1	CA moles adaorbed moles/gm (cat) x 10 ⁴	1/CA	1/6 _A = 2/L
0	10.5	ł	4.5	0.017	0 205
0,035	20.2	29.40	5°.6	0.1105	11200
	34.4	7.35	15.35	0,0654	0.7543
92.5.1	40.1	1.01	21.30	0.0470	2,0365
1077	67.9	0.275	29.90	0,0335	0520-0
	27.9	0.219	34,70	0.0208	0.0183
	845 G	0.158	37,80	0.0265	0.0150
- 0 F		0.128	39.60	0.0253	0.3146
	0 0 0	0.102	41.90	0.0239	0.0134
16.4U	¥6.3	0.083	43.90	0.0229	41 (0.0
	COT	0.064	46.90	0.0214	90,0,0
		0.051	49.1N	0.0204	0.3059
1.63	414	0,043	50.90	0.0197	0.0002

÷ć<u>i</u>ć- •

ाम अद्या देखे दुर्णुकु

A. · <u>...</u>· ्रम्स सेल्क्रम्ब र

ιđ.

TABLE VII

Call.

Ť

ъ'ą

- 2

<u>_____</u>___=

					- - -
Equilthrium Pressure (atma)	Voltance adsorrhed (STP) mel/gra (cat)	1/P atm ⁻ 1	C _A moles adjorbed molea/gm (cut) x 104	1/C _A	1/C _A - 1/L'
0.221	18.2	4.54	3.12	0.123	0.112
0.816	31.6	1.23	14.05	0.0701	0.0596
2.69	50.4	0.371	22.60	0.0442	0,0337
6.22	66.2	0.161	29.60	0.0338	0.0233
11.05	78.1	060.0	34.90	0.0286	0.0181
4.06	58.3	0.246	26,10	0.0384	0.0279
10.7	77.9	0.034	34.65	0.0288	0.0183
16.5	86.3	0.061	38.60	0.0259	0.0154
21.0	90.7	0.048	40.40	0.0247	G.0142
24.5	92.3	0.041	41.40	0.0241	0.0136
27.0	94.7	0.037	41.70	0,0240	0.0135
28,8	96.1	0.035	42.80	0.0234	0.0129
30.2	96.7	0.033	43.20	0.0231	0.0126

17

	ADSORPTI NIC	ION DATA FOR XEL OXIDE SI	HYDROGEN AT 194 / 'JTH LICATE AS CATA''		
Equi Libțium pressure (atms)	Volumme adsorbed (STP) ml/gm (cat)	1/P stm ⁻¹	CA moles adëorbed moles/gm (cat) x 10 ⁴	1/C _A	1/cA - 1/L'
1.38	1,45	0.724	0.647	1.550	1.539
3.67	3.15	0.277	1.405	0.710	0.699
6.12	7.17	0.163	3.200	0.313	0,302
6.36	7.72	0.153	3.450	0.290	0,279
12,8	9.47	0.078	4.24	0.236	0.225
16.1	11.1	0.062	4.96	0.201	0.190
19.5	12.5	0.051	5.59	0.179	0.168
22.8	13.9	0.044	6.19	0.162	0.151
26.3	15.3	0.038	6.84	0.146	0.135
29.6	16.7	0.034	7.45	0.134	0.123

TABLE VIII

(F

Ę

14분들(응)

ない、日本語の一般



аў. Т







20

ι¥ Γ

.

din pipis

<u>____</u>

Ă. 1


이번 모양으로 주가가 1983년 전 11월 - 11일 - 11일

1 -R :

1.12

<u>ani≱</u>

12-



21

. .



Figure 6. Correlation of Hydrogen on Nickel Oxide Silicate According to Equation (2)

Ę,

i gerenti

語言語

TABLE IX

VALUES OF L' AND n

Temperature (°K)	Slope of curve (Figure 5)	Nearest fraction
63.16°K	0.377	2/5
77°K	0.433	2/5
87.8°K	0,450	2/5
194.6°K	1.000	
Hydrogen Adsor Temperature (°K)	ption On Nickel Oxide Silica Slope of curve (Figure 6)	L' = 95.24 Nearest fraction n
Hydrogen Adsor Temperature (°K) 63.16°K	ption On Nickel Oxide Silica Slope of curve (Figure 6) 0.429	L' = 95.24 Nearest fraction n 2/5
Hydrogen Adsor Temperature (°K) 63.16°K 77°K	ption On Nickel Oxide Silica Slope of curve (Figure 6) 0.429 0.426	L' = 95.24 Nearest fraction n 2/5 2/5
Hydrogen Adsor Temperature (°K) 63.16°K 77°K 87.8°K	ption On Nickel Oxide Silica Slope of curve (Figure 6) 0.429 0.426 0.418	L' = 95.24 Nearest fraction n 2/5 2/5 2/5 2/5

TABLE X

랑

÷ tu j

> 1 Ŧ

j,

VALUES OF K'

Temperature (*K)	Hydrous ferric oxide	Nickel oxide silicate	' L	
63.16 77 87.8 194.5	0.260 0.133 0.095 0.017	0.598 0.314 0.211 0.008	۔ بنہ ۳۲	
	* * ****			
	لى يې د چېرورىد كې د پې د د د د	به میکند. «استان بر اینکند» بر اینکانی بر بستان سیستان به میچاند اینکانی اینکانی بر اینکانی بر اینکانی بر اینکانی بر اینکانی بر ا		
			· ·	
	-	•		
۰. د				
r ,*				

1997 **- 19**97 - 1997 -

المدر التطويقين

13*=*1

4

Ē

Ξ

w edito

in lange





TABLE XI

ADSORPTION ISOTHERNS FOR HYDROGEN

Bydrous ferric oxide gel adsorbent					
(*K)	$1.0(v_{m})^{2/5}$				
-63.16	$C_{H_2} = \frac{1}{1 + (0.26)(p_{H_2})^{2/5}}$				
-77	$C_{H_2} = \frac{5.12(p_{H_2})^{2/5}}{1 + (0.13)(p_{H_2})^{2/5}}$				
-878	$C_{H_2} = \frac{3.65(P_{H_2})^{2/5}}{1 + (0.10)(P_{H_2})^{2/5}}$				
-194.6	$C_{H_2} = \frac{0.65(P_{H_2})}{1 + (0.17)(P_{H_2})}$				
Nickel oxide/silicate adsorbent					
(°K)	₹ 56.95(p _µ) ^{2/5}				
-63.16	$C_{H_2} = \frac{H_2}{1 + (0.60)(p_{H_1})^{2/5}}$				
[%] ~77	$C_{H_2} = \frac{\frac{29.91(P_{H_2})^{2/5}}{1 + (0.31)(P_{H_2})^{2/5}}}{1 + (0.31)(P_{H_2})^{2/5}}$				
-87.8	$C_{H_2} = \frac{\frac{20.10(p_{H_2})^{2/5}}{1 + (0.21)(p_{H_2})^{2/5}}}{1 + (0.21)(p_{H_2})^{2/5}}$				
-194.6	$C_{H_2} = \frac{0.76(p_{H_2})}{1 + (0.01)(p_{H_2})}$				

APAPL-TR-\$6-142

, , =

ļ

Ę.

REFERENCES

- 1. Barrick, P. L., Weitzel, D. W. and Connolly, T. W., Proc. Cryogenic Bar. Conf. 1, 285, 1954.
- Weitzel, D. H. and O. E. Park, "Iron Catalyst for Production of Liquid Paral drogen," <u>Rev. Sci. Insty.</u> 27, 57-8, 1956.
- Schmauch, G. E., Clark, R. G., Kurirke, J. F., and Jamhishar, A., <u>Investigation of the Para-Ortho Shift of Hydrogen</u>, ASD-TOR-63-833, Part I, Aeronautical Systems Division, Wright-Patterson Air Force Base, Ohio, July 1462.
- Koble, R. A., and Corrigan, T. E., "Adsorption isotherms for Pure Hydrocarbons," Ind. and Eng. Chem. Vol. 44, February 1952.
- 5. Schmauch, G. B., Clark, R. G., Kurirka, J. F., and Jambhehar, A., <u>Investigation of</u> <u>the Para-Ortho Shift of Hydrogen</u>, ASO-TDR-63-833, Part II, Aeronautical Stystens Division, Wright-Patterson Air Force Base, Ohio, October 1963.
- 6. Bonhoeffer, K. F. and P. Harteck, "Para- and Ortho Hydrogen," <u>Z Physik Chem. Abt. B4</u>, 113-41, 1929.
- Bonhoeffer, K. F. and A. Farkas, "The Para-hydrogen Transformation on Platinum: A Relation Between Catalysis and Accommondation," <u>Z Physik Chem. Abt. B12</u>, 231-46, 1931.
- 8. Rummel, K. W., "The Para-Hydrogen Transformation on Carbon Surfaces at Low Temperatures," <u>Z Physik Chem. A167</u>, 231-39, 1933.
- 9. Taylor, H. S., and A. Sherman, "The Ortho-Para Hydrogen Conversion at Surfaces," J. Am. Chem. Soc. 53, 1614-5, 1931.

1 ್ಷ ತ್ರಿತಿ 1.5 IDECLASSIFIED Society Casesification DOCUMENT CONTROL DATA - PLD of fits, holy all channel and indexing constantion as STRIBUL THE & ACTIVITY (Comments suches) WAT SECURITY CLASS PICATE Air Frees Acro Propulsion Laboratory UNCLASSIFIED Research and Toolmology Division Whight-Patterson Air Paros Base, Chio REPORT TITLE THE ROLL OF ADSORPTION IN THE CATALYTIC PARA-ORTHO-HYDROGEN CUNVERSION. - OXECRIPTINE WITES (Type of speed and Mohesine Antes) Technick ANTHONS) J (IT) ander, Jr. Herbert R. TOTAL NO. OF PAGES 74. NO. OF BETS REPORT NUMBER(8) -9045 AFAPL-TR-68-142 7 304802 OTHER DEPORT NOT (4 ST scher ment that may be secion R. A VA & ABILITY/LINKYATIGH NOTICES This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of the Air Force Aero Propulsion Laboratory (APFL), Wright-Patterson Air Force Base. Ohio. - ENERTARY NOTES 12. SPONSORING BILITARY ACTIVITY Air Force Asro Propulsion Laboratory Wright-Patterson Air Foron Base, Chio BATBACT Adsorption isothermand the form $C_{A} = \frac{L'K'(p_{A})^{n}}{1+K'(p_{A})^{n}}$ were determined for two para-ortho-hydrogen conversion capalysts, hydrons ferric oxide gel and nickel oxide silicate, at temperatures from 65 K to 196 K and at pressures from 1 to 10 stmospheres. For the catalysts studied, Languagir's isotherm holds at 194.6 K, while at lower temperatures (approximately 60-90 K), the adsorption mechanism appears to be ģ one where two molecules are adsorbed on five effective centers. (Distribution of this abstract is unlimited) ml (011 570) UNCLASSIFIED Security Clussification

UNCLASSIFIED Security Classification

	LINK A		LINK B		LINKC	
KEY WONDJ Z	ROLE	W 7	ROLE	W T	HOLE	WY
Para-ortho shift of hyirogon Hydrous ferric oxide ostalyst Nickel oxide silicate catalyst Ortho-hydrogen isotherus Hydrogen catalysts Active conters Para-hydrogen catalysts	ROLE	WY	ROLE	W Y	ROLE	

άĘ

- J#

T AT

=.

UNFTRUCTION!

1. ORIGINATING ACTIVITY: Enter the same and address of the contractor, subcontractor, grantee, Department of Defense activity as other organisation (conporete author) issuing the report.

24. REPORT BECURITY CLASSIFICATION: Baler the overall accurity classification of the report. Indicate whother "Restricted Data" is included. Marking is to be in accordsace with appropriate security regulations.

26. GROUP: Automatic downgrading is specified in DoD Di-rective 5200, 10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that options rankings have been used for Group 3 and Group 4 as authorided.

REPORT TITLE: Enty the complete report title in all 3. capital letters. Titles in all cases should be backasified. If a meanineful title cannot be selected without classified. show title classification in all capitals in parenthesis inmediately following the title-

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive datos when a specific reporting period is covered.

5. AUTHOR(8): Enter the nase(s) of suthor(s) as shown os or in the report. Enter last name, first name, suddle initial. If military, show rark and branch of service. The rase of the principal wather is an absolute minimum requirement.

6. REPORT DAT2: Reter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7s. TOTAL NUMBER OF PAOEd: The lots, page count should follow normal pagination procedures, Le., enter the number of pages containing information.

75. NUMBER OF REFERENCES. Erter the total number of references cited in the report.

Sa. CONTRAC'T OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or great under which the report was written.

86. Sc. & Sd. PROJECT NUMBER: Enter the appropriate militry department identification, such as project member, subproject number, system numbers, task number, etc.

ORIGIN \TOR'S REPORT NUMBER(W): Enter the off-9. cial report number by which the document will be identified and controlled by the originating activity. This number swat be unique to this report.

95. OTHER REPORT NURBER(S): If the report has been assigned any other report studes a (either by the originator or by the aponcor), also onter this number(s).

10. AVAILABILITY/LIMITATION NOTICER Tates any lim itstions on further dissemination of the report, other than those

ed by security classification, using standard statements such as:

كشنه

- (1) "Qualified requestors may obtain copies of this report from DDC."
- "Foreign announcement and dissemination of this report by DDC is not authorized." (2)
- "U. 8. Government agencies may obtain copies of this report directly from DDC. Other vasified DDC (5) users shall request through
- "U. R. military agencies way obtain copies of this report directly from DDC. Other qualified users **(4**) shall request through
- "All distribution of this report is controlled. Qual-(5) ified DDC users shall request through

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indi-cate this fact and enter the price, if known

11. SUPPLEMENTARY NOTEN Use for additional explana-LOFY BOLDS.

12. SPONSULING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory spousoring (pay-ing for) the research and development. Include address.

15. ABSTRACT: Rater an abstract giving a brief and factual summary of the document indicative or the report, even though it may also appear claswhere in the body of the technical re-port. If additional space is required, a continuation sheet shall port. If addi be existing

It is highly desirable that the abstract of classified reports be unclassified. Each paragreph of the abstract shall and with an indication of the military security classification of the information in the paregraph, represented as (T8). (8). (C). or (U).

There is no limitation on the length of the abstract. How-ever, the suggested length in from 150 to 225 words.

14. KEY WORDE: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no scrurity classification is required. Identifrom, such as equipment model designative, rade mane, subtary $\mu \sigma j \sigma \tau$ is one name, geographic location, may be used as key words but will be followed by an adication of technical context. The assignment of links, rules, and vs ights 's optional.

> UNCLASSIFIED loculty Cleasification

> > ÷ 1

AFLC-WPAPE-MIL 45 3M

4 - E

swi s