



---

**Electrically-generated spin polarization in non-magnetic semiconductors**

**Vanessa Sih  
UNIVERSITY OF MICHIGAN**

---

**03/31/2016  
Final Report**

DISTRIBUTION A: Distribution approved for public release.

Air Force Research Laboratory  
AF Office Of Scientific Research (AFOSR)/ RTB1  
Arlington, Virginia 22203  
Air Force Materiel Command

**REPORT DOCUMENTATION PAGE**

Form Approved  
OMB No. 0704-0188

The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to the Department of Defense, Executive Service Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

**PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.**

<b>1. REPORT DATE (DD-MM-YYYY)</b> 14-03-2016		<b>2. REPORT TYPE</b> Final Report		<b>3. DATES COVERED (From - To)</b> 01-07-2012 - 31-12-2015	
<b>4. TITLE AND SUBTITLE</b> (YIP) - Electrically-generated spin polarization in non-magnetic semiconductors				<b>5a. CONTRACT NUMBER</b>	
				<b>5b. GRANT NUMBER</b> FA9550-12-1-0258	
				<b>5c. PROGRAM ELEMENT NUMBER</b>	
<b>6. AUTHOR(S)</b> Sih, Vanessa A.				<b>5d. PROJECT NUMBER</b>	
				<b>5e. TASK NUMBER</b>	
				<b>5f. WORK UNIT NUMBER</b>	
<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b> Regents of the University of Michigan Office of Research and Sponsored Projects 3003 S. State St. Ann Arbor MI 48109-1274				<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>	
<b>9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b> Air Force Office of Scientific Research 875 North Randolph Street, Rm 3112 Arlington, VA 22203				<b>10. SPONSOR/MONITOR'S ACRONYM(S)</b>	
				<b>11. SPONSOR/MONITOR'S REPORT NUMBER(S)</b>	
<b>12. DISTRIBUTION/AVAILABILITY STATEMENT</b> Distribution A - Approved for Public Release					
<b>13. SUPPLEMENTARY NOTES</b>					
<b>14. ABSTRACT</b> The objective of the research was to investigate and determine the mechanism that produced electrically-generated electron spin polarization in non-magnetic semiconductor heterostructures. Electrically-generated electron spin polarization was shown to be inversely proportional to the measured momentum-dependent spin splitting in strained indium gallium arsenide, contrary to theoretical expectation. The measurements were conducted by systematically varying the direction and magnitude of the in-plane current and net drift momentum in a device with a cross-bar geometry. The role of electrically-generated electron spin polarization in producing dynamic nuclear polarization was investigated, and nuclear spin polarization was produced that could be aligned either with or against the applied magnetic field, depending on the direction of the current. A series of indium gallium arsenide epilayer samples with varying indium composition and doping density were produced and measured in order to determine how changing the sample parameters, such as spin-orbit splitting, spin relaxation time, momentum scattering time, and carrier density, affect the electrical spin generation efficiency.					
<b>15. SUBJECT TERMS</b> Spin polarization; spin coherence; nuclear spin polarization; semiconductors; optics.					
<b>16. SECURITY CLASSIFICATION OF:</b>			<b>17. LIMITATION OF ABSTRACT</b>	<b>18. NUMBER OF PAGES</b>	<b>19a. NAME OF RESPONSIBLE PERSON</b> Vanessa Sih
<b>a. REPORT</b>	<b>b. ABSTRACT</b>	<b>c. THIS PAGE</b>			<b>19b. TELEPHONE NUMBER (Include area code)</b> (734) 763-7906

Reset

Standard Form 298 (Rev. 8/98)  
Prescribed by ANSI Std. Z39.18  
Adobe Professional 7.0

## INSTRUCTIONS FOR COMPLETING SF 298

**1. REPORT DATE.** Full publication date, including day, month, if available. Must cite at least the year and be Year 2000 compliant, e.g. 30-06-1998; xx-06-1998; xx-xx-1998.

**2. REPORT TYPE.** State the type of report, such as final, technical, interim, memorandum, master's thesis, progress, quarterly, research, special, group study, etc.

**3. DATES COVERED.** Indicate the time during which the work was performed and the report was written, e.g., Jun 1997 - Jun 1998; 1-10 Jun 1996; May - Nov 1998; Nov 1998.

**4. TITLE.** Enter title and subtitle with volume number and part number, if applicable. On classified documents, enter the title classification in parentheses.

**5a. CONTRACT NUMBER.** Enter all contract numbers as they appear in the report, e.g. F33615-86-C-5169.

**5b. GRANT NUMBER.** Enter all grant numbers as they appear in the report, e.g. AFOSR-82-1234.

**5c. PROGRAM ELEMENT NUMBER.** Enter all program element numbers as they appear in the report, e.g. 61101A.

**5d. PROJECT NUMBER.** Enter all project numbers as they appear in the report, e.g. 1F665702D1257; ILIR.

**5e. TASK NUMBER.** Enter all task numbers as they appear in the report, e.g. 05; RF0330201; T4112.

**5f. WORK UNIT NUMBER.** Enter all work unit numbers as they appear in the report, e.g. 001; AFAPL30480105.

**6. AUTHOR(S).** Enter name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. The form of entry is the last name, first name, middle initial, and additional qualifiers separated by commas, e.g. Smith, Richard, J, Jr.

**7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES).** Self-explanatory.

**8. PERFORMING ORGANIZATION REPORT NUMBER.** Enter all unique alphanumeric report numbers assigned by the performing organization, e.g. BRL-1234; AFWL-TR-85-4017-Vol-21-PT-2.

**9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES).** Enter the name and address of the organization(s) financially responsible for and monitoring the work.

**10. SPONSOR/MONITOR'S ACRONYM(S).** Enter, if available, e.g. BRL, ARDEC, NADC.

**11. SPONSOR/MONITOR'S REPORT NUMBER(S).** Enter report number as assigned by the sponsoring/monitoring agency, if available, e.g. BRL-TR-829; -215.

**12. DISTRIBUTION/AVAILABILITY STATEMENT.** Use agency-mandated availability statements to indicate the public availability or distribution limitations of the report. If additional limitations/ restrictions or special markings are indicated, follow agency authorization procedures, e.g. RD/FRD, PROPIN, ITAR, etc. Include copyright information.

**13. SUPPLEMENTARY NOTES.** Enter information not included elsewhere such as: prepared in cooperation with; translation of; report supersedes; old edition number, etc.

**14. ABSTRACT.** A brief (approximately 200 words) factual summary of the most significant information.

**15. SUBJECT TERMS.** Key words or phrases identifying major concepts in the report.

**16. SECURITY CLASSIFICATION.** Enter security classification in accordance with security classification regulations, e.g. U, C, S, etc. If this form contains classified information, stamp classification level on the top and bottom of this page.

**17. LIMITATION OF ABSTRACT.** This block must be completed to assign a distribution limitation to the abstract. Enter UU (Unclassified Unlimited) or SAR (Same as Report). An entry in this block is necessary if the abstract is to be limited.

Final Performance Report for “(YIP) – Electrically-generated spin polarization in non-magnetic semiconductors” (Contract/Grant Number: FA9550-12-1-0258)

Author: Vanessa Sih

Date: March 14, 2016

## **Abstract**

The objective of the research was to investigate and determine the mechanism that produced electrically-generated electron spin polarization in non-magnetic semiconductor heterostructures. Electrically-contacted indium gallium arsenide samples were fabricated and measured using time- and spatially-resolved magneto-optical measurements. Measurements of electron spin dynamics as a function of pump-probe spatial overlap and applied electric and magnetic fields were used to characterize the momentum-dependent spin-orbit fields. The electrically-generated electron spin polarization was shown to be inversely proportional to the measured momentum-dependent spin splitting in strained indium gallium arsenide, contrary to theoretical expectation. The measurements were conducted by systematically varying the direction and magnitude of the in-plane current and net drift momentum in a device with a cross-bar geometry and by varying the direction of the applied magnetic field with a rotatable cryostat. The role of electrically-generated electron spin polarization in producing dynamic nuclear polarization was investigated, and nuclear spin polarization was produced that could be aligned either with or against the applied magnetic field, depending on the direction of the current. A phase shift in the time-resolved Faraday rotation data due to electron spin polarization from previous pump pulses was characterized, and an analytic solution for this phase shift was found. The electron g-factor was also shown to change with increasing in-plane electric field due to increasing electron temperature. A series of indium gallium arsenide epilayer samples with varying indium composition and doping density were produced and measured in order to determine how changing the sample parameters, such as spin-orbit splitting, spin relaxation time, momentum scattering time, and carrier density, affect the electrical spin generation efficiency.


## **Summary of Work Accomplished**

The goal of this project was to enable the design of materials with large, robust electrically-generated electron spin polarization by experimentally determining how key material parameters, such as spin-orbit splitting, spin decoherence rates, momentum scattering time, and carrier density, govern the magnitude of electrically-generated spin polarization in semiconductors.

Custom indium gallium arsenide (InGaAs) heterostructures were supplied by the research groups of Prof. David Awschalom at the University of California at Santa Barbara (currently at U. Chicago) and Prof. Rachel Goldman at the University of Michigan. Electrically-contacted devices for the experiments were fabricated using photolithography, chemical etching, metallization, and thermal annealing at the Lurie Nanofabrication Facility at Michigan.


Time- and spatially-resolved magneto-optical spectroscopy were conducted to measure the electron spin decoherence time, map the momentum-dependent spin-orbit fields, and determine the magnitude of current-induced spin polarization. A cross-bar-shaped device with four

electrical contacts was designed and fabricated so that the direction of the in-plane electric field could be varied. A rotatable cryostat mount was used so that the direction of the applied magnetic field could be controlled relative to the sample axes.




**Figure 1.** (a) The InGaAs epilayer (blue) is etched into a cross pattern with four electrical contacts (orange). Kerr rotation measures the component of spin polarization along the laser axis. (b) Voltages applied to the contacts determine the electron drift momentum  $\vec{k}$ , at angle  $\phi$  with respect to the [100] crystal direction.  $\vec{B}_{ext}$  is oriented at angle  $\theta$  by rotating the cryostat. (c) Total spin-orbit field as a function of  $\vec{k}$  if the Rashba field is twice as large as the linear Dresselhaus field. (d) The spin-orbit field  $\vec{B}_{int}$  makes an angle with respect to  $\vec{B}_{ext}$  and the steady-state in-plane spin polarization. Reproduced from [2].

These measurements and phenomenological modeling established that spins are dynamically polarized along the direction of the spin-orbit field, but the steady-state electrically-generated spin polarization can deviate from this direction due to anisotropic spin relaxation. Contrary to existing theories, the measurements also show that the electric field directions corresponding to the smaller spin-orbit splitting produce the larger electrical spin generation efficiency [2]. Detailed descriptions of the optical techniques and modeling are published in Ref. [D1].



**Figure 2.** Electrical spin generation efficiency for each direction of in-plane electric field plotted against the spin-orbit splitting for the same direction for (a) two cross-bar devices and (b) three fixed-channel devices. Reproduced from [2].

Current-induced electron spin polarization was shown to produce nuclear hyperpolarization through dynamic nuclear polarization. Time-resolved Faraday rotation measurements were used to monitor the total effective magnetic field produced by the sum of the applied magnetic field, spin-orbit field, and nuclear (Overhauser) field as a function of laboratory time and applied electric field. The nuclear field saturated over a timescale of 100 s and was shown to depend on the direction of the current-induced electron spin polarization relative to the applied magnetic field. The dependence of the saturated magnetic field as a function of temperature, electric field strength and external magnetic field strength was measured [3].



**Figure 3.** Total magnetic field measured using time-resolved Faraday rotation with the electrically-generated electron spin polarization parallel [panels (a) and (c)] and perpendicular [panels (b) and (d)] to the applied magnetic field. All data were measured at 10 K with  $B = 200$  mT. Light red and light blue shading indicate  $V_{DC} = 2$  V and  $-2$  V, respectively. Inset text gives the total change in nuclear field for the labelled transition. Panels (a) and (b) show transitions of the form  $V_{DC} = 0$  to  $\pm 2$  V, which include contributions from effects that depend on current magnitude, such as the changing spatial overlap of the optically-induced spin polarization with the region of interest and electrical heating. Panels (c) and (d) show transitions of the form  $V_{DC} = -2$  V to  $2$  V, which only includes effects due to the change in current polarity. Reproduced from [D2].

In the course of performing time-resolved Faraday rotation measurements as a function of applied magnetic field, a phase shift in the time-resolved Faraday rotation data was identified, and an analytic solution for this phase shift as a function of spin lifetime was found [5]. Detailed descriptions of the measurement techniques and modeling are published in Ref. [D2].

A closer analysis of the time- and spatially-resolved Faraday rotation measurements used to measure the magnitude and direction of the spin-orbit fields found that the measured electron  $g$ -factor also exhibits a dependence on applied electric field, which can be attributed to the increased electron temperature [8].

A series of indium gallium arsenide epilayer samples with varying indium composition and doping density were produced and measured in order to determine how changing the sample parameters, such as spin-orbit splitting, spin relaxation time, momentum scattering time, and carrier density, affect the electrical spin generation efficiency.

### Graduate students involved in this project

Benjamin M. Norman  
 Christopher J. Trowbridge  
 Marta Luengo-Kovac  
 Michael Macmahon  
 Eunice Paik

## Dissertations produced

- [D1] “Electrical Generation of Spin Polarization in Strained III-V Semiconductors,” Benjamin Michael Norman, Ph.D. thesis, University of Michigan, Ann Arbor (2014), available online: <http://hdl.handle.net/2027.42/108822>
- [D2] “Electron and Nuclear Spin Dynamics and Coupling in InGaAs,” Christopher J. Trowbridge, Ph.D. thesis, University of Michigan, Ann Arbor (2015), available online: <http://hdl.handle.net/2027.42/113488>

## Publications in peer-reviewed journals

- [1] “Spin lifetime measurements in GaAsBi thin films,” B. Pursley, M. Luengo-Kovac, G. Vardar, R. S. Goldman, and V. Sih, *Applied Physics Letters* **102**, 022420 (2013).
- [2] “Current-induced spin polarization in anisotropic spin-orbit fields,” B. M. Norman, C. J. Trowbridge, D. D. Awschalom, and V. Sih, *Physical Review Letters* **112**, 056601 (2014). Selected as an Editors’ Suggestion.
- [3] “Dynamic nuclear polarization from current induced spin polarization,” C. J. Trowbridge, B. M. Norman, Y. K. Kato, D. D. Awschalom, and V. Sih, *Physical Review B* **90**, 085122 (2014)
- [4] “Anisotropic spin dephasing of impurity-bound electron spins in ZnO,” J. Lee, A. Venugopal, and V. Sih, *Applied Physics Letters* **106**, 012403 (2015)
- [5] “Phase effects due to previous pulses in time-resolved Faraday rotation measurements,” C. J. Trowbridge and V. Sih, *Journal of Applied Physics* **117**, 063906 (2015)
- [6] “Robustness of n-GaAs carrier spin properties to 5 MeV proton irradiation,” B. C. Pursley, X. Song, R. O. Torres-Isea, E. A. Bokari, A. Kayani, and V. Sih, *Applied Physics Letters* **106**, 072403 (2015)
- [7] “Amplifying optical rotation using a coupled waveguide and ring resonator,” T. W. Saucer, C. Zenger, B. Pursley, and V. Sih, *Optics Express* **23**, 6050-6057 (2015)
- [8] “g-factor modification in a bulk InGaAs epilayer by an in-plane electric field,” M. Luengo-Kovac, M. Macmahon, S. Huang, R. S. Goldman, and V. Sih, *Physical Review B* **91**, 201110(R) (2015)
- [9] “Resonant and time-resolved spin noise spectroscopy,” Brennan C. Pursley, X. Song, and V. Sih, *Applied Physics Letters* **107**, 182102 (2015)

1.

**1. Report Type**

Final Report

**Primary Contact E-mail****Contact email if there is a problem with the report.**

vsih@umich.edu

**Primary Contact Phone Number****Contact phone number if there is a problem with the report**

7347637906

**Organization / Institution name**

University of Michigan, Ann Arbor

**Grant/Contract Title****The full title of the funded effort.**

(YIP) - Electrically-generated spin polarization in non-magnetic semiconductors

**Grant/Contract Number****AFOSR assigned control number. It must begin with "FA9550" or "F49620" or "FA2386".**

FA9550-12-1-0258

**Principal Investigator Name****The full name of the principal investigator on the grant or contract.**

Vanessa Sih

**Program Manager****The AFOSR Program Manager currently assigned to the award**

Harold Weinstock

**Reporting Period Start Date**

07/01/2012

**Reporting Period End Date**

12/31/2015

**Abstract**

The objective of the research was to investigate and determine the mechanism that produced electrically-generated electron spin polarization in non-magnetic semiconductor heterostructures. Electrically-contacted indium gallium arsenide samples were fabricated and measured using time- and spatially-resolved magneto-optical measurements. Measurements of electron spin dynamics as a function of pump-probe spatial overlap and applied electric and magnetic fields were used to characterize the momentum-dependent spin-orbit fields. The electrically-generated electron spin polarization was shown to be inversely proportional to the measured momentum-dependent spin splitting in strained indium gallium arsenide, contrary to theoretical expectation. The measurements were conducted by systematically varying the direction and magnitude of the in-plane current and net drift momentum in a device with a cross-bar geometry and by varying the direction of the applied magnetic field with a rotatable cryostat. The role of electrically-generated electron spin polarization in producing dynamic nuclear polarization was investigated, and nuclear spin polarization was produced that could be aligned either with or against the applied magnetic field, depending on the direction of the current. A phase shift in the time-resolved Faraday rotation data due to electron spin polarization from previous pump pulses was characterized, and an analytic solution for this phase shift was found. The electron g-factor was also shown to change with increasing in-plane electric field due to increasing electron temperature. A series of indium gallium

DISTRIBUTION A: Distribution approved for public release.



arsenide epilayer samples with varying indium composition and doping density were produced and measured in order to determine how changing the sample parameters, such as spin-orbit splitting, spin relaxation time, momentum scattering time, and carrier density, affect the electrical spin generation efficiency.

### **Distribution Statement**

This is block 12 on the SF298 form.

Distribution A - Approved for Public Release

### **Explanation for Distribution Statement**

If this is not approved for public release, please provide a short explanation. E.g., contains proprietary information.

### **SF298 Form**

Please attach your SF298 form. A blank SF298 can be found [here](#). Please do not password protect or secure the PDF. The maximum file size for an SF298 is 50MB.

[AFD-070820-035\\_Sih\\_1.pdf](#)

**Upload the Report Document. File must be a PDF. Please do not password protect or secure the PDF. The maximum file size for the Report Document is 50MB.**

[Sih AFOSR final report 2016.pdf](#)

**Upload a Report Document, if any. The maximum file size for the Report Document is 50MB.**

### **Archival Publications (published) during reporting period:**

Dissertations produced

[D1] "Electrical Generation of Spin Polarization in Strained III-V Semiconductors," Benjamin Michael Norman, Ph.D. thesis, University of Michigan, Ann Arbor (2014), available online: <http://hdl.handle.net/2027.42/108822>

[D2] "Electron and Nuclear Spin Dynamics and Coupling in InGaAs," Christopher J. Trowbridge, Ph.D. thesis, University of Michigan, Ann Arbor (2015), available online: <http://hdl.handle.net/2027.42/113488>

Publications in peer-reviewed journals

[1] "Spin lifetime measurements in GaAsBi thin films," B. Pursley, M. Luengo-Kovac, G. Vardar, R. S. Goldman, and V. Sih, Applied Physics Letters 102, 022420 (2013).

[2] "Current-induced spin polarization in anisotropic spin-orbit fields," B. M. Norman, C. J. Trowbridge, D. D. Awschalom, and V. Sih, Physical Review Letters 112, 056601 (2014). Selected as an Editors' Suggestion.

[3] "Dynamic nuclear polarization from current induced spin polarization," C. J. Trowbridge, B. M. Norman, Y. K. Kato, D. D. Awschalom, and V. Sih, Physical Review B 90, 085122 (2014)

[4] "Anisotropic spin dephasing of impurity-bound electron spins in ZnO," J. Lee, A. Venugopal, and V. Sih, Applied Physics Letters 106, 012403 (2015)

[5] "Phase effects due to previous pulses in time-resolved Faraday rotation measurements," C. J. Trowbridge and V. Sih, Journal of Applied Physics 117, 063906 (2015)

[6] "Robustness of n-GaAs carrier spin properties to 5 MeV proton irradiation," B. C. Pursley, X. Song, R. O. Torres-Isea, E. A. Bokari, A. Kayani, and V. Sih, Applied Physics Letters 106, 072403 (2015)

[7] "Amplifying optical rotation using a coupled waveguide and ring resonator," T. W. Saucer, C. Zerger, B. Pursley, and V. Sih, Optics Express 23, 6050-6057 (2015)

[8] "g-factor modification in a bulk InGaAs epilayer by an in-plane electric field," M. Luengo-Kovac, M. Macmahon, S. Huang, R. S. Goldman, and V. Sih, Physical Review B 91, 201110(R) (2015)

[9] "Resonant and time-resolved spin noise spectroscopy," Brennan C. Pursley, X. Song, and V. Sih, Applied Physics Letters 107, 182102 (2015)

### **Changes in research objectives (if any):**

**Change in AFOSR Program Manager, if any:**

**Extensions granted or milestones slipped, if any:**

DISTRIBUTION A: Distribution approved for public release.

**AFOSR LRIR Number**

**LRIR Title**

**Reporting Period**

**Laboratory Task Manager**

**Program Officer**

**Research Objectives**

**Technical Summary**

**Funding Summary by Cost Category (by FY, \$K)**

	Starting FY	FY+1	FY+2
Salary			
Equipment/Facilities			
Supplies			
Total			

**Report Document**

**Report Document - Text Analysis**

**Report Document - Text Analysis**

**Appendix Documents**

**2. Thank You**

**E-mail user**

Mar 14, 2016 23:55:36 Success: Email Sent to: vsih@umich.edu