

The findings in this report are not to be construed as an official Department of the Army Position.

DISPOSITION

Destroy this report when no longer needed. Do not return to the originator.

· · · · . .

- i

٠. ـ

• •

ł,

٠

ł

Image: Contract of the contraction of the contraction of the contract of the co		N PAGE	READ INSTRUCTIONS BEFORE COMPLETING FORM
THE COMPARATIVE SENSITIVITY OF SUPERFINE THE COMPARATIVE SENSITIVITY OF SUPERFINE BETA AND DEXTRINATED LEAD AZIDE - THE COMPARATIVE SENSITIVITY OF SUPERFINE BETA AND DEXTRINATED LEAD AZIDE - THE COMPARATIVE SENSITIVITY OF SUPERFINE BETA AND DEXTRINATED LEAD AZIDE - THE COMPARATIVE SENSITIVITY OF SUPERFINE BETA AND DEXTRINATED LEAD AZIDE - THE COMPARATIVE SENSITIVITY OF SUPERFINE BETA AND DEXTRINATED LEAD AZIDE - THE COMPARATIVE SENSITIVITY OF SUPERFINE BETA AND DEXTRINATED LEAD AZIDE - THE COMPARATIVE SENSITIVITY OF SUPERFINE BETA AND DEXTRINATED LEAD AZIDE - BETA AND DEXTRINATED LEAD AZID	REPORT NUMBER	2. GOVT ACCESSI	ON NO. 3. RECIPIENT'S CATA' OG NUMBER
The contractive sensitivity of the sensitivity and sen	Tighenhalf Memoranitaliam-2198		
FIGH AND DEXTRINATED LEAD A2IDE Indended in the contract of the	THE COMPARATIVE SENSITIVITY OF	SHPERETNE	A THE CP REPORT & PERIOD COVERED
AUTHOR(7) Bernard D, Pollock Mallace E. Voreck Service Servic	PETN AND DEXTRINATED LEAD AZIDE	SUPERFINE	Technical memail
Bernard D, Pollock Wallace E, Voreck Explosives Division, FRL Picatinny Arsenal Dover, NJ 07801 Conjective office HAME AND ADDRESS La BERNARD DATE Conjective office HAME AND ADDRESS La BERNARD DATE Picatinny Arsenal Dover, NJ 07801 Conjective office HAME AND ADDRESS La BERNARD DATE Picatinny Arsenal Dover, NJ 07801 Conjective office HAME AND ADDRESS La BERNARD DATE Picatinny Arsenal Dover, NJ 07801 Conjective office HAME AND ADDRESS La BERNARD DATE Picatinny Arsenal Dover, NJ 07801 Conjective of the American Date La BERNARD DATE Picatinny Arsenal Dover, NJ 07801 Conjective of the American Date La BERNARD DATE Picating Conference of the American Date Conjective of the American Date Conje	AUTHOR(=)	<u></u>	8. CONTRACT OR GRANT NUMBER(*)
TERPORTING OF ANT ATTOM NAME AND ADDRESS EXPLOSIVES DIVISION, FRL Picatinny Arsenal Dover, NJ 07801 Conserved of Picet NAME AND ADDRESS Conserved of Picet NAME ADDRESS Conserved of Mile Report Approved for public release, distribution unlimited. Conserved of Picet Name and Address and Miles Picet Name Picet Conserved of Picet Name Address and Miles Picet Name Picet Picet Name Picet Name Address and Address and Picet Picet Name Picet Picet Name Picet Name Picet Name Address and Picet Picet Name Picet Picet Name Picet Name Picet Name Picet Picet Picet Name Picet Picet Name Picet Picet Name Picet Picet Name Picet Pic	Bernard D./Pollock Wallace E./Voreck		
UDUCT, NO ODD UDUCT, NO ODD UDUCT, NO ODD UDUCTANE AND A DRESS UDUCTOR TO THE TAKE AND A DRESS UDUCTOR TO THE POWNER TO THE POWNER TO THE POWNER TO THE POWNER TO THE THE POWNER TO THE	PERFORMING ORGANIZATION NAME AND ADDR Explosives Division, FRL Picatinny Arsenal Dover NL 07801	E\$5	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
Februarization A MODIFIEND ADDRESS (II different from Controlling Office) A MODIFIEND ADDRESS (Continue on reviews adds If necessary and Identify by Mock number) Lead azide, Impact sensitivity Electrostatic sensitivity Ball drop test A Advinct (Continue on reviews adds If necessary and Identify by Mock number) Lead azide, Impact sensitivity Superfine PETN Hot wire sensitivity A MODIFICATION OF the Materia and Identify by Mock number) The sensitivity Ball drop test A Advinct (Continue on reviews add Minuthy by Mock number) Is estimated as "Superfine" PETN Hot wire sensitivity A bernact (Continue on review add Minuthy by Mock number)	I. CONTROLLING OFFICE NAME AND A DRESS		12. REPORT DATE
Lower Continue on control of the sharrest misred in Block 20, 11 different Pom Report) Unclassif of Lost Ribution Statement (of the sharrest misred in Block 20, 11 different Pom Report) Unclassif of Distribution Statement (of the sharrest misred in Block 20, 11 different Pom Report) Unclassif of Distribution Statement (of the sharrest misred in Block 20, 11 different Pom Report) Unclassif of Distribution Statement (of the sharrest misred in Block 20, 11 different Pom Report) Unclassif of Distribution Statement (of the sharrest misred in Block 20, 11 different Pom Report) Unclassif of Distribution Statement (of the sharrest misred in Block 20, 11 different Pom Report) Supplemental work performed for the George C. Marshall Space Flight Center, Alabama 35812 Ket WORDS (Continue on correct side (Insecteory and Identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Superfine PETN Hot wire sensitivity Applicability of Special PETN Initiability sensitivity data Electrostatic sensitivity Ball drop test Advance Compared with that of dextributed lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those UNCLASSIFIED security CLASSIFIED security CLASSIFIED	(1)330.	()	February 1976
Unclassified 13. DESTRIBUTION STATEMENT (of this Report) Approved for public release, distribution unlimited. 7. DISTRIBUTION STATEMENT (of the Abstract missed in Block 20, If different from Report) A supplemental work performed for the George C. Marshall Space Flight Center, Alabama 35812 4. KEY WORDS (Continue on reverse side if necessary and identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Superfine PETN Hot wire sensitivity Applicability of Special PETN Hot wire sensitivity Applicability of Special PETN Hot wire sensitivity Sensitivity data Electrostatic sensitivity Ball drop test 1. AsyNACT (Continue on reverse side if necessary and identify by block number) Lead azide, Impact sensitivity Sensitivity data Electrostatic sensitivity Ball drop test 1. AsyNACT (Continue on reverse side if necessary and identify by block number) The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those 1. Jum 7, 1473 FORTION OF 'HOV SE IS DESOLETE UNCLASSIFIED SECUNITY CLASSIFIED SECUNITY CLASSIFIED	4. MONITORING AGENCY NAME & ADDRESS(II dill	erent from Controlling C	ffice) 15. SECURITY CLASS. (of this report)
1se DECLASSIFICATION/DOWNGRADING 4. DISTRIBUTION STATEMENT (of the Report) Approved for public release, distribution unlimited. 7. DISTRIBUTION STATEMENT (of the abs/rect entered in Block 20, If different from Report) 6. SUPPLEMENTARY NOTES Experimental work performed for the George C. Marshall Space Flight Center, Alabama 35812 7. KEY WORDS (Continue on revues side if necessary and identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Electrostatic sensitivity of Special PETN Hot wire sensitivity Sensitivity data Electrostatic sensitivity Ball drop test Advine Trespect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those D 1/MATY 1473 EDITION OF 1 NOV 45 IS OBSOLETE			Unclassif od
DISTRIBUTION STATEMENT (of the Report) Approved for public release, distribution unlimited. DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 11 different from Report) DISTRIBUTION STATEMENT (of the absorber and isore 20, 20, 20, 20, 20, 20, 20, 20, 20, 20,			154. DECLASSIFICATION/DOWNGRADING SCHEDULE
Approved for public release, distribution unlimited. T. DISTRIBUTION STATEMENT (of the desired in Block 20, If different from Report) A. SUPPLEMENTARY HOTES Experimental work performed for the George C. Marshall Space Flight Center, Alabama 35812 A. KEY WJROS (Continue on reverse side if necessary and identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Superfine PETN Hot wire sensitivity Applicability of Special PETN Initiability sensitivity data Electrostatic sensitivity Ball drop test A APACT (Center - environ of N measured of Identify by block number) The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those D 1 JAM 73 EDITION OF 1 HOV 68 IS OBSOLETE UNCLASSIFIED SECURITY CLASSIFIED SECURITY CLASSIFIED	6. DISTRIBUTION STATEMENT (of this Report)		
Approved for public release, distribution unlimited. 7. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, If different from Report) a. SUPPLEMENTARY NOTES Experimental work performed for the George C. Marshall Space Flight Center, Alabama 35812 b. KEY WJROS (Continue on review aids if necessary and identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Superfine PETN Hot wire sensitivity Applicability of Special PETN Hot wire sensitivity sensitivity data Electrostatic sensitivity Ball drop test 1 ANYTACT (Condum on review of M materiary and identify by block number) The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both hots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those D_1_MARTS 1473 EDITION OF 1 NOVER IS DEFOLETE UNCLASSIFIED SECURITY CLASSIFICATION OF THIS FAGE (Them Date Entered)			
 DISTRIBUTION STATEMENT (of the abairect inferred in Block 20, If different From Report) SUPPLEMENTARY NOTES Experimental work performed for the George C. Marshall Space Flight Center, Alabama 35812 KEY WURDS (Continue on reverse elds if necessary and identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Superfine PETN Hot wire sensitivity Applicability of Special PETN Initiability sensitivity data Electrostatic sensitivity Ball drop test Advance of the office office of the office office of the office office office office office office office of the office office			
Experimental work performed for the George C. Marshall Space Flight Center, Alabama 35812 KEY WORDS (Continue on reverse side if necessary and identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Superfine PETN Hot wire sensitivity Applicability of Special PETN Initiability sensitivity data Electrostatic sensitivity Ball drop test ANTACT (Centhus a reverse othe M mercenser and identify by block number) The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those D 1 JAM 73 EDITION OF 1 NOV 68 IS OBSOLETE UNCLASSIFIED SECUMITY CLASSIFICATION OF THIS PAGE (Them Date Entered)	7. DISTRIBUTION STATEMENT (of the abstract ente	red in Block 20, if diffe	rent from Report)
KEY WORDS (Continue on reverse side if necessary and identify by block number) Lead azide, Impact sensitivity Electrostatic sensitivity Superfine PETN Hot wire sensitivity Applicability of sensitivity data Special PETN Initiability sensitivity data Electrostatic sensitivity Ball drop test sensitivity data AsymAct (Continue on reverse side N messessery and identify by block number) The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. D i JAM 73 EDITION OF I NOV SB IS OBSOLETE UNCLASSIFIED SECURITY CLASSIFICATION OF THIS PAGE (When Date Entered) SECURITY CLASSIFICATION OF THIS PAGE (When Date Entered)	7. DISTRIBUTION STATEMENT (of the abetract ente 8. SUPPLEMENTARY NOTES	red in Block 20, il diff	rent from Report)
Superfine PETN Hot wire sensitivity Applicability of Special PETN Initiability sensitivity data Electrostatic sensitivity Ball drop test sensitivity data AdornACT (Conthus a reverse of M mecrosery and identify by block number) The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. D 1 JAM 73 EDITION OF 1 NOV 65 IS OBSOLETE UNCLASSIFIED SECURITY CLASSIFICATION OF THIS PAGE (Them Data Entered) Mag 2000	7. DISTRIBUTION STATEMENT (of the abstract ente a. supplementary notes Experimental work performed for Alabama 35812	red in Block 20, 11 diffe	Marshall Space Flight Center,
The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those D 1 JAM 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE UNCLASSIFIED SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)	 7. DISTRIBUTION STATEMENT (of the obstract entered) 8. SUPPLEMENTARY NOTES Experimental work performed for Alabama 35812 9. KEY WORDS (Continue on reverse side if necessaria) 1. Net work of the state of the	the George C.	Marshall Space Flight Center,
The sensitivity of two different lots of a special grade of PETN, designated as "superfine" PETN was compared with that of dextrinated lead azide with respect to impact, shock, short high temperature pulses, and gaseous electrostatic discharge. Results of the seven tests employed showed that both lots were clearly less sensitive than the reference dextrinated lead azide. Responses were not markedly different than those D 1 JAM 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE UNCLASSIFIED SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)	 7. DISTRIBUTION STATEMENT (of the abstract entered) 8. SUPPLEMENTARY NOTES Experimental work performed for Alabama 35812 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 9. KEY WORDS (Continue on reverse elde 11 necessaria) 	the George C. y and Identify by block mpact sensitiv lot wire sensitiv nitiability sall drop test	Marshall Space Flight Center, number) Vity Electrostatic sensitivity Sivity Applicability of sensitivity data
D 1 JAN 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE UNCLASSIFICATION OF THIS PAGE (When Date Entered)	 7. DISTRIBUTION STATEMENT (of the abstract enternance) a. SUPPLEMENTARY NOTES Experimental work performed for Alabama 35812 a. KEY WORDS (Continue on reverse elde if necessar Lead azide, I superfine PETN H Special PETN I Electrostatic sensitivity E a. ASTRACT (Continue on reverse elde M mecessar) 	the George C. y and Identify by block mpact sensitiv lot wire sensitiv nitiability sall drop test	Marshall Space Flight Center, number) 'ity Electrostatic sensitivity :ivity Applicability of sensitivity data
SECURITY CLASSIFICATION OF THIS PAGE (When Date Entered)	 7. DISTRIBUTION STATEMENT (of the abstract enternation of the abstract entern	the George C. y and Identify by block mpact sensitiv lot wire sensitiv all drop test and Identify by block mathematic sensitive all drop test and Identify by block sensitive sensitive all drop test and Identify by block sensitive sensitive as compared with lock, short hig Results of the ly less sensitive sensitive sensitive sensitive sensitive as were not mathematical sensitive s	Marshall Space Flight Center, number) 'ity Electrostatic sensitivity ivity Applicability of sensitivity data (h temperature pulses, and the seven tests employed ive than the reference arkedly different than those
282 900	 7. DISTRIBUTION STATEMENT (of the abstract enternation of the abstract entern	the George C. y and Identify by block mpact sensitiv lot wire sensitiv all drop test and Identify by block mat identify by block arent lots of a cock, short hig Results of the lock, short hig Results of the sensitive as compared with the sensitive as compared with a sensitive a	Marshall Space Flight Center, Marshall Space Flight Center, number) 'ity Electrostatic sensitivity ivity Applicability of sensitivity data number) a special grade of PETN, th that of dextrinated lead the seven tests employed tive than the reference arkedly different than those UNCLASSIFIED
	 7. DISTRIBUTION STATEMENT (of the abstract enternation of the abstract en	the George C. y and identify by block mpact sensitiv lot wire sensitiv sall drop test and identify by block rent lots of a tas compared with ock, short hig Results of the res were not mat secure secure	Marshall Space Flight Center, number) Yity Electrostatic sensitivity Sivity Applicability of sensitivity data Number) A special grade of PETN, th that of dextrinated lead th temperature pulses, and the seven tests employed tive than the reference arkedly different than those UNCLASSIFIED TY CLASSIFICATION OF THIS PAGE (Them Data Entered)

i

and the second second

1

. ..

٦.

:

. . .

.



....

**

The citation in this report of the names of commercial firms or commercially available products or services does not constitute official endorsement or approval of such commercial firms, products, or services by the United States Government.

i

in:4

.

a,

TABLE OF CONTENTS

	Page No.
Introduction	1
Description of the Explosives	3
Experimental Tests and Results	3
Impact Sensitivity (Bureau of Mines Apparatus)	4
Discussion	4
Impact Sensitivity (Ball Drop Apparatus)	5
Initiation Sensitivity (Minimum Priming Charge)	6
Small Scale Gap Test	8
Hot Wire Sensitivity	12
Electrostatic Sensitivity (Standard Picatinny Arsenal Test)	19
Electrostatic Sensitivity (Explosives Division Parametric Test)	21
Conclusion and Recommendations	23
Acknowledgement	24
References	26
Distribution List	27
Tables	
1 Test plan for the explosive sensitivity study	2
2 Summary of impact sensitivity data, Bureau of Mine Apparatus	5
3 50% heights by the ball-drop method	6
4 Minimum priming charge - Results for initiation sensitivity test	9
5 Minimum priming charge - Original test results for initiation sensitivity test	10
6 Small scale gap test results	13

7	Summary of hot wire sensitivity data	18
8	Summary of electrostatic sensitivity data	20
9	Electrostatic sensitivities (joules) by the parametric method	22
10	Summary of test results	25
Figures		
1	Schematic of minimum priming charge test	7
2	Small scale gap test	11
3	Shock sensitivity vs theoretical density	14
4	Hot wire ignition test	15
5	Schematic of hot wire sensitivity test	16

INTRODUCTION

This study was undertaken to compare the sensitivity of a special grade of PETN--designated here as "superfine" PETN¹-.to that of dextrinated lead azide with respect to impact, shock, heat, and electric discharge. This material consists of granular crystallites about 10 microns in size.

The information was required in order to determine the acceptability of this material for NASA Space Shuttle applications. In addition, a number of comparison tests were performed on other explosives of interest to NASA, for which information in the literature was lacking or sparse.

The experimental work, described later in some detail, includes provisions for comparisons of sensitivity to impact by the Bureau of Mines method (Ref 1), and by a ball-drop method used by the Explosives Division for primary explosives (Ref 2); to shock using the "sensitivity-to-initiation" test (Ref 3) and the small scale gap test devised by the Navy (Ref 4); to short pulses of heat (Ref 5); and to electrostatic discharge by the standard method used at Picatinny Arsenal (Ref 1). In addition, a supplementary electrostatic test using a parametric procedure and an apparatus employing parallel plate electrodes (Ref 6) was also used on the grounds of greater sensitivity and closer approach to voltage and capacitance values encountered in practice.

A summary of the tests performed, and a list of the test explosives together with their identification by lot number, are given in Table : For convenience, the Ensign-Bickford PETN is designated as "PETN (E-B)" and the DuPont material as "PETN (DuP)." The regular grade PETN, which meets Mil-P-387 specifications, is designated without a subscript.

¹U.S. Patent 3, 754, 061 Issued to C.D. Forest, August 1971, assigned to DuPont.

-	
ble	I
Ta	

.

۰.

L.

Test plan for the explosive sensitivity study

	Im	pact	Sho	ock	Heat	Electr	rostatic
Explosive (Identification)	bureau or Mines (cm)	Ball Drop (inches)	Initiation Sensitivity (g LA)	SSGT (decfbands)	Hot Wire (mjoules)	Picatinny Arsenal (joules)	Explosives Division (joules)
PETN (E-B) Ensign-Bickford 9-56A	X	×	×	X	×	×	×
PETN (BuP) DuPont L-71N011A-254	×	×	×	×	×	×	×
Lead Azide, dextrinated Olin-Matheson OMC 69-104	×				×	×	×
PETN Uni dynamics 5-309		×		×	×		
HNS-II* Ensign-Bickford ENB-5735-02	×		×		×		
HMX (Class B) Holston SR 070402					×		
RDX (Class B) (lot number not kn	own)				×		

*HNS (Hexanitrostilhene): This is the fine size fraction. HNS-I is the coarser fraction.

į

٦,

DEUCRIPTION OF THE EXPLOSIVES

Two lots of superfine PETN were tested. One was supplied by Ensign-Bickford and the other by the Pompton Lakes Facility of DuPont. Both batches were shipped under alcohol-water mixture. Laboratory portions were removed from these wet batches, filtered, and washed with methyl alcohol on a Buc mer funnel, and then dried for twenty-four hours in a vacuum oven at 60-65°C. All vacuum-dried materials were kept in closed conductive rubber containers until used.

Where samples had to be prepared by pressing, the pressing operation was performed in a room kept at 25°C and 50-55% RH.

EXPERIMENTAL TESTS AND RESULTS

The term "minimum" energy (or other stimulus) when used in connection with sensitivity data refers to the lowest level at which at least one fire is obtained in ten trials. Occasionally the next lowest level is given, i.e., the highest level at which some specified number of consecutive (commonly ten) no-fires is obtained. This is referred to as a "zero" level. As a matter of prudence, however, both values should be regarded only as a measure of the level below which it is not feasible to estimate initiation probabilities; one <u>must not</u> assume that initiation cannot occur at lower levels or that an explosive is "safe" if a higher level is not used.

An alternative commonly used value for comparing sensitivities is the "50% Point," i.e., the level at which probability of initiation is 50%. This value is estimated in this work by the Bruceton method, which is described in Reference 7 under "US/Impact/02." The testing is carried out in the region where both positive and negative trials occur, and the level of stimulus is changed after each trial in accordance with a definite pattern. Thus, if a given trial is negative (no fire), the stimulus is increased to the next higher step. If the given trial is positive, the level is decreased one step. The steps are equal, and usually are chosen to approximate one standard deviation.

Impact Sensitivity (Bureau of Mines Apparatus)

Experimenta?

In this test (Ref 1, 7) a small amount, nominally 20 mg, of the loose powder is placed on a steel anvil of Rockwell hardness C 60-65 and a striker of similar hardness is lowered onto the powder. The surfaces of both anvil and striker are smooth. A drop weight of 2 kg mass is allowed to drop by free fall onto the striker and the result is noted. Any evidence of reaction, such as sound, smoke, or light, is taken as a "fire."

Results

Results are summarized in Table 2 and are for the minimum heights at which one explosion occurred in ten or fewer trials. Tetryl has been included in this test for reasons given in the "Discursion" following.

Discussion

It is common practice, in testing for impact sensitivity, to include one or more "standard" explosives to ensure that the apparatus is functioning properly. In the test plan of Table 1, the lead azide served this purpose; however, the result was lower than is sometimes observed (e.g., see Ref 3). Tstryl was therefore run to determine whether or not the apparatus was consistent or whether the lead azide result was anomalous. Comparison of the results obtained in this work with values for the azide and tetryl from the literature show that both are less than literature values by roughly the same amount. It was therefore assumed that a valid comparison between the superfine PETN and lead azide could be made.

The average value of the two superfine PETN samples is 15.5 cm, or very nearly twice the height for the lead azide, and indicates a significantly lower sensitivity to impact than is shown by azide.

Summary of impact sensitivity data, Bureau of Mine Apparatus

Explosive	<u>10% Ht (cm)</u>
PETN (E-B)	13
PETN (DuP)	18
Lead Azide	8
HINS	15
Tetryl	20

Impact Sensitivity (Ball Drop Apparatus)

Experimental

The essential features of the ball drop assembly (Ref 2) are a small hardened steel block, a 1/2 inch diameter ball bearing (8.33 g), a grooved track to release the ball bearing at a given height, and a ring stand to hold the assembly. The block is provided with a pair of side rails, whose height above the impact block is adjusted by means of shims to 0.013 inch. In practice, about 35 mg of explosive is put in the center of the block, and the powder is leveled off to a thickness of 0.013 inch by running a straightedge or plastic rod along the side rails. The block is centered beneath the track, whose height is selected, the ball is allowed to roll off the track and fall onto the powder, and the result noted.

Results

Results are summarized in Table 3, together with other available comparative data. Note that no fires were obtained for any of the PETN samples at the maximum available height of 45 inches. In contrast, the data for several different lots of various types of lead azide (including dextrinated) during a number of surveillance and other studies were in the range of 21.3 to 24.3 inches.

50% heights by the ball-drop method

	<u> </u>	t, inches
Explosive	This Work	PATR 4357
PETN (E-B)	45+	
PETN (DuP)	45+	
PETN	45+	
Lead Azide		21.3-24.3

Discussion

V

This test shows unequivocally that the superfine PETN powder is much less sensitive to impact than is lead azide.

Initiation Sensitivity (Minimum Priming Charge)

Experimental

In this test (Ref 3) the sample consists of 0.4 g of the test explosive, which is pressed at 3,000 psi into an empty No. 6 blasting cap. The test variable is the amount of lead azide, which is pressed on top of the test explosive. The amount of lead azide is varied in increments of 0.01 g. A steel witness disc, 1 inch diameter x 1/16 inch thick, of cold rolled steel, is used as a criterion of detonation: a positive result is indicated by a hole being blown through the disc. The procedure was to repeat trials at decreasing increments of lead azide in order to determine the larges, quantity that would result in ten consecutive no-fires.

The experimental setup is shown in schematic form in Figure 1.



Results

The test for all PETN samples was terminated when the amount of lead azide had been reduced to 0.005 g, since it was not feasible to use lesser amounts. Results are summarized in Table 4. The procedure is also shown in Table 5. PETN samples could not be fired without lead azide.

Discussion

A direct comparison of shock sensitivity between PETN and lead azide cannot be made in this test; however, it is apparent that the superfine PETN should offer no problem in application due to difficulty in initiation.

Small-Scale Gap Test

Experimental

In this test (Ref 4) an explosive is subjected to an attenuated shock from a standard source. The source consists of a column of RDX in a 1.00-inch-OD brass tube having an ID of 0.204 inch and 1.50 inch length. The RDX is pressed to a loading density of 1.56 g/cc. The test explosive is pressed at 16,000 psi into a similar brass tube in seven increments in order to achieve as uniform a loading density as possible. Attenuation is produced by inserting various thicknesses of polymethylmethacrylate (PMMA) between the donor and the test explosive (the acceptor). A 1/2-inch-thick block is used as a witness plate to determine the occurrence of a fire. Two shots are fired without any attenuation and the depth of the dent produced in the block is measured. In subsequent shots, a dent equal to or greater than 1/2 the "barefoot" dent is taken arbitrarily as a fire. The arrangement is illustrated in Figure 2 except that the chamber used to contain the explosion is not indicated. The shock strength in "decibangs" is defined by the equation:

S (decibangs) = 30 - 10 (Log X)

where S is the shock strength and X is the total thickness of the PMMA discs in units of 1/1000 inch (mils). Note that the thinner the gap, the greater is the shock strength. A negative value means only that the gap was greater than 1000 mils.

ł

Minimum priming charge Results for initiation sensitivity test

<u>Explosive</u>	Weight of Lead Azide (g)
PETN (E-B)	< 0.005
PETN (DuP)	< 0.005
PETN	< 0.005
HNS-II	0.05

9

 「「「「「「「」」」」

Tab	le	5
-----	----	---

.

$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	PETN	(E-B)	Pi	ETN	HN	<u>S-II</u>
$\begin{array}{cccccccccccccccccccccccccccccccccccc$	mg LA	Result	mg LA	<u>Result</u>	mg LA	Result
$\begin{array}{cccccccccccccccccccccccccccccccccccc$	40	+	10	+	100	-
$ \begin{array}{cccccccccccccccccccccccccccccccccccc$	30	+	10	+	100	+
$ \begin{array}{cccccccccccccccccccccccccccccccccccc$	20	+	5	+	90	-
$ \begin{array}{cccccccccccccccccccccccccccccccccccc$	10	+	5	+	90	-
$ \begin{array}{cccccccccccccccccccccccccccccccccccc$	5	-	5	+	80	+
$ \begin{array}{cccccccccccccccccccccccccccccccccccc$	5	-	5	+	70	+
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	5	+	0	-	60	-
$\begin{array}{cccccccccccccccccccccccccccccccccccc$			0	-	60	-
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	End of	test	0	-	60	-
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$			0	-	60	+
PETN(DuP) 0 - 50 - mg LA Result 50 - 50 - 10 + 50 - 50 - 5 - 50 - 50 - 5 - 50 - 50 - 5 - 50 - 50 - 5 - 50 - 50 - 5 - 50 - 50 - 5 - 50 - 50 -			0	-	50	-
solution solution mg LA Result solution 10 + 50 - 5 - 50 - 5 - 50 - 5 - 50 - 5 - 50 - 5 - 50 - 5 - 50 - 5 - 50 -	PFTN/	DuP)	0	-	50	-
$\begin{array}{cccccccccccccccccccccccccccccccccccc$					50	-
mg LA Result 50 - 10 + 50 - 5 - 50 - 5 - 50 - 5 - 50 - 5 - 50 - 5 - 50 -		a - .			50	-
$\begin{array}{cccccccccccccccccccccccccccccccccccc$	mg LA	Result			50	-
10 + 50 - 5 - 50 - 5 - 50 - 5 - 50 -	••				50	-
5 - 50 - 5 - 50 - 5 - 50 -	10	+			50	-
5 - 50 - 5 - 50 -	5	-			50	-
5 - 50 -	5	-			50	-
5 +	5 5	-+			50	-

Minimum priming charge Original test results for initiation sensitivity test

٩.

<u>6</u>___

10

Ċ,



The Bruceton procedure was used to estimate the 50% points. For reasons of safety, regular PETN was used as reference material, rather than lead azide.

Results

The data are summarized in Table 6, together with pertinent information for the reference materials taken from Reference 4. Sensitivity to shock is a function of loading density; therefore, the values in the table are to be taken as estimates of the 50% points, for samples having the average density and standard deviations (sd) given in the second column. In the case of lead azide, the sensitivity is not markedly affected in the density range given. This range includes most densities obtained in practice. The data are also shown graphically in Figure 3.

Discussion

An evaluation of the data in Table 6 is most conveniently made visually by referring to the plots of shock strength, "S", vs % TMD (% theoretical maximum density) in Figure 3. In the plots for the PETN samples run in this work, the horizontal lines through the points indicate the standard deviations of the sample densities.

Although the "range of action" (i.e., the range of stimulus values within which one obtains both positive and negative trials, and which are used to calculate the 50% points) in this test was greater than was reported in Reference 4, the ranges were well separated from the data for the lead azide and clearly indicate the considerably lesser sensitivity to shock than is shown by azide. The values are all clustered fairly close together and near those given in Reference 4 for regular PETN, indicating that there was no gross experimental discrepancy. In light of these facts, it is concluded that both superfine PETN samples are less sensitive than lead azide to shock, and there is no marked difference between the different lots of the test explosives.

Hot Wire Sensitivity

Experimental

The test selected for this work was that for the qualification testing of primary explosives (Ref 5, 8, 9). The sample configuration is illustrated in Figure 4, and the test circuit is illustrated in Figure 5. The test variable was the voltage to which the

12

 (\cdot)

. مر شو . ٤.

1

"

÷.

Small-scale gap test results

	% Theoretical mavimum dencity	<u>Sensitivit</u>	v in decibangs
Explosive	% TMD (Sd)	This Work	Reference 8
PETN (E-B)	92.7% (sd = 3.5%)	3,38	
PETN (DuP)	92.0% (sd = 2.8%)	3.63	
PETN	93.5% (sd = 3.9%)	3.63	3.17 (at 93% TMD)
Lead Azide (dextringted)			3 to2 (for 2.775 - 3.663 g/cc)



and the set of a



....

-

Ņ

me.



• 2.

:

Fig 5 Schematic of hot wire sensitivity test

Ę

• • • •

Ļ

(

16

P S

1

*

1.0-mF capacitor was charged, the voltage being varied in increments of 0.03 log unit, with 100 volts as the "zero" level. The Eruceton procedure was used to estimate the 50% points.

An experimental difficulty centered about the choice of the criterion for "fire" in the case of the less sensitive explosives. There was no difficulty at all with the lead azide, since a fire was very clearly evident by sound, complete consumption of the explosive sample, and shattering of the header. In the other samples, however, there were no such obvious "signals;" indeed, it was found that the wire burned out at levels not much above those required for lead azide, and at higher levels the burning out of the bare wire gave as much or more "fireworks," as was shown by the explosive samples. Accordingly, the criterion used was based on visual observation and used light emission, movement of the powder (as shown by a puff of white smoke), and sparks. There was a considerable element of subjectivity involved. In the opinion of the author, the results for the PETN and other secondary explosives are probably highly conservative, since there was no sound, or evidence of chemical decomposition products, or discoloration. The "puff of smoke" used as a partial criterion was probably dust blown out by expanding hot air.

Results

The results of the test are summarized in Table 7. Because of the ambiguity of the criterion of fire in the cases of the less sensitive explosives, the values given for these explosives should be considered as lower limits of energy for 50% probability of initiation and should not be used for quantitative comparisons with lead azide, or for comparison among themselves.

Discussion

The data indicate that all test explosives are less sensitive to short high temperature pulses than is lead azide.

Summary of hot wire sensitivity data

Explosive	E _{50X} (Millijoules)	
Lead azide	5	"Well behaved;" no trouble
PETN (E-B)	26	In this and the following tests, the criterion of fire was "visible flame, powder movement and sound." In case of doubt, "fire" was assumed.
PETN (DuP)	21	
PETN	21	
HNS-II	30	
HMX	35	
RDX	17	

Electrostatic Sensitivity (Standard Picatinny Arsenal Test)

Experimental

The apparatus (Ref 1) consists of a sample holder and a movable electrode, a set of capacitors which can be charged by a variable voltage supply, switches, interlocks, and timing mechanisms.

The samples were 50-mg portions of loose powder. The procedure was to place the explosive in a shallow depression in a steel holder, and to allow the discharge that occurs as the needle electrode approaches the sample to arc around or through the sample. Capacitors of various sizes could be used, and these could be charged to different voltages to obtain a range of energy values as calculated by the formula:

 $E = CV^2/2$ (in joules)

where E is the energy, C is capacity in farads, and V is in volts.

The operator looks for any evidence of reaction, and 'ita are recorded in terms of fraction fired out of ten samples for each energy setting. Results are expressed in terms of the minimum energy at which one or more fires are obtained in ten trials.

Results

Results are summarized in Table 8. Two groups of tests were run. In the first, an appreciable difference between the two superfine PETN samples was observed, and it was also noted that the humidity was higher than normal. It was considered advisable for these reasons to repeat the tests at a lower humidity, and to include a sample of lead azide for comparison.

Discussion

The data for the lead azide is in good agreement with published data. Presumably, therefore, the data for the other samples are valid, and indicate some difference, though not a major one, between the sensitivities of the two superfine PETN samples. The sensitivity of the PETN samples is comparable to that of HMX.

Summary of electrostatic sensitivity data

Picatinny Arsenal Standard Test

<u>This Work (joules)</u>			
<u>Explosive</u>	<u>lst Group</u>	2nd Group	From Reference 3
PETN (E-B)	9.76	9.76	
PETN (DuP)	1.33	4.96	
PETN		6.28 (Ref 11)	11.0
HMX	11.02		
Lead azide		0.004	0.006

20

£

Electrostatic Sensitivity (Explosives Division Parametric Test)

Experimental

The apparatus (Ref 6) is of the fixed-gap type and consists of a parallel gap assembly, a set of the capacitors and resistances, a variable source of voltage, a voltmeter, and switching devices. The gap assembly consists of a pair of smooth, parallel, steel electrodes separated by a thin sheet of dielectric material, usually 0.0075" thick electrical insulating tape in which a 3/16" diameter hole has been punched. A small amount, about 6 to 7 mg, of powder is put into the hole and the upper electrode placed over the sample. This arrangement provides good confinement and greater sensitivity than for less confined conditions.

As originally developed, capacitances approximating those likely to be found in the field--up to about 2000 pf--were usually used, and these were charged to a sufficient voltage to ensure gaseous breakdown, depending on the nature of the powder. In addition, lumped resistance, ranging from zero to several thousand ohms, may be inserted in the discharge circuit.

The circuit resistance has several effects on the discharge. Thus (depending on voltage relative to resistance) the resistance changes the discharge from an oscillatory to a unidirectional one, from arc to glow form, affects duration, and at the higher values may give rise to a relaxation oscillation instead of a single continuous gasecus discharge (Ref 6). Concurrent with these effects is a change, in a non-monotonic manner, in the fraction of stored energy that is delivered to the gap. It is to evaluate these effects on electrostatic sensitivity that this test was devised.

Various capacitors were charged to sufficient voltage to cause breakdown; however, it was necessary in these tests to use considerably larger capacitors than were usually used for primary explosives in order to obtain any positive results for PETN.

Results

Results are expressed as "zero" energies, based on twentyfive consecutive no-fires, and are summarized in Table 9.

Note the lower sensitivity of both samples of superfine PETN than lead azide at both zero circuit resistance and at high values. At the zero resistance, the discharge would be unidirectional and of glow form.

Electrostatic sensitivities (joules) by the parametric method

Explosive	0 Ohms	10 ⁵ Ohms	<u>10⁶ Ohms</u>
PETN (E-B)	0.37	1.83+	1.83+
PETN (DuP)	0.27	1.83+	1.83+
Lead azide (dextrinated)	5.6 x 10^{-3}		3.9×10^{-3}

∿44£ ¹⁶157 *Na

Discussion

These results show a two-order-of-magnitude difference between the superfine PETN and azide at zero circuit resistance, and a three-order difference at high resistance. In this the parametric test confirms results of the Picatinny Arsenal test.

CONCLUSION AND RECOMMENDATIONS

Before summarizing, some comments about the limitations and usefulness of sensitivity data, and a cautionary note, are in order. First, current theory holds that initiation occurs when a critical volume at some local site reaches a temperature at which reaction is too fast to be quenched by the surrounding material. Thus, if energy released in such a "hot spot" can raise the temperature of the surrounding matter to reaction temperature rapidly, a runaway condition is set up. Although it is probable that the conditions controlling the transfer of energy (presumably heat) to the surrounding material are subject to considerable statistical variation, and there may be considerable question as to the validity of assumptions made in attempts to apply the theory, the underlying idea that initiation requires a localized region of high energy density does appear plausible. It is also reasonable to believe that the required critical amount of energy for the average local site is very much smaller than is very often available. It is difficult to anticipate the ways in which energy may become concentrated in a small region. The tests used are intended to simulate, so far as possible, the real hazard situation, but it should be kept in mind that such a procedure does not give a very good sampling of the situations that give rise to hazards, nor of the statistical variations in site conditions. This factor probably accounts for some of the unexplained accidents that have occurred.

A second point concerns the statistical nature of the initiation process and of sensitivity data in general. In practice we are interested in either the high or the low "tail" of the firing curve; either we want the explosive not to fire (with great certainty) or we do want it to fire (on demand) with great certainty. It is not feasible to determine such conditions directly because of the prohibitively large number of trials needed for any degree of roliability. Hence, one is constrained to work in the more accessible range, say from about 10% to 90% probability and to extrapolate in some manner to the region of interest. For this it is necessary to assume

some probability distribution function--usually the Gaussian--which implies that there is a non-zero probability at all levels despite the frequent use of "zero probability" in connection with minimumtype data. There is no assurance that the assumed function does accurately reflect initiation probability at low levels (it may be higher) and in any case there is considerable inherent uncontainty in making a long extrapolation. Experience has shown some correlation between these kinds of results and accident frequency, and in practice it is customary to compare data for a test explosive with that for materials for which there is a large body of experience. This is the practice followed in this study.

The results of these tests are summarized in Table 10, and indicate that superfine PETN is similar to standard PETN, and is less sensitive than lead azide to mechanical impact, explosive shock, short high temperature pulses, and electrostatic discharge. Nevertheless, in light of the comments above, one is definitely not justified in neglecting well established safety practices nor in being "disrespectful" in the handling of explosives, however insensitive they appear to be in tests such as these.

ACKNOWLEDGEMENT

The authors are indebted to Hugh Caldwell of Ensign-Bickford and to Carl E. Hutter of the Explosives Products Division of DuPont for providing the test explosives used in this work. We also wish to thank Everett W. Dalrymple, Walter B. Zimny, and Maurice S. Kirshenbaum, who performed much of the test work, and Nathaniel M. Palmer and Henry J. Jackson, who prepared the samples for the smallscale gap, the hot wire, and the initiation sensitivity tests.

3

à

Table 10

نټ
resul
test
of
Summary

Terk N

11

- **4**. (1)

۰.

i

	Imp	act	Sho	Ċ	Heat	Electr	ostatic
<u>Explosive</u>	Bureau of Mines (cm)	Ball Drop (inches)	Initiation Sensitivity (mg_LA)	Small Scale Gap Test (decibangs)	Hot Wire (millijoules)	Standard PA Test (joules)	Expl Div Parametric (joules)
Superfinc PETN (E~B)	13	45+	0.005	3.38	26	9.75/9.75	0.37 to 1.83+
PETA (DuP)	18	45+	0.005	3.63	21	1.33/4.96	0.27 to 1.83+
PETN (Mi1-P-38)		45+	0.005	3.63	21	6.28	
HNS-11	15		0.05		30		
RDX					17		
XMH					35	11.02	
Lead azide	8	21.3 -			S	0.004	3.9 x 10 ⁻³ to 5.6 x 10 ⁻³

REFERENCES

- 1. Clear, A. J., "Standard Laboratory Procedures," Picatinny Arsenal Technical Report 3278 (Rev 1), 1965.
- 2. Voreck, W. E., "Photomicrographic Examination of Explosives," Picatinny Arsenal Technical Report 4093, AD 876,322, August 1970.
- 3. Engineering Design Handbook, Explosive Series, "Properties of Explosives of Military Interest," AMCP 706-177, March 1967.
- 4. Ayres, J. N., Montesi, L. J., Bauer, R. J., "Small Scale Gap Test Data Compilation 1959-1972, Vol 1," NOLTR 73-132, 1973.
- 5. "Safety and Performance Tests for Qualification of Explosives," prepared by NWC, China Lake, NAVORD OD 44811, January 1972.
- 6. Kirshenbaum, M. S., "Response of Lead Azide to Spark Discharges Via a New Parallel-Plate Electrostatic Sensitivity Apparatus," Picatinny Arsenal Technical Report 4559, AD 768,161, June 1973.
- 7. Walker, G. R. (ed.), "Manual of Sensitiveness Tests," Canadian Armament Research and Development Establishment, 1966.
- 8. Conversation with Mr. Vignault, NWC (China Lake), 10 July 1974.
- 9. Conversation with H. Leopold, NOL (White Oak), 25 October 1974.
- 10. Campisi, J., Propellants Division, FRL, Private Communication.
- 11. Federoff, B. T., Sheffield, O. E., Encyclopedia of Explosives, Vol 5, Picatinny Argenal Technical Report 2700, 1972.

DISTRIBUTION LIST

1 . .

Copy No.

Commander Picatinny Arsenal ATTN: _SARPA-FR	1-30
SARPA-TS-S Dover, NJ 07801	31-35
Defense Documentation Center Cameron Station Alexandria, VA 22314	36-47
Commander U.S. Army Materiel Command ATTN: AMCRD ANCDL Washington, DC 20315	48 49
Commander U.S. Army Armament Command ATTN: AMSAR-RDT (Dr. E. J. Haug, Jr) Rock Island, IA 61201	50
Commander U.S. Army Ballistic Research Laboratories ATTN: Technical Library AMXBR, Dr. Phillip M. Howe Aberdeen Proving Ground, MD 21005	51 52
Commander U.S. Army Frankford Arsenal ATTN: Technical Library Bridge and Tacony Streets Philadelphia, PA 19137	53
Commander Iowa Army Ammunition Plant ATTN: Mr. J. Polson Burlington, IA 52601	54
Commander U.S. Naval Weapons Center ATTN: Technical Library (Code 753) China Lake, CA 93555	55

27

hereft, "The second

Commander U.S. Naval Surface Weapons Center White Oak Laboratory ATTN: Technical Library Explosives Dynamics Branch (Mr. I. Kabik) Silver Spring, MD 20910	56-57
Commander U.S. Naval Ordnance Station ATTN: Technical Library Indian Head, MD 20640	58
Commander U.S. Army Armament Development & Test Center ATTN: Technical Library Eglin Air Force Base, FL 32542	59
Dr. R. Van Dolah Explosives Research Laboratories Bureau of Mines Pittsburgh, PA 15230	60
Robert S. White ET-14 NASA Marshall Space Flight Center Alabama 35812	61-73
Carl R. Hutter Explosives Products Division DuPont Company Pompton Lakes, NJ 07444	74
Hugh Caldwell Ensign-Bickford Company Simsbury, CT 06070	75
Los Alamos Scientific Laboratory Box 1663 ATTN: Thomas Larson Los Alamos, NM 87544	76
Lawrence Livermore Laboratory P.O. Box 808 Livermore, CA 94550	77

ļ

2.

÷4

28

١

Sandia Laboratories ATTN: Technical Library P.O. Box 5800 Albuquerque, NM 87115

NS THE CONTRACT

29

. in 14

.

,

١