	U.S. DEPARTMENT OF COMMERCE National Technical Information Service
	AD-A030 955
Nonm	etallic
Water	rstops
Army Engineer Wa	terways Experiment Station Vicksburg Miss
Oct 70	

<u>इन्ह</u> क श्र' र

L



This document has been approved for public release and sale; its distribution is unlimited

Destroy this report when no longer needed. Do not return it to the originator.

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.



and the second and the second second second second

MISCELLANEOUS PAPER C-70-22

NONMETALLIC WATERSTOPS

Ьу

G. C. Hoff, B. J. Houston



October 1970



Published by: 33. S. Army Engineer Waterways Experiment Station, Vicksburg, Mississippi

ARMY-WRC VICKSBURG, MIGS

823

This document has been approved for public release and sale; its distribution is unlimited

FOREWORD

This paper was prepared at the request of ACI Committee 50% on "Joint Sealants" for consideration for inclusion in a Symposium on Joint Sealants to be held at the ACI 1971 Annual Meeting on 6-12 March 1971 in Denver, Colorado.

TA7

No (1-70-22 Cep 2

> The various investigations which provided the majority of the information and data discussed herein were conducted by the U. S. Army Engineer Waterways Experiment Station (WES), Vicksburg, Miss., under the sponsorchip of the Office, Chief of Engineers, under Engineering Studies Item 012, "Investigation of Watersteps for Construction Joints." The work was accomplished during the period since 1956 under the general supervision of Mr. T. B. Kannedy, former Chief, and Mr. Bryant Nather, present Chief of the WES Concrete Division, Mr. J. M. Polatty, Chief of the Engineering Mechanics Branch, and Mr. R. V. Tye, Jr., Chief of the Engineering Sciences Branch. Mr. B. J. Houston war the projec: leader ' the majority of the work discussed, and Mr. G. C. Hoff and he prepared this paper.

> > 69355

西方ちょう うちょう

SYNOPSIS

Nonmetallic waterstops having suitable properties for use in joints in hydraulic structures of concrete have been made successfully from natural rubber, synthetic rubber, and polyvinyl chloride. To perform satisfactorily, a waterstop must have sufficient strength and extensibility to avoid being ruptured by joint movement, and it must maintain strength and extensibility over the temperature range and in spite of chemical attack from the environment of service. It must also have suitable dimensions and configuration and be installed so as to avoid waterflow ground the embedded ends.

Field and laboratory studies have led to the conclusion that suitable waterstop materials should have a tensile strength of at least 1400 psi (plastic), 2000 psi (rubber), the ability to elongate 280 percent (plastic) or 360 percent (rubber), and to have various levels of maintenance of relevant properties after various chemical and thermal exposures.

NONMETALLIC WATERSTOPS

by

G. C. Hoff and B. J. Houston

The principal function of a waterstop is to serve as a barrier to the passage of water through, across, or along a construction joint in a concrete structure exposed to water on one or more surfaces. Such structures include dams, locks, power plants, pumping plants and canal linings.

MATER LALS

ために見るとうないと思いては、このないとなどである

Steel, lead, wrought iron, and copper have been used as waterstop mexerials generally as rigid plates or flexible diaphragms. Copper has been most used because of its ductility. It has a tensile yield strength of 30-40,000 psi with a modulus of elasticity of $15-16 \ge 10^6$ psi. Copper is nevertheless too stiff to accommodate large relative movements of a concrete joint. It is also easily damaged during concrete vibration. Repeated opening and closing of the joint may cause fatigue failure.

To overcome the s ortcomings of metal vaterstops, rubber waterstops were introduced in the early 1930's and used in the construction of the Imporial Dam on the Colorado River and the All-American Ganal in Southern California in 1935.¹ A variety of different rubber waterstop configurations were proposed. Those used by the Bureau of Reclamation between

1935 and 1953 were described by Allen and Higginson.¹ Rubber waterstops were also discussed by Kellam and Loughborough² in their account of the use of waterstops by the Hydro-Electric Power Commission of Ontario. A typical rubber waterstop can have a tensile strength of 3000 psi, a 500 percent elongation, and a modulus of elasticity at break of 600 psi.

「「「「「「「「「「「「「「「「「「「「」」」」」」」

Plastic waterstops were introduced in the midfifties with such plastics as polyvinyl chloride, polyethylene, polyurethane, styrenebutadiene, and others being used. Polyvinyl chloride, however, is the material usually used for plastic waterstop. The mechanical properties of any of the vorious plastics used can be varied widely by changing the formulation or method of compounding or both. The plastic used in a typical plastic waterstop, however, might be expected to have a tensile strength of 2000 psi, an elongation of 300-400 percent, and a modulus of approximately 600 psi.

CONFIGURATIONS AND APPLICATIONS

The four basic shapes for nonmetallic waterstops are shown in fig. 1. They are commonly called the: (a) labyrinth, (b) flat corrugated, (c) two-bulb dumbbell, and (d) three-bulb dumbbell. Many variations of these shapes exist, including those having noncircular bulbs or addicional vertical fins on the horizontal flange or center bulbs of shapes (b) or (d) or both.

Waterstops of shapes (b), (c), and (d) are used by embedding onehalf of their width in the concrete on each side of the joint so that the material spans th+ joint. The side bulbs of waterstops (c) and

(d) are greater in diameter than the web thickness and thus resist the tendency of the waterstop to be pulled out when joint movement occurs. The ribs or corrugations on type (b) perform the same anchorage function. Hollow-center bulbs (0-bulbs) as shown for (b) and (d) provide additional flexibility to the waterstop and help reduce the shearing stresses that occur in the waterstop when it is deformed transversely.

The use of waterstops (b), (c), and (d) requires splitting and bracing of the concrete form so that the waterstop can protrude from one placement into the area where the adjacent placement will occur. Labyrinth waterstops (type (a)) are designed to lie within the joint rather than extend through it and do not require splitting of the form. They are usually used where the joint is classified as a nonworking joint, i.e., little or no differential joint movement is anticipated. The need to split the form may also be avoided with waterstop of types (b), (c), and (d) if the flange to be embedded in the second placement of concrete is split and the halves are turned 90 deg and installed within the form for the first placement. These halves must be brought together and embedded in the second concrete placement. Waterstops of these designs are referred to as nail-on, unfold waterstops as opposed to the nail-on, labyrinth type.³

Dumbbell and flat corrugated type waterstops are usually used across working joints, i.e., joints where movements are expected.

Two-bulb dumbbells are generally used across joints where a predetermined amount of total lateral movement is expected or where continued lateral movement occurs through continues expansion or contraction of the joint. In both instances, the movement stretches the waterstop laterally across its width (fig. 2a). The three-bulb waterstop is usually used for unkeyed vertical or horizontal joints. In this instance, the joint movement can occur transversly (fig. 2b) across the thickness of the waterstop as well as laterally. When just transverse movement occurs, the center bulb is deformed as shown in fig. 3a. When both transverse and lateral movements occur simultaneously, the deformations as shown in fig. 3b result. The flat corrugated waterstop is used in the same situations described for the dumbbell types.

PERFORMANCE

To avoid costly and difficult if not impossible replacements of malfunctioning waterstops in a concrete structure, the waterstop should have a useful life comparable to that of the structure. Such factors as long-term durability, temperature sensitivity, extensibility, and water retentivity are all essential in establishing what the useful life of a water:top might be.

Durability

n have a start of the

and the second second

Performance requirements for waterstops in concrete structures vary greatly, depending on location and type of structure. The ideal situation would be to have one material for universal use. It is more

likely, however, that under some conditions one material will perform better while under other conditions another will perform better. In order to establish the long-term durability of nonmetallic waterstops, the U.S. Army Corps of Engineers initiated a research program in 1956 to determine the effects of different exposure conditions on various types of nonmetallic waterstops.^{4,5,6} Specimens of natural rubber, synthetic rubber, and polyvinyl chloride were studied in both streased and unstressed conditions for the following exposure conditions: (a) exposure to freezing and thawing in a marine environment, (b) exposure to wetting and drying in a warm marine environment, (c) outdoor exposure in a moderate climate, (d) indoor exposure (air without sunlight), (e) exposure in a weak solution of sodium and magnesium sulfate, (f) exposure to cold contaminated water, (g) exposure to cold fresh water, (h) exposure to warm contaminated water, and (i) exposure to warm fresh water. Visual inspections of the exposed specimens were made periodically for a time span of seven to nine years. Exposures (a) and (b) were obtained by placing the waterstop specimens at mean tide elevation on the beaches of Treat Island, Maine, and St. Augustine, Florida, respectively. Exposures (c), (d), and (e) were obtained at the U. S. Army Engineer Waterways Experiment Station concrete laboratory at Jackson, Mississippi. Exposures (f) and (g) were obtained where the Granite City, Illinois, sewage ditch empties into the Chain-of-Rocks Canal on the Mississippi River and at the upper river guidewall extension cells of the Mississippi River Lock No. 26 at Alton, Illinois, respectively.

Exposures (h) and (i) were obtained in an oil refinery waste drainage ditch near New Orleans, Louisiana, and in the Bayou Sorrel Lock on the Plaquemine-Morgan City Alternate Route Intercoastal Waterway in Louisiana, respectively. 8

The unstressed condition of the waterstop samples was achieved by hanging the waterstops from a seasoned oak strip or metal pipe. The stressed condition was achieved by bending the waterstop around the strip or pipe.

Some exposure tests of embedded waterstops were also conducted at Treat Island, St. Augustine, and Jackson outdoors. These samples consisted of 6-in. lengths cut from the finished waterstops. The ends of these lengths were embedded in 6- by 6-in. concrete cubes which were allowed to harden for 14 days. At that time, the joint was opened 1 in. and blocked in this position with the waterstop material stretched.

The detailed results of this exposure study have been reported by Houston.4,5,6

Results of the visual inspections of the specimens are summarized in table 1. All butyl, neoprene, natural, and service rubber test samples were affected by exposure at most of the exposure stations, with the more pronounced effects being on the specimens exposed at Jackson outdoors, at St. Augustine, and at Granite City in contaminated water.

A number of physical tests were performed on the weathered waterstops to evaluate changes in their physical properties. The test methods

employed in nonmetallic waterstop evaluations are listed in table 2. With the exception of butyl rubber, all other types of rubber experienced decreases in tensile strength and elongation with respect to the as-received, no-stress condition. All types of rubber experienced increases in the stress level at 300 percent elongation and in the hardness. The compressive set of butyl, service, and one type of neoprene decreased and increased for the natural rubber and one type of neoprene. Generally, of the natural and synthetic rubber materials from which the waterstops were made, neoprene best withstood most exposure conditions with natural, butyl, and service rubber following in that order. All rubbers were more affected by exposure when stressed than when unstressed, and less affected when embedded in concrete than when not embedded. Those specimens exposed to sunlight and air experienced more degradation with respect to performance than those that were immersed or indoors.

The polyvinyl chloride (PVC) specimens represented material produced by five manufacturers, with one of the manufacturers providing four different PVC formulations. All weathered PVC specimens showed increase: in tensile strength with respect to the as-received, no-stress material. The general tendency was for increased ultimate elongations with some exceptions. All weathered PVC specimens lost their ability to maintain their structural integrity to temperatures as low as those obtained by the unweathered specimens. All four formulations from the one manufacturer showed increased low temperature stiffness with exposure but the other products all experienced decreases. As with rubber, PVC was more

affected by hot sunlight and air than by other exposure conditions to which it was subjected. It was more affected when stressed than when unstressed, and less affected when embedded in concrete than when not. A number of the PVC specimens appeared to lose their plasticizer with exposure and became hard and brittle.

and the second states of the second

Temperature sensitivity

The performance of a waterstop in a given environment is influenced by tem; erature regardless of its weathered condition. Tests of waterstops made of natural rubber, neoprene, and PVC^7 were conducted in an environmental cabinet (fig. 4) to determine the effect of reduced temperatures on the ultimate strength and elongation. Reductions from 73 F to 0 F for PVC waterstops produced tensile strength increases from 40 to 100 percent and ultimate elongation reductions from 25 to 70 percent. A similar behavior was observed for the rubbers, but it was not as pronounced. Stressing the PVC and rubbers to 90 percent of their ultimate elongation at 73 F and then reducing the temperatures to -15 F did not induce failure in the specimens. Additional stretching at the -15 F temperature would result in failure, however.

Extensibility

Extensibility of waterstops is an essential characteristic for satisfactory performance. Large joint movements can occur such as the 12- to 14-in. movements experienced in an outlet conduit at West Branch Dam on the Mahoning River in Pennsylvania, This movement resulted in

the rupture of a three-bulb, 9-in.-wide PVC waterstop. As mentioned earlier, the extensibility the waterstop is capable of is temperature dependent and tends to decrease with decreasing temperatures. Full size pieces of waterstop show less ability to elongate than the smaller pieces used for acceptance tests.⁷

の行政が対応になった。現在ではなどのないができた。このではないないないないではないできたができたがないであるとなっていたができた。

Tests of PVC waterstops⁸ having eight different shapes representing waterstops used in concrete-lined canals, indicated that, in general, satisfactory performance, indicated by an absence of leakage, could be obtained for lateral joint movements up to 3/8 in These types of waterstops are usually about 2 in. long, yet they could be extended over an additional 2 in. before rupture.

The ability of the waterstop to deform when differential settlement induces transverse movements between blocks containing the waterstop is also essential for a satisfactory performance. The benefits derived from a central O-bulb in the waterstop for this purpose can be seen in fig. 3a. A shear test was conducted⁹ on a three-bulb, 9-in.-wide, 36-in.long waterstop which spanned the joint between concrete blocks. The sides of the waterstop were completely embedded in concrete. The joint had a 1-in. opening. Differential movements of almost 3 in. with no lateral movements of the blocks did not damage the waterstops. Similar tests of a three-bulb, 9-in. waterstop for only lateral movements indicated that movements of 5 in. could be accommodated.¹

Water retentivity

ere en a mon ABARA A

The ability of waterstops to resist the passage of water has been evaluated^{2,11,12} using the test apparatus shown in fig. 5. The waterstops form a continuous loop and include a splice where the two ends meet. By jacking the top and bottom blocks apart, the waterstop is subjected to elongation. The effectiveness of the waterstop in resisting the flow of water along the joint can then be determined for any desired degree of joint movement.

and a state of the second s

From this test, it was found that both the corrugated or ribbedflange waterstops and dumbbell waterstops were effective in retaining water provided care is exercised in splining and embedding them.^{2,10} The corrugated or ribbed-flange waterstops appeared to be somewhat more effective, however. It was indicated² that when the dumbbell shape was extended the flat web portion of the waterstop was reduced in thickness, leaving only the bulbs at the ends in contact with the concrete. This permitted some seepage. When the corrugated waterstop was extended, the pull was taken by the ribs nearest the center of the waterstop, thus leaving the other ribs and the major part of the waterstop still in contact with the concrete. The rib-flanged waterstops require more care than the dumbbell types during vibration and consolidation of the concrete directly in contact with the waterstop so that the waterstop is not displaced and to ensure that the concrete is worked in between the ribs for maximum surface contact.

Results of a study of labyrinth waterstops^{1]} indicated that they were as effective in retaining water as other shapes tested provided there is little or no joint movement. Labyrinth waterstops will not tolerate a joint movement of 1/4 in. without their water recentivity being seriously reduced. At joint openings of 1/8 in., these waterstops performed satisfactorily when water pressures were less than 100 psi. The failure of the labyrinth water lops to recain water when large joint movements occurred was due, in general, to fracture and failure of the concrete contained between the anchor legs of the labyrinth rather than by a rupture of the waterstop itself. The dotted lines in fig. 6 indicate possible areas of the concrete fracture.

To ensure satisfactory water retentivity, the waterstop must be sound, strong, and homogeneous over its entire length, including all splices of the material. Host manufacturers of waterstops will perform splicing in the production plant or furnish field splicing kits along with recommendations as to how to do it. It has been found that in the case of ribbed designs, the continuity of the ribs must be preserved in the area of the splice or leakage will occur.² Special tools are available for this purpose. Splices are usually fused, vulcanized, or glued. The tensile strength of a fused splice, used commonly in splicing PVC waterstops, is usually less than the strength of the unspliced material. It will, however, average nearer the strength of the unspliced material than will that of a vulcanized splice of either natural or synthetic rubber.¹⁰ Vulcanizel splices are also reduced in

11

WY CAL

strength with respect to the unspliced material. Glued sleave splices are generally stronger than vulcanized splices of the same waterstop. Glued lapped splices are not as strong, however, as the vulcanized splices, but can be made stronger by overlapping a greater length.

12,0247

Alternative and a state of the state of the

からいないとないというのでもいないないないで

and the second statistical statist

WATERSTOP SPECIFICATIONS

Based on the knowledge gained from experience in using waterstops and results of investigations,⁴⁻⁷, ¹⁰⁻¹² the Corps of Engineers has developed specifications for the acceptance of rubber and PVC waterstops.¹³ A summary of the requirements is shown in table 3. The specimens used in the testing of PVC waterstops are obtained by hot-pressing the finished waterstop into a sheet form and then using appropriate cutting dies, with buffing as necessary. This procedure replaces earlier practices of obtaining specimens of sheet material from the manufacturers with a certification that they represented the same material as used in extruding the waterstop. The hot-press can be seen in fig. 7. Rubber waterstop test samples are obtained by alicing and bu³fing from portions of the finished waterstop.

Additional information on waterstop specifications can be obtained from references 14 through 16.

i 2

REFERENCES

 Allen, E. A., and Higginson, E., "Waterstops in Articulated Concrete Construction," <u>Proceedings, ACI Journal</u>, vol 52, pp 83-91, Sep 55.

 Kellam, B., and Loughborough, M. T., "Waterstops for Joints in Concrete," <u>Proceedings, ACI Journal</u>, vol 55, pp 1269-1286, June 1959.
 ACI Committee 504, "Guide to Joint Scalants for Concrete Structures," <u>Proceedings, ACI Journal</u>, vol 67, pp 489-536, July 1970

4. Houston, B. J., <u>Investigation of Nonmetallic Waterstops</u>; <u>Preliminary</u> <u>Laboratory and Field Exposure Tests</u>, Technical Report No. 6-546, Report 1, May 1960, U. S. Army Engineer Waterways Experiment Station, CE, Vicksburg, Miss.

 Houston, B. J., <u>Investigation of Nonmetallic Waterstops; Progress</u> <u>Report of Laboratory and Field Exposure Tests</u>, Technical Amport No. 6-546, Report 3, June 1963. W. S. Army Engineer Waterways Experiment Station, CE, Vicksburg, Miss.

Houston, B. J., <u>Investigation of Nonmetallic Wicerstops</u>; <u>Effect of Exposure</u>, Technical Report No. 6-546, Report 6, January 1968, ¹¹. S. Army Sngineer Waterways Experiment Station, CE, Vicksburg, Miss.

 Houston, B. J., <u>Investigation of Nonmetallic Waterstops: Effect of</u> <u>Sample Size and Low Temperature on Waterstop Test Results</u>, Technica' Report No. 5-545, Report 7, U. S. Army Engineer Waterways Expe. 'ment Station, CE, Vicksburg, Miss. (DRAFT).

8. Johns, H., <u>Extension Tests in PVC Contraction Joint Forming Waterstops</u>, Rep rt No. ChE-103, September 1959, U. S. Bureau of Reclamaticn, Derver, Colo. 9. Fabry, J. W., "Shear Test of 9-in. Type A Rubber Waterstop in a 1-in. Expansion Joint, Dos Amigos (Mile 18) Pumping Plant, San Luis Unit--Central Valley Project. Report C-1197, August 1966, U. S. Bureau of Reclamation, Denver, Colo.

Houston, B. J., <u>Investiggin of Nonmetallic Waterstops; Water</u>
 Retentivity and Tensile Strength of Splices, Technical Report No.
 6-545, Report 4, December 1965, U. S. Army Engineer Waterways Experiment
 Station, CE, Vicksburg, Miss.

Houston, B. J., <u>Investigation of Nonmetallic Waterstops</u>; <u>Water</u>
 <u>Retentivity of Labyrinth-Shaped Waterstops</u>, <u>Technical Report No.</u>
 6-546, Report 5, U. S. Army Engineer Waterways Experiment Station,
 CE, Vicksburg, Miss. (DEAFT).

12. Papper, L., <u>Investigation of Nonmetallic Waterstops; Evaluation</u> of the Effect-of-Alkalies and Accelerated Extraction Tests, Technical Report No. 6-546, Report 2, March 1961, U. S. Army Engineer Waterways Experiment Station, CE, Vicksburg, Miss.

13. U. S. Army Engineer Waterways Experiment Station, CE, <u>Handbook For</u> <u>Concrete and Cement</u>, with quarterly supplements, August 1949, Vicksburg, Miss.

14. Office, Chief of Engineers, DA, <u>Guide Specifications, Civil Works</u> <u>Construction, Standard Guide Specifications for Concrete</u>, CE 1401.01, Washington, D. C.

15. Office, Chief of Engineers, DA, <u>Guide Specifications, Civil Works</u> <u>Construction, Metals, Miscellaneous Materials, and Standard Articles</u>, CE 1402, Washington, D. C.

a a serie vynastanistik fan de meriken i serie om serie i serie fan de serie i serie i serie fan de serie serie a serie vynastanistik fan de serie serie i serie i serie i serie i serie serie i serie serie i serie serie serie • 16. Office, Chief of Engineers, DA, Engineering and Design, Waterstops, IM 1110-2-2102, Washington, D. C. 15

247

an an an a star a star

E. 733(2)

ircle '

an order with the other states and the

Piero and

日本にはたいではいいと

de la

2526

wrary of Vondition of operiments After Rapauret as recerdined is often in the first

							1 - Louise			Con-
Speciaen	Serena				-u1	341		Cold Contemi-	:	Dated
ý	Condition	Trat Islan!	St Augustine	Outdoors	door	Jee	Cold Ne - Hateres	nated Water	Varia Fresh Vater	Later
(JW	Unst ressed	Sound Crashe at 5 vr	Sound at 1 yr then loat Sound at 3 yr then loat	Sound Crather at 1 vr.	Sound	Sound Sound	Sound at 5 yr Sound at 5 yr	Crazing at 4 yr Crazing at 2 yr	Sound at 1 yr then lost Sound at 4 yr then lost	Sound
				cracked at 2 vr						
	into thed	. UT-101	Craine at 1 yr	Sound	:	:	:	:	:	:
1.400	has stressed	t-und	Jound	Soun:	Sound	Sound	Sound at 5 yr	Crazing at 3 yr	Sound	Sound
	Brat Mabe Stri	umun1 	Sound at) yr then lost 'reaing at - yr	Cracked at 1 yr Youni	Sound	Sound 	Sound at 5 yr	Crazing at 3 yr	Sourd	
							•			
CO8-5	Unstressed		Sound Carobad at 1 ve	Sound	Sound	Sound	Sound at 5 yr	Creating at 3 Y	Sound at i yr then lost Sound at h yr then lost	Sound
	141 - 147	ional intervention	resident to be	Crasing after 5 yr	:	:				:
	'nu' ressed	Soun 1	Crasing at 4 yr	Cruzing at 3 yr	Sound	Sound	Crazing at 1 yr	Crazing at 2 yr	Soft at 1 yr, craing	Sound
	****	Fraing at 1 yr	Sound at 3 yr then lost	Crazing at 1 yr,	Sound	p05	Crazing at 1 yr,	Craiing at 2 yr	Soft at 1 yr, craring	Sound
			Creative at 1 vr	cracked at 2 yr Craring at 3 yr	:	:	crecked at 5 yr	:	et 5 yr 	:
	Chitressed Deni	Gound Frailing at 2 yr	Craing a: 4 yr Suuni at 3 yr then loat	Sound Craring at 7 yr	Sound	Sound	Crazing at 1 yr Crazing at 1 yr, crichad at 5 yr	Crating at 4 yr Crating at 2 yr	Sound at 1 yr tien lost Sound at 4 yr then lost	Sound
	habedded	Craeing at 4 yr	Creating at 3 yr	Cruting at 3 yr	:	:		:	:	:
4					Pares 2	County	er (te suiter)	Crastine at 3 vr	Sound	Sound
	bent	urack, 1 mt 2 yr. Urack, 1 mt 2 yr. Badly crackel at 5 yr	Jourd at 3 yr then lost	badly cracked at 2 yr	Sound	Sound	Crating at 1 yr. Cracked after 4 yr	Crazing at 2 yr	Sound	Sourt
	Babedded	Cratine at 3 yr	Crazing at 4 yr	Madly cracked at 2 yr, torn at 8 yr	:	:	# *	:	:	:
C- 45	Contrensed	Soun *	Crackel at 4 yr	Sound	Sound	Sound	Crazing at 1 yr	Crazing at 3 yr	Sound at 7 yr then lost	(unr)
	bent	reacted at 1 yr. baily created at 5 yr	Cranked at 3 yr	Cracked at 2 yr	Sound	Sourse	Crasing at 1 yr, cracked at 4 yr	Crazing at 3 yr, cracked at 4 yr	Sound at 6 yr then lost	Series
	Pabe Med	Crac ne at 3 yr	Crating at 3 yr	Completely torn at 1 yr	:	:	:	:	:	:
sh- }	lhatressed Bent	Sourt Gracked at 2 yr. Maily created at 6 yr	Crecked at 4 yr Creckel a: 3 yr	Crazing at 3 yr Hadly cracked at 2 yr	Sound	Sound	Crazing at 1 yr Crazing at 1 yr, cracind at 4 yr,	Crezing at 3 yr Crazing at 2 yr, creched at 5 yr	Sound at 1 yr then lost	Sound
	Pathedad	Crating at 1 yr	Sound	Daily cracked at 2 yr	:	:	:	:	ł	:
1.00-2	l'his tressed	Sound	Sound at 6 yr then lost	Crazing at 3 yr	Sound	:	:	:	:	:
	ðent Iske låe 1	50-12-1 50-12-1	Sound at ? yr then lost Creiing at 3 yr	Crazing at 2 yr Crazing at 6 yr	sound	::	::	::	::	::
PVC-2(2)	Unstrased		:	:	:	Sound	Broken when bent at	Sound	Sound at 4 yr then lost	Sound
							low temperature for inspection at 3 yr			
	Pert.			:	:	Sound	Sourd	Sound	Sound at 4 yr then losi	South
	Deliberty.	:	•	:	:	:	:	:	:	:

-

16

(Continued)

Special condition given without time limit are conditions after full axosure time.
 All ape imput jost after here resoure at a mouth of unlike the.

いたちちょうちます

(呼んるま))

ş

ţ

.

Saraha San San Barran Sarah

			Table 1 (Co	nc luded)			New Orleans Distric	
			Jacks	8	а. З	louis Distri t		Con-
Conditio	n. Treat laland	St. Augustine	Outdoora	100re fui	Cold Fresh 1	G: 1 Contami - Ister anted Mater	Varm Presh Water	nated Water
Chatress Sent	ed Sound Sound	: :	Bound	2	:	:		:
Paberbled	Tom at 2 yr	: :	Sound			::	::	::
c) Unitrees	7	:	:	:	und Broken when be low temperat for Inspecti 3 yr	nt at Broken when bent ure at low tempera. on at ture for in- spection at 2	Srund at 4 yr then lost	Sound
Bent	:	:	:	ଟ୍ର :	ad Sound	yr Bound	Sound at 4 yr then	Sound
Bees led	:	:	:	:	:	:	lost	;
Underess	ed Sound Sound	Bound at 2 yr then lost Sound at 2 yr them lost	Crasing at 5 yr Crasing at 5 yr	Sound	::	::	::	: :
7-79-444	Concrete broken at	: 2 yr Crating at 5 yr	Sound	:	:	:	: :	::
) Unatress	:	:	:	1	nd Sound	Bound	Sound at 4 yr then	Bound
P	:	:	:	1	nd Sound	Bound	Sound at 4 yr then	Sound
Mebedan.	:	:	:	:	:	;	1001	;
Unatress Bent Babested	rd Sound Sound Sound	:::	Sound Sound Sound	Sound	:::	:::	:::	:::
2) Unitress	:	:	;	:	nd Sound	Sound, one cracked when bent at low	Sound at 4 yr then lost	Sound
Bent	:	:	:	304	nd Sound	bound Bound	Sound at 4 yr then	Sound
Medded	:	;	:	;	1	:	loet	:
Uhatress Nent Pabedded	rd Sourd Sourd Sourd	Sound at 2 yr then logt Crazing at 5 yr	Crazing at 3 yr Crazing at 8 yr Sound	nos punos nos punos	nd Sound Sound n ^d Sound Sound	Sound Sound **	Sound Bound 	Sound Sound
Unitresse	d Journel	Sound	Crasing at 3 yr	Sound Sou	ad Sound	Sound	Sound at 1 yr then	Sound
Ment.	Sound	Sound at 2 yr then lost	Crazing at 8 yr	Sound Sou	nd Sound	Sound	lost Sound at 4 yr then Sont	Sound
Peroval.	Sound	Crazing at 5 yr	Sound	:	:	:		:
	;;	::	::	нов 1 : :	ad Sound xi Sound	Cracked at 5 yr Crasing at 4 yr	Sound at à yr then	Sound
Medded	:	:	:	:	:	:	loet	:
) Unstress	2 Sound Bound	Sound at 2 yr then lost Sound at 2 yr them lost	:	то <u>с</u> 	A Sound	Sound	Sound	Sound
							dame at h u. then	

ì

Tat	le	2
-----	----	---

Contraction of the

政治が出た言葉を見ませるよう

Summary of Tests Normally Performed on Waterstops

				Ty	pe of
	Test Mer	chod Desi	gnation	Watersi	op Tested
Physical Property Evaluated	CRD-C ^a	FTMS ^b 601	ASTMC	Rubber	Other Plastic
Tensile strength	568	4111		x	x
Hardness	569	3021		x	
Low-temperature brittleness	570	5311.1			x
Stiffness	571		D747		x
Accelerated extraction	572				x
Elongation	573	4121		x	x
300 percent modulus	574	4131		x	
Water absorption	575	6631		x	
Compressive se.	576	3311		x	
Oxygen aging	577	7111		x	
Effect of alkalies	572			x	

a See reference 13.

And State of States

AN CENTO

b Federal Test Method Standard 601.

C American Society for Testing and Materials Standard Method of Test.

Compression set

3311

i

576

Blongation, ultimate	Tensile stress	Change in weight, water immersion
4121	1814	6631
1	:	i
573	574) ⁽)

ultimate
Blongation,
4121
ł
:73

Hardness, durometer

3021

ł

569

Tensile strength

4111

1

568

Specifications for Rubber Waterstops (CRD-C 513¹³) Tested

Title

FTMS 601

CRD-C¹³

Method of Test Designation NEW ST

Requirement

Specimens

No. of

Tensile strength, using Die III, not less than...2000 pef At least 5

Hardness, Shore durometer, type A, between 60 and 70

Ultimate elongation using Die III, not less than...350% 300% modulus, not less than ... 900 pat

immersion at 73.4 + 2 F calculated as percent by weight, Water absorption after 7 days not more than. .5

Compression set, not more than...30% Tensile strength after aging. oxygen bomb method, not less than...80%

expressed as a percentage of the Tensile strength, using Die III, strength of the unspliced material...not less than 50

And the second second

(Continued)

Tensile strength as directed

1115

ł

568

Job-made and factory-made splices

Oxygen pressure test

7111

ł

577

Nonmetailic Waterstop Specifications

Table 3

1 Carlo

Sizaran Sanakan Serah Banah Banahati Serahati Sanakan Serah

CALUED IN A CARACTER OF A CALE OF A CALE

۵۰ میلانانیمیزیوناند و میرونورد.

Now Write to sta

tione ar Joan

たいたいでは、日本であたいとないとないと

ŝ

CORANGE TANKS TO A TRANSPORT

. .

A BRANCH STUDIA

Q72

		Requirement	<u>; 572¹³)</u>	Censile strength, using Die III, 10t less than1400 psi	Jltimate elongation, using Die III, not less than280%	Jow-temperature brittleness, no Sign of failure such as cracking Dr chipping at35 F	Stiffness in flexure, 1/2-in. Pan, not less than400 psi	<pre>Jltimate elongation, using Die II, not less than300% ensile strength using Die III, tot less thanl500 psi</pre>	Change in weight after 7 days, between0.10 and +0.25%	Change in Shore durometer read- ing after 7 days, not more than 5	Censile strength, using Die III, 10t less than 1120 psi
	No. of Snecimena	Tested	erstops (CRD-(N L H	S N	en en	۲۰ ۲۰	ν Γ - Fr	e E	0 4 1	As directed 1
Table 3 (Concluded)		Title	ications for Polyvinyl Chloride Wat	Tensile strength	Ultimate elongation	Method of test for brittleness tempers.ure of plastics and elastomers by impact	Methoć of test for stiffness in flexure of plastics	CE specifications for polyvinyl chloride waterstops - acceler- ated extraction	CE specifications for polyvinyl chloride waterstops - effect of alkalies		Tensile strength
	rest on	FTMS 601	Specif	1114	4121	1	;	ł	;	cory-made s	4111
	thod of ' esignati	WLSV		1	1	D746	D747	1	t I	and fact	l
	Me	CRD-C ¹³		568	573	570	571	572	572	Jор-шаde	568
								20	$\mathbf{\mathcal{D}}$		

į ŝ

* * * * *

1

1 1

ł

ł i i

•









i yaw





Contraction of the second second

Æ

Star . Cart Barry

Сv,