

AD-A034 801


OGDEN AIR LOGISTICS CENTER HILL AFB UTAH PROPELLANT L--ETC F/G 21/8.2
PROPELLANT SURVEILLANCE REPORT LGM-30 F AND G STAGE 1, PHASE E,--ETC(U)
OCT 76 J A THOMPSON
MANCP-360(76)

UNCLASSIFIED

NL

1 of 2
AD
A034801





MICROCOPY RESOLUTION TEST CHART
 NATIONAL BUREAU OF STANDARDS-1963-A

ADA034801

HEADQUARTERS
OGDEN AIR LOGISTICS CENTER
UNITED STATES AIR FORCE
HILL AIR FORCE BASE, UTAH 84406

2

FG

PROPELLANT
SURVEILLANCE REPORT
LGM-30 F&G STAGE 1
PHASE E, SERIES II
TP-H1011

PROPELLANT LABORATORY SECTION

MANCP REPORT

360 (76)

NOVEMBER 1976

DDC
RECEIVED
JAN 25 1977
RECEIVED

A

APPROVED FOR PUBLIC RELEASE, DISTRIBUTION UNLIMITED

PROPELLANT SURVEILLANCE REPORT
LGM-30 F & G STAGE I (TP-H1011)

Author

John A. Thompson
JOHN A. THOMPSON, Chemist
Component & Combustion Test Unit

Engineering & Statistical Review By

John K. Scambia
JOHN K. SCAMBIA, Project Engineer
Service Engineering

Edward J. Erickson
EDWARD J. ERICKSON, Statistician
Data Analysis Unit

Recommended Approval By

Leonidas A. Brown
LEONIDAS A. BROWN, Chief
Component & Combustion Test Unit

Approved By

Don F. Woods
DON F. WOODS, Chief
Propellant Laboratory Section

NOV 1976

Industrial Products & Ldg Gear Division
Directorate of Maintenance
Ogden Air Logistics Center
United States Air Force
Hill Air Force Base, Utah 84406

ASSESSMENT For	
NTIS	White Section <input checked="" type="checkbox"/>
DDC	Blue Section <input type="checkbox"/>
UNANNOUNCED JUSTIFICATION	
BY DISTRIBUTION / MANAGEMENT COPIES	
Dist.	APPROVAL / DATE
A	

See 1473

ABSTRACT

This report contains propellant test results from cartons of TP-H1011 bulk propellant representing LGM-30 F and G First Stage Minuteman Motors. This report uses a statistical approach to analyze the bulk carton propellant data. Testing was accomplished in accordance with MMEMP Project M72632-5MP116P.

The data from this test period are combined with data from previous testing and entered into the G085 computer for storage, analysis and regression analysis. From the statistical analysis of all data tested to date (11 and one half years for F and G), significant degradation of the propellant does not appear likely for at least two years past the oldest data point.

Each point on the regression plot represents the mean of all samples at that particular age. The number of samples at each point is indicated on the sample size summary sheet on the page accompanying each regression plot or group of regression plots. The data range at any age can be found by suitable inquiry of the G085 system.

TABLE OF CONTENTS

	<u>Page</u>
Abstract	ii
List of Figures	iv
List of References	ix
Glossary of Terms and Abbreviations	xiii
Introduction	1
Table 1 - Test Program	3
Statistical Approach	4
Test Results	7
Conclusions	11
Distribution List	122
DD 1473	123

LIST OF FIGURES

<u>Figure Nr</u>		<u>Page</u>
	Regression Plot, Very Low Rate Tensile	
1	Strain at Maximum Stress	13
2	Maximum Stress	14
3	Strain at Rupture	15
4	Stress at Rupture	16
5	Modulus	17
	Regression Plot, Low Rate Biaxial Tensile	
6	Strain at Maximum Stress	19
7	Maximum Stress	20
8	Strain at Rupture	21
9	Stress at Rupture	22
10	Modulus	23
	Regression Plot, Low Rate Tensile	
11	Strain at Maximum Stress	25
12	Maximum Stress	26
13	Strain at Rupture	27
14	Stress at Rupture	28
15	Modulus	29
	Regression Plot, High Rate Triaxial Tensile	
16	Strain at Maximum Stress	31
17	Maximum Stress	32
18	Strain at Rupture	33

LIST OF FIGURES (cont)

<u>Figure Nr</u>		<u>Page</u>
19	Stress at Rupture	34
20	Modulus	35
	Regression Plot, High Rate Hydrostatic Tensile	
21	Strain at Maximum Stress	37
22	Maximum Stress	38
23	Strain at Rupture	39
24	Stress at Rupture	40
25	Modulus	41
	Regression Plot, Stress Relaxation .5% Strain, -65°F	
26	Modulus at 10 sec	43
27	Modulus at 50 sec	44
28	Modulus at 100 sec	45
29	Modulus at 1000 sec	46
	Regression Plot, Stress Relaxation .5% strain, -40°F	
30	Modulus at 10 sec	48
31	Modulus at 50 sec	49
32	Modulus at 100 sec	50
33	Modulus at 1000 sec	51
	Regression Plot, Stress Relaxation 3% Strain, 20°F	
34	Moduls at 10 sec	53
35	Modulus at 50 sec	54

LIST OF FIGURES (cont)

<u>Figure Nr</u>		<u>Page</u>
36	Modulus at 100 sec	55
37	Modulus at 1000 sec	56
	Regression Plot, Stress Relaxation 3% Strain, 77°F	
38	Modulus at 10 sec	58
39	Modulus at 50 sec	59
40	Modulus at 100 sec	60
41	Modulus at 1000 sec	61
	Regression Plot, Stress Relaxation 3% strain, 100°F	
42	Modulus at 10 sec	63
43	Modulus at 50 sec	64
44	Modulus at 100 sec	65
45	Modulus at 1000 sec	66
	Regression Plot, Stress Relaxation 3% Strain, 140°F	
46	Modulus at 10 sec	68
47	Modulus at 50 sec	69
48	Modulus at 100 sec	70
49	Modulus at 1000 sec	71
	Regression Plot, Stress Relaxation 3% Strain, 180°F	
50	Modulus at 10 sec	73
51	Modulus at 50 sec	74
52	Modulus at 100 sec	75
53	Modulus at 1000 sec	76

LIST OF FIGURES (cont)

<u>Figure Nr</u>		<u>Page</u>
54	Regression Plot, Constant Strain	78
	Regression Plot, Dynamic Response, 70 gm	
55	Loss Tangent, 200 Hz	80
56	Storage Shear Modulus, 200 Hz	81
57	Loss Tangent, 400 Hz	82
58	Storage Shear Modulus, 400 Hz	83
59	Regression Plot, Hardness	85
60	Regression Plot, Burning Rate	87
	Regression Plot, Pressure Time	
61	Maximum Pressure	89
62	Time to Maximum Pressure	90
63	Regression Plot, Ignitability	92
	Regression Plot, TCLE	
64	Thermal Coefficient of Linear Expansion Below tg	94
65	Thermal Coefficient of Linear Expansion Above tg	95
	Regression Plot, Sol Gel	
66	Gel Swell Ratio	97
67	Crosslink Density	98
68	Percent Extractables	99
69	Density	100
	Regression Plot, TGA, 9°C rise/min	

LIST OF FIGURES (cont)

<u>Figure Nr</u>		<u>Page</u>
70	Ignition Temperature	102
71	Percent Weight Loss at Ignition	104
72	Percent Weight Loss at 250°C Hold	106
	Regression Plot, DTA, 12°C rise/min	
73	Endotherm	108
74	Exotherm 1	110
75	Exotherm 2	112
76	Exotherm 3	114
77	Ignition Temperature	116
78	Regression Plot, Tear Energy	117
	Regression Plot, DSC	
79	Endotherm Peak Temperature	119
80	Exotherm Peak Temperature	120

LIST OF REFERENCES

<u>Report Nr</u>	<u>Title</u>	<u>Report Date</u>
	LGM-30 First Stage, wing I Test Reports	
29A	Test Report (Missile in silo)	13 Jan 64
29B	Zero Time Test Results	29 Jan 64
29C	Zero Time Test Results (Supplement 1)	30 Mar 64
29D	Zero Time Test Results (Aft Closure)	9 Jun 64
29E	Zero Time (Aft Closure Supplement 1)	24 Jun 64
29F	ATP Phase I Test Results	30 Mar 65
29G	ATP Phase I Test Results	19 Aug 65
29H	ATP Phase I Test Results	10 Sep 65
32A	Zero Time, wings II-V Test Results	17 Mar 65
32B	Zero Time, wings II-V Test Results (Aft Closure)	18 Mar 65
32C	ATP Phase I, wings II-V Test Results	3 Nov 65
49	ATP Phase I, wings II-V (First Group)	18 Mar 66
53	ATP Phase I, wings II-V (Second Group)	22 Apr 66
55	ATP Phase I, wings II-V (Third Group)	29 Apr 66
58	ATP Phase I, wings II-V (Fourth Group)	6 May 66
61	ATP Phase I, wings II-V (Fifth Group)	10 Jun 66
66	ATP Phase I, wings II-V (Sixth Group)	22 Jul 66
76	ATP Phase II, Wing I Test Results	24 Jan 67
78	Zero Time, wing VI Test Results	3 Feb 67
104	ATP Phase I, wing VI (First Group)	12 Oct 67
118	ATP Phase II, wings II-V (First Group)	5 Mar 68

LIST OF REFERENCES (CONT)

<u>Report Nr</u>	<u>Title</u>	<u>Report Date</u>
126	ATP Phase II, Wings II-V (Second Group)	11 Apr 68
130	ATP Phase II, Wings II-V (Third Group)	3 May 68
162	ATP Phase I, wing VI (Second Group)	30 Sep 69
176	ATP Phase II, wing VI (First Group)	15 Apr 70
181	ATP Phase III, wing I	7 May 70
185	ATP Phase I, wing VI (Third Group)	22 Jun 70
195	ATP Phase III, wings II-V (Retest)	29 Oct 70
223	Surveillance Report LGM-30 Stage I (TP-H1011)	Sep 71
239	Surveillance Report LGM-30 Stage I (TP-H1011 and TP-H1043)	Apr 72
258	Surveillance Report LGM-30 A & B Stage I (TP-H1011)	Nov 72
268	Surveillance Report LGM-30 A & B Stage I (TP-H1011)	May 73
271	Surveillance Report LGM-30 F & G Stage I Phase A Series II, (TP-H1011)	Jul 73
277	Surveillance Report LGM-30 F & G Stage I Phase A Series III, (TP-H1011)	Oct 73
280	Surveillance Report LGM-30 A & B Stage I (TP-H1011)	Nov 73
288	Propellant Surveillance Report LGM-30 A & B, Stage I, TP-H1043	Mar 74
290	Propellant Surveillance Report LGM-30 F & G, Stage I, Phase B, Series I TP-H1011	Mar 74
300	Minuteman Stage I Motor Reliability Improvement Program Surveillance	May 74

LIST OF REFERENCES (CONT)

<u>Report Nr</u>	<u>Title</u>	<u>Report Date</u>
302	Propellant Surveillance Report LGM-30 A & B Stage 1, TP-H1011	Nov 74
313	Stage 1 Propellant Surveillance Report, Propellant Containing Glacial Acrylic Acid	Oct 74
315	Propellant Surveillance Report LGM-30 F & G Stage 1, TP-H1011	Jan 75
316	Propellant Surveillance Report LGM-30 A & B Stage 1, TP-H1011	Feb 75
319	Propellant Surveillance Report LGM-30 Dissected Motors, Phase VI, TP-H1011	Apr 75
321	Propellant Surveillance Report LGM-30 F & G Stage 1, Phase B, Series II, TP-H1011	Apr 75
325	Propellant Surveillance Report LGM-30 A & B Stage 1, TP-H1011	Jun 75
328	Propellant Surveillance Report LGM-30 A & B Stage 1, TP-H1011	Sep 75
330	Propellant Surveillance Report LGM-30 F & G Stage 1, TP-H1011	Oct 75
335	Stage 1 Motor Reliability Improvement Program	Dec 75
337	Propellant Surveillance Report LGM-30 A & B, Stage 1, TP-H1043	Feb 76
339	Stage 1, New MAPO & ERL-510 Qualification	Mar 76
341	Propellant Surveillance Report LGM-30 Dissected Motors, Phase VII, TP-H1011	Mar 76

LIST OF REFERENCES (CONT)

<u>Report Nr</u>	<u>Title</u>	<u>Report Date</u>
343	Propellant Surveillance Report LGM-30 A & B, Stage 1, TP-H1011	Jun 76
345	Propellant Surveillance Report LGM-30 F & G, Stage 1 Phase B, Series III, TP-H1011	Jun 76
350	Qualification of a New MAPO Source and ERL-510 Curing Agent for Minuteman, Stage 1, UF-2121 Liner	Sep 76
351	Propellant Surveillance Report LGM-30 A & B, Stage 1, TP-H1011	Sep 76
354	Minuteman Stage 1 Motor Reliability Improvement Program Surveillance	Sep 76

GLOSSARY OF TERMS AND ABBREVIATIONS

Aging Trend	A change in properties or performance resulting from aging of material or component
CSA	Cross Sectional Area
DB	Dogbone
Degradation	Gradual deterioration of properties or performance
E	Modulus (psi), defined as stress divided by strain along the initial linear portion of the curve.
EB	End Bonded
EGL	Effective Gage Length
em	Strain at maximum stress
er	Strain at rupture
"F" ratio	The ratio of the variance accounted for by the regression function to the random unexplained variance. The regression function having the most significant "F" ratio is used for plotting data. The ratio is also used in detecting significant changes in random variation between succeeding time points
JANNAF	Joint Army, Navy, NASA, Air Force Committee
MANCP	Propellant Lab Section at Ogden Air Logistics Center
Ogden ALC	Ogden Air Logistics Center, Air Force Logistics Command
r or R	The Correlation Coefficient is a measure of the degree of closeness of the linear relationship between two variables
Regression Equation	The general form of the regression equation is $Y = a + bx$
Regression Line	Line representing mean test values with respect to time
S_b	Standard error of estimate of the regression coefficient

GLOSSARY OF TERMS AND ABBREVIATIONS (cont)

S_e or $S_{Y.X}$	Standard deviation of the data about the regression line
S_m	Maximum Stress
S_r	Stress at rupture
Standard Deviation (S_y)	Square root of variance
Strain Rate	Crosshead speed divided by the EGL
"t" test	A statistical test used to detect significant differences between a measured parameter and an expected value of the parameter (determines if regression slope differs from zero at the 95% confidence level)
Variance	The sum of squares of deviations of the test results from the mean of the series after division by one less than the total number of test results
3 Sigma Band	The area between the upper and lower 3 sigma limit. It can be expected that 99.73% of the inventory represented by the test samples would fall within this range assuming that the population is normally distributed.
90-90 Band	It can be stated with 90% confidence that 90% of the inventory represented by the test samples would fall within this range assuming that the population is normally distributed

INTRODUCTION

A. PURPOSE:

Laboratory testing has been performed for eleven and one-half years on First Stage LGM-30 F and G Minuteman Motor propellant blocks to evaluate the effects of aging on TP-H1011 propellant. This report contains those tests conducted on propellant as instructed in MMEMP Test Directive GTD-1C, Amendment 2, LGM-30 First Stage Operational Propellant Laboratory Testing.

Statistical analysis of the data from tests performed will provide early warning if serious degradation trends develop. Annual evaluation of the propellant provides data for input into engineering reliability analysis for service life predictions.

B. BACKGROUND:

LGM-30 F and G testing was started in 1966 with phase testing at 24 month intervals (Report Numbers 78 - zero time; 104, 162, 185-Phase I, 176, 239, 257-Phase I, 271-Phase III). Report Number 257 was the first time that LGM-30 F and G data were statistically analyzed separately from LGM-30A and B data. The present report is a continuation of testing and statistical analysis.

Zero time testing for LGM-30A, B, F and G was started as soon as possible after receipt of the propellant by MANCP. Data from these tests were used to establish a base line for each test parameter.

The LGM-30F and G propellant test matrix (Table 1) is used to determine the number of specimens to be taken from each propellant loaf and the specific test or tests to which these specimens are to be subjected. Very low rate and low rate tensile specimens are taken on all LGM-30F and G blocks. Specimens for other physical and combustion tests are taken from every third (LGM-30F and G) block.

TABLE 1

SAMPLE PLAN

The Procedure for determining tests to be performed on propellant batch samples of LGM-30 F & G First Stage Motors are as follows:

1. Divide the USAF motor serial numbers into three groups by dividing the last three digits of each serial number by three to determine the remainder integer, e.g., 154 ÷ 3 = 51 with a remainder integer of 1.
2. Use the remainder integer to enter the following matrix to determine the group of tests to be performed on the forward, middle, and aft batch samples associated with a particular motor serial number.

TP-H1011 PROPELLANT BATCH SAMPLE	GROUP MATRIX		
	GROUP I	GROUP II	GROUP III
Forward	1	2	0
Middle	0	1	2
Aft	2	0	1

Each group will receive the following tests:

	TEST MATRIX		
	GROUP I	GROUP II	GROUP III
High Rate Triaxial	Dynamic Response	High Rate Hydrostatic	
Creep	Stress Relaxation	Sol Gel	
Biaxial Low Rate	Burning Rate	DSC	
TCLC	Heat of Explosion	TGA	
Hardness	Pressure Time	DTA	
Ignitability		Impact	

NOTE: Low Rate and Very Low Rate Tensile tests are performed on all blocks.

STATISTICAL APPROACH

In order to determine aging trends for shelf/service life predictions, as directed by Service Engineering, First Stage LGM-30 F and G Minuteman Motor propellant blocks have been under-going testing since 1966, statistically analyzed and reported on a regular test cycle by this laboratory.

The primary reason for performing statistical analysis on test data is for the detection of propellant changes due to aging that would affect motor reliability. The method of analysis called regression was used to examine data and to draw meaningful conclusions about dependency relationships that may exist i.e., relationship between age versus test results.

In selecting the best fit model for the regression equation, six models were fitted to the data (see regression models at the end of this statistical approach). The linear model $Y = a + bX$ was found to be the best fit model for the regressions in this report 93% of the time. By using the best fit model, the regression line becomes a more accurate predictor of future trends. The model used is shown in the regression equation at the top of every regression plot and those which are not linear will also be listed and discussed in the test results section.

Individual data points from different time periods were used to establish a least squares trend line for the data. The variance about the regression line, obtained using individual values of the dependent variable, was used to compute a tolerance interval such that at the 90% confidence level 90% of the sample distribution falls within this interval. This tolerance interval was extrapolated to a maximum of 24 months into the future from age of the oldest motor tested. The 't' values and the

significance of this statistic, which are reported for each regression model, give an indication of the "statistical significance" of the slope of the trend line as compared to a line of zero slope. Data were plotted by computer. The 'y' axis is computed so that the values at one inch intervals are peculiar to the data spread of the parameter tested. Plotted data points represent means at the particular ages at which testing occurred. The number of specimens at each age point is indicated on the sample size summary sheet accompanying the regression plot. Variance at each test age can be determined by consulting the G085 data storage system.

A comparison of the slopes of the regression trend lines and their Y - axis intercepts found in the regression equation was performed. Of the tests common to this test period and the last test performed (MANCP Report Nr 345 (76)), the following observations were made: There has been an average increase of 21% in the number of total samples tested. 54.29% of the aging trend lines have become flatter or closer to a line of zero slope which indicates less change due to age, 34.28% of the aging trend lines show more change although the changes are gradual and no operational problems are expected at this time; and 11.43% of the aging trend lines show no change from the last test period.

As the number of samples tested and age of samples is increased, the over all aging trend is becoming closer to a line of zero slope showing less effect due to aging.

A post cure effect (propellant stabilizing after the first year or two) has been observed on some of the early test data (Stress Relaxation at -65°F, -40°F, and 20°F; DTA Exotherm 1, Exotherm 2; and Dynamic Response)

which tended to bias and skew the projected trend lines. To overcome this factor, two methods of analysis were performed: First, where possible, non-linear models were used that would best fit the total data (DTA Exotherm 1 and Exotherm 2 data; Dynamic Response data); second, where non-linear models did not fit the data, this early data was eliminated (Stress Relaxation at -60°F, -40°F, and 20°F data). By compensating for this post cure biasing a more accurate aging trend line for service life prediction is provided.

REGRESSION MODELS

Reciprocal of X	$Y = a + b (1/X)$
Natural log of X	$Y = a + b (\text{LN } X)$
LOG to the base 10 of X	$Y = a + b (\text{LOG } X)$
Square Root of X	$Y = a + b \sqrt[2]{X}$
Cube Root of X	$Y = a + b \sqrt[3]{X}$
Linear equation	$Y = a + bX$

TEST RESULTS

VERY LOW RATE TENSILE (0.002 in/in/min):

The very low rate tensile data shows a statistically significant decrease for strains and an increase for stresses and modulus. The trends are gradual for the respective curves and no problems are indicated for at least two years after the last test date (Figures 1 thru 5).

LOW RATE BIAXIAL TENSILE:

A statistically significant gradual decrease is shown for strains and a statistically significant gradual increase for stresses and modulus (Figures 6 thru 10).

LOW RATE TENSILE:

Low rate tensile data shows a statistically significant gradual decrease for strains and a gradual increase for stresses and modulus (Figures 11 thru 15).

HIGH RATE TRIAXIAL:

The strains show a statistically significant decrease, the stresses a statistically significant increase and modulus shows no change (Figures 16 thru 20). All changes are gradual and no problems are indicated.

HIGH RATE HYDROSTATIC:

The strains show a statistically significant gradual decrease with the stresses and modulus showing a statistically significant gradual increase (Figures 21 thru 25).

TENSILE SUMMARY:

The test data shows that the strain is gradually decreasing and the stress is gradually increasing for Wing Six propellant. Therefore, based on the analyses of data from the tensile test parameters, it does not appear that meaningful degradation is occurring at this time and no operational problems are expected for at least two years beyond the last data point.

STRESS RELAXATION MODULUS:

For the 0.5% strains at -65°F , a statistically significant gradual increase is shown (Figures 26 thru 29). There is a statistically significant gradual decrease (for the 0.5% strain at -40°F), except for the 10 second regression which shows no trend (Figures 30 thru 33).

The 3% strain at 20°F , 77°F , 100°F , 140°F and 180°F shows either a statistically significant gradual increase or no change (Figures 34 thru 53). An exception is shown at 20°F , 10 seconds which shows a statistically significant gradual decrease (Figure 34).

CONSTANT STRAIN:

A statistically significant gradual decrease is shown. This correlates well with the tensile testing and stress relaxation modulus which indicates that the propellant polymer continues to cross link. It should be noted that the constant strain starts at 10% strain and is increased at 5% increments. As seen by the regression, a large proportion of the specimens broke at the 25% strain level. This breaking at the 25% level is particularly apparent from about 7 years to the latest data points (Figure 54).

DYNAMIC RESPONSE:

The storage shear modulus at 200 and 400 Hz shows a statistically significant increase (Figures 55 thru 58). The best statistical models found are reciprocal of X for storage shear and the natural log of X for loss tangent. The changes are gradual and no operational problems are indicated.

HARDNESS:

Shore A ten second hardness data shows a statistically significant gradual increase (Figure 59). The hardness, stress relaxation, constant strain and dynamic response all correlate well with the tensile testing. As in the tensile testing, the statistically significant changes shown by the above tests are gradual and no operational problems are expected for at least two years beyond the last test data date.

BURNING RATE:

The burning rate shows a statistically significant gradual decrease (Figure 60).

PRESSURE TIME:

Maximum pressure shows no change from a zero slope while time to maximum pressure shows a statistically significant gradual decrease (Figures 61 and 62).

IGNITABILITY:

Ignitability shows no significant change (Figure 63).

TCLE:

The thermal coefficient of linear expansion for both below and above T_g (glass point) show a statistically significant gradual increase (Figures 64 and 65).

SOL GEL:

The gel swell ratio and percent extractables show no significant changes, cross link density and density show a statistically significant gradual increase (Figures 66 thru 69).

TGA:

The ignition temperature and percent weight loss at ignition show a statistically significant gradual increase. The percent weight loss at 250°C hold is not changing significantly at this time (Figures 70 thru 72).

DTA:

The endotherm does not show a significant change. The first and second exotherm show a statistically significant gradual decrease and their fit model is LOC to the base 10 of X. The third exotherm and the ignition temperature show a statistically significant gradual increase (Figures 73 thru 77).

TEAR ENERGY:

No significant change is shown in the regression (Figure 78).

DSC:

A statistically significant decrease is shown for the endotherm, first exotherm peak, and second exotherm peak (Figures 79 thru 81). The changes are gradual and no operational problems are expected in the propellant.

CONCLUSIONS

Eleven and one-half years of aging at ambient temperature (77°F) has not greatly changed the properties of the propellant. Some test parameters indicate slight aging trends, but nothing that would adversely affect the operational characteristics of the rocket motor propellant.

From the statistical analysis it does not appear that significant propellant degradation is occurring. Based on the eleven and one-half years of accumulated data, there is no reason to suspect that properties will show much change for at least two years past the last data point. Therefore, propellant reliability should not change appreciably over that time period. Since failure limits are not available for the parameters tested, this statement is based on the fact that the slope of the regression curves where statistically significant are, with few exceptions, relatively flat or close to a line of zero slope and have not changed appreciably from the last test period.

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
2.0	1	33.0	122	58.0	253	83.0	42	109.0	96
9.0	10	34.0	136	59.0	299	84.0	26	110.0	42
10.0	5	35.0	89	60.0	403	85.0	30	111.0	21
11.0	15	36.0	195	61.0	245	86.0	61	112.0	100
12.0	15	37.0	126	62.0	300	87.0	104	113.0	223
13.0	30	38.0	108	63.0	232	88.0	120	114.0	70
14.0	10	39.0	93	64.0	115	89.0	130	115.0	62
15.0	32	40.0	110	65.0	87	90.0	114	116.0	171
16.0	25	41.0	141	66.0	61	91.0	62	117.0	82
17.0	55	42.0	117	67.0	23	92.0	49	118.0	65
18.0	25	43.0	142	68.0	96	93.0	78	119.0	121
19.0	37	44.0	100	69.0	165	94.0	51	120.0	24
20.0	18	45.0	135	70.0	203	95.0	55	123.0	39
21.0	50	46.0	116	71.0	114	96.0	77	124.0	27
22.0	12	47.0	148	72.0	92	97.0	48	125.0	66
23.0	46	48.0	138	73.0	62	98.0	21	126.0	44
24.0	49	49.0	151	74.0	125	99.0	36	127.0	92
25.0	36	50.0	126	75.0	138	100.0	16	128.0	51
26.0	47	51.0	316	76.0	105	101.0	60	129.0	24
27.0	44	52.0	296	77.0	130	102.0	12	130.0	28
28.0	51	53.0	256	78.0	27	103.0	37	131.0	15
29.0	37	54.0	226	79.0	71	104.0	45	132.0	3
30.0	61	55.0	387	80.0	50	106.0	5	139.0	3
31.0	76	56.0	382	81.0	78	107.0	10		
32.0	129	57.0	303	82.0	57	108.0	63		


WING 6.V.L.R.TENSILE,

.CHS=C.002 IN/MIN TP-H1011

This sample size summary is applicable for figures 1 thru 5.

$Y = ((+2.0645570E-01) + (-2.6414852E-05) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 11697
 STORAGE CONDITIONS = AMB TEMP/RH
 TEST CONDITIONS = AMB TEMP/RH


F = +2.5592086E+01
 R = -4.6724108E-02
 t = +5.0588621E+00
 N = 11699



WING 6.V.L.R. TENSILE, STRAIN AT MAX STRESS, CHS=0.002 IN/MIN TP-H1011

Figure 1

$Y = ((+7.6921551E+01) + (+5.1428570E-02) * X)$
 F = +5.1196798E+02 SIGNIFICANCE OF F = SIGNIFICANT $\sigma = +6.8497906E+00$
 R = +2.0465385E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_e = +2.2742485E-03$
 t = +2.2619433E+01 SIGNIFICANCE OF t = SIGNIFICANT $S_t = +6.7050385E+00$
 N = 11700
 DEGREES OF FREEDOM = 11698
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6. V. L. R. TENSILE, MAXIMUM STRESS, CHS=0.002 IN/MIN TP-H1011

Figure 2

$Y = ((+2.2915991E-01) + (-5.4166351E-05) * X)$
 F = +8.4824864E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = -8.4847075E-02 SIGNIFICANCE OF R = SIGNIFICANT
 t = +9.2100415E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 11700 DEGREES OF FREEDOM = 11698
 STORAGE CONDITIONS = AMB TEMP/ RH TEST CONDITIONS = AMB TEMP/ RH





FIG 6. V.L.R. TENSILE STRAIN AT RUPTURE, CHS=0.002 IN/MIN TP-M1011

Figure 3


$Y = ((+7.1568505E+01) + (+6.0835034E-02) * X)$
 F = +4.6864913E+02 SIGNIFICANCE OF F = SIGNIFICANT
 R = +2.0018449E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +2.1648905E+01 SIGNIFICANCE OF t = SIGNIFICANT
 N = 11228 DEGREES OF FREEDOM = 11226
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = AMB TEMP/AH



WING 6.V.L.R. TENSILE STRESS AT RUPTURE, CHS=0.002 IN/MIN TP-H1011

Figure 4

$Y = ((+5.9198130E+02) + (+6.0681149E-01) * X)$
 F = +5.3836167E+02 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +7.8620028E+01$
 R = +2.0925045E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_0 = +2.6152712E-02$
 t = +2.3202622E+01 SIGNIFICANCE OF t = SIGNIFICANT $S_1 = +7.7076981E+01$
 N = 11759 DEGREES OF FREEDOM = 11757
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.V.L.R. TENSILE MODULUS, CHS=0.002 IN/MIN TP H1011

Figure 5


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
1.0	1	38.0	4	63.0	28	90.0	6	121.0	2
12.0	2	39.0	6	64.0	16	92.0	6	123.0	2
13.0	2	40.0	8	65.0	6	93.0	8	125.0	4
15.0	4	41.0	4	66.0	7	94.0	12	127.0	10
16.0	2	42.0	4	67.0	6	95.0	18	129.0	4
17.0	7	43.0	2	69.0	4	96.0	10	130.0	4
19.0	4	44.0	2	70.0	6	97.0	8	131.0	2
20.0	2	45.0	4	71.0	4	99.0	4	134.0	13
21.0	6	46.0	6	72.0	4	100.0	2	135.0	4
22.0	4	47.0	2	73.0	12	101.0	4	136.0	2
23.0	7	48.0	4	74.0	16	102.0	6	138.0	20
24.0	12	49.0	4	75.0	23	103.0	2	139.0	22
25.0	9	50.0	6	76.0	10	104.0	2		
26.0	16	51.0	28	77.0	17	105.0	2		
27.0	8	52.0	31	78.0	16	106.0	4		
28.0	18	53.0	24	79.0	6	108.0	2		
29.0	13	54.0	12	80.0	6	109.0	20		
30.0	18	55.0	14	81.0	6	110.0	23		
31.0	22	56.0	8	82.0	4	111.0	4		
32.0	32	57.0	14	83.0	10	113.0	2		
33.0	14	58.0	10	84.0	2	116.0	34		
34.0	16	59.0	6	85.0	2	117.0	26		
35.0	6	60.0	14	87.0	4	118.0	14		
36.0	14	61.0	8	88.0	2	119.0	30		
37.0	2	62.0	28	89.0	2	120.0	14		

WING 6, L.P. BIAXIAL TENSILE, CHS=0.2 IN/MIN TPH=1011


This sample size summary is applicable for figures 6 thru 10.

$Y = ((+2.1684878E-01) + (-4.2227702E-05) * X)$
 F = +8.8119211E+00 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +1.6280303E-02$
 R = -9.0970137E-02 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +1.4225323E-05$
 t = +2.9684880E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +1.6220478E-02$
 N = 1058 DEGREES OF FREEDOM = 1056
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = AMB TEMP/AH



WING 6, L. A. BIAXIAL TENSILE STRAIN AT MAX STRESS, CHS=0.2 IN/MIN TPH-1011
 Figure 6


$Y = ((+1.1935298E+02) + (+1.8779315E-02) * X)$
 F = +1.2222069E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = +1.0696497E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +3.4960076E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 1058 DEGREES OF FREEDOM = 1056
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.L.R. BIAxIAL TENSILE. MAXIMUM STRESS. CHS=0.2 IN/MIN TPH-1011

Figure 7


Y = ((+2.4492980E-01) + (-3.2951382E-05) * X)
 F = +4.3402517E+00 SIGNIFICANCE OF F = SIGNIFICANT $\sigma = +1.8048710E-02$
 R = -6.4008805E-02 SIGNIFICANCE OF R = SIGNIFICANT $S_0 = +1.5816710E-05$
 t = +2.0833270E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_1 = +1.8020232E-02$
 N = 1057 DEGREES OF FREEDOM = 1055
 STORAGE CONDITIONS = AMB TEMP/AM TEST CONDITIONS = AMB TEMP/AM



WING 6.L.R. BIAXIAL TENSILE, STRAIN AT RUPTURE, CHS=0.2 IN/MIN TPH-1011

Figure 8


$T = (+1.1954182E+02) + (+2.2263769E-02) * X$
 F = +1.5049750E+01 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +6.5818546E+00$
 R = +1.1859388E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_0 = +5.7389712E-03$
 t = +9.8794007E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_1 = +6.5385020E+00$
 N = 1057 DEGREES OF FREEDOM = 1055
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.L.R. BIAXIAL TENSILE, STRESS AT RUPTURE, CHS=0.2 IN/MIN TPH-1011

Figure 9

$Y = 1 (+9.176667E+02) + (+6.8978027E-01) * X$
 F = +5.8008080E+01 SIGNIFICANCE OF F = SIGNIFICANT $S_0 = +1.0497580E+02$
 R = +2.2829431E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +8.9778494E-02$
 t = +7.6163036E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +1.0225185E+02$
 N = 1057 DEGREES OF FREEDOM = 1055
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.L.A. BIAXIAL TENSILE MODULUS, CHS=0.2 [N/MIN TPH-1011]

Figure 10


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
2.0	3	28.0	64	53.0	76	78.0	147
4.0	57	29.0	34	54.0	77	79.0	102
5.0	151	30.0	46	55.0	55	80.0	105
6.0	191	31.0	43	56.0	34	81.0	109
7.0	171	32.0	103	57.0	73	82.0	57
8.0	140	33.0	73	58.0	62	83.0	79
9.0	185	34.0	54	59.0	87	84.0	30
10.0	183	35.0	32	60.0	105	85.0	30
11.0	192	36.0	118	61.0	150	86.0	36
12.0	199	37.0	65	62.0	185	87.0	135
13.0	195	38.0	25	63.0	244	88.0	114
14.0	201	39.0	60	64.0	89	89.0	107
15.0	185	40.0	50	65.0	58	90.0	60
16.0	197	41.0	20	66.0	42	91.0	55
17.0	157	42.0	60	67.0	54	92.0	53
18.0	18	43.0	75	68.0	50	93.0	61
19.0	40	44.0	15	69.0	70	94.0	65
20.0	4	45.0	20	70.0	120	95.0	50
21.0	60	46.0	55	71.0	72	96.0	71
22.0	25	47.0	79	72.0	119	97.0	56
23.0	30	48.0	40	73.0	120	98.0	25
24.0	62	49.0	77	74.0	154	99.0	20
25.0	27	50.0	93	75.0	175	100.0	18
26.0	56	51.0	154	76.0	123	101.0	61
27.0	38	52.0	196	77.0	145	102.0	10
						130.0	18
						134.0	72
						135.0	9
						136.0	15
						137.0	12
						138.0	120
						139.0	102
						169.0	3

WING 6.L.R.TENSILE, CHS=2.0 IN/MIN TP-H1011

This sample size summary is applicable for figures 11 thru 15.


Y = ((+2.600411E-01) + (-6.1274222E-05) * X)
 F = +2.9465070E+02 SIGNIFICANCE OF F = SIGNIFICANT
 R = -1.4923120E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +1.5318912E+01 SIGNIFICANCE OF t = SIGNIFICANT
 N = 10904 DEGREES OF FREEDOM = 10902
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.L.R. TENSILE, STRAIN AT MAX STRESS, CHS=2.0 IN/MIN TP-H1011

Figure 11


$Y = ((+1.2984604E+02) + (+5.0646437E-02) * X)$
 F = +4.7764006E+02 SIGNIFICANCE OF F = SIGNIFICANT
 R = +2.1049813E-01 SIGNIFICANCE OF R = SIGNIFICANT
 I = +2.1854978E+01 SIGNIFICANCE OF I = SIGNIFICANT
 N = 10904 DEGREES OF FREEDOM = 10302
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.L.R. TENSILE, MAXIMUM STRESS, CHS=2.0 IN/MIN TP-H1011


Figure 12

$Y = ((+3.2357371E-01) + (-1.4840222E-04) * X)$
 $F = +8.0398132E+02$ SIGNIFICANCE OF F = SIGNIFICANT $\alpha = +2.0997591E-02$
 $R = -2.6896398E-01$ SIGNIFICANCE OF R = SIGNIFICANT $S_e = +5.2357576E-06$
 $t = +2.8943982E+01$ SIGNIFICANCE OF t = SIGNIFICANT $S_e = +2.0224816E-02$
 $N = 10304$ DEGREES OF FREEDOM = 10302
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = AMB TEMP/AH



MING 6.L.A. TENSILE, STRAIN AT RUPTURE, CHS=2.0 IN/MIN TP-H1011


$F = +7.2480636E+01$
 $R = +8.3588926E-02$
 $t = +8.5135560E+00$
 $N = 10303$
 $Y = ((+1.2060300E+02) + (+1.7511746E-02) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 10301
 STORAGE CONDITIONS = AMB TEMP/RH
 TEST CONDITIONS = AMB TEMP/RH



WING 6 L.R. TENSILE STRESS AT RUPTURE, CHS=2.0 IN/MIN TP-H1011

Figure 14

Y = | | +9.5062851E+02) + | +8.1536284E-01) * X)
 F = +7.2888799E+02 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +1.2070731E+02$
 R = +2.5713607E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +3.0200943E-02$
 t = +2.6997925E+01 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +1.1665422E+02$
 N = 10297 DEGREES OF FREEDOM = 10295
 STORAGE CONDITIONS = AMB TEMP/AM TEST CONDITIONS = AMB TEMP/AM



WING 6, L. R. TENSILE, MODULUS, CHS-2.0 IN/MIN TP-H1011

Figure 15

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
1.0	2	52.0	8	79.0	17	110.0	29
24.0	6	53.0	10	80.0	2	111.0	6
25.0	6	54.0	2	81.0	3	113.0	8
26.0	10	55.0	18	82.0	4	115.0	29
27.0	3	56.0	5	84.0	2	115.0	32
28.0	11	57.0	14	85.0	3	116.0	38
29.0	14	58.0	4	87.0	6	117.0	12
30.0	14	59.0	1	88.0	8	118.0	8
31.0	16	61.0	5	89.0	11	119.0	19
32.0	17	62.0	12	90.0	13	120.0	24
33.0	9	63.0	13	91.0	10	127.0	6
34.0	15	64.0	18	93.0	10	128.0	2
35.0	8	65.0	18	94.0	8	129.0	2
36.0	2	66.0	10	95.0	6	138.0	2
37.0	4	68.0	2	96.0	2	139.0	16
39.0	3	69.0	2	97.0	7		
40.0	3	70.0	10	98.0	2		
42.0	2	71.0	14	100.0	2		
44.0	2	72.0	12	101.0	4		
45.0	2	73.0	18	102.0	4		
46.0	2	74.0	18	103.0	4		
47.0	4	75.0	12	105.0	6		
49.0	4	76.0	16	106.0	4		
50.0	8	77.0	10	108.0	2		
51.0	4	78.0	6	109.0	13		

WING 6.H.P. TRIAXIAL TENSILE, CHS=1750 IN/MIN AT 800 PSI

This sample size summary is applicable for figures 16 thru 20.

$Y = ((+3.0267253E-01) + (-4.3831170E-05) * X)$
 F = +4.2801763E+00 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +1.9337515E-02$
 R = -7.2323563E-02 SIGNIFICANCE OF R = SIGNIFICANT $S_0 = +2.1186159E-05$
 t = +2.0688586E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_1 = +1.9298717E-02$
 N = 816 DEGREES OF FREEDOM = 814
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH





FIG 6, H.R. TRIAXIAL TENSILE, STRAIN AT MAX STRESS, CHS=1750 IN/MIN, 800 PSI

Figure 16


$F = +2.8061695E+01$
 $R = +1.8419931E-01$
 $C = +5.2973291E+00$
 $N = 801$
 STORAGE CONDITIONS = AMB TEMP/RH
 $Y = ((+6.4650564E+02) + (+2.4176105E-01) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF C = SIGNIFICANT
 DEGREES OF FREEDOM = 799
 $G_1 = +4.2131845E+01$
 $S_0 = +4.5638292E-02$
 $S_e = +4.1436829E+01$



WING 6.H.R. TRIAXIAL TENSILE, MAXIMUM STRESS, CHS=1750 IN/MIN, 800 PSI

Figure 17


$Y = ((+3.4662795E-01) + (-1.1139298E-04) * X)$
 F = +1.7788052E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = -1.4629720E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +4.2175884E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 816 DEGREES OF FREEDOM = 814
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6, H.R. TRIAXIAL TENSILE STRAIN AT RUPTURE, CHS=1750 IN/MIN, 800 PSI

Figure 18


$F = +1.6289160E+01$ SIGNIFICANCE OF F = (+1.9862166E-01) * X)
 $R = +1.4004133E-01$ SIGNIFICANCE OF R = SIGNIFICANT
 $t = +4.0352398E+00$ SIGNIFICANCE OF t = SIGNIFICANT
 $N = 816$ DEGREES OF FREEDOM = 814
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.H.R. TRIAXIAL TENSILE STRESS AT RUPTURE, CHS=1750 IN/MIN, 800 PSI

Figure 19

Y = ((+4.2877476E+03) + (+6.3205131E-01) * X)
 F = +3.9617328E-01 SIGNIFICANCE OF F = NOT SIGNIFICANT G_r = +9.9259026E+02
 R = +2.0317942E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT S_e = +1.0901110E+00
 t = +5.7980452E-01 SIGNIFICANCE OF t = NOT SIGNIFICANT S_e = +9.9299474E+02
 N = 816 DEGREES OF FREEDOM = 814
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6.H.A. TRIAXIAL TENSILE, MODULUS, CHS=1750 IN/IN MIN AT 800 PSI

Figure 20


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
24.0	9	51.0	11	78.0	21	107.0	10
25.0	12	52.0	42	79.0	55	109.0	21
26.0	6	53.0	22	80.0	5	110.0	32
27.0	21	54.0	10	82.0	6	111.0	12
28.0	12	55.0	31	83.0	10	112.0	6
29.0	29	56.0	26	85.0	5	113.0	75
30.0	18	57.0	39	86.0	5	114.0	41
31.0	21	58.0	25	87.0	21	115.0	15
32.0	31	59.0	4	88.0	15	116.0	15
33.0	23	60.0	5	89.0	40	117.0	75
34.0	21	61.0	16	90.0	40	118.0	12
35.0	5	62.0	40	91.0	15	119.0	34
36.0	8	63.0	84	92.0	14	120.0	29
37.0	9	64.0	17	93.0	20	121.0	3
38.0	10	65.0	25	94.0	20	123.0	15
39.0	5	68.0	16	95.0	10	124.0	12
40.0	3	69.0	27	96.0	5	125.0	30
41.0	5	70.0	27	97.0	20	126.0	12
42.0	1	71.0	24	98.0	5	127.0	24
43.0	5	72.0	11	101.0	15	128.0	21
44.0	10	73.0	44	102.0	5	129.0	6
45.0	5	74.0	38	103.0	5	130.0	9
46.0	5	75.0	28	104.0	14	131.0	6
49.0	8	76.0	19	105.0	5	136.0	3
50.0	5	77.0	15	106.0	5	139.0	12

WING 6.H.R.HYDROSTATIC. .1750 IN/MIN. 800 PSI

This sample size summary is applicable for figures 21 thru 25.


Y = ((+3.7260239E-01 | + (-3.1133390E-04) * X)
 F = +1.6274829E+02 SIGNIFICANCE OF F = SIGNIFICANT
 R = -3.0095434E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +1.9518442E+01 SIGNIFICANCE OF t = SIGNIFICANT
 N = 1845 DEGREES OF FREEDOM = 1843
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = AMB TEMP/AH



WING 6. H. R. HYDROSTATIC, STRAIN AT MAX STRESS, 1.750 IN/MIN, 800 PSI


Figure 21

$Y = ((+4.2238751E+02) + (+4.9797762E-01) * X)$
 F = +7.9252348E+01 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_f = +7.4542012E+01$
 R = +2.0304900E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_e = +5.5937591E-02$
 t = +8.9023787E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_f = +7.3008995E+01$
 N = 1845 DEGREES OF FREEDOM = 1843
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6. H.R. HYDROSTATIC, MAXIMUM STRESS, 1.750IN/MIN, 800 PSI

F = +9.7118133
 -2.2965151E-01
 +9.8548533E+00
 1843
 STORAGE CONDITIONS = AMB TEMP/RH
 Y = ((+4.3214128E-01) + (-2.8884056E-04) * X)
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF I = SIGNIFICANT
 DEGREES OF FREEDOM = 1841
 TEST CONDITIONS = AMB TEMP/RH
 S_r = +3.9186389E-02
 S_e = +2.9309473E-05
 S_t = +3.8202338E-02



WING 6. H. R. HYDROSTATIC STRAIN AT RUPTURE, 1750 IN/MIN, 800 PSI

Figure 23

$Y = ((+4.0067046E+02) + (+4.2583690E-01) * X)$
 F = +6.4030596E+01 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_f = +7.0635091E+01$
 R = +1.8329774E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_e = +5.3216893E-02$
 t = +8.0019120E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_e = +6.9457978E+01$
 N = 1845 DEGREES OF FREEDOM = 1843
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH





FIG 6. H. R. HYDROSTATIC STRESS AT RUPTURE, 1750 IN/MIN, 800 PSI

Figure 24

$Y = ((+2.2746579E+03) + (+3.8720914E+00) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1842
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH
 F = +5.1305869E+01
 R = +1.6461641E-01
 t = +7.1628115E+00
 N = 1844
 $\sigma_f = +7.1503777E+02$
 $S_b = +5.4057424E-01$
 $S_c = +7.0547440E+02$



WING 6. H. R. HYDROSTATIC, MODULUS, 1750 IN/IN, 800 PSI

Figure 25


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
49.0	2	74.0	29	99.0	3	128.0	15
50.0	26	75.0	23	100.0	6	129.0	2
51.0	49	76.0	17	101.0	6	130.0	3
52.0	43	77.0	34	102.0	5	131.0	3
53.0	18	78.0	16	103.0	6	134.0	6
54.0	27	79.0	3	104.0	3	135.0	3
55.0	18	80.0	14	105.0	6	138.0	27
56.0	15	81.0	5	107.0	6	139.0	39
57.0	21	82.0	11	108.0	9		
58.0	20	83.0	6	109.0	6		
59.0	9	84.0	5	110.0	6		
60.0	9	85.0	6	111.0	3		
61.0	21	86.0	3	112.0	8		
62.0	46	87.0	18	113.0	45		
63.0	23	88.0	16	114.0	15		
64.0	27	89.0	15	115.0	12		
65.0	9	90.0	6	116.0	17		
66.0	2	91.0	5	117.0	12		
67.0	9	92.0	6	118.0	9		
68.0	3	93.0	16	119.0	17		
69.0	20	94.0	14	120.0	3		
70.0	30	95.0	9	124.0	21		
71.0	38	96.0	14	125.0	17		
72.0	30	97.0	12	126.0	18		
73.0	30	98.0	7	127.0	12		

WING 6. STRESS RELAXATION MODULUS, 0.5% STRAIN, SEC.-65 DEG F, TPH-1011


This sample size summary is applicable for figures 26 thru 29.

$Y = ((+3.8757882E+04) + (+4.5377654E+01) * X)$
 F = +1.6246927E+01 SIGNIFICANCE OF F = SIGNIFICANT $\sigma = +1.0682178E+04$
 R = +1.1454654E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_p = +1.1257874E+01$
 t = +4.0307478E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_e = +1.0616208E+04$
 N = 1224 DEGREES OF FREEDOM = 1222
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = -065 DEG AMB AH



WING 6. STRESS RELAXATION MODULUS, 0.5% STRAIN, 10 SEC, -65 DEG F, TPH-1011

Y = ((+3.2659565E+04) + (+4.3354688E+01) * X)
 F = +1.7686818E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = +1.1944524E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +4.2055699E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 1224 DEGREES OF FREEDOM = 1222
 STORAGE CONDITIONS = AMB TEMP/AM TEST CONDITIONS = -065 DEG/AM




WING 6. STRESS RELAXATION MODULUS, 0.5% STRAIN, 50 SEC, -65 DEG F, TPH-1011

Figure 27

$\bar{Y} = ((+3.0049535E+04) + (+4.0925369E+01) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1222
 STORAGE CONDITIONS = AMB TEMP/RH
 TEST CONDITIONS = -065 DEG/RH
 $\sigma = +9.2900202E+03$
 $S_e = +9.7857774E+00$
 $S_t = +9.2280160E+03$


F = +1.7490191E+01
 R = +1.1878886E-01
 t = +4.1821275E+00
 N = 1224



WING 6. STRESS RELAXATION MODULUS, 0.5% STRAIN, 100 SEC, -65 DEG F, TPH-1011

Figure 28

$F = +9.4599792E+00$
 $R = +8.7646579E-02$
 $t = +3.0757079E+00$
 $N = 1224$
 STORAGE CONDITIONS = AMB TEMP/RH
 $Y = ((+2.3312189E+04) + (+2.4889949E+01) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1222
 $\sigma_1 = +7.6575323E+03$
 $S_1 = +8.0924293E+00$
 $S_1 = +7.6311839E+03$
 TEST CONDITIONS = -065 DEG/RH



WING 6 STRESS RELAXATION MODULUS, 0.5% STRAIN, 1000 SEC, -65 DEG F, TPH-1011

Figure 29

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
49.0	6	74.0	25	99.0	6	127.0	44
50.0	27	75.0	19	100.0	3	128.0	11
51.0	51	76.0	26	101.0	6	129.0	1
52.0	44	77.0	30	102.0	6	131.0	1
53.0	14	78.0	17	103.0	6	134.0	27
54.0	30	79.0	3	104.0	3	135.0	3
55.0	18	80.0	16	105.0	6	138.0	24
56.0	12	81.0	6	107.0	6	139.0	42
57.0	24	82.0	12	108.0	9		
58.0	18	83.0	6	109.0	6		
59.0	9	84.0	9	110.0	6		
60.0	12	85.0	3	111.0	3		
61.0	20	86.0	6	112.0	9		
62.0	48	87.0	15	113.0	47		
63.0	24	88.0	20	114.0	13		
64.0	21	89.0	12	115.0	9		
65.0	9	90.0	5	116.0	18		
66.0	6	91.0	9	117.0	12		
67.0	6	92.0	12	118.0	9		
68.0	6	93.0	12	119.0	15		
69.0	21	94.0	13	120.0	3		
70.0	30	95.0	6	123.0	2		
71.0	41	96.0	18	124.0	10		
72.0	36	97.0	14	125.0	13		
73.0	23	98.0	9	126.0	16		

WING 6. STRESS RELAXATION MODULUS. 0.5X STRAIN. SEC.-40 DEG F. TPH-1011

This sample size summary is applicable for figures 30 thru 33

Y = ((+1.8051550E+04) + (-3.3567262E+00) * X)
 SIGNIFICANCE OF F = NOT SIGNIFICANT S = +4.5681585E+03
 SIGNIFICANCE OF R = NOT SIGNIFICANT S = +4.6646321E+00
 SIGNIFICANCE OF t = NOT SIGNIFICANT S = +4.5690239E+03
 N = 1274 DEGREES OF FREEDOM = 1272
 STORAGE CONDITIONS = AMB TEMP/AM TEST CONDITIONS = -040 DEG/AM





FIG 6. STRESS RELAXATION MODULUS, 0.5% STRAIN, 10 SEC. -40 DEG F, TPH-1011

Figure 30

Y = ((+1.3045946E+04) + (-7.1879942E+00) * X1)
 F = +5.0779704E+00 SIGNIFICANCE OF F = SIGNIFICANT S₁ = +3.1293889E+03
 R = -6.3057446E-02 SIGNIFICANCE OF R = SIGNIFICANT S₂ = +3.1897679E+00
 I = +2.2534352E+00 SIGNIFICANCE OF I = SIGNIFICANT S₃ = +3.1243885E+03
 N = 1274 DEGREES OF FREEDOM = 1272
 STORAGE CONDITIONS = AMB TEMP/AM TEST CONDITIONS = -40 DEG/AM



WING 6. STRESS RELAXATION MODULUS, 0.5% STRAIN, 50 SEC. -40 DEG F. TPH-1011


Figure 31

$F = +6.7988083E+00$
 $R = -7.2914732E-02$
 $t = +2.6074524E+00$
 $N = 1274$

$Y = ((+1.1423992E+04) + (-7.1689576E+00) * X)$

SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1272

STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = -040 DEG/AH



WING 6, STRESS RELAXATION MODULUS, 0.5% STRAIN, 100 SEC. -40 DEG F, TPH-1011

Figure 32

$Y = ((+7.5551074E+03) + (-5.5845329E+00) * X)$
 F = +0.7998801E+00 SIGNIFICANCE OF F = SIGNIFICANT
 R = -8.7169749E-02 SIGNIFICANCE OF R = SIGNIFICANT
 t = +3.1207980E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 1274 DEGREES OF FREEDOM = 1272
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = -040 DEG/RH




FIGURE 6. STRESS RELAXATION MODULUS, 0.5% STRAIN, 1000 SEC, -40 DEG F, TPH-1011


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
49.0	6	74.0	33	99.0	6	127.0	11
50.0	27	75.0	29	100.0	3	128.0	15
51.0	59	76.0	23	101.0	9	129.0	3
52.0	45	77.0	28	102.0	5	131.0	3
53.0	15	78.0	21	103.0	6	134.0	24
54.0	32	79.0	6	104.0	3	135.0	3
55.0	18	80.0	21	105.0	6	138.0	9
56.0	18	81.0	12	107.0	6	139.0	57
57.0	27	82.0	12	108.0	9		
58.0	15	83.0	9	109.0	6		
59.0	6	84.0	9	110.0	6		
60.0	22	85.0	3	111.0	3		
61.0	21	86.0	15	112.0	24		
62.0	49	87.0	14	113.0	38		
63.0	24	88.0	21	114.0	14		
64.0	24	89.0	15	115.0	9		
65.0	12	90.0	15	116.0	15		
66.0	9	91.0	12	117.0	12		
67.0	7	92.0	12	118.0	9		
68.0	6	93.0	15	119.0	24		
69.0	29	94.0	12	120.0	3		
70.0	24	95.0	14	123.0	6		
71.0	43	96.0	18	124.0	17		
72.0	39	97.0	6	125.0	15		
73.0	18	98.0	9	126.0	17		

WING 6. STRESS RELAXATION MODULUS. 3.0% STRAIN. SEC. 20 DEG F, TPH-1011


This sample size summary is applicable for figures 34 thru 37.

Y = 11 + 1.7413524E+03) + 1 -5.0793592E-01) * X)
 F = +4.3101177E+00 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_f = +2.4175564E+02$
 R = -5.5940803E-02 SIGNIFICANCE OF R = SIGNIFICANT $S_r = +2.4437177E-01$
 t = +2.0760823E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_t = +2.4146495E+02$
 N = 1375 DEGREES OF FREEDOM = 1373
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +020 DEG/RH



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 10 SEC, 20 DEG F, TPH-1011


$Y = ((+1.0296644E+03) + (+1.6707002E-01) * X)$
 F = +1.3450593E+00 SIGNIFICANCE OF F = NOT SIGNIFICANT $\alpha = +1.4235915E+02$
 R = +3.1284040E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT $S_0 = +1.4405482E-01$
 t = +1.1597669E+00 SIGNIFICANCE OF t = NOT SIGNIFICANT $S_1 = +1.4234128E+02$
 N = 1375 DEGREES OF FREEDOM = 1373
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = +020 DEG/AH



WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, 50 SEC, 20 DEG F, TFM-1011


Figure 35

Y = ((+8.7548564E+02) + (+1.6456630E-01) * X)
 F = +1.8096403E+00 SIGNIFICANCE OF F = NOT SIGNIFICANT G₁ = +1.2091376E+02
 R = +3.6280633E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT S₁ = +1.2233332E-01
 t = +1.3452287E+00 SIGNIFICANCE OF t = NOT SIGNIFICANT S₂ = +1.2087815E+02
 N = 1375 DEGREES OF FREEDOM = 1373
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = +020 DEG/AH



WING 6. STRESS RELAXATION MODULUS. 3.0% STRAIN, 100 SEC, 20 DEG F, TPH-1011

$\gamma = ((+5.6842487E+02) + (+1.7264543E-01) * X)$
 F = +3.7589186E+00 SIGNIFICANCE OF F = NOT SIGNIFICANT $\sigma_f = +8.8076956E+01$
 R = +5.2251951E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT $S_p = +8.9047893E-02$
 t = +1.9387930E+00 SIGNIFICANCE OF t = NOT SIGNIFICANT $S_t = +8.7988662E+01$
 N = 1375 DEGREES OF FREEDOM = 1373
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = +020 DEG/AH



WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, 1000 SEC, 20 DEG F, TPH-1011

Figure 37


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
2.0	3	27.0	12	53.0	6	78.0	24	103.0	6
3.0	6	28.0	24	54.0	36	79.0	9	104.0	6
4.0	18	29.0	33	55.0	15	80.0	15	105.0	3
5.0	22	30.0	34	56.0	18	81.0	21	107.0	7
6.0	21	31.0	24	57.0	27	82.0	9	108.0	9
7.0	35	32.0	33	58.0	12	83.0	6	109.0	6
8.0	27	33.0	23	59.0	9	84.0	9	110.0	6
9.0	36	34.0	27	60.0	23	85.0	3	111.0	3
10.0	32	35.0	18	61.0	15	86.0	15	112.0	21
11.0	37	36.0	28	62.0	56	87.0	21	113.0	47
12.0	44	38.0	9	63.0	21	88.0	18	114.0	17
13.0	30	39.0	6	64.0	27	89.0	18	115.0	9
14.0	34	40.0	9	65.0	12	90.0	21	116.0	21
15.0	39	41.0	9	66.0	9	91.0	9	117.0	9
16.0	18	42.0	9	67.0	3	92.0	15	118.0	9
17.0	25	43.0	9	68.0	9	93.0	12	119.0	21
18.0	1	44.0	3	69.0	24	94.0	9	120.0	3
19.0	7	45.0	6	70.0	33	95.0	15	123.0	6
20.0	4	46.0	9	71.0	44	96.0	18	124.0	18
21.0	9	47.0	9	72.0	36	97.0	15	125.0	15
22.0	6	48.0	3	73.0	18	98.0	6	126.0	19
23.0	3	49.0	6	74.0	33	99.0	9	127.0	12
24.0	19	50.0	21	75.0	27	100.0	3	128.0	15
25.0	15	51.0	76	76.0	24	101.0	9	129.0	3
26.0	24	52.0	49	77.0	30	102.0	3	131.0	3
								132.0	2
								134.0	24
								135.0	3
								138.0	18
								139.0	39

WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, SEC. 77 DEG F, TPH-1011

This sample size summary is applicable for figures 38 thru 41.


F = +2.5667841E+01
 R = +1.0594809E-01
 t = +5.0663439E+00
 N = 2263
 STORAGE CONDITIONS = AMB TEMP/RH
 DEGREES OF FREEDOM = 2261
 TEST CONDITIONS = +077 DEG/RH
 Y = ((+5.8252503E+02) + (+2.6995046E-01) * X)
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 S = +9.6084444E+01
 S_e = +5.3283090E-02
 S_e = +9.5564774E+01



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 10 SEC, 77 DEG F, TPH-1011


Figure 38

$Y = ((+4.6808456E+02) + (+1.9965505E-01) * X)$
 F = +2.9554190E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = +1.0153911E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +4.8532659E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 2263 DEGREES OF FREEDOM = 2261
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = +077 DEG/AH



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 50 SEC, 77 DEG F, TPH-1011


$Y = ((+4.3826283E+02) + (+1.7686876E-01) \times X)$
 F = +2.1298399E+01 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +6.9044107E+01$
 R = +9.6602122E-02 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +3.8324657E-02$
 t = +4.6150124E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +6.8736389E+01$
 N = 2263 DEGREES OF FREEDOM = 2261
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +077 DEG/RH



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 100 SEC. 77 DEG F, TPH-1011

Figure 10

$F = +1.9839912E+01$ $(+3.5403961E+02) + (+1.3682180E-01) * X$
 $R = +9.3286264E-02$ SIGNIFICANT
 $t = +4.4542016E+00$ SIGNIFICANT
 $N = 2262$ SIGNIFICANT
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +077 DEG/RH
 DEGREES OF FREEDOM = 2260



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 1000 SEC, 77 DEG F, TPH-1011

Figure 41


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
12.0	3	41.0	12	66.0	12	91.0	12	117.0	9
13.0	3	42.0	6	67.0	3	92.0	15	118.0	9
15.0	6	43.0	9	68.0	9	93.0	15	119.0	21
17.0	15	44.0	3	69.0	24	94.0	12	120.0	3
19.0	6	45.0	9	70.0	27	95.0	15	123.0	9
20.0	3	46.0	6	71.0	45	96.0	15	124.0	15
21.0	9	47.0	9	72.0	39	97.0	9	125.0	15
22.0	6	48.0	3	73.0	18	98.0	9	126.0	18
23.0	3	49.0	6	74.0	36	99.0	6	127.0	12
24.0	6	50.0	27	75.0	24	100.0	3	128.0	15
25.0	9	51.0	57	76.0	26	101.0	6	129.0	3
26.0	9	52.0	42	77.0	30	102.0	6	130.0	3
28.0	3	53.0	12	78.0	21	103.0	6	134.0	24
29.0	9	54.0	28	79.0	9	104.0	6	135.0	3
30.0	9	55.0	18	80.0	15	105.0	3	138.0	27
31.0	3	56.0	21	81.0	18	107.0	5	139.0	39
32.0	9	57.0	22	82.0	9	108.0	9		
33.0	9	58.0	15	83.0	9	109.0	6		
34.0	3	59.0	12	84.0	9	110.0	6		
35.0	15	60.0	15	85.0	3	111.0	3		
36.0	24	61.0	20	86.0	9	112.0	24		
37.0	3	62.0	48	87.0	6	113.0	36		
38.0	6	63.0	21	88.0	11	114.0	18		
39.0	9	64.0	30	89.0	6	115.0	9		
40.0	9	65.0	9	90.0	15	116.0	21		

WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, SEC. 100 DEG F, TPH-1011

This sample size summary is applicable for figures 42 thru 45.


$Y = ((+4.5372671E+02) + (+8.1000793E-02) * X)$
 F = +2.0464918E+00 SIGNIFICANCE OF F = NOT SIGNIFICANT $\sigma_1 = +7.0791678E+01$
 R = +9.5989816E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT $S_0 = +5.6594229E-02$
 t = +1.4912553E+00 SIGNIFICANCE OF t = NOT SIGNIFICANT $S_1 = +7.0768216E+01$
 N = 1582 DEGREES OF FREEDOM = 1580
 STORAGE CONDITIONS = AMB TEMP/AM TEST CONDITIONS = +100 DEG/AM



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 10 SEC, 100 DEG F, TPH-1011


Figure 42

$Y = ((+3.7672720E+02) + (+1.2528255E-01) * X)$
 F = +7.4752029E+00 SIGNIFICANCE OF F = SIGNIFICANT
 R = +6.8642777E-02 SIGNIFICANCE OF R = SIGNIFICANT
 S_e = +2.7340817E+00 SIGNIFICANCE OF S_e = SIGNIFICANT
 N = 1581 DEGREES OF FREEDOM = 1579
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +100 DEG/RH



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 50 SEC, 100 DEG F, TPH-1011


F = +1.1438113E+01
 R = +8.4804481E-02
 t = +3.3820279E+00
 N = 1581
 Y = ((+3.5136346E+02) + (+1.4496839E-01) * X)
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1579
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +100 DEG/RH



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 100 SEC, 100 DEG F, TPH-1011

Figure 4/4

$Y = ((+2.7872007E+02) + (+1.2593571E-01) * X)$
 F = +1.3759648E+01 SIGNIFICANCE OF F = SIGNIFICANT G = +4.2601725E+01
 R = +9.2945539E-02 SIGNIFICANCE OF R = SIGNIFICANT S_r = +3.3950425E-02
 t = +3.7094000E+00 SIGNIFICANCE OF t = SIGNIFICANT S_e = +4.2430740E+01
 N = 1581 DEGREES OF FREEDOM = 1579
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +100 DEG/RH



WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, 1000 SEC, 100 DEG F, TPH-1011

Figure 45

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MCNTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MCNTHS)	NR SAMPLES
12.0	3	39.0	12	64.0	30	89.0	6	115.0	9
13.0	3	40.0	9	65.0	9	90.0	12	116.0	21
15.0	6	41.0	6	66.0	12	91.0	15	117.0	9
16.0	3	42.0	12	67.0	3	92.0	12	118.0	15
17.0	12	43.0	9	68.0	9	93.0	15	119.0	21
19.0	6	44.0	3	69.0	27	94.0	15	120.0	3
20.0	6	45.0	3	70.0	15	95.0	14	123.0	9
21.0	6	46.0	6	71.0	51	96.0	15	124.0	15
22.0	3	47.0	9	72.0	39	97.0	9	125.0	15
23.0	6	48.0	6	73.0	18	98.0	9	126.0	18
24.0	18	49.0	6	74.0	32	99.0	6	127.0	12
25.0	18	50.0	27	75.0	24	100.0	3	128.0	12
26.0	18	51.0	60	76.0	30	101.0	6	129.0	2
27.0	15	52.0	51	77.0	30	102.0	5	131.0	3
28.0	21	53.0	12	78.0	21	103.0	6	134.0	24
29.0	33	54.0	27	79.0	8	104.0	3	135.0	3
30.0	36	55.0	18	80.0	14	105.0	3	138.0	18
31.0	24	56.0	18	81.0	15	107.0	6	139.0	42
32.0	33	57.0	24	82.0	9	108.0	9		
33.0	21	58.0	15	83.0	9	109.0	6		
34.0	33	59.0	9	84.0	9	110.0	6		
35.0	18	60.0	17	85.0	3	111.0	3		
36.0	21	61.0	24	86.0	9	112.0	21		
37.0	3	62.0	48	87.0	12	113.0	36		
38.0	3	63.0	21	88.0	12	114.0	18		

WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, SEC. 140 DEG F, TPH-1011

This sample size summary is applicable for figures 46 thru 49.


PARAMETER = RELAXATION MODULUS

UNIT OF MEASURE = PSI


F = +1.2358880E+00
 R = +2.6348190E-02
 t = +1.1117050E+00
 N = 1781

Y = ((+3.1849817E+02) + (+3.7732128E-02) * X)
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF t = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 1779

STORAGE CONDITIONS = AMB TEMP/ RH TEST CONDITIONS = +140 DEG/ RH




$Y = 11 + 2.699092E+02$) + ($+7.6300669E-02$) * X)
 F = $+7.2971567E+00$ SIGNIFICANCE OF F = SIGNIFICANT $\sigma_f = +3.9277295E+01$
 R = $+6.9914586E-02$ SIGNIFICANCE OF R = SIGNIFICANT $s_r = +2.8245646E-02$
 t = $+2.7013249E+00$ SIGNIFICANCE OF t = SIGNIFICANT $s_t = +3.9208002E+01$
 N = 1781 DEGREES OF FREEDOM = 1779
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = $+140$ DEG/RH



WING 6. STRESS RELAXATION MODULUS. 3.0% STRAIN. 50 SEC. 140 DEG F. TPH-1011

Figure 4.7


F = +8.9778844E+00
 R = +7.0860780E-02
 t = +2.9963118E+00
 N = 1781
 STORAGE CONDITIONS = RMB TEMP/RH
 DEGREES OF FREEDOM = 1779
 SIGNIFICANCE OF F = (+7.8937673E-02) * X)
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 SIGNIFICANCE OF F = SIGNIFICANT
 S₁ = +3.6372901E+01
 S₂ = +2.6144700E-02
 S₃ = +3.6291663E+01
 TEST CONDITIONS = +140 DEG/RH



WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, 100 SEC, 140 DEG F, TPH-1011

Figure 48

F = +1.6123847E+01
 R = +9.4799955E-02
 t = +4.0154511E+00
 N = 1780
 STORAGE CONDITIONS = AMB TEMP/RH
 DEGREES OF FREEDOM = 1778
 TEST CONDITIONS = +140 DEG/RH
 Y = ((+1.9889728E+02) + (+8.6648146E-02) * X)
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 S₁ = +3.0072135E+01
 S₂ = +2.1578682E-02
 S₃ = +2.9945118E+01



WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, 1000 SEC, 140 DEG F, 7PH-1011

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
12.0	3	39.0	12	64.0	27	89.0	21	115.0	9
13.0	3	40.0	9	65.0	12	90.0	21	116.0	21
15.0	6	41.0	6	66.0	12	91.0	15	117.0	9
16.0	3	42.0	12	67.0	3	92.0	12	118.0	8
17.0	12	43.0	9	68.0	9	93.0	15	119.0	15
19.0	6	44.0	3	69.0	18	94.0	14	120.0	3
20.0	6	45.0	6	70.0	20	95.0	15	123.0	9
21.0	6	46.0	3	71.0	27	96.0	15	124.0	15
22.0	3	47.0	12	72.0	45	97.0	9	125.0	15
23.0	6	48.0	6	73.0	21	98.0	9	126.0	18
24.0	18	49.0	6	74.0	30	99.0	6	127.0	12
25.0	20	50.0	27	75.0	27	100.0	3	128.0	9
26.0	15	51.0	51	76.0	33	101.0	6	129.0	6
27.0	15	52.0	50	77.0	24	102.0	6	131.0	3
28.0	23	53.0	15	78.0	27	103.0	6	138.0	9
29.0	29	54.0	27	79.0	9	104.0	3	139.0	41
30.0	33	55.0	15	80.0	15	105.0	6		
31.0	27	56.0	18	81.0	18	107.0	6		
32.0	33	57.0	27	82.0	6	108.0	9		
33.0	21	58.0	15	83.0	12	109.0	6		
34.0	30	59.0	9	84.0	9	110.0	6		
35.0	15	60.0	15	85.0	3	111.0	3		
36.0	27	61.0	24	86.0	12	112.0	24		
37.0	3	62.0	46	87.0	15	113.0	39		
38.0	3	63.0	21	88.0	27	114.0	15		

WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, SEC, 180 DEG F, TPH-1011


This sample size summary is applicable for figures 50 thru 53.

$F = +2.1642071E+01$
 $R = +1.1018369E-01$
 $t = +4.6521040E+00$
 $N = 1763$

$Y = ((+2.4894853E+02) + (+1.2600842E-01) * X)$ * X)

SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1761


STORAGE CONDITIONS = AMB TEMP/AM
 TEST CONDITIONS = +180 DEG/AM



WING 6, STRESS RELAXATION MODULUS, 3.0% STRAIN, 10 SEC, 180 DEG F, TPH-1011

Figure 50

$Y = ((+2.1005600E+02) + (+1.0977879E-01) * X)$
 F = +2.4851328E+01 SIGNIFICANCE OF F = SIGNIFICANT $\sigma = +2.9442418E+01$
 R = +1.1796472E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +2.2021334E-02$
 t = +4.9851106E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +2.9245144E+01$
 N = 1763 DEGREES OF FREEDOM = 1761
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +180 DEG/RH



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 50 SEC, 180 DEG F, 7PH-1011

Figure 51

$Y = 11 + 1.9511620E+02) + (+1.0539216E-01) * X)$
 F = +2.6876035E+01 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +2.7195785E+01$
 R = +1.2260661E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +2.0329454E-02$
 t = +5.1842102E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +2.6998265E+01$
 N = 1763 DEGREES OF FREEDOM = 1761
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = +180 DEG/RH





FIGURE 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 100 SEC, 180 DEG F, TPH-101

$Y = ((+1.4821970E+02) + (+1.1039576E-01) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1761
 STORAGE CONDITIONS = AMB TEMP/RH
 TEST CONDITIONS = +180 DEG/RH
 $\sigma = +2.2806478E+01$
 $S_e = +1.6975317E-02$
 $S_t = +2.2543847E+01$

F = +4.2293056E+01
 R = +1.5314449E-01
 t = +6.5033111E+00
 N = 1763
 UNIT OF MEASURE = PSI
 PARAMETER = RELAXATION MODULUS



WING 6. STRESS RELAXATION MODULUS, 3.0% STRAIN, 1000 SEC, 180 DEG F, TPH-1011

Figure 53

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
24.0	10	52.0	15	78.0	16	104.0	3
25.0	25	53.0	20	79.0	5	105.0	3
26.0	10	54.0	10	80.0	20	109.0	3
27.0	5	55.0	10	81.0	15		
28.0	10	56.0	18	82.0	8		
29.0	15	58.0	20	83.0	20		
30.0	5	59.0	16	84.0	10		
31.0	21	60.0	15	85.0	14		
32.0	10	61.0	27	86.0	11		
33.0	26	62.0	0	87.0	10		
34.0	10	63.0	15	88.0	10		
35.0	12	64.0	17	89.0	3		
36.0	8	65.0	15	90.0	15		
37.0	28	66.0	5	91.0	20		
38.0	17	67.0	20	92.0	12		
39.0	15	68.0	20	93.0	0		
40.0	18	69.0	5	94.0	10		
42.0	12	70.0	15	95.0	8		
43.0	15	71.0	28	96.0	18		
44.0	10	72.0	15	97.0	6		
46.0	10	73.0	8	98.0	10		
47.0	15	74.0	10	99.0	5		
48.0	13	75.0	15	101.0	3		
49.0	25	76.0	20	102.0	11		
50.0	14	77.0	20	103.0	3		

$Y = ((+2.5802889E+01) + (-8.7941418E-03) * X)$
 F = +8.6826303E+00 SIGNIFICANCE OF F = SIGNIFICANT
 R = -9.0732892E-02 SIGNIFICANCE OF R = SIGNIFICANT
 t = +2.9466303E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 1048 DEGREES OF FREEDOM = 1046
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH




Figure 54


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
3.0	3	31.0	3	58.0	6	83.0	1
4.0	7	32.0	9	59.0	2	84.0	3
5.0	4	33.0	9	60.0	2	85.0	2
6.0	4	34.0	7	61.0	10	86.0	2
7.0	6	36.0	5	62.0	2	87.0	2
8.0	3	37.0	8	63.0	5	89.0	4
9.0	13	38.0	2	64.0	4	90.0	1
10.0	18	39.0	2	65.0	2	91.0	4
11.0	21	40.0	6	66.0	4	93.0	2
12.0	16	41.0	2	67.0	5	94.0	2
13.0	11	42.0	5	68.0	6	95.0	2
14.0	16	43.0	4	69.0	4	96.0	2
15.0	6	44.0	5	70.0	8	97.0	2
16.0	5	45.0	1	71.0	10	98.0	2
17.0	2	46.0	2	72.0	4	101.0	3
18.0	9	47.0	2	73.0	10	102.0	4
19.0	1	48.0	2	74.0	8	103.0	2
20.0	6	49.0	5	75.0	8	104.0	2
21.0	3	50.0	2	76.0	12	105.0	2
23.0	9	52.0	3	77.0	8	108.0	1
24.0	7	53.0	9	78.0	3	109.0	2
25.0	5	54.0	3	79.0	3		
26.0	2	55.0	6	80.0	4		
28.0	2	56.0	2	81.0	6		
30.0	2	57.0	1	82.0	4		

WING 6 SI TP-HIGH DYNAMIC RESPONSE, CENTER-WT 70 GM.

This sample size summary is applicable for figures 55 thru 58.


F = +9.2726208E+01
 R = +4.0557122E-01
 K = +9.6294448E+00
 N = 478
 STORAGE CONDITIONS = AMB TEMP/RH
 Y = ((+2.9463194E+03) + (+3.5653298E+03) / X)
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF K = SIGNIFICANT
 DEGREES OF FREEDOM = 471
 TEST CONDITIONS = AMB TEMP/RH
 S₁ = +4.4645391E+02
 S₂ = +3.7025227E+02
 S₃ = +4.0852018E+02




WING 6 S1 TP-H1011 DYNAMIC RESPONSE, CENTER-WT 70 CM, STOR SHEAR AT 200 HZ

Figure 55


$Y = ((+3.4674785E+03) + (+7.4012335E+03) / X)$
 F = +2.6542330E+02 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +6.2593497E+02$
 R = +5.9994452E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +4.5429147E+02$
 t = +1.6291817E+01 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +5.0130422E+02$
 N = 474 DEGREES OF FREEDOM = 472
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



WING 6 S1 TP-H1011 DYNAMIC RESPONSE, CENTER-WT 70 GM, STOR SHEAR AT 400 HZ




F = +2.3980511E+01
 R = +2.2010766E-01
 S = +4.8969900E+00
 N = 473
 STORAGE CONDITIONS = AMB TEMP/RH
 Y = ((+5.7290217E-01) + (+1.9064256E-02) * LN (X))
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF S = SIGNIFICANT
 DEGREES OF FREEDOM = 471
 TEST CONDITIONS = AMB TEMP/RH



WING 6 S1 TP-H1011 DYNAMIC RESPONSE, CENTER-WT 70 GM, LOSS TANGENT AT 200 HZ

$Y = ((+4.8906819E-01) + (+5.7178632E-02) * LN (X))$
 $F = +1.8535762E+02$ SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +9.4553813E-02$
 $R = +5.3101205E-01$ SIGNIFICANCE OF R = SIGNIFICANT $S_0 = +4.1987993E-03$
 $t = +1.3614610E+01$ SIGNIFICANCE OF t = SIGNIFICANT $S_1 = +8.0206352E-02$
 $N = 474$ DEGREES OF FREEDOM = 472
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = AMB TEMP/AH



WING 6 S1 TP-H1011 DYNAMIC RESPONSE, CENTER-W7 70 GM. LOSS TANGENT AT 400 HZ

Figure 58

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
4.0	66	29.0	36	54.0	48	79.0	31
5.0	108	30.0	66	55.0	49	80.0	45
6.0	123	31.0	56	56.0	30	81.0	58
7.0	114	32.0	58	57.0	41	82.0	50
8.0	114	33.0	50	58.0	39	83.0	5
9.0	117	34.0	41	59.0	61	84.0	35
10.0	108	35.0	43	60.0	70	85.0	8
11.0	124	36.0	61	61.0	51	86.0	46
12.0	75	37.0	20	62.0	60	87.0	30
13.0	93	38.0	48	63.0	49	88.0	38
14.0	104	39.0	28	64.0	58	89.0	30
15.0	109	40.0	23	65.0	56	90.0	37
16.0	108	41.0	30	66.0	45	91.0	16
17.0	121	42.0	33	67.0	30	92.0	16
18.0	93	43.0	31	68.0	66	93.0	23
19.0	46	44.0	3	69.0	77	94.0	17
20.0	25	45.0	35	70.0	110	95.0	41
21.0	33	46.0	63	71.0	37	96.0	5
22.0	30	47.0	40	72.0	66	97.0	19
23.0	33	48.0	50	73.0	36	98.0	10
24.0	42	49.0	28	74.0	91	99.0	10
25.0	24	50.0	13	75.0	64	100.0	6
26.0	54	51.0	64	76.0	62	101.0	5
27.0	36	52.0	52	77.0	72	103.0	16
28.0	36	53.0	18	78.0	45	104.0	6

STAGE 1 VING 6 TO-H 1011 SHORF A, 10 SECOND HARDNESS

$Y = ((+6.4861957E+01) + (+4.0846009E-03) * X)$
 $F = +1.3605509E+01$ SIGNIFICANCE OF F = SIGNIFICANT
 $R = +5.1162969E-02$ SIGNIFICANCE OF R = SIGNIFICANT
 $I = +3.6885846E+00$ SIGNIFICANCE OF I = SIGNIFICANT
 $N = 5186$ DEGREES OF FREEDOM = 5184
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH





Figure 59

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
10.0	3	38.0	9	64.0	23	89.0	13
12.0	6	39.0	5	65.0	18	90.0	28
14.0	6	40.0	12	66.0	6	91.0	14
15.0	3	41.0	6	67.0	15	92.0	11
16.0	6	42.0	12	68.0	12	93.0	9
17.0	6	43.0	9	69.0	6	94.0	8
18.0	12	44.0	6	70.0	21	95.0	9
19.0	3	45.0	6	71.0	9	96.0	6
20.0	3	46.0	9	72.0	6	97.0	9
21.0	6	47.0	15	73.0	12	98.0	17
22.0	3	49.0	12	74.0	26	99.0	6
23.0	3	50.0	15	75.0	35	100.0	6
24.0	3	51.0	3	76.0	33	102.0	3
25.0	6	52.0	12	77.0	27	103.0	6
26.0	9	53.0	6	78.0	11	104.0	4
27.0	6	54.0	21	79.0	31	105.0	3
28.0	9	55.0	15	80.0	9	106.0	14
30.0	3	56.0	3	81.0	12	111.0	3
31.0	6	57.0	18	82.0	6	114.0	33
32.0	6	58.0	24	83.0	6	115.0	20
33.0	3	59.0	21	84.0	8	116.0	16
34.0	9	60.0	36	85.0	6	117.0	6
35.0	3	61.0	15	86.0	6	118.0	2
36.0	9	62.0	40	87.0	12		
37.0	16	63.0	33	88.0	12		

STAGE I WING 6 TP-M1011 BURNING RATE AT 1000 PSI

$Y = ((+3.2341016E-01) + (-2.2904327E-04) * X)$
 F = +1.7907365E+02 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_f = +1.5797605E-02$
 R = -3.6528611E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_e = +1.7410132E-05$
 t = +1.3155746E+01 SIGNIFICANCE OF t = SIGNIFICANT $S_e = +1.4656578E-02$
 N = 1126 DEGREES OF FREEDOM = 1124
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 1000 PSI



STAGE I WING 6 TP-M1011 BURNING RATE AT 1000 PSI

Figure 60

*** SAMPLE SIZE SUMMARY ***


AGE (MONTHS)	NP SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NP SAMPLES
11.0	1	40.0	11	65.0	27	90.0	36
14.0	1	41.0	4	66.0	18	91.0	24
15.0	1	42.0	9	67.0	8	92.0	9
16.0	5	43.0	4	68.0	5	93.0	17
18.0	1	44.0	7	69.0	4	94.0	15
19.0	4	45.0	4	70.0	7	95.0	19
20.0	5	46.0	3	71.0	2	96.0	12
21.0	4	47.0	7	72.0	5	97.0	17
22.0	4	48.0	1	73.0	2	98.0	15
24.0	10	49.0	9	74.0	1	100.0	3
25.0	13	50.0	4	75.0	30	101.0	9
26.0	12	51.0	14	76.0	26	102.0	6
27.0	18	52.0	9	77.0	22	103.0	6
28.0	18	53.0	20	78.0	13	105.0	9
29.0	25	54.0	10	79.0	7	106.0	6
30.0	12	55.0	16	80.0	21	108.0	3
31.0	30	56.0	12	81.0	24	113.0	3
32.0	30	57.0	19	82.0	7	115.0	36
33.0	39	58.0	16	83.0	9	116.0	42
34.0	15	59.0	24	84.0	9	117.0	3
35.0	38	60.0	13	85.0	3	118.0	3
36.0	18	61.0	10	86.0	3		
37.0	10	62.0	17	87.0	3		
38.0	2	63.0	20	88.0	12		
39.0	4	64.0	40	89.0	24		

STAGE I WING 6 TP-H 1011

PRESSURE TIME

This sample size summary is applicable to figures 61 and 62.

$Y = ((+3.6044170E+03) + (-1.7555498E-01) * X)$
 F = +2.7246567E+00 SIGNIFICANCE OF F = NOT SIGNIFICANT $\sigma_f = +1.0153164E+02$
 R = -4.7458949E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT $S_e = +1.0635447E-01$
 t = +1.6508534E+00 SIGNIFICANCE OF t = NOT SIGNIFICANT $S_e = +1.0145924E+02$
 N = 1209 DEGREES OF FREEDOM = 1207
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 500 PSI INT PRES



$Y = ((+6.9238258E-01) + (-4.6002211E-04) * X)$
 $F = +6.4158639E+01$ SIGNIFICANCE OF F = SIGNIFICANT
 $R = -2.2466100E-01$ SIGNIFICANCE OF R = SIGNIFICANT
 $t = +8.0099088E+00$ SIGNIFICANCE OF t = SIGNIFICANT
 $N = 1209$ DEGREES OF FREEDOM = 1207
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 500 PSI INT PRES





Figure 62

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
7.0	7	32.0	1	57.0	2	82.0	4
8.0	6	33.0	4	58.0	3	83.0	6
9.0	3	34.0	4	59.0	6	84.0	4
10.0	5	35.0	1	60.0	4	85.0	2
11.0	1	36.0	7	61.0	3	86.0	2
12.0	1	37.0	5	62.0	5	88.0	3
13.0	2	38.0	3	63.0	1	89.0	4
14.0	1	39.0	2	64.0	8	90.0	7
15.0	3	40.0	3	65.0	5	91.0	9
16.0	2	41.0	3	66.0	6	92.0	3
17.0	3	42.0	3	67.0	9	93.0	14
18.0	2	43.0	4	68.0	3	94.0	6
19.0	2	44.0	3	69.0	5	95.0	5
20.0	2	45.0	2	70.0	6	96.0	2
21.0	2	46.0	1	71.0	4	97.0	6
22.0	1	47.0	5	72.0	3	98.0	2
23.0	6	48.0	5	73.0	4	100.0	1
24.0	3	49.0	2	74.0	1	101.0	2
25.0	3	50.0	4	75.0	3	102.0	3
26.0	1	51.0	2	76.0	10	103.0	1
27.0	3	52.0	4	77.0	10	104.0	2
28.0	1	53.0	3	78.0	12	105.0	3
29.0	2	54.0	4	79.0	4	106.0	1
30.0	1	55.0	2	80.0	10	109.0	1
31.0	4	56.0	2	81.0	12	113.0	1
						116.0	19
						117.0	6
						118.0	2

STAGE 1 WING 6, TP-H 1011, IGNITABILITY, IGN THRESHOLD POINT, 168 CAL/50 CM/SEC

Y = ((+6.3481388E+01) + (-7.6839365E-03) * X)
 F = +1.3595745E-01 SIGNIFICANCE OF F = NOT SIGNIFICANT $\sigma = +1.2398641E+01$
 R = -1.8918972E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT $S_e = +2.0839263E-02$
 t = +3.6872409E-01 SIGNIFICANCE OF t = NOT SIGNIFICANT $S_x = +1.2411855E+01$
 N = 407 DEGREES OF FREEDOM = 405
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 168 CAL/SQCM/SEC



STAGE 1 WING 6, TP-H 1011, IGNITABILITY, IGN THRESHOLD POINT, 168 CAL/SQ CM/SEC

Figure 63


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
13.0	3	42.0	12	69.0	18	93.0	21
14.0	3	43.0	12	69.0	24	94.0	21
16.0	6	44.0	6	70.0	12	95.0	21
17.0	3	45.0	9	71.0	18	96.0	6
18.0	9	47.0	15	72.0	6	97.0	6
20.0	6	48.0	3	73.0	3	98.0	21
22.0	9	49.0	6	74.0	3	99.0	6
23.0	6	50.0	6	75.0	9	100.0	9
24.0	12	51.0	3	76.0	19	102.0	9
25.0	18	52.0	18	77.0	18	103.0	3
26.0	9	53.0	27	78.0	18	104.0	3
27.0	24	54.0	9	79.0	9	105.0	9
28.0	21	55.0	18	80.0	15	106.0	9
29.0	24	56.0	18	81.0	30	108.0	6
30.0	27	57.0	12	82.0	3	110.0	3
31.0	33	58.0	27	83.0	15	113.0	6
32.0	30	59.0	9	84.0	6	117.0	36
33.0	24	60.0	15	85.0	9	118.0	36
34.0	33	61.0	9	86.0	9	119.0	6
35.0	12	62.0	15	87.0	6	124.0	21
37.0	23	63.0	12	88.0	3	125.0	27
38.0	3	64.0	15	89.0	12	126.0	9
39.0	3	65.0	21	90.0	9	127.0	27
40.0	12	66.0	12	91.0	9	128.0	18
41.0	6	67.0	12	92.0	3	129.0	6
						130.0	9
						131.0	6

STAGE 1, WING 6, TP-HI011 - THERMAL COEFFICIENT OF LINEAR EXPANSION

This sample size summary is applicable to figures 64 and 65.


$Y = ((+5.9998676E-05) + (+1.7961767E-08) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1930
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 5 DEGREES C/MIN
 F = +9.5086169E+00
 R = +8.4253109E-02
 t = +3.0896044E+00
 N = 1932



STAGE 1, WING 6, TP-M1011 THERMAL COEFFICIENT OF LINEAR EXPANSION BELOW 1G

Figure 64

F = +4.6355128E+01
 R = +1.8952010E-01
 t = +6.8084600E+00
 N = 1332
 Y = ((+8.2444502E-05) + (+9.8845947E-08) * X)
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1330
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 5 DEGREES C/MIN




*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
10.0	4	37.0	12	62.0	40	87.0	8
12.0	4	38.0	12	63.0	36	88.0	20
13.0	4	39.0	12	64.0	48	89.0	28
14.0	8	40.0	20	65.0	44	90.0	24
15.0	4	41.0	8	66.0	16	91.0	40
16.0	4	42.0	4	67.0	16	92.0	16
17.0	4	43.0	16	68.0	8	93.0	12
18.0	20	44.0	4	69.0	8	94.0	16
19.0	12	45.0	8	70.0	12	95.0	20
20.0	8	46.0	12	71.0	28	96.0	12
22.0	8	47.0	16	72.0	12	97.0	12
23.0	12	48.0	24	73.0	8	98.0	16
24.0	4	49.0	16	74.0	36	99.0	8
25.0	28	50.0	8	75.0	28	100.0	4
26.0	24	51.0	8	76.0	40	103.0	8
27.0	24	52.0	24	77.0	32	106.0	8
28.0	28	53.0	36	78.0	32	107.0	8
29.0	24	54.0	4	79.0	32	110.0	48
30.0	28	55.0	24	80.0	32	115.0	48
31.0	44	56.0	36	81.0	12	116.0	12
32.0	52	57.0	12	82.0	8	117.0	4
33.0	36	58.0	40	83.0	12		
34.0	28	59.0	20	84.0	8		
35.0	52	60.0	28	85.0	9		
36.0	24	61.0	32	86.0	4		

STAGE IS WING 6. TP-HIC11. SOL 6FT.


This sample size summary is applicable to figures 66 thru 69.

$Y = ((+3.9286159E+00) + (+2.8596258E-04) * X)$
 F = +2.3223919E+00 SIGNIFICANCE OF F = NOT SIGNIFICANT $\sigma = +2.1399416E-01$
 R = +9.5380018E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT $S_e = +1.8764692E-04$
 t = +1.5239396E+00 SIGNIFICANCE OF t = NOT SIGNIFICANT $S_e = +2.1391789E-01$
 N = 1855 DEGREES OF FREEDOM = 1853
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = AMB TEMP/AH




STAGE 1. WING 6, TP-H1011, SOL GEL, GEL SWELL RATIO

$Y = ((+1.0548425E-02) + (+1.4146579E-05) * X)$
 F = +4.2693390E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = +1.4998172E-01 SIGNIFICANCE OF R = SIGNIFICANT
 t = +6.5340179E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 1857 DEGREES OF FREEDOM = 1855
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH




STAGE 1, WING 6, TP-H1011, SOL GEL, CROSSLINK DENSITY

$Y = 1(+6.6896950E+00) + (+1.3571656E-03) * X1$
 F = +2.5419309E+00 SIGNIFICANCE OF F = NOT SIGNIFICANT $\sigma_1 = +9.6963379E-01$
 R = +3.7092298E-02 SIGNIFICANCE OF R = NOT SIGNIFICANT $\sigma_2 = +8.5129797E-04$
 t = +1.5943434E+00 SIGNIFICANCE OF t = NOT SIGNIFICANT $\sigma_3 = +9.6923039E-01$
 N = 1853 DEGREES OF FREEDOM = 1851
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



STAGE 1, WING 6 TP-HIOLL, SOL GEL, PERCENT EXTRACTABLES

$Y = ((+1.7686961E+00) + (+2.8011459E-05) * X)$
 F = +1.0757469E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = +7.5932459E-02 SIGNIFICANCE OF R = SIGNIFICANT
 t = +3.2798581E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 1857 DEGREES OF FREEDOM = 1855
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



STAGE 1, WING 6, TP-M1011, SOL GEL, DENSITY

Figure 69

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
1.0	3	61.0	1	110.0	2
11.0	1	62.0	1		
13.0	1	63.0	2		
15.0	1	64.0	3		
16.0	1	65.0	2		
18.0	1	66.0	1		
20.0	2	67.0	4		
29.0	1	69.0	4		
35.0	1	70.0	1		
36.0	4	71.0	2		
37.0	4	72.0	1		
39.0	3	73.0	4		
40.0	3	75.0	2		
41.0	3	76.0	1		
42.0	3	79.0	0		
45.0	3	87.0	1		
47.0	1	91.0	1		
48.0	2	95.0	3		
49.0	1	97.0	6		
50.0	3	99.0	3		
51.0	3	102.0	3		
53.0	3	103.0	6		
56.0	1	104.0	3		
57.0	3	105.0	2		
59.0	1	106.0	2		


TGA IGNITION TEMPERATURE, 9 DEGREE C RISE/MINUTE

STAGE I WING 6

$Y = ((+2.9504724E+02) + (+2.4794194E-01) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 118
 STORAGE CONDITIONS = AMB TEMP/RH
 TEST CONDITIONS = AMB TEMP/RH

$G = +L.7979821E+01$
 $S = +5.2529916E-02$
 $S_e = +L.6007465E+01$

F = +2.2278934E+01
 R = +3.9852078E-01
 t = +4.7200566E+00
 N = 120



STAGE I MING 6 TGA IGNITION TEMPERATURE, 9 DEGREE C RISE/MINUTE

Figure 70

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
1.0	3	61.0	1	110.0	2		
11.0	1	62.0	1				
13.0	1	63.0	2				
15.0	1	64.0	3				
16.0	1	65.0	2				
19.0	1	66.0	1				
20.0	2	67.0	4				
27.0	1	69.0	4				
35.0	1	70.0	1				
36.0	4	71.0	2				
37.0	4	72.0	1				
39.0	1	73.0	4				
40.0	2	75.0	2				
41.0	3	76.0	1				
42.0	3	79.0	6				
45.0	2	87.0	1				
47.0	1	91.0	1				
48.0	2	95.0	3				
49.0	1	97.0	5				
50.0	2	99.0	2				
51.0	3	102.0	3				
53.0	3	103.0	5				
56.0	1	104.0	1				
57.0	3	105.0	2				
59.0	1	106.0	2				

STAGE I WING 6 TGA PERCENT WEIGHT LOSS AT IGNITION, 9 DEG C RISE/MIN

$Y = ((+2.4679652E+01) + (+4.6565684E-02) * X)$
 F = +7.2489674E+00 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_1 = +5.1367539E+00$
 R = +2.5079539E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_1 = +1.7295292E-02$
 t = +2.6929906E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_2 = +4.9955515E+00$
 N = 110 DEGREES OF FREEDOM = 108 TEST CONDITIONS = 9 DEG C RISE/MIN
 STORAGE CONDITIONS = 8MB TEMP/RH




Figure 71


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
36.0	1	106.0	1
37.0	1	110.0	1
39.0	1		
40.0	1		
41.0	1		
42.0	1		
45.0	1		
50.0	1		
53.0	1		
57.0	1		
64.0	1		
67.0	1		
69.0	1		
73.0	1		
75.0	1		
79.0	2		
87.0	1		
91.0	1		
95.0	1		
97.0	2		
99.0	1		
102.0	1		
103.0	2		
104.0	1		
105.0	1		

SAGE I WING 6 TGA % WT LOSS AT 250 DEG C HOLD. 12 DEG RISE/MIN TO HOLD

F = +5.7614699E-01
 R = +1.4199229E-01
 I = +7.5904307E 01
 N = 30
 STORAGE CONDITIONS = AMB TEMP/RH
 TEST CONDITIONS = 12 DEG R/M T0HL0

Y = ((+2.154967E+01) + (+1.6689284E-02) * X)
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF I = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 28



SAGE I WING 6 TGA % WT LOSS AT 250 DEG C HOLD, 12 DEG RISE/MIN TO HOLD

Figure 72


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
5.0	9	36.0	17	61.0	8	86.0	12
6.0	27	37.0	8	62.0	8	87.0	15
7.0	11	38.0	6	63.0	12	88.0	12
8.0	9	39.0	5	64.0	5	89.0	23
12.0	3	40.0	15	65.0	10	90.0	27
13.0	3	41.0	2	66.0	9	91.0	9
16.0	5	42.0	8	67.0	16	92.0	9
17.0	12	43.0	12	68.0	6	93.0	9
18.0	2	44.0	3	69.0	12	94.0	11
20.0	5	45.0	6	70.0	19	95.0	3
21.0	5	46.0	6	71.0	20	96.0	11
22.0	6	47.0	14	72.0	16	97.0	11
23.0	5	48.0	14	73.0	14	98.0	8
24.0	6	49.0	5	74.0	9	99.0	9
25.0	2	50.0	3	75.0	9	100.0	6
26.0	14	51.0	2	76.0	8	101.0	5
27.0	9	52.0	5	77.0	7	102.0	10
28.0	12	53.0	13	78.0	16	103.0	12
29.0	12	54.0	8	79.0	24	104.0	2
30.0	13	55.0	15	80.0	30	105.0	3
31.0	20	56.0	11	81.0	23	106.0	11
32.0	18	57.0	12	82.0	18	108.0	6
33.0	8	58.0	14	83.0	26	109.0	9
34.0	24	59.0	9	84.0	12	110.0	2
35.0	11	60.0	17	85.0	8	113.0	21

Copy available to DDC does not permit fully legible reproduction

STAGE 1 WING 6; TP-H 1011; DTA; ENDOTHERM 1; 12 DEGREE CENTIGRADE RISE/MIN

$Y = ((+2.439879E+02) + (-8.2521059E-03) * X)$
 SIGNIFICANCE OF F = NOT SIGNIFICANT $\sigma_1 = +5.6563754E+00$
 SIGNIFICANCE OF R = NOT SIGNIFICANT $S_0 = +4.7213620E-03$
 SIGNIFICANCE OF t = NOT SIGNIFICANT $S_1 = +5.6518335E+00$
 N = 1279 DEGREES OF FREEDOM = 1277
 STORAGE CONDITIONS = RMB TEMP/RH TEST CONDITIONS = 12 DEG. RISE/MIN



STAGE I NING 6. TP-H 1011, OTR, ENDOTHERM 1, 12 DEGREE CENTIGRADE RISE/MIN

Figure 73


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NK SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
5.0	9	36.0	17	61.0	8	96.0	12	114.0	42
6.0	27	37.0	9	62.0	8	97.0	15	115.0	15
7.0	11	38.0	6	63.0	12	98.0	12	116.0	3
8.0	9	39.0	5	64.0	4	89.0	23	117.0	13
12.0	3	40.0	15	65.0	10	90.0	27	118.0	38
13.0	3	41.0	2	66.0	9	91.0	9	124.0	3
15.0	5	42.0	8	67.0	16	92.0	9	125.0	15
17.0	12	43.0	12	68.0	6	93.0	9	126.0	15
18.0	2	44.0	3	69.0	12	94.0	11	127.0	3
20.0	5	45.0	6	70.0	18	95.0	3	128.0	15
21.0	5	46.0	6	71.0	20	96.0	11	129.0	9
22.0	6	47.0	14	72.0	16	97.0	11	130.0	6
23.0	5	48.0	14	73.0	14	98.0	8	131.0	9
24.0	6	49.0	5	74.0	9	99.0	9	132.0	6
25.0	2	50.0	3	75.0	9	100.0	6		
26.0	14	51.0	2	76.0	8	101.0	5		
27.0	9	52.0	5	77.0	7	102.0	10		
28.0	12	53.0	13	78.0	15	103.0	12		
29.0	12	54.0	7	79.0	24	104.0	2		
30.0	13	55.0	15	80.0	30	105.0	8		
31.0	20	56.0	11	81.0	23	106.0	11		
32.0	18	57.0	12	82.0	18	108.0	6		
33.0	8	58.0	14	83.0	25	109.0	9		
34.0	24	59.0	9	84.0	12	110.0	2		
35.0	11	60.0	16	85.0	8	113.0	21		

STAGE 1 WING 6, TP-H 1011, DTA, EXOTHERM 1, 12 DEGREE CENTIGRADE RISE/MIN

$F = +2.0219467E+02$ SIGNIFICANCE OF F = 31272
 $R = -3.7094596E-01$ SIGNIFICANCE OF R = 1272
 $t = +1.4219524E+01$ SIGNIFICANCE OF t = 1272
 $N = 1274$ DEGREES OF FREEDOM = 1272
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 12 DEG. RISE/MIN

$Y = ((+3.0959270E+02) + (-6.6614896E+00) * LOG (X))$
 $\sigma_1 = +5.4945790E+00$
 $\sigma_2 = +4.6047405E-01$
 $\sigma_3 = +5.0501319E+00$



STAGE I WING 6, TP-H LOLL, OTR, EXOTHERM 1, 12 DEGREE CENTIGRADE RISE/MIN


Figure 74

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
12.0	3	40.0	13	65.0	9	90.0	26	118.0	38
13.0	3	41.0	2	66.0	9	91.0	9	124.0	7
16.0	5	42.0	8	67.0	10	92.0	9	125.0	15
17.0	12	43.0	10	68.0	6	93.0	9	126.0	14
18.0	2	44.0	3	69.0	12	94.0	11	127.0	3
20.0	5	45.0	6	70.0	12	95.0	3	128.0	13
21.0	5	46.0	6	71.0	20	96.0	10	129.0	8
22.0	6	47.0	14	72.0	14	97.0	10	130.0	6
23.0	5	48.0	14	73.0	14	98.0	8	131.0	9
24.0	6	49.0	5	74.0	9	99.0	9	132.0	6
25.0	2	50.0	3	75.0	9	100.0	6		
26.0	11	51.0	2	76.0	8	101.0	5		
27.0	8	52.0	4	77.0	7	102.0	10		
28.0	6	53.0	11	78.0	15	103.0	11		
29.0	10	54.0	7	79.0	24	104.0	2		
30.0	9	55.0	15	80.0	30	105.0	7		
31.0	13	56.0	10	81.0	23	106.0	11		
32.0	18	57.0	11	82.0	18	108.0	6		
33.0	6	58.0	14	83.0	22	109.0	9		
34.0	20	59.0	9	84.0	12	110.0	2		
35.0	11	60.0	15	85.0	7	113.0	21		
36.0	17	61.0	8	86.0	12	114.0	42		
37.0	8	62.0	8	87.0	15	115.0	15		
38.0	4	63.0	12	88.0	12	116.0	3		
39.0	2	64.0	4	89.0	23	117.0	13		

AGE : WING 6, TP-H 1011, DTA, EXOTHERM 2, 12 DEGREE CENTIGRADE RISE/MIN

$Y = (1 + 3.495729E+02) + (-6.8995469E+00) * LOG (X)$
 F = +6.960739E+01 SIGNIFICANCE OF F = SIGNIFICANT
 R = -2.390301E-01 SIGNIFICANCE OF R = SIGNIFICANT
 I = +8.547894E+00 SIGNIFICANCE OF I = SIGNIFICANT
 N = 1152 DEGREES OF FREEDOM = 1150
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = 12 DEG. RISE/MIN



STAGE 1 WING 6, TP-H 1011, DTA, EXOTHERM 2, 12 DEGREE CENTIGRADE RISE/MIN


Figure 75

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
15.0	1	64.0	2	116.0	1
17.0	3	65.0	4	117.0	1
22.0	1	77.0	1	118.0	2
24.0	1	78.0	3	128.0	2
26.0	2	79.0	18	130.0	2
27.0	1	80.0	12		
28.0	1	81.0	9		
29.0	2	82.0	7		
30.0	2	83.0	9		
31.0	1	84.0	7		
34.0	2	86.0	1		
35.0	2	87.0	6		
37.0	1	88.0	8		
40.0	5	89.0	16		
42.0	3	90.0	12		
46.0	2	91.0	6		
47.0	3	92.0	5		
49.0	1	94.0	2		
53.0	2	96.0	6		
54.0	1	97.0	3		
55.0	1	108.0	3		
57.0	5	109.0	4		
58.0	2	113.0	11		
59.0	6	114.0	21		
60.0	4	115.0	4		

STAGE 1 WING 6, TP-H 1011, DTA, EXOTHERM 3, 12 DEGREE CENTIGRADE RISE/MIN

$Y = ((+9.6449822E+02] + (+7.9491539E-02) * X)$
 F = +3.2994879E+01 SIGNIFICANCE OF F = SIGNIFICANT $\alpha = +5.8257457E+00$
 R = +9.4865471E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_p = +1.9840920E-02$
 t = +5.7988919E+00 SIGNIFICANCE OF t = SIGNIFICANT $S_e = +5.4716463E+00$
 N = 240 DEGREES OF FREEDOM = 238
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = 12 DEG. RISE/MIN



STAGE 1 WING 6, TP-H 1011, OTA, EXOTHERM 3, 12 DEGREE CENTIGRADE RISE/MIN


Figure 76

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
5.0	9	35.0	17	61.0	7	86.0	11
6.0	27	37.0	7	62.0	6	87.0	9
7.0	11	38.0	6	63.0	12	88.0	5
8.0	9	39.0	5	64.0	3	89.0	7
12.0	3	40.0	10	65.0	8	90.0	18
13.0	3	41.0	2	66.0	8	91.0	5
16.0	4	42.0	5	67.0	13	92.0	7
17.0	9	43.0	11	68.0	6	93.0	9
18.0	2	44.0	3	69.0	12	94.0	9
20.0	2	45.0	5	70.0	19	95.0	3
21.0	5	46.0	4	71.0	20	96.0	5
22.0	2	47.0	11	72.0	16	97.0	4
23.0	5	48.0	13	73.0	14	98.0	6
24.0	5	49.0	4	74.0	9	99.0	3
25.0	2	50.0	3	75.0	9	100.0	6
26.0	12	51.0	2	76.0	8	101.0	5
27.0	8	52.0	5	77.0	6	102.0	8
28.0	11	53.0	11	78.0	13	103.0	11
29.0	10	54.0	8	79.0	7	104.0	1
30.0	10	55.0	15	80.0	19	105.0	5
31.0	19	56.0	11	81.0	14	106.0	8
32.0	16	57.0	7	82.0	11	108.0	3
33.0	8	58.0	12	83.0	19	109.0	5
34.0	22	59.0	3	84.0	7	110.0	2
35.0	9	60.0	12	85.0	8	113.0	13

STAGE 1 WING 6, TP-H 1011, DTA, IGNITION TEMPERATURE, 12 DEGREE CENT, RISE/MIN

$Y = ((+3.7057536E+02) + (+5.4148649E-02) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT $S_1 = +1.1500024E+01$
 SIGNIFICANCE OF R = SIGNIFICANT $S_2 = +1.0292510E-02$
 SIGNIFICANCE OF t = SIGNIFICANT $S_3 = +1.1351951E+01$
 DEGREES OF FREEDOM = 1015
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = 12 DEG. RISE/MIN



STAGE 1 WING 6. TP-H 1011. OTA, IGNITION TEMPERATURE, 12 DEGREE CENT. RISE/MIN


Figure 77

$Y = ((+1.0801750E+00) + (+9.9008850E-04) * X)$
 SIGNIFICANCE OF F = NOT SIGNIFICANT $G_1 = +4.2168889E-01$
 SIGNIFICANCE OF A = NOT SIGNIFICANT $S_1 = +1.8299746E-09$
 SIGNIFICANCE OF I = NOT SIGNIFICANT $S_2 = +4.2924519E-01$
 DEGREES OF FREEDOM = 94
 STORAGE CONDITIONS = AMB TEMP/AH TEST CONDITIONS = 77 DEG/F AMB-AH

F = +2.9271067E-01
 A = +5.5716097E-02
 I = +5.4102742E-01
 N = 96

Sample Size Summary

Age months	Nr Samples
26.0	13
31.0	12
36.0	11
57.0	13
59.0	14
65.0	12
91.0	7
94.0	14



STAGE I WING 6 TP-H1011 TEAR ENERGY TEST/TEMP=77 DEG F

Figure 78


*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
28.0	6	71.0	15	104.0	3
30.0	3	75.0	3	105.0	6
32.0	2	76.0	3	107.0	6
34.0	2	78.0	30	108.0	3
35.0	3	79.0	42	110.0	1
36.0	7	80.0	56	111.0	34
37.0	3	81.0	42	112.0	13
39.0	6	82.0	32	113.0	4
41.0	3	83.0	50	118.0	40
42.0	3	84.0	3	119.0	22
48.0	3	86.0	3	120.0	4
52.0	3	88.0	6	122.0	4
53.0	3	90.0	3		
54.0	3	91.0	9		
55.0	3	92.0	5		
59.0	10	93.0	6		
60.0	18	94.0	3		
61.0	21	95.0	3		
62.0	15	96.0	12		
63.0	5	97.0	6		
64.0	3	98.0	12		
66.0	14	99.0	18		
67.0	54	100.0	9		
68.0	78	101.0	3		
69.0	36	102.0	6		

STAGE I WING 6 DIFFERENTIAL SCANNING CALORIMETER ENDOTHERM PEAK TEMP

This sample size summary is applicable for figures 79 thru 81.


$Y = ((+5.2168177E+02) + (-3.9905498E-02) * X)$
 F = +1.2840918E+02 SIGNIFICANCE OF F = SIGNIFICANT $\sigma_f = +2.2014099E+00$
 R = -3.6756489E-01 SIGNIFICANCE OF R = SIGNIFICANT $S_e = +3.5216391E-03$
 t = +1.1981512E+01 SIGNIFICANCE OF t = SIGNIFICANT $S_t = +2.0485515E+00$
 N = 824 DEGREES OF FREEDOM = 822
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



STAGE I WING 6 DIFFERENTIAL SCANNING CALORIMETER ENDOTHERM PEAK TEMP

Figure 79


F = +4.1148254E+01 SIGNIFICANCE OF F = (-9.1995108E-02) * X
 R = -2.1899985E-01 SIGNIFICANT
 t = +6.4146904E+00 SIGNIFICANCE OF t = SIGNIFICANT
 N = 824 DEGREES OF FREEDOM = 822
 STORAGE CONDITIONS = AMB TEMP/RH. TEST CONDITIONS = AMB TEMP/RH



STAGE I WING 6 DIFFERENTIAL SCANNING CALORIMETER EXOTHERM 1 PEAK TEMP

Figure 80

F = +1.3206600E+01
 R = -1.2574726E-01
 I = +3.6340886E+00
 N = 824
 STORAGE CONDITIONS = AMB TEMP/RH
 Y = ((+6.1430108E+02) + (-9.5974470E-02) * X)
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF I = SIGNIFICANT
 DEGREES OF FREEDOM = 822
 TEST CONDITIONS = AMB TEMP/RH
 $\sigma_1 = +1.5476020E+01$
 $\sigma_2 = +2.6409501E-02$
 $\sigma_3 = +1.5362512E+01$



STAGE I WING 6 DIFFERENTIAL SCANNING CALORIMETER EXOTHERM 2 PEAK TEMP

Figure 81

DISTRIBUTION

	<u>NR</u> <u>COPIES</u>
OOALC	
MMWRMT	1
MMWRME	1
DDC (TISIR) Cameron Station, Alexandria, VA 22314	2
SAMSO, Norton AFB, CA 92409	
MNNP	1
TRW Systems, Norton AFB, CA 92409	
Attn: Mr. J. C. Metcalf, Bldg 523/315	1
AFPRO, Thiokol Chemical Corporation	2
Wasatch Division	
P.O. Box 524	
Brigham City, UT 84302	
(Cy to R. E. Keating)	
AFRPL (MKPB) Edwards AFB, CA 93523	1
SAC (LGMB) Offutt AFB, NE 68113	1
U. S. Naval Ordnance Station, Indian Head, MD 20640	1
Attn: Dr. James H. Wiegand	
Fleet Support Dept., Propulsion	
System Development Division, Code FS7	
CPIA, Johns Hopkins University	1
Attn: Dr. P. L. Nichols	
8621 Georgia Avenue	
Silver Springs, MD 20910	
Naval Plant Branch Representative	1
Attn: Mr. David W. Pratt	
Bacchus Works	
Magna, UT 84044	

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 360 (76) ✓	2. GOVT ACCESSION NO.	3. RECIPIENT CATALOG NUMBER (14) MANCP-360(76)
4. TITLE (and Subtitle) Propellant Surveillance Report LGM-30 F & G Stage 1, Phase E, Series II, TP-H1011, ✓ and	5. TYPE OF REPORT & PERIOD COVERED Test Results - Semi-annual	
	6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) John A. /Thompson (10)	8. CONTRACT OR GRANT NUMBER(s)	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Propellant Lab Section ✓ Directorate of Maintenance 00/ALC Hill AFB, Utah 84406	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS MMEMP Project M72632-5MP116P	
11. CONTROLLING OFFICE NAME AND ADDRESS Service Engineering Division Directorate of Material Management 00/ALC Hill AFB, Utah 84406	12. REPORT DATE (11) October 1976	13. NUMBER OF PAGES 137 (12) 138p.
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	
15a. DECLASSIFICATION/DOWNGRADING SCHEDULE		
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release, Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Solid Propellant Minuteman		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) This report contains propellant test results from cartons of TP-H1011 bulk propellant representing LGM-30 F and G First Stage Minuteman Motors. This report uses a statistical approach to analyze the bulk carton propellant data. Testing was accomplished in accordance with MMEMP Project M72632-5MP116P. The data from this test period are combined with data from previous →		

Block 20 continued

testing and entered into the G085 computer for storage, analysis and regression analysis. From the statistical analysis of all data tested to date (11 and one half years for F and G), significant degradation of the propellant does not appear likely for at least two years past the oldest data point.

Each point on the regression plot represents the mean of all samples at that particular age. The number of samples at each point is indicated on the sample size summary sheet on the page accompanying each regression plot or group of regression plots. The data range at any age can be found by suitable inquiry of the G085 system.