U.S. DEPARTMENT OF COMMERCE National Technical Information Service

AD-A036 431

DISPERSION RELATIONS AND MODE SHAPES FOR WAVES IN LAMINATED VISOELASTIC COMPOSITES BY VARIATIONAL METHODS

STANFORD UNIVERSITY California

October 1976

の語言で見ていたというないとないないないであるとの

FINAL REPORT

ONR Scientific Report Contract report No. 26

DISPERSION RELATIONS AND MODE SHAPES FOR WAVES IN LAMINATED VISCOELASTIC COMPOSITES BY VARIATIONAL METHODS

DEPARTMENT OF MECHANICAL ENGINEERING

OF

APPLIED

MECHANICS

BY

Subrata Mukherjee and E. H. Lee

Lee DECOLOLUTION AND C

Office of Naval Research Grant N00014-75-C-0698

SUDAM 76-4

October 1976

Approved for Public Release; Distribution unlimited.

REPRODUCED BY NATIONAL TECHNICAL INFORMATION SERVICE



STANFORD UNIVERSITY STANFORD, CALIFORNIA

94305

SECURITY CLASSIFICATION OF THIS PAGE (When D	UNCLASSIFIED		
SECURITY CLASSIFICATION OF THIS PAGE (When Date Entered)			
REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS	
REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER	
Contract No. 26			
TITLE (and Sublille)		5. TYPE OF REPORT & PERIOD COVERE	
DISPERSION RELATIONS AND MODE SHAPES FOR		FINAL REPORT	
WAVES IN LAMINATED VISCOELASTIC COMPOSITES BY VARIATIONAL METHODS		6. PERFORMING ORG. REPORT NUMBER	
		B. CONTRACT OR GRANT NUMBER(a)	
Subrata Mukherjee and E. H.	Lee	N00014-75-C-0698	
PERFORMING ORGANIZATION NAME AND ADDRESS Stanford University Division of Applied Mechanics Department of Mechanical Engineering Stanford, California 94305		10. PROGRAM ELEMENT, PROSECT, TASI AREA & WORK UNIT NUMZERS	
		NP 064-471	
		NR UU4=4/1	
CONTROLLING OFFICE NAME AND ADDRESS		12. REPORT DATE	
Office of Naval Research		Uctober 19/6	
Department of the Navy		13. NUMBER OF PAGES	
Washington, D. C. 20025 MON: TORING AGENCY NAME & ADDRESS(II different from Controlling Office)		15. SECURITY CLASS. (of this report)	
		UNCLASSIFIED	
		150, DECLASSIFICATION/DOWNGRADING SCHEDULE	
Approved for public release	; distribution unl	imited	
DISTRIBUTION STATEMENT (of this Report) Approved for public release	; distribution unl	imited	
DISTRIBUTION STATEMENT (of the Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter same as above	; distribution unl	imited m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter Same as above SUPPLEMENTARY NOTES	; distribution unl	imited m Report)	
DISTRIBUTION STATEMENT (of the Report) Approved for public release DISTRIBUTION STATEMENT (of the abetract enter same as above SUPPLEMENTARY NOTES	; distribution unl	imited m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the abstract enter same as above SUPPLEMENTARY NOTES -0-	; distribution unl	imited	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter Same as above SUPPLEMENTARY NOTES -0-	; distribution unl red in Black 20, 11 different from	imited m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter Same as above SUPPLEMENTARY NOTES -0- KEY WORDS (Continue on reverse eide if necesary	; distribution unl red in Block 20, 11 dillerent from	imited m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the abstract enter same as above SUPPLEMENTARY NOTES -0- KEY WORDS (Continue on reverse eide if necessary Viscoelasticity , Floquet wa	; distribution unl red in Block 20, 11 different from and identify by block number)	imited m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter Same as above SUPPLEMENTARY NOTES -0- KEY WORDS (Continue on reverse elde if necessary Viscoelasticity, Floquet wa Composite material, Dispersi Wave proposation	; distribution unl red in Block 20, 11 dillerent free end identify by block number) aves lon relations	imited m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the abstract enter Same as above SUPPLEMENTARY NOTES -O- KEY WORDS (Continue on reverse eide if necessary Viscoelasticity , Floquet Wa Composite material, Dispersi Wave propagation	; distribution unl red in Block 20, 11 different from end identify by block number) aves lon relations	imited m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter Same as above SUPPLEMENTARY NOTES -O- KEY WORDS (Continue on reverse side if necessary Viscoelasticity, Floquet wa Composite material, Dispers: Wave propagation ABSTRACT (Continue on reverse side if necessary The propagation of oscillat	; distribution unl; red in Block 20, 11 dillerent from and identify by block number) aves lon relations end identify by block number) tory waves through	m Report)	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter Same as above SUPPLEMENTARY NOTES -O- KEY WORDS (Continue on reverse eide if necessary Viscoelasticity, Floquet wa Composite material, Dispers: Wave propagation ABSTRACT (Continue on reverse eide if necessary The propagation of oscillation as been analyzed on the basis of lifferential equation systems with	; distribution unl; red in Block 20, 11 different from and identify by block number) aves lon relations end identify by block number) tory waves through of Floquet theory. hich it has proved	m Report) periodic elastic composite This leads to self-adjoin convenient to solve by var	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the obstract enter Same as above SUPPLEMENTARY NOTES -O- KEY WORDS (Continue on reverse side if necessary Viscoelasticity, Floquet wa Composite material, Dispers: Wave propagation ABSTRACT (Continue on reverse side if necessary The propagation of oscillation as been analyzed on the basis of ifferential equation systems wittional methods. Many composite oron-epoxy material, consist of	; distribution unl; red in Block 20, 11 different from and identify by block number) aves ion relations and identify by block number) tory waves through of Floquet theory. nich it has proved es, such as the light strong reinforcing	<pre>m Report) periodic elastic composite This leads to self-adjoin convenient to solve by var ght-weight high-strength ng components in a plastic</pre>	
DISTRIBUTION STATEMENT (of this Report) Approved for public release DISTRIBUTION STATEMENT (of the ebstrect enter Same as above SUPPLEMENTARY NOTES -O- KEY WORDS (Continue on reverse eide if necessary Viscoelasticity, Floquet wa Composite material, Dispersi Wave propagation ABSTRACT (Continue on reverse eide if necessary The propagation of oscillat has been analyzed on the basis of lifferential equation systems wi stional methods. Many composite oron-epoxy material, consist of hatrix. The latter can exhibit difficant influence on wave propagation	; distribution unl; red in Block 20, 11 dillerent free end identify by block number) aves lon relations end identify by block number) tory waves through of Floquet theory. hich it has proved es, such as the light f strong reinforcing viscoelastic proper	m Report) periodic elastic composite This leads to self-adjoin convenient to solve by var ght-weight high-strength ng components in a plastic erties which can have a sig atics.	

and the second second second for a second second for the second second second second second second second second

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

i

20. continued

Replacement of the elastic constant by the viscoelastic complex modulus changes the mathematical structure so that the differential equation system is no longer self-adjoint. However, a modification of the variational principles is suggested which retains formal selfadjointness, and yields variational principles which contain additional boundary terms. These are applied to the determination of wave speed and mode shapes for a laminated composite made of homogeneous elastic reinforcing plates in a homogeneous viscoelastic matrix for plane waves propagating normally to the reinforcing plates. These results agree well with the exact solution which can be evaluated in this simple case. The variational principles permit solutions for periodic, but otherwise arbitrary variation of material properties.

..

Dispersion Relations and Mode Shapes for Waves in Laminated Viscoelastic Composites by Variational Methods

Subrata Mukherjee Assistant Professor Department of Theoretical and Applied Mechanics Cornell University Ithaca, New York

and

E.H. Lee Professor Division of Applied Mechanics Stanford University Stanford, California



· . .]//

Abstract

The propagation of oscillatory waves through periodic elastic composites has been analyzed on the basis of Floquet theory. This leads to self-adjoint differential equation systems which it has proved convenient to solve by variational methods. Many composites, such as the lightweight high-strength boron-epoxy material, consist of strong reinforcing components in a plastic matrix. The latter can exhibit viscoelastic properties which can have a significant influence on wave propagation characteristics.

Replacement of the elastic constant by the viscoelastic complex modulus changes the mathematical structure so that the differential equation system is no longer self-adjoint. However, a modification of the variational principles is suggested which retains formal self-adjointness, and yields variational principles which contain additional boundary terms. These are applied to the determination of wave speeds and mode shapes for a laminated composite made of homogeneous elastic reinforcing plates in a homogeneous viscoelastic matrix for plane waves propagating normally to the reinforcing plates. These results agree well with the exact solution which can be evaluated in this simple case. The variational principles permit solutions for periodic, but otherwise arbitrary variation of material properties.

- iV-

INTRODUCTION

A composite medium typically consists of a matrix material with an embedded reinforcing material in the form of fibers or laminations. A laminated composite can usually be modelled as alternating layers of matrix and filament arranged in a periodic manner, while a fiber reinforced composite can often be represented by a homogenious matrix in which a two dimensional doubly periodic array of filaments is embedded.

A convenient method for analysing wave propagation in composite media is the use of Floquet theory. This approach has been recently used by several authors [1-7] to study steady state wave propagation in periodic elastic composites. Of these, some [1-5] used variational methods while others [6-7] used direct numerical methods involving discretization of the governing differential equations and associated quasi-periodic boundary conditions.

In practice, the matrix in a composite is often a polymer which exhibits viscoelastic properties. This leads to dissipation as well as dispersion. Free wave propagation in an infinite laminated viscoelastic composite was studied by the present authors in [8] using Floquet theory and finite difference methods. In the viscoelastic case, forced steady wave propagation leads to real frequencies and complex wave numbers (attenuating waves) while free waves with no applied tractions have complex frequencies and real wave numbers (damped waves) [8].

Consideration of viscoelastic properties of the matrix leads to complex viscoelastic moduli which are functions of the frequency that can be real or complex. Even in the elastic case [1] it is convenient to utilize complex analysis to incorporate the changing phase as the

- 1 -

wave traverses the periodic medium, so that the displacement is expressed by

$$\tilde{u} = u(x)e^{i\omega t}$$

などのないたいなどのないで、ためになるので、

where ω is the frequency, t is time and u(x) is complex. Application of variational methods involves integrals of the type

$$I(u_1, u_2) = \int_{-a/2}^{a/2} \{-\eta(x) \frac{du_1^*}{dx} \frac{du_2}{dx} + \rho(x) \omega^2 u_1^* u_2^* \} dx$$

where n(x) is the elastic modulus variation, $\rho(x)$ that of the density, a is the periodic cell length and * denotes the complex conjugate For eld licity with η and frequency ω real, the integrals are Hermitian: $I(u_1, u_2) = I^*(u_2, u_1)$ and self-adjoint differential operator systems result for determining the displacement or stress fields. For viscoelasticity, when η and ω are complex, the integrals are not Hermitian since $\eta^{n} \neq \eta$ and the resulting differential operators are non-self-adjoint. However, if one formally bases the theory on real analysis, so that the complex conjugate sign is removed from the integral even though u(x) is complex, the integral is then symmetric: $I(u_1, u_2) =$ $I(u_2,u_1)$, and hence formally self-adjoint differential operators are generated. This is so, with u(x) complex, even though the integral I(u,u) is then no longer physically an energy integral and the variational principle no longer expresses Hamilton's principle. This formulation introduces an additional boundary term, so that the system is formally self adjoint: a self-adjoint operator but not with the appropriate boundary conditions. These boundary terms can be included to generate variational principles, and the ones presented here are formulated in this way.

In this paper, the strain energy [1], complimentary energy [2] and Hellinger-Reissner [3-5] variational principles are extended so that they can be used in the viscoelastic case. As an illustration, the extended version of the Hellinger-Reissner [4] variational principle is applied to the problem of free waves in an infinite one dimensional viscoelastic composite [8]. This principle is chosen because it gave very accurate results in the elastic case [4]. A composite with two homogeneous layers per cell is studied with the filament elastic and the matrix modelled as a three element solid. The Rayleigh-Ritz method is used to obtain dispersion relations and mode shapes and the results compared with the exact solution which exists in this case. For two homogeneous components the elastic solution has been obtained in closed form [9,2] and this can be adapted to the case of linear viscoelastic components. The question of rapidity of convergence to the exact solution is discussed.

The present method can be used to study wave motions in general onedimensional periodic viscoelastic composites which otherwise exhibit arbitrary variations of material properties. Waves in fiber reinforced viscoelastic composites can be studied by using similar variational principles in two dimensions.

- 3 -

GOVERNING EQUATIONS

We consider wave propagation in a one dimensional laminated viscoelastic composite, and, in particular, choose a two material composite as showr in Fig. 1. This example is chosen because the variational principles to be presented in the next section can then be easily compared with those in the elastic case [1-5]. Variational principles for any general one-dimensional inhomogenious periodic viscoelastic medium can be easily obtained by suitable modification of these principles.

The composite covers the full space $-\infty < x < \infty$. We study onedimensional strain waves propagating in a direction x normal to the interface planes. For harmonic waves, the stress and displacement are of the form $\tilde{\sigma} = \sigma(x)e^{i\omega t}$ and $\tilde{u} = u(x)e^{i\omega t}$. The quantities σ and u are, in general, complex.

Within each cell, the governing differential equations are

$$\frac{d\sigma}{dx} + \rho(x)\omega^2 u = 0 \tag{1}$$

$$\sigma = \eta(\mathbf{x}, \omega) \frac{\mathrm{d}\mathbf{u}}{\mathrm{d}\mathbf{x}}$$
 (2)

where $\eta = \lambda + 2\mu$ in terms of complex Lamé viscoelastic moduli of the constituent materials. The quantities η and ρ are periodic with period a

$$\eta(x+a;\omega) = \eta(x;\omega)$$
, $\rho(x+a) = \rho(x)$

and within each cell they are discontinuous functions defined by

- 4 -

$$\eta(\mathbf{x};\omega) , \rho(\mathbf{x}) = \begin{cases} \eta_1(\omega), \rho_1 & -a/2 < x < -b/2 \\ \eta_2(\omega), \rho_2 & -b/2 < x < b/2 \\ \eta_1(\omega), \rho_1 & b/2 < x < a/2 \end{cases}$$

We note that η_1 and η_2 are, in general, complex functions of the possibly complex frequency ω .

By Floquet theory [1] the displacement and stress satisfy the quasiperiodic boundary conditions across each cell

$$u(a/2) = u(-a/2)e^{1Qa}$$
 (3)

$$\sigma(a/2) = \sigma(-a/2)e^{iqa}$$
(4)

where q is the wave number.

The interfaces are assumed perfectly bonded so that u and $_{\sigma}$ are continuous across them

$$u(x_{o}^{+}) = u(x_{o}^{-}) \qquad x_{o}^{-} = \pm b/2$$
 (5)

$$\sigma(x_{0}^{+}) = \sigma(x_{0}^{-}) \qquad x_{0}^{-} = \pm b/2$$
 (6)

- 5 -

VARIATIONAL PRINCIPLES

1. Strain energy principle

Let us choose a pair of sectionally continuous and differentiable functions u and σ which satisfy the constitutive equation (2), the quasi-periodic boundary conditions (3) and (4) and continuity condition (5). The solution (u. σ) which also satisfies the equation of motion (1) and the continuity condition (6) is given by the variational equation

$$\delta I(u) + \sigma(a/2) \delta u(a/2) (1 - e^{-2iqa}) = 0$$
 (7)

where

W. Margaret Margaret

index.

$$I(u) = \int_{-a/2}^{a/2} \left\{ -\frac{n(x)}{2} \left(\frac{du}{dx} \right)^2 + \frac{\rho(x)\omega^2 u^2}{2} \right\} dx .$$

Proof:

Taking variations with respect to u and after carrying out the necessary integrations, we obtain

$$\begin{split} \delta T(u) + \sigma(a/2) \delta u(a/2) (1 - e^{-2iqa}) &= \int_{-a/2}^{a/2} \left\{ \frac{d}{dx} (\eta(x) \frac{du}{dx}) + \rho(x) \omega^2 u \right\} \delta u dx \\ &+ \left\{ \sigma(a/2) - \eta_1 \frac{du}{dx} (a/2) \right\} \delta u(a/2) \\ &+ \eta_1 \frac{du}{dx} (-a/2) \delta u(-a/2) - \sigma(a/2) \delta u(a/2) e^{-2iqa} \\ &+ < \eta(b/2) \frac{du}{dx} (b/2) \delta u(b/2) > \\ &+ < \eta(-b/2) \frac{du}{dx} (-b/2) \delta u(-b/2) > . \end{split}$$

Here we use the notation

$$\langle g(x_{0}) \rangle = g(x_{0}^{+}) - g(x_{0}^{-})$$

If u and σ are restricted to the subclass of functions which satisfy equations(2), (3), (4) and (5), this expression reduces to

$$\int_{-a/2}^{a/2} \left(\frac{d\sigma}{dx} + \rho(x)\omega^2 u\right) \delta u \, dx + \langle \sigma(b/2) \rangle \delta u(b/2) + \langle \sigma(-b/2) \rangle \delta u(-b/2)$$

This expression vanishes for arbitrary δu if and only if u and σ satisfy equations (1) and (δ).

2. Complementary energy principle

Let us choose a pair of sectionally continuous and differentiable functions u and σ which satisfy the equation of motion (1), the quasi-periodic boundary conditions (3) and (4) and continuity condition (6). The solution (u, σ) which also satisfies the constitutive equation (2) and the continuity condition (5) is given by the variational equation

$$\delta J(\sigma) + u(a/2)\delta\sigma(a/2)(1-e^{-2iqa}) = 0$$
 (8)

where

Second St.

$$J(\sigma) = \int_{-a/2}^{a/2} \left\{ -\frac{\sigma^2}{2\eta(x)} + \frac{(\sigma^2)^2}{2\rho(x)\omega^2} \right\} dx$$

and the prime denotes differentiation with respect to x.

Proof:

Taking variations with respect to σ and after carrying out the necessary integrations we obtain

$$\delta J(\sigma) + u(a/2)\delta\sigma(a/2)[1-e^{-2iqa}] = \int_{-a/2}^{a/2} - \left\{ \frac{\sigma}{n(x)} + \frac{d}{dx} \left(\frac{\sigma}{\rho(x)\omega^2} \right) \right\} \delta\sigma \, dx$$
$$+ \left(u(a/2) + \frac{\sigma'(a/2)}{\rho_1 \omega^2} \right) \delta\sigma(a/2)$$
$$- \frac{\sigma'(-a/2)}{\rho_1 \omega} \delta\sigma(-a/2) - u(a/2) \delta\sigma(a/2) e^{-2iqa}$$
$$- \left\{ \frac{\sigma'(b/2)}{\rho(b/2)\omega^2} \delta\sigma(b/2) \right\}$$
$$- \left\{ \frac{\sigma'(b/2)}{\rho(b/2)\omega^2} \delta\sigma(b/2) \right\}$$
$$- \left\{ \frac{\sigma'(-b/2)}{\rho(-b/2)\omega^2} \delta\sigma(-b/2) \right\}$$

8

If u and σ are restricted to the subclass of functions which satisfy equations (1), (3), (4) and (6), this expression reduces to

$$\int_{-a/2}^{a/2} \left(\frac{du}{dx} - \frac{\sigma}{n(x)}\right) \delta \sigma \, dx + \langle u(b/2) \rangle \delta \sigma (b/2) + \langle u(-b/2) \rangle \delta \sigma (-b/2).$$

This expression vanishes for arbitrary $\delta\sigma$ if and only if u and σ satisfy equations (2) and (5).

3. Hellinger-Reisiner principle.

でいたいです。ため、「いい」という

とうてもうないのでいたが、ないないないないないであるのできたので

Let us choose a pair of sectionally continuous and differentiable functions u and σ which satisfy the quasi-periodic boundary conditions (3) and (4) and continuity condition (5). The solution (u, σ)which also satisfies the equation of motion (1), the constitutive equation (2) and continuity condition (6) is given by the variational equation

$$\delta K(u,\sigma) + \sigma(a/2) \delta u(a/2) (1 - e^{-2iqa}) = 0$$
(9)

where

$$K(u,\sigma) = \int_{-a/2}^{a/2} \left(-\sigma \frac{du}{dx} + \frac{\sigma^2}{2\eta(x)} + \frac{\rho(x)\omega^2 \upsilon^2}{2}\right) dx$$

Proof

Taking variations with respect to u and σ and after carrying out the necessary integrations we obtain

$$\delta K(u,\sigma) + o(a/2) \delta u(a/2) (1 - e^{-2iqa}) = \int_{-a/2}^{a/2} (\frac{d\sigma}{dx} + p(x)\omega^2 u) \delta u \, dx + \int_{-a/2}^{a/2} (\frac{\sigma}{\eta(x)} - \frac{du}{dx}) \delta \sigma \, dx$$
$$+ \sigma(-a/2) \delta u(-a/2) - \sigma(a/2) \delta u(a/2) e^{-2iqa}$$

+ <
$$\sigma(b/2)\delta u(b/2)$$
 > + < $\sigma(-b/2)\delta u(-b/2)$ > .

If u and σ are restricted to the subclass of functions which satisfy equations (3), (4) and (5), this expression reduces to

$$\int_{-a/2}^{a/2} \left(\frac{d\sigma}{dx} + \rho(x)\omega^2 u\right) \delta u \, dx + \int_{-a/2}^{a/2} \left(\frac{\sigma}{\eta(x)} - \frac{du}{dx}\right) \delta \sigma \, dx + \langle \sigma(b/2) \rangle \delta u(b/2) + \langle \sigma(-b/2) \rangle \delta u(-b/2).$$

This expression vanishes for arbitrary δu and $\delta \sigma$ if and only if u and σ satisfy equations (1), (2) and (6).

4. A general variational principle

The variational equation

$$\delta[K(u,\sigma)+L_{b}+L_{-b}] + \sigma(a/2)\{\delta u(a/2)-\delta u(-a/2)e^{-iqa}\} + \{u(a/2)e^{-iqa}-u(-a/2)\}\delta\sigma(a/2) = 0$$
(10)

- 9 -

where

$$L_{b} = -\frac{1}{2}[\sigma(b^{-}/2) + \sigma(b^{+}/2)] < u(b/2) >$$
$$L_{-b} = -\frac{1}{2}[\sigma(-b^{-}/2) + \sigma(-b^{+}/2)] < u(-b/2)$$

and $K(u,\sigma)$ is defined in equation (9) is completely equivalent to the original boundary-value problem (1)-(6).

Proof.

Taking variations with respect to u and σ and after carrying out the necessary integrations, we obtain

$$\int_{-a/2}^{a/2} \left(\frac{d\sigma}{dx} + \rho(x)\omega^2 u\right) \delta u \, dx + \int_{-a/2}^{a/2} \left(\frac{\sigma}{\eta(x)} - \frac{du}{dx}\right) \delta \sigma dx$$

+
$$\{u(a/2)e^{-iqa}-u(-a/2)\}\delta\sigma(a/2) - \{\sigma(a/2)e^{-iqa}-\sigma(-a/2)\}\delta u(-a/2)$$

$$-\frac{1}{2} < u(b/2) > \{\delta\sigma(b^{+}/2) + \delta\sigma(b^{-}/2)\} - \frac{1}{2} < u(-b/2) > \{\delta\sigma(-b^{+}/2) + \delta\sigma(-b^{-}/2)\} + \frac{1}{2} < \sigma(-b/2) > \{\delta u(-b^{+}/2) + \delta u(-b^{-}/2)\} + \frac{1}{2} < \sigma(-b/2) > \{\delta u(-b^{+}/2) + \delta u(-b^{-}/2)\}$$

This expression vanishes for arbitrary δu and $\delta \sigma$ if and only if u and σ satisfy the complete set of equations (1)-(6).

>

A NUMERICAL EXAMPLE

1. The problem an' method of solution.

As an illustration, we consider an application of the extended version of the Hellinger-Reissner principle (9). This principle offers greater flexibility than the strain energy or complementary energy principles and Nemat-Nasser [4] used its elastic analog to obtain very accurate results for wave propagation in elastic composites. The general variational principle (10) is not used since, in the one-dimensional case, it is easy to choose test functions for u and σ which are continuous and satisfy the quasi-periodic boundary conditions (3) and (4). The two-dimensional version of (10) should prove very useful for study of wave propagation in fiber reinforced viscoelastic composites.

The exact dispersion relation for this problem was obtained by Sun, Achenbach and Herrmann [9]

$$\cos qa = \cos(\frac{\omega(a-b)}{c_1})\cos(\frac{\omega b}{c_2}) - \frac{1+p^2}{2p}\sin(\frac{\omega(a-b)}{c_1})\sin(\frac{\omega b}{c_2})$$
(11)
where $c_1^2 = n_1/\rho_1$, $c_2^2 = n_2/\rho_2$ and $p^2 = \rho_2 n_2/\rho_1 n_1$

The exact equation for the mode shape is given in [2].

We note that since we are studying free waves in an infinite viscoelastic composite n_1 is a complex function of the complex frequency ω . The wave number q is real.

We obtain approximate solutions for various numbers of terms in series expansions for u and σ and compare these with the exact solution. This tests the efficiency of the variational principle (9).

- 11 -

We define dimensionless quantities

$$X = x/a , U(X) = u(x)/a , S(X) = \sigma(x)/\eta_2$$

$$Q = qa , \bar{K}(U,S) = K(u,\sigma)/\eta_2 a ,$$

$$\Omega = a_{\rho_1}^2 \omega^2/\eta_2 , \theta = \rho_2/\rho_1 , \xi = \eta_2/\eta_1 ,$$

$$\alpha = b/a .$$

In terms of these, equation (9) becomes

$$\delta \bar{K}(U,S) + S(1/2)\delta U(1/2)(1-e^{-2iQ}) = 0 \qquad (12)$$

where

¥.

š.

ŗ¢.

$$\bar{K}(U,S) = \int_{-1/2}^{1/2} (-S \frac{dU}{dX} + \frac{S^2}{2} \frac{\eta_2}{\eta(X)} + \frac{\rho(X)U^2\Omega}{2\theta_1}) dX$$

We expand U and S in series

$$U = \sum_{j=-n}^{n} c_{j}U_{j}(\chi) = \sum_{-n}^{n} c_{j}e^{i(Q+2\pi j)\chi}$$

$$s = \sum_{k=-n}^{n} D_{k} S_{k}(\chi) = \sum_{-n}^{n} D_{k} e^{i(Q+2\pi_{k})\chi}$$
(13)

It is clear that U and S satisfy (3), (4), (5) and (6).

Substituting (13) into (12) and after performing the necessary integrations, we obtain

- 12 -

$$\bar{\mathbf{k}}(\mathbf{U},\mathbf{S}) = \sum_{\mathbf{j},\mathbf{k}^{\mathtt{m}}=\mathbf{n}}^{\mathbf{n}} \left(C_{\mathbf{j}}C_{\mathbf{k}} \mathbf{I}_{\mathbf{j}\mathbf{k}}^{\mathbf{u}} + D_{\mathbf{j}}D_{\mathbf{k}} \mathbf{I}_{\mathbf{j}\mathbf{k}}^{\mathbf{s}} - C_{\mathbf{j}}D_{\mathbf{k}} \mathbf{I}_{\mathbf{j}\mathbf{k}}^{\mathbf{su}} \right)$$

$$S(1/2)\delta U(1/2)(1-e^{-2iQ}) = \sum_{j,k=-n}^{n} J_{jk}^{su} \delta C_{j}$$
 (14)

where

Service

$$I_{jk}^{u} = \int_{-1/2}^{1/2} \frac{\rho(X)}{\rho_{1}} \frac{\Omega}{2} U_{j}(X) U_{k}(X) dX$$

$$= \frac{\Omega[(-1)^{j+k} \sin Q + (\theta - 1) \sin \{\alpha(Q + \pi(j + k))\}]}{2(Q + \pi(j + k))} \quad \text{if } Q \neq -\pi(j + k)$$

$$= \frac{\Omega(1 + \alpha(\theta - 1))}{2} \quad \text{if } Q = -\pi(j + k)$$

$$I_{jk}^{S} = \int_{-1/2}^{1/2} \frac{n_{2}}{2n(X)} S_{j}(X) S_{k}(X) dX$$

=
$$\frac{\sin\{\alpha(Q+\pi(j+k))\} + \xi[(-1)^{j+k} \sin Q - \sin\{\alpha(Q+\pi(j+k))\}]}{2(Q+\pi(j+k))} \quad \text{if } Q \neq -\pi(j+k)$$

=
$$\frac{\alpha + \xi(1-\alpha)}{2} \qquad \text{if } Q = -\pi(j+k)$$

- 13 -

- 2

211-9-23-

7

1.40

·

7944

15

3

$$I_{jk}^{su} = \int_{-1/2}^{1/2} \frac{dU_{j}(x)}{dx} S_{k}(x) dx$$

$$= \frac{(-1)^{j+k} i(Q+2\pi j) sinQ}{Q+\pi (j+k)} \quad \text{if } Q \neq -\pi (j+k)$$

$$= i(Q+2\pi j) \quad \text{if } Q = -\pi (j+k)$$

 $J_{jk}^{su} = (1-e^{-2iQ})e^{i(Q+\pi(j+k))}$

ないたいというないとないではないであるというというというなかであってあるとないできょうとう

Taking variations and equating the coefficients of δC_j and δD_k to zero, we obtain the matrix equation

$$\begin{bmatrix} 2\underline{i}^{u} & \underline{j}^{su} - \underline{i}^{su} \\ -(\underline{i}^{su})^{T} & 2\underline{i}^{s} \end{bmatrix} \begin{bmatrix} \underline{c} \\ \underline{D} \end{bmatrix} = \begin{bmatrix} \underline{0} \\ -\underline{0} \\ \underline{0} \end{bmatrix}$$
(15)

The matrices I^{u} , I^{s} , J^{su} and I^{su} are each of order m x m (where m = 2n+1). The elements of I^{u} and I^{s} are functions of the complex frequency ω through Ω and η . Thus, for any given wave number Q, the frequency ω can be obtained by solving the equation

$$det[\underline{N}(\omega, q)] = 0 \tag{16}$$

where N is a 2m x 2m matrix

Once an eigenvalue ω is known, the correpsonding eigenvector and hence the mode shapes U and S can be easily calculated.

In order to proceed further, we must assume a functional form for $\xi(\omega)$. We assume, as in[8] that the matrix is a standard linear solid and the filament is elastic, so that

$$n_1(s) = \frac{n_1^R + s \tau_1 n_1^G}{1 + s \tau_1}, \quad n_2(s) = n_2^G$$
 (17)

where $s = i\omega$, n_1^R and n_1^G are the "rubbery" (at long time) and "glassy" (at short time) moduli respectively and τ_1 is the relaxation time of the matrix material. The filament is elastic so that n_2 is independent of ω and is real.

The standard linear solid is used as an example. The method applies to any linear viscoelastic material as long as $\eta_1(\omega)$ and $\eta_2(\omega)$ are known. We define some further dimensionless quantities

$$\eta^{G} = \eta_{2}^{G}/\eta_{1}^{G} , \delta_{1} = \eta_{1}^{R}/\eta_{1}^{G}$$

$$t_{1} = c_{1}^{G}\tau_{1}/\alpha , s' = sa/c_{1}^{G}$$

$$\hat{\omega} = -i s' \left[\frac{1-(1-\theta)\alpha}{1-(1-\eta^{G})\alpha} \right]^{1/2}$$

$$G = \sqrt{G}$$
(18)

where $C_1^G = \sqrt{n_1^G}/p_1$ is a reference phase velocity.

In terms of these

$$\xi(s) = \frac{\eta^{G}(1+s't_{1})}{(\delta_{1}+s't_{1})}$$
(19)

 $\Omega(s) = -(s')^2/\eta^G .$

. . .

We now rewrite the matrix $\tilde{N}(s)$ in order to show the frequency dependence explicitly. Thus, equation (16) becomes

$$\det \begin{bmatrix} As'^{2} & B \\ B \\ ---- & --- \\ -E & (1+s't_{1}) \\ -E & G+F & (\delta_{1}+s't_{1}) \end{bmatrix} = 0$$
(20)

where A, B, E, F, G are $(m \times m)$ matrices given by

$$A_{jk} = -\frac{\left[(-1)^{j+k} \sin Q + (\theta - 1) \sin \left\{\alpha \left(Q + \pi \left(j + k\right)\right)\right\}\right]}{\eta^{G}(Q + \pi \left(j + k\right))} \quad \text{if } Q \neq -\pi \left(j + k\right)$$

$$= -\frac{(1+\alpha(\theta-1))}{\eta^{G}} \qquad \text{if } Q = -\pi(j+k)$$

$$B_{jk} = J_{jk}^{su} - I_{jk}^{su}$$

$$E_{jk} = I_{kj}^{su}$$

$$F_{jk} = \frac{n \left[(-1)^{j+k} \sin Q - \sin \left\{ \alpha (Q + \pi (j+k)) \right\} \right]}{Q + \pi (j+k)} \quad \text{if } Q \neq -\pi (j+k)$$

$$= \eta^{G}(1-\alpha) \qquad \text{if } Q = -\pi(j+k)$$

$$G_{jk} = \frac{\sin\{\alpha(Q+\pi(j+k))\}}{Q+\pi(j+k)} \quad \text{if } Q \neq -\pi(j+k)$$

 $= \alpha \qquad \qquad \text{if } Q = -\pi(j+k) .$

The elements of A, B, E, F and G are known once the wave number and the other parameters of the problem are specified. Equation (20) represents a nonlinear eignevalue problem since many of the elements of N 3

are nonlinear functions of s. It is possible to reduce this to a standard eigenvalue problem so that s' is an eigenvalue of a new matrix M of order 3m x 3m. This increases the size of the problem but we can now use any of the standard computer algorithms for determination of eigenvalues of a matrix.

We observe that

$$\det \begin{bmatrix} M_{11} & M_{12} \\ \dots & M_{12} \\ \dots & M_{21} & M_{22} \end{bmatrix} = \det [M_{11}M_{22} - M_{11}M_{21}M_{11}^{-1}M_{12}]$$

if the matrices are conformable and M_{ll}^{-1} exists, so that equation (20) can be expanded as

$$det[\underline{I} s'^{3} + \underline{P} s'^{2} + \underline{H} s' + \gamma \underline{H}] = 0 \qquad (21)$$

where

1.5

and a state of the state of the

$$P = R^{-1}(F + C\delta_{1})$$

$$H = t_{1}R^{-1}E A^{-1}B$$

$$\gamma = \delta_{1}/t_{1}$$

$$R = t_{1}(C + E) ,$$

and I is the unit matrix.

Now s' is an eigenvalue of a 3m x 3m matrix M defined as

$$M = \begin{bmatrix} 0 & I & 0 \\ 0 & 0 & I \\ -\gamma H & -H & -P \end{bmatrix} .$$
(22)

1557 Q

This can be easily proved by expanding the equation

$$det[M-I s'] = 0$$
 (23)

2. Results and conclusions.

Numerical calculations are carried out for the following values of the parameters [8]

$$\eta^{G} = 4$$
 and 50 $\theta = 3$

$$\delta_1 = .70$$
 $t_1 = .0455$ $\alpha = .5$

m = 7 and 11

The wave number Q is specified and only the range $0 \le Q \le \pi$ needs to be studied [10] because the Floquet form of the solution is not uniquely determined.

The dispersion curves are obtained by calculating the eigenvalues of M (equation (22)) using an IBM 360/67 computer. A standard QR algorithm is used. Once the frequency is known for a certain Q we calculate the corresponding eigenvector of the matrix N (equations 15, 20). Now the mode shape U and S are obtained from equation (13).

Figures 2, 3, 4 and 5 show the real and imaginary parts of the frequency $\hat{\omega}$ as a function of the wave number Q for the first 5 modes. The approximate solutions for m = 7 and 11 are compared with the exact solution obtained from (11). The agreement is excellent with m = 11 for the first two modes but the approximate solutions become progressively inaccurate for higher modes. The maximum error in the real part of the frequency for m = 11 is of the order of 10% and occurs for the fifth mode for $Q = \pi$. The error is much higher for the imaginary part of the frequency for the fifth mode. We recall that $\hat{\omega}_{I}$ determines the rate of exponential decay in time.

A comparison with [8] shows that in this case the finite difference scheme is more efficient. Also, a comparison with [4] shows that the Hellinger-Reissner principle does not work as efficiently as it does in the elastic case. The fundamental mode, however, is obtained very accurately with m = 7 and this mode dominates since the higher modes decay faster.

Mode shapes are shown in Figs. 6 and 7. The real parts of the displacement and stress are shown for the fundamental mode for $Q = \pi/2$. The normalzing constant is chosen as in [8] so that U(0) = 1 + 0i. The results for m = 1l are in excellent agreement with the exact solution even though the stress and displacement are expanded in series of smooth functions (13) while the solutions contain sharp discontinuities in slope at the interfaces. The stress solution is more accurate than in [8] because here it is obtained independently rather than being obtained from U by numerical differentiation.

The Hellinger-Reissner principle enables us to obtain continuity of both stress and displacement across the interface while if the strain energy principle is used together with a smooth displacement field a stress discontinuity results [1].

To sum up, this paper presents some varational principles which can be used to study wave propagation in laminated viscoelastic composites. A numerical example gives encouraging results. These principles can be easily extended to higher dimensions to study wave propagation in fiber reinforced viscoelastic composites.

- 19 -

ACKNOWLEDGMENT

-

This research was supported by the Office of Naval Research under Contract N0001475-C-0698 with Stanford University, Stanford, California.

 $S_{2,2,2}$

1512-55

REFERENCES

- Y. Kohn, J.A. Krumhansl and E.H. Lee, Variational methods for dispersion relations and elastic properties of composite materials. J. Appl. Mech. 39, 327 (1972).
- 2. E.H. Lee, A survey of variational methods for elastic wave propagation analysis in composites with periodic structures, Dynamics of Composite Materials, ASME 122 (1972).
- 3. S. Nemat Nasser, General variational methods for waves in elastic composites, Jn. Elasticity 2, 73 (1972).
- S. Nemat Nasser, Harmonic waves in layered composites. J. Appl. Mech. 39, 850 (1972).
- 5. S. Nemat Nasser and F.C.L. Fu, Harmonic waves in layered composites: Bounds on frequencies. J. Appl. Mech. 41, 288 (1974).
- 6. W.H. Yang and E.H. Lee, Modal analysis of Floquet waves in composite material, Jn. Appl. Mech. 41, 429 (1974).
- 7. G.H. Golub, L. Jenning and W.H. Yang, Waves in periodically structured medium. To appear.
- S. Mukherjee and E.H. Lee, Dispersion relations and mode shapes for waves in laminated viscoelastic composites by finite difference methods. Jn. Computers and Structures, 5, 279 (1975).
- 9. C.T. Sun, J.D. Achenbach and G. Herrmann, Continuum theory for a laminated medium, Jn. Appl. Mech. 35, 467 (1968).

10. E.H. Lee and W. Yang, On waves in composite materials with periodic structure, SIAM Jn. Appl. Math. 25, 492 (1973).

- 21 -









-24-







- 27-



and the second second

