

AD-A048 819

OGDEN AIR LOGISTICS CENTER HILL AFB UTAH PROPELLANT L--ETC F/G 21/9.2
PROPELLANT SURVEILLANCE REPORT LGM-30A, B, F AND G STAGE I TP-H--ETC(U)
DEC 77 J A THOMPSON
MANCP-385(77)

JNCLASSIFIED


NL

| OF |
ADA048819

EEF
TAC



END
DATE
FILED
2 - 78
DDC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963

AD A 0 4 8 8 1 9

DDC/TISIR

2
SC

HEADQUARTERS
OGDEN AIR LOGISTICS CENTER
UNITED STATES AIR FORCE
HILL AIR FORCE BASE, UTAH 84406


PROPELLANT
SURVEILLANCE REPORT
LGM - 30A, B, F & G STAGE 1
TP - H 1043

PROPELLANT LAB. SECTION

MANCP REPORT

NR 385(77)

DECEMBER 1977



APPROVED FOR PUBLIC RELEASE, DISTRIBUTION UNLIMITED

AD No. —
DDC FILE COPY

MANCP REPORT NR 385(77)
MMWRM PROJECT M82937C and
M82938C

PROPELLANT SURVEILLANCE REPORT

LGM-30 A, B, F & G STAGE I

TP-H1043 AFT CLOSURE PROPELLANT

Author

John A. Thompson
JOHN A. THOMPSON Chemist
Component & Combustion Test Unit

Engineering & Statistical Review By

John K. Scambia
JOHN K. SCAMBIA, Project Engineer
Service Engineering

Edward J. Erickson
EDWARD J. ERICKSON, Statistician
Data Analysis Unit

Recommended Approval By

Leónidas A. Brown
LEONIDAS A. BROWN, Chief
Component & Combustion Test Unit

Ronald F. Larsen
RONALD F. LARSEN, Chief
Physical & Mechanical Test Unit

Approved By

Don F. Woods
DON F. WOODS, Chief
Propellant Laboratory Section

December 1977

Industrial Products & Ldg Gear Division
Directorate of Maintenance
Ogden Air Logistics Center
United States Air Force
Hill Air Force Base, Utah 84406

ACCESSION NO.	
RTB	White Section <input checked="" type="checkbox"/>
DOC	Buff Section <input type="checkbox"/>
UNARMED	
JUSTRIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
DIST.	AVAIL. AND OR SPECIAL
A	23 E.H.

DISTRIBUTION STATEMENT A
Approved for public release;
Distribution Unlimited

(See 1473)

ABSTRACT

This report contains propellant test results from cartons of TP-H1043 propellant representing selected batches used in the aft closure of First Stage Minuteman Motors. Data from TP-H1043 propellant obtained from the aft closures of the LGM-30A, B, F and G Motors are reported in regression analyses for the fourth time and the third time using the G085 computer system. Testing was accomplished in accordance with MMWRME Project M82937C and M82938C.

An analysis of all parameters indicate that no significant degradation is anticipated for at least two years past the oldest data point.

Each point on the regression plot represents all samples at that particular age. The number of samples at each point is indicated on the sample size summary sheet on the page accompanying each regression plot. The data range at any age can be found by suitable inquiry of the G085 system.

TABLE OF CONTENTS

	<u>Page</u>
Abstract	ii
List of Figures	iv
List of References	v
Glossary of Terms and Abbreviations	vi
Section I, Introduction	
A. Purpose	1
B. Background	1
C. Sampling Plan	2
D. Statistical Approach	2
Section II, Test Results	3
Section III, Conclusions and Recommendations	4
Distribution List	23
DD 1473	24

LIST OF FIGURES

<u>Figure Nr</u>	<u>TP-H1043</u>	<u>Page</u>
Regression Plot, Low Rate Tensile		
1	Strain at Maximum Stress	6
2	Maximum Stress	7
3	Strain at Rupture	8
4	Stress at Rupture	9
5	Modulus	10
Regression Plot, High Rate Tensile		
6	Strain at Maximum Stress	12
7	Maximum Stress	13
8	Strain at Rupture	14
9	Stress at Rupture	15
10	Modulus	16
Regression Plot, Hardness		
11	Shore A, Initial Average	18
12	Shore A, 10 Second Average	19
13	Shore C, Initial Average	21
14	Shore C, 10 Second Average	22

LIST OF REFERENCES

<u>Report Nr</u>	<u>Title</u>	<u>Report Date</u>
LGM-30 First Stage, Wing I Test Reports		
29D	Zero Time Test Results (Aft Closure)	9 Jun 64
29E	Zero Time (Aft Closure Supplement 1)	24 Jun 64
32B	Zero Time, Wings II-V Test Results (Aft Closure)	18 Mar 65
185	ATP Phase I, Wing VI Series III	Jun 70
195	ATP Phase III, Wing II-V	Nov 70
239	Propellant Surveillance Report (TP-H1043)	Apr 72
288	Propellant Surveillance Report (TP-H1043)	Mar 74
337	Propellant Surveillance Report (TP-H1043)	Feb 76

GLOSSARY OF TERMS AND ABBREVIATIONS

Aging Trend	A change in properties or performance resulting from aging of material or component
CSA	Cross Sectional Area
DB	Dogbone
Degradation	Gradual deterioration of properties or performance
E	Modulus (psi), defined as stress divided by strain along the initial linear portion of the curve
EB	End Bonded
EGL	Effective Gage Length
em	Strain at maximum stress
er	Strain at rupture
"F" ratio	The ratio of the variance accounted for by the regression function to the random unexplained variance. The regression function having the most significant "F" ratio is used for plotting data. The ratio is also used in detecting significant changes in random variation between succeeding time points.
JANNAF	Joint Army, Navy, NASA, Air Force Committee
MAGCP	Propellant Lab Section at OOAMA
OOAMA	Ogden Air Materiel Area, Air Force Logistics Command
Regression Equation	The general form of the regression equation is $Y = a + bx$
Regression Line	Line representing mean test values with respect to time
s_b	Standard error of estimate of the regression coefficient
s_e or $s_{Y.X}$	Standard deviation of the data about the regression line

GLOSSARY OF TERMS AND ABBREVIATIONS (cont)

SM	Maximum Stress
Sr	Stress at rupture
Standard Deviation(S)	Square root of variance
Strain Rate	Crosshead speed divided by the EGL
"t" test	A statistical test used to detect significant differences between a measured parameter and an expected value of the parameter (determines if regression slope differs from zero at the 95% confidence level)
Variance	The sum of squares of deviations of the test results from the mean of the series after division by one less than the total number of test results
3 Sigma Band	The area between the upper and lower 3 sigma limit. It can be expected that 99.73% of the inventory represented by the test samples would fall within this range assuming that the population is normally distributed.
90-90 Band	It can be stated with 90% confidence that 90% of the inventory represented by the test samples would fall within this range assuming that the population is normally distributed.

SECTION I
INTRODUCTION

A. PURPOSE:

Quality assurance tests have been conducted for 10 1/2 years on First Stage LGM-30 TP-H1043 aft closure propellant.

Statistical analysis of the tests performed, as directed by Engineering, should provide early warning if serious degradation trends occur. Evaluation of the propellant provides data that can be put directly into engineering reliability and service life predictions. Testing was performed in accordance with MMWRME Directive GTD-1C, Amendments 1 and 2.

B. BACKGROUND:

TP-H1043 propellant is used in the aft closure of LGM-30A, B, F and G First Stage Motors.

This test period represents the fourth time that TP-H1043 propellant has been reported by regression analysis. This is also the third time that data has been processed utilizing the GO85 system.

This report represents a large increase in the number of samples tested. Moreover, the age distribution increased to cover a 10 1/2 year time period (4 to 14 1/2 years).

The slope of the respective regressions for this report (Figures 1 thru 14) and the previous report (1976) are very close. This is the first time that the regression slopes of two successive test periods matched well. This is probably due to the increased number of samples and the stabilizing of post cure chemical changes in the binder.

C. SAMPLING PLAN:

As many as four aft closures are cast from the one TP-H1043 propellant mix. In order to reduce the number of tests, only one batch from each mix will be tested to obtain uniform test results. The selected batches are from the same batch as those previously tested and reported in MAGCP Reports 185(70), 195(70), 239(72), and 288(74).

Low rate tensile, high rate tensile and hardness tests were performed on each propellant batch mix.

D. STATISTICAL APPROACH:

Linear regression analysis was used as the method of data evaluation. Data from different time periods were used to establish a least squares trend line for the data. The variance about the regression line, obtained using individual values of the dependent variable, was used to compute a tolerance interval such that at the 90% confidence level, 90% of the sample distribution fall within this interval. This tolerance interval was extrapolated to a maximum of 24 months. The "t" values and the significance of this statistic, which are reported for each regression model, give an indication of the "statistical significance" of the slope of the trend line as compared to a line of zero slope.

Each point on the regression analysis is a calculation of all samples at that particular age. The number of samples at each point is indicated on the sample size summary sheet accompanying each regression plot. The data range at any age can be found by suitable inquiry of the GO85 system.

SECTION II
TEST RESULTS

A. LOW RATE TENSILE:

All of the low rate test parameters show a statistically significant decrease (Figures 1 thru 5). The strain regressions (Figures 1 and 3) show a very gradual decrease. Regression slopes for stresses and modulus (Figures 2, 4 and 5) show a change with respect to time. This change is less than in the previous report. Although all of the regression trends show a decrease, the propellant still shows good stability and from this analysis the propellant will perform satisfactorily for at least two years beyond the last data point.

B. HIGH RATE TENSILE:

The strain and stress regressions show a statistically significant decrease with the modulus showing a statistically significant increase (Figures 6 thru 10). For all of the regressions, the slopes are gradual.

C. HARDNESS:

Shore A and C initial hardness test data regressions show a statistically significant gradual decrease and the 10 second test data regression shows no significant change.

SECTION III
CONCLUSIONS AND RECOMMENDATIONS

The slopes of the regressions are gradual and closer to a line of zero slope than in the previous report. From this analysis, no significant degradation seems likely and the propellant service life may be extended for at least two years from the date of last testing.

It is recommended that testing be continued to assure service life extension and confirm the present trend.

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
57.0	2	93.0	54	119.0	3	146.0	18
59.0	9	94.0	93	120.0	15	147.0	6
60.0	3	95.0	33	121.0	21	148.0	15
61.0	6	96.0	27	122.0	3	149.0	9
62.0	9	97.0	3	123.0	12	150.0	5
63.0	6	98.0	3	124.0	9	151.0	3
64.0	3	99.0	6	126.0	6	152.0	12
65.0	5	101.0	6	127.0	3	154.0	6
66.0	9	102.0	9	128.0	12	155.0	5
67.0	6	103.0	9	130.0	6	156.0	9
68.0	3	104.0	3	131.0	6	157.0	12
69.0	5	105.0	6	132.0	9	158.0	12
70.0	3	106.0	6	133.0	12	159.0	8
80.0	12	107.0	21	134.0	12	160.0	6
81.0	12	108.0	33	135.0	6	161.0	12
82.0	9	109.0	33	136.0	9	162.0	9
83.0	15	110.0	27	137.0	12	163.0	6
84.0	39	111.0	33	138.0	12	164.0	9
85.0	28	111.0	27	139.0	9	165.0	9
86.0	29	112.0	33	140.0	12	166.0	12
87.0	32	113.0	26	141.0	12	167.0	17
88.0	30	114.0	15	142.0	12	168.0	9
89.0	56	115.0	23	143.0	17	169.0	10
90.0	67	116.0	9	144.0	9	170.0	12
91.0	151	117.0	23	145.0	15	171.0	3
92.0	144	118.0				172.0	12
						173.0	9

TENSILE STRAIN AT MAX STRESS (EM), CHS=2.0 IN/MIN, TP-H1043, WING 266


This sample size summary applies to Figures 1 thru 5

$\gamma = +1.5199155E-01$
 $F = +1.3332441E+01$
 $R = -8.7450990E-02$
 $s_i = +3.6513615E+00$
 $N = 1732$
 $\text{STORAGE CONDITIONS} = \text{AMB TEMP/RH}$

$\sigma_t = +2.4943902E-02$
 $S_o = +2.1977117E-05$
 $S_e = +2.4855518E-02$

$\text{DEGREES OF FREEDOM} = 1730$
 $\text{TEST CONDITIONS} = \text{AMB TEMP/RH}$

$\text{PARAMETER} = \text{STRAIN AT MAX STRESS}$
 $\text{UNIT OF MEASURE} = \text{IN/IN}$
 $0.04 \quad 0.08 \quad 0.12 \quad 0.16 \quad 0.20 \quad 0.24$



TENSILE STRAIN AT MAX STRESS (EMI) . CH3=2.0 IN/MIN. TP-H1043. WING 246

Figure 1

$\gamma = ((+1.9262341E+02) + (-2.3828838E-01) \times X)$
 $F = +8.6120002E+01$
 $R = -2.1770089E-01$
 $S = +9.2800863E+00$
 $t = 1733$
 $N = 1791$
 $F = \text{SIGNIFICANCE OF } F$
 $R = \text{SIGNIFICANCE OF } R$
 $S = \text{SIGNIFICANCE OF } S$
 $t = \text{DEGREES OF FREEDOM} = 1791$
 $\gamma = \text{TEST CONDITIONS} = \text{AMB TEMP/RH}$

UNIT OF MEASURE = PSI
 PARAMETER = MAXIMUM STRESS

TENSILE MAXIMUM STRESS, CHS=2.0 IN/MIN, TP-H1043, WINGS 2 & 6





Figure 2

$F = +6.9206323E+00$
 $R = -6.3122312E-02$
 $t = +2.6307094E+00$
 $N = 1732$
 Y = $(+3.0261188E-01) + (-1.1205284E-04) \times X_1$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1730
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH

PARAMETER = STRAIN AT RUPTURE
 UNIT OF MEASURE = IN/IN



$F = +9.104905E+01$
 $R = -2.2354125E-01$
 $t = +9.5419628E+00$
 $N = 1738$
 STORAGE CONDITIONS = AMB TEMP/RH


$\gamma = ((+1.6286068E+02) + (-2.4581212E-01) * X)$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 DEGREES OF FREEDOM = 1731
 TEST CONDITIONS = AMB TEMP/RH

$G = +2.9887514E+01$
 $S^* = +2.5761169E-02$
 $S_r = +2.9139608E+01$

PARMETER = STRESS AT RUPTURE

UNIT OF MEASURE = PSI


0.00 4.00 8.00 12.00 16.00 20.00 24.00 28.00 32.00



TENSILE STRESS AT RUPTURE (PSI). CHS=2.0 IN/MIN. TP-H1043. WINGS 2 & 6

Figure 4

$F = +2.9596838E+01$ SIGNIFICANCE OF $F =$ SIGNIFICANT
 $R = -1.29692886E-01$ SIGNIFICANCE OF $R =$ SIGNIFICANT
 $t = +5.4402976E+00$ SIGNIFICANCE OF $t =$ SIGNIFICANT
 $N = 1732$ DEGREES OF FREEDOM = 1730
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



TENSILE MODULUS (E), CHS=2.0 IN/MIN, TP-H1043, WINGS 2 & 6

Figure 5

*** SAMPLE SIZE SUMMARY ***

AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES	AGE (MONTHS)	NR SAMPLES
57.0	2	93.0	15	120.0	15	146.0	15
59.0	3	94.0	27	121.0	21	147.0	8
60.0	6	95.0	15	122.0	3	148.0	10
61.0	9	96.0	24	123.0	12	149.0	6
62.0	6	93.0	9	124.0	9	150.0	6
63.0	9	99.0	21	126.0	3	151.0	6
64.0	2	100.0	3	127.0	3	152.0	3
65.0	6	101.0	12	126.0	9	153.0	12
65.0	6	102.0	12	129.0	9	155.0	6
67.0	2	103.0	3	130.0	6	156.0	6
69.0	6	105.0	5	131.0	3	157.0	9
72.0	6	106.0	3	132.0	12	158.0	9
80.0	6	107.0	12	133.0	11	159.0	12
81.0	9	108.0	24	134.0	6	160.0	9
82.0	3	109.0	32	135.0	15	161.0	9
83.0	21	110.0	29	136.0	9	162.0	12
84.0	30	111.0	27	137.0	12	163.0	9
85.0	32	112.0	33	138.0	12	164.0	6
86.0	30	113.0	30	139.0	9	165.0	10
87.0	30	114.0	28	140.0	12	166.0	9
88.0	28	115.0	26	141.0	6	167.0	12
89.0	29	116.0	24	142.0	12	168.0	16
90.0	34	117.0	9	143.0	21	169.0	9
91.0	37	118.0	23	144.0	12	170.0	15
92.0	39	119.0	3	145.0	12	171.0	18
						173.0	15
						174.0	8

TENSILE STRAIN AT MAX STRESS, CHS=1750.0 IN/MIN, TP-H1043. WINGS 2 & 6


This sample size summary applies to figures 6 thru 10

$f = +7.1899013E+01$
 $R = -2.2968341E-01$
 $t = +8.4793286E+00$
 $N = 1293$
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t = SIGNIFICANT
 SIGNIFICANCE OF f = SIGNIFICANT
 DEGREES OF FREEDOM = 1291

TEST CONDITIONS = AMB TEMP/RH
STORAGE CONDITIONS = AMB TEMP/RH

PARMETER = STRAIN AT MAX STRESS

UNIT OF MEASURE = IN/IN



TENSILE STRAIN AT MAX STRESS, CHS=1750.0 IN/MIN, TP-H1043, WINGS 2 & 6

Figure 6

$F = +4.9863522E+01$
 $R = -1.9284091E-01$
 $t^2 = +7.0614108E+00$
 $N = 1293$
 STORAGE CONDITIONS = AMB TEMP/RH

$Y = ((+5.2380653E+02) + (-3.9263957E-01) * X) * \bar{X}$
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF t^2 = SIGNIFICANT
 DEGREES OF FREEDOM = 1291
 TEST CONDITIONS = AMB TEMP/RH

UNIT OF MEASURE = PSI
 PARAMETER = MAXIMUM STRESS




Figure 7

$F = +4.0688217E+01$
 $R = -1.7479662E-01$
 $t = +6.3787316E+00$
 $N = 1293$
 $\text{STORAGE CONDITIONS} = \text{AMB TEMP/RH}$
 $\text{TEST CONDITIONS} = \text{AMB TEMP/RH}$

$$Y = ((+3.1256014E-01) + (-2.8181051E-04) * X)$$

$\sigma_f = +4.3667919E-02$
 $S_a = +4.4179709E-05$
 $S_t = +4.3012281E-02$

DEGREES OF FREEDOM = 1291

SIGNIFICANCE OF R = SIGNIFICANT

SIGNIFICANCE OF T = SIGNIFICANT

SIGNIFICANCE OF Y = SIGNIFICANT

TEST CONDITIONS = AMB TEMP/RH

UNIT OF MEASURE = IN/IN

PARAMETER = STRAIN AT RUPTURE




Figure 8

$F = +2.2571568E+01$
 $R = -1.3108530E-01$
 $t = +4.7509545E+00$
 $N = 1293$
 $F = SIGNIFICANCE OF$
 $R = SIGNIFICANCE OF$
 $t = SIGNIFICANCE OF$
 $DGREES OF FREEDOM = 1291$
 $STORAGE CONDITIONS = AMB TEMP/RH$


PARAMETER = STRESS AT RUPTURE
 UNIT OF MEASURE = PSI
 *10¹
 0.00 4.00 8.00 12.00 16.00 20.00 24.00 28.00 32.00

- 15 -

TENSILE STRESS AT RUPTURE, CHS=1750.0 IN/MIN, TP-H1043, WINGS 2 & 6

Figure 9

$\gamma = ((+4.4487897E+03) + (+2.4621513E+01) * X) / 1291$
 $F = +1.0006043E+02$ SIGNIFICANT OF F
 $R = +2.6819964E-01$ SIGNIFICANT OF R
 $\zeta = +1.0003021E+01$ SIGNIFICANT OF ζ
 $N = 1293$ DEGREES OF FREEDOM = 1291
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH



TENSILE MODULUS, CHS=1750.0 IN/MIN, TP-H1043, WINGS 2 & 6

Figure 10

*** SAMPLE SIZE SUMMARY ***

AGE MONTHS	NR SAMPLES	AGE MONTHS	NR SAMPLES	AGE MONTHS	NR SAMPLES	AGE MONTHS	NR SAMPLES
56.0	5	92.0	9	120.0	20	148.0	15
58.0	5	93.0	6	121.0	40	149.0	9
59.0	10	94.0	11	123.0	20	150.0	5
60.0	5	95.0	6	124.0	13	151.0	5
61.0	15	96.0	3	126.0	6	152.0	5
62.0	10	98.0	1	127.0	3	153.0	5
63.0	10	99.0	1	128.0	12	155.0	5
64.0	10	101.0	10	130.0	6	156.0	10
65.0	10	102.0	11	131.0	6	158.0	25
66.0	10	103.0	15	132.0	9	159.0	5
67.0	11	105.0	10	133.0	15	160.0	5
68.0	5	106.0	5	134.0	9	161.0	15
78.0	2	107.0	20	135.0	12	163.0	5
80.0	4	108.0	30	136.0	6	164.0	5
81.0	1	109.0	35	137.0	21	165.0	10
82.0	14	110.0	40	138.0	3	166.0	25
83.0	16	111.0	25	139.0	9	167.0	10
84.0	25	112.0	35	140.0	15	168.0	15
85.0	32	113.0	35	141.0	9	169.0	5
86.0	19	114.0	35	142.0	18	170.0	10
87.0	21	115.0	30	143.0	12	171.0	15
88.0	22	116.0	20	144.0	8	173.0	10
89.0	28	117.0	15	145.0	16	174.0	5
90.0	14	118.0	40	146.0	18		
91.0	13	119.0	10	147.0	3		

WING 2-6 HARDNESS SHORE A 10 SECOND TP/H1043 PROPELLANT

This sample size summary applies to Figures 11 and 12

$\gamma = ((+8.5152877E+01) + (-7.1012327E-03) * X)$
 $F = +1.0647380E+01$ SIGNIFICANT OF F = SIGNIFICANT
 $R = -8.9926283E-02$ SIGNIFICANCE OF R = SIGNIFICANT
 $t = +3.2630323E+00$ SIGNIFICANCE OF t = SIGNIFICANT
 $N = 1308$ DEGREES OF FREEDOM = 1306
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH




Figure 11

$F = +3.2969393E-02$
 $R = +5.0243329E-03$
 $t = +1.8157476E-01$
 $N = 1308$
 Y = $((+7.7547546E+01) + (+5.0149942E-04)) * X$
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF t = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 1306
 STORAGE CONDITIONS = AMB TEMP/RH
 TEST CONDITIONS = AMB TEMP/RH

UNIT OF MEASURE = SHORE A
 PARAMETER = 10 SECOND HARDNESS
 68.00 72.00 76.00 80.00 84.00 88.00




Figure 12

*** SAMPLE SIZE SUMMARY ***

AGE MONTHS	NR SAMPLES	AGE MONTHS	NR SAMPLES	AGE MONTHS	NR SAMPLES	AGE MONTHS	NR SAMPLES
56.0	5	92.0	2	120.0	20	148.0	15
58.0	5	93.0	4	121.0	40	149.0	9
59.0	10	94.0	7	123.0	20	150.0	5
60.0	5	95.0	4	124.0	15	151.0	5
61.0	15	96.0	3	126.0	6	152.0	5
62.0	10	98.0	1	127.0	3	153.0	5
63.0	10	99.0	1	128.0	12	155.0	5
64.0	10	101.0	10	130.0	6	156.0	10
65.0	10	102.0	11	131.0	6	158.0	30
66.0	10	103.0	15	132.0	9	159.0	5
67.0	11	105.0	10	133.0	15	160.0	5
68.0	5	106.0	5	134.0	9	161.0	15
78.0	2	107.0	20	135.0	12	163.0	5
80.0	4	108.0	30	136.0	6	164.0	5
81.0	1	109.0	35	137.0	21	165.0	10
82.0	14	110.0	40	138.0	3	166.0	25
83.0	16	111.0	25	139.0	9	167.0	10
84.0	25	112.0	35	140.0	15	168.0	15
85.0	32	113.0	35	141.0	9	169.0	5
86.0	19	114.0	35	142.0	18	170.0	10
87.0	21	115.0	30	143.0	12	171.0	15
88.0	22	116.0	20	144.0	8	173.0	10
89.0	25	117.0	15	145.0	16	174.0	5
90.0	13	118.0	40	146.0	18		
91.0	11	119.0	10	147.0	3		

WING 2-6 HARDNESS SHORE C 10 SECOND TP/H1043 PROPELLANT

This sample size summary applies to Figures 13 and 14




Figure 13

$\gamma = ((+3.4165867E+01) + (+3.7264669E-03) * X) * \sigma_t$
 $F = +1.0927652E+00$ SIGNIFICANT OF F = NOT SIGNIFICANT
 $R = +2.9070238E-02$ SIGNIFICANCE OF R = NOT SIGNIFICANT
 $t = +1.0453541E+00$ SIGNIFICANCE OF t = NOT SIGNIFICANT
 $N = 1294$ DEGREES OF FREEDOM = 1292
 STORAGE CONDITIONS = AMB TEMP/RH TEST CONDITIONS = AMB TEMP/RH

PARAMETER = 10 SECOND HARDNESS
 UNIT OF MEASURE = SHORE C
 0.00 28.00 33.00 38.00 43.00 48.00

WING 246 HARNESS SHORE C 10 SECOND TP-H1043 PROPELLANT




Figure 14

DISTRIBUTION

	NR <u>COPIES</u>
OOALC	1
MMWRME	1
MMWRMT	1
DDC (TISIR) Cameron Station, Alexandria, VA 22314	2
SAMSO, Norton AFB, CA 92409	1
MNNP	1
TRW Systems, Norton AFB, CA 92409	1
Attn: Mr. J. C. Metcalf, Bldg 523/315	1
AFPRO, Thiokol Chemical Corporation	2
Wasatch Division	
P. O. Box 524	
Brigham City, Utah 84302	
(Cy to R. E. Keating)	
AFRPL (MKPB) Edwards AFB, CA 93523	1
SAC (LGMB) Offutt AFB, NB 68113	1
U. S. Naval Ordnance Station, Indian Head, MA 20640	1
Attn: Dr. James H. Wiegand	
Fleet Support Dept., Propulsion	
System Development Division, Code FS7	
CPIA, Applied Physics Laboratory	1
John Hopkins University	
Johns Hopkins Road	
Laurel, MD 20810	
Attn: Dr. Pl L. Nichols	
Naval Plant Branch Representative	
Attn: Mr. David W. Pratt	
P.O. Box 157	
Bacchus Works	
Magna, Utah 84044	

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 14 MANCP [REDACTED] -385 (77)	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) 6 Propellant Surveillance Report LGM-30A, B, F and G Stage I TP-H1043 Aft Closure Propellant.	5. TYPE OF REPORT & PERIOD COVERED 9 Test Results - Semi Annual rpt.	6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) 10 John A. Thompson	8. CONTRACT OR GRANT NUMBER(s)	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Propellant Lab Section Directorate of Maintenance Hill AFB, UT 84406	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS	
11. CONTROLLING OFFICE NAME AND ADDRESS Service Engineering Division Directorate of Materiel Management Hill AFB, UT 84406	12. REPORT DATE 11 Dec [REDACTED] 77	13. NUMBER OF PAGES 12 32 p. 25
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release, Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Solid Propellant Minuteman Aft Closure		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) This report contains propellant test results from cartons of TP-H1043 propellant representing selected batches used in the aft closure of First Stage-Minuteman Motors. Data from TP-H1043 propellant obtained from the aft closures of the LGM-30A, B, F and G Motors are reported in regression analyses for the fourth time and the third time using the GO-85 computer system. Testing was accomplished in accordance with MMWRME Projects M82937C and M82938C. An analysis of all parameters indicate that no significant degradation is		

407387

[Signature]

anticipated for at least two years past the oldest data point.

Each point on the regression plot represents all samples at that particular age. The number of samples at each point is indicated on the sample size summary sheet on the page accompanying each regression plot. The data range at any age can be found by suitable inquiry of the GO-85 system.

A