

AD-A050 571

NAVAL RESEARCH LAB WASHINGTON D C F/G 21/4
CAN PYROPHORIC MATERIALS FORM IN OIL TANKERS WITH INERT GAS FIR--ETC(U)
DEC 77 W A AFFENS
NRL-MR-3678 SBIE-AD-E000 106 NL

UNCLASSIFIED

1 of 1
AD
A050671



END
DATE
FILMED
3 - 78
DDC

12

ade000106

NRL Memorandum Report 3678

AD A 050571

Can Pyrophoric Materials Form in Oil Tankers with Inert Gas Fire Protection Systems?

W. A. AFFENS

*Combustion and Fuels Branch
Chemistry Division*

December 1977

AD No. _____
DDC FILE COPY



DDC
RECEIVED
MAR 1 1978
B

NAVAL RESEARCH LABORATORY
Washington, D.C.

Approved for public release; distribution unlimited.

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER NRL Memorandum Report 3678	2. REPORT ACCESSION NO. NRL-MR	3. RECIPIENT'S CATALOG NUMBER 9	
4. TITLE (and Subtitle) CAN PYROPHORIC MATERIALS FORM IN OIL TANKERS WITH INERT GAS FIRE PROTECTION SYSTEMS?		5. TYPE OF REPORT & PERIOD COVERED Final report on one phase of an NRL problem.	
7. AUTHOR(s) W. A. Affens		6. PERFORMING ORG. REPORT NUMBER	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Naval Research Laboratory Washington, D. C. 20375		8. CONTRACT OR GRANT NUMBER(s)	
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Coast Guard (G-MMT-4/82) Washington, D. C. 20590		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NRL Problem C01-03A	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) 12-14 p.		13. REPORT DATE 11 December 1977	
		13. NUMBER OF PAGES 13	
		15. SECURITY CLASS. (of this report) UNCLASSIFIED	
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) <div style="border: 1px solid black; padding: 5px; text-align: center;"> DISTRIBUTION STATEMENT A Approved for public release; Distribution Unlimited </div>			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) <div style="border: 1px solid black; padding: 5px; display: inline-block;"> 18 SBIE </div> <div style="float: right; text-align: center;"> DDC RECEIVED MAR 1 1978 REGULATIVE B </div>			
18. SUPPLEMENTARY NOTES <div style="border: 1px solid black; padding: 5px; display: inline-block;"> 19 ADE QQQ # 106 </div>			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Pyrophoric Ignition Inert gas systems Oil tankers Flue gas inerting Flammable gases Crude oil			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A literature study and analysis was made concerning the potential hazard of pyrophoric ignition of flammable vapors in oil tankers with inert gas systems (IGS). Only two pyrophor possibilities seem to be likely: Formation of ferrous sulfide (FeS) and/or ferrous oxide (FeO). Both FeS and FeO may be formed in an oxygen limited atmosphere, such as would be the case with a flue gas IGS. Formation of FeS also requires an atmosphere containing hydrogen sulfide (H ₂ S), as would be the condition with 'sour' crudes, so that the hazard of the formation of (Continues) → over			

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

251 950

Handwritten signature

20. Abstract (Continued)

pyrophoric FeS must be considered for such crudes. Furthermore, if sea water is present in the oil tank, oils which do not contain H_2S can become "sour" by the action of sulfate reducing bacteria on sulfates in the water. It is concluded that in the event of failure of an IGS system, the ullage space should not be exposed to air suddenly.



DISTRIBUTION STATEMENT A
Approved for public release
Distribution Code 000

REGISTRATION
MAR 2 1978
B

CONTENTS

INTRODUCTION..... 1
INERT GAS SYSTEMS (IGS)..... 1
PYROPHORIC MATERIALS..... 2
PYROPHORIC MATERIALS IN OIL TANKS?..... 2
PYROPHORIC IRON SULFIDE..... 3
PYROPHORIC IRON OXIDE..... 4
PYROPHORIC MATERIALS AND INERT GAS SYSTEMS..... 4
OTHER CONSIDERATIONS..... 5
SUMMARY AND CONCLUSIONS..... 6
REFERENCES..... 7
TABLE I.....10

ACCESSION for		
NTIS	White Section	<input checked="" type="checkbox"/>
DDC	Buff Section	<input type="checkbox"/>
UNANNOUNCED		<input type="checkbox"/>
JUSTIFICATION _____		
BY _____		
DISTRIBUTION/AVAILABILITY CODES		
Dist.	AVAIL.	and/or SPECIAL
A		

CAN PYROPHORIC MATERIALS FORM IN OIL TANKERS WITH INERT GAS FIRE PROTECTION SYSTEMS?

INTRODUCTION

The U. S. Coast Guard has under consideration a proposal to require inert gas systems (IGS) for fire protection on certain vessels which carry crude oil and similar flammable cargoes (1). Questions have been raised, however, concerning possible problems which may arise if IGS are used. In this regard, NRL has been requested to address some of the potential problems. This report is concerned with one of the problems, namely, the likelihood of formation of pyrophoric materials. This is important because pyrophors, under certain conditions, might ignite the flammable vapors, a phenomena which the IGS is intended to prevent. NRL has made a literature study and analysis to determine whether the use of IGS on tank vessels might contribute to the formation of pyrophors.

INERT GAS SYSTEMS (IGS)

In order for a fire to occur in a tanker, there must be a proper proportion of fuel vapor and oxidizers (most commonly oxygen in air), and a suitable ignition source. There are, therefore, three options for fire prevention on a tanker with flammable liquid cargoes: (a) remove the flammable vapors ("gas-freeing"), (b) remove the oxygen or lower its concentration below that required to propagate a flame ("inerting"), or, (c) eliminate all possible sources of ignition. Experience has shown that it is not always possible to eliminate or control the wide variety of potential ignition sources (flames, electric sparks, hot surfaces, static electricity, etc.) which can be present on tankers. Since gas-freeing is not usually feasible, and sometimes introduces its own hazards (2), a combination of b and c (above) is frequently used for fire prevention purposes on oil tankers.

It is not the purpose of this report to analyze the relative efficiencies of the three fire prevention methods, nor to go into detail concerning inerting systems except as they might influence the formation of pyrophoric materials. Rather, the purpose is to address the question: can pyrophoric materials form in oil tankers with IGS?

Note: Manuscript submitted December 7, 1977.

IGS have been in widespread use for many years to reduce the risk of explosion in cargo tanks of oil carriers (3-6). The function of an inert gas, such as nitrogen, carbon dioxide, etc., is to reduce the oxygen concentration below its limit of about 11% for combustion of hydrocarbon vapors (7). Most IGS use flue gas from the ship's boiler for inerting, after first removing most of the undesirable constituents, such as SO_2 , by scrubbing through a sea water scrubber. The composition of the resulting scrubbed flue gas varies depending on the fuel and other factors, but a range of reported compositions is shown in Table I (3-6). The chief constituents are nitrogen, carbon dioxide, and oxygen. Note that the oxygen concentration is well below the limit of about 11%. In general, the oxygen concentration is below 6%. The question now arises as to whether such an atmosphere (oxygen lean) would enhance the formation of pyrophoric materials.

PYROPHORIC MATERIALS

Pyrophoric is derived from "pyro" (fire) + "phor" (carry) and literally means "fire bearing" (8). It refers to any substance which will ignite spontaneously on exposure to air (8-11). Certain metals, such as thorium, cerium, zirconium, titanium, magnesium and their alloys are particularly effective in emitting sparks as a result of friction and are referred to as "pyrophoric metals" or "pyrophoric alloys" (12-14). The sparks, which are the result of spontaneous ignition of the fragmented particles burning in air, are capable of igniting a flammable gas mixture, such as is the case with a cigarette-lighter flint (misch metal). Some pyrophoric materials, however, may ignite spontaneously on exposure to air and do not require fragmentation by abrasion or friction for ignition to occur. These include phosphorous; hydrides of phosphorus, boron, silicon, and lithium; cacodyl; zinc dimethyl; and finely divided metals such as iron, magnesium, aluminum, uranium, lead, nickel, cobalt, and bismuth (8, 15); and two ferrous compounds: FeO (15, 16, 18) and FeS (15-19).

PYROPHORIC MATERIALS IN OIL TANKS?

The question is now raised: Of the wide variety of pyrophors which have been mentioned, is it likely that any of these might be present in an oil tank? The answer to this question would appear to be negative, with the possible exceptions of FeS and FeO . Tank linings consist of iron, or

zinc-coated iron (14), and various stages of iron rust. Iron as such is not pyrophoric (except in a very finely divided state) (15), nor is zinc metal (14). It would not be likely that either the oil cargo or the flue gas would contain any of the above mentioned pyrophors. Could there be a reaction between the walls of the tank and/or other constituents of the oil and/or the flue gas which might contribute to the formation of pyrophors? Since the most likely pyrophor possibilities in a tanker would be FeS and/or FeO, could these be formed in the tank by chemical reactions between two or more of the components which are likely to be present? If so, might the flue gas enhance such a reaction even if it does not take part?


PYROPHORIC IRON SULFIDE

Ferrous sulfide (FeS) has been known to be pyrophoric since it was reported by Berzelius in 1826 (15, 17). When pyrophoric FeS is exposed to air it may ignite spontaneously with the evolution of considerable heat. If flammable vapors are present, a fire may occur. This hazard has been known to a wide variety of industries. For example, when Town gas is treated with $\text{Fe}(\text{OH})_2$ to remove H_2S ("sweetening"), FeS is formed. It is necessary to take precautions to avoid auto ignition of the FeS (20), e.g., preventing sudden exposure to air. Similar hazards are known to the chemical industry where FeS may accumulate in catalyst beds in hydrotreating processes (21). In the petroleum industry, hydrogen sulfide from "sour crudes" (crude oil containing H_2S) have been known to react with rust scale in pipe lines, drilling equipment, and other machinery to form pyrophoric FeS. Pyrophoric FeS has been known to have caused ignitions of flammable vapors in oil wells and pipe lines (22-24).


Directly related to the Coast Guard problem are studies by the American Petroleum Institute (API) (25,26) and recent work at the Shell Thornton Research Centre in Chester, England (17,18). These studies expressed concern with the hazard of formation of pyrophoric FeS in tankers containing sour crudes and the subsequent ignition of flammable vapors.

The Shell work was a detailed laboratory study and analysis of the problem and included studies of the reactivity of FeS as a function of the type of iron oxide from which it is derived. They concluded that it is quite possible for pyrophoric FeS to be formed in the ullage space of an oil tank containing sour crude, and that ignition from this type of material may be the solution to many unexplained oil tanker explosions.

The reaction of iron rust with H₂S (ignoring hydration effects) is represented in the Shell papers (17,18) by the following equation:



The oxidation of FeS in air regenerates the Fe₂O₃ with considerable heat (17,18):



In connection with the Coast Guard problem, an extensive search of the chemical literature has been made, and it is clear that FeS is the prime candidate for consideration of all the possible pyrophoric materials which might exist or be formed in an oil tank. The formation of FeS from rust scale, however, does require the presence of H₂S, and an atmosphere with a limited supply of oxygen such as would be the case when inerting with flue gases (18).

PYROPHORIC IRON OXIDE

Another pyrophoric compound which could be present in an oil tanker under certain conditions is ferrous oxide (or hydroxide when moisture is present). Pyrophoric FeO can be prepared in the laboratory by treatment of iron with steam at 350° C in a limited oxygen atmosphere, or by other methods (15). It has been cited as a possible pyrophor which might be formed under the top surface of iron rust scale in an atmosphere of flue gas (16,18). FeO/Fe(OH)₂ have been shown to be pyrophoric and are known to oxidize readily in air at room temperature (15). On sudden exposure to air they can ignite spontaneously (15,16). The hazard of ignition of flammable vapors by pyrophoric FeO is considered to be a real possibility (16,18).

As has been mentioned, considerable knowledge has been accumulated concerning pyrophoric FeS, but this is not the case with pyrophoric FeO, particularly as concerned with its possible formation in oil tanks. The potential hazard of pyrophoric FeO in inerted oil tanks is based on deduction from its known properties, but this hazard has not been investigated specifically. More research is needed on this pyrophoric material.

PYROPHORIC MATERIALS AND INERT GAS SYSTEMS

In the discussions so far it has been seen that the chief influence of inert gas systems in the formation of pyrophors is that they maintain a limited oxygen supply.

This is conducive to the formation of pyrophoric FeS (in the presence of sour crudes) and FeO or Fe(OH)₂. The question still remains, however, whether any of the components of the flue gas might contribute to the formation of pyrophors in some other manner. The components of scrubbed flue gas are derived from the end products of the oxidation (burning) of ships fuels and consist chiefly of nitrogen, CO₂, oxygen, and water vapor with lesser concentrations of SO₂, SO₃, and CO as shown in Table I. At temperatures which are likely to prevail in an oil tank, it does not appear that there are any probable reactions with the iron or rust scale of the tank walls which might form a pyrophor beyond the FeS or FeO (15) previously mentioned. There are some references in the literature to reactions of iron oxides with sulfur dioxide or carbon dioxide which might conceivably lead to the formation of FeS or FeO, but these reactions can only occur at elevated temperatures (15).

OTHER CONSIDERATIONS

There are two other considerations which are related to this problem. The first concerns a potential ignition hazard which may result from flue gas inerting which should be mentioned, even though it is outside the scope of this report - that of static electricity. Recent research has shown that charged particles and mist droplets from scrubbed flue gas can generate appreciable electrostatic charges which would be more than sufficient to ignite flammable hydrocarbon vapors if discharged as an electric spark (27). The hazard of static electricity must be considered, even in inert gas systems, whether the static build up is from the charged droplets in mists or particulate matter, or from tank washing or other reasons (6, 27-29). In normal operations, of course, the inerting will prevent the formation of flammable atmospheres, but in case of failure of the IGS and the introduction of air, potential hazards due to static electricity may arise (27).

The second consideration concerns a possible source of H₂S from sea water. Oils which do not contain H₂S can turn "sour" by the action of microorganisms. The Navy has experienced problems with fuel contamination in fuel tanks ballasted with sea water (30). Sulfate reducing bacteria reduce the sulfate in sea water and form sulfide as the reduced product (30). This sulfide, as H₂S, turns the fuel "sour" and makes it corrosive to metals. Iron sulfide has been shown to form in the linings of fuel tanks by this means (30). Since there is likely to be sea water present in the cargo space of oil tankers, the formation of sour fuel and pyrophoric iron sulfide from the action of sulfate reducing bacteria should not be ignored.

SUMMARY AND CONCLUSIONS

A literature study and analysis has been made concerning pyrophoric ignition with particular attention to pyrophoric materials which might be present in oil tankers inerted by flue gas.

Only two pyrophors are likely to be present in an inerted tanker - FeS (if H₂S is present) and FeO.

Based on recent studies at the Thornton Laboratories in Chester, England (17, 18), there does appear to be a possibility that pyrophoric FeS or FeO may be generated in oxygen-limited atmospheres, such as in a tanker inerted by flue gas. Research is needed concerning the probability of formation of pyrophoric FeO in inerted tank systems.

If for some reason the inerting system should fail, and if the walls of the tank were suddenly exposed to air, it is quite possible that the pyrophoric material might ignite spontaneously and in turn ignite the flammable vapors in the tank. For these reasons, if the ullage space in an inerted tank is to be exposed to air, this should be done gradually so that the pyrophors might be oxidized slowly and hence their pyrophoricity eliminated.

REFERENCES

- (1) Federal Register, Monday, May 16, 1977, Part II, page 24874.
- (2) The Secretary of the Treasury's Committee on Tanker Hazards, Final Report to the Secretary of the Treasury, U. S. Coast Guard, 14 August 1963.
- (3) A. E. Stanford, "What Inert-Gas Systems Mean to a Marine Operator", Soc. of Naval Architects and Marine Engineers, Annual Meeting, New York, N. Y., November 14-15, 1963.
- (4) Shipping World and Shipbuilder, "Explosions in Tankers", 421-424, March 1970.
- (5) W. O. Willey, "Tank Cleaning", Safety at Sea International, 17-29, September 1972.
- (6) R. I. Bass, T. E. Owen, and F. T. Dodge, "Bulk Carrier Operations Safety Enhancement Project", Phase 1 Final Report, Southwest Research Institute, San Antonio, Texas, June 1976.
- (7) H. F. Coward and G. W. Jones, "Limits of Flammability of Gases and Vapors", Bureau of Mines, Bulletin No. 503, 1952.
- (8) Thorpe's Dictionary of Applied Chemistry, Longmans, Green and Co., London, 4th Ed., 1950, Volume X, 327-329.
- (9) C. A. Hampel and G. G. Hawley, "Glossary of Chemical Terms", Van Nostrand Reinhold, New York, 1976.
- (10) L. M. Miall, "A New Dictionary of Chemistry", Interscience New York, 1961.
- (11) D. H. Hey (Ed.) Kingzett's Chemical Encyclopedia, D. Van Nostrand, Princeton, N. J., 9th Ed., 1967.
- (12) R. B. Smith, "Pyrophoricity - A Technical Mystery Under Vigorous Attack", Nucleonics, 14, 28 December 1956.
- (13) C. R. Schmitt, "Pyrophoric Materials - A Literature Review", J. Fire and Flammability, 2, 1957 (1971).
- (14) W. A. Affens and E. A. Lange, "Ignition of Flammable Gases in Crude-Oil Tankers as a Result of Metal Fracture", NRL Report 8013, June 29, 1976. (AD A027411)
- (15) J. W. Mellor, "A Comprehensive Treatise on Inorganic and Theoretical Chemistry", Longmans, Green, London, 1922-1937.

- (16) A. Bell, "Corrosion and Fires in Marine Boiler Air Pre-heaters", Trans. Inst. Marine Engineers, 72, 309 (1960).
- (17) R. I. Hughes, T. D. B. Morgan and R. W. Wilson, "Is Pyrophoric Iron Sulphide a Possible Source of Ignition?". Nature, 248, 670 (1974).
- (18) R. I. Hughes, T. D. B. Morgan and R. W. Wilson, "The Generation of Pyrophoric Material in the Cargo Tanks of Crude Oil Carriers", Trans. Inst. Marine Engineers, 88 153 (1976).
- (19) R. H. Griffith and A. R. Morcom, "The Interconversion of Iron Oxides and Sulphides", J. Chem. Soc., 148, 786 (1945).
- (20) L. Shnidman (Ed.), "Gaseous Fuels", Amer. Gas Assoc., New York, 2nd Ed., 1954, pp. 82-84; 234.
- (21) L. M. Lovell, "Stabilizing Pyrophoric Materials in a Catalyst Bed", U. S. Patent 3,838,066, 24 Sept. 1974; Chem. Abstracts 82, No. 88374B (1975).
- (22) I. G. Zakirov, M. G. Gazimov, K. M. Kadeev, K. I. Makh'yanova and E. Z. Farrakhov (USSR), "Production of Petroleum Containing Hydrogen Sulfide", Bezop. Tr. Promsti, 18, 42 (1974) (Russ), Chem. Abst. 83, p. 16, No. 149883m, (1975).
- (23) K. I. Makh'yanova, M. G. Gazimov, E. Z. Farrakhov, I. G. Zakirov and R. G. Abdulkhairova, "Neutralization of Pyrophoric Formations", (Tartar. Nauchno-Issled Inst., USSR) Nefte Prom. Neftepromysl. Delo 9, 61 (1974) (Russ.) Chem. Abst. 82, No. 88255p (1975).
- (24) R. M. Khasaev, A. S. Agaev, L. L. Obukhova and T. G. Sil'vestrova (USSR), "Effect of Hydrodynamic Conditions in Wells on the Activity of Pyrophoric Formations", (Vses. Nauchno-Issled Inst. Tekh. Bezop. Nefte Prom., USSR), Neftprom. Delo 5, 36 (1973) (Russ.); Chem. Abst. 79, p. 68, No. 116747j (1973).
- (25) American Petroleum Institute, Washington, D. C., Interim Report, Tanker Accident Study Group, November 1970.
- (26) Ibid., November 1971.
- (27) International Chamber of Shipping, London, "Tanker Safety: Static Electricity and Inert Gas," ICS(76)78, 30 July 1976.

- (28) The Motor Ship, "Prevention of Explosions in Tankers - Electrostatic Charge Generation in Supertankers and the Final Report of I.C.S.", March 1976, p. 119.
- (29) Ibid, "Reduction of Static Electricity in Cargo or Ballast Tanks", p. 123.
- (30) R. N. Hazlett, "Control of Sulfate Reducing Bacteria in Navy Fuel Systems," NRL Memorandum Report 1737, December 28, 1966. (AD 805N30L)

TABLE I
COMPOSITION OF SCRUBBED FLUE GAS (3-6)

<u>CONSTITUENT</u>	<u>RANGE</u> <u>% v/v</u>
N ₂	75 - 85
CO ₂	11 - 15
O ₂	2 - 8
H ₂ O (vapor)	.0.8 - 8
SO ₂	0.02 - 0.11
SO ₃	Trace
CO	0.1