

AD-A052 336

HUGHES RESEARCH LABS MALIBU CALIF
DOUBLE DOPED RAP FLUORIDES. (U)
MAR 78 M ROBINSON

F/G 7/2

UNCLASSIFIED

N00014-78-C-0203
NL

| OF |
AD
A052336



END
DATE
FILMED
5-78
DDC

13

SC

ADA 052336

DOUBLE DOPED RAP FLUORIDES

M. Robinson
Hughes Research Laboratories
3011 Malibu Canyon Road
Malibu, CA 90265

March 1978

N00014-78-C-0203
Contract Final Report
20 December 1977 through 15 February 1978

Approved for public release; distribution unlimited.

Prepared for
OFFICE OF NAVAL RESEARCH
Department of the Navy
800 N. Quincy Street
Arlington, VA 22217

AD No.
DDC FILE COPY

DDC
RECEIVED
APR 3 1978
RECEIVED
F

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) DOUBLE DOPED RAP FLUORIDES		5. TYPE OF REPORT & PERIOD COVERED Final Report 20 Dec 77 - 15 Feb 78
6. AUTHOR M. Robinson		7. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Hughes Research Laboratories 3011 Malibu Canyon Road Malibu, CA 90265		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy 800 N. Quincy St. Arlington, VA 22217		12. REPORT DATE Mar 78
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES 8 P1
		15. SECURITY CLASS. (of this report) UNCLASSIFIED
16. DISTRIBUTION STATEMENT (of this Report)		15a. DECLASSIFICATION DOWNGRADING SCHEDULE
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) Approved for public release; distribution unlimited		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Double Doped, RAP, Hydrogen Fluoride, Czolhralski, Calcium Fluoride, Strontium Fluoride		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Single crystals of calcium fluoride and strontium fluoride double doped with Na ⁺ and Ce ³⁺ were czochralski grown using RAP (HF) to maximize anion purity.		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

172 600

slf

TABLE OF CONTENTS

SECTION		PAGE
1	INTRODUCTION	1
2	EQUIPMENT AND MATERIALS	2
	A. Equipment	2
	B. Materials	2
3	EXPERIMENTAL	3
	A. Melt Preparation and Discussion	3
	B. Crystal Growth	3

ACCESSION for	
NTIS	Write Section <input checked="" type="checkbox"/>
DDC	B. Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION _____	
BY _____	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	SPECIAL
A	✓

SECTION 1

INTRODUCTION

The objective of this program is the production of single crystals of calcium fluoride (CaF_2) and strontium fluoride (SrF_2), both double doped with Na^+ and Ce^{3+} . The crystals were grown by the Czochralski method utilizing hydrogen fluoride (HF) RAP to maximize anion purity.

SECTION 2
EQUIPMENT AND MATERIALS

A. EQUIPMENT

1. Astro Industries graphite resistance furnace with stainless steel shell

B. MATERIALS

1. HF - Matheson 99.9%
2. Helium (He) - Airco 99.995%
3. CaF₂ EM Labs 99.999%
4. SrF₂ EM Labs 99.999%
5. CeF₃ Research Chemicals 99.99%
6. NaF MCB Reagent grade
7. Vitreous carbon crucibles from Beckwith Corporation

SECTION 3
EXPERIMENTAL

A. MELT PREPARATION AND DISCUSSION

The host material and its dopants, all in powder form, were contained in a 50-mm diameter vitreous carbon crucible and situated at the top of the furnace hot zone. The furnace was evacuated with a roughing pump and the temperature was increased slowly to 600°C for outgassing. The furnace was then backfilled with He and a flow of 1 LPM was initiated. The temperature was then raised slowly to approximately 100°C higher than the pulling temperature (Tables 1 and 2). During this slow temperature rise the dopants diffuse into the host lattice to form a solid solution. This decreases the volatility of NaF and its reactivity to HF. At this point the melt is ready for an HF atmosphere and a minimum loss of NaF is ensured. The preliminary He melting step is important, because previous work at HRL has shown that losses from the crucible were high when pure NaF was melted in an HF atmosphere. HF reacts to form NaHF_2 , which is readily vapor-transported to the cold portions of the furnace. However, when NaF can first be dissolved in the host in the absence of RAP, as described above, subsequent meltings in HF do not promote sodium loss.

B. CRYSTAL GROWTH

After the first He melting the atmosphere is adjusted by flow-rate manipulation to give 90% He and 10% HF. The melt is allowed to see this atmosphere for 4 hours before the start of crystal growth.

Growth is spontaneously nucleated on a 3 mm platinum rod and a steady state growth rate of 9.5 mm-hr^{-1} is enforced. At the end of the run the crystal is withdrawn from the melt rapidly and the furnace is allowed to cool to room temperature.

Table 1. Crystal Growth Conditions and Results for
Double Doped CaF₂

Processing Data: ATMOSPHERE - 90% He - 10% HF
 PULLING TEMPERATURE ~ 1450°C
 PULL RATE - 9.5 mm-hr⁻¹
 ROTATION RATE - 29 R.P.M.
 COOL DOWN - 2 Hrs.

	Mole % CaF ₂	CeF ₃	NaF	Starting Weight (g)	Crystal Weight (g)	Residue (g)	Wt. Loss (g)
Prep 1*	99.8835	0.0104	0.1060				
1478	-	-	-	170.76	7.20	-	-
Prep 2	99.8845	0.0110	0.1046				
1978	-	-	-	170.90	13.2	157.45	0.18
1478	-	-	-	157.45	5.17	151.93	0.35
Prep 3	99.8722	0.022	0.1059				
11678	-	-	-	175.28	4.16	170.87	0.25
11978	-	-	-	170.87	14.64	156.16	0.32

*Prep. 1 consists of a boule grown from CaF₂ chunks instead of powder, with ends polished for spectroscopic examination. This is a complimentary crystal.

Table 2. Crystal Growth Conditions and Results for
Double Doped SrF₂

Processing Data: ATMOSPHERE - 90% He - 10% HF
 PULLING TEMPERATURE ~ 1500°C
 PULL RATE - 9.5 mm-hr⁻¹
 ROTATION RATE - 29 R.P.M.
 COOL DOWN - 2 Hrs.

	Mole % SrF ₂	CeF ₃	NaF	Starting Weight (g)	Crystal Weight (g)	Residue (g)	Wt. Loss (g)
Prep. 4	99.8882	0.0107	0.1012				
12078*	-	-	-	213.71	1.92	211.79	0
12378	-	-	-	211.79	19.25	192.24	0.30
12478	-	-	-	191.96	8.10	183.64	0.22
Prep. 5	99.8925	0.0063	0.1013				
2678**	-	-	-	243.00	20.74	221.91	0.35
2778	-	-	-	221.91	16.60	204.96	0.35
2978***	-	-	-	204.96	17.64	187.04	0.28

* Growth run 12078, was aborted due to equipment malfunction.

** For growth run 2678, crystal diameter was considered too irregular for delivery. However, the crystal was delivered and should be considered complimentary.

*** Cooldown on crystal 2978 was as follows: Cooled to ~ 300°C below melting point in 16 hours. Then, cooled to room temperature in 2 hours.