

AD-A066 706

ARMY MOBILITY EQUIPMENT RESEARCH AND DEVELOPMENT COMM--ETC F/6 11/7
DEVELOPMENT OF AN ANTIFREEZE EXTENDER AND WATER INHIBITOR FOR A--ETC(U)
DEC 78 J H CONLEY, R G JAMISON

UNCLASSIFIED

NERADCON-2265

NL

1 OF 1
AD
A066706



END
DATE
FILMED
5-79
DDC

AD AO 66706

DDC FILE COPY



13



AD

Report 2265

LEVEL II

DEVELOPMENT OF AN ANTIFREEZE EXTENDER AND WATER INHIBITOR FOR AUTOMOTIVE COOLING SYSTEMS

by James H. Conley and Robert G. Jamison

DDC REPRINT APR 2 1979

December 1978

Approved for public release; distribution unlimited.

U.S. ARMY MOBILITY EQUIPMENT RESEARCH AND DEVELOPMENT COMMAND FORT BELVOIR, VIRGINIA

79 04 02 040

**Destroy this report when it is no longer needed.
Do not return it to the originator.**

**The citation in this report of trade names of commercially
available products does not constitute official endorsement
or approval of the use of such products.**

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 2265	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
6 (4) DEVELOPMENT OF AN ANTIFREEZE EXTENDER AND WATER INHIBITOR FOR AUTOMOTIVE COOLING SYSTEMS -		5. TYPE OF REPORT & PERIOD COVERED 9 Final Report
7. AUTHOR(s) 10 James H. Conley Robert G. Jamison		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Fuels and Lubricants Div, DRDME-GL; Energy and Water Resources Lab; U.S. Army Mobility Equipment Research and Development Command; Fort Belvoir, Virginia 22060		8. CONTRACT OR GRANT NUMBER(s) 12 16p.
11. CONTROLLING OFFICE NAME AND ADDRESS Fuels and Lubricants Div, DRDME-GL; Energy and Water Resources Lab; U.S. Army Mobility Equipment Research and Development Command; Fort Belvoir, Virginia 22060		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 16 1L762733AH20
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) 14 MERADCOM-2265		11. REPORT DATE 11 December 1978
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		13. NUMBER OF PAGES 17
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		15. SECURITY CLASS. (of this report) Unclassified
18. SUPPLEMENTARY NOTES		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Antifreeze Extender Corrosion Inhibitor Water Inhibitor Used Antifreeze Reuse		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The object of this study was to develop an inhibitor combination that when added to used antifreeze with depleted inhibitors (intended for disposal) would extend the use of the antifreeze for at least one year. It was further intended that this inhibitor combination would replace the presently used Federal Specification O-I-490, "Inhibitor, Corrosion, Liquid Cooling System" in water-cooled automotive cooling systems. Results of this study show that the inhibitor designated as Blend 18 is effective in both applications. ←		

DD FORM 1 JAN 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

403 160

BW

9 04 02 010

CONTENTS

Section	Title	Page
I	INTRODUCTION	1
II	TEST DETAILS	1
III	TEST RESULTS	2
IV	CONCLUSION	9

ACCESSION for

NTIS White Section

DOC Buff Section

UNANNOUNCED JUSTIFICATION

BY DISTRIBUTION/AVAILABILITY NOTES

CLASSIFICATION

A

ILLUSTRATIONS

Figure	Title	Page
1	Aluminum Water Pump After 555 Hours at 115.5°C (240°F) with 1.5-Percent 0-I-490 Corrosion Inhibitor in Corrosive Water	7
2	Aluminum Water Pump After 700 Hours at 115.5°C (240°F) with 3-Percent Blend 18 in Corrosive Water	8

TABLES

Table	Title	Page
1	Analysis of Commercial Inhibitor	3
2	Experimental Inhibitor Formulations	3
3	ASTM D-1384 Glassware Corrosion Test Results	5
4	ASTM D-2570 Simulated Service Test Results	6

DEVELOPMENT OF AN ANTIFREEZE EXTENDER AND WATER INHIBITOR FOR AUTOMOTIVE COOLING SYSTEMS

I. INTRODUCTION

A shortage of ethylene glycol for antifreeze usage was brought about as a result of the 1973 energy crisis. The feedstock (petroleum naphtha) used for the manufacture of ethylene glycol was diverted to more lucrative fields, particularly automotive gasoline, both leaded and unleaded. Instead of being cracked to ethylene to manufacture ethylene glycol, a large portion of the naphtha was used directly for formulating gasolines and other solvents that were in short supply. Additionally the soaring demand for ethylene glycol for use in polyester fiber and film further reduced the availability for antifreeze.

Because of the increasing concern to improve energy conservation and the desirability to extend the service life of engine antifreezes, a program was initiated to determine the feasibility of reclaiming or reusing antifreeze. The results of this study are reported in MERADCOM Report 2168¹ and show that it is possible to reclaim used antifreeze and restore it to a usable condition. Four commercial materials were evaluated; three were eliminated because of corrosion of the metal specimens and excessive foaming in the glassware corrosion test ASTM Method D1384.² The one commercial inhibitor found to be satisfactory was tested further in the ASTM-D-2570 simulated service test³ and was found to meet our initial requirements. But since this was a proprietary material and the company did not plan to market it, a program was initiated to formulate an additive package having similar or superior characteristics.

II. TEST DETAILS

Initially the satisfactory commercial material tested previously was analyzed to identify and/or characterize the components. Total solids, infrared spectrophotometry, X-ray diffraction studies, and atomic absorption spectrophotometry were conducted.

Eighteen formulations were compounded based upon the above analysis. Of these eighteen blends, Blends 17 and 18 were further tested in the laboratory.

¹ James H. Conley and Robert G. Jamison, "Reclaiming Used Antifreeze," MERADCOM Report 2168, March 1976.

² ASTM D-1384, "Corrosion Tests for Engine Coolants in Glassware."

³ ASTM D-2570, "Simulated Service Corrosion Testing of Engine Coolants."

Laboratory screening tests were conducted in two phases. The first phase consists of testing in accordance with ASTM Method D-1384, "Corrosion Test for Engine Coolants in Glassware." This method covers a simple beaker-type screening test for evaluating the effects of engine coolants on metal specimens under controlled laboratory conditions. Specimens of metals typical of those present in automotive cooling systems are totally immersed in the test antifreeze solution with aeration for 336 hours at 87.8°C (190°F). The corrosion inhibitive properties of the test solution are evaluated on the basis of the weight changes incurred by the specimens. Each test is run in triplicate and the average weight change is determined for each metal. This method will generally distinguish between coolants that are definitely deleterious from the corrosion standpoint and those that are suitable for further evaluation.

The second phase of the laboratory screening tests was conducted according to ASTM Method D-2570, "Simulated Service Corrosion Testing of Engine Coolants." This method evaluates the effect of a circulating engine coolant on metal test specimens and automotive cooling system components under controlled laboratory conditions. The method specifies cooling system components, type of coolant, and coolant flow conditions that are considered typical of current automotive use. The test temperature specified in this method is 87.8°C (190°F), but for the purposes of this study tests were also conducted at 115.5°C (240°F) in order to study the cavitation corrosion effect on an aluminum water pump. This test is significant if the results include comparable test information on a coolant of known service performance characteristics such as MIL-A-46153 antifreeze⁴ and O-I-490 corrosion inhibitor⁵ in water.

III. TEST RESULTS

Analysis of a commercial reinhibitor is shown in Table 1. Results show this material is essentially a water solution containing approximately 30 percent by weight solids. Elements identified by infrared, X-ray diffraction, and atomic absorption include boron, sodium, silicon, traces of potassium, calcium, and an unidentified organic antioxidant.

Eighteen formulations were compounded using the analysis in Table 1 as the guide. Problems with solubility of various silicates and organic antioxidants eliminated 16 of the formulations. The two formulations listed in Table 2 were further studied in the laboratory corrosion tests.

⁴ Military Specification MIL-A-46153, "Antifreeze, Ethylene Glycol, Inhibited, Heavy-Duty, Single-Package," 14 August 1973.

⁵ Federal Specification O-I-490, "Inhibitor Corrosion, Liquid Cooling System," 26 April 1965.

Table 1. Analysis of Commercial Inhibitor

No.	Parameter	Content
1	Total Solids	29.5% by weight.
2	Residue by Infrared	Water solution of borates and silicates.
3	X-ray Diffraction	Silicates with traces of phosphorus. Chloride and iron.
4	Atomic Absorption	2.9% boron; 5.3% sodium; 0.6% silicon with traces of potassium and calcium.
5	Infrared of Water Extraction	Organic Antioxidant, not identified.
6	Concentrated pH	12.7.
7	Reserve Alkalinity	3% solution 8.5.
8	Specific Gravity	1.230.

Table 2. Experimental Inhibitor Formulations

Blend 17

29% by weight Sodium Metaborate.
 3% by weight Sodium Mercaptobenzothiazole (50% solution).
 4.6% by weight Sodium Silicate.
 63.4% by weight Distilled Water.
 Concentrated pH 12.25.
 3% Reserve Alkalinity 9.8.
 Specific Gravity 1.193.

Blend 18

29% by weight Sodium Metaborate.
 3% by weight Sodium Mercaptobenzothiazole (50% solution).
 4.6% by weight Potassium Silicate.
 63.4% by weight Distilled Water.
 Concentrated pH 12.5.
 3% Reserve Alkalinity 11.8.
 Specific Gravity 1.192.

Table 3 shows the results of tests conducted using ASTM Method D-1384. Test No. 6 clearly shows that Blend 18 is superior to Blend 17 in used antifreeze (Test No. 2). Test No. 6 also compares favorably to Test No. 7 which is conducted on new MIL-A-46153 antifreeze. Test No. 5 shows there is no adverse affect when a 3-percent concentration of Blend 18 is added to new MIL-A-46153 antifreeze. Test No. 4 shows that Blend 18 can also be used to reduce corrosion effectively in corrosive water. Foaming tendency of both blends was checked and neither showed an increase in foam formation.

Results of testing according to ASTM-D-2570 are shown in Table 4. Blend 17 produced less corrosion on the solder specimen than did Blend 18 when used at a 3-percent concentration in corrosive water. But during testing the packaged material was found to be unstable. After a storage period of only one month, the material began to precipitate out and testing was discontinued on Blend 17. Although Blend 18 gave higher solder weight losses during testing, there was no adverse affect on the solder in the radiator. All other metals were satisfactory. Blend 18 is effective in reducing corrosion of all metals in used antifreeze and does not adversely affect new antifreeze. Blend 18 was especially effective in corrosive water at 115.5°C (240°F) when compared to O-I-490 inhibited corrosive water at the same temperature.

Figure 1 shows the cavitation corrosion on the aluminum water pump used in Test No. 7 with O-I-490 as the corrosion inhibitor, and Figure 2 shows the water pump from Test No. 6 using Blend 18 as the corrosion inhibitor. There is no clear evidence of corrosion of any kind on the pump from the test using Blend 18. In fact, the pump is as good as new. The use of Blend 18 in the cooling system of an aluminum block engine operating at temperatures at 115.5°C (240°F) with water is a significant improvement over the presently used O-I-490 inhibitor system.

A field test has been initiated in military vehicles, both facility vehicles and tactical vehicles to confirm the results of the laboratory testing of Blend 18 and will continue for at least one year. Vehicles were checked and those vehicles that were marginally inhibited were used for the field test. Blend 18 was also added to two vehicles with adequate coolant.

A patent covering Blend 18 is being applied for through the MERADCOM Office of Chief Counsel patent attorney.

A further plan has been developed to use this technology in the development of a long-life cooling system. The inhibitor system will be incorporated into a replaceable canister/filter-type conditioner that will require periodic replacement and will allow continued use of the antifreeze, thus reducing the demand for antifreeze replacement.

Table 3. ASTM D-1384 Glassware Corrosion Test Results

Solution	Weight Loss per Specimen (mg)					
	Copper	Solder	Brass	Steel	Cast Iron	Aluminum
1. 3% Blend 17 in corrosive water	8.6	21.4	11.1	2.3	Nil	0.6 ^a
2. 3% Blend 17 in used antifreeze	14.3	49.9	11.6	181.6 ^b	204.1 ^c	6.3
3. 3% Commercial Reinhibitor in used antifreeze	7.5	33.8	8.0	2.8	250.9 ^c	3.4
4. 3% Blend 18 in corrosive water	8.2	18.6	9.2	2.1	3.7	8.5 ^d
5. 3% Blend 18 in new MIL-A-46153 antifreeze	8.2	21.0	9.0	1.7	2.2	1.1
6. 3% Blend 18 in used antifreeze	10.7	16.9	8.8	5.3	1.7	Gain
7. New MIL-A-46153 antifreeze	7.9	17.3	8.4	0.5	+1.8	5.9
Max. weight loss limit	10.0	30.0	10.0	10.0	10.0	30.0

- ^a Aluminum specimens pitted.
- ^b Heavy etching at corner of specimen.
- ^c Heavy etching overall.
- ^d Slight etching.

Table 4. ASTM D-2570 Simulated Service Test Results

Solution	Test Temp (°F)	Test Duration (hr)	Weight Loss per Specimen (mg)					
			Copper	Solder	Brass	Steel	Cast Iron	Aluminum
1. 3% Blend 17 in corrosive water	190	1064	23.2	41.8	15.5	2.9	1.2	54.2 ^a
2. 3% Blend 18 in corrosive water	190	1064	15.3	208.3	15.1	2.8	Gain	29.5
3. 3% Blend 18 in new MIL-A-46153 antifreeze	190	1064	8.1	20.9	9.2	1.1	1.0	4.4
4. 3% Blend 18 in used antifreeze	190	1064	9.9	270.1	12.0	15.0	2.8	421.0
5. 1.5% 0-I-490B in corrosive water	190	1064	2.1	170.8	5.2	1.2	+1.6	620.9
6. 3% Blend 18 in corrosive water	240	700	+22.13 ^b	225.6	+3.7 ^b	2.7	+4.9	14.5
7. 1.5% 0-I-490B in corrosive water	240	555	No specimens were used in this test					
Max. weight loss limit			20	300	20	20	20	400

^a Moderate etching.

^b Specimens tin plated.




Figure 1. Aluminum water pump after 555 hours at 115.5°C (240°F) with 1.5-percent 0-I-490 Corrosion Inhibitor in corrosive water.



Figure 2. Aluminum water pump after 700 hours at 115.5°C (240°F) with 3-percent Blend 18 in corrosive water.

IV. CONCLUSION

Blend 18 is an effective inhibitor for use in returning used antifreeze to an acceptable level of corrosion protection to allow one year's additional use. It is an excellent replacement for the presently used O-I-490 inhibitor in systems that require only water as the coolant. It is especially useful in military vehicles containing aluminum components that often operate at temperatures well above the 87.8°C (190°F) temperature due mostly to the unusual operating conditions.

DISTRIBUTION FOR MERADCOM REPORT 2265

No. Copies	Addressee	No. Copies	Addressee
	Department of Defense		
1	Director, Technical Information Defense Advanced Research Project Agency 1400 Wilson Blvd Arlington, VA 22209	1	Technical Library Chemical Systems Laboratory Aberdeen Proving Ground, MD 21010
1	Director Defense Nuclear Agency ATTN: STTL Washington, DC 20305	1	Commander US Army Aberdeen Proving Ground ATTN: STEAP-MT-U (GE Branch) Aberdeen Proving Ground, MD 21005
12	Defense Documentation Center Cameron Station Alexandria, VA 22314	2	Director US Army Materiel Systems Analysis Agency ATTN: DRXSY-CM DRXSY-MP Aberdeen Proving Ground, MD 21005
	Department of the Army		
1	Commander, HQ TRADOC ATTN: ATEN-ME Fort Monroe, VA 23651	1	Director US Army Ballistic Research Lab ATTN: DRDAR-TSB-S (STINFO) Aberdeen Proving Ground, MD 21005
1	HQDA (DAME-AOA-M) Washington, DC 20310	1	Director US Army Engineer Waterways Experiment Station ATTN: Chief, Library Branch Technical Information Ctr Vicksburg, MS 39180
1	HQDA (DALO-TS M-P) Washington, DC 20310		
1	HQDA (DAEN-RDL) Washington, DC 20314	1	Commander Picatinny Arsenal ATTN: SARPA-TS-S No. 59 Dover, NJ 07801
1	HQDA (DAEN-MCE-D) Washington, DC 20314		
1	Commander US Army Missile Research & Development Command ATTN: DRSMI-RR Redstone Arsenal, AL 35809	1	Commander US Army Troop Support and Aviation Materiel Readiness Command ATTN: DRSTS-KTE 4300 Goodfellow Blvd St Louis, MO 63120
1	Chief, Engineer Division DCSLOG ATTN: AFKC-LG-E HQ Sixth US Army Presidio of San Francisco, CA 94129	2	Director Petrol & Fld Svc Dept US Army Quartermaster School Fort Lee, VA 23801
1	Director Army Materials and Mechanics Research Center ATTN: DRXMR-STL Technical Library Watertown, MA 02172	1	Commander US Army Electronics Research and Development Command ATTN: DRSEL-GG-TD Fort Monmouth, NJ 07703

No. Copies	Addressee	No. Copies	Addressee
1	President US Army Aviation Test Board ATTN: STEBG-PO Fort Rucker, AL 36360	1	Commander Headquarters, 39th Engineer Battalion (Cbt) Fort Devens, MA 01433
1	US Army Aviation School Library P.O. Drawer 0 Fort Rucker, AL 36360	1	President US Army Armor and Engineer Board ATTN: ATZK-AE-TD-E Fort Knox, KY 40121
1	HQ, 193D Infantry Brigade (CZ) Directorate of Facilities Engineering Fort Amador, Canal Zone	1	Commander and Director USAFESA ATTN: FESA-RTD Fort Belvoir, VA 22060
1	Commander Special Forces Detachment (Airborne) Europe APO New York 09050	1	Director US Army TRADOC Systems Analysis Activity ATTN: ATAA-SL (Tech Lib) White Sands Missile Range, NM 88002
2	Engineer Representative US Army Standardization Group, UK Box 65, FPO New York 09510	1	HQ, USAEUR & Seventh Army Deputy Chief of Staff, Engineer ATTN: AEAEN-MT-P APO New York 09403
1	Commander Rock Island Arsenal ATTN: SARRI-LPL Rock Island, IL 61201	1	HQ, USAEUR & Seventh Army Deputy Chief of Staff, Operations ATTN: AEAGC-FMD APO New York 09403
1	HQ, DA, ODCSLOG Directorate for Transportation and Services Army Energy Office Room 1D570 Washington, DC 20310	1	Commandant US Army Field Artillery School ATTN: ATSF-WD-SD Fort Sill, OK 73503
1	Plastics Technical Evaluation Ctr Picatinny Arsenal, Bldg 176 ATTN: A. M. Anzalone SARPA-FR-M-D Dover, NJ 07801		MERADCOM
1	Commander Frankford Arsenal ATTN: Library, K2400, B1 51-2 Philadelphia, PA 19137	1	Commander, DRDME-Z Technical Director, DRDME-ZT Assoc Tech Dir/R&D, DRDME-ZN Assoc Tech Dir/Engrg & Acq, DRDME-ZE Spec Asst/Matl Asmt, DRDME-ZG Spec Asst/Tech Asmt, DRDME-ZK CIRCULATE
1	Learning Resources Center US Army Engineer School Bldg 270 Fort Belvoir, VA 22060	1	C, Ctrmine Lab, DRDME-N C, Elec Pwr Lab, DRDME-E C, Cam & Topo Lab, DRDME-R C, Mar & Br Lab, DRDME-M C, Mech & Constr Eqpt Lab, DRDME-H C, Ctr Intrus Lab, DRDME-X C, Matl Tech Lab, DRDME-V Director, Product A&T Directorate, DRDME-T CIRCULATE
1	President US Army Airborne, Communications and Electronics ATTN: STEBF-ABTD Fort Bragg, NC 28307		

No. Copies	Addressee	No. Copies	Addressee
5	Energy & Water Res Lab, DRDME-G	1	AFSC/INJ
30	Fuels & Lubricants Div, DRDME-GL		Andrews AFB, MD 20334
3	Tech Reports Ofc, DRDME-WP		
3	Security Ofc (for liaison officers), DRDME-S	1	AFCEC/XR/21
2	Tech Library, DRDME-WC		Tyndall AFB, FL 32401
1	Programs & Anal Directorate, DRDME-U	1	HQ USAF/PREES
1	Pub Affairs Ofc, DRDME-I		ATTN: Mr. Edwin B. Mixon
1	Ofc of Chief Counsel, DRDME-L		Bolling AFB-Bldg 626
			Washington, DC 20332
	Department of the Navy	1	AFAPL/SFL
			Wright-Patterson AFB, OH 45433
1	Director, Physics Program (421) Office of Naval Research Arlington, VA 22217	1	Department of Transportation Library, FOB 10A, TAD-494.6 800 Independence Ave., SW Washington, DC 20591
1	Director Naval Research Laboratory ATTN: Code 2627 Washington, DC 20375		Others
1	Commander, Naval Facilities Engineering Command Department of the Navy ATTN: Code 032-A 200 Stovall St Alexandria, VA 22332	1	Professor Raymond R. Fox School of Engineering and Applied Science The George Washington University Washington, DC 20052
1	US Naval Oceanographic Office Library (Code 1600) Washington, DC 20373	1	Reliability Analysis Center Rome Air Development Ctr ATTN: I. L. Krulac Griffiss AFB, NY 13441
1	Officer-in-Charge (Code L31) Civil Engineering Laboratory Naval Construction Battalion Ctr Port Hueneme, CA 93043		
1	Director Earth Physics Program Code 463 Office of Naval Research Arlington, VA 22217		
1	Naval Training Equipment Center ATTN: Technical Library Orlando, FL 32813		
	Department of the Air Force		
1	HQ USAF/RDPS (Mr. Allan Eaffy) Washington, DC 20330		
1	Mr. William J. Engle Chief, Utilities Branch HQ, USAF/PREEU Washington, DC 20332		