

AD-A070 533

ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND WATER--ETC F/G 20/12
MAGNETIC MOMENT OF PRESSURE QUENCHED CADMIUM SULFIDE. (U)

MAY 79 C G HOMAN, D P KENDALL, R K MACCRONE


UNCLASSIFIED

ARLCB-TR-79006

SBIE -AD-E440 029

NL

1 OF 1
AD
A070533



END
DATE
FILMED
8 - 79
DDC

12 LEVEL III

AD-E440 029

DA 070533

TECHNICAL REPORT ARLCB-TR-79006

MAGNETIC MOMENT OF PRESSURE QUENCHED CADMIUM SULFIDE

C. G. Homan
D. P. Kendall
R. K. MacCrone

May 1979



US ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND
LARGE CALIBER WEAPON SYSTEMS LABORATORY
BENÉT WEAPONS LABORATORY
WATERVLIET, N. Y. 12189

AMCMS No. 611102H600211

DA Project No. 1L1161102H60

PRON No. 1A924324GGGG

DDC
RECEIVED
JUN 28 1979
B

DDC FILE COPY

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

79 06 01 031

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARLCB-TR-79006	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) MAGNETIC MOMENT OF PRESSURE QUENCHED CADMIUM SULFIDE		5. TYPE OF REPORT & PERIOD COVERED
AUTHOR(s) C. G. Homan R. K. MacCrone D. P. Kendall		6. PERFORMING ORG. REPORT NUMBER
PERFORMING ORGANIZATION NAME AND ADDRESS Benet Weapons Laboratory Watervliet Arsenal, Watervliet, N.Y. 12189 URDAR-LCB-TL		8. CONTRACT OR GRANT NUMBER(s)
10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 611102H600211 DA Project No. 1L1161102H60 PRON No. 1A924324GGGG		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research and Development Command Large Caliber Weapon Systems Laboratory Dover, New Jersey 07801		12. REPORT DATE May 1979
13. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES 16
15. SECURITY CLASS. (of this report) UNCLASSIFIED		15. SECURITY CLASS. (of this report)
15a. DECLASSIFICATION/DOWNGRADING SCHEDULE		
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Presented at Physics Colloquium at RPI, 18 April '79, Troy, NY.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Cadmium Sulfide Paramagnetism High Pressure Phase Transitions Magnetic Properties 1000000		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Magnetic moment measurements of cadmium sulfide (CdS) polycrystalline samples, pressure quenched from above the semi-conducting to conducting transition pressure (40 kbars) at rates approaching 10^6 bars/sec, have been made in a vibrating sample magnetometer to fields approaching 1000 Oersted. The samples exhibit the complex magnetic behavior of low field diamagnetism ($\chi_v > -5 \times 10^{-5}$ cgs units) transforming at fields of several hundred Oersted to positive magnetism.		

Continued from Block 20

to positive magnetism ($\chi_v > 3 \times 10^4$ cgs units). This magnetic behavior contrasts with unquenched samples which yield the normal diamagnetism of CdS ($\chi_v = -1.5 \times 10^{-6}$ cgs units). These anomalous magnetic effects are observed at both RT and LN₂ temperatures at atmospheric pressure.

ACKNOWLEDGEMENT

The authors acknowledge the helpful discussions with Drs. Edmund Brown and Paul Cote, the ac diamagnetic measurements by John Barrett, and the technical assistance of William Yaiser. The Eagle-Picker sample material was provided through the kind offices of Dr. J. Bray of the General Electric R&D Center.

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DDC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or special
A	

ACKNOWLEDGEMENT

The authors acknowledge the helpful discussions with Drs. Edmund Brown and Paul Cote, the ac diamagnetic measurements by John Barrett, and the technical assistance of William Yaiser. The Eagle-Picker sample material was provided through the kind offices of Dr. J. Bray of the General Electric R&D Center.

Accession For	
NTIS G&A&I	<input checked="" type="checkbox"/>
DDC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/ _____	
Availability Codes	
Dist	Avail and/or special
A	

CONTENTS

	<u>PAGE</u>
ACKNOWLEDGEMENT	1
INTRODUCTION	1
APPROACH TO THE PROBLEM	2
RESULTS	3
DISCUSSION	6
REFERENCES	10

ILLUSTRATIONS

<u>FIGURE</u>		<u>PAGE</u>
1	Typical resistometric trace of optical grade polycrystalline CdS. See reference 2.	7
2	D.C. magnetic moment measurements vs field for optical grade polycrystalline CdS after various pressure treatments.	8
3	Simulated magnetic moment behavior of a sample containing a volume V_1 of positive magnetic susceptibility χ_1 and a volume V_2 of superconducting material assuming a linear superposition of magnetic moments.	9

INTRODUCTION

An anomalous, diamagnetic transition in pressure quenched cadmium sulfide, (CdS) has recently been reported by Homan and Kendall.¹ Using a low frequency technique (Hartshorn bridge) a transition from a strongly diamagnetic state to a paramagnetic state (or weakly paramagnetic to strongly paramagnetic state, etc.) was observed at temperatures up to 150K in CdS specimens that were pressure quenched at rates of about 10^6 bars/sec, from pressures just above the semiconductor-conductor transition. These specimens exhibited a layered morphology consisting of opaque, lenticular platelets of varying thickness imbedded in a compacted powder matrix.

The character of these platelets was studied by optical and scanning electron microscopy, transmission x-ray analysis, microhardness and chemical etching techniques. The platelets are mechanically and chemically different from the matrix material and are probably amorphous, although microcrystallinity cannot be ruled out. They comprise a volume fraction of 10 to 15 percent, the larger fraction being obtained by quenches from the higher pressures.

In order to obtain more quantitative measurements of the magnetic properties and to preclude the possibility of a spurious ac effect, magnetic moment measurements as a function of static magnetic field strength were performed and these results are reported in this present paper.

¹C. G. Homan and D. P. Kendall, Bull. Am. Phys. Soc. 24, 316 March 1979. Details published in Benet Laboratory Technical Report No. ARLCB-TR-79-004 April 1979.

APPROACH TO THE PROBLEM

Samples were prepared as in reference 1, from optical grade CdS powder,² compacted into discs and then pressurized in a gasketed Bridgeman anvil pressure device loaded in a servo-hydraulic tensile testing machine. The sample resistance during pressurization was determined by measuring the resistance across the anvils using dc specimen currents not exceeding 10 milliamps. A typical resistance vs pressure trace is shown in Figure 1. The pressure values shown in this figure are approximate since an accurate pressure calibration for this device was not determined. The specimen resistance was taken to be a reproducible measure of pressure, since the sample geometry and weight were nearly identical at approximately 3.0 mm in diameter and 0.5 mm thick, and weighs 14.5 mg.

Samples were quenched from pressures which produced specimen resistance values ranging from 50 ohms to 8 ohms. Pressure quench rates were either 1 to 2×10^6 bars/sec, 5 to 6×10^6 bars/sec or less than 10^3 bars/sec.

The magnetic moment measurements were made using a Princeton Applied Research vibrating sample magnetometer. Extensive previous use has shown no evidence for experimental artifacts. However, a

²Samples were prepared from optronic grade CdS from Alpha Inorganics, Stock No. 20130 compacted in a small piston cylinder device to a pressure of about 2 kbars. Starting pellets were found to be near theoretical density by a gravimetric technique. Spectrographic analysis by the spark emission method and a quantitative chemical analysis of our samples indicated the following metallic impurities: Fe = 12 ppm, Mg = 3.6 ppm, Cu = 4.2 ppm, Ag = 3.5 ppm, Bi < 1 ppm, Al < 1.4 ppm, Ge < 1 ppm, Not detected, Ni < 1 ppm, Mn < .46 ppm, Pb < .07 ppm, Cr < 2.8 ppm, Co < 1 ppm.

series of tests were also performed during these measurements to check for spurious results. These included measuring comparable signals using known materials ($\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$) and obtaining agreement with literature values of the susceptibility, changing specimen holders, changing geometrical configurations of pick-up wires, etc., and running the instrument without the cylinder normally surrounding the vibrating rod. In all cases, no evidence for deviant behavior was observed.

It had been previously found that CdS samples pressure quenched from resistance values of the order of 50 ohms at 2×10^6 bars/sec were metastable in their magnetic properties at room temperature with recovery times in the order of hours. Therefore, after pressure quenching at room temperature, these samples were kept at 77K for about an hour before being placed in the sample holder of the magnetometer at room temperature and again cooled to 77K for making the magnetic measurements.

RESULTS

The results in Figure 2 represent the average of several runs on the same sample that was pressure quenched from 50 ohms at 1 to 2×10^6 bars/sec. The result is typical of such pressure quenched samples, although some variation in the magnitude and position of the discontinuities in magnetic behavior is observed between specimens. We show for comparison the magnetic behavior of the original, unpressurized starting material, and of samples slowly pressure quenched at about 10^3 bars/sec from the same pressure. The magnetic behavior of the

empty sample holder is also shown for comparison. The small paramagnetism of the sample holder is due to absorbed oxygen.³ The same sample holder was used during the whole sequence of measurements.

As can be seen, the magnetic behavior of the fast quenched specimens shows several striking features. First, the sample is strongly diamagnetic to around 50 Oersted, with the magnitude of the volume susceptibility being -5×10^{-5} cgs units. Above about 70 Oersted, there is a transition to an intermediate magnetic state in which the magnetic moment is positive and whose susceptibility is about $+2 \times 10^{-4}$ cgs units. Above 150 Oersted, these samples transformed to a state whose positive susceptibility is at least twice as large as the intermediate state. The calculations were made on the assumption that the entire sample is contributing to the magnetic behavior. Corrections were made for the magnetic behavior of the Teflon sample holder.

The samples were slowly warmed to room temperature in the order of several hours, during which time recovery of the magnetic behavior occurred as evidenced by a subsequent run at 77K in which these large magnetic effects were not observed. Following another short room temperature anneal, the ac diamagnetic transition previously described was observed on warming from 4.2K in the mutual inductance bridge at 20K. One further room temperature anneal lasting about an hour was made and no ac diamagnetic transition occurred above the Pb superconducting transition calibration temperature.

³M. Centanni and P. A. Casabella in "Amorphous Magnetism" edited by R. A. Levy and R. Hasegaw. Plenum Press, NY, 1977, pp 663-671.

Preliminary studies on the stability of the magnetic properties indicate that slight increases in pressure and quench rate result in enhanced stability. For example, samples pressure quenched from a resistance of about 10 ohms at a rate of about 5×10^6 bars/sec are more stable in their magnetic properties, with the strong diamagnetism remaining for days rather than hours at room temperature.

The form of the magnetization curves is the same as that shown in Figure 2 and no systematic variation of the volume susceptibilities with these quenching parameters was found. However, variations in the critical fields were noted.

A sample quenched from 15 ohms at 2×10^6 bars/sec was tested for magnetic behavior at both room temperature and 77K. At both temperatures the form of the results was similar to that shown in Figure 2. However, the lower critical field (shown at 50 Oersted in Figure 2) occurred at 88 Oersted at 77K and 40 Oersted at room temperature.

Preliminary investigation of the effect of impurities was made on samples fabricated from CdS powder from a different source.⁴ This sample material was lighter in color suggesting a different impurity content. Based on manufacturers data, it had a lower total impurity content. These samples showed significantly different

⁴These samples were prepared from CdS from Eagle-Picker, Ultrahigh Purity Grade. The nominal analysis provided by the manufacturer was qualitatively examined by the spark emission technique. This analysis suggested less total impurities than the original material and showed traces of Fe, Mg, Cu, Ag, Bi, Al, Ge Not detected, Ni, Mn, Pb, Cr, Co.

resistance vs pressure curves. Samples pressure quenched from a resistance of about 30 ohms at 5 to 6×10^6 bars/sec showed different scanning electron microscopic morphology and significantly less paramagnetic effects. This suggests that the impurity spectrum and concentration in the parts per million range may be significant and warrant further study.

DISCUSSION

We note that the magnetization curves shown in Figure 2 can be simulated by the superposition of some regions in our sample behaving with strong positive magnetic behavior (paramagnetism) with other regions behaving with classical type II superconducting magnetic behavior as shown in Figure 3. However, careful experimental determination of other physical properties, such as the resistivities of our sample or the platelets must be made as functions of temperature and magnetic field in order to either confirm or deny this intriguing possibility. Experiments to determine these additional physical properties are in progress at the present time.




Figure 1. Typical resistometric trace of optical grade polycrystalline CdS. See ref. 2




Figure 2. D.C. magnetic moment measurements vs field for optical grade polycrystalline CdS after various pressure treatments.




Figure 3. Simulated magnetic moment behavior of a sample containing a volume V_1 of positive magnetic susceptibility χ_1 and a volume V_2 of superconducting material assuming a linear superposition of magnetic moments.

REFERENCES

1. C. G. Homan and D. P. Kendall, Bull. Am. Phys. Soc. 24, 316 March 1979. Details published in Benet Laboratory Technical Report No. ARLCB-TR-79-004, April 1979.
2. Samples were prepared from optronic grade CdS from Alpha Inorganics, Stock No. 20130 compacted in a small piston cylinder device to a pressure of about 2 kbars. Starting pellets were found to be near theoretical density by a gravimetric technique. Spectrographic analysis by the spark emission method and a quantitative chemical analysis of our samples indicated the following metallic impurities:
Fe = 12 ppm, Mg = 3.6 ppm, Cu = 4.2 ppm, Ag = 3.5 ppm, Bi < 1 ppm, Al < 1.4 ppm, Ge < 1 ppm, Not detected, Ni < 1 ppm, Mn < .46 ppm, Pb < .07 ppm, Cr < 2.8 ppm, Co < 1 ppm.
3. M. Centanni and P. A. Casabella in "Amorphous Magnetism" edited by R. A. Levy and R. Hasegawa. Plenum Press, NY, 1977, pp 663-671.
4. These samples were prepared from CdS from Eagle-Picker, Ultrahigh Purity Grade. The nominal analysis provided by the manufacturer was qualitatively examined by the spark emission technique. This analysis suggested less total impurities than the original material and showed traces of Fe, Mg, Cu, Ag, Bi, Al, Ge Not detected, Ni, Mn, Pb, Cr, Co.

WATERVLIET ARSENAL INTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>
COMMANDER	1
DIRECTOR, BENET WEAPONS LABORATORY	1
CHIEF, DEVELOPMENT ENGINEERING BRANCH	1
ATTN: DRDAR-LCB-DA	1
-DM	1
-DP	1
-DR	1
-DS	1
-DC	1
CHIEF, ENGINEERING SUPPORT BRANCH	1
CHIEF, RESEARCH BRANCH	2
ATTN: DRDAR-LCB-RA	1
-RC	1
-RM	1
-RP	1
TECHNICAL LIBRARY	5
TECHNICAL PUBLICATIONS & EDITING UNIT	2
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY DIRECTOR, BENET WEAPONS LABORATORY, ATTN:
DRDAR-LCB-TL, OF ANY REQUIRED CHANGES.

EXTERNAL DISTRIBUTION LIST (CONT)

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
COMMANDER US ARMY RESEARCH OFFICE P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER DEFENSE DOCU CEN ATTN: DDC-TCA CAMERON STATION ALEXANDRIA, VA 22314	12
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2800 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CEN BATTELLE COLUMBUS LAB 505 KING AVE COLUMBUS, OHIO 43201	1
DIRECTOR US ARMY INDUSTRIAL BASE ENG ACT ATTN: DRXPE-MT ROCK ISLAND, IL 61201	1	MPDC 13919 W. BAY SHORE DR. TRAVERSE CITY, MI 49684	1
CHIEF, MATERIALS BRANCH US ARMY R&S GROUP, EUR BOX 65, FPO N.Y. 09510	1	MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRXSY-MP ABERDEEN PROVING GROUND MARYLAND 21005	1
COMMANDER NAVAL SURFACE WEAPONS CEN ATTN: CHIEF, MAT SCIENCE DIV DAHLGREN, VA 22448	1		
DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27 (DOC LIB) WASHINGTON, D.C. 20375	1 1		
NASA SCIENTIFIC & TECH INFO FAC P.O. BOX 8757, ATTN: ACQ BR BALTIMORE/WASHINGTON INTL AIRPORT MARYLAND 21240	1		

NOTE: PLEASE NOTIFY COMMANDER, ARRADCOM, ATTN: BENET WEAPONS LABORATORY, DRDAR-LCB-TL, WATERVLIET ARSENAL, WATERVLIET, N.Y. 12189, OF ANY REQUIRED CHANGES.

EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRDTA-UL MAT LAB - DRDTA-RK WARREN, MICHIGAN 48090	1 1
COMMANDER US ARMY MAT DEV & READ. COMD ATTN: DRCDE 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	COMMANDER US MILITARY ACADEMY ATTN: CHMN, MECH ENGR DEPT WEST POINT, NY 10996	1
COMMANDER US ARMY ARRADCOM ATTN: DRDAR-TSS DRDAR-LCA (PLASTICS TECH EVAL CEN) DOVER, NJ 07801	2 1	COMMANDER REDSTONE ARSENAL ATTN: DRSMI-RB DRSMI-RRS DRSMI-RSM ALABAMA 35809	2 1 1
COMMANDER US ARMY ARRCOM ATTN: DRSAR-LEP-L ROCK ISLAND ARSENAL ROCK ISLAND, IL 61299	1	COMMANDER ROCK ISLAND ARSENAL ATTN: SARRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61202	1
DIRECTOR US Army Ballistic Research Laboratory ATTN: DRDAR-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER HQ, US ARMY AVN SCH ATTN: OFC OF THE LIBRARIAN FT RUCKER, ALABAMA 36362	1
COMMANDER US ARMY ELECTRONICS COMD ATTN: TECH LIB FT MONMOUTH, NJ 07703	1	COMMANDER US ARMY FGN SCIENCE & TECH CEN ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1
COMMANDER US ARMY MOBILITY EQUIP R&D COMD ATTN: TECH LIB FT BELVOIR, VA 22060	1	COMMANDER US ARMY MATERIALS & MECHANICS RESEARCH CENTER ATTN: TECH LIB - DRXMR-PL WATERTOWN, MASS 02172	2

NOTE: PLEASE NOTIFY COMMANDER, ARRADCOM, ATTN: BENET WEAPONS LABORATORY, DRDAR-LCB-TL, WATERVLIET ARSENAL, WATERVLIET, N.Y. 12189, OF ANY REQUIRED CHANGES.