

AD

AD-E400 305

MEMORANDUM REPORT ARLCD-MR-78007

**DYNAMIC MODELING OF  
POST FAILURE CONDITIONS  
OF REINFORCED CONCRETE SUBJECTED TO BLAST**

MICHAEL F. LEONDI

**TECHNICAL  
LIBRARY**

APRIL 1979



**US ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND  
LARGE CALIBER  
WEAPON SYSTEMS LABORATORY  
DOVER, NEW JERSEY**

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.

The views, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.


Destroy this report when no longer needed. Do not return to the originator.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Memorandum Report ARLCD-MR-78007	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) DYNAMIC MODELING OF POST FAILURE CONDITIONS OF REINFORCED CONCRETE SUBJECTED TO BLAST	5. TYPE OF REPORT & PERIOD COVERED	
	6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s)  Michael F. Leondi	8. CONTRACT OR GRANT NUMBER(s)	
9. PERFORMING ORGANIZATION NAME AND ADDRESS ARRADCOM, LCWSL Manufacturing Technology Div (DRDAR-LCM-S) Dover, NJ 07801	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS	
11. CONTROLLING OFFICE NAME AND ADDRESS ARRADCOM, TSD STINFO (DRDAR-TSS) Dover, NJ 07801	12. REPORT DATE March 1979	
	13. NUMBER OF PAGES 16	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) ARRADCOM, LCWSL Manufacturing Technology Div (DRDAR-LCM-S) Dover, NJ 07801	15. SECURITY CLASS. (of this report)  Unclassified	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Dynamic modeling, reinforced concrete Fragmentation, reinforced concrete Secondary fragments Post-failure fragments Maximum fragment velocity		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A dynamic modeling analysis of post-failure fragments of reinforced concrete subjected to blast overpressures was performed. The analysis related the physical (constitutive) properties as well as the geometric relationships of the model and the prototype. Results indicated that a replica model can provide rational test data if all the mechanical and geometric properties of the reinforced concrete element are reflected in the model.		

**SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)**



**SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)**

## ACKNOWLEDGMENTS

The author wishes to express his sincere appreciation to Dr. W. E. Baker of Southwest Research Institute and Messrs. J. Marsicovete, J. Moroney, and E. Krajkowski of ARRADCOM for valuable contributions and assistance in the preparation of this report.

## TABLE OF CONTENTS

	Page No.
Introduction	1
Problem Definition and Solution	1
Mechanics of Fragmentation	1
Dynamic Modeling of Reinforced Concrete Elements	3
PI Terms from Dimensional Homogeneity	3
Scale Factors	5
Conclusions and Recommendations	6
References	6
Distribution List	11
Tables	
1 List of parameters from explosive fragmentation of reinforced concrete elements	7
2 PI terms - explosive fragmentation	8
Figure	
1 Explosive fragmentation.	9

## INTRODUCTION

In support of an Army-wide modernization program, the Army Armament Research and Development Command, Dover, NJ, is engaged in the development of safety criteria as a project entitled, "Safety Engineering in Support of Ammunition Plants."

Prior to investigating the explosive fragmentation of reinforced concrete structures (one aspect of the safety engineering program), a feasibility study of sub-scale dynamic modeling was conducted to determine:

1. The applicability of sub-scale modeling to random mass fragments of reinforced concrete subjected to excessive blast loads.
2. The physical relationships between the model and the prototype in constitutive properties, panel geometry, and boundary conditions as well as the resulting fragment weight/shape, density, and distribution.

## PROBLEM DEFINITION AND SOLUTION

In munitions manufacturing facilities, reinforced concrete plays an essential role as a building material for both dividing walls (between quantities of explosive) and exterior walls and roofs.

Mechanics of Fragmentation (ref. 1)

When a reinforced concrete element is substantially overloaded by a blast wave, the element fails and concrete fragments (post-failure) are displaced at high velocities (fig. 1).

Failure of an element is characterized by the dispersal of concrete fragments formed by the cracking and displacement of the concrete between the donor and receiver layers of the reinforcement. As an element deflects and the concrete begins to crush, the compression stresses normally resisted by the concrete are transferred to the reinforcement. With increased deflections, these compression forces tend to buckle the reinforcement outward, initiating rapid disintegration of the element.

The velocity of individual fragments varies and depends on: (1) the magnitude of the excess (or blast) impulse minus the flexural impulse capacity of the element (area under the resistance-time curve), (2) the mass of the fragment, (3) the location of the fragment prior to collapse, (4) the interaction between fragments during their flight, and (5) the strength and time history of the compressive stress wave transmitted through the wall as the blast wave is reflected. Although the velocities of individual fragments differ, the average translational velocity,  $v_s$  (avg), of the debris after complete failure can be approximated from the excess impulse,  $i_e$ , and the unit mass,  $m$ , of the barrier; i.e., the momentum of the wall after collapse is numerically equal to the excess impulse,  $i_e = mv_f$  (avg).

Also,

$$i^2 = C_u \frac{(pHd_c^3 f_{ds}) + C_f d_c^2 v_f^2}{H}$$

where

$i$  = applied unit blast impulse

$pH$  = reinforcement ratio in the horizontal direction

$d_c$  = distance between the centroids of the compression and tension reinforcement.

$f_{ds}$  = dynamic design stress for the reinforcement

$H$  = span height

$v_f$  = maximum velocity of the post-failure fragments

$C_u$  = impulse coefficient for ultimate deflection  $X_u$

$C_f$  = post-failure fragment coefficient

The reflected shock wave is also transmitted through the wall as a compressive wave, and reflects from the rear surface as a tension wave which partially cancels the incoming compressive wave. If the shock strength is great enough and its decay rate rapid enough, a net tensile stress will occur at some distance from the rear surface. The concrete (which is weak in tension) will fail and spall off. The thickness of the spall and its velocity can be estimated



from knowledge of the reflected wave properties and the constitutive properties of the concrete.

### Dynamic Modeling of Reinforced Concrete Elements

The following exercise defines the physical similarity between reinforced concrete elements in the model and the prototype subjected to blast overloading as described in reference 2. The constitutive, geometric, and mechanical parameters dictated by the scope of the problem are given in table 1.

### PI TERMS FROM DIMENSIONAL HOMOGENEITY

By inspection (already dimensionless)

$$\pi^{13} = \psi$$

$$\pi^{14} = K$$

Technique from reference 2: Matrix Solution

$$F^0 L^0 T^0 \stackrel{d}{=} W^{a_1} R^{a_2} \rho_c^{a_3} \rho_s^{a_4} C_c^{a_5} T_c^{a_6} U_s^{a_7} T_s^{a_8} L_c^{a_9} L_s^{a_{10}} L_A^{a_{11}} E_s^{a_{12}} E_c^{a_{13}} W_F^{a_{14}} V^{a_{15}}$$

Using matrix algebra (identity submatrix)

Form a matrix:

	W	R	$\rho_c$	$\rho_s$	$C_c$	$T_c$	$U_s$	$T_s$	$L_c$	$L_s$	$L_A$	$E_s$	$E_c$	$W_F$	V
	$a_1$	$a_2$	$a_3$	$a_4$	$a_5$	$a_6$	$a_7$	$a_8$	$a_9$	$a_{10}$	$a_{11}$	$a_{12}$	$a_{13}$	$a_{14}$	$a_{15}$
F	+1	0	+1	+1	+1	+1	+1	+1	0	0	0	+1	+1	+1	0
L	+1	+1	-4	-4	-2	-2	-2	-2	+1	+1	+1	-2	-2	+1	3
T	0	0	2	2	0	0	0	0	0	0	0	0	0	0	0

Matrix algebra steps:

Step 1 - Divide row 3 by row 2.

Step 2 - Subtract new row 3 from row 1, and write new row 1.

Step 3 - Subtract row 1 from row 2.

Step 4 - Multiply row 3 by row 4 and add to row 2. Write new row 2.

Therefore, identity submatrix in the following matrix:

	$a_1$	$a_2$	$a_3$	$a_4$	$a_5$	$a_6$	$a_7$	$a_8$	$a_9$	$a_{10}$	$a_{11}$	$a_{12}$	$a_{13}$	$a_{14}$	$a_{15}$
F	+1	0	0	0	+1	+1	+1	+1	0	0	0	+1	+1	+1	0
L	0	+1	0	0	-3	-3	-3	-3	+1	+1	+1	-3	-3	0	+3
T	0	0	+1	+1	0	0	0	0	0	0	0	0	0	0	0

Then, by inspection

$$a_1 = -a_5 - a_6 - a_7 - a_8 - a_{12} - a_{13} - a_{14}$$

$$a_2 = 3a_5 + 3a_6 + 3a_7 + 3a_8 - a_9 - a_{10} - a_{11} + 3a_{12} + 3a_{13} - 3a_{15}$$

$$a_3 = -a_4$$

Substituting in the original equation

$$\begin{aligned}
 F^0 L^0 T^0 \stackrel{d}{=} & W^{-a_5 - a_6 - a_7 - a_8 - a_{12} - a_{13} - a_{14}} R^{3a_5 + 3a_6 + 3a_7 + 3a_8 - a_9 - a_{10} - a_{11}} \\
 & + 3a_{12} + 3a_{13} - 3a_{15} \\
 & \times \rho_c^{-a_4} \rho_s^{a_4} C_c^{a_5} T_c^{a_6} U_s^{a_7} T_s^{a_8} L_c^{a_9} L_s^{a_{10}} L_A^{a_{11}} E_s^{a_{12}} \\
 & \times E_c^{a_{13}} W_F^{a_{14}} V^{a_{15}}
 \end{aligned}$$

Collecting terms of like exponent, we have the model law. This can be expressed as:

$$\left. \begin{array}{l} \frac{(W_F)}{W} \\ \frac{V}{R^3} \\ \frac{\psi}{K} \end{array} \right\} f_i \frac{\rho_s}{\rho_c}, \frac{R^3 C_c}{W}, \frac{R^3 T_c}{W}, \frac{R^3 U_s}{W}, \frac{R^3 T_s}{W}, \frac{L_c}{R}, \frac{L_s}{R}, \frac{L_A}{R}, \frac{R^3 E_s}{W}, \frac{R^3 E_c}{W}$$

The law can also be stated in the form of table 2.

### SCALE FACTORS

Various relations between scale factors can be determined from the dimensionless terms.

$$\pi_1 \rightarrow \lambda_{\rho_s} = \lambda_{\rho_c} = 1 \text{ (set equal to 1 for ease in fabricating model)}$$

$$\begin{aligned} \pi_2, \pi_3, \pi_4, \pi_5, \pi_6, \pi_7 \rightarrow \frac{\lambda}{\lambda^3 R} &= \lambda_{C_c} = \lambda_{T_c} = \lambda_{U_s} = \lambda_{T_s} \\ &= \lambda_{E_s} = \lambda_{E_c} \end{aligned}$$

$$\pi_8, \pi_9, \pi_{10} \rightarrow \lambda_{L_c} = \lambda_{L_s} = \lambda_{L_A} = \lambda_R$$

$$\pi_{11} \rightarrow \lambda_{W_F} = \lambda_W$$

$$\pi_{12} \rightarrow \lambda_V = \lambda_R^3$$

These interrelations are all satisfied by a replica model<sup>1</sup> with geometry identical to the prototype. Although wave transmission effects are not shown in scale, they will scale properly because all constitutive properties and densities are unchanged.

## CONCLUSIONS AND RECOMMENDATIONS

The preceding similarity exercise has demonstrated that

1. A replica model accurately reflects the performance of a prototype system.
2. Failure modes of a replica model are representative for geometrically similar panels.
3. The model also exhibits similar relationships for fragment mass and velocity, distribution, and debris density.

For economic reasons and ease in testing, it is recommended that subscale replica models be used with a scale factor as small as possible without sacrificing the quality of the model.

## REFERENCES

1. "Structures to Resist the Effects of Accidental Explosions," Dept of the Army TM 5-1300, June 2, 1969.
2. W. E. Baker, P. S. Westing, F. T. Dodge, Similarity Methods in Engineering Dynamics, SPARTAN BOOKS, San Antonio, TX, 1973.

---

<sup>1</sup>A replica model is a physical model of a prototype which is geometrically similar in all respects and employs the same materials in the same locations as the prototype (ref. 2).

Table 1. List of parameters for explosive fragmentation of reinforced concrete elements


<u>No.</u>	<u>Parameter</u>	<u>Dimension</u>	<u>Description</u>
1	W	FL	Energy in blast source
2	R	L	Radial distance of blast
3	$\rho_c$	$FT^2/L^4$	Density concrete
4	$\rho_s$	$FT^2/L^4$	Density steel
5	$C_c$	$F/L^2$	Compressive strength (concrete)
6	$T_c$	$F/L^2$	Tensile strength (concrete)
7	$U_s$	$F/L^2$	Ultimate strength (steel)
8	$T_s$	$F/L^2$	Tensile strength (steel)
9	$L_c$	L	Characteristic geom. of element
10	$L_s$	L	Characteristic geom. of rebar
11	$L_A$	L	Aggregate size
12	$E_s$	$F/L^2$	Elastic moduli (steel)
13	$E_c$	$F/L^2$	Elastic moduli (concrete)
14	$W_f$	FL	Energy imparted into fragments
15	V	$L^3$	Vol of fragments
16	$\psi$	--	Distribution function of fragments
17	K	--	% energy absorbed by element

Table 2. PI terms - explosive fragmentation

$\pi_1 = \rho_s / \rho_c$	}	CONSTITUTIVE SIMILARITY
$\pi_2 = R^3 C_c / W$		
$\pi_3 = R^3 T_c / W$		
$\pi_4 = R^3 U_s / W$		
$\pi_5 = R^3 T_s / W$		
$\pi_6 = R^3 E_s / W$		
$\pi_7 = R^3 E_c / W$		
$\pi_8 = L_c / R$	}	GEOMETRIC SIMILARITY
$\pi_9 = L_s / R$		
$\pi_{10} = LA / R$		
$\pi_{11} = W_F / W$		SIMILAR ENERGY TRANSFERS
$\pi_{12} = V / R^3$		SIMILAR MASS TRANSFERS
$\pi_{13} = \psi$		DISTRIBUTION FUNCTION
$\pi_{14} = K$		% ENERGY ABSORBED

DONOR  
(Explosive Charge)

REINFORCED CONCRETE  
PROTECTIVE ELEMENT



ENERGY AND IMPULSE BALANCES

$$\text{Blast Energy In} = \text{Strain Energy} + \text{Sum of Fragment Kinetic Energies}$$

$$= \frac{\text{Sum of Fragment Kinetic Energies}}{(1 - K) \text{ (where } K = \% \text{ Blast Energy Absorbed)}}$$

$$\text{Applied Impulse} = \text{Flexural Impulse Capacity} + \text{Excess Impulse}$$




Figure 1. Explosive fragmentation.

## DISTRIBUTION LIST

### Commander

US Army Armament Research & Development Command

ATTN: DRDAR-CG  
DRDAR-LC  
DRDAR-LCM  
DRDAR-LCM-S (15)  
DRDAR-SF  
DRDAR-TSS (5)  
DRDAR-LCU-P

Dover, NJ 07801

### Commander

US Army Materiel Development & Readiness Command

ATTN: DRCDE  
DRCIS-E  
DRCPA-E  
DRCPP-I  
DRCDI  
DRCSG-S

5001 Eisenhower Avenue  
Alexandria, VA 22333

### Commander

USDRC Installations and Services Agency

ATTN: DRCIS-RI-IU  
DRCIS-RI-IC

Rock Island, IL 61299

### Commander

US Army Armament Materiel Readiness Command

ATTN: DRSAR-IR (2)  
DRSAR-IRC  
DRSAR-ISE (2)  
DRSAR-IRC-E  
DRSAR-PDM  
DRSAR-LC (2)  
DRSAR-ASF (2)  
DRSAR-SF (3)  
DRSAR-LEP-L

Rock Island, IL 61299



Chairman  
Dept of Defense Explosives Safety Board  
Hoffman Building 1, Room 856C  
2461 Eisenhower Avenue  
Alexandria, VA 22331

Project Manager for Munitions Production  
Base Modernization and Expansion  
US Army Materiel Development & Readiness Command  
ATTN: DRCPM-PBM-LA  
DRCPM-PBM-SF  
DRCPM-PBM-EP  
Dover, NJ 07801

Director  
Ballistic Research Laboratory  
ARRADCOM  
ATTN: DRDAR-BLE, C. Kingery (2)  
Aberdeen Proving Ground, MD 21010

Defense Documentation Center (12)  
Cameron Station  
Alexandria, VA 22314

Commander  
US Army Construction Engineering  
Research Laboratory  
ATTN: CERL-ER  
Champaign, IL 61820

Office, Chief of Engineers  
ATTN: DAEN-MCZ-E  
Washington, DC 20314

US Army Engineer District, Huntsville  
ATTN: Construction Division-HAD-ED (2)  
P.O. Box 1600 West Station  
Huntsville, AL 35807

Commander  
Indiana Army Ammunition Plant  
ATTN: SARIN-OR  
SARIN-SF  
Charlestown, IN 47111

Commander  
Kansas Army Ammunition Plant  
ATTN: SARKA-CE  
Parsons, KS 67537

Commander  
Lone Star Army Ammunition Plant  
ATTN: SARLS-IE  
Texarkana, TX 57701

Commander  
Milan Army Ammunition Plant  
ATTN: SARMI-S  
Milan, TN 38358

Commander  
Radford Army Ammunition Plant  
ATTN: SARRA-IE  
Radford, VA 24141

Commander  
Badger Army Ammunition Plant  
ATTN: SARBA  
Baraboo, WI 53913

Commander  
Holston Army Ammunition Plant  
ATTN: SARHO-E  
Kingsport, TN 37662

Commander  
Iowa Army Ammunition Plant  
ATTN: SARIO-A  
Middletown, IA 52638

Commander  
Joliet Army Ammunition Plant  
ATTN: SARJO-SS-E  
Joliet, IL 60436

Commander  
Longhorn Army Ammunition Plant  
ATTN: SARLO-O  
Marshall, TX 75670

Commander  
Louisiana Army Ammunition Plant  
ATTN: SARLA-S  
Shreveport, LA 71102

Commander  
Newport Army Ammunition Plant  
ATTN: SARNE-S  
Milan, TN 38358

Commander  
Pine Bluff Arsenal  
ATTN: SARPE-ETS  
Pine Bluff, AR 71601

Commander  
Sunflower Army Ammunition Plant  
ATTN: SARSU-O  
Lawrence, KS 66044

Commander  
Volunteer Army Ammunition Plant  
ATTN: SARVO-T  
Chattanooga, TN 34701

Weapon System Concept Team/CSL  
ATTN: DRDAR-ACW  
Aberdeen Proving Ground, MD 21010

Technical Library  
ATTN: DRDAR-CLJ-L  
Aberdeen Proving Ground, MD 21010

Technical Library  
ATTN: DRDAR-TSB-S  
Aberdeen Proving Ground, MD 21005

Benet Weapons Laboratory  
Technical Library  
ATTN: DRDAR-LCB-TL  
Watervliet, NY 12189

US Army Materiel Systems Analysis Activity  
ATTN: DRXSY-MP  
Aberdeen Proving Ground, MD 21005