

AD-A091 973

TEXAS UNIV AT AUSTIN DEPT OF CHEMISTRY

F/6 7/4

THE HETEROGENEOUS PHOTOCATALYTIC DECOMPOSITION OF BENZOIC ACID --ETC(U.

OCT 80 I IZUMI, F F FAN, A J BARD

N00014-78-C-0592

UNCLASSIFIED

TR-14

NL

END
DATE
FILMED
DTIC

LEVEL

12

OFFICE OF NAVAL RESEARCH

15 Contract N00014-78-C-0592

Task No. NR 051-693

TECHNICAL REPORT No. 14

AD A091973

6 The Heterogeneous Photocatalytic Decomposition of Benzoic Acid and Adipic Acid on Platinized TiO_2 Powder. The Photo-Kolbe Decarboxylative Route to the Breakdown of the Benzene Ring and to the Production to Butane.

10 IKUICHIRO
I. Izumi, Fu-Ren F. Fan, and Allen J. Bard

Prepared for Publication

14 TF-14

in the

Journal of Physical Chemistry

11 27 OCT 1980

9 Technical report

DTIC
ELECTE
NOV 14 1980

The University of Texas at Austin
Department of Chemistry
Austin, Texas 78712

October 29, 1980

Reproduction in whole or in part is permitted for any purpose of the United States Government.)

This document has been approved for public release and sale; its distribution is unlimited.

DDC FILE COPY

347830

80 11 13 006

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 14 /	2. GOVT ACCESSION NO. AD-A091	3. RECIPIENT'S CATALOG NUMBER 973
4. TITLE (and Subtitle) THE HETEROGENEOUS PHOTOCATALYTIC DECOMPOSITION OF BENZOIC ACID AND ADIPIC ACID ON PLATINIZED TiO ₂ POWDER. THE PHOTO-KOLBE DECARBOXYLATIVE ROUTE TO THE BREAKDOWN OF THE BENZENE RING AND TO THE PRODUCTION OF BUTANE.		5. TYPE OF REPORT & PERIOD COVERED 1 Sept. 1980 to 31 Aug. 1981
7. AUTHOR(s) I. Izumi, Fu-Ren F. Fan, Allen J. Bard		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry University of Texas at Austin Austin, TX 78712		8. CONTRACT OR GRANT NUMBER(s) N00014-78-C-0592 /
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 800 N. Quincy Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE October 29, 1980
		13. NUMBER OF PAGES 35
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) This document has been approved for public release and sale; its distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Prepared for publication in the Journal of Physical Chemistry		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) photocatalytic photo-Kolbe decarboxylative		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The heterogeneous photocatalytic decomposition of adipic acid in deaerated aqueous solutions containing a suspension of platinized TiO ₂ (anatase) powder leads to the formation of CO ₂ and butane with lesser amounts of valeric acid and negligibly small quantities of oligomeric materials. A mechanism for this photo-Kolbe reaction, which yields different products than the electrochemical Kolbe reaction, is proposed. The photodecomposition of benzoic acid in oxygen-containing solution at platinized TiO ₂ was also investigated. The reaction product is predominantly		

DD FORM 1473

JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

CO₂, with intermediate production of salicylic acid and phenol. A mechanism for the reaction based on photogeneration of hydroxyl radicals and adsorption of intermediates on the powder surface is proposed.

↗

Unclassified

10-12-80

The Heterogeneous Photocatalytic Decomposition of Benzoic
Acid and Adipic Acid on Platinized TiO_2 Powder. The
Photo-Kolbe Decarboxylative Route to the Breakdown of the
Benzene Ring and to the Production of Butane.

Ikuichiro Izumi, Fu-Ren F. Fan and Allen J. Bard

Department of Chemistry

The University of Texas at Austin

Austin, Texas 78712

(ABSTRACT)

The heterogeneous photocatalytic decomposition of adipic acid in deaerated aqueous solutions containing a suspension of platinized TiO_2 (anatase) powder leads to the formation of CO_2 and butane with lesser amounts of valeric acid and negligibly small quantities of oligomeric materials. A mechanism for this photo-Kolbe reaction, which yields different products than the electrochemical Kolbe reaction, is proposed.

The photodecomposition of benzoic acid in oxygen-containing solution at platinized TiO_2 was also investigated. The reaction product is predominantly CO_2 , with intermediate production of salicylic acid and phenol. A mechanism for the reaction based on photogeneration of hydroxyl radicals and adsorption of intermediates on the powder surface is proposed.

(End of Abstract)


Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
ERIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Avail and/or	
Dist Special	
A	

Introduction

Semiconductor materials are currently of much interest in electrochemical systems which can utilize solar energy for the production of electricity or useful chemical species. Recently semiconductor powders suspended in solution have been used to carry out heterogeneous photocatalytic and photosynthetic processes.¹ For example, applications of particulate semiconductors, e.g., TiO_2 and ZnO , to photocatalytic oxidation of cyanide,^{2,3} sulfite,³ acetate⁴ and other substances^{5,6} have demonstrated the versatility and ease of application of these methods. Recent studies from this laboratory have shown that irradiation of reaction mixtures containing suspended platinized TiO_2 (Pt/TiO_2) powders can promote several photocatalytic and photosynthetic reactions, such as the photo-Kolbe reaction, in which acetic acid is decomposed to methane and carbon dioxide,^{4,6} and even the photosynthesis of amino acids from methane-ammonia-water mixtures.⁷ To extend the scope of synthetic methods at illuminated semiconductor powders, we describe here the heterogeneous photooxidation of benzoic acid on Pt/TiO_2 powders in the presence of oxygen, and also the heterogeneous photocatalytic decomposition of adipic acid in deaerated aqueous solution.

The oxidation of benzoic acid has been demonstrated by the thermal decomposition of the cupric or molybdenum salt to phenol and carbon dioxide,⁸ by the radiolysis of aqueous solutions of benzoic acid or benzoate to monohydroxylated compounds and carbon dioxide derived from the carboxyl group,⁹⁻¹¹ and by the Kolbe electrolysis in nonaqueous solvents to products due to the intermediacy of benzoyloxy and/or phenyl radicals.¹² We report here that the photocatalytic oxidation of benzoic acid in aqueous solutions containing suspended Pt/TiO_2 powders involves the breakdown of the benzene ring through the addition of hydroxyl radicals to aromatic rings (unlike the usual electrochemical Kolbe reactions described above).

The electrolysis of dicarboxylic acids in aqueous media has been reported to yield olefins and alcohols, containing two carbons less than the starting material.¹³ We report here the heterogeneous photocatalytic decomposition of adipic acid, a six-carbon saturated aliphatic dicarboxylic acid, on Pt/TiO₂ to yield n-butane, valeric acid and CO₂ (eq. 1).



This predominant decarboxylation reaction to yield an uncoupled alkane thus follows previous studies from this laboratory in which unactivated monocarboxylic acids at ambient temperature are decomposed efficiently to the corresponding alkanes in a reaction pathway different from the electrochemical one.

Experimental Section

Materials. Benzoic acid (reagent grade, Matheson, Coleman and Bell), salicylic acid (reagent grade, Baker and Adamson), sodium hydroxide (analytical reagent grade, Mallinckrodt Chemicals), barium hydroxide (reagent grade, MC & B) and adipic acid (reagent grade, Baker Chemical Co.) were used without further purification. Triply distilled water was used to prepare aqueous solutions. All solvents and other chemicals used were reagent or spectrophotometric grade and were used without further purification. The cation exchange resin (Dowex 50W-X8, Baker Chemical Co.) was used after swelling with triply distilled water and exchanging Na⁺ ions with H⁺ ions. The platinized TiO₂ powders were made by photodecomposition of hexachloroplatinic acid onto TiO₂ powders (reagent grade, Matheson, Coleman and Bell, 125-250 μm) and contained 10% platinum by weight.¹⁴

Apparatus. A 2500 W Xe-Hg lamp (Model UF30KK, Christie Electric Corp., Los Angeles, Calif.), operated at 1600 W, was used as the light source for all preparative runs; a 450 W Xe lamp with Model 6242 power supply (Oriel Corp., Stamford, Conn.) served in several analytical runs. The reaction cell with a flat window for irradiation and the water bath were both of Pyrex; the bath temperature usually was set to 27±1°C. Irradiation was performed by illuminating the

sample (a stirred suspension of typically 100 mg of powder in 25 mL solution) through the water bath and the reaction cell. GC-Mass spectra of reaction gases were obtained with an automated Gas Chromatograph/EI-CI Mass Spectrometer System (Finnigan, Model 2000). Infrared spectra were taken on a Beckman IR-9 spectrophotometer. UV-visible spectra were recorded with a Cary Model 14 spectrophotometer. Electrochemical experiments were performed using PAR Model 173 Potentiostat (Princeton Applied Research, Princeton, NJ) and a PAR Model 173 Universal Programmer. Fluorescence measurements were made with an Aminco-Bowman spectrophotofluorometer.

Product Analysis. (a) A typical preparative experiment for the photooxidation of benzoic acid consisted of illuminating 25 mL of a solution containing 0.305 g (0.10 M) benzoic acid, 10 mL of 0.20 M NaOH, distilled water and 100 mg of 10% platinized TiO_2 powder kept in suspension by bubbling oxygen through the solution. The gases produced during the irradiation under O_2 were collected in a mercury-containing gas volumetric apparatus.¹⁵ After termination of photolysis, a directly attached, evacuated gas sample cell for use in analysis by GC-Mass spectrometry was filled with the gas mixture in the volumetric apparatus. The rate of carbon dioxide evolution was determined gravimetrically in another preparative run. The reaction gases were swept out of the reaction vessel with a stream of oxygen and were bubbled through a saturated solution of $\text{Ba}(\text{OH})_2$ in 0.2 M sodium hydroxide. The precipitated BaCO_3 was filtered off, washed with distilled water, dried at 120°C , and weighed. The reaction mixture, that had a yellow-brown color after irradiation, was brought to pH 10 with 0.2 M NaOH and then extracted with ether. No neutral material and organic bases resulted from the ether layer. The aqueous layer was then extracted with carbon tetrachloride after being acidified to pH 1-2 with 1 M HCl. A small amount of resinous brown solid (solid (1)) formed at the interface between the CCl_4 and aqueous layers. The carbon tetrachloride layer was dried over Na_2SO_4 and carefully removed under reduced pressure at room temperature to give unreacted benzoic acid with m.p. $119\text{--}121^\circ\text{C}$ ($122\text{--}123^\circ\text{C}$ for

standard sample). The aqueous layer was extracted again with ether. The ether layer obtained here was treated by the same procedure as that of the CCl_4 layer described above to give a resinous yellowish solid (solid (2)). Na^+ ions in the aqueous layer were exchanged with H^+ ions through a column of cation exchange resin, and a resinous shiny brown solid (solid (3)) was obtained. For the determination of hydroxylated intermediates, a fluorimetric method was employed, as follows. The reaction mixture was extracted with carbon tetrachloride after being acidified to pH 1-2 with 1 M HCl to remove colored products into the aqueous layer. The CCl_4 layer was extracted with 5 wt % sodium bicarbonate and then the aqueous layer, adjusted to pH 5, was examined in the spectrofluorometer.

(b) Fenton Reactions: The reaction between Fenton's reagent and benzoate were carried out as described by Cier, et. al.¹⁶ 5 mmol benzoic acid and 5 mmol NaOH were dissolved in 75 mL of H_2O . The reaction chamber was a one-compartment cell fitted with three side-arms (one for nitrogen gas input, one for gas output and the other with a septum for injecting reagents). The aqueous benzoate solution prepared above was put in the reaction chamber and deaerated for 30 min. 5 mmol of FeSO_4 was then added to the solution. After the solution became clear, 10 mmol H_2O_2 (~ 1.13 mL of 30% H_2O_2) was injected slowly into the reaction chamber with a syringe. After a reaction time of ~ 30 h, the CO_2 gas generated and the product mixture were collected, separated and analyzed as described above.

(c) A typical experiment for the photooxidation of adipic acid was performed as follows. In a Pyrex cell connected to a gas volumetric system, 25 mL of a mixture of 0.365 g (0.10 M) adipic acid, 12.5 mL of 0.2 M sodium hydroxide, triply distilled water and 100 mg of 10% platinized TiO_2 powder was irradiated with a 2.5 KW Xe-Hg lamp (operated at 1.6 Kw) while stirring at 45°C . Before and during irradiation the mixture was deaerated with purified nitrogen. After

irradiation for 40 h, the gaseous products, which were collected in a gas buret, were analyzed by GC-Mass spectrometry. The identities of the products were confirmed by comparison with a standard sample. The yield of CO_2 was determined quantitatively by trapping as BaCO_3 in a separate experiment. After irradiation the colorless reaction mixture, which had an unpleasant odor, was adjusted to pH 10 with 0.2 M NaOH and extracted with ether. The aqueous layer was acidified to pH 1-2 with 1 M HCl and then extracted with a large amount of benzene. The aqueous layer was further extracted with ether to yield unreacted adipic acid (m.p. $148-150^\circ\text{C}$ compared to $149-151^\circ\text{C}$ for a standard sample).¹⁷ The benzene layer was dried over Na_2SO_4 and evaporated under reduced pressure at 40°C to give a liquid product. The infrared spectrum of the liquid product was identical to that of a standard sample of valeric acid with strong absorption at wave numbers (cm^{-1}) of 530-560, 950, 1120, 1235, 1295, 1430, 1735, and 3000.

Results

Photocatalytic Decarboxylation of Benzoic Acid on Platinized TiO_2 Powders.

Illumination of suspensions of platinized TiO_2 powders in aqueous benzoic acid/sodium benzoate mixtures in the presence of oxygen leads to the observable evolution of carbon dioxide. After the illumination was stopped, the gaseous products, which were collected in a gas volumetric system, were analyzed by GC-Mass spectrometry. The mass spectrum: m/e, (rel intensity) consisted of signals due to CO_2 , 44 (44.9%), 16 (11.5%) with background signals due to O_2 , 32 (100%); and air contaminants, nitrogen, 28 (27.9%); and water, 18 (4.9%). No benzene signals were obtained. The only gaseous product evolved under illumination was thus CO_2 . The CO_2 yield (determined as BaCO_3) as a function of the time of illumination at $27 \pm 1^\circ\text{C}$, as shown in Fig. 1, gives a CO_2 evolution rate of 0.05 mmol/h. From the yellow-brown reaction mixture the unreacted benzoic acid was recovered by the separation procedure described in the experimental section. The

amount of the unreacted benzoic acid was also determined by titration of the solution. Following the procedure of Kaeding,¹⁸ the CCl_4 layer obtained in the separation procedure was titrated to the thymol blue end point with a standard solution of 0.2 M NaOH. The results from the gravimetric and titrimetric methods agreed to within $\sim 10\%$. The mole ratio of the CO_2 evolved to the benzoic acid consumed (from the titration results) is shown in Fig. 1. It increased from the value of ~ 1.8 after 3 h illumination to values above 4. Three kinds of resinous solids (1) - (3) were also obtained in the separation of the reaction mixture. Analysis of these products produced after 3 days illumination of benzoic acid/benzoate solution with Pt/TiO_2 powders showed that the 1.76 mg of yellowish solid (2) was soluble in ether and the 23.2 mg of shiny brown solid (3) was soluble in water and methanol. All resinous products were insoluble in CCl_4 . The infrared spectra of thin films of these solids showed the OH frequency at 3480 cm^{-1} , accompanied by two broad absorption waves at 2700 cm^{-1} and 3120 cm^{-1} , and the $>\text{C}=\text{O}$ frequency at 1725 cm^{-1} with a shoulder at 1630 cm^{-1} .¹⁹ The infrared spectrum was very similar to that of phenolic resin²⁰ particularly in the region of wave numbers higher than 1100. Thus the resinous products all appear to be the same kind of hydroxylated polymer containing carbonyl groups.

In a separate experiment, the yellow-brown reaction mixture after acidification was directly extracted with ether. After being dried over sodium sulfate and careful removal of most of the solvent, the concentrated ether solution was examined by gas chromatography (SE-30 column). No peaks corresponding to benzene, biphenyl, or phenyl benzoate were obtained.

A fluorimetric technique was used to identify and determine any hydroxylated benzoates.⁹ The reaction mixture, after removal of the brownish resinous products, showed an excitation spectrum maximized at 303 nm and an emission peak at 408 nm. The positions of the peaks and the shapes of the spectra are identical to those of

standard salicylic acid solutions. No p-hydroxybenzoate was found. The fluorescence spectrum of salicylic acid was shown to be unaffected by the presence of unreacted benzoic acid, so that the concentration of salicylic acid in an illuminated sample could be derived from the maximum fluorescence emission intensity relative to that of the standard sample. The yield of salicylic acid thus obtained is shown in Fig. 2. The initial formation rate (for ~30 min) of salicylic acid was $0.5 \mu\text{mol/h.mL}$; this rate decreased to about one-fifth of the initial value at longer times.

Several control experiments were carried out to eliminate possible effects of sample contamination and to investigate other paths for photodecarboxylation of benzoic acid under O_2 . Passing oxygen for 72 h in the dark through the same solution with Pt/TiO_2 under otherwise identical conditions as the irradiation experiments showed only a negligible amount of CO_2 production (less than 5.1×10^{-3} times that under the illumination, see Table I). A 58 h illumination under the same conditions but under nitrogen also produced a negligible amount of carbon dioxide (8.2×10^{-3} times of that under oxygen). Two experiments in nonaqueous solvents were performed as follows. A solution of benzoic acid in benzene under oxygen was illuminated and produced only a trace amount of CO_2 ($\sim 10^{-2}$ times that in water). However, a solution of benzoic acid/tetra-n-butylammonium benzoate in acetonitrile under illumination yielded a small amount of CO_2 (12.7% of that in water).

(Text continued on page 9)

When potassium ferricyanide was added to the deaerated aqueous solution containing benzoic acid/benzoate and Pt/TiO₂, which was then illuminated under nitrogen, CO₂ was produced in an amount ~15.1% of that under oxygen. Thus the photodecomposition rate under nitrogen increased by 18.4 times when potassium ferricyanide was present in the solution. Preliminary experiments concerning the reactions between Fenton's reagent, which produces hydroxyl radicals, and benzoate showed that carbon dioxide, phenol, and hydroxylated benzoate were the major products (Table 1). This demonstrates the possibility of at least the initial stages of the photodecomposition process occurring by attack of ·OH on benzoic acid and intermediates.

Photocatalytic Decarboxylation of Adipic Acid on Pt/TiO₂ Powders. Similar to the behavior of benzoic acid mentioned above, illumination of suspension of Pt/TiO₂ powders in aqueous adipic acid solutions leads to the observable evolution of CO₂. After irradiation for 40 h, the gaseous products were analyzed by GC-Mass spectrometry. The mass spectrum for the separated gas components showed signals corresponding to carbon dioxide, m/e = 44; n-butane, m/e (rel intensity) = 43(100), 41(31.8), 42(15.1), 58(14.0), 39(11.7); and hydrogen, respectively. The identity of n-butane was confirmed by comparison with a standard sample [43(100), 41(27.2), 42(12.8), 58(16.8), 39(9.6)]. No additional gaseous reaction products such as cyclobutane or butene were obtained. The amount of CO₂ evolved (determined as BaCO₃ in a separate experiment) as a function of time of irradiation is shown in Fig. 3. The rate of production of CO₂ was constant at 50 µmol/h. After irradiation the colorless reaction mixture was analyzed as mentioned in the experimental section. Only adipic acid and valeric acid were present in significant amounts. An analysis of the products showed that the ratio of adipic acid reacted : CO₂ evolved : valeric acid produced : n-butane produced was 1.0 : 1.75 : 0.25 : 0.76. Several control experiments in the absence of Pt/TiO₂ and without irradiation²¹ under similar conditions as described above resulted in only minute amounts of CO₂ corresponding to ~6 µmol/h.

Electrochemical Measurements. As shown in previous studies,^{4,6} the photocatalytic activity of suspended powders can be correlated with the behavior of semiconductor electrodes in photoelectrochemical (PEC) measurements.^{4,6} The current-potential (*i*-*V*) behavior of a rutile single crystal electrode in an aqueous solution (pH \sim 5) containing 20 mM benzoic acid, 80 mM sodium benzoate, and 0.5 M sodium perchlorate as the supporting electrolyte is shown in Fig. 4. In the dark, only a very small anodic current was observed on TiO₂ electrodes both in deaerated and in oxygen-saturated solutions (curves 1 and 2). Note, however, that in oxygen-saturated solutions, the TiO₂ electrodes showed higher cathodic background currents than in deaerated solutions, presumably because of oxygen reduction. Under illumination, the anodic current was substantially enhanced. The onset potential, V_{on} , of the photocurrent and the shape of the anodic photovoltammetric curves were essentially unaffected by the absence or the presence of oxygen or the benzoic acid/benzoate mixture (curves 3-5), with $V_{on} \sim -0.30$ V vs. SCE. Following the principles for photocatalyst design discussed previously,^{1b,1c} where the rate of reaction at the catalyst powder is determined by the system operating at a potential where the anodic and cathodic currents are equal in magnitude, TiO₂ powder alone, even in the presence of oxygen, is not expected to be a very efficient catalyst. The role of Pt was examined by observing the *i*-*V* curves of a Pt electrode in these solutions. The reduction of protons on Pt in the presence of benzoic acid occurs at potentials more negative than -0.40 V vs. SCE (curve 6), so that H⁺ reduction, even at Pt, is not a useful photocatalyst half reaction, as opposed to the results on aliphatic carboxylates. The reduction of oxygen on Pt (curve 7) occurs at potentials much more positive than either V_{on} or the potentials at which reduction of oxygen on TiO₂ occurs. Thus, the photocatalytic activity of TiO₂ powder for the oxidation of benzoic acid is substantially enhanced by the presence of Pt and oxygen.




The current-potential behavior of a rutile single crystal electrode in an aqueous solution (pH \sim 5) containing 0.10 M adipic acid half-neutralized with NaOH and 0.5 M sodium perchlorate as the supporting electrolyte is shown in Fig. 5. Thus, the photo-induced oxidation of adipic acid (presumably as the adipate ion) on an illuminated n-type TiO_2 rutile single crystal electrode takes place at slightly more negative potentials than the reduction of protons on platinum (see curves 1 and 3). Therefore, the photooxidation of adipate ions on n-type TiO_2 and the reduction of protons on platinum can easily take place simultaneously at the two electrodes under short circuit conditions, i.e., without applied potential. Moreover, the photooxidation of n-valeric acid, the intermediate in the photo-oxidation of adipic acid to n-butane, on TiO_2 and the reduction of protons on platinum can also be rationalized by similar voltammetric curves. Thus, as in previous studies,^{4,6} the Pt/ TiO_2 powders act as a multitude of small, short-circuited electrode systems.

Discussion

In the presence of oxygen, several n-type semiconductor powders have been shown to behave as photocatalysts and promote the oxidation of substrates.¹⁻⁶ Irradiation of a semiconductor with light of energy higher than the band gap results in creation of holes in the semiconductor valence band (VB) and electrons in the conduction band (CB) followed by trapping of the separated charges in shallow traps (tr) at the powder-solution interface.



As recently discussed in connection with the photo-Kolbe reaction at Pt/TiO₂ powder,⁴ adsorbed species, e.g., OH⁻, could also provide a site for trapping of the holes. These trapped carriers can recombine or the h_{tr}⁺ can be scavenged by oxidizable species (for example, H₂O, H₂O₂, C₆H₅COO⁻, or adipate ion), and e_{tr}⁻ by reducible species (for example, O₂ or H⁺) in the solution. Thus the following reactions appear reasonable for the photooxidation of benzoic acid (adsorption of intermediates on the powder surface is possible, but is not specifically indicated in the equations below):



The electrochemical measurements suggest that the reduction of H⁺ on Pt and the reduction of O₂ at TiO₂ do not occur at a high enough rate at the potentials where photooxidation of benzoate takes place for these to be effective half reactions at the catalyst particle. The role of the Pt for this reaction is thus to provide a site for the more efficient reduction of O₂ (eq. 7). In fact the photodecarboxylation of benzoate does not occur to an appreciable extent in deaerated solutions containing Pt/TiO₂ (Table I).²² The addition of ferri-cyanide to a deaerated solution to provide an alternate species which can be reduced causes decomposition of benzoate, but at a much smaller rate than in the presence of O₂. Thus, intermediates that form during the reduction of O₂ may also play a role in the oxidation process, as shown in reactions (7) - (9). Recent experiments involving spin trapping and electron spin resonance



spectroscopic detection of intermediates formed during irradiation of Pt/TiO₂ in aqueous solutions have demonstrated the intermediacy of $\cdot\text{OH}$ and HO₂ \cdot .²³

Since the mole ratio of CO₂ evolved to benzoic acid consumed is much larger than 1 (Fig. 1), breakdown of the benzene ring must be occurring. This possibility has been confirmed by experiments on the photooxidation of aerated solutions of benzene, where CO₂ production has been established. Detailed studies of the photocatalytic decomposition of hydrocarbons at Pt/TiO₂ have been reported.²⁴

The mode of decomposition of the benzene ring has not been established. However, the detection of salicylic acid in the experiments described here suggests that attack by $\cdot\text{OH}$ radicals is a likely route. The probable role of $\cdot\text{OH}$ in these reactions is also supported by experiments showing the reaction of benzoic acid with Fenton's reagent as well as earlier studies on the radiolysis of benzoic acid solution.^{10,11} The shape of the concentration-time profiles for salicylic acid production (Fig. 2) can be qualitatively explained. The salicylic acid, which results from attack on the parent benzoic acid by $\cdot\text{OH}$, builds to a steady concentration, since it is produced from the benzoic acid whose concentration does not change significantly, and is also converted to more highly oxidized products (ultimately CO₂) by reaction with $\cdot\text{OH}$, holes, or other intermediates.

Note that the photocatalytic decarboxylation of benzoate differs from that found with acetate⁴ and adipate under similar conditions (pH ~5), where decomposition even in the absence of O₂ occurs. This implies that reaction (6) might be more favorable with aliphatic carboxylic acids than with aromatic acids. Although the observed onset potential for oxidation of adipic acid at n-TiO₂ is slightly more negative than for benzoic acid, this effect alone is probably insufficient to account for this difference in behavior. At this stage the most likely explanation is that aromatic intermediates in the benzoate system adsorb on the


Pt sites and decrease the rate of the hydrogen evolution reaction. It is well-known that many adsorbed organic species can "poison" Pt electrodes towards proton reduction.²⁵ Note that only a small increase in the hydrogen overpotential can cause a significant decrease in the reaction rate at the Pt/TiO₂ powders. The lower molecular weight intermediates of adipic acid may never leave the TiO₂-sites and are less likely to poison the proton reduction reaction. Oxidation of adipic acid might take place through the following reactions:



The breakdown of valeric acid then follows a similar route, leading to butane.

The products found for the adipic acid oxidation are useful in providing information about the path of the photo-Kolbe reaction, since several possible routes are possible, as shown in the scheme below:

General scheme of adipic acid decarboxylation



The Kolbe electrolysis of dicarboxylic acids has been reported to occur via carbonium ions (VII) and to produce alcohols (VIII), lactones (IX), and olefins (X).^{13,26} Homogeneous photochemical reactions of dicarboxylic acids either in FeCl_3 solution^{27a} or with uranyl salt as a sensitizer^{27b} usually produce monocarboxylic acids. The results reported here showed that n-butane (II) was the predominant product during the photocatalytic decarboxylation of the adipic acid on Pt/TiO_2 with no cyclobutane (V) or oligomers (VI) obtained. This suggests that the diradical (III) was not formed. Whether any dimers (I) were formed is still not clear and bears further investigation. However their yield is very low, consistent with previous findings that radical intermediates react with $\text{H}\cdot$ or are reduced before extensive dimerization occurs. This probably can be attributed to the rather low surface density of adsorbed alkyl radicals at the prevailing light flux and catalyst surface area. The density of active sites on the catalyst powders may also be quite small.²⁸ The lifetime of these adsorbed radicals is also sufficiently small that further oxidation to the carbonium ion by another photogenerated hole does not occur. This accounts for the difference between the products of the electrochemical Kolbe reaction (olefins and alcohols)¹³ or oligomers (e.g. the Brown-Walker reaction)²⁹ and those of the photo-Kolbe reaction. The absence of appreciable amount of intermediates (e.g. valeric acid in the case of adipic acid and salicylic acid in the case of benzoic acid) in the oxidative breakdown probably indicates they largely remain adsorbed on TiO_2 sites on the particles and are decomposed before they escape to the bulk solution.

Because the predominant photocatalytic breakdown of benzoic acid forms CO_2 , and not the usual electrochemical Kolbe type intermediates, e.g., biphenyl and phenyl benzoate, such a process may be of use in the treatment of waste streams containing this intermediate, as has been suggested previously for removal of cyanide, sulfite³ and aliphatic carboxylates.⁴

Acknowledgment

The support of this research by the Educational Ministry of Japan (to I.I.), by the Office of Naval Research (to F.F.F.), and the National Science Foundation (CHE 8000682) is gratefully appreciated.

References and Notes

1. See e.g., (a) Freund, T.; Gomes, W.P. Catal. Rev. 1969, 3, 1. (b) Bard, A.J. J. Photochem. 1979, 10, 59. (c) Bard, A.J. Science, 1980, 207, 139, and references therein. (d) Formenti, M.; Teichner, S.J. Specialists Periodical Reports (The Chemical Society, London) 1979, 2, Chapter 4 (in press).
2. Frank, S.N.; Bard, A.J. J. Am. Chem. Soc. 1977, 99, 4667.
3. Frank, S.N.; Bard, A.J. J. Phys. Chem. 1977, 81, 1484.
4. Kraeutler, B.; Bard, A.J. J. Am. Chem. Soc. 1978, 100, 5985.
5. (a) Watanabe, T.; Takizawa, T.; Honda, K. J. Phys. Chem. 1977, 81, 1845. (b) Miyake, M.; Yoneyama, H.; Tamura, H. Bull. Chem. Soc. Japan 1977, 50, 1492. (c) Miyake, M.; Yoneyama, H.; Tamura, H. Denki Kagaku 1977, 45, 411. (d) Inoue, T.; Fujishima, A.; Kenishi, S.; Honda, K. Nature 1979, 277, 637. (e) Hemminger, J.C.; Carr, R.; Somarjai, G.A. Chem. Phys. Lett. 1978, 57, 100.
6. Kraeutler, B.; Bard, A.J. J. Am. Chem. Soc. 1978, 100, 2239.
7. Reiche, H.; Bard, A.J. J. Am. Chem. Soc. 1979, 101, 3127.
8. (a) Kaeding, W.W. J. Org. Chem. 1961, 26, 3144. (b) Kaeding, W.W.; Lindblom, R.O.; Temple, R.G. Ind. Eng. Chem. 1961, 53, 805. (c) Dosovitskii, E.I.; Ioffe, I.I. Kinetika i Kataliz 1964, 5(6), 1104. (d) Navazio; Giancarlo; Scipioni; Andrea Chim. Ind. 1968, 50 (10), 1086.
9. Armstrong, W.A.; Black, B.A.; Grant, D.W. J. Phys. Chem. 1960, 64, 1415.
10. Matthews, R.W.; Sangster, D.F. J. Phys. Chem. 1965, 69, 1938; Loeff, I.; Swallow, A.J. J. Phys. Chem. 1964, 36, 549.
11. Downes, A.M. Australian J. Chem. 1958, 11, 154.
12. (a) Fichter, F.; Stenzl, H. Helv. Chim. Acta 1939, 22, 970. (b) Wilshire, J.F.K. Australian J. Chem. 1963, 16, 432. (c) Koyama, K.; Yoshida, K.; Tsutsumi, S. Bull. Chem. Soc. Japan 1966, 39, 516.

13. (a) Vanzetti, B.L. Gazz. Chim. Ital. 1904, 34, II, 504; ibid. 1907, 37, II, 338; ibid. 1907, 37, II, 386. (b) Weedon, B.C.L. Quart. Rev. (London) 1952, 6, 380.
14. Kraeutler, B.; Bard, A.J. J. Am. Chem. Soc. 1978, 100, 4317.
15. This gas volumetric system was identical to that reported in reference 4.
16. Cier, A.; Nofre, C.; Ranc, M.; Lefier, A. Bull. Soc. Chim. France 1959, 1523.
17. The ether layer obtained here was dried over anhydrous sodium sulfate and evaporated carefully under reduced pressure at room temperature to give a white crystal, adipic acid.
18. Kaeding, W.W. J. Org. Chem. 1961, 26, 3144.
19. Except for these absorption peaks, some distinct absorption peaks were also observed at 660, 725, 785, 1135, 1250, 1295, 1400 and 1445 cm^{-1} .
20. Referred to as phenol-resorcinol-formaldehyde resin (0.5:0.5:0.6, alkaline condensed); Hummel, D.O.; Schall, F. "Infrared Analysis of Polymers, Resins and Additives - An Atlas," Vol. I, Part 2, Wiley-Interscience: New York, 1969; spectrum number 321.
21. The control experiment in the dark was carried out with bubbling N_2 for one day. No CO_2 was precipitated as BaCO_3 .
22. A negligibly small amount of CO_2 may result from the adsorbed oxygen on powders.
23. Jaeger, C.D.; Bard, A.J. J. Phys. Chem. 1979, 83, 3746.
24. Izumi, I.; Dunn, W. W.; Wilbourn, K. O.; Fan, F-R. F.; Bard, A. J. J. Phys. Chem. 1980, 84, 0000 (in press).
25. See e.g. Vetter, K. J. "Electrochemical Kinetics," Academic Press: New York, 1967, pp. 567-570.
26. Overberger, C.G.; Kabasakalian, P. J. Am. Chem. Soc. 1957, 79, 3182.
27. (a) Kuhnle, J.A.; Lundin, R.E.; Waiss, A.C. Jr. J. Chem. Soc. 1972, Chem. Commun. 5, 287. (b) Heckler, G.E.; Taylor, A.E.; Jensen, C.; Percival, D.; Jensen, R.; Fung, P. J. Phys. Chem. 1963, 67, 1.

28. Photoelectrophoresis experiments on anatase powders have shown that the photogenerated positive charge carriers, presumably trapped at the interfacial sites, were ~ 3500 electronic charges on a powder of diameter $\sim 1\mu\text{m}$. (See Takahashi, A.; Aikawa, Y.; Toyoshima, Y.; Sujigara, M. J. Phys. Chem. 1979, 83, 2854; Dunn, W. W.; Aikawa, Y.; Bard, A. J.; manuscript in preparation.
29. (a) Adamov, A.A.; Kovsman, E.P.; Freidlin, G.H.; Tarkhanov, G.A. Electrokhimiya 1975, 11, 1973. (b) Kovsman, E.P.; Freidlin, G.N.; Tyurin, Yu. M. Khim. Prom. (Moscow) 1973, 49, 16. (c) Weinberg, N.L. (ed.) "Technique of Electroorganic Synthesis," Vol. V, Part I, John Wiley & Sons: New York, 1974; p. 795.

Table I. Heterogeneous photocatalytic carbon dioxide evolution under illumination at platinized TiO_2 powder and control experiments.

<u>Pt/TiO₂ Powder</u>	<u>Solution Composition</u>	<u>Conditions</u>	<u>Amount of CO₂ evolved, mmole</u>	<u>Rate of CO₂ evolved, mmole/h</u>
Yes	0.020 M HBz ^a 0.080 M NaBz in water	3-96 h illuminated under O ₂	0.350 - 4.10	$\sim 5.0 \times 10^{-2}$
Yes	0.020 M HBz 0.080 M NaBz in water	72 h in the dark under O ₂	0.0182	2.5×10^{-4}
Yes	0.020 M HBz 0.080 M NaBz in water	58 h illuminated under N ₂	0.0238	4.1×10^{-4}
Yes	0.10 M HBz in benzene	72 h illuminated under O ₂	0.162	2.3×10^{-3}
Yes	0.125 M HBz 0.125 M tetra-n- butylammonium benzoate in acetonitrile	48 h illuminated under O ₂	0.304	6.3×10^{-3}
Yes	0.020 M HBz 0.080 M NaBz 0.10 M K ₃ Fe(CN) ₆ in water	19.5 h illuminated under N ₂	0.147	7.54×10^{-3}
No ^b	0.060 M NaBz in water	Fenton's reagent	0.40	---

^aHBz is benzoic acid; NaBz is sodium benzoate.

^bWith Fenton's reagent (0.06 M FeSO₄ and 0.12 M H₂O₂). In addition to CO₂ 0.12 mmol phenol and 6.8×10^{-3} mmol of salicylic acid were formed.

Figure Captions

Fig. 1 CO_2 yield (circles) and the mole ratio of CO_2 evolved to benzoic acid consumed (triangles) as functions of the time of illumination. Oxygen-saturated aqueous solutions containing 20 mM benzoic acid and 80 mM sodium benzoate with 100 mg of suspended 10% platinized anatase powder were irradiated with a 2.5 kW Xe lamp (operated at 1.6 kW) at 27°C .

Fig. 2 Salicylic acid yield as a function of the time of illumination. Experimental conditions same as in Fig. 1.

Fig. 3 CO_2 yield as a function of the time of illumination of 37.5 mL 0.067 M deoxygenated adipate solutions with 100 mg of suspended 10% platinized anatase powders irradiated with a 2.5 kW Xe lamp (operated at 1.6 kW) at $\sim 40^\circ\text{C}$.

Fig. 4 Voltammetric curves at Pt and n-type TiO_2 single crystal electrodes. A 450-W Xe lamp with a water filter was used as the light source. Scan rate, 100 mV/sec. Initial potentials at positive extremes.

1. TiO_2 in the dark under N_2 ; 0.5 M NaClO_4 containing 20 mM benzoic acid and 80 mM sodium benzoate.
2. TiO_2 in the dark under O_2 ; same solution as in 1.
3. TiO_2 in the light under N_2 ; same solution as in 1.
4. TiO_2 in the light under O_2 ; same solution as in 1.
5. TiO_2 in the light under N_2 ; 0.5 M NaClO_4 .
6. Pt; under N_2 ; same solution as in 1.
7. Pt; under O_2 ; same solution as in 1.

Fig. 5 Current-potential curves at Pt and n- TiO_2 single crystal electrodes in 0.5 M NaClO_4 solutions containing 0.10 M adipic acid half-neutralized

with NaOH. A 450 W Xe lamp fitted with a water infrared filter was the light source. Scan rate, 100 mV/sec.

1. On Pt; Initial potential, 0.20 V vs. SCE.
2. On n-TiO₂ in the dark; Initial potential, -0.31 V vs. SCE.
3. On n-TiO₂ in the light; Initial potential, -0.31 V vs. SCE.

Curves 2 and 3 use the left-handed current scale and curve 1 uses the right-handed scale.




Fig 1




Fig 2




Fig 3




Fig. 4




Fig 5

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 472 800 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Branch Office Attn: Dr. George Sandoz 536 S. Clark Street Chicago, Illinois 60605	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Area Office Attn: Scientific Dept. 715 Broadway New York, New York 10003	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
ONR Western Regional Office 1030 East Green Street Pasadena, California 91106	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
ONR Eastern/Central Regional Office Attn: Dr. L. H. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Office of Naval Research Attn: Dr. Richard S. Miller 800 N. Quincy Street Arlington, Virginia 22217	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1

TECHNICAL REPORT DISTRIBUTION LIST, GENNo.
Copies

Dr. Rudolph J. Marcus
Office of Naval Research
Scientific Liaison Group
American Embassy
APO San Francisco 96503

1

Mr. James Kelley
DTNSRDC Code 2803
Annapolis, Maryland 21402

1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Paul Delahav Department of Chemistry New York University New York, New York 10003	1	Dr. P. J. Hendra Department of Chemistry University of Southampton Southampton SO9 5NH United Kingdom	1
Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 44106	1	Dr. Sam Perone Department of Chemistry Purdue University West Lafayette, Indiana 47907	1
Dr. D. N. Bennion Department of Chemical Engineering Brigham Young University Provo, Utah 84602	1	Dr. Royce W. Murray Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1
Dr. R. A. Marcus Department of Chemistry California Institute of Technology Pasadena, California 91125	1	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
Dr. J. J. Auburn Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. C. E. Mueller The Electrochemistry Branch Materials Division, Research & Technology Department Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910	1
Dr. Adam Heller Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. G. Goodman Globe-Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. T. Katan Lockheed Missiles & Space Co, Inc. P.O. Box 504 Sunnyvale, California 94088	1	Dr. J. Boechler Electrochimica Corporation Attention: Technical Library 2485 Charleston Road Mountain View, California 94040	1
Dr. Joseph Singer, Code 302-1 NASA-Lewis 21000 Brookpark Road Cleveland, Ohio 44135	1	Dr. P. P. Schmidt Department of Chemistry Oakland University Rochester, Michigan 48063	1
Dr. B. Brummer EIC Incorporated 55 Chapel Street Newton, Massachusetts 02158	1	Dr. H. Richtol Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1
Library P. R. Mallory and Company, Inc. Northwest Industrial Park Burlington, Massachusetts 01803	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. A. B. Ellis Chemistry Department University of Wisconsin Madison, Wisconsin 53706	1	Dr. R. P. Van Duyne Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. M. Wrighton Chemistry Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. B. Stanley Pons Department of Chemistry University of Alberta Edmonton, Alberta CANADA T6G 2G2	1
Larry E. Plew Naval Weapons Support Center Code 30736, Building 2906 Crane, Indiana 47522	1	Dr. Michael J. Weaver Department of Chemistry Michigan State University East Lansing, Michigan 48824	1
S. Ruby DOE (STOR) 600 E Street Washington, D.C. 20545	1	Dr. R. David Rauh EIC Corporation 55 Chapel Street Newton, Massachusetts 02158	1
Dr. Aaron Wold Brown University Department of Chemistry Providence, Rhode Island 02192	1	Dr. J. David Margerum Research Laboratories Division Hughes Aircraft Company 3011 Malibu Canyon Road Malibu, California 90265	1
Dr. R. C. Chudacek McGraw-Edison Company Edison Battery Division Post Office Box 28 Bloomfield, New Jersey 07003	1	Dr. Martin Fleischmann Department of Chemistry University of Southampton Southampton 509 5NH England	1
Dr. A. J. Bard University of Texas Department of Chemistry Austin, Texas 78712	1	Dr. Janet Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. M. M. Nicholson Electronics Research Center Rockwell International 3370 Miraloma Avenue Anaheim, California	1	Dr. R. A. Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. Donald W. Ernst Naval Surface Weapons Center Code R-33 White Oak Laboratory Silver Spring, Maryland 20910	1	Mr. James R. Moden Naval Underwater Systems Center Code 3632 Newport, Rhode Island 02840	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. R. Nowak Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Dr. John Kincaid Department of the Navy Strategic Systems Project Office Room 901 Washington, DC 20376	1
Dr. John F. Houlihan Shenango Valley Campus Pennsylvania State University Sharon, Pennsylvania 16146	1	M. L. Robertson Manager, Electrochemical Power Sonices Division Naval Weapons Support Center Crane, Indiana 47522	1
Dr. M. G. Sceats Department of Chemistry University of Rochester Rochester, New York 14627	1	Dr. Elton Cairns Energy & Environment Division Lawrence Berkeley Laboratory University of California Berkeley, California 94720	1
Dr. D. F. Shriver Department of Chemistry Northwestern University Evanston, Illinois 60201	1	Dr. Bernard Spielvogel U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709	1
Dr. D. H. Whitmore Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Dr. Denton Elliott Air Force Office of Scientific Research Bldg. 104 Bolling AFB Washington, DC 20332	1
Dr. Alan Bewick Department of Chemistry The University Southampton, SO9 5NH England	1		
Dr. A. Himy NAVSEA-5433 NC #4 2541 Jefferson Davis Highway Arlington, Virginia 20362	1		