



19) BR-77779 18 DRIC 14 RAE-TM- MAT-358 ROYAL BLISHMENT memors 358 Technical 1') 19 Received for printing 16 January 1981 APPLICATIONS OF THE MICROSCAN 9 MICROANALYSER. 10 P. D/Pitcher 1) JAN SI

SUPPLARY

The basic principles of electron microprobe analysis are outlined, and the essential features of the Microscan 9 instrument described. Applications of the M9 are illustrated by means of practical examples.

ę

Copyright C Controller HNSO London 1981

370430 sit

LIST OF CONTENTS

1	INTR		3		
2	BASI	CIPLES		3	
3	DESC	N OF THE M9 SYSTEM		3	
4	APPL	ICATIO	18		5
	4.1	Quali	tative and semi-quantitative analysis		5
		4.1.1	Energy dispersive analysis		5
		4.1.2	X-ray images		5
		4.1.3	Line scans		6
		4.1.4	Step scanning of specimen		6
		4.1.5	Spectral scanning		6
	4.2	Fully	quantitative analysis		7
5	CONCLUDING REMARKS		REMARKS		8
Illus	trati	ons		Figures	1-10

Report documentation page

2

inside back cover

Page

NTIS GRA&I T DTIC TAB [] Unannounced [] Justification By Distribution/ Available to Codes /or	Accession For	,
DTIC TAB [] Unannounced [] Justification Re Distribution/ Available to Codes /or	NTIS GRAAI	X
Unannounced [] Justification By Distribution/ Available to Codes /or	DTIC TAB	เปิ
Justification Ry Distribution/ Avail as to Codes /or	Unannounced	[]
By Distant int/ Available to Chies /or	Justification	L
By Distribution/ Avril site Codes /or	<u>-</u>	
Distributions/ Avril site Codes /or	By	
Awrite of the Childs /or	_Distant From	
/or	Avr 11 - 11 t	Chies
	•	/or
Dist . L	Dist .	1
Λ_{-}		
HT I	WY I	
V \		•

ŧ

2H Hat 358

INTRODUCTION

1

The M9 is a computer-controlled electron probe microanalyser which is used to obtain information on the chemical composition of small regions, typically down to about $1\mu m$ diameter. The purpose of this Memorandum is to outline the principles of operation of the instrument and to indicate its functions and capabilities with some typical examples of its applications.

2 BASIC PRINCIPLES

A sufficiently energetic beam of electrons (the electron probe) incident on a specimen will generate X-rays which have energies and wavelengths characteristic of the individual elements of which the specimen is composed. These X-rays are analysed to yield information on the elements present in the specimen. There are two methods of detecting and counting the X-rays; these are known as energy dispersive and wavelength dispersive systems.

In the energy dispersive system, X-rays pass through a protective beryllium window into a solid state detector of silicon treated with lithium and held at liquid nitrogen temperature. The X-rays interact with the silicon and produce voltage pulses, the amplitudes of which are proportional to the X-ray energy. The pulses are amplified and fed into a multichannel analyser which separates pulses of different amplitude into several hundred channels and allows them to accumulate. Thus a spectrum is built up, and when the multichannel analyser is calibrated, peaks corresponding to the elements present in the specimen are obtained. Essentially, a rapid, qualitative or semi-quantitative simultaneous analysis of all the elements in the specimen (except those with atomic number Z < 11) may be performed, and a visual presentation of the entire spectrum is available when data accumulation is initiated.

In the wavelength dispersive system, crystals are used to diffract X-rays of a particular wavelength into counters (ie when Bragg's Law is obeyed). Thus only X-rays from the element under consideration are analysed at any one time. The counter is a gas-filled proportional type which produces pulses whose voltage is proportional to the energy of the X-rays, and so an X-ray count rate (counts per second) is obtained for a particular element in the specimen.

In quantitative work, the X-ray count rates for elements in the specimen are compared to those from standards of known composition (often pure elements), while maintaining constant operating conditions. To a first approximation, the ratio of count rates for the specimen to that for the standard gives the concentration of the element in the specimen. However, in practice, differences between the specimen and standard influence X-ray generation and corrections have to be made. Much effort has gone into creating methods for making the corrections, and these are known as ZAF correction procedures since they allow for atomic number (Z), absorption (A) and fluoresence (F) effects.

3 DESCRIPTION OF THE M9 SYSTEM

The M9 is a computer-controlled instrument with an energy dispersive detector and two fully focussing spectrometers each containing three crystals. The fact that the

spectrometers are fully focussing means that for all Bragg angles covered $(15-66^{\circ})$, the X-ray source, the crystal surface and the X-ray counter all lie on the same circle (Rowland circle). Each spectrometer has two counters in tandem; one xenon gas sealed counter for heavy elements, and in front of that either an ordinary flow counter (Channel A) or a light element flow counter (Channel B). The flow counters use argon - 10% methane gas. All elements with $Z \ge 11$ can be detected with the energy dispersive system, while the spectrometers cover all elements from boron (Z = 5) to uranium (Z = 92).

4

The specimen stage, spectrometers and X-ray counters are controlled with commands given to the computer via the teletype, with manual operation by a 'tracker ball' for stage and spectrometer movements when necessary. Electron imaging functions (including image processing) are basically as for a normal scanning electron microscope with area scans, line scans and spot mode possible. The accelerating voltage can be varied from 1-60 kV, with probe currents from about 10^{-9} up to 5 x 10^{-6} A possible. Polaroid and 35mm cameras are available for image recording, and an X-Y plotter is used to record energy dispersive X-ray spectra. In addition, X-ray peaks from the spectrometers can be acquired using a chart recorder.

There is a binocular microscope for preliminary surveys and setting up, as well as a monocular microscope for viewing the specimen while analysis is in progress. A Faraday cage can be inserted into the electron beam, and the probe current set to the required level by monitoring it on a digital meter. This meter is also used to monitor specimen current, magnification and accelerating voltage.

The computer is also used to perform other operating functions, eg move the stage to specimen change position, insert or withdraw the Faraday cage. Additionally, data collection and processing is handled by the computer, and results printed out on the teletype. An important feature is the ZAF program which enables corrected quantitative data to be acquired. All the necessary data for the ZAF corrections is held in the computer memory, in the 'standards tables', which also contain information for measurements on standards and unknowns, eg stage co-ordinates of standard, spectrometer channel and crystal, Bragg angle, counter variables, standard count rate, kV, probe current. Approximate data in the tables is updated each time the standards are measured, ie Bragg angle, probe current, kV, standard count rate, and then referred to during measurements on the unknown.

Stage and spectrometer repeatability are $\pm 2 \ \mu m$ and $\pm 0.00167^{\circ}$, respectively, with the absolute Bragg angle accurate to $\pm 0.042^{\circ}$. Quoted values for limit of detectability are 0.001% for Cu and 0.01% for C at an absorbed current of 0.1 μ A. Absolute accuracy for quantitative analysis is a function of specimen, standard quality, operating conditions and efficiency of the ZAF correction procedure. Normally totals for an analysis should be 100% \pm 1 or 2%.

The specimen is usually mounted using conventional metallographic techniques, and the surface should be clean, flat and polished. It is placed in a specimen holder, with the standards block, and is situated normal to the electron beam in the instrument. NonIM Mat 3

conducting specimens need to be made conducting, eg by carbon coating. Qualitative work is possible on fracture surfaces.

4 APPLICATIONS

There are basically two types of work which can be carried out; (a) qualitative or semi-quantitative and (b) fully quantitative analysis. Examples of applications will be given for these two types in turn.

4.1 Qualitative and semi-quantitative analysis

Initially it is often desired to ascertain or confirm the elements present in the specimen. An area of interest is first selected using the optical microscope or TV mode electron image at low magnification. The specimen position is set by focussing the optical image using the Z-axis control, and the kV and probe current set as required.

Electron images of a high strength Al-Zn-Mg-Cu alloy containing inclusion stringers, formed using backscattered electrons and the absorbed specimen current are shown in Fig 1a&b respectively. Backscattered electrons are usually used, although the absorbed current image is sometimes useful for showing extra detail. Additional image processing (gamma control, grey levels etc) are also possible. Initial element identification is best done using the energy dispersive system.

4.1.1 Energy dispersive analysis

The spectra, obtained on the X-Y plotter, for spot analyses from the matrix and two types of inclusion are shown in Figs 2 to 4. The analysis points are indicated by A, B and C in Fig 1. Peaks corresponding to Al, Cu and Zn are readily seen in Fig 2, and that of Mg is partly overlapped by the Al peak. (The argon peak is anomolous, possibly originating from the gas of the proportional counters.) The spectra were obtained under identical operating conditions and hence differences in peak heights indicate the relative amounts of each element for each spot analysed, is spot B is rich in Fe and Cu, and spot C rich in Mg and Si. Thus semi-quantitative information on the chemical composition of the inclusions has been obtained. It is of course also possible to obtain spectra for area and line scans, as well as for the spot analyses.

4.1.2 X-ray images

X-ray images are produced by using the computer to set the appropriate spectrometer to accept the characteristic X-rays of interest, and displaying each pulse as a bright spot on the visual display, which is scanned in synchronisation with the electron probe. Thus the image consists of a large number of spots, the brighter areas indicating a higher concentration of the element in that area. The energy dispersive system can also be used, but generally gives poorer images.

Examples are given in Fig 1c-f, corresponding to the area shown in the electron image above. The inclusion stringers clearly contain two types of inclusion, one rich in Cu and Fe, the other rich in Mg and Si. Mg and Cu also exist in solid solution or in fine precipitates, as indicated by background levels.

LM Mat 350

At low magnifications, using the crystals, defocussing will occur resulting in a loss of intensity at the edges of the image, ie the electron probe deviation is so large that Bragg's Law is not precisely obeyed. 'Hybrid' scanning, in which the electron probe is scanned in the Y-axis only and the specimen stage is automatically stepped in the Xaxis, may be used at magnifications of 150% and 300% to overcome this.

4.1.3 Line scans

Line scans are graphs of the concentration variation for a particular element against distance along a line on the specimen surface. They are obtained by a slow, single scan across the specimen with a spectrometer set up for the element of interest. The deflection of the spot moving across is proportional to the count rate.

An example, corresponding to the line X-X in Fig 1a, is given in Fig 5. Once again the coincidence of Cu and Fe, and of Mg and Si, is apparent. Line scans give a better indication of relative concentration than X-ray images, and are useful for investigating segregation, composition of closely spaced particles etc.

4.1.4 Step scanning of specimen

The computer can be used to step the specimen stage in the X or Y directions (or at a specified angle or in a raster) at set increments over a set distance. At each point, the count rate for the elements specified is printed out on the teletype, as illustrated in Fig 6. In this example the specimen was stepped in the X-direction in 0.03mm steps for 0.24 mm, the probe current being 5×10^{-8} A. At each point the X, Y and Z co-ordinates are printed out, and the element, spectrometer channel and angle, and the count rate (counts per second) are also given, in this case for Mg only. In the example, the count rate rises from about 450 c/s to about 4500 c/s and down again, is the scan passes through an Mg-rich inclusion.

A graphical representation may be obtained using the chart recorder, with the ratemeter output being fed to the recorder input. The example of Fig 7 shows plots for Cu and Mg, peaks occurring where the probe impinges on Cu- and Mg-rich inclusions. The specimen current is also monitored, and appears to be decreased somewhat when the probe impinges on inclusions, particularly the Cu-rich ones.

Step scanning gives similar data to slow line scans, but is useful for programmed raster scans, and scans over large distances, when defocussing would affect slow line scans.

4.1.5 Spectral scanning

This mode of operation is used to scan the spectrometers in conjunction with the chart recorder to obtain a graphical record of a peak. The spectrometer is stepped through a certain angle at set increments and the count rates recorded on the chart recorder, which is also stepped as required. An example is shown in Fig 8, which was obtained by setting the electron probe on a Cu-rich particle and stepping the spectrometer from $22-23^{\circ}$ in 0.005° steps using the appropriate crystal. With the energy dispersive system available, spectral scanning is not often necessary to determine the

녗

Mat

ž

elements present, but it could be useful for graphical records of peaks for light elements, or for observing the shape of peaks.

4.2 Fully quantitative analysis

358

Mat

5

For fully quantitative work a clean, flat, polished specimen surface is required, and all measurements on both standards and specimen should be made under the same operating conditions. The general analysis program (GAP) used for quantitative work includes warnings to the operator of deviations in kV or probe current, although small variations in probe current are acceptable and corrected for automatically. The standards are first measured, using the parameters stored in the standards table. An example is given in Fig 9. The general analysis program is entered, specifying the operating kV (GAP; 25). The elements selected in this case were Al, Zn, Mg, Cu, Zr, Fe and Si (MPS;), with the average of three analyses being taken for each element (AVS; 3). The probe current was 5×10^{-8} A. On the command GO the program automatically sets up the stage and spectrometers for each element in turn, performs a peak search to optimise the Bragg angle, obtains count rates and averages these if more than one analysis is specified, and updates the standard tables with the kV and probe current used, standard count rate, Bragg angle and ZAF correction factor.

The results are listed in columns, which from the left give (Fig 9); element, spectrometer channel and peak angle, peak c/s, positive background c/s, negative background c/s, peak minus background c/s, standard deviation (20) c/s, and standard ZAF factor.

Having measured the standards, the points or areas of interest in the unknown specimen are analysed. An example, from a spot analysis in the matrix in Fig 1a, is given in Fig 10. Still in the GAP mode, the command UNK is used to set up either a single point analysis (as in the present case) or a series of points along a line or in a raster, ie the stage can be stepped in the X and/or Y axes and an analysis performed at each point. The elements to be included are specified (STD;) and if a ZAF correction is required this is also typed in. The command GO initiates the program.

The results format for the uncorrected data is similar to that for the standards measurements, but the last two columns are uncorrected concentration (%) and standard deviation (2σ) of the uncorrected concentration. When ZAF has been specified, the three columns printed out are uncorrected concentration (%), corrected concentration (%) and corrected concentration. The centre column, corrected concentration, is generally of most interest. When more than one analysis is specified, an average of all the points is also given at the end.

Compound standards are used for elements such as nitrogen, oxygen, sulphur, and the standard tables are easily modified to allow for the use of such standards. An alloy of known composition could be used as a compound standard for analyses of similar alloy types, as long as the standard is homogeneous on a microscopic scale. The advantage of using such a standard is that a small ZAF correction is required and an immediate comparison of the unknown and standard without ZAF correction is possible.

5 CONCLUDING REMARKS

8

It is clear that the M9 is a powerful tool for the acquisition of data on the chemical composition of small areas. Computer control has greatly speeded up a potentially laborious technique. The instrument is useful for any application where variations in chemical composition on a microscale need to be evaluated, eg segregation, diffusion of particular elements, identification of inclusions, contamination by undesirable substances etc. Results may be presented in a variety of ways, depending on the particular requirement, and a range of work from qualitative analysis of fracture surfaces to fully quantitative analysis of carefully prepared microsections is possible.





e

TM Mat 358

4. 3



Fig la-f (a) Backscattered electron image, (b) specimen current image, (c-f) X-ray images for Cu, Fe, Mg and Si respectively 1000×



Fig 2 X-ray spectrum for spot A in Fig la. (matrix)

TM Mat 358

Fig 2

TM Mat 358

Ļ.

¥

L alpha lines

: . . ł E • • Qu (KB) . . . 3 5 . . . 8 · · · · · · :: ¥ 3 • ••• 3 ٤ 2 3 * ••• . : ÷ 3 ę - -- -- -· · · · • Fe(Kß) ž ÷ s 8 ¥ 8 2 2 Ē 3 룊 : ŝ 3 . . . ž 5 . . . : g Ĩ · · · : : ដ • 1 • 3 . ••• • -: 5 3 • • • • • . . · · · . . . ž 6 8 · · · . . · - • · · · ••• 2 • • ž : 6 ų · · · · · · · · · · 2 7 5 . •••• · · ::: :: IV 5 2 ŝ . . 5 a 1 •••• •••• · • · · · · ••• 3 : : 3 CA 15 M 24 1 . . . :: ••• :: · · · · · · · · · · • • • • · · · · · · · · · · •••

X-ray spectrum for spot B in Fig la. (inclusion rich in Cu and Fe)

F1g 3

Link Systems Ltd X Ray Analysis

K alpha lines

¥ I • Za(K6) i 3 Ŧ · · . . . : : • 5 8 ••• ••• -í :-: • 3 ¥ Æ : : ••• • • : i :1 . • • ₹ 3 5 · · · · · · · • • 4 3 ;: ++++ , ••• 1 ž £ • • · · · · • • · · · 8 • ¥ ••• 5 · · · £ :: Link Systems Ltd X Ray Analysis ••• ••• ŝ • 2 . . . • • 3 ž ••• : : 5 . . • • K alpha lines 9 a d ••• · · · · · • · • · • . 3 :: 5 ; 2 ş · · · ; · · · · ••• • S ž • 1 . • 3 : 5 : z • į ••• 8 9 : • ł Ŧ ę ş 2 ; ñ Si ī Ĵ. · } • 1 . 5 1 4 2 i ŝ s 3 CR FR M ZN GR SE IMMICO.CU GA AS . • • X 11 :1 11 ÷ • • + • • :: • . t + - |- |-| | | : i t

Fig 4 X-ray spectrum for spot C in Fig la, (inclusion rich in Mg and Si)

358

TH Mat

Fig 4

L alpha lines

Figs 546



Fig 5 X-ray line scans for the elements indicated, corresponding to line X-X in Fig la

```
STS;.003;.024;0;0
#SSE#MG
#GO
STANDARD
5.00*10~-8
DATE 3 6 80 TIME 12 25 50
    X26.847 Y20.385 Z17
    B22.232
              451.5
MG
    X26.850 Y20.385 Z17
    B22.232
              578.2
MG
    X26.853 Y20.385 Z17
MG
    B22.232
              664.6
    X26.856 Y20.385 Z17
    B22.232
             1121.3
MG
    X26.859 Y20.385 Z17
             4522.6
MG
    B22.232
    X26.862 Y20.385 Z17
    B22.232
MG
             4134.4
    X26.865 Y20.385 Z17
MG
    B22.232
             1181.4
    X26.868 Y20.385 Z17
MG
    B22.232
              669.4
    X26.871 Y20.385 Z17
MG 822.232
              599.0
4.99*10~-8
DATE 3 6 80 TIME 12 29 7
ŧ
```

TM Mat 358

Fig 6 Print-out of results for step scanning of specimen, with spectrometers set up for Mg only. See text for interpretation



Fig 7 Step scanning of specimen using chart recorder to monitor count rates for Cu and Mg. Peaks correspond to inclusions, either Cu-rich or Mg-rich. Specimen current (SCA) is also monitored

TM Mat 358

Fig 7



Fig 8 Spectral scanning; Cu peak

TM Mat 358

.

Fig 8

GAP;25 #MPS;AL;ZN;MG;CU;ZR; #AVS;3 #BLT;2 #GO	FEISI	ENTER GENERAL ANALYSIS MODE MEASURE PURE STANDARDS TAKE 3 READINGS AND AVERAGE BLANKET ANALYSIS TIME (2 seconds) INITIATE PROGRAM					
STANDARD 5.00#10^-8							
DATE 1 6 80 TIME 25 KU	14 39 50 background c/a			_			
angle gross c/s	+ -	net c/s	2σ	ZAF factor			
FE A28.737 12017.7	15.	5 12002.2	155.4	0.447455			
FE A28.737 11918.6	16.	1 11902.5	154.4	0.447455			
FE A28.737 11900.5	13.	11887.4	154.4	0.447455			
CU A22.482 9317.0	17.1	9299.9	136.9	0.467782			
CU A22.482 9247.1	23.3	9223.8	135.9	0.467782			
CU A22.482 9218.1	20.3	9197.8	135.9	0.467782			
ZN A20.866 7745.1	22.3	3 7722.8	124.4	0.468817			
ZN A20.866 7869.9	33.	1 7836.8	125.5	0.468817			
ZN A20.866 7837.6	31.	1 7806.5	125.5	0.468817			
ZR A43.957 13817.6	68.	5 13749.3	166.4	0.358136			
2K A43+73/ 13041+8 76 A47 057 17471 A	0J+1	3 133/0+0	163+4	0.358136			
2K 443,70/ 13031.4	04+4	2 1330/+2	103+4	V+33813 <u>8</u>			
NG 822+232 40033+2	0•. 7.	L 40047+1	203.7	0.311040 0.711944			
MG 822,232 4073011	5.4	5 40722+J	284.5	0.311846			
AL 818.571 58959.0	44.9	58914.1	343.5	0.111040			
AL B18.571 59182.8	45.5	59137.3	344.4	0.333987			
AL B18.571 59096.1	42.9	59053.2	343.9	0.333987			
SI B15.794 58388.2	94.6	58293.6	341.9	0.336367			
SI B15.794 58158.6	92.7	58065.9	341.4	0.336367 =			
SI B15.794 57432.9	105.5	57327.4	338.9	0.336367			
4.88*10^-8							
DATE 1 6 80 TIME	14 54 18						
Ŧ							

Fig 9 Results print-out of measurements on pure standards. The columns have been headed to assist interpretation

Fig 10

				- <u></u>						
	GAP#25 #UNK #STD#AL#ZN#MG#CU#ZR#FE#SI #ZAF #GO				MEASURE UNKNOWN ANALYSE THESE ELEMENTS PERFORM ZAF CORRECTION					
	STAI	NDARI 0±10') `-8							
	DATI 25 I	E 1 KV	6	80 TIME	14 57 8					
-									UR	
÷		X24	611	Y23.997	Z17		. –			
	FE	A28	737	7.2		6.9	0.3	1.6	0.00	0.01
		822 (477)	, 232 . 897		Ο.Δ	32.3	172.1	13.3	1.42	0.09
		R18.	571	42904.0	31.8		42872.2	131.1	72.62	0.22
	ZN	A20	866	451.0	0110	11.0	440.0	13.4	5.64	0.17
	SI	B15.	.794	35.4	38.9		0.0	3.8	0.00	0.01
	ZR	A43.	9 57	22.6		7.0	15.6	3.1	0.11	0.02
	***									_
	TOT								81.12	0,53
• •			ITR	CR						
-	ZAF	COR	~~	4 ITER						
	MG	1	.33	1.71	2.83					
· - ·	AL	72	.62	89.68	169.45					
	SI	0.	.00	0.00	0.00					
	FE	0.	.00	0.00	0.00					
	CU	1	42	1.68	2.10					
1	ZN	5.	-64	6,66	8.29					
<u> </u>	2K	0.	•11	0+22	0.30					
	TOT	81 .	.12	99.95	182,97					
. - 	5.0	1#10'	8							
F	DAT	E 1	6	80 TIME	15 1 14					

Fig 10 Results of analysis on unknown. Uncorrected results are indicated by UR, and corrected results by CR

i.

٠.

Ę

7. We applications of the Manuscon 9 starsmithyse

L Car Thightendad This is Parally Lineses

75. (Par Conductors Papers) Title, Place and Date of Conference

in the second states of the second states and the second states and the second states and the second states and	and the second		and the second	بمأياك ويعصص والتقيات فالتان	The second s
8. Amdrid 9. Dermanne, babbete	So. Author 2		St. Anthons 3,4		
Pitemer, P.D.		" 			
11 Configuration	12. Period		13. Prolect		
	an / 1 ²³				
	NA.				
15. Distribution streament		ar e Tari		¥.	

5.2 16

(a) Committed by - Mond of Materials Department, Bill

(b) Special Mattations (if any) --

· · · · · ·

16. Descriptors (Raywords) (Descripters, underst * are miscout from THUT)

Microscan 9- Microsnalysis.

17. Aboltant

13

2

The basic principles of electron microprote antipets are antiched and the second states of the Microson 9 Marty and Sandard Antibet. Applications of the Microson 9 Marty and Sandard Antipets and San

a.2