

ADA 126398

June 1982 MRDC41097.4RD

RESEARCH ON FERROELECTRIC MATERIALS FOR
MILLIMETER WAVE APPLICATIONS

R&D Status Report No. 4 (Quarterly)
For the Period March 1, 1982 through May 31, 1982
General Order No. 41097

ARPA Order No:	4240
Program Code:	1D10
Name of Contractor:	Rockwell International Corporation
Effective Date of Contract:	August 5, 1981
Contract Expiration Date:	October 5, 1982
Amount of Contract Dollars:	\$379,182
Contract Number:	F49620-81-C-0090
Principal Investigators:	Dr. R. R. Neurgaonkar (805)498-4545, ext. 109 Professor L. E. Cross Pennsylvania State University (814) 865-1181 Dr. W. F. Hall (805)498-4545, ext. 189 Dr. W. W. Ho (805)498-4545, ext. 194

Sponsored by:

Advanced Research Projects Agency (DoD)
ARPA Order No. 4240
Monitored by AFOSR under Contract No. F49620-81-C-0900

Approved for public release;
distribution unlimited.

DTIC FILE COPY

DTIC
ELECTE
APR 5 1983

Rockwell International
Microelectronics Research
and Development Center

A

83 04 05 167



A. PROGRESS

In the current reporting period a study has been initiated concerning the tradeoffs in millimeter wave component design between the use of low-loss ferroelectric materials and conventional ferrites. The object of this study is to quantify advantages and disadvantages in a radar system context specifically for the planar dielectric lens and for individual phase shifters. The results of this study will clarify the potential utility of ferroelectrics and specify a range of materials parameters which are favorable for the selected radar system applications.

Another effort recently begun is the measurement of TiO_2 single crystal samples from 30-40 GHz and from 90-100 GHz. These crystals have relatively high dielectric constants (~ 100) at microwave frequencies and show low loss. Thus, these measurements will provide a rigorous test of the analysis methods currently being used on the ferroelectric samples.

Material research is an important part of this work; and hence the selection of a suitable class of materials is a major task. In the present work, the tungsten bronze and perovskite structural families have been selected since these families offer a wide range of compositions exhibiting excellent electro-optic, dielectric, piezoelectric and other properties. At present, several bronze compositions such as $\text{Sr}_{.6}\text{Ba}_4\text{Nb}_2\text{O}_6$, $\text{Pb}_{1-x}\text{Ba}_x\text{Nb}_2\text{O}_6$, $\text{Sr}_2\text{KNb}_5\text{O}_{15}$ and $\text{Ba}_{2-x}\text{Sr}_x\text{K}_{1-y}\text{Na}_y\text{Nb}_5\text{O}_{15}$ are now available from our current DARPA and other contracts. and have been evaluated. The work on these crystals is interesting and based on these results, the necessary changes in compositions are being made. The Czochralski bulk single crystal growth technique has successfully been established to develop approximately 1.5 to 1.8 cm in diameter $\text{Sr}_{.5}\text{Ba}_{.5}\text{-Nb}_2\text{O}_6$ crystals. The crystals are of excellent quality and high frequency dielectric measurements are in progress on this crystal.

Recently, the tungsten bronze solid solutions systems $\text{Pb}_{1-2x}\text{K}_x\text{M}_x^{3+}\text{Nb}_2\text{O}_6$, $\text{M} = \text{La}$ or Bi , have been developed and some of the compositions in these systems appear to be promising for study of their high-frequency dielectric properties.




All of these compositions possess orthorhombic tungsten bronze structure and will be evaluated in terms of their usefulness for millimeter wave applications.

B. MAJOR EQUIPMENT

A new crystal puller unit has been installed and is now available for current growth work on tungsten bronze family crystals.

C. CHANGES IN PERSONNEL

Nothing to report.



D. TRIPS, VISITS AND PAPERS

The following two papers from our current work have been submitted for publication:

1. "Structural and dielectric properties of the phase $Pb_{1-2x}K_xM_x^{3+}Nb_2O_6$, M= La or Bi, " R. R. Neurgaonkar, J. R. Oliver, W. K. Cory and L. E. Cross.
2. "Low and high frequency dielectric properties of ferroelectric tungsten bronze $Sr_2KNb_5O_{15}$ crystals " R. R. Neurgaonkar, W. W. Ho, W. K. Cory, and W. F. Hall and L. E. Cross.



E. PROBLEMS

Nothing to report.

F. FUTURE PLANS

Bulk single crystal growth of the tungsten bronze composition $Ba_{2-x}Sr_xK_{1-y}Na_yNb_5O_{15}$ for microwave dielectric characterization will be continued. Based on these results, the necessary changes in crystal composition will be made.

Further investigations of the millimeter wave dielectric properties of SBN and other bronze compositions (PKLN) will be carried out, including measurements of reflection and transmission at elevated temperatures in the frequency range 30-40 GHz. Certain other ferroelectric crystals will also be examined. The work on TiO_2 single crystal will be continued.

G. FISCAL STATUS

Current Amount provided:	\$ 354,382
Expenditures to date:	280,388
Estimated Funds to Complete Work:	73,994
Estimated Date of Completion:	December 4, 1982

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER ACCESS TR-83- 0124	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER	
4. TITLE (and Subtitle) RESEARCH ON FERROELECTRIC MATERIALS FOR MILLIMETER WAVE APPLICATIONS		5. TYPE OF REPORT & PERIOD COVERED QUARTERLY REPORT 31 MAY 82 to 01 MARCH 82	
		6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) Professor L. E. Cross		8. CONTRACT OR GRANT NUMBER(s) F49620-81-C-0090	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Rockwell International 1049 Camino Dos Rios Thousand Oaks, CA 91360		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 61102F 2306/B2	
11. CONTROLLING OFFICE NAME AND ADDRESS Air Force Office of Scientific Research Building #410 Bolling AFB, Washington, DC 20332		12. REPORT DATE June 1982	
		13. NUMBER OF PAGES 03	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED	
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)			
19. SUPPLEMENTARY NOTES			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) This effort is an attempt to grow and measure the millimeter-wave properties of tungsten Bronze Ferroelectrics. Difficulties (apparently with the growth) have stalled progress during this period.			

UNCLASSIFIED