

AD-A134 562

EFFECT OF PRESSURE ON CONDUCTIVITY IN POLY(ETHYLENE  
OXIDE) COMPLEXED WITH ALKALI METAL SALTS(U) NAVAL  
ACADEMY ANNAPOLIS MD DEPT OF PHYSICS

1/1

UNCLASSIFIED


J J FONTANELLA ET AL. MAY 83 TR-7

F/G 7/3

NL



END  
DATE  
FORM  
11 24 4  
DATE



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

AD-A134 562

12

OFFICE OF NAVAL RESEARCH

Contract N00014-83-AF-00001

Task No. NR 627-793

TECHNICAL REPORT NO. 7

EFFECT OF PRESSURE ON CONDUCTIVITY IN POLY(ETHYLENE OXIDE)  
COMPLEXED WITH ALKALI METAL SALTS

by

John J. Fontanella and Mary C. Wintersgill

Prepared for Publication

in

Proceedings of the 4th International  
Conference on Solid State Ionics to be  
published as a special issue of "Solid State Ionics".

U. S. Naval Academy  
Department of Physics  
Annapolis, MD 21402

May 1983

Reproduction in whole or in part is permitted for  
any purpose of the United States Government

This document has been approved for public release  
and sale; its distribution is unlimited

DTIC  
ELECTE  
NOV 8 1983  
S D  
D

DTIC FILE COPY

88 11 07 016

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 7	2. GOVT ACCESSION NO. A134502	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) EFFECT OF PRESSURE ON CONDUCTIVITY IN POLY(ETHYLENE OXIDE) COMPLEXED WITH ALKALI METAL SALTS		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report
7. AUTHOR(s) JOHN J. FONTANELLA, MARY C. WINTERSGILL		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Physics Department U. S. Naval Academy Annapolis, MD 21402		8. CONTRACT OR GRANT NUMBER(s) N0001483AF00001
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Attn: Code 413, 800 N. Quincy St. Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR No. 627-793
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE May 1983
		13. NUMBER OF PAGES 7
		15. SECURITY CLASS. (of this report)
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release and sale. Distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Solid electrolytes, polymer electrolytes, Poly(ethylene oxide), polymer slat complexes, pressure, Activation volume, free volume, dynamical diffusion theory.		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) → Audio frequency complex admittance measurements at a number of temperatures have been performed on PEO complexed with various alkali metal perchlorates and thiocyanates at pressures up to 0.2 GPa. In general, the activation volumes tend to increase with the size of both the cation and anion. The trend is best explained if the ion transport mechanism involves both anions and cations. The results are in good agreement with the predictions of a dynamical diffusion theory with an attempt mode Grunelsen →		

DD FORM 1473  
1 JAN 73EDITION OF 1 NOV 65 IS OBSOLETE  
S/N 0102-014-6601

parameter appropriate for interchain vibrations. This implies that diffusion takes place via interstice-interstice hopping of the ions. Next, it is shown that free volume considerations lead to unreasonable results if  $T_0$  is interpreted as the glass transition temperature. Finally, the effect of pressure on the activation volume is determined.

<b>Accession For</b>	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
AI	

DTIC  
COPY  
REQUESTED

## EFFECT OF PRESSURE ON CONDUCTIVITY IN POLY(ETHYLENE OXIDE)

### COMPLEXED WITH ALKALI METAL SALTS

J. J. Fontanella, M. C. Wintersgill, J. P. Calame, F. P. Pursel, and D. R. Figueroa\*  
Physics Department, U. S. Naval Academy, Annapolis, Md. 21402, USA

C. G. Andeen  
Physics Department, Case Western Reserve University, Cleveland, Ohio, 44106, USA

Audio frequency complex admittance measurements at a number of temperatures have been performed on PEO complexed with various alkali metal perchlorates and thiocyanates at pressures up to 0.3 GPa. In general, the activation volumes tend to increase with the size of both the cation and anion. The trend is best explained if the ion transport mechanism involves both anions and cations. The results are in good agreement with the predictions of a dynamical diffusion theory with an attempt mode Gruneisen parameter appropriate for interchain vibrations. This implies that diffusion takes place via interstice-interstice hopping of the ions. Next, it is shown that free volume considerations lead to unreasonable results if  $T_0$  is interpreted as the glass transition temperature. Finally, the effect of pressure on the activation volume is determined.

### 1. INTRODUCTION

Ion conducting poly(ethylene oxide)(PEO) has been attracting a great deal of attention<sup>1-24</sup> because of possible application as the electrolyte in solid state batteries. As the effect of pressure on the conductivity provides useful information concerning ion transport, such studies of PEO complexed with various salts were undertaken and the results are presented here.

### 2. EXPERIMENT AND RESULTS

Films of PEO (Polysciences, MW  $5 \times 10^6$ ) with various amounts of alkali metal perchlorates and thiocyanates were prepared as described elsewhere.<sup>21</sup> As before, aluminum electrodes were evaporated onto the surfaces. One face had a central circular electrode of about 8 mm diameter while the other was about 10 mm in diameter. The samples were 0.25-0.5 mm thick. The configuration was chosen to be optimal for the apparatus used. Such a configuration does not readily yield absolute values of the conductivity at a high accuracy, however, since the primary goal of the present work is the relative change in conductance with pressure, this was considered to be a reasonable procedure.

The complex admittance measurements were made using a fully automated microprocessor-controlled bridge constructed by one of the authors (CGA). The bridge operates at five audio frequencies from 100-10,000 Hz, and is as accurate as the best commercially available manual bridges (General Radio 1616, for example).

At the relatively low temperatures of the present work, it was found that there was usually very little difference between the 1,000 and 10,000 Hz values of conductance, even though the samples were rather thin. As pressure increased, however, the apparent conductance

became lower for the lower frequencies. This effect can be seen in Figure 1 where the results for  $\text{PEO}_8\text{-NaClO}_4$  are shown. This is due to enhanced blocking electrode effects. However, this dispersion has little effect on the zero pressure slope, though the curvature is affected somewhat. In this paper, the 10,000 Hz data will be taken to represent the conductance of the sample.

Two different high pressure bombs were used, each with a design similar to that described elsewhere.<sup>25</sup> The pressures were generated using




Figure 1:  $\text{Ln}(G(\text{ohm}^{-1}))$  vs.  $P(\text{GPa})$  for  $\text{PEO}_8\text{-NaClO}_4$  at 314.9K. The data are:  $\circ$ -increasing pressure and  $\times$ -decreasing pressure at 10,000 Hz;  $+$ -increasing pressure and  $\Delta$ -decreasing pressure at 1,000 Hz. The solid line is the best fit curve for the 10,000 Hz data.

Table 1: Various experimental and theoretical results related to the effect of pressure on the ionic conductivity in PEO complexed with alkali metal salts.

Material and Sample Number	T(k)	$\ln(G_0(\Omega^{-1}))$	$a(\text{GPa})^{-1}$	$b(\text{GPa})^{-2}$	$g(\text{eV})$	$v(\text{cm}^3/\text{mol})$	$\gamma_d$	$\lambda_V(\text{GPa})^{-1}$	$\lambda_V/\gamma_d$
PEO <sub>5</sub> -LiSCN									
1	310	-12.9	-12.4	4.5	1.13	32.3	1.27	0.72	6
1	318	-11.5	-12.6	5.8	1.13	33.7	1.31	0.91	8
PEO <sub>3</sub> -LiClO <sub>4</sub>									
1	299	-10.8	-12.0	8.1	0.76	30.3	1.77	1.3	11
1	307.2	-9.7	-14.0	16.5	0.76	36.4	2.12	2.3	19
1	315.2	-8.3	-14.5	13.1	0.76	38.6	2.25	1.8	15
2 (gas)	310.2	-9.7	-14.4	19.2	0.76	37.8	2.20	2.5	22
3	310	-9.7	-12.0	4.1	0.76	31.5	1.83	0.66	6
PEO <sub>3</sub> -NaClO <sub>4</sub>									
1	306.9	-12.1	-17.6	21.3	0.92	45.5	2.20	2.4	20
1	310.4	-11.5	-18.5	23.9	0.92	48.4	2.33	2.5	21
1	314.9	-10.6	-17.8	17.8	0.92	47.3	2.28	2.0	17
1	320.4	-9.7	-16.8	15.1	0.92	45.4	2.19	1.7	15
1	329.8	-8.2	-21.4	20.5	0.92	59.5	2.87	1.9	16
2	309.6	-11.0	-15.6	15.9	0.92	40.7	1.96	2.0	17
3	309.6	-11.8	-13.5	9.1	0.92	35.2	1.69	1.3	11
2	324.8	-8.7	-18.7	21	0.92	51.2	2.47	2.2	19
3	324.8	-9.2	-18.9	21.7	0.92	51.7	2.50	2.3	20
PEO <sub>4.5</sub> -NaClO <sub>4</sub>									
1	294.2	-11.6	-18.1	11.5	0.78	44.9	2.55	1.2	11
1	303.9	-10.5	-15.2	6.7	0.78	39.0	2.27	0.87	7
1	310.2	-10.0	-14.7	7.0	0.78	38.5	2.19	0.94	8
1	315.3	-9.3	-14.3	8.1	0.78	38.1	2.17	1.15	10
1	323.4	-8.6	-13.9	8.2	0.78	38.0	2.16	1.14	10
PEO <sub>4.5</sub> -NaSCN									
1	310.2	-6.2	-10.0	1.7	0.41(0.76)	26.6	2.88(1.55)	0.33	3
1	318.2	-5.8	-10.6	3.2	0.41(0.76)	29.0	3.14(1.69)	0.59	5
*	321.7	-	-9.0	-	0.41(0.76)	24.9	2.70(1.45)	-	-
*	318.5	-	-9.0	-	0.41(0.76)	24.6	2.66(1.44)	-	-
PEO <sub>4.5</sub> -KSCN									
1	310.2	-9.8	-10.7	5.0	1.10	27.9	1.13	0.92	8

\*Sample provided by R. Dupon and D.F. Shriver, Northwestern University

Both argon and nitrogen gases as well as Spinesstic 22 oil. The measurements of the pressure were made using a Heise 7 kbar Bourdon tube pressure gauge. In many cases, the data runs using either argon or nitrogen gas as the pressurising medium proved not to be entirely satisfactory. The samples frequently failed after one or two data runs, either by an apparent short circuit or by generating a voltage. Furthermore, the samples turned white during the pressure run. All the samples returned to their initial transparency after heating at 100C in vacuum for a few hours. Using the Spinesstic 22 as the pressure fluid, however, the samples showed no such effects and the change in appearance of the samples is therefore attributed to dissolved gas in the samples. However, the dissolved gas had very little effect on the conductivity as can be seen

in Figure 2 where the results for PEO<sub>3</sub>-LiClO<sub>4</sub> obtained using both gas and oil are shown. Clearly, the effect of pressure on the conductivity is independent of the pressurising medium. Samples removed from the pressure bomb after a week of constant immersion in the Spinesstic 22 were scrutinised for signs of swelling or chemical interaction but none showed any effects from the oil.

In interpreting the results, the equation:

$$\ln(G) = \ln(G_0) + aP + bP^2 \quad (1)$$

where  $G_0$ ,  $a$ , and  $b$  are constants, was best-fitted to the data.  $G$  is the conductance in  $\Omega^{-1}$  and  $P$  is the pressure in GPa. The results of the best-fits are listed above in Table 1.

### 3. DISCUSSION

The data were used to calculate an activation volume associated with the conduction process. The activation volume is defined as:

$$v = \left( \frac{-\partial g}{\partial P} \right)_T \quad (2)$$

where  $g$  is the Gibbs energy. The problem is to determine the most appropriate method to associate the Gibbs energy with the ionic conductivity. The difficulty arises from the uncertainty as to whether the Arrhenius equation:

$$\sigma = \frac{\sigma_0}{T} \exp(-h/KT) \quad (3)$$

where  $h$  is the enthalpy, or a free volume expression:

$$\sigma = \frac{\sigma_0}{T} \exp\left(-\frac{h_a}{k(T-T_0)}\right) \quad (4)$$

should be used to describe the conductivity. As will be shown below, the free volume expression leads to unreasonable results and thus the Arrhenius equation will be used.

#### 3.1. Arrhenius Analysis

The assumption of Arrhenius behavior leads to an activation volume:

$$v = -kT \left[ \frac{\partial \ln \sigma}{\partial P} = \frac{\partial \ln \sigma_0}{\partial P} + \frac{1}{k} \left( \frac{\partial h}{\partial P} \right) \right] \quad (5)$$

where the entropy,  $s$ , is given by  $g = h - Ts$ . Assuming that the electric field inside the sample is uniform:

$$G = \frac{A}{d} \quad (6)$$

where  $A$  is the area of the electrodes, and  $d$  is their separation, it follows that:

$$\frac{\partial \ln \sigma}{\partial P} = \frac{\partial \ln G}{\partial P} + \frac{1}{3} \quad (7)$$

where  $\chi$  is the isothermal compressibility. Further, assuming that the only pressure dependent terms in the pre-exponential are the attempt mode frequency,  $\nu_a$ , the number of charge carriers per unit volume,  $n$ , and the mean squared jump distance,  $r$ , that is:

$$\sigma_0 = C_0 n r^2 \nu_a \quad (8)$$

and also that the entropy is independent of pressure, Equation (5) becomes:

$$v = -kT \left[ \frac{\partial \ln G}{\partial P} + \chi_a \right] \quad (9)$$

In this expression, the attempt mode Gruneisen




Figure 2:  $\ln(G(\text{ohm}^{-1}))$  vs.  $P(\text{GPa})$  for  $\text{PEU}_2\text{-Li}_{104}$ . The data are:  $\circ$ -Increasing pressure and  $\times$ -Decreasing pressure using nitrogen gas at 310.2K;  $\triangle$ -Increasing pressure and  $\nabla$ -Decreasing pressure using Spinelitic  $\text{Zr}$  at 317.2K. The data are at 10,000 Hz.

parameter,  $\chi_a$  is given by:

$$\chi_a = \frac{\partial \ln \nu_a}{\partial \ln G} \quad (10)$$

The compressibility of pure PEU is  $0.117(\text{GPa})^{-1}$  as reported by Ito.<sup>6</sup> As values for complexed PEU do not appear to be available at present, this value will be used for the complexed material also. There is considerable ambiguity as to the appropriate value of  $\chi_a$ . Bulk Gruneisen constants for polymers are on the order of 6-10,<sup>27</sup> while mode Gruneisen constants range from 0.060 to about 2.28.<sup>28</sup> However, the activation volume is relatively insensitive to the value of  $\chi_a$  since, for  $\chi_a = 2$  for example, the correction factor in Equation (9) ( $\chi_a$ ) is about  $0.23(\text{GPa})^{-1}$  which represents a difference of only about 1.5% in the activation volume.

In order to be internally consistent, dynamical diffusion theory will be used to estimate  $\nu_a$ . Specifically, it follows from Flynn<sup>29</sup> that:

$$\nu_a = \frac{2}{3} \nu_0 \quad (11)$$

This equation has been used successfully in similar applications for ionic crystals.<sup>30</sup> Inserting Equation (11) into Equation (9), the working equation becomes:

$$v = -kT \left[ \frac{\partial \ln G}{\partial P} + \frac{1}{3} \right] \quad (12)$$

The resultant values of the activation volumes are listed in the seventh column of Table 1






Figure 3:  $\text{Ln}(\sigma(\text{ohm-cm})^{-1})$  vs.  $1000/T(\text{K}^{-1})$  for PEO complexed with various alkali metal thiocyanates: (a)  $\text{PEO}_{4.5}\text{-LiSCN}$  (b)  $\text{PEO}_{4.5}\text{-KSCN}$  (c)  $\text{PEO}_{4.5}\text{-NaSCN}$ .




Figure 4:  $\text{Ln}(\sigma(\text{ohm-cm})^{-1})$  vs.  $1000/T(\text{K}^{-1})$  for PEO complexed with various alkali metal perchlorates: (a)  $\text{PEO}_{4.5}\text{-NaClO}_4$  (b)  $\text{PEO}_5\text{-LiClO}_4$  (c)  $\text{PEO}_5\text{-LiClO}_4$ .

using values of the Gibbs energy approximated by the enthalpies determined from the slopes in Figures 3 and 4.

There are several interesting features of these results. The most important trend is that in general the activation volume increases with both the size of the cation and anion. For example,  $v$  for  $\text{PEO}_{4.5}\text{-NaClO}_4$  is significantly larger than that for  $\text{PEO}_{4.5}\text{-LiSCN}$ . One simple explanation for this result is that the difference is due to the difference in size and shape of the anions and that the anions are mobile. That is, the tetrahedral perchlorate ion requires more volume increase of the polymer matrix than does the linear thiocyanate ion in order for transport to take place. Also, it is possible that a larger number of perchlorate ions than thiocyanate ions may be mobile. These considerations support the recent results of Weston and Steele<sup>19,20</sup> and Sorensen and Jacobsen<sup>23</sup> which imply that the anions are mobile.

Of course, other explanations are possible. For example, it is not necessary that the anions be mobile. Their function may simply be to decrease the free volume, which should in turn increase the activation volume for motion of cations. However, the difference between  $\text{PEO-NaSCN}$  and  $\text{PEO-NaClO}_4$  seems to be too large to be attributable to cation motion alone. Other explanations may be associated with morphology or degree of crystallinity. Experiments are currently underway to ascertain the extent to which such factors are influencing transport processes.

Most trends shown by the remaining results are also consistent with an argument based on ion

size. Specifically, the activation volume for  $\text{PEO}_5\text{-LiClO}_4$  is smaller than for  $\text{PEO}_{4.5}\text{-NaClO}_4$  and  $v$  for  $\text{PEO}_{4.5}\text{-NaSCN}$  is slightly smaller than for  $\text{PEO}_{4.5}\text{-KSCN}$ . The latter results are particularly significant since electrical relaxation studies show that there are severe local distortions of the polymer chains in  $\text{PEO-KSCN}$ .<sup>21</sup> Finally,  $v$  for  $\text{PEO}_5\text{-LiClO}_4$  appears to be larger than for  $\text{PEO}_5\text{-NaSCN}$  though the difference is not so dramatic as for the sodium complexed materials.

The one clear exception to the rule of scaling of  $v$  with ion size is that  $v$  for  $\text{PEO}_5\text{-LiSCN}$  is larger than for  $\text{PEO}_{4.5}\text{-NaSCN}$ . However, it should be kept in mind that the  $\text{LiSCN}$  complexed materials were prepared without taking great care to exclude water and were, in fact, synthesized using hydrated  $\text{LiSCN}$ .<sup>21</sup> Consequently, the  $\text{PEO}_5\text{-LiSCN}$  results may be anomalous as the role of the water has yet to be determined.

Next, information concerning the transport mechanism can be obtained from further consideration of dynamical diffusion theory. In particular, the values of  $v_a$  in Equation (11) necessary to predict the experimental values of the activation volume are of interest. These values of  $v_a$  have been calculated and are listed in Table 1. It is seen that the values are all greater than 1.0. This implies that it is the low frequency interchain vibrations of the polymer which control the ionic motion. This is because intrachain mode Gruneisen parameters are usually much smaller, typically 0.000-0.5 while interchain  $v_a$ 's are larger than 1.0 (Ref. 28). The reason for this is simply that interchain vibrations (chain-chain) are much more strongly affected by pressure than intrachain vibrations (motions within the chain). The difference is

enhanced by the smaller frequencies which appear in the denominator of the expression for  $\sigma$ , Equation 10. Consequently, the picture of ion motion in PEO suggested by the results of the present pressure work is that at high temperatures both anions and cations undergo "interstice-interstice" hopping via low frequency interchain vibrations. "Interstices" are taken to be the spaces between the polymer chains. The reason for choosing the "interstices" rather than the chains themselves as the normal sites for both anions and cations at high temperatures is that if the ions reside on the chains, the effect of pressure should be to increase the conductivity since the chains would be closer together at elevated pressures. For "interstice-interstice" jumping, increased closeness of the chains should inhibit the motion thus decreasing the conductivity, as is observed experimentally.

As an alternative transport mechanism, the intrahelical jumping process, is often discussed in conjunction with these materials, some comments here are appropriate. This process is ruled out by the large mode Gruneisen parameter as that transport mechanism would require intrachain vibrations. However, chain-end bridging, which must be associated with an intrahelical jumping process in real materials, would probably require interchain vibrations and thus such a process might be consistent with the present results. However, the conclusion that the intrahelical jumping process is not dominant in these materials is consistent with the recent results of Papke et al.<sup>15</sup>

### 3.2. Free Volume Analysis

The pressure results can also be used to comment on free volume theory as represented by Equation (4). Papke et al.<sup>14</sup> have shown that on the basis of a configurational entropy model Equation (4) can be derived in which:

$$E_a = k_B \left[ \frac{q S_C^*}{B} \right] \quad (13)$$

where B is a constant,  $S_C^*$  is a configurational entropy, and  $T_0$  is a parameter usually associated with the glass transition temperature. In order to use Equation (4) to comment on the activation volume, the first step is to consider:

$$\frac{\partial \ln \sigma}{\partial P} = \frac{S_C^*}{k_B} \left[ v T_0 + G \left( \frac{T_0}{P} \right) \right] \quad (14)$$

assuming that  $S_C^*$  and B are independent of pressure. The two terms in Equation (14) are of approximately equal magnitude if  $T_0$  is identified with the glass transition temperature since, for polymers in general,  $(\partial S_C^* / \partial P)$  is about  $15 \text{ kJ/kbar}$ <sup>12</sup> and for PEO,  $T_0$   $250 \text{ K}$ <sup>19</sup> and  $v = 30 \text{ cm}^3/\text{mol}$ . Using these numbers, both terms in parentheses are about  $12 \times 10^{-27} \text{ k-m}^3$ .




Figure 5: Activation volume vs. temperature calculated using equation (15) and the values of the parameters given in the text.

These considerations have further implications concerning the activation volume and the nature of  $T_0$ . It follows from Equation (4) that:

$$v = \frac{q(1-f_0)}{k_B} \left[ \frac{\partial \ln \sigma_0}{\partial P} - \frac{\partial \ln \sigma}{\partial P} \right] = \frac{qf}{f_0(1-f_0)} \left( \frac{\partial T_0}{\partial P} \right) \quad (15)$$

Using the same numbers as above and values of  $q = 0.5 \text{ eV}$ ,  $(\partial \ln \sigma_0 / \partial P) = 0$ ,  $(\partial \ln \sigma / \partial P) = -15 \text{ GPa}^{-1}$ , and  $f_0 = 4 \text{ kJ/mol}$ ,<sup>20</sup> the values of the activation volume at various temperatures indicated by Equation (15) are plotted in Figure 5. The discontinuity at  $T_0$  and large negative values of  $v$  for  $T$  just above  $T_0$  are apparent. In fact, at  $T = 300 \text{ K}$ , which is about the temperature of the present experiment, Equation (15) yields  $v = -27 \text{ cm}^3/\text{mol}$ , a negative activation volume. As such activation volumes seem inappropriate for the present system, it is concluded that in free volume theory  $T_0$  cannot be interpreted as the glass transition temperature.

However, it is clear that the conductivity is often non-Arrhenius, obeying Equation (4) and thus free volume theory is useful, though the interpretation of  $T_0$  is unclear. An alternative interpretation is to attribute the curvature in the Arrhenius plots to "association" by analogy with ionic crystals. In PEO, association both with the chains and with each other (ion pairing) must be considered. Similar considerations have been suggested previously by Papke et al.<sup>14</sup> Additionally, the polymer is probably multiphase and thus some of the curvature may also be attributable to equilibration among the various phases.

### 3.3. Variation of $v$ with Pressure

Finally, a few comments will be made concerning the curvature of the  $\ln(\sigma)$  vs. pressure plots. The values of  $b$  in Equation (1) range from about 2 to 20(GPa)<sup>-2</sup>. These values are not unphysical as can be seen from the following analysis. Ignoring the correction term in Equation (9), the "compressibility of the activation volume,"  $\kappa_V$ , can be calculated from:

$$\kappa_V = - \frac{1}{V} \left( \frac{\partial \ln \sigma}{\partial P} \right)_T = \frac{2kTb}{V} \quad (16)$$

The results of the calculations are listed in Table 1. It is seen that the compressibility of the activation volume range from about 3% to 22%. This agrees with the theoretical expectations<sup>33-35</sup> and the experimental results<sup>30</sup> in ionic crystals where the compressibility of the migration volume is found to be on the order of 5-23 times the compressibility of the host lattice.

#### 4. SUMMARY

In summary, the effect of pressure on the ionic conductivity in alkali metal perchlorate and thiocyanate complexed P2O has been measured. The primary results are as follows:

(a) The activation volume scales with the size of both the anion and the cation. The simplest explanation of this is that both the anion and cation are mobile.

(b) The experimental results for the activation volume are in good agreement with the predictions of a dual ion diffusion theory with an attempt mode Gruber parameter of about 2. This implies that the motion of the ions is governed by interchain vibrations thus favoring interstitial-interstitial hopping of the ions.

(c) Free volume analysis lead to a negative activation volume if  $V_0$  is interpreted as the glass transition temperature. Consequently, curvature in the Arrhenius plots may better be interpreted in terms of "association" of the ions with the chains or with each other. In addition, equilibration of a multiphase system with the ions was observed.

(d) The compressibility of the activation volume is found to be about an order of magnitude larger than the compressibility of the host polymer.

#### ACKNOWLEDGMENTS

The authors would like to thank R. Dupon and D. E. Shriver of Northwestern University for providing a sample of PEO4.5-NaSCN. They would also like to thank J. E. Rabolt of IBM, San Jose, CA for helpful discussions. This work was supported in part by the Office of Naval Research.

#### REFERENCES

\*On leave from Simon Bolivar University, Caracas, Venezuela

- [1] Jenton, D.I., Parker, J.M., and Wright, P.V., *Polymer* 14 (1973) 589.
- [2] Wright, P.V., *Br. Polymer J.*, 7 (1975) 319.
- [3] Wright, P.V., *J. Polymer Sci.: Polymer Phys.*, 14 (1976) 955.
- [4] Parker, J.M., Wright, P.V., and Lee, C.C., *Polymer*, 22 (1981) 1305.
- [5] Lee, C.C. and Wright, P.V., *Polymer*, 23 (1982) 681.
- [6] Payne, D.R. and Wright, P.V., *Polymer*, 23 (1982) 690.
- [7] Archer, W.I. and Armstrong, R.D., *Electrochimica Acta*, 26 (1980) 1669.
- [8] Archer, W.I. and Armstrong, R.D., *Electrochimica Acta*, 26 (1980) 1671.
- [9] Dupon, R., Whitmore, D.H., and Shriver, D.E., *J. Electrochem. Soc.*, 128 (1981) 715.
- [10] Papke, B.L., Ratner, M.A., and Shriver, D.E., *J. Phys. Chem. Solids*, 42 (1981) 493.
- [11] Papke, B.L., Dupon, R., Ratner, M.A., and Shriver, D.E., *Solid State Ionics*, 5 (1981) 685.
- [12] Shriver, D.E., Papke, B.L., Ratner, M.A., Dupon, R., Wong, T., and Brodwin, M., *Solid State Ionics*, 5 (1981) 83.
- [13] Papke, B.L., Ratner, M.A., and Shriver, D.E., *J. Electrochem. Soc.*, 129 (1982) 1434.
- [14] Papke, B.L., Ratner, M.A., and Shriver, D.E., *J. Electrochem. Soc.*, 129 (1982) 1694.
- [15] Dupon, R., Papke, B.L., Ratner, M.A., Whitmore, D.H., and Shriver, D.E., *J. Am. Chem. Soc.*, 104 (1982) 671.
- [16] Arnold, M.F., Anabundo, J.M., and Duclot, M.J., in *Fast Ion Transport in Solids*, eds. Vashita, P., Mundy J.N., and Shenoy, G.B., (North Holland, Amsterdam, 1979) p. 131.
- [17] Lanzetta, J.J., Bailey, W., Frydrych, D., and Torv, B.S., *Solid State Ionics*, 4 (1981) 61.
- [18] Weston, J.E. and Steele, B.C.H., *Solid State Ionics*, 5 (1981) 347.
- [19] Weston, J.E. and Steele, B.C.H., *Solid State Ionics*, 7 (1982) 75.
- [20] Weston, J.E. and Steele, B.C.H., *Solid State Ionics*, 7 (1982) 81.
- [21] Fontanella, J.J., Wintersgill, M.C., Calame, J.P., Andeen, C.G., *Solid State Ionics*, to be published.
- [22] Wintersgill, M.C., Fontanella, J.J., Calame, J.P., Emerson, T.R., Andeen, C.G., *Solid State Ionics*, submitted.
- [23] Sorensen, F.R. and Jacobsen, I., *Electrochimica Acta*, 27 (1982) 1671.
- [24] Sorensen, F.R. and Jacobsen, I., *Polymer Bulletin*, 9 (1983) 47.
- [25] Fontanella, J., Andeen, C., and Schuele, B., *Phys. Rev.* B6 (1972) 582.
- [26] De, I., in *High Pressure Science and Technology*, 1981, MRSI conference, Vol. 1, ed. by J. P. Pomeroy and Technology, Ed. Chakrabarti, S.C., and Barber, H.S., (Plenum

- [27] Broadhurst, M.G. and Mopsik, F.L., J. Chem. Phys., 52 (1970) 3064.
- [28] Wu, C.K., Jura, G. and Shen, M., J. Appl. Phys., 43 (1972) 4348.
- [29] Flynn, C.P., Point Defects and Diffusion, (Oxford: Clarendon, 1972).
- [30] Fontanella, J.J., Wintersgill, M.G., Chadwick, A.V., Samatian, E., and Andeen, C.G., J. Phys. of Solid State Phys., 14 (1981) 2451.
- [31] Zallen, R., Phys. Rev. B9 (1974) 4415.
- [32] Quedsted, D.L. and Eskofoe-Iaorizi, M., J. Appl. Phys. 53 (1982) 6574.
- [33] Varotsos, P.A., J. Physique Lett. 38 (1977) L-455.
- [34] Varotsos, P.A., Phys. Rev. B18 (1978) 2683.
- [35] Varotsos, P. and Alexopoulos, K., Phys. Stat. Sol. (a)47 (1978) K133.

#### NOTE ADDED IN PROOF

After the completion of the work described above, two experiments were performed which extend and support the results reported above. First, careful differential scanning calorimeter (DSC) measurements were performed on all samples using a DuPont 990 DSC. The data for  $\text{PEO}_{4.5}\text{-NaClO}_4$  and  $\text{PEO}_{4.5}\text{-NaSCN}$  were extremely similar consisting of a weak, narrow melting at low temperatures (20-30C), a strong, narrow melting at high temperatures (150-180C), and a weak, broad endothermic event between these two peaks. This supports the comparison of these two materials at all temperatures. That data will be presented in detail elsewhere.

Second, the temperature range of the pressure measurements was extended to 350K for the two most important materials,  $\text{PEO}_{4.5}\text{-NaClO}_4$  and  $\text{PEO}_{4.5}\text{-NaSCN}$ . The results for  $\text{PEO}_{4.5}\text{-NaClO}_4$  can be represented by:

$$\ln(G(\Omega^{-1})) = -7.9 - 10.2P + 4.6P^2$$

and

$$\ln(G(\Omega^{-1})) = -8.0 - 7.3P$$

describes the data for  $\text{PEO}_{4.5}\text{-NaSCN}$ . The latter material was a hot-pressed sample provided by Northwestern University while the former was a film prepared in our laboratory. These results lead to activation volumes of 30.2 and 22.0  $\text{cm}^3/\text{mol}$ , respectively. Once again, the activation volume for  $\text{PEO}_{4.5}\text{-NaClO}_4$  is found to be much larger than for  $\text{PEO}_{4.5}\text{-NaSCN}$ . Consequently, this extends and supports the arguments above concerning ion size effects on  $v$  and the resultant conclusion concerning anion motion in these materials. Next, the activation volumes are smaller at 350K than at lower temperatures though not small enough to change any of the arguments presented above concerning the transport mechanism. That is, since  $\gamma_a = 1.72$  and  $2.38(1.29)$  for these materials at 350K, these are still much larger than would be expected for intrachain mode gammas. Finally, it is noted that the extremely large decrease in  $v$  (26.4 to 15.9  $\text{cm}^3/\text{mol}$  for 313 to 350K) as temperature increases which is reported by Chadwick, Strange, and Worboys for  $\text{PEO}_{4.5}\text{-NaSCN}$  at this conference, is not reproduced in the present work. However, it is noted that the  $\text{PEO}_{4.5}\text{-NaSCN}$  studied at 350K in the present

work was hot-pressed while that of Chadwick et al. was a film. Consequently, some of the difference may be due to the difference between the preparative techniques. In support of this, the  $\text{PEO}_{4.5}\text{-NaSCN}$  films studied in the present work showed significant curvature while the hot-pressed samples did not. Further, the zero pressure slope for the hot-pressed sample is about 10% lower than for the film. In addition, the  $\text{PEO}_{4.5}\text{-NaClO}_4$ , which is a film, does exhibit a somewhat larger decrease in activation volume as temperature increases (38.5 to 30.2  $\text{cm}^3/\text{mol}$  for 310 to 350K) than does the hot-pressed  $\text{PEO}_{4.5}\text{-NaSCN}$ . However, the decrease is still much smaller than that observed by Chadwick et al. Whatever the magnitude, it is clear that  $v$  does decrease with increasing temperature. Some decrease is expected since, as temperature increases and the polymer expands, the free volume increases and thus the activation volume should decrease. However, the decrease in activation volume appears to be too large to be explained by this effect. Rather, these results may represent evidence for an "association" process occurring in the polymer. In such a model, the large decrease in activation volume follows since at low temperatures there is a "volume of formation" for the associated ions in addition to a "motion volume." The activation volume then decreases because the "formation volume" decreases due to increased "dissociation" as temperature increases.

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Office of Naval Research Attn: Code 413 500 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
CNR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper NPPC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. Paul Delahay Department of Chemistry New York University New York, New York 10003	1	Dr. P. J. Hendra Department of Chemistry University of Southampton Southampton SO0 5NH United Kingdom	1
Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 41106	1	Dr. Sam Perone Chemistry & Materials Science Department Lawrence Livermore National Lab. Livermore, California 94550	1
Dr. D. N. Bennion Department of Chemical Engineering Brigham Young University Provo, Utah 84602	1	Dr. Royce W. Murray Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1
Dr. R. A. Marcus Department of Chemistry California Institute of Technology Pasadena, California 91125	1	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
Dr. J. J. Auburn Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. C. E. Mueller The Electrochemistry Branch Materials Division, Research and Technology Department Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910	1
Dr. Adam Heller Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. G. Goodman Johnson Controls 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. T. Katan Lockheed Missiles and Space Co., Inc. P. O. Box 504 Sunnyvale, California 94088	1	Dr. J. Boechler Electrochimica Corporation Attn: Technical Library 2485 Charleston Road Mountain View, California 94040	1
Dr. Joseph Singer, Code 302-1 NASA-Lewis 21090 Brookpark Road Cleveland, Ohio 44135	1	Dr. P. P. Schmidt Department of Chemistry Oakland University Rochester, Michigan 48063	1
Dr. B. Brummer E-I Incorporated 77 Chapel Street Newton, Massachusetts 02158	1		
Library E. B. Millory and Company, Inc. Northwest Industrial Park Burlington, Massachusetts 01803	1		



TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. H. Richtol Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1	Dr. R. P. Van Duyne Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. A. B. Ellis Chemistry Department University of Wisconsin Madison, Wisconsin 53706	1	Dr. B. Stanley Pons Department of Chemistry University of Alberta Edmonton, Alberta CANADA T6G 2G2	1
Dr. M. Wrighton Chemistry Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139		Dr. Michael J. Weaver Department of Chemistry Michigan State University East Lansing, Michigan 48824	1
Larry E. Plew Naval Weapons Support Center Code 30736, Building 2906 Grane, Indiana 47522	1	Dr. R. David Rauh EIC Corporation 55 Chapel Street Newton, Massachusetts 02158	1
S. Fuby EGE (STOR) 600 E Street Providence, Rhode Island 02192	1	Dr. J. David Margerum Research Laboratories Division Hughes Aircraft Company 3011 Malibu Canyon Road Malibu, California 90265	1
Dr. Aaron Kold Brown University Department of Chemistry Providence, Rhode Island 02192	1	Dr. Martin Fleischmann Department of Chemistry University of Southampton Southampton SO9 5NH England	1
Dr. R. C. Chudacek M. Law-Edison Company Edison Battery Division Post Office Box 28 Bloomfield, New Jersey 07003	1	Dr. Janet Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. A. J. Bard University of Texas Department of Chemistry Austin, Texas 78712	1	Dr. R. A. Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. M. M. Nicholson Electronics Research Center Rockwell International 3370 Miraloma Avenue Anaheim, California	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. Donald W. Ernst Naval Surface Weapons Center Code R-33 White Oak Laboratory Silver Spring, Maryland 20910	1	Mr. James R. Moden Naval Underwater Systems Center Code 3632 Newport, Rhode Island 02840	1
Dr. R. Nowak Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Dr. Bernard Spielvogel U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709	1
Dr. John F. Houlihan Shenango Valley Campus Pennsylvania State University Sharon, Pennsylvania 16146	1	Dr. Denton Elliott Air Force Office of Scientific Research Bolling AFB Washington, D.C. 20332	1
Dr. D. F. Shriver Department of Chemistry Northwestern University Evanston, Illinois 60201	1	Dr. David Aikens Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1
Dr. D. H. Whitmore Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Dr. A. P. E. Lever Chemistry Department York University Downsview, Ontario M3J1P3 Canada	1
Dr. Alan Bewick Department of Chemistry The University Southampton, SO9 5NH England		Dr. Stanislaw Szpak Naval Ocean Systems Center Code 6343 San Diego, California 95152	1
Dr. A. Hily NAVSEA-5433 MC #4 2541 Jefferson Davis Highway Arlington, Virginia 20362		Dr. Gregory Farrington Department of Materials Science and Engineering University of Pennsylvania Philadelphia, Pennsylvania 19104	
Dr. John Kincaid Department of the Navy Strategic Systems Project Office Room 901 Washington, D.C. 20376		Dr. Bruce Dunn Department of Engineering & Applied Science University of California Los Angeles, California 90024	

TECHNICAL REPORT DISTRIBUTION LIST, 359

<u>No.</u> <u>Copies</u>	<u>No.</u> <u>Copies</u>
M. L. Robertson Manager, Electrochemical and Power Sonics Division Naval Weapons Support Center Crane, Indiana 47522 1	Dr. T. Marks Department of Chemistry Northwestern University Evanston, Illinois 60201 1
Dr. Elton Cairns Energy & Environment Division Lawrence Berkeley Laboratory University of California Berkeley, California 94720 1	Dr. D. Cipris Allied Corporation P. O. Box 3000R Morristown, New Jersey 07960 1
Dr. Micha Tomkiewicz Department of Physics Brooklyn College Brooklyn, New York 11210 1	Dr. M. Philpot IBM Corporation 5600 Cottle Road San Jose, California 95193 1
Dr. Lesser Blum Department of Physics University of Puerto Rico Rio Piedras, Puerto Rico 00931 1	Dr. Donald Sandstrom Washington State University Department of Physics Pullman, Washington 99164 1
Dr. Joseph Gordon, II IBM Corporation K33/281 5600 Cottle Road San Jose, California 95193 1	Dr. Carl Kannewurf Northwestern University Department of Electrical Engineering and Computer Science Evanston, Illinois 60201 1
Dr. Robert Somoano Jet Propulsion Laboratory California Institute of Technology Pasadena, California 91103 1	Dr. Edward Fletcher University of Minnesota Department of Mechanical Engineering Minneapolis, Minnesota 55455 1
Dr. Johann A. Joebstl NSA Mobility Equipment R&D Command BRME-EC Fort Belvoir, Virginia 22060 1	Dr. John Fontanella <del>U.S. Naval Academy</del> Department of Physics Annapolis, Maryland 21402 1
Dr. Judith H. Ambrus NASA Headquarters M.S. RTS-6 Washington, D.C. 20546 1	Dr. Martha Greenblatt Rutgers University Department of Chemistry New Brunswick, New Jersey 08903 1
Dr. Albert R. Landgrebe U.S. Department of Energy M.S. 6B025 Forrestal Building Washington, D.C. 20595 1	Dr. John Wassib Kings Mountain Specialties P. O. Box 1173 Kings Mountain, North Carolina 28086 1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>	<u>No.</u> <u>Copies</u>
Dr. J. J. Brophy University of Utah Department of Physics Salt Lake City, Utah 84112	1	
Dr. Walter Roth Department of Physics State University of New York Albany, New York 12222	1	
Dr. Thomas Davis National Bureau of Standards Polymer Science and Standards Division Washington, D.C. 20234	1	
Dr. Charles Martin Department of Chemistry Texas A&M University	1	
Dr. Anthony Sammells Institute of Gas Technology 3424 South State Street Chicago, Illinois 60616	1	
Dr. H. Tachikawa Department of Chemistry Jackson State University Jackson, Mississippi 39217	1	
Dr. W. M. Risen Department of Chemistry Brown University Providence, Rhode Island	1	