

AD-A136 314

PREPARATION OF A PROFILED FILM OF DIAMOND-LIKE CARBON  
ON GERMANIUM SUBSTRATES(U) BARR AND STROUD LTD GLASGOW  
(SCOTLAND) J S ORR NOV 83 EOARD-TR-84-05

1/1

UNCLASSIFIED


F49620-83-C-0112

F/G 20/12

NL



END  
DATE  
FILMED  
1 84  
DTIC



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. Report Number EOARD TR-84-05	2. Govt Accession No.	3. Recipient's Catalog Number	
4. Title (and Subtitle)  Preparation of a Profiled Film of Diamond- Like Carbon on Germanium Substrates		5. Type of Report & Period Covered Final Scientific Report 1 June to 9 August 1983	
		6. Performing Org. Report Number	
7. Author(s) J. S. Orr		8. Contract or Grant Number F49620-83-C-0112	
9. Performing Organization Name and Address Barr & Stroud Ltd. Caxton Street Anniesland Glasgow G13 1HZ, UK		10. Program Element, Project, Task Area & Work Unit Numbers 61102F 2301/D1 Work Unit Serial No. 163	
11. Controlling Office Name and Address European Office of Aerospace Research and Development/LSP Box 14, FPO New York 09510		12. Report Date November 1983	
		13. Number of Pages 12	
14. Monitoring Agency Name and Address		15.	
16. & 17. Distribution Statement Approved for public release; distribution unlimited.			
18. Supplementary Notes			
19. Key Words HARD COATINGS                      ENVIRONMENTALLY DURABLE COATINGS PROTECTIVE COATINGS              HARD CARBON COATINGS              THIN FILMS			
20. Abstract The objective of this contract was to prepare a profiled film of the Barr and Stroud diamond-like carbon coatings on germanium substrates. This report describes the techniques used to prepare the films and the results of optical measurements. The samples have been supplied to the US Government for further optical and environmental analysis. ←			

PREPARATION OF A PROFILED FILM OF  
DIAMOND-LIKE CARBON ON GERMANIUM SUBSTRATES

Report of Results for USAF Contract F49620-83-C-0112DEF

Compiled by: J.S. Orr

Approved by: B.C. Monachan, Project Leader  
A.J.N. Hope, Project Manager



NOVEMBER 1983

<b>Accession For</b>	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A1	

BARR AND STROUD LIMITED

Registered Office

Caxton Street  
Annieisland  
GLASGOW G13 1HZ

London Office

Melrose House  
4-6 Savile Row  
LONDON W1X 1AF

1. SUMMARY

The objective of this contract was to prepare a profiled film of the Barr and Stroud diamond-like carbon coating on five germanium substrates. The profile of the film was to be in accordance with Figure 1 and the substrates coated on one face. The specification of the substrates used is listed in Table 1.

This report describes the techniques used to prepare the films and the results of optical measurements on the samples.

2. DEPOSITION TECHNIQUE

A masking technique was developed specifically to prepare profiled films for this contract. The construction of the mask is illustrated in Figure 2. The mask was cut from  $\frac{3}{1000}$ " thick molybdenum sheet using a spark erosion technique to avoid any sharp edges which could damage the substrate surface. The mask could slide in a groove machined in an aluminium holder and was retained in position by two thin aluminium strips. In the middle of the electrode was a hole for the substrate. Shims of molybdenum were used to adjust the height of the substrate so that its upper surface was level with the lower surface of the mask. The complete structure was firmly bolted to the RF electrode of a sputtering unit. The position of the mask was adjusted from outside the vacuum system with a linear motion vacuum feedthrough acting via an insulated rod against a bracket on the mask.

The deposition technique and conditions for the coating are proprietary to Barr and Stroud and confidential. The thickness of the films was controlled by measuring the time of the deposition while keeping the deposition conditions constant (e.g. pressure, gas flow rate, RF power, bias voltage, etc). A series of tests was performed to obtain a calibration curve of thickness against time.

Each substrate was cleaned by hand using an optical handkerchief and iso-propyl alcohol. In addition the substrates were cleaned for about 15 minutes using an argon discharge with the mask in the position which exposed the complete substrate. Immediately after the argon discharge clean the mask was moved to its second position where all but the area to be uncoated was exposed and  $\lambda/4$  of the coating was deposited ( $\lambda = 3.8\mu\text{m}$ ). The mask was then moved about  $3/8$ " and a further  $\lambda/4$  deposited. This was repeated a further two times. In order to ensure good adhesion of the coating and consistent deposition rates, the discharge was not interrupted from the start of the argon clean to the completion of the coating.

### 3. RESULTS OF MEASUREMENTS

Witness pieces were subjected to a number of durability tests and the results are summarised in Table 2.

The transmission of each step of every sample was measured using a Fourier Transform Infra-red Spectrometer. The transmission of a typical sample is illustrated in Figures 3, 4, 5 and 6. The estimated optical thickness for each sample is summarised in Table 3 along with the target values.

### 4. CONCLUSION

Five germanium substrates have been successfully coated with a profiled film of diamond-like carbon to the requested specification within experimental limits.

JSO/LP

1.12.83

Optical Thickness

Where  $\lambda = 3.8 \mu\text{m}$





FIGURE 1

GEOMETRY OF ARG 4 FILM  
(TARGET)



MASKING ARRANGEMENT


FIGURE 2



NICOLET MX-1 SAMPLE NO. 4 (1st STEP)

NR= 128  
SC= 80  
PF= 108  
DF= 1.00  
CAN 6


FIGURE 3



NICOLET MX-1 SAMPLE NO. 4 (2nd STEP)

NO= 128  
SC= 80  
PF= 109  
DF= 1.00  
GRAN 8


FIGURE 4



NICOLET MX-1 SAMPLE NO. 4 (3rd STEP)

NS= 128  
SC= 80  
PF= 109  
DF= 1.00  
GAN B


FIGURE 5



NICOLET MX-1 SAMPLE NO. 4 (4th STEP)

NS= 128  
SC= 80  
PF= 100  
DF= 1.00  
CAN 8

FIGURE 6



SPECIFICATION FOR SUBSTRATES

- 1) Diameter  $1.52'' + 0.000''$   
 $- 0.005''$
- 2) Thickness  $0.25 - 0.375''$
- 3) Flatness 2 fringes visible or better
- 4) Parallelism 30 sec of arc or better

TABLE 1

RESULTS OF DURABILITY TESTS ON WITNESS PIECES

Test	Relevant Specification	Witness Piece 1 (Optical thickness $\lambda/4$ where $\lambda = 3.2\mu\text{m}$ )	Witness Piece 2 (Optical thickness $\lambda/4$ where $\lambda = 15.9\mu\text{m}$ )
Abrasion	MIL-C-675A para 4.6.11	pass	pass
Adhesion	MIL-M-13508B para 4.4.6	pass	pass
Salt Solution	MIL-C-675A para 4.6.8	pass	pass
Wiper Action	(see below)	pass	pass

Wiper Action: Coatings subjected to 10,000 wipes with a windscreen blade loaded to 20 grams and operating with a sand/water mixture to DEF STAN 07-55 Type C without measurable deterioration.

TABLE 2

ESTIMATED OPTICAL THICKNESS OF EACH STEP

	Optical thickness in $\lambda/4$ where $\lambda = 3.8\mu\text{m}$			
	Step 1	Step 2	Step 3	Step 4
Target Values	1.00	2.00	3.00	4.00
Sample 1	1.16	2.21	3.16	4.21
Sample 2	1.11	2.13	3.03	3.84
Sample 3	1.11	2.03	3.03	3.89
Sample 4	1.08	2.08	3.03	4.00
Sample 5	1.24	2.13	3.05	3.95

TABLE 3