



MICROCOPY RESOLUTION TEST CHART NATIONAL BUREAU OF STANDARDS-1963-A

÷

.

AD-A142 951

AMMRC TR 84-6

AD

B

023

# INTERDEPENDENCE OF EQUIVALENT STEADY STRESS, CRACK GROWTH AND FAILURE ON SEQUENCE AND AMPLITUDE OF IRREGULAR LOADING

REINIER BEEUWKES, Jr. MECHANICS AND STRUCTURAL INTEGRITY LABORATORY

February 1984

E

Approved for public release; distribution unlimited.

ARMY MATERIALS AND MECHANICS RESEARCH CENTER Watertown, Massachusetts 02172

	IN PAGE	READ INSTRUCTIONS
REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
AMMRC TR 84-6		
. TITLE (and Subtitle)		S TYPE OF REPORT & PERIOD COVERE
INTERDEPENDENCE OF EQUIVALENT S	STEADY STRESS,	
CRACK GROWTH AND FAILURE ON SEC	QUENCE AND	Final Report
AMPLITUDE OF IRREGULAR LOADING		6 PERFORMING ORG. REPORT NUMBER
AUTHOR(s)		B. CONTRACT OR GRANT NUMBER(a)
Reinier Beeuwkes, Jr.		
		10 BROCK AM EL ENENT DROIECT TAS
Army Materials and Mechanics R	ess Asearch Center	AREA & WORK UNIT NUMBERS
Watertown, Massachusetts 02172	2	D/A Project: 1L161102AH4
DRXMR-S		
1. CONTROLLING OFFICE NAME AND ADDRESS		12. REPORT DATE
U. S. Army Materiel Developmen	nt and Readiness	February 1984
Command, Alexandria, Virginia	22333	24
14. MONITORING AGENCY NAME & ADDRESS(IL dill	erent from Controlling Office)	15. SECURITY CLASS, (of this report)
		UNCIASSIFICATION DOWNGRADING
		SCHEDULE
Approved for public release; d:	istribution unlimit	ed. m Report)
Approved for public release; d:	istribution unlimit prod in Bluck 20. II dille and tro	ed . m Report)
Approved for public release; d: TO DISTRIBUTION STATEMENT (of the observect entry as an unclassified Special Public Beeuwkes, Jr. In this edition; along with a change of reference William Matthews. S. KEY WORDS (Continue on reverse side if necessar	istribution unlimit wood in Block 20, if different fro t was issued in sm lication, AMMRC SP , a few typographi ces on page 19. I	ed. m Report) all quantity in August 197 77-9, authored by Reinier cal changes have been made t has been reviewed by
Approved for public release; di TO DISTRIBUTION STATEMENT (of the obstract onto as an unclassified Special Public Beeuwkes, Jr. In this edition along with a change of reference William Matthews. Stress analysis	istribution unlimit was issued in sm lication, AMMRC SP , a few typographi ces on page 19. I y and identify by block number) Loadi	ed. m Report) all quantity in August 197 77-9, authored by Reinier cal changes have been made t has been reviewed by ng (mechanics)
Approved for public release; di DISTRIBUTION STATEMENT (of the ebettect entry as an unclassified Special Public Beeuwkes, Jr. In this edition along with a change of reference William Matthews. Stress analysis Crack propagation	istribution unlimit frod in Block 20. If different fro t was issued in sm lication, AMMRC SP , a few typographi ces on page 19. I y and identify by block number Loadi Strai	ed. m Report) all quantity in August 197 77-9, authored by Reinier cal changes have been made t has been reviewed by ng (mechanics) n (mechanics)
Approved for public release; d: TO DISTRIBUTION STATEMENT (of the observent entry as an unclassified Special Public Beeuwkes, Jr. In this edition; along with a change of reference William Matthews. Stress analysis Crack propagation Fracture (mechanics)	istribution unlimit was issued in sm lication, AMMRC SP , a few typographi ces on page 19. I y and identify by block number) Loadi Strai	ed. m Report) all quantity in August 197 77-9, authored by Reinier cal changes have been made t has been reviewed by ng (mechanics) n (mechanics)
Approved for public release; di TO DISTRIBUTION STATEMENT (of the obstract entry as an unclassified Special Public Beeuwkes, Jr. In this edition; along with a change of reference William Matthews. Stress analysis Crack propagation Fracture (mechanics)	istribution unlimit red in Block 20. Il diller was in lication, AMMRC SP , a few typographi ces on page 19. I r and identify by block number) Loadi Strai	ed. m Report) all quantity in August 197 77-9, authored by Reinier cal changes have been made t has been reviewed by ng (mechanics) n (mechanics)
Approved for public release; d: TO. DISTRIBUTION STATEMENT (of the ebettect entry as an unclassified Special Public Beeuwkes, Jr. In this edition; along with a change of reference William Matthews. Stress analysis Crack propagation Fracture (mechanics) Continue on reverse side II necessory	istribution unlimit red in Block 20. II diller one fro t was issued in sm lication, AMMRC SP , a few typographi ces on page 19. I y and identify by block number) Loadi Strai	ed. m Report) all quantity in August 197 77-9, authored by Reinier cal changes have been made t has been reviewed by ng (mechanics) n (mechanics)
Approved for public release; di DISTRIBUTION STATEMENT (of the obstract entry as an unclassified Special Public Beeuwkes, Jr. In this edition; along with a change of reference William Matthews. Stress analysis Crack propagation Fracture (mechanics) D. ABSTRACT (Continue on reverse side II necessary (Si	istribution unlimit red in Block 20. If different fro t was issued in sm lication, AMMRC SP , a few typographi ces on page 19. I r end identify by block number) Loadi Strai r end identify by block number) EE REVERSE SIDE)	ed. m Report) all quantity in August 197 77-9, authored by Reinier cal changes have been made t has been reviewed by ng (mechanics) n (mechanics)

. **T**V - - - Ne

#### UNCLASSIFIED SECURITY CLASSIFICATION OF THIS PAGE (When Date Entertal)

Block No. 20

### ABSTRACT

This paper shows how to predict the minimum or other life of material limited by cyclic crack growth and crack failure as a function of the different sequences of amplitudes of loading that may occur under random, quasi-random, or controllable loading conditions. It is assumed that the incremental growth, as well as the criterion of failure, is independent of the history of loading and environment. The method covers the most commonly used law of crack growth and of crack failure. It is obviously applicable to other cyclically induced cumulative phenomena, e.g., degradation as in erosion or thermal fatigue.

#### UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE When Date Entered)

# CONTENTS

5745.5

53.55 - 1.22.57

No. of the Island

AND COURSE PRESERVED IN COURSE IN

							Page
INTRODUCTION	• • • •		· · · ·	• •		 	. 1
CONDITION FOR MAXIMUM AND	MINIMUM	CRACK	GROWTH.			 	. 2
EQUIVALENT STEADY STRESS.	••••		· · · ·		• •	 	. 10
PROBABILITY OF FAILURE			••••	• •		 	. 13
l. Random Loading . 2. Ordered Loading.	•••••	· · ·	•••••	 	 	  · · ·	. 14 . 19
APPENDIX			• • • •	• •		 	. 21



Accession For NTTS STOL DTIC TYPE ] 11 Unarte Ju ' ----B7.... -Distribution/ Avail bility Codes Avail tubjor Dist | Special

0110 A CO

# Page

#### INTRODUCTION

If one accepts some of the most common types of laws for rate of crack growth and crack failure, including the assumption that incremental growth is independent of the history of loading, one is in a position to address himself to some important questions of general behavior, including that of the effect on crack growth and life of different types of loads.

In particular, we are concerned in this paper with the effect of load sequence on crack growth and failure, in cases where the loading is a spectrum of loads of different amplitudes. To take an example, let us suppose we have a gun or other tube, containing a small internal crack, to which a series of internal pressures, some high, some low, are to be applied. We may ask, will the ultimate crack growth be less if the high pressures are applied first, when the crack is shortest, than if they are applied last, when the crack is longer? And, since crack length and stress may be simultaneously significant in cataclysmic, e.g.,  $K_{IC}$  failure, what sequence of loads will give the shortest life? And is this serious condition likely to occur under random loading?

Representation and the second second

Provide a succession of the second se

Also, are there circumstances such that for growth under many cycles of loading, sequence of loading is unimportant? If so, what is the equivalent steady stress that gives the same growth per cycle of stressing as does a spectrum of loads? What do we mean by the term cycle of stressing for an irregular spectrum?

It is to such questions that this paper is addressed. Our treatment has been heuristic rather than mathematically complete; it is hoped that a method of treatment of such questions has been made sufficiently self-evident that the reader can use it for himself, for his own particular problems, if he so chooses.

#### CONDITION FOR MAXIMUM AND MINIMUM CRACK GROWTH

The growth  $\Delta a$ , of a crack of length "a", per cycle of nominal loading stress, S, is commonly given by

 $\Delta \mathbf{a}/\mathrm{cycle} = C_1 \quad \mathbf{K}^m = C_2 \quad \mathbf{S}^m \quad \mathbf{a}^{m/2} \quad \mathbf{Y}_c^m, \qquad m \ge 2$ 

in regions of K or "a" where the C's are constants and K is the toughness stress<sup>\*</sup>intensity parameter. S as used in the above formula is usually taken to be  $S_{max}-S_{min}$ , where  $S_{max}$  is the maximum and  $S_{min}$  the minimum stress in a cycle of stressing. If the loading spectrum is irregular in shape, we define each rise in stress as a cycle.  $Y_c$  is a parameter, constant or increasing\* with increase in "a" and expressing the geometry involved, such as 1.1215 for an edge crack or  $1/\sqrt{\cos \pi a/w}$  for a central crack in a plate of width w. We assume that the constants  $C_1$  and  $C_2$  may be different in different regions of crack length and, correspondingly, that there may be sudden transitions in the rate of crack growth as a crack grows longer. Though we have some exceptional evidence of sudden decreases in rate, this finding should be further investigated, and we shall assume here that the rate does <u>not</u> decrease with crack growth. Furthermore, we restrict ourselves to cases where the loading stresses are tensile, thus avoiding the complication of complete crack closure by compression and ambiguous experimental results.

Thus, for N stresses, S (=  $S_{max}-S_{min}$ )

$$\sum \frac{\Delta a}{a^{m/2} Y_c^m} = C_2 \sum S^m$$
  
$$\sum over N \text{ stresses, } S$$

\*For cracks leading to failure; this restriction eliminates cases of crack closure resulting from crack growth toward a negatively stressed region. and the sum on the left must increase, as will "a" when the sum on the right increases with additional cycles of S.\*

Thus "a" will be greater at any stage of crack growth, the larger the sum on the right. And the latter sum will obviously be greatest if the largest values of S, occurring in the entire spectrum of loading, are crowded into it (independent of order, so long as they are the largest). Therefore, with the above law of crack growth "a" will be maximum up to any number of cycles, N, if the largest occurring values of S are used up, in computing the sum up to the N stresses, on the right. And if, on the other hand, the smallest values of S are used first, "a" will be minimum.

The intermediate cases of crack growth for n cycles may be found, in order of severity, by progressively decreasing the sum of the n stresses on the right. The probability of occurrence of any number n of selected loads out of a total of N occurring in a representative<sup>+</sup> cyclic graph of loading is

 $P = \frac{n! (N-n)!}{N!}$ 

Contraction of the

The final value of "a", i.e., the total growth corresponding to use of . all the cycles of S, is a fixed value, independent of the order of application of the stresses, S.

<sup>\*</sup>In conformance with restrictions made up to this point, it will be observed that we confine ourselves to the case where the increments are linearly additive. That is, we confine ourselves to laws of growth for which the incremental growth per load application is independent of the history of loading and environment. Later on it may be noted that we have implicitly restricted our failure criteria in the same way.

<sup>+&</sup>quot;Representative" here means long enough to determine frequencies of occurrence of all loads. Although the loading spectrum of a machine under test may be controlled, in practice one is interested in ensemble characteristics.

Figure 1 illustrates by a simple example the above formula for an initial crack length a = 1 and a loading stress sequence of three cycles, S = 1, 2, 3. (The stresses and lengths may be considered to be measured in any units the reader desires, e.g., S in ksi, "a" in inches.) It demonstrates the method of computation for "a" as well as the  $\Delta a/a$  of the above equation, and shows the equality of both sides of the equation.

Our argument above will perhaps be made clearer by considering the above growth law expressed in integral form. This representation is possible because the steps  $\Delta a$  are very small and numerous. We have

$$\int_{a_0}^{a} \frac{da}{a^{m/2} Y_c^m} = C_2 \int_0^N S^m dN$$

Suppose, for simplicity Y<sub>c</sub>is constant.

Then

$$\frac{if m>2}{\frac{1 - (a_0/a)^{m/2 - 1}}{Y_c a_0^{m/2 - 1}(m/2 - 1)}} = C_2 \int_0^N S^m dN$$

$$\frac{if m=2}{Y_{c}^{-2}} + \frac{1}{n} a/a_{o} = C_{2} \int_{0}^{N} S^{2} dN$$

Here "a" is the crack length after any specified number, N, of cycles of stressing.\* In either case, m > 2 or m = 2, the larger "a" is, the larger the left hand term is, and this will be greatest when the integral on the right is greatest, that is, when it contains the largest values of S. Thus "a" is maximum when the integral on the right contains the largest values of S. \*So long as "a" remains in a region where  $C_2$  is constant.

	Start	Cycle 1	Cycle 2	Cycle 3
Stress, S	0	1	2	3
s <sup>2</sup>	0	1	4	9
$\Sigma s^2$	0	1	5	14
$\Delta a=S^2a$	<u>0</u>	1 x 1 = 1	4x2=8	9x10=90
a=a_+∑∆a	1	1+1=2	·→ 2+8=10	10+90=100
∆a/a	0	1/1=1	8/2=4	90/10=9
ΣΔa/a	0	1	5	14

Figure 1. Simple Example. Growth Law  $\Delta a/cycle$  of stressing = S<sup>2</sup>a. Crack Length  $a = a_0 + \Sigma S^2 a$  and  $\Sigma \Delta a/a = \Sigma S^2$  for N = 1, 2, and 3 Cycles of Stressing.

ANALYSSE ROODDOD REALERED BODDODD ADDIDDOD ADDIDDOD ADDIDDOD ADDIDDOD ADDIDDOD ADDIDDOD

Clearly the order of application of these (N) selected largest stress cycles is of no importance since the integral on the right may be conceived as an area made up of the sum of small rectangular areas of base dN and height S<sup>m</sup>, the order of addition being inconsequential.

Abrupt changes in C upon reaching certain crack lengths, representing transitions to higher rates of crack growth as the crack grows longer, do not invalidate the above conclusion. For, obviously, we wish the crack to have a maximum length up to the transition and thereafter we may consider the transition point with its associated crack length, as the start of a new problem. Pushing the transition points closer together, we approach the case of a continuously increasing C.

Analytically, if C is an increasing function of "a", it will go under the summation of integral on the left, as  $Y_{c}$  does, but obviously will not invalidate the above conclusions. In this respect, it may be satisfying to consider the writer's crack growth law with transitions. The crack growth laws between transitions are like those just considered with m=2 in  $K^m \sim S^m a^{m/2}$  but the constants are theoretical. The constant in any region is double that in the preceding region and for constant loading stress, the crack length at any transition is twice the length at the preceding transition, i.e.,  $\bar{a}_n = 2^n \bar{a}_0$ . These crack growth transitions  $\bar{a}_n$ ,  $\bar{N}_n$ , on an "a" vs N plot fall on a hyperbola

$$N-\bar{N}_{o} = \frac{2\ln 2}{C_{th}} (1 - \bar{a}_{o}/a)$$

where  $\bar{a}_0$ ,  $\bar{N}_0$  are values of  $\bar{a}_n$ ,  $\bar{N}_n$ .

Scholard Contraction

" $\bar{a}_0$ " is a length characteristic of the material considered. For some materials the usual initial crack length in common crack growth specimens does not greatly differ from  $\bar{a}_0$ . In this case N<sub>0</sub> = 0, of course.

$$C_{th} = C S^2 = \left[ \left( \frac{2}{3} \right)^{1/3} \left( 1 - \mu^2 \right)^{4/3} \left( \frac{1}{E} \right)^{4/3} \left( \frac{1}{Y} \right)^{2/3} \right] S^2$$

where E is Young's modulus,  $\mu$  is Poisson's ratio and Y is the yield strength under cyclic loading corresponding to stress\* S.

\*The above formula for  $C_{th}$  is for the usual case of very small scale yielding near the crack tip, thus for small S/Y ( $\equiv S_y/Y$ ), or, more generally, for isotropic loading  $S_x = S_y$  with essentially isotropic yielding.

A more generally applicable formula for the case where the loading stress  $S_{\rm X}$  along the crack, and the loading stress  $S_{\rm Y}$  perpendicular to the crack, rise and fall together is

$$C_{th} = \frac{(2/3)^{1/3} [E/(1-\mu^2)]^{-4/3} Y^{-2/3} S_y^2}{\left\{1 - (\sqrt{3}/2) (S_y/Y) [(1 - S_x/S_y)]\right\}^{2/3}}$$

(This formula is the same as it was in the corresponding footnote of the first (1977) issue of this report except that a term then supposed to render the formula applicable to orthotropic yielding has been removed.)

For simplicity, it is this hyperbola, which is periodically correct, that we consider as our growth law, instead of the actual law with transitions.

Differentiating N,

$$\frac{dN}{da} = \frac{2 \ln 2}{C_{th}} \frac{a_o}{a^2} \quad (S = Const. \text{ for each increment and cycle of crack growth.})$$

Hence

$$\frac{(2\ln 2)}{a^2} = C \sum_{n=1}^{\infty} S^2$$
N stresses

where  $C = C_{th}/S^2 = Const.$  Or, in integral form,

$$\int_{a_0}^{a} \frac{(2\ln 2) \ \tilde{a}_0 \ da}{a^2} = C \int_{0}^{N} S^2 \ dN$$

i.e.,

$$(21n2) (\tilde{a}_{0}/a_{0}) (1 - a_{0}/a) = C \int_{0}^{N} S^{2} dN$$

(Note that m = 4, page 4, also gives an "a" vs N hyperbola of this shape, with stresses to the fourth power instead of second power as here, a difference not noticeable in constant stress tests in which growth rate constants are determined empirically.)

The form of these expressions validates the conclusions already drawn. The maximum crack length up to any number of cycles corresponds to application of the cycles of greatest stress, independent of order. Figure 2 shows the effect of load sequence by extending the simple example of Figure 1 to all possible sequences of the three loading stresses given there. Since there are three distinct loading stresses, there are six cases in all, S = 1, 2, 3; S = 1, 3, 2; S = 2, 1, 3; S = 2, 3, 1; S = 3, 1, 2; S = 3, 2, 1 for the first, second, and third cycles, respectively. As noted, equal crack lengths result from application of a set of loads independent of order of application. Up to any point, use of the largest loads results in greatest "a" and use of the smallest loads results in least "a".

It is not difficult, in some cases, to satisfactorily approximate a spectrum of numerous loads, which may be applied in any sequence, by a few loads such that the effects and frequency of application of different load sequences may be easily handled and visualized without the aid of a large computer. Thus, for example, since d ln a  $\sim S^m$  dN with  $Y_c = Const.$ , in the rate of crack growth formula, if there are  $n_1$ ,  $n_2$  ...  $n_o$  numbers of stresses  $S_1$ ,  $S_2$  ...  $S_o$ , respectively, we might form the products  $n_1 S_1^m$ ,  $n_2 S_2^m$  .....  $n_o S_o^m$ , then omit any stress levels for which any of these products are unimportant compared to the remainder, then lump the remaining stress levels into a few which are applied for the total number of cycles contained in their components, e.g., for stress level p, of these few

$$S_p^m = \frac{n_x S_x^m + n_{x+1} S^m + etc.}{n_x + n_{x+1} + etc.}$$

applied for the number of cycles  $n_p$  equal to the sum in the denominator of the right-hand side.

Figure 3a is an illustration of crack growth where stresses are applied repetitively, for an m = 2 crack growth equation.

			Start	Cycle 1	Cycle 2	Cycle 3	
1.	Stress,	<u>S</u>	0	1	2	3	
		$\Delta a=S^{2}a$	0	(1)(1)=1	(4)(2)=8	(9)(10)=90	
		a=a <sub>0</sub> + ΣΔa	1	1+1=2		10+90=100	
2.		<u>S</u>	0	1	3	2	
		∆a	0	(1)(1)=1	(9)(2)=18	(4)(20)=80	
		а	1	2	20	100	
3.		<u>S</u>	0	2	1	3	
		∆a	0	(4)(1)=4	(1)(5)=5	(9)(10)=90	
		a	1	5	10	100	
4.		<u>S</u>	0	2	3	1	
		∆ <b>a</b>	0	(4)(1)=4	(9)(5)=45	(1)(50)=50	
		a	1	5	50	100	
5.		<u>S</u>	0	3	1	2	
		Δa	0	(9)(1)=9	(1)(10)=10	(4)(20)=80	
		a	1	10	20	100	
6.		S	0	3	2	1	
		∆a	0	(9)(1)=9	(4)(10)=40	(1)(50)=50	
		a	1	10	50	100	

Figure 2. Example: Effect of Sequence of Loading Stress S on Crack Growth Δa/cycle of Stressing=S<sup>2</sup>a. Initial (S=0) Crack Length, a=1. S=1, 2, and 3. Note Independence of Order of Application, e.g., a=100 for S=1, 2, and 3 in all cases and a=10 for two cycles, S=1 and 2, Cases 1 and 3.

St haddaa haaaaa maad

ale la la la la la

#### EQUIVALENT STEADY STRESS

By the term <u>equivalent steady stress</u> applied to a cracked specimen, we mean a cyclic stress of constant amplitude whose application would result in the same crack growth as that due to any specified portion of a loading spectrum of irregular amplitude, if the number of cycles of load application were the same for each type of loading.

As so defined, it may have different values for portions of the spectrum made up of different loads, but it will have a unique value for the whole spectrum since this includes all the loads.

The expressions for equivalency are apparent from the summation or integral expressions we have already obtained. Since for both the constant amplitude steady and the irregular stress the crack growth is to be the same, the left-hand sides of these expressions must be the same whether produced by a steady stress or an irregular stress. Thus if there are  $N_r$  cycles in the portion of the spectrum being considered, and if the steady equivalent stress is  $S_{eq}$ , the sum or integral on the right must be equal to  $S_{eq}^m N_r$ .

That is,

$$S_{eq}^{m} N_{r} = \int_{0}^{N_{r}} S^{m} dN = \sum_{N_{r}} S^{m}$$

for the power laws; m = 2 for the envelope hyperbola.

Thus if there are  $n_1$  stresses  $S_1$ ,  $n_2$  stresses  $S_2$ , ...  $n_r$  stresses  $S_r$ , such that

$$\sum_{i=1}^{n_i} n_i = N_r; \quad n_i/N_r = f_i$$

Part A With  $\frac{da}{dt} = S^2 a/100$  $\ln a_1/a_0 = S_1^2 n_1/100 \qquad \ln a_2/a_1 = S_2^2 n_2/100 \qquad \ln a_3/a_2 = S_3^2 n_3/100$  $\ln a_3/a_0 = \ln a_2/a_0 + \ln a_3/a_2$  $\ln a_2/a_0 = \ln a_1/a_0 + \ln a_2/a_1$ Region, i, 0 (Start) 1 2 3 Cycles, n<sub>i</sub> 2 10 0 1 s<sub>i</sub> 1 2 3 0  $S_{i}^{2} n_{i}^{100} 0$ 0.10 0.08 0.09  $\Sigma s_1^2 n_i / 100$ 0 0.18 0.10 0.27  $\ln a_i/a_{i-1}(=S_i^2n_i/100)$ 0.10 0.08 0.09  $\Sigma \ln a_i / a_{i-1} (= \Sigma S_{i}^2 n_i / 100) = 0$  $\ln a_1/a_0 = 0.10 \ln a_2/a=0.18 \ln a_3/a_0 = 0.27$ a<sub>i</sub>  $a_0 = 1$  $a_1 = 1.11$   $a_2 = 1.20$  $a_{\chi} = 1.31$ Part B Let  $\Sigma n_{i} = N_{t}(=13);$  $n_i/N_t = f_i$  $\ln a_3/a_0 = (S_1^2 n_1 + S_2^2 n_2 + S_3^2 n_3)/100$ =  $(S_1^2 f_1 + S_2^2 f_2 + S_3^2 f_3)N_t/100 = S_{eq}^2 N_t/100$ Thus  $S_{eq}^2 = S_1^2 f_1 + S_2^2 f_2 + S_3^2 f_3 = 1 (10/13) + 4(2/13) + 9 (1/13) = 27/13$  $S_{eq} = 1.44$ 

Figure 3. Example with m=2, da/dN= $S^2a/100$ . Amplitude (Part A) and Equivalent Steady Stress (Part B) when n<sub>1</sub> Cycles of S<sub>1</sub>, n<sub>2</sub> Cycles of S<sub>2</sub>, and n<sub>3</sub> Cycles of S<sub>3</sub> are applied in succession.

we have\*

$$S_{eq}^{m} N_{r} = n_{1} S_{1}^{m} + n_{2} S_{2}^{m} + \dots + n_{r} S_{r}^{m}$$
$$= (f_{1} S_{1}^{m} + f_{2} S_{2}^{m} + \dots + f_{r} S_{r}^{m}) N_{r}$$

whence

$$S_{eq}^{m} = f_1 S_1^{m} + f_2 S_2^{m} + \dots + f_r S_r^{m}$$

in which m = 2 for the hyberbola envelope law as well as the m = 2 power law.

Figure 3b shows the calculation for S for the simple case of Figure 3a, eq where three loads were applied in succession for different numbers of cycles.

For another example, suppose that the distribution of frequencies is Gaussian in N<sub>r</sub> cycles,  $\sigma$  being the standard deviation.

$$S_{eq}^{m} N_{r} = \int S^{m} \frac{N_{r}}{\sqrt{2\pi}} \exp\left[-\frac{1}{2}\left(\frac{S-S_{\mu}}{\sigma}\right)^{2}\right] d\left(\frac{S-S_{\mu}}{\sigma}\right)$$

where S<sub>µ</sub> is the mean value of the cyclic stress rise S = S<sub>max</sub> - S<sub>min</sub>, so that

$$S = \left[ \left( S - S_{\mu} \right) + S_{\mu} \right] \text{ and thus}$$

$$S_{eq}^{m} = \frac{\sigma^{m}}{\sqrt{2\pi}} \int \left[ \frac{S - S_{\mu}}{\sigma} + \frac{S_{\mu}}{\sigma} \right]^{m} \exp\left[ -\frac{1}{2} \left( \frac{S - S_{\mu}}{\sigma} \right)^{2} \right] d\left( \frac{S - S_{\mu}}{\sigma} \right)$$

$$= \frac{\sigma^{m}}{\sqrt{2\pi}} \int \left( x + \frac{S_{\mu}}{\sigma} \right)^{m} \exp\left( -\frac{x^{2}}{2} \right) dx$$

\*See Appendix for a cyclic relationship in lieu of equivalent stress.

where  $X \equiv (S-S\mu)/\sigma$ 

Since the lower limit (least value) of S is zero, the lower limit of X is - (S $_{\mu}/\sigma).$ 

If this and the upper limit are large, we may assume the integration is between  $-\infty$  and  $+\infty$ .

Let us assume this is the case and that  $\underline{m} = 2$ . Then  $S_{eq}^2 = \frac{\sigma^2}{\sqrt{2\pi}} \int_{-\infty}^{+\infty} \left[ x^2 + 2x \frac{S_{\mu}}{\sigma} + \left( \frac{S_{\mu}}{\sigma} \right)^2 \right] \exp\left( -\frac{x^2}{2} \right) dx$ 

The exponential function is positive and symmetrical about X = 0 so that the middle term in the brackets makes no contribution and we have

$$S_{eq}^2 = \sigma^2 + S_{\mu}^2$$
 "Gaussian S e"

Naturally, if  $\sigma$  is zero, there is no scatter and S = S  $\mu$ 

The case of the parabolic distribution, with its finite cut-off, is treated for general values of m as part of the problem of probability of failure.

#### PROBABILITY OF FAILURE

In this section we consider, in an illustrative way, the probability of failure of a piece of material containing a crack or notch and subjected to the various succession of loads of a given spectrum of loading. It is presumed that the piece will fail when the loading stress reaches a critical value,  $S_{mc}$ . In current cases of interest concerning cracks, this value of  $S_{mc}$  is commonly obtained from an association of critical toughness value,  $K_{IC}$ , and crack length. The latter depends on the number of cycles of loading together with the equivalent steady stress to which the piece has been subjected. The practical limitations of this approach to  $S_{mc}$  and probability of failure will be briefly considered along with notch failure.

We first consider the case of random loading and then a class of ordered loading. In the latter case we consider, in particular, the effect of the condition for maximum crack growth.

# 1. Random Loading

CARLENCE CONTRACTOR OF CONTRACTOR

Let us assume that the distribution of both the maximum stresses  $S_m$ ,  $S_m \equiv S_{max}$ , and the stress rises,  $S \equiv S_{max} - S_{min}$  are parabolic\* with the same standard deviation  $\sigma$ . Let  $S_{m\mu}$  be the mean value of  $S_{max}$  and  $S_{\mu}$  be the mean value of the rises, S.

Thus, for the maximum stresses

$$\mathbf{f} = \frac{3\sqrt{5}}{20\sigma} \left[ 1 - \frac{\left(\mathbf{S}_{m} - \mathbf{S}_{m\mu}\right)^{2}}{5\sigma^{2}} \right], \quad -\sigma\sqrt{5} \leq \left(\mathbf{S}_{m} - \mathbf{S}_{m\mu}\right) \leq \sigma\sqrt{5}$$

with f = 0 for  $S_m \ge \sigma\sqrt{5}$  and for  $S_m \le -\sigma\sqrt{5}$ 

so that the probability that  $S_m \ge S_{mc}$  is

$$P (S_{m} \ge S_{mc}) = \int \frac{3\sqrt{5}}{20\sigma} \left[ 1 - \frac{(S_{m} - S_{m\mu})^{2}}{5\sigma^{2}} \right] d (S_{m} - S_{m\mu})$$
$$= (3\sqrt{5}/20) \left\{ 2\sqrt{5}/3 - \left[ (S_{mc} - S_{m\mu})/\sigma \right] \left[ 1 - (1/15) (S_{mc} - S_{m\mu})^{2}/\sigma^{2} \right] \right\}$$

\*Note that the constants in the expressions used below are not the same as that of the peak region of the Gaussian distribution. Here  $\sigma$  is the  $\sigma$  of the parabolic distribution, not the  $\sigma$  of the Gaussian.

for 
$$-\sigma\sqrt{5} \leq (S_m - S_{m_1}) \leq \sigma\sqrt{5}$$

deres a

with P = 0 for  $S_m \ge \sigma\sqrt{5}$  and for  $S_m \le -\sigma\sqrt{5}$ .

Similarly for the stress differences,  $S = S_{max} - S_{min}$ ,

$$\mathbf{f} = \frac{3\sqrt{5}}{20\sigma} \left[ 1 - \frac{(S-S_{\mu})^2}{5\sigma^2} \right], \quad -\sigma\sqrt{5} \leq (S-S_{\mu}) \leq \sigma\sqrt{5}$$

with f = 0 for  $S \ge \sigma\sqrt{5}$  and for  $S \le -\sigma\sqrt{5}$ ,

so that the equivalent stress,  $S_{eq}$ , is given by

$$S_{eq}^{m} N_{r} = \int_{-\sigma\sqrt{5}}^{\sigma\sqrt{5}} S^{m} N_{r} \left(\frac{3\sqrt{5}}{20\sigma}\right) \left[1 - \frac{(S-S_{\mu})^{2}}{5\sigma^{2}}\right] d(S-S_{\mu})$$

where the crack growth per cycle is proportional to  $S^{\text{m}}$ .

Since

$$S^{m} = (X+S_{\mu})^{m} \text{ with } X = S-S_{\mu},$$

$$S^{m}_{eq} = \frac{3\sqrt{5}}{20\sigma} \int_{-\sigma\sqrt{5}}^{+\sigma\sqrt{5}} (X+S_{\mu})^{m} \left[1 - \frac{X^{2}}{5\sigma^{2}}\right] dX$$

$$= \frac{\delta(m+2) \left[(\delta+\tau)^{m+2} + (-\delta+\tau)^{m+2}\right] - \tau \left[(\delta+\tau)^{m+2} - (-\delta+\tau)^{m+2}\right]}{\delta^{3} (m+1) (m+2) (m+3) (2/3)}$$

where  $\delta = \sigma \sqrt{5}$  and  $\tau = S_{ij}$ .

Thus\* if m = 1,  $S_{eq} = S_{\mu}$  m = 2,  $S_{eq}^2 = S_{\mu}^2 + \sigma^2$  m = 3,  $S_{eq}^3 = S_{\mu}^3 + 3S_{\mu}\sigma^2$ m = 4,  $S_{eq}^4 = S_{\mu}^4 + 6 S_{\mu}^2\sigma^2 + (15/7) \sigma^4$ 

The form of the expression for  $S_{eq}$  for m = 2 is the same as it is for the Gaussian distribution which we derived heretofore even though the approximate form of the peak region of the Gaussian, which is also parabolic, has different constants.

Knowing  $S_{eq}$  from this formula we can compute the crack length after any number of cycles of loading prior to failure. If m = 2 we may, for example, have the writer's crack growth law, or his periodically correct hyperbolic simplification (page 7) of it. In the latter case,<sup>†</sup>

$$(\delta + \tau)^{m+2} = \Sigma 0 + \Sigma E \text{ by binomial expansion}$$
where  $\Sigma 0 = \Sigma 1 \text{ st}$ ,  $3 \text{ rd}$ ,  $5 \text{ th}$ , etc., terms  

$$\Sigma E = \Sigma 2 \text{ nd}$$
,  $4 \text{ th}$ ,  $6 \text{ th}$ , etc., terms  
whence  $For \text{ even m}$   

$$S_{eq}^{m} = \frac{3[\delta(m+2)\Sigma 0 - \tau\Sigma E]}{\delta^{3}(m+1)(m+2)(m+3)}$$

$$S_{eq}^{m} = \frac{3[\delta(m+2)\Sigma E - \tau\Sigma 0]}{\delta^{3}(m+1)(m+2)(m+3)}$$

$$F(1) \text{ Let it take N}_{0} \text{ cycles to get to a}_{0}$$

$$N_{0} - \tilde{N}_{0} = (2 \ln 2/C_{th})(1 - \bar{a}_{0}/a_{0}) \text{ (v.: } p. 6)$$
(2) Let it take  $(N + N_{0})$  cycles to get to "a" (changing the meaning of N  
on page 6)  

$$(N + N_{0}) - \bar{N}_{0} = (2 \ln 2/C_{th})(1 - \bar{a}_{0}/a)$$
(3) Subtract (1) from (2), above, to get the N cycles it takes to get from  
 $a_{0}$  to "a."  

$$N = -(2 \ln 2/C_{th})(\bar{a}_{0}/a - \bar{a}_{0}/a_{0})$$
which gives  

$$a = a_{0}/\left[1 - (a_{0}/\bar{a}_{0})(C_{th}N)/(2 \ln 2)\right] (v.: p. 7)$$
in all of which  $C_{th} = C S_{e0}^{2}$ 

$$a = a_0 / [1 - (a_0 / \bar{a}_0) (C S_{eq}^2 N) / (2 \ln 2)]$$

where  $\bar{a}_0$  is a material constant (~~2 mm),  $a_0$  is the measure of the initial crack length (half length of a central crack in a wide plate) and  $S_{eq}$  is the equivalent range of loading stress acting perpendicularly to the crack, derived above for the parabolic distribution.

If a critical stress intensity factor,  $K_{IC}$ , is applicable to the material used and is known for the temperature where failure is to be evaluated,

$$K_{IC} = (S_{mc} \vee a) Y_{o}$$
  
i.e.,  $S_{mc} = K_{IC} / (\sqrt{a} Y_{c})$ 

where  $S_{mc}$  is the peak loading stress corresponding to  $K_{IC}$ ,  $Y_{c}$  is a parameter which is constant or increases for cracks leading to failure, and "a" is a crack length or depth which we find from our crack growth formula. Thus

$$S_{mc} = (K_{IC}/Y_c) / \left\{ a_0 / [1 - (a_0/\bar{a}_0) (C S_{eq}^2 N) / 2 \ln 2) \right\}$$

and our probability of failure is given by our formula for P, that is, the probability of occurrence of a stress equal to or greater than  $S_{mc}$ :

$$P(S_{m} \ge S_{mc}) = (3\sqrt{5/20}) \left\{ 2\sqrt{5/3} - [(S_{mc} - S_{m\mu})/\sigma] [1 - (1/15)(S_{mc} - S_{m\mu})^{2}/\sigma^{2}] \right\}$$

where  $S_{mu}$  is the mean value the peak stresses.

For  $(S_{mc}-S_{m\mu}) \ge \sigma \sqrt{5}$ , the probability P is zero. Since  $S_{mc}$  is the value of  $K_{IC}/(\sqrt{a} Y_c)$  it is not a loading stress per se, but is the stress required to cause fracture, a stress value which the loading stress may or may not equal. Thus  $S_{mc}$  may exceed any loading stresses applied in our bounded loading spectrum in which case there is zero probability of the occurrence of any loading stress as large as  $S_{mc}$ . As the crack length measure a, increases with increase in N, or  $K_{IC}$  decreases with (ordinarily) decrease in temperature,  $S_{mc} = K_{IC}/\sqrt{a}$  may decrease from a safe high value until it lies within the loading range, in which case there will be a probability of failure given by the above formula for P. If  $S_{mc}$  falls so that  $S_{mc}-S_{m\mu} = -\sigma\sqrt{5}$ , P = 1 and failure is certain.

In fact  $K_{IC}$  may fall so far and so rapidly with temperature decrease on the lower side of the toughness transition temperature that  $S_{mc}$  is practically independent of changes in length a. In this case  $S_{mc}$  may be lower than the operating range of stresses and the failure may be regarded as a <u>stress failure</u> independent of crack length, associated with operation below the transition temperature, rather than as a  $K_{IC}$  failure. Failures insensitive to crack length, but responsive to stress and transition temperature have been observed and studied by this writer.

On the other hand, there are cases where the crack growth necessary to bring  $S_{mc}$  down to the operating range of stress is so great that only a practically insignificant amount of life would remain even if  $K_{IC}$ failure did not intervene. In practice, through-the-section yielding may even occur in the net section below the crack, before a critical failure stress is attained, such that the resultant deformation may render the piece useless. In this case, however, the critical stress  $S_{mc}$  would not be found from the usual formula for  $K_{IC}$  which presuppose small scale yielding.

Fatigue life may, of course, be estimated by use of the equivalent steady stress if one employs a fatigue life law conformable in type to that used in our analysis of crack growth. Power law approximations to

any exact law are suitable. Thus if we have a stressed notch to deal with, we may calculate a life to first macroscopic crack appearance and a subsequent life using for crack depth a depth which includes the original notch depth. If appreciable crack growth occurs, the type of analysis for probability of failure with simple cracks which we have illustrated above, would be applicable. The probability of failure prior to cracking may be gotten from the above formula for P, omitting the crack growth equation.  $S_{mc}$  in this case might be determined from destructive tests on notched material made after a few cycles of loading, or estimated from the fracture stress F of the material, if this is known, by using theory which takes account of yielding about the notch root. (1,2,3)

#### 2. Ordered Loading

Here we deal with a finite number of loads of different amplitudes, as with a gun that may be loaded with a variety of charges and whose life is limited by crack growth if not terminated by the application of a sufficient load or corresponding  $K_{IC}$ . We wish to know what material toughness would be required to withstand any selected load of the loading spectrum, after the application in any sequence, of any other selected loads.

For the most severe condition, these loads would be chosen to give maximum crack growth and the loading stress applied after their application

<sup>(1)</sup> BEEUWKES, R., Jr. "Characteristics of Crack Failure," Surfaces and Interfaces, Syracuse University Press, Syracuse, NY, Vol. II, 1968, p. 277.

<sup>(2)</sup> BEEUWKES, R., Jr. "Determination of Fracture Stress and Effective Crack Tip Radius from Toughness (K<sub>IC</sub>) and Yield Strength (Y)," Army Materials and Mechanics Research Center, AMMRC TR 78-44, October 1978.

<sup>(3)</sup> TRACEY, DENNIS M., and FREESE, COLIN E. "Cyclic Plasticity Near a Cracklike Elliptical Flaw," Mechanics of Materials, Vol.I, 1982, p. 151-159.

would be chosen to be the maximum loading stress in the entire spectrum of loads. Although this final load may be included among those causing the maximum crack growth, this inclusion is unimportant where there are many cycles of loading since no appreciable growth occurs in any one loading.

The crack depth resulting from application of any group of loads may be found as discussed in preceding sections. If the final loading stress in the group is  $S_m$ , failure by the  $K_{IC}$  criterion will occur if

$$(S_m \sqrt{a}) Y_c \geq K_{IC}$$

assuming  $K_{IC}$  is known. Conversely the toughness necessary to prevent failure must be greater than the product on the left-hand side of this relationship.

# APPENDIX

## Cyclic Relationship in Lieu of Equivalent Stress

We had (top of page 12)

 $S_{eq}^{m}$   $N_{r} = n_{1} S_{1}^{m} + n_{2} S_{2}^{m} + \dots + n_{r} S_{r}^{m}$ 

with  $\Sigma n_i = N_r$ 

Let n<sub>f1</sub>, n<sub>f2</sub> etc. be defined by

 $S_1^m n_{f1} = S_{eq}^m N_r$ 

 $S_2^m n_{f2} = S_{eq}^m N_r$  etc.

Then

$$S_{eq}^{m} N = n_{1} \frac{eq r}{n_{f1}} + n_{2} \frac{eq r}{n_{f2}} + \dots + n_{r} \frac{eq r}{m_{fr}}$$

whence

$$\sum_{i=1}^{r} \frac{n_{i}}{n_{fi}} = 1$$

of which a particular case may be fatigue provided the  $n_{fi}$  correspond to fatigue failures and S and N to the endurance limit.

CopiesToCommander, U.S. Army Agency for Aviation Safety, Fort Rucker, AL 363621 ATTN: Technical LibraryCommander, USACDC Air Defense Agency, Fort Bliss, TX 799161 ATTN: Technical Library Commander, U.S. Army Engineer School, Fort Belvoir, VA 220601 ATTN: LibraryCommander, U.S. Army Engineer Waterways Experiment Station, Vicksburg, MS 391801 ATTN: Research Center Library Commander, U.S. Army Engineer Materways Experiment Station, Vicksburg, MS 391801 ATTN: Research Center LibraryCommander, U.S. Army Environmental Hygiene Agency, Edgewood Arsenal, MD 210101 ATTN: Chief, Library BranchTechnical Director, Human Engineering Laboratories, Aberdeen Proving Ground, MD 210051 ATTN: Technical Reports OfficeCommandant, U.S. Army Quartermaster School, Fort Lee, VA 238011 ATTN: Quartermaster School LibraryCommander, U.S. Army Radio Propagation Agency, Fort Bragg, NC 283071 ATTN: SCCR-2Naval Research Laboratory, Washington, DC 20375 1 ATTN: Dr. C. 1. Chang - Code 5830 22Dr. G. R. Yoder - Code 6384
Commander, U.S. Army Agency for Aviation Safety, Fort Rucker, AL 36362 1 ATTN: Technical Library Commander, USACDC Air Defense Agency, Fort Bliss, IX 29916 1 ATTN: Technical Library Commander, U.S. Army Engineer School, Fort Belvoir, VA 22060 1 ATTN: Library Commander, U.S. Army Engineer Waterways Experiment Station, Vicksburg, MS 39180 1 ATTN: Research Center Library Commander, U.S. Army Environmental Hygiene Agency, Edgewood Arsenal, MD 21010 1 ATTN: Chief, Library Branch Technical Director, Human Engineering Laboratories, Aberdeen Proving Ground, MD 21005 1 ATTN: Technical Reports Office Commandant, U.S. Army Quartermaster School, Fort Lee, VA 23801 1 ATTN: Quartermaster School Library Commander, U.S. Army Radio Propagation Agency, Fort Bragg, MC 28307 1 ATTN: SCCR-2 Naval Research Laboratory, Washington, DC 20375 1 ATTN: Dr. C. 1. Chang - Code 5830 2 Dr. G. R. Yoder - Code 6384
<ul> <li>Arthin Technical Frontary</li> <li>Commander, USACDC Air Defense Agency, Fort Bliss, IX (1916)</li> <li>ATTN: Technical Library</li> <li>Commander, U.S. Army Engineer School, Fort Belvoir, VA (22060)</li> <li>ATTN: Library</li> <li>Commander, U.S. Army Engineer Waterways Experiment Station, Vicksburg, MS (39180)</li> <li>ATTN: Research Center Library</li> <li>Commander, U.S. Army Engineer Haterways Experiment Station, Vicksburg, MS (39180)</li> <li>ATTN: Research Center Library</li> <li>Commander, U.S. Army Environmental Hygiene Agency, Edgewood Arsenal, MD (2000)</li> <li>ATTN: Chief, Library Branch</li> <li>Technical Director, Human Engineering Laboratories, Aberdeen Proving Ground, MD (2005)</li> <li>ATTN: Technical Reports Office</li> <li>Commandant, U.S. Army Quartermaster School, Fort Lee, VA (23801)</li> <li>ATTN: Quartermaster School Library</li> <li>Commander, U.S. Army Radio Propagation Agency, Fort Bragg, NC (28307)</li> <li>ATTN: SCCR-2</li> <li>Naval Research Laboratory, Washington, DC (20375)</li> <li>ATTN: Dr. C. I. Chang - Code (5830)</li> <li>Dr. G. R. Yoder - Code (6384)</li> </ul>
<ul> <li>Alimi Technical Library</li> <li>Commander, U.S. Army Engineer School, Fort Belvoir, VA 22060</li> <li>ATTM: Library</li> <li>Commander, U.S. Army Engineer Waterways Experiment Station, Vicksburg, MS 39180</li> <li>ATTN: Research Center Library</li> <li>Commander, U.S. Army Environmental Hygiene Agency, Edgewood Arsenal, MD 21010</li> <li>ATTN: Chief, Library Branch</li> <li>Technical Director, Human Engineering Laboratories, Aberdeen Proving Ground, MD 21005</li> <li>ATTN: Technical Reports Office</li> <li>Commandant, U.S. Army Quartermaster School, Fort Lee, VA 23801</li> <li>ATTN: Quartermaster School Library</li> <li>Commander, U.S. Army Radio Propagation Agency, Fort Bragg, MC 28307</li> <li>ATTN: SCCR-2</li> <li>Naval Research Laboratory, Washington, DC 20375</li> <li>ATTN: Dr. C. 1. Chang - Code 5830</li> <li>Dr. G. R. Yoder - Code 6384</li> </ul>
<ul> <li>Arthi, Elbrary</li> <li>Commander, U.S. Army Engineer Waterways Experiment Station, Vicksburg, MS 39180</li> <li>ATTN: Research Center Library</li> <li>Commander, U.S. Army Environmental Hygiene Agency, Edgewood Arsenal, MD 21010</li> <li>ATTN: Chief, Library Branch</li> <li>Technical Director, Human Engineering Laboratories, Aberdeen Proving Ground, MD 21005</li> <li>ATTN: Technical Reports Office</li> <li>Commandant, U.S. Army Quartermaster School, Fort Lee, VA 23801</li> <li>ATTN: Quartermaster School Library</li> <li>Commander, U.S. Army Radio Propagation Agency, Fort Bragg, MC 28307</li> <li>ATTN: SCCR-2</li> <li>Naval Research Laboratory, Washington, DC 20375</li> <li>ATTN: Dr. C. I. Chang - Code 5830</li> <li>Dr. G. R. Yoder - Code 6384</li> </ul>
<ol> <li>ATTN: Research Center Library</li> <li>Commander, U.S. Army Environmental Hygiene Agency, Edgewood Arsenal, MD 21010</li> <li>ATTN: Chief, Library Branch</li> <li>Technical Director, Human Engineering Laboratories, Aberdeen Proving Ground, MD 21005</li> <li>ATTN: Technical Reports Office</li> <li>Commandant, U.S. Army Quartermaster School, Fort Lee, VA 23801</li> <li>ATTN: Quartermaster School Library</li> <li>Commander, U.S. Army Radio Propagation Agency, Fort Bragg, NC 28307</li> <li>ATTN: SCCR-2</li> <li>Naval Research Laboratory, Washington, DC 20375</li> <li>ATTN: Dr. C. I. Chang - Code 5830</li> <li>Dr. G. R. Yoder - Code 6384</li> </ol>
<ol> <li>ATŤN: Chief, Library Branch</li> <li>Technical Director, Human Engineering Laboratories, Aberdeen Proving Ground, MD 21005</li> <li>ATTN: Technical Reports Office</li> <li>Commandant, U.S. Army Quartermaster School, Fort Lee, VA 23801</li> <li>ATTN: Quartermaster School Library</li> <li>Commander, U.S. Army Radio Propagation Agency, Fort Bragg, NC 28307</li> <li>ATTN: SCCR-2</li> <li>Naval Research Laboratory, Washington, DC 20375</li> <li>ATTN: Dr. C. I. Chang - Code 5830</li> <li>Dr. G. R. Yoder - Code 6384</li> </ol>
<ol> <li>ATTN: Technical Reports Office</li> <li>Commandant, U.S. Army Quartermaster School, Fort Lee, VA 23801</li> <li>ATTN: Quartermaster School Library</li> <li>Commander, U.S. Army Radio Propagation Agency, Fort Bragg, NC 28307</li> <li>ATTN: SCCR-2</li> <li>Naval Research Laboratory, Washington, DC 20375</li> <li>ATTN: Dr. C. I. Chang - Code 5830</li> <li>Dr. G. R. Yoder - Code 6384</li> </ol>
Fort Lee, VA 23801 1 ATTN: Quartermaster School Library Commander, U.S. Army Radio Propagation Agency, Fort Bragg, NC 28307 1 ATTN: SCCR-2 Naval Research Laboratory, Washington, DC 20375 1 ATTN: Dr. C. I. Chang - Code 5830 2 Dr. G. R. Yoder - Code 6384
Commander, U.S. Army Radio Propagation Agency, Fort Bragg, NC 28307 1 ATTN: SCCR-2 Naval Research Laboratory, Washington, DC 20375 1 ATTN: Dr. C. I. Chang - Code 5830 2 Dr. G. R. Yoder - Code 6384
Naval Research Laboratory, Washington, DC 20375 1 ATTN: Dr. C. I. Chang – Code 5830 2 Dr. G. R. Yoder – Code 6384
Chief of Naval Research, Arlington VA 22217 1 ATTN: Code 471
Commander, U.S. Air Force Wright Aeronautical Laboratories, Wright-Patterson Air Force Base, OH - 45433
1 AFWAL/MLLP, M. Forney Jr. 1 AFWAL/MLLP, M. Stanley Schulman
1 Edward J. Morrissey, AFWAL/MLTE, Wright Patterson Air Force Base, OH 45433
National Aeronautics and Space Administration, Washington, DC 20546 1 ATTN: Mr. G. C. Deutsch – Code RW
National Aeronautics and Space Administration, Marshall Space Flight Center, Huntsville, AL 35812 1 ATTN: R. J. Schwinghammer, EHOl, Dir, M&P Lab
1 Mr. W. A. Wilson, EH41, Bldg. 4612
<ol> <li>Ship Research Committee, Maritime Transportation Research Board, National Research Council, 2101 Constitution Ave., N. W., Washington, DC 20418</li> </ol>
1 Librarian, Materials Sciences Corporation, Guynedd Plaza 11 Bethlehem Pike, Spring House, PA 19477
Panametrics, 221 Crescent Street, Waltham, MA 02154 1 ATTN: Mr. K. A. Fowler
1 The Charles Stark Draper Laboratory, 68 Albany Street, Cambridge, MA 02139
Wyman-Gordon Company, Worcester, MA 01601 1 ATTN: Technical Library
Lockheed-Georgia Company, 86 South Cobb Drive, Marietta, Marietta, GA 30063 1 ATTN: Materials and Processes Engineering Dept. 71–11 Zone 54
General Dynamics, Convair Aerospace Division, P.O. Box 748, Fort Worth, TX 76101 1 ATTN: Mfg. Engineering Technical Library
<ol> <li>Mechanical Properties Data Center, Belfour Stulen Inc., 13917 W. Bay Shore Drive, Traverse City, M1 49684</li> <li>May D. J. Ductore TALC</li> </ol>
J Mr. R. J. Zentner, EAI Corporation, 198 Thomas Johnson Drive, Suite 16, Frederick, MD 21701 Director, Army Materials and Mechanics Research Center.

5567518181818181818

<u>Misinta Catata</u>

This paper shows how to predict the minimum or other life of material limited by cyclic crack growth and crack failure as a function of the different sequences of amplitudes of loading that may occur under random, quasi-random, or controllable loading conditions. It is assumed that the incremental growth, as well as the riterion of failure, is independent of the history of loading and environment. The method covers the most commonly used law of crack growth and of crack failure. It is obviously applicable to other cyclically induced cumulative phenomena, e.g., degradation as in erosion or thermal fatigue. UNLIMITED DISTRIBUTION UNLIMITED DISTRIBUTION This paper shows how to predict the minimum or other life of material limited by cyclic crack growth and crack failure as a function of the different sequences of amplitudes of loading that may occur under random, quasi-random, or controllable loading conditions. It is assumed that the incremental growth, as well as the eriterion of failure. is independent of the history of loading and environment. The method covers the most commonly used law of crack growth and of crack failure. It is obviously applicable to other cyclically induced cumulative phenomena, e.g., degradation as in erosion or thermal fatigue. Fracture (mechanics) Fracture (mechanics) Crack propagation UNCLASSIFIED Crack propagation Key Words Stress analysis Key Words Stress analysis Ş ð Technical Report AMMRC TR 84-6, February 1984, 24 pp -illus, D/A Project 1L161102AH42 Technical Report AMMRC TR 84-6, February 1984, 24 pp illus, D/A Project IL161102AH42 Watertown, Massachusetts 021/2 Interdefendence of Equivalent Steady Stress, Crack Grownth and Failure om Sequence and Amplitude of Irregular Loading -STRESS, Materials and Mechanics Research Center, MATERIOM, MASSACHUSETTS 02172 INTERDEPENDENCE OF EQUIVALENT STEADY STRE CRACK GROWTH AND FAILURE ON SEQUENCE AND AMPLITUDE OF IRREGULAR LOADING -Materials and Mechanics Research Center, Reinier Beeuwkes, Jr. Reinier Beeuwkes, Jr. Army Army UNCLASSIFIED UNLIMITED DISTRIBUTION This paper shows how to predict the minimum or other life of material limited by cyclic crack growth and crack failure as a function of the different sequences of amplitudes of loading that may occur under random, quasi-random, or controllable loading conditions. It is assumed that the incremental growth, as well as the incremental growth, as well as the method covers the most commonly used law of crack growth and of crack failure. It is obviously applicable to other cyclically induced cumulative phenomena, e.g., degradation as in erosion or thermal fatigue. UNLIMITED DISTRIBUTION This paper shows how to predict the minimum or other life of material limited by cyclic crack growth and crack failure as a function of the different sequences of amplitudes of loading that may occur under random, quasi-random, or controllable loading conditions. It is assumed that the incremental growth, as well as the criterion of failure, is independent of the history of loading and environment. The method covers the most commonly used law of crack growth and of crack failure. It is obviously applicable to other cyclically induced cumulative phenomena, e.g., degradation as in erosion or thermal fatigue. Fracture (mechanics) Crack propagation Fracture (mechanics) Crack propagation UNCLASSIFIED Key Words Stress analysis Key Words Stress analysis 8 8 Technical Report AMMRC TR 84-6, February 1984, 24 pp -illus, D/A Project 1L161102AH42 Technical Report AMMRC TR 84-6, February 1984, 24 pp illus, D/A Project 1L161102AH42 Materials and Mechanics Research Center, Watertom, Massachusetts 021/2 INTERDEFENDENCE OF EQUIVALENT STEADY STRESS, CRACK ERONTH AND FAILURE ON SEQUENCE AND AMPLITUDE OF TRREGULAR LOADING -Materials and Mechanics Research Center, Materionn, Massachusetts 021/2 Materionn, Massachusetts 021/2 INTERDEFENDENCE OF EQUIVALENT STEADY STRESS, CRACK ERONTH AND FAILURE ON SEQUENCE AND AMPLITUDE OF IRREGULAR LOADING -Reinier Beewkes, Jr. Reinier Beewkes, Jr Â Army

1. 2. C. C.

1115555. 1

CONSTRUCTION OF A DATA OF A DATA

A CONTRACTOR

AND A CONTRACT OF A CONTRACT O

AT THE PROPERTY OF

