

AD-A149 303


CHEMICAL AND PHOTOGRAPHIC EVALUATION OF RIGID EXPLOSIVE  
TRANSFER LINES(U) NAVAL SURFACE WEAPONS CENTER SILVER  
SPRING MD E G KAYSER MAY 84 NSWC/TR-84-66


1/1

UNCLASSIFIED

F/G 19/1

NL





MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS 1963-A

12

NSWC TR 84-66

# CHEMICAL AND PHOTOGRAPHIC EVALUATION OF RIGID EXPLOSIVE TRANSFER LINES


BY ELEONORE G. KAYSER

RESEARCH AND TECHNOLOGY DEPARTMENT

MAY 1984

Approved for public release; distribution unlimited.

**S** DTIC  
ELECTE **D**  
JAN 02 1985  
**E**



## NAVAL SURFACE WEAPONS CENTER

Dahlgren, Virginia 22448 • Silver Spring, Maryland 20910

"Original contains color  
plates: All DTIC reproductions  
will be in black and  
white"

84 12 20 013

AD-A149 303

DTIC FILE COPY

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER NSWC TR 84-66	2. GOVT ACCESSION NO. AD-A149303	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) CHEMICAL AND PHOTOGRAPHIC EVALUATION OF RIGID EXPLOSIVE TRANSFER LINES		5. TYPE OF REPORT & PERIOD COVERED Interim 7/1980-5/1984
7. AUTHOR(s) Eleonore G. Kayser		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Naval Surface Weapons Center (Code R16) White Oak Silver Spring, MD 20910		8. CONTRACT OR GRANT NUMBER(s)
11. CONTROLLING OFFICE NAME AND ADDRESS		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE May 1984
		13. NUMBER OF PAGES 53
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release; distribution is unlimited.		15. SECURITY CLASS. (of this report)  UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)		
SMDC	HNS	
DETONATING CORD	DIPAM	
EXPLOSIVE TRANSFER LINE	SHIELDED MILD DETONATING CORD	
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)		
<p>—&gt; This paper describes the chemical and photographic analyses performed on 112 explosive transfer lines used to initiate aircraft emergency escape systems for a variety of military and NASA aircraft. The purpose was to provide quantitative chemical data on in-service explosive transfer lines as affected by both age and heat treatment. These data are necessary in order to make reliable, responsible, and conservative estimations of in-service cord life extension. The approach was to (a) develop a test methodology, (b) characterize the types of transfer lines in use in this country.</p>		

DD FORM 1473

JAN 73

EDITION OF NOV 5: IS OBSOLETE  
S/N 0102-LE-014-9601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

(c) analyze these lines following a repeat of the thermal tests conducted in the original qualification, and (d) conduct a degradation investigation on the explosives currently in use. The results of this testing indicate that rigid explosive transfer lines are not adversely affected by age, service, or a repeat of the thermal qualification tests.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

FOREWORD

This report contains the analytical results generated on HNS and DIPAM removed from explosive transfer lines. The chemical and photographic techniques described in this report are part of a joint service life evaluation program funded by the Army Aviation Systems Command (AVSCOM), St. Louis, Missouri, the U.S. Air Force B-1 Program, and the National Aeronautics and Space Administration (NASA) under NASA Defense Purchase Request No. L-9492B. This program was managed at the NASA Langley Research Center, Hampton, Virginia.

The identification of commercial materials and/or manufacturers implies neither criticism nor endorsement by the Naval Surface Weapons Center.

The author wishes to thank Dr. Marriner K. Norr and the Photographic Department at NSWC-White Oak for their contributions in the form of scanning electron micrographs and the color macrophotographs; Larry J. Bement of the NASA Langley Research Center, Hampton, Virginia, and Morry L. Schimmel of the McDonnell Aircraft Company, St. Louis, Missouri, for their helpful suggestions and comments; and especially Eugene E. Kilmer of the Naval Surface Weapons Center, White Oak, for making it all possible.

Approved by:

*Kurt Mueller*  
 KURT MUELLER, Head  
 Energetic Materials Division

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

"Original contains color plates: All DTIC reproductions will be in black and white"



## CONTENTS

	<u>Page</u>
INTRODUCTION . . . . .	1
EXPERIMENTAL . . . . .	5
TECHNICAL APPROACH . . . . .	5
LINES TESTED . . . . .	6
TESTING SEQUENCE . . . . .	6
EXPLOSIVE MATERIALS . . . . .	6
BOOSTER TIP SAMPLING . . . . .	6
TRANSFER LINE SAMPLING . . . . .	11
HPLC CONDITIONS . . . . .	11
COLOR MACROPHOTOGRAPHY . . . . .	11
SCANNING ELECTRON MICROSCOPY (SEM) . . . . .	11
RESULTS AND DISCUSSION . . . . .	13
CONCLUSIONS . . . . .	37
REFERENCES . . . . .	38
NOMENCLATURE . . . . .	39

## ILLUSTRATIONS

<u>Figure</u>		<u>Page</u>
1	CROSS SECTION OF RIGID EXPLOSIVE TRANSFER LINE (1 GRAIN = 65 mg) . . . . .	3
2	TEMPERATURE/TIME CYCLES (100 EACH) REQUIRED FOR THERMAL QUALIFICATION OF RIGID EXPLOSIVE TRANSFER LINES . . . . .	7
3	CHEMICAL STRUCTURES AND MEETING POINTS OF EXPLOSIVES IN RIGID EXPLOSIVE TRANSFER LINES . . . . .	9
4	DISSECTION SITES USED FOR PHOTOGRAPHIC AND CHEMICAL ANALYSES . . .	10
5	HPLC CHROMATOGRAM OF HNS, HNBIB, AND DIPAM . . . . .	12
6	INTERNAL END VIEW OF A BOOSTER TIP REMOVED FROM A TRANSFER LINE EXPOSED TO 425°F FOR 50 HR. PERCENTAGES ARE EXPLOSIVE REMAINING BY WEIGHT . . . . .	23
7	SIDE VIEW OF FERRULE CHARGE REMOVED FROM A TRANSFER LINE EXPOSED TO 500°F FOR 50 HRS . . . . .	24
8	SIDE VIEW OF FERRULE CHARGE REMOVED FROM A TRANSFER LINE EXPOSED TO 425°F FOR 50 HRS . . . . .	24
9	PHOTOGRAPHIC ANALYSES OF AH-1S BOOSTER TIP EXPLOSIVE . . . . .	25
10	PHOTOGRAPHIC ANALYSES OF AH-1S TRANSFER LINE EXPLOSIVE . . . . .	26
11	COLOR MACROPHOTOGRAPHS OF AH-1G BOOSTER TIP EXPLOSIVE; ALL LINES ARE 9 YEARS OLD . . . . .	27
12	SCANNING ELECTRON MICROGRAPHS OF AH-1G BOOSTER TIP EXPLOSIVE; ALL LINES ARE 9 YEARS OLD . . . . .	28
13	COLOR MACROPHOTOGRAPHS OF AH-1G TRANSFER LINE EXPLOSIVE; ALL LINES ARE 9 YEARS OLD . . . . .	29
14	SCANNING ELECTRON MICROGRAPHS OF AH-1G TRANSFER LINE EXPLOSIVE; ALL LINES ARE 9 YEARS OLD . . . . .	30



## ILLUSTRATIONS (CONT.)

<u>Figure</u>		<u>Page</u>
15	PHOTOGRAPHIC ANALYSES OF F-14 BOOSTER TIP EXPLOSIVE . . . . .	31
16	PHOTOGRAPHIC ANALYSES OF F-14 TRANSFER LINE EXPLOSIVE . . . . .	32
17	PHOTOGRAPHIC ANALYSES OF B-1 BOOSTER TIP EXPLOSIVE . . . . .	33
18	PHOTOGRAPHIC ANALYSES OF B-1 TRANSFER LINE EXPLOSIVE . . . . .	34
19	PHOTOGRAPHIC ANALYSES OF F-111 TRANSFER LINE EXPLOSIVE . . . . .	35
20	PHOTOGRAPHIC ANALYSES OF F-111 BOOSTER TIP EXPLOSIVE . . . . .	36

## TABLES

<u>Table</u>		<u>Page</u>
1	NUMBER OF LINES AND RATED SERVICE LIFE OF VARIOUS AIRCRAFT . . . .	2
2	TYPES OF SMDC LINES CURRENTLY IN USE . . . . .	4
3	EXPLOSIVE TRANSFER LINES TESTED . . . . .	8
4	CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE F-111 AIRCRAFT AFTER 4 YEARS OF SERVICE . . . . .	14
5	CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE AH-1G AIRCRAFT AFTER 7 YEARS OF SERVICE . . . . .	15
6	CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE AH-1S AIRCRAFT AFTER 4.7 YEARS OF SERVICE . . . . .	17
7	CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE F-15 AIRCRAFT AFTER 6 YEARS OF SERVICE . . . . .	18
8	CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE B-1 AIRCRAFT AFTER 3 YEARS OF SERVICE . . . . .	19
9	CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE F-14 AIRCRAFT AFTER 3 YEARS OF SERVICE . . . . .	20
10	EFFECT OF HEAT ON CHEMICAL COMPOSITION . . . . .	21
11	CHEMICAL ANALYSIS OF EXPLOSIVE TRANSFER LINES . . . . .	22

## INTRODUCTION

Extending the service life of explosive transfer lines, used to initiate and sequence aircraft emergency crew escape systems, provides an opportunity for significant savings<sup>1</sup> for a wide variety of military and NASA aircraft (see Table 1). Previous surveillance programs<sup>2</sup> have relied on methods which provided limited information on the functional status of transfer lines having full service, and the projection of further service extension. The purpose of the effort described in this report is to provide quantitative information on explosive transfer lines which will contribute to responsible, conservative, service life determinations.

Rigid explosive transfer lines (Figure 1), commonly called shielded mild detonating cord (SMDC), are designed to transfer a fully contained explosive stimulus, and are the most extensively applied components in aircraft crew escape systems. These lines utilize small quantities of highly stable explosives (i.e., 2,2',4,4',6,6'-hexanitrostilbene (HNS)<sup>3</sup> and dipicramide (DIPAM)<sup>4</sup>) in a metal sheath (i.e., silver or aluminum). SMDC lines are normally used to interconnect the components of emergency escape functions. More than one million cords have been manufactured for various aircraft, spacecraft, and missiles, which include the Army AH-1, the NASA/Army Rotor Systems Research Aircraft (RSRA), the NASA Space Shuttle,<sup>5</sup> the Air Force F-111,<sup>6</sup> F-15, F-16, and B-1, and the Navy TA-7, S-3A, F-14, and F-18. To date, this program has evaluated transfer lines from the following aircraft: the Army AH-1G, and AH-1S, the Air Force F-111, F-15, and B-1, and the Navy F-14. Each of the lines used in these aircraft is different from the others in terms of materials and manufacturing processes and represents all of the rigid transfer line types in use in this country (see Table 2).

The establishment of a rated service life for these lines has been approached on a conservative basis, due to the life-critical function that they perform. A relatively short service life, from three to five years for most aircraft systems, was originally established. Until recently, little interchange of service life technology has occurred among the various aircraft surveillance programs. The chemical and photographic techniques described in this report are part of a joint Army, Air Force, NASA, explosive transfer line service life extension program.<sup>7</sup>

More than 800 rigid explosive transfer lines<sup>7</sup> have been evaluated. Lines were removed after full service from the Army AH-1G and AH-1S, the Air Force F-111, B-1, and F-15 and the Navy F14 aircraft. Seven year-old B-1 lines with no service were also evaluated. These lines represent the three explosive cord types (1) silver-sheathed HNS-II, (2) aluminum-sheathed HNS-II, and (3) silver-sheathed DIPAM currently in use. The three manufacturing methods used to

TABLE 1. NUMBER OF LINES AND RATED SERVICE LIFE OF VARIOUS AIRCRAFT

AIRCRAFT	NO. OF LINES/AIRCRAFT	SERVICE LIFE IN YEARS	
		INITIAL	CURRENT (as of May 84)
AH-1G*	13	5	on condition
AH-1S*	16	5	on condition
B-1 (capsule)	1200	3	13
B-1B	504	3	15
F-111	258	1.5	15
F-14	156	3	5
F-15 (fighter)	22	6	15
F-15 (trainer)	68	6	15
F-16	27	15	15
F-18 (fighter)	13	5	5
F-18 (trainer)	52	5	5
RSRA	145	5	on condition

\*Projected savings of \$9M with extension to 10 years.<sup>1</sup>




FIGURE 1. CROSS SECTION OF RIGID EXPLOSIVE LINE (1 GRAIN = 65 MG)

TABLE 2. TYPES OF SMDC LINES CURRENTLY IN USE

SMDC LINES	AIRCRAFT/SPACECRAFT/MISSILE
HNS-II	
(silver sheathed)	AH-1
" "	EA-6
" "	F-14
" "	F-16
" "	F-18
" "	RSRA
" "	S-3A
" "	Harpoon Missile
" "	Delta Launch Vehicle
HNS-II	
(aluminum sheathed)	B-1
" "	Trident Missile
DIPAM	
(silver sheathed)	F-111
" "	F-15

fabricate these cords are: (1) swage-hammering of fully annealed tubes, (2) swage-hammering of work-hardened tubes using three 425°F/one-hour annealing cycles, and (3) pultrusion (see Nomenclature).

The overall objectives of this program<sup>7</sup> were:

1. to develop a chemical and functional test methodology, and establish standards for comparison to all subsequent samples;
2. to determine chemical and functional reproducibility among line types, manufacturing methods, and batches;
3. to determine effects of age and service on the oldest available lines;
4. to evaluate lines with rated service which have undergone a repeat thermal qualification test;
5. to conduct thermal degradation studies to determine the limits at which line functionality can be maintained; and
6. to establish degradation limits and mechanisms for the energetic materials HNS and DIPAM.

The chemical<sup>5,7,8</sup> and photographic<sup>7</sup> analyses (color macrophotographs and scanning electron microphotographs (SEM's)) were developed and carried out at the Naval Surface Weapons Center-White Oak, while the functional tests (velocity and energy measurements) as well as the nondestructive tests were (helium leak detection and X-ray photography) were developed and performed at the NASA Langley Research Center. The results of all these tests can be found in reference 7.

## EXPERIMENTAL

### TECHNICAL APPROACH

The technical approach included the five following test objectives:

1. Establish chemical standards against which all subsequent test groups would be compared. The most recently manufactured lines with the least service were used to establish this baseline. New lines with no history of service would have provided the best reference standards. However, only new AH-1S aircraft lines were available.
2. Determine the effects of age (shelf life) without service. The only components available for this study were the spares for the B-1 aircraft system qualification with a storage life of 7 to 8 years.
3. Evaluate the effects of rated, installed service time (service life) on lines from each aircraft. The oldest age-with-service group was used for this evaluation with the exception of the AH-1G where the service life demonstration

was omitted. Thermal qualification tests including 72-hour exposure at -110°F to +200°F for the Army AP-1G and AH-1S as well as the thermal parameters detailed in Figure 2 were repeated on full service lines to provide a credible basis for possible service life extension.

4. Define the chemical and physical changes which occur as the transfer lines degrade.

5. Determine to what extent material degradation can cause functional failure. Since no functional failure due to ambient storage and/or service was observed, degradation was induced by exposure to elevated temperatures. Lines subjected to 50-hour exposures at 375°F, 400°F, 425°F, and 450°F were chemically and photographically analyzed. To investigate even broader degradation limits, lines from the F-111 aircraft were exposed to temperatures up to 600°F. Each line was inventoried in terms of aircraft, service, manufacturer, manufacturing lot, manufacturing process, manufacturing date, part number, and serial number.

#### LINES TESTED

Data describing the investigated rigid explosive transfer lines can be found in Table 3.

#### TESTING SEQUENCE

The chemical and photographic analyses were carried out in the following order:

1. Color Macrophotographs
2. SEM
3. HPLC Analyses


#### EXPLOSIVE MATERIALS

The explosives used in the investigated rigid transfer lines include HNS<sup>9,10,11</sup> (Navy Spec. WS-5003<sup>12</sup>) and DIPAM (Navy Spec. WS-4660<sup>13</sup>). HNS-I, the initial product derived in the synthesis is used in the booster tips due to its sensitivity to low initiation inputs (pressure impulse and fragment impacts), while HNS-II (recrystallized HNS-I) is employed in the transfer lines because of its more desirable flow properties. High purity standards of HNS, DIPAM, and HNBiB (major impurity in HNS synthesis) were prepared to provide a reference calibration for the materials removed from the five aircraft types. The chemical structure and thermal properties of these compounds can be found in Figure 3.

#### BOOSTER TIP SAMPLING

The booster tip (Figure 4) was dissected with a tube cutter at the ferrule charge-to-booster charge plane. The cup was cut and broken open to minimize any physical disturbance of the pressed explosive. For the HPLC analyses, HNS was





(A) F-14 AIRCRAFT.

(B) B-1 AIRCRAFT.


(C) F-111 AIRCRAFT.

FIGURE 2. TEMPERATURE/TIME CYCLES (100 EACH) REQUIRED FOR THERMAL QUALIFICATION OF RIGID EXPLOSIVE TRANSFER LINES


TABLE 3. EXPLOSIVE TRANSFER LINES TESTED

AIRCRAFT	EXPLOSIVE CORE	MDC SHEATH	MANUFACTURING PROCESS (MDC)	MANUFACTURER	INITIAL SERVICE (Years)	NO. OF LINES/AIRCRAFT	PYRO CHANGE-OUT TIME (Manhours)
AH-1G	HNS-II	silver	swage/hammer, with annealing	Teledyne McCormick-Selph (TMC/S)	5	13	60
AH-1S	HNS-II	silver	pultrusion	Space Ordnance Systems (SOS)	5	16	60
F-14	HNS-II	silver	swage/hammer, no annealing	Explosive Technology (ET)	3	156	500
B-1 (capsule)	HNS-II	aluminum	swage/hammer, with annealing	Teledyne McCormick-Selph (TMC/S)	3	1200	40,000
F-111	DIPAM	silver	swage/hammer, with annealing	Teledyne McCormick-Selph (TMC/S)	1.5	258	.
F-15	DIPAM	silver	swage/hammer, no annealing	Explosive Technology (ET)	6	22-68	


DIPAM  
 DIPICRAMIDE  
 MOLECULAR WEIGHT = 454



HNS  
 2, 2', 4, 4', 6, 6' - HEXANITROSTILBENE  
 MOLECULAR WEIGHT = 450



HNBiB  
 2, 2', 4, 4', 6, 6' - HEXANITROBIBENZYL,  
 DIPICRYLETHANE  
 MOLECULAR WEIGHT = 452




COMPOUND

DIPAM  
 HNS-I  
 HNS-II  
 HNBiB


MELTING POINT

583<sup>o</sup>F  
 601<sup>o</sup>F  
 604<sup>o</sup>F  
 424<sup>o</sup>F

FIGURE 3. CHEMICAL STRUCTURES AND MELTING POINTS OF EXPLOSIVES  
 IN RIGID EXPLOSIVE TRANSFER LINES



(A) BOOSTER TIP



(B) TRANSFER LINE

FIGURE 4. DISSECTION SITES USED FOR PHOTOGRAPHIC AND CHEMICAL ANALYSES

removed from the cup and the material was mechanically blended. The samples were weighed on a Mettler Microbalance (standard deviation 1.0ugm) and then dissolved in dimethylsulfoxide (DMSO). Two to three HPLC analyses were determined on each booster tip. Additional analyses were obtained whenever changes were observed. The HNS-I booster tip analyses were reproducible to within +3%.

#### TRANSFER LINE SAMPLING

The explosive cord (Figure 4) was cut with a tubing cutter approximately 4cm from each end, and at the midpoint if the cord length was greater than 26cm (10 inches). For the HPLC analyses, a 1 to 2mm cross section was cut from the cord. DMSO was added to the Ag or Al sheathed transfer line samples. This solution was placed in an ultrasonic bath at room temperature for approximately 30 minutes to completely dissolve the explosive. The quantity of explosive was determined by the tare in weighing the original and empty cord length. Two or more transfer lines were tested with a minimum of 3 HPLC analyses on each sample. Additional lines and samples were tested whenever changes were observed.

#### HPLC CONDITIONS

A high performance liquid chromatograph (Waters Associates Model ALC 202) equipped with a 254nm wavelength detector, a solvent delivery system (Model 6000), and a U6K high pressure loop injector was used with a Model RCM-100 module containing a reverse-phase C-18 Radial-Pak cartridge. Sample solutions were eluted isocratically at ambient temperature. Column flow was 2.0ml/minute, with the mobile phase consisting of HPLC grade methanol and distilled water, 50:50(v,v). The solvent mixtures were not degassed prior to HPLC analysis and sample injections of 2 to 20 microliters were used. A typical time plot of the materials<sup>8</sup> used in this study can be found in Figure 5.

#### COLOR MACROPHOTOGRAPHY

Color photographs (15-25X magnification) were taken of cross sections of the booster tips. In order to expose the core, a 2-inch section was opened longitudinally with a Nicholson flat file. The photographs were obtained with a Polaroid camera and a Wild Microscope lens (M-75, type 352873), made in Herrbrugg, Switzerland - Kodak Vericolor II, type L (4X5) film was used for documentation.

#### SCANNING ELECTRON MICROSCOPY (SEM)

The SEM photographs were obtained with an AMRAY, Model 1000A, scanning electron microscope (5000X magnification). The SEM data were processed on a cathode ray tube (7 inch diagonal, 2500 line resolution) and photographed with a Polaroid camera. Sample preparation included vacuum sputter-coating with gold.

ISOCRATIC ELUTION  
DETECTOR WAVELENGTH: 254 NM  
MOBILE PHASE: METHANOL:WATER (50:50, BY VOLUME)  
FLOW RATE: 2.0 ML/MIN  
SCALE: 0.05 ABSORBANCE UNITS FULL SCALE  
SAMPLE SIZE: 5 $\mu$ l  
CHART SPEED: 0.5 CM/MIN  
SAMPLE SOLVENT: DMSO  
R<sub>t</sub>: RETENTION TIME AT MAX. PEAK HEIGHT, MINUTES  
T<sub>0</sub>: TEST START




FIGURE 5. HPLC CHROMATOGRAM OF HNS, HNBIB, AND DIPAM

## RESULTS AND DISCUSSION

To date, a total of 112 transfer lines have been analyzed chemically and photographically. This evaluation revealed physical and chemical changes in both HNS and DIPAM at elevated temperatures (>375°F/50 hours). Material uniformity was shown to exist among (a) various line manufacturers, (b) several manufacturing methods, (c) line types, and (d) material batches. None of the five aircraft line types exhibited any significant change due to (a) shelf life ranging from 1 to 10 years, (b) service life of 3 to 7 years, (c) rated service with a repeat thermal qualification, or (d) thermal exposure up to and including a 375°F/50 hour heat cycle (see Tables 4 through 11) which is well beyond the temperature requirements (Figure 2) for the above mentioned aircraft.<sup>1</sup>

Material degradation was only noted at high thermal inputs. As expected, the HNBiB (mp 424°F) degraded more rapidly than the HNS (mp 602°F). The weight percent of HNBiB found in the HNS-I of the AH-1G, AH-1S, F-111, and F-14 lines was approximately 2%, and 6% for the B-1, while the percentage of HNBiB in the HNS-II ranged from zero to 2.1 percent. DIPAM exhibited no degradation up to and including the 450°F/50 hour heat cycle. The effects of thermal inputs on DIPAM up to and including 550°F can be seen in Table 10. Essentially, total DIPAM decomposition (94.6%) occurred at 500°F.

HNS-II degradation in the aluminum sheathing was less than that observed in the silver sheathing. This could be due to the lower HNS-II loading density of the aluminum cords. The velocity data<sup>7</sup> obtained from the Ag and Al cords corroborates these results. HNS degradation observed at the high temperatures was also accelerated by the presence of HNBiB. The higher the concentration of HNBiB, the greater the degree of degradation.

As heat-induced degradation occurred in the explosive materials, both color and physical texture changed. The booster tip explosive was found to darken progressively from the outer circumference (Figure 6). Removal and analysis of the darkened material revealed considerably more degradation at the explosive/stainless steel interface than could be found in the center material. Heat-induced decomposition of the HNS-I contained in the ferrule can be seen in Figures 7 and 8. The percentage of explosive material remaining after exposure to 500°F for 50 hours is shown in Figure 7. The density variations noted in Figure 8 were caused by pressing the explosive into the conical cavity (ferrule). Increased decomposition was observed where HNS compaction was the highest (lowest density at the left - Figure 8).

Color macrophotographs and scanning electron micrographs provided qualitative corroboration for the chemical analyses by high performance liquid chromatography. The results of these chemical and photographic analyses were also corroborated by actual functional tests as described in reference 7. The color macrophotographs show a darkening of the explosive material with increased thermal inputs (Figures 9-11, 13, 15-20). SEM photographs (Figures 9, 10, 12, 14-20) indicate a gradual roughening of the particles, as degradation increased, leading finally to a perforated "swiss cheese"-like texture.

TABLE 4. CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE F-111 AIRCRAFT AFTER 4 YEARS OF SERVICE

TEST GROUP	TEST PARAMETERS	LINE MANUFACTURER - Tmc/S		ROOSTER TIP		TRANSFER LINE		LOT NO.	SERIAL NO.
		MFG. DATE	WT. % HNS-I	WT. % HNS-I	WT. % HNBiB	WT. % DIPAM	WT. % DIPAM		
PS	as received	1/75	96.7±0.6	3.8±0.2	97.4±1.0	MSV 8555-5	37304895		
PS	as received	1/75	96.3±0.4	3.4±0.0	97.4±0.2	MSV 8555-5	28200253		
PS	as received	1/75	98.2±1.3	3.6±0.1	100.0±2.0	MSV 8555-5	36504503		
PS	as received	6/72	99.7±0.4	1.5±0.1	99.3±0.3	MSV 8553-10	49349468		
SLD	as received	5/72	97.0±0.2	2.1±0.3	101.9±2.0	MSV 8553-5	39339383		
SLD	as received	5/72	98.1±0.3	2.1±0.1	96.4±2.0	MSV 8553-5	39439457		
SLD	as received	6/72	98.1±1.0	2.0±0.2	98.2±1.0	MSV 8553-10	45949091		
SLD	as received	6/72	97.2±0.1	1.9±0.1	96.9±0.1	MSV 8553-10	64349649		
SLD	as received	6/72	98.1±0.0	1.8±0.0	98.0±0.9	MSV 8553-10	64449675		
SLD	as received	6/72	95.1±1.0	3.6±0.2	98.0±0.5	MSV 8553-10	46049150		
RTQ	Figure 2	6/72	98.0±1.5	1.8±0.2	98.3±0.5	MSV 8553-9	09646449		
RTQ	Figure 2	6/72	97.4±1.3	1.7±0.2	98.9±0.1	MSV 8553-9	09646527		
DI	400°F/50 hrs	1/75	93.1±1.1	2.5±0.2	101.1±0.3	MSV 8555-5	49308638		
DI	400°F/50 hrs	1/75	88.9±1.2	2.1±0.1	96.9±1.5	MSV 8555-5	26199420		
DI	425°F/50 hrs	1/75	75.3±0.8	1.4±0.1	100.0±2.3	MSV 8555-5	65702369		
DI	425°F/50 hrs	1/76	82.9±1.3	1.4±0.2	96.6±1.5	MSV 8555-5	65702418		
DI	450°F/50 hrs	1/75	71.9±2.9	0.8±0.0	100.0±3.2	MSV 8555-5	63401029		
DI	450°F/50 hrs	1/75	65.5±1.1	0.8±0.0	100.8±2.2	MSV 8555-6	26414524		
DI	500°F/50 hrs	2/75	8.6±1.5	*	*	MSV 8555-4	P/N 1609		
DI	500°F/50 hrs	11/74	32.7±3.2	8.3±0.0	8.3±0.0	MSV 8555-4	40289904		
DI	500°F/50 hrs	11/74	23.7±3.7	8.1±0.0	8.1±0.0	MSV 8555-3	25988189		
DI	550°F/50 hrs	10/74	*	*	*	MSV 8555-3	25493359		
DI	550°F/50 hrs	10/74	0.3±1.3	<0.1	<0.1	MSV 8555-3	25493359		
DI	550°F/50 hrs	10/74	*	*	*	MSV 8555-3	26288244		
DI	600°F/50 hrs	10/74	0.9±3.7	*	*	MSV 8555-3	24993152		
DI	600°F/50 hrs	10/74	0.4±3.5	*	*	MSV 8555-3	24492992		
DI	600°F/50 hrs	10/74	*	*	*	MSV 8555-3	09692597		

\*Both booster tips were burst by internal pressure, transfer line was empty



TABLE 5. CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE AH-1G AIRCRAFT AFTER 7 YEARS OF SERVICE

TEST GROUP	TEST PARAMETERS	MFG. DATE		BOOSTER TIP		TRANSFER LINE		LOT NO.	SERIAL NO.
		WT. % HNS-I	WT. % HNS-II	WT. % HNS-I	WT. % HNS-II	WT. % HNS-I	WT. % HNS-II		
LINE MANUFACTURER - TMC/S									
TEST PERIOD 2/81 - 5/82									
PS	as received	2/77	93.4±0.1	5.5±0.2	100.0±0.5	0.0	0.0	7967-1	1523
PS	as received	7/72	98.7±0.2	1.7±0.1	95.4±1.5	1.1±0.0	1.1±0.0	7180-9	443
PS	as received	2/77	93.0±0.1	5.2±0.2	94.2±0.2	0.0	0.0	7967-1	1546
RTQ	-110°F/72 hrs	9/72	98.9±0.9	1.3±0.2	96.4±0.5	2.0±0.2	2.0±0.2	7180-13	970
RTQ	-110°F/72 hrs	9/72	94.5±0.0	1.7±0.1	93.9±0.4	1.3±0.0	1.3±0.0	7180-13	983
RTQ	-110°F/72 hrs	7/72	92.3±0.8	1.6±0.3	92.2±0.1	0.0	0.0	7180-9	665
RTQ	-110°F/72 hrs	7/72	93.9±0.3	2.5±0.1	95.6±0.5	0.4±0.2	0.4±0.2	7180-9	650
RTQ	+200°F/72 hrs	4/72	90.2±0.3	5.5±0.5	94.4±0.5	0.0	0.0	7180-2	229
RTQ	+200°F/72 hrs	5/72	93.8±0.7	2.0±0.2	93.9±0.4	0.7±0.2	0.7±0.2	7180-3	252
RTQ	+200°F/72 hrs	7/72	96.0±0.3	1.7±0.2	96.5±0.3	0.9±0.2	0.9±0.2	7180-9	531
RTQ	+200°F/72 hrs	5/72	99.0±0.4	2.0±0.5	94.9±0.3	1.1±0.3	1.1±0.3	7180-3	238
RTQ	+200°F/72 hrs	6/72	96.8±1.0	1.9±0.1	95.6±0.0	1.0±0.0	1.0±0.0	7180-9	330
RTQ	+200°F/72 hrs	6/72	94.6±0.1	1.8±0.1	94.5±0.2	0.9±1.0	0.9±1.0	7180-7	342
DI	375°F/50 hrs	2/77	92.7±0.5	4.2±0.2	96.9±1.5	0.0	0.0	7967-1	1562
DI	375°F/50 hrs	2/77	92.4±1.0	4.1±0.1	97.6±3.3	0.0	0.0	7967-1	1645
DI	400°F/50 hrs	7/72	93.4±0.2	1.8±0.2	51.4±3.7	0.0	0.0	7180-9	531
DI	400°F/50 hrs	5/72	92.2±1.8	2.0±0.0	89.9±2.0	0.0	0.0	7180-3	238
DI	400°F/50 hrs	10/73	90.7±0.5	1.4±0.2	87.8±1.0	0.7±0.3	0.7±0.3	7452-3	1216
DI	400°F/50 hrs	9/72	91.6±0.4	1.6±0.2	71.0±2.0	0.9±0.4	0.9±0.4	7180-13	1051
DI	400°F/50 hrs	8/72	91.4±0.9	2.0±0.2	66.6±5.0	0.0	0.0	7180-12	791
DI	400°F/50 hrs	7/72	91.4±0.9	1.3±0.1	51.7±4.8	0.0	0.0	7180-9	545
DI	425°F/50 hrs	8/72	88.5±2.6	1.1±0.1	11.5±1.4	0.0	0.0	7180-12	800
DI	425°F/50 hrs	8/72	93.1±1.5	1.3±0.1	53.6±0.9	0.0	0.0	7180-11	858
DI	425°F/50 hrs	8/72	88.4±0.8	1.2±0.1	42.1±2.1	0.0	0.0	7180-11	884
DI	425°F/50 hrs	8/72	93.4±2.9	1.1±0.5	6.0±1.2	0.0	0.0	7180-11	716
DI	425°F/50 hrs	8/72	88.3±0.3	0.9±0.0	43.3±0.7	0.0	0.0	7180-11	894
DI	425°F/50 hrs	8/72	93.9±0.7	0.9±0.0	41.4±0.2	0.0	0.0	7180-12	901
DI	425°F/50 hrs	8/72	93.5±1.8	0.9±0.1	0.0	0.0	0.0	7180-12	927
DI	425°F/50 hrs	8/72	93.6±1.9	1.2±0.3	37.9±5.2	0.0	0.0	7180-12	921
DI	425°F/50 hrs	9/72	90.4±0.1	1.0±0.0	44.0±2.9	0.0	0.0	7180-13	894

TABLE 5. (Cont.)

TEST GROUP	TEST PARAMETERS	MFG. DATE	BOOSTER TIP		TRANSFER LINE		LOT NO.	SERIAL NO.
			WT. % HNS-I	WT. % HNBIB	WT. % HNS-II	WT. % HNBIB		
DI	425°F/50 hrs	7/72	91.4±0.9	0.7±0.1	11.1±0.8	0.0	7180-9	549
DI	425°F/50 hrs	9/72	91.3±1.0	1.7±0.2	47.1±1.0	0.0	7180-13	939
DI	425°F/50 hrs	7/72	84.7±2.0	0.7±0.1	0.0	0.0	7180-9	544
DI	425°F/50 hrs	6/72	89.6±0.5	1.3±0.1	2.9±0.4	0.0	7180-7	441
DI	425°F/50 hrs	8/72	90.1±2.0	1.5±0.1	7.0±0.5	0.0	7180-12	904
DI	425°F/50 hrs	7/72	90.5±1.0	1.4±0.2	0.0	0.0	7180-9	576

TABLE 6. CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE AH-1S AIRCRAFT AFTER 4.7 YEARS OF SERVICE

TEST GROUP	TEST PARAMETERS	L. LINE MANUFACTURER - SOS		BOOSTER TIP		TRANSFER LINE		LOT NO.	SERIAL NO.
		MFG. DATE	WT. % HNS-I	WT. % HNBIB	WT. % HNS-II	WT. % HNBIB			
PS	as received	7/77	96.0±1.0	3.6±0.8	97.5±0.5	0.0	SNF5	897	
	as received	7/77	98.0±0.5	2.0±0.2	96.5±0.0	0.0	SNF4	322	
SLD	as received	2/78	96.0±1.5	2.9±0.8	98.5±1.0	0.1±0.0	SNE14	1724	
	as received	2/78	96.4±1.2	3.4±0.4	98.6±1.6	0.2±0.1	SNE14	1684	
RTQ	-110°F/72 hrs	2/78	95.0±0.8	3.2±0.5	99.6±1.5	0.2±0.2	SNE14	1710	
	-110°F/72 hrs	2/78	98.0±1.3	3.4±0.2	98.3±1.0	0.1±0.0	SNE14	1699	
	+200°F/72 hrs	2/78	97.0±1.2	3.4±0.5	96.8±0.8	0.1±0.1	SNE14	1681	
	+200°F/72 hrs	2/78	97.9±0.6	3.4±0.6	96.4±0.9	0.1±0.1	SNE14	1693	
DI	375°F/50 hrs	12/79	96.1±1.0	2.3±0.2	100.5±0.2	0.0	TAE11	4157	
	375°F/50 hrs	12/79	96.4±1.0	1.3±0.1	99.2±1.2	0.0	TAE11	4156	
DI	400°F/50 hrs	7/77	91.7±0.1	3.5±0.2	86.1±2.0	0.5±0.1	SNE4	797	
	400°F/50 hrs	7/77	88.7±0.2	2.6±0.0	89.1±0.7	0.0	SNE4	813	

TABLE 7. CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE  
F-15 AIRCRAFT AFTER 6 YEARS OF SERVICE

LINE MANUFACTURER - ET  
TEST PERIOD 10/82 - 2/83

TEST GROUP	TEST PARAMETERS	MFG. DATE	WT. % HNS-I	BOOSTER TIP WT. % HNBIB	TRANSFER LINE		LOT NO.	SERIAL NO.
					DIPAM			
SLD	6 years of service	4/74	100.0±3.0	0.5±0.0	98.0±2.5		ETI-1-6	0373
SLD	6 years of service	4/74	98.0±2.5	0.5±0.2	97.1±1.0		ETI-1-6	0373
SLD	6 years of service	4/74	97.2±1.0	1.0±0.1	94.5±1.0		ETI-1-6	0373

TABLE 8. CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED  
ON THE B-1 AIRCRAFT AFTER 3 YEARS OF SERVICE

LINE MANUFACTURER - Tmc/s  
TEST PERIOD 5/81 - 4/82

TEST GROUP	TEST PARAMETERS	MFG. DATE	BOOSTER TIP		TRANSFER LINE		LOT NO.	SERIAL NO.
			WT.% HNS-I	WT.% HNBiB	WT.% HNS-II	WT.% HNBiB		
PS	as received	3/77	94.0±0.6	4.9±0.0	97.0±0.5	0.0	7886-21	10434
PS	as received	7/73	92.8±0.2	6.0±0.2	97.9±0.4	0.0	7060-269	43717
SL	as received	6/73	90.8±0.4	6.3±0.3	93.3±0.4	1.5±0.2		74225
SL	as received	4/73	90.4±0.2	6.6±0.4	95.4±0.5	1.2±0.1	7060-213	74201
DI	375°F/50 hrs	3/77	96.4±0.2	4.4±2.0	99.8±0.1	0.0	7886-21	10400
DI	375°F/50 hrs	3/77	92.3±0.1	5.2±0.1	100.2±1.9	0.0	7886-21	10403
DI	400°F/50 hrs	3/77	89.6±0.2	5.0±0.2	93.8±0.3	0.0	7886-21	10577
DI	400°F/50 hrs	3/77	90.1±0.1	5.1±0.2	93.1±1.0	0.0	7886-21	10578
DI	425°F/50 hrs	3/77	85.9±0.6	3.3±0.2	85.4±0.5	0.0	7886-21	10513
DI	425°F/50 hrs	3/77	87.5±0.5	3.2±0.3	91.3±0.1	0.0	7886-21	10512
RTQ	Figure 2	7/73	88.2±2.0	5.8±0.2	94.3±0.0	2.0±0.1	7060-275	82102
RTQ	Figure 2	7/73	89.5±0.5	6.7±0.2	94.0±0.8	2.1±0.2	7060-274	34253
RTQ	Figure 2	4/73	89.3±0.3	5.6±0.2	94.7±0.0	0.7±0.2	7060-216	34190

TABLE 9. CHEMICAL ANALYSES OF RIGID EXPLOSIVE TRANSFER LINES INSTALLED ON THE F-14 AIRCRAFT AFTER 3 YEARS OF SERVICE

LINE MANUFACTURER - ET  
TEST PERIOD 12/81 - 3/83

TEST GROUP	TEST PARAMETERS	MFG. DATE	BOOSTER TIP		TRANSFER LINE		LOT NO.	SERIAL NO.
			WT. % HNS-I	WT. % HNBIB	WT. % HNS-II	WT. % HNBIB		
PS	as received	2/75	97.8±0.1	0.8±0.1	100.0±0.0	0.0	4-ETI-0275	3380-12
PS	as received	2/75	99.4±0.2	0.8±0.1	100.0±0.1	0.0	4-ETI-0275	3380-2
SLD	as received	2/72	95.8±0.1	3.8±1.6	99.8±0.0	0.0	3002-79	43
SLD	as received	2/72	96.6±0.1	3.5±1.2	100.0±0.0	0.0	3002-79	44
RTQ	Figure 2	10/73	95.7±0.6	3.0±0.4	97.7±0.3	0.0	ETI-2-150	3164-28
RTQ	Figure 2	10/73	93.5±0.5	4.1±0.3	98.3±0.1	0.0	ETI-2-150	3164-20
RTQ	Figure 2	10/73	97.5±0.2	3.7±0.1	97.1±0.0	0.0	ETI-2-150	3164-5
DI	375°F/50 hrs	2/75	94.2±0.3	4.0±0.5	97.2±0.0	0.0	ETI-2-213	3380-15
DI	375°F/50 hrs	2/75	94.8±0.2	3.6±0.5	100.0±0.0	0.0	2-ETI-0275	3380-22
DI	375°F/50 hrs	2/75	93.5±0.5	2.6±0.3	100.0±0.00	0.0	3-ETI-0275	3380-18
DI	400°F/50 hrs	3/75	97.7±0.2	0.0	95.5±0.2	0.0	11-ETI-0375	3380-6
DI	400°F/50 hrs	3/75	90.3±0.2	0.0	95.6±0.2	0.0	10-ETI-0375	3380-16
DI	400°F/50 hrs	3/75	95.8±1.2	3.9±0.2	92.6±0.4	0.0	10-ETI-0375	3380-6
DI	425°F/50 hrs	3/75	76.8±2.0	1.1±0.1	53.1±3.0	0.1±0.0	11-ETI-0375	3380-12
DI	425°F/50 hrs	3/75	94.0±0.5	2.2±0.2	66.3±1.3	0.1±0.0	11-ETI-0375	3380-16
DI	425°F/50 hrs	3/75	95.5±0.2	2.7±0.1	70.0±2.0	0.2±0.1	12-ETI-0375	3380-8
DI	425°F/50 hrs	3/75	91.2±0.3	2.1±0.1	65.0±3.0	0.2±0.1	14-ETI-0375	3380-13
DI	425°F/50 hrs	3/75	89.0±1.0	2.3±0.1	47.1±5.0	0.2±0.2	12-ETI-0375	3380-22
DI	425°F/50 hrs	5/75	91.0±0.3	2.1±0.2	70.3±3.0	0.2±0.2	40-ETI-0575	3380-33
DI	425°F/50 hrs	3/75	92.8±0.3	3.0±0.2	78.1±1.0	0.2±0.2	12-ETI-0375	3380-17
DI	425°F/50 hrs	3/75	91.1±0.5	2.1±0.2	95.3±0.3	0.1±0.1	12-ETI-0375	3380-14

TABLE 10. EFFECT OF HEAT ON CHEMICAL COMPOSITION

AIRCRAFT	EXPLOSIVE (SHEATH)	AS RECEIVED	REPEAT THERMAL QUALIFICATION	AVERAGE CHEMICAL RESULTS % EXPLOSIVE BY WEIGHT						
				375°F/ 50 HRS	400°F/ 50 HRS	425°F/ 50 HRS	450°F/ 50 HRS	500°F/ 50 HRS	550°F/ 50 HRS	
AH-1S	HNS-II/ HNBiB (silver)	98.6/0.1	97.8/0.0	99.8/0.0	87.9/0.1					
AH-1G	"	96.5/0.6	94.8/1.0	98.4/0.2	77.0/0.2	23.2/0.0				
F-14	"	100/0.0	97.7/0.9	99.1/0.9	94.6/0.0	68.2/0.2				
B-1	HNS-II/HNBiB (aluminum)	97.5/0.0	94.3/1.6	100/0.0	93.5/0.0	88.4/0.0				
F-111	DIPAM (silver)	98.4	98.6	99.4	98.3	100	5.4			0.1
F-15	"	96.5								
<u>BOOSTER TIPS</u>										
AH-1S	HNS-I/ HNBiB (304 stain- less steel)	96.2/3.2	97.0/3.4	96.3/1.8	91.2/2.9					
AH-1G	"	96.2/3.3	94.8/2.4	95.2/2.7	91.5/2.2	90.7/1.1				
F-14	"	98.6/0.8	93.5/2.9	93.4/3.3	91.0/1.6	90.2/2.2				
B-1	"	93.4/5.5	89.0/6.0	94.4/4.8	88.9/5.1	86.7/3.3				
F-111	"	97.5/2.5	97.7/1.8	91.0/2.3	79.1/1.4	74.8/0.9	22.0/0.0			1.3/0.0
F-15	"	98.4/0.7								

TABLE 11. CHEMICAL ANALYSIS OF EXPLOSIVE TRANSFER LINES

SAMPLE	NO. OF LINES/ UNITS TESTED	NO. OF YEARS IN SERVICE	AVERAGE CHEMICAL ANALYSIS RESULTS*		
			BOOSTER TIP HNS-I/HNBiB	TRANSFER LINE HNS-II/HNBiB	DIPAM
RSRA	3	5.0	97.7/2.7	97.3/0.1	
F-15	3	6.0	98.4/0.7		96.5
F-111	4	4.0	99.0/2.2		99.3
AH-1S	2	4.7	96.2/3.2	98.6/0.1	
AH-1G	1	7.0	98.7/1.7	95.4/1.1	
B-1	1	3.0	94.0/4.9	97.0/9.9	
F-14	2	3.0	96.2/3.7	99.9/0.0	

\*average weight percent





FIGURE 6. INTERNAL END VIEW OF A BOOSTER TIP REMOVED FROM A TRANSFER LINE EXPOSED TO 425° FOR 50 HR. PERCENTAGES ARE EXPLOSIVE REMAINING BY WEIGHT

Copy available to DTIC does not permit fully legible reproduction




FIGURE 7. SIDE VIEW OF FERRULE CHARGE REMOVED FROM A TRANSFER LINE EXPOSED TO 500° F FOR 50 HRS (HNS-I WT % = 0.7-2.6 %)




FIGURE 8. SIDE VIEW OF FERRULE CHARGE REMOVED FROM A TRANSFER LINE EXPOSED TO 425° F FOR 50 HRS


Copy available to DTIC does not permit fully legible reproduction





AV. WT. % HNS+HNBiB = 93.7  
3 YEARS TOTAL AGE,  
+400° F FOR 50 HOURS




SCANNING ELECTRON MICROGRAPHS



AV. WT. % HNS+HNBiB = 98.0  
4.7 YEARS TOTAL SERVICE,  
5.1 YEARS TOTAL AGE




AV. WT. % HNS+HNBiB = 99.8  
NO SERVICE,  
3 YEARS TOTAL AGE



BOOSTER TIP

FIGURE 9. PHOTOGRAPHIC ANALYSES OF AH-1S BOOSTER TIP EXPLOSIVE



AV. WT. % HNS=88.1  
3 YEARS TOTAL AGE,  
+400° F FOR 50 HOURS



SCANNING ELECTRON MICROGRAPHS




AV. WT. % HNS=99.8  
4.7 YEARS TOTAL SERVICE,  
5.1 YEARS TOTAL AGE



AV. WT % HNS= 97.0  
NO SERVICE,  
3 YEARS TOTAL AGE



FIGURE 10. PHOTOGRAPHIC ANALYSES OF AH-1S TRANSFER LINE EXPLOSIVE





AV WT % HNS · HNBiB · 98.6%

S L AND · 375 F FOR 50 HOURS



AV WT % HNS · HNBiB · 98.3

S L AND · 400 F FOR 50 HOURS



AV WT % HNS · HNBiB · 94.3%

S L AND · 425 F FOR 50 HOURS



AV WT % HNS · HNBiB · 91.8





FIGURE 11. COLOR MACROPHOTOGRAPHS OF AH 1G BOOSTER TIP EXPLOSIVE ALL LINES ARE 9 YEARS OLD


Copy available to all... permit fully legible reproduction

S.L. AND DELTA QUALIFICATION  
(+200 F FOR 72 HOURS)




AV. WT. % HNS + HNBIB=95.7%

S.L. AND +425 F FOR 50 HOURS



AV. WT. % HNS + HNBIB=91.8%

5 TO 7 YEAR SERVICE LIFE (S.L.)




AV. WT. % HNS + HNBIB=98.6%

S.L. AND +400 F FOR 50 HOURS



AV. WT. % HNS + HNBIB=94.3%

S.L. AND +375 F FOR 50 HOURS



AV. WT. % HNS + HNBIB=98.3%




FIGURE 12. SCANNING ELECTRON MICROGRAPHS OF AH-1G BOOSTER TIP EXPLOSIVE: ALL LINES ARE 9 YEARS OLD

S.L. AND DELTA QUALIFICATION  
(+200 F FOR 72 HOURS)



AV. WT. % HNS + HNBiB = 94.5%

S.L. AND +425 F FOR 50 HOURS



AV. WT. % HNS + HNBiB = 21.7%

5 TO 7 YEAR SERVICE LIFE (S.L.)




AV. WT. % HNS + HNBiB = 97.1%

S.L. AND +400 F FOR 50 HOURS



AV. WT. % HNS + HNBiB = 82.2%

S.L. AND +375 F FOR 50 HOURS



AV. WT. % HNS + HNBiB = 98.0





FIGURE 13. COLOR MACROPHOTOGRAPHS OF AH 1G TRANSFER LINE EXPLOSIVE. ALL LINES ARE 9 YEARS OLD


S.L. AND DELTA QUALIFICATION  
(+200 F FOR 72 HOURS)




5 TO 7 YEAR SERVICE LIFE (S.L.)



S.L. AND +425° F FOR 50 HOURS



S.L. AND +400° F FOR 50 HOURS



S.L. AND +375° F FOR 50 HOURS





FIGURE 14. SCANNING ELECTRON MICROGRAPHS OF AH-1G TRANSFER LINE EXPLOSIVE: ALL LINES ARE 9 YEARS OLD



COLOR MACROPHOTOGRAPHS




SCANNING ELECTRON MICROPHOTOGRAPHS



AV. WT. HNS + HNBIB - 98.6%  
3 YEARS SERVICE AND  
6.5 YEARS TOTAL AGE

AV. WT. % HNS + HNBIB = 99.6%  
3 YEARS SERVICE AND  
9 YEARS TOTAL AGE



AV. WT. % HNS + HNBIB = 92.4%  
3 YEARS SERVICE,  
6.5 YEARS TOTAL AGE,  
+425 F FOR 50 HOURS




BOOSTER TIP

FIGURE 15. PHOTOGRAPHIC ANALYSES OF F-14 BOOSTER TIP EXPLOSIVE

COLOR MACROPHOTOGRAPHS



SCANNING ELECTRON MICROGRAPHS



NSWC TR 84-66

AV. WT. % HNS = 100%  
3 YEARS SERVICE AND  
6.5 YEARS TOTAL AGE



AV. WT. % HNS = 99.9%  
3 YEARS SERVICE AND  
9 YEARS TOTAL AGE

AV. WT. % HNS + HNBIB = 56.3%  
3 YEARS SERVICE,  
6.5 YEARS TOTAL AGE,  
+425 F FOR 50 HOURS




FIGURE 16. PHOTOGRAPHIC ANALYSES OF F-14 TRANSFER LINE EXPLOSIVE

COLOR MACROPHOTOGRAPHS




SCANNING ELECTRON MICROPHOTOGRAPHS



WT. % HNS + HNBIB = 98.9%  
3 YEARS SERVICE AND  
3.5 YEARS TOTAL AGE

AV. WT. % HNS + HNBIB = 97.1%  
NO SERVICE AND  
7 YEARS TOTAL AGE



AV. WT. % HNS = 89.9%  
3 YEARS SERVICE,  
3.5 YEARS TOTAL AGE,  
+425° F FOR 50 HOURS





BOOSTER TIP

FIGURE 17. PHOTOGRAPHIC ANALYSES OF B-1 BOOSTER TIP EXPLOSIVE

COLOR MACROPHOTOGRAPHS



SCANNING ELECTRON MICROGRAPHS



AV. WT. % HNS + HNBiB = 97.0%  
3 YEARS SERVICE AND  
3.5 YEARS TOTAL AGE

AV. WT. % HNS + HNBiB = 95.7%  
NO SERVICE AND  
7 YEARS TOTAL AGE

AV. WT. % HNS = 88.35%  
3 YEARS SERVICE,  
3.5 YEARS TOTAL AGE,  
+425 °F FOR 50 HOURS








FIGURE 18. PHOTOGRAPHIC ANALYSES OF 3:1 TRANSFER LINE EXPLOSIVE

COLOR MACROPHOTOGRAPHS



SCANNING ELECTRON MICROPHOTOGRAPHS



AV. WT. % DIPAM 100.9%  
4 YEARS SERVICE AND  
5.5 YEARS TOTAL AGE


AV. WT. % DIPAM 97.4%  
4 YEARS SERVICE AND  
8.5 YEARS TOTAL AGE

AV. WT. % DIPAM 100.3%  
4 YEARS SERVICE,  
5.5 YEARS TOTAL AGE,  
+450 F FOR 50 HOURS





FIGURE 19. PHOTOGRAPHIC ANALYSES OF F-111 TRANSFER LINE EXPLOSIVE

COLOR MACROPHOTOGRAPHS




SCANNING MICROPHOTOGRAPHS



WT. % HNS + HNBiB = 99.1%  
4 YEARS SERVICE AND  
5.5 YEARS TOTAL AGE

WT. % HNS + HNBiB = 99.7%  
4 YEARS SERVICE AND  
8.5 YEARS TOTAL AGE

AV. WT. % HNS + HNBiB = 78.4%  
4 YEARS SERVICE,  
5.5 YEARS TOTAL AGE,  
+450° F FOR 50 HOURS



BOOSTER TIP

FIGURE 20. PHOTOGRAPHIC ANALYSES OF F.111 BOOSTER TIP EXPLOSIVE

## CONCLUSIONS

The effects of service, age, and thermal degradation were determined on transfer lines (used to initiate emergency escape systems) removed from the Army AH-1G and AH-1S, the Air Force B-1 and F-111, and the Navy F-14 aircraft. The results of this study indicate that the HNS and DIPAM explosive lines were not adversely affected by age (ambient storage from 1 to 10 years), service life (from 3 to 7 years) or a repeat thermal qualification cycle. These findings suggest that significant savings in the cost of (a) HNS and DIPAM rigid explosive transfer lines, (b) manhours needed for pyro change-out time, and (c) aircraft down-time can be realized for military and NASA aircraft by extending the service life of rigid explosive transfer lines. These data, when added to functional and nondestructive test results can be used to make responsible, conservative judgments concerning cord life extension.

## REFERENCES

1. Boen, J. M., and Bement, L. J., Astronautics and Aeronautics, 21, No. 4, p. 76, 1983.
2. Carr, B. M., Service Life Evaluation Program (SLEP) for F-14A Aircraft Canopy Jettisoning and Ejection Seat Ballistic Sequencing System Explosive Actuated Devices, Indian Head Technical Report 755, Aug 1982.
3. Shipp, K. G. and Kaplan, L. A., J. Org. Chem., Vol. 31, 1966, p. 857.
4. Dacons, J. C., Adolph, H. G., and Komet, M. J., Heat Resistant Explosives, XIII. Preparation and Properties of 3,3'-Diamino-2,2',4,4',6,6'-hexanitrobiphenyl, DIPAM, NOLTR 62-82, May 1962.
5. Kilmer, E. E., Hexanitrostilbene (HNS): Review of Chemical Assays and Detonation Cord Performance, II, NSWC TR 80-13, Oct 1980.
6. Kilmer, E. E., Overviews of HNS Production/Properties/Applications, NSWC TR 79-181, Jul 1979.
7. Bement, L. J., Kayser, E. G., and Schimmel, M. L., "Service Life Evaluation of Rigid Explosive Transfer Lines," NASA Technical Paper No. 2143, Aug 1983.
8. Kayser, E. G., Analysis Method for Explosive Materials - I. Polynitro Compounds, NSWC TR 81-123, 3 Mar 1982.
9. Kilmer, E. E., Hexanitrostilbene (HNS): Review of Industrial Syntheses and Recrystallizations, NSWC TR 79-497, Mar 1980.
10. Kayser, E. G., Analysis of 2,2',4,4',6,6'-Hexanitrostilbene (HNS) by High Performance Liquid Chromatography, NSWC/WOL TR 77-154, 14 Mar 1978.
11. Kayser, E. G., An Investigation of the Shipp Hexanitrostilbene (HNS) Process, NSWC TR 80-111, 25 Aug 1980.
12. Material Specification for HNS Explosive, WS 5003 J, Surface Weapons Center, U.S. Navy, 18 Feb, 1981.
13. Purchase Description DIPAM Explosive, WS 4660 C, Surface Weapons Center, U.S. Navy, 22 May 1968.



## NOMENCLATURE

Al	Aluminum
Ag	Silver
BT	Booster tip
DI	Degradation investigation
DIPAM	Dipicramide
DMSO	Dimethylsulfoxide
ET	Explosive Technology
HNBiB	2,2',4,4',6,6'-hexanitrobibenzyl
HNS	2,2',4,4',6,6'-hexanitrostilbene
HPLC	High performance liquid chromatography
MDC	Mild detonating cord
on condition	SMDC lines remain in an aircraft and their condition verified by periodic sampling using the chemical, photographic, and functional tests established in this program <sup>7</sup>
PS	Performance standard, newest available
Pultrusion	Process in which a tube containing explosive is pulled through various fixed dies that reduce the tube diameter to the required dimensions
Pyro change-out	Removal and replacement of explosive components from aircraft
RSRA	NASA/Army rotor systems research aircraft
RTQ	Repeat thermal qualification
SEM	Scanning electron microphotograph
SL	Shelf life
SLD	Service life demonstration
SMDC	Shielded mild detonating cord
SOS	Space Ordnance Systems
Swage/Hammer with annealing	Process in which an explosive is press-loaded into a work-hardened tube. The tube is then moved through segmented dies and rapidly hammered to reduce the cross section. The die diameters are decreased during multiple passes until the desired explosive core load (grains/foot) are achieved. Three 218°C (425°F)-one hour heat cycles are used to anneal the work hardened tube during the process.

NOMENCLATURE (Cont.)

Swage/Hammer  
without annealing

Process in which fully annealed tubes are moved  
through segmented dies until the desired core  
loads are achieved.

TMc/S

Teledyne McCormick Selph

## DISTRIBUTION

	<u>Copies</u>		<u>Copies</u>
Commanding Officer Naval Weapons Support Center Crane, IN 47522	1	Commanding Officer Naval Weapons Station Attn: Technical Library NEDED	1 1 1
Commander Naval Air Systems Command Attn: AIR-1116 Washington, DC 20361	1	L. Carlton Yorktown, VA 23690	1
Commander Naval Sea Systems Command Attn: SEA-62A SEA-64E (R. Beauregard) SEA-09G32 (Technical Library)	1 1 1	Director Air & Ordnance Prog, OASN Office of Assistant Sec. of Navy (Shipbuilding & Logistics) Attn: Frank Swafford Navy Department Washington, DC 20360	1 1
Washington, DC 20362	1	Commanding Officer Naval Academy Attn: Hd Weps Dept Annapolis, MD 21402	1
Office of Naval Research Attn: ONR-175 (Technical Library) ONR-473 (R. Miller)	1 1	Superintendent Naval Postgraduate School Monterey, CA 93940	1
801 N. Quincy Street Arlington, VA 22217	1	Director Strategic Systems Projects Office Attn: M. Baron (SSPO-2731) Department of the Navy Washington, DC 20376	1
Chief of Naval Operations Washington, DC 20360	1	Commanding Officer Ballistics Research Laboratory Attn: Technical Library Aberdeen Proving Ground Aberdeen, MD 21005	1
Commander Naval Weapons Center Attn: Technical Library China Lake, CA 93555	1	Commanding Officer U.S. Armament Research & Development Command Attn: Explosives Division SARPA-FR-E-C/BLDG 407 W. Fisco Dover, NJ 07801	1 1 1
Commanding Officer Naval Ordnance Station Attn: W. Carr D. Taylor (Code 51) D. Chappell D. Carillo (51223A) Indian Head, MD 20640	1 1 1 1		

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Commanding General Army Material Command Department of the Army Washington, DC 20316	1	AFLC/MMWRME Attn: D. Burton Hill AFB Provo, UT 84056	1
Commander Army Rocket and Missile Agency Redstone Arsenal Huntsville, AL 35809	1	Director Defense Technical Information Center Cameron Station Alexandria, VA 22314	12
U.S. Army Aviation System Command (AVSCOM) Attn: J. Boen (DRDAV-EED)	10	Library of Congress Attn: Gift and Exchange Division	4
M. L. Baucio (DRDAV-NS)	1	Washington, DC 20540	
MAJGEN O. E. Gonzales	1	Lyndon B. Johnson Space Center National Aeronautics & Space Administration	
4300 Goodfellow Blvd. St. Louis, MO 63120		Attn: Technical Library T. Graves (EP4)	1 1
Headquarters US Army DARCOM Attn: James Laster (DRCSA-JS)	1	2101 Webster-Seabrook Road Houston, TX 77058	
5001 Eisenhower Ave. Alexandria, VA 22333		George C. Marshall Space Flight Center National Aeronautics & Space Administration	
Commander Systems Engineering Group Attn: RTD	1	Attn: Technical Library Robert White (EP-14)	1 1
Wright-Patterson Air Force Base, OH 45433		Huntsville, AL 35812	
Chief of Staff U.S. Air Force Attn: AFORD-AR	1	University of California Lawrence Livermore National Laboratory	
Washington, DC 20350		Attn: Milton Finger Walter Selig	1 1
Air Force Inspection and Safety Center Attn: R. C. Delgado	1	P.O. Box 808 Livermore, CA 94550	
Norton AFB, CA 92409		Chemtronics Division of Airtronics Attn: Technical Library	1 1 1
AFWAL/FIER Attn: MAJ W. Miller (ASD/B-1)	1	H. Hudson	1
P. Mullen (AELE)	1	F. Hudson	1
R. C. Brashears (Code ASD/ ENECC)	1	Old Bee Tree Road Swannanoa, NC 28778	
H. Peot (ASD/B-1)	1		
B. J. White	1		
Wright Patterson AFB, OH 45433			

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Ensign Bickford Company Attn: B. Boggs 660 Hopmeadow Street Simsbury, CT 06070	1	Mason & Hanger-Silas Mason Company, Inc. Pantex Plant Attn: Dr. Clyde Alley Ted Stull P.O. Box 30020 Amarillo, TX 79177	1 1
General Dynamics Attn: W. Early (Code 2813) K. Monroe P.O. Box 748 Fort Worth, TX 76101	1 1	McDonnell Douglas Astronautics Company Attn: H. W. Fairchild 5301 Bolsa Avenue Huntington Beach, CA 92647	1
Grumman Aerospace Corporation Attn: Library R. Gerard/B15 South Oyster Bay Road Bethpage, NY 11714	1 1	Explosive Technology Attn: F. Burkdoll D. Moore P. Posson P.O. Box KK Fairfield, CA 94533	1 1 1
Teledyne McCormick Selph Attn: Library P.O. Box 6 Hollister, CA 95023	1	McDonnell Douglas Corporation Attn: M. Schimmel (D-353 B-32) Post 315 R. M. Chinnery (D-353 B-34) E. R. Lake (D-353, B-32) P.O. Box 516 St. Louis, MO 62166	20 1 1
Lockheed Missiles & Space Corporation, Inc. Attn: I. B. Gluckman F. Chapman (B3-20, B15) P.O. Box 504 Sunnyvale, CA 94086	1 1	Douglas Aircraft Company Attn: R. G. McIntyre (Dept. C1-E76) 3855 Lakewood Blvd. Long Beach, CA 90846	1
Los Alamos National Laboratory Attn: Dr. L. Smith Harry Flaugh P.O. Box 1663 Los Alamos, NM 87544	1 1	Rocketdyne Chemical Corp. Attn: J. Trom Dept. 529-165 Mail Code AB37 6633 Canoga Ave. Canoga Park, CA 91304	1
Sandia Corporation Attn: Dr. N. Brown P.O. Box 5400 Albuquerque, NM 87115	1	Scot Inc. Attn: S. Levin 2525 Curtiss St. Downers Grove, IL 60515	1
Space Ordnance Systems, Inc. Attn: Dr. N. Zable 375 Santa Trinita Sunnyvale, CA 94006	1	Martin Marietta Attn: N. Butterfield P.O. Box 179 Denver, CO 80201	1
Langley Research Center National Aeronautics & Space Administration Attn: L. Bement Hampton, VA 23665	20		

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Irv Kabik 11412 Fair Oaks Drive Silver Spring, MD 20902	1	Space Ordnance Systems Attn: R. Ritche 25977 Sand Canyon Road Saugus, CA 91351	1
Jet Propulsion Laboratory Attn: W. Gin 125-124 4800 Oak Grove Drive Pasadena, CA 91103	1	Rockwell International Attn: L. Corvin (MA2) Los Angeles, CA 90009	1
Franklin Institute Attn: C. Davey Benjamin Franklin Parkway Philadelphia, PA 19103	1	Internal Distribution: R11 (H. Adolph) R11 (M. Kamlet) R11 (J. Holden) R11 (C. Gotzmer) R11 (V. Ringbloom) R11 (J. Leahy) R11 (K. Mueller) R12 (E. Kilmer) R16 (L. Lee) R16 (D. Glover) R16 (J. Hoffsommer)	1 1 1 1 1 1 1 1 1 1 1
Hi Shear Corp. Attn: H. Karp 2600 Skyparks Drive Torrance, CA 90509	1	R16 (R. Renner) R16 (E. Kayser) R16 (S. Deiter) R16 (H. Haiss) R34 (M. Norr) E431 E432	1 1 20 1 2 9 3
Aerospace Corp. Attn: W. J. Fitzgerald El Segundo, CA 90245	1		

**END**

**FILMED**

2-85

**DTIC**