

AD-A149 477

AN INFRARED STUDY OF THE HYDROGENATION OF CARBON  
DIOXIDE ON SUPPORTED RHODIUM CATALYSTS(U) AUBURN UNIV  
AL DEPT OF CHEMISTRY M A HENDERSON ET AL. 07 JAN 85

1/1


UNCLASSIFIED

TR-4 N00014-83-K-0637

F/G 7/4

NL

											END		
											FORMED		
											etc.		



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

UNCLASSIFIED  
SECURITY

AD-A149 477

(11)

DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION Unclassified		1b. RESTRICTIVE MARKINGS	
2a. SECURITY CLASSIFICATION AUTHORITY		3. DISTRIBUTION/AVAILABILITY OF REPORT Unlimited	
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE			
4. PERFORMING ORGANIZATION REPORT NUMBER(S) 4		5. MONITORING ORGANIZATION REPORT NUMBER(S)	
6a. NAME OF PERFORMING ORGANIZATION Auburn University	6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION Office of Naval Research-Code 413	
6c. ADDRESS (City, State and ZIP Code) Department of Chemistry (Dr. S. D. Worley) Auburn University Auburn University, AL 36849		7b. ADDRESS (City, State and ZIP Code) 800 North Quincy St. Arlington, VA 22217	
8a. NAME OF FUNDING/SPONSORING ORGANIZATION ONR	8b. OFFICE SYMBOL (If applicable) Code 413	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-83-K-0637	
8c. ADDRESS (City, State and ZIP Code) See 7b		10. SOURCE OF FUNDING NOS.	
		PROGRAM ELEMENT NO.	PROJECT NO.
		TASK NO.	WORK UNIT NO.
11. TITLE (Include Security Classification) An Infrared Study of the Hydrogenation of Carbon Dioxide on Supported Rhodium Catalysts		NR 634-844	
12. PERSONAL AUTHOR(S) M. A. Henderson and S. D. Worley			
13a. TYPE OF REPORT Technical	13b. TIME COVERED FROM _____ TO _____	14. DATE OF REPORT (Yr., Mo., Day) 85 Jan.7	15. PAGE COUNT 33
16. SUPPLEMENTARY NOTATION Accepted for publication by J. Phys. Chem.			
17. COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB. GR.	
		Infrared Spectroscopy, Carbon Dioxide, Hydrogenation, Methanation, Supported Rhodium Catalysts.	
19. ABSTRACT (Continue on reverse if necessary and identify by block number)			
An infrared study of the methanation of CO <sub>2</sub> on supported Rh catalysts has been performed. This reaction has been shown to occur over these catalysts with higher turnover frequency at a given temperature and Rh loading than does the methanation of CO. A support effect has been demonstrated for the reaction over the supported Rh catalysts (TiO <sub>2</sub> > Al <sub>2</sub> O <sub>3</sub> > SiO <sub>2</sub> in reactivity). A key surface intermediate during the methanation reaction is a carbonyl hydride species, as evidenced by a prominent infrared band in the 2020-2040/cm region which shifts by 5-10 cm <sup>-1</sup> when D <sub>2</sub> is substituted for H <sub>2</sub> in the reaction mixture. This carbonyl hydride species can be produced in the absence of H <sub>2</sub> by migration of H from the support to Rh. The dissociation of CO <sub>2</sub> on supported Rh has been shown to be enhanced by the presence of H <sub>2</sub> and impurity boron.			
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS <input type="checkbox"/>		21. ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a. NAME OF RESPONSIBLE INDIVIDUAL S. D. Worley		22b. TELEPHONE NUMBER (Include Area Code) 205-826-4043	22c. OFFICE SYMBOL A

DTIC FILE COPY

DTIC ELECTED  
JAN 17 1985

OFFICE OF NAVAL RESEARCH  
CONTRACT N00014-83-K-0637

Task No. NR 634-844

TECHNICAL REPORT NO. 4

An Infrared Study of the Hydrogenation of  
Carbon Dioxide on Supported Rhodium Catalysts

by

M. A. Henderson and S.D. Worley  
Department of Chemistry  
Auburn University  
Auburn University, AL 36849

Prepared for Publication

in

J. Phys. Chem.



September 11, 1984

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
AI	

Reproduction in whole or in part is permitted for any purpose of the United States Government.

This document has been approved for public release and sale; its distribution is unlimited.

An Infrared Study of the Hydrogenation of Carbon Dioxide on Supported  
Rhodium Catalysts

M.A. Henderson and S.D. Worley\*

Department of Chemistry, Auburn University, Auburn University, AL 36849

ABSTRACT

An infrared study of the methanation of CO<sub>2</sub> on supported Rh catalysts has been performed. This reaction has been shown to occur over these catalysts with higher turnover frequency at a given temperature and Rh loading than does the methanation of CO. A support effect has been demonstrated for the reaction over the supported Rh catalysts (TiO<sub>2</sub> > Al<sub>2</sub>O<sub>3</sub> > SiO<sub>2</sub> in reactivity). A key surface intermediate during the methanation reaction is a carbonyl hydride species, as evidenced by a prominent infrared band in the 2020-2040 cm<sup>-1</sup> region which shifts by 5-10 cm<sup>-1</sup> when D<sub>2</sub> is substituted for H<sub>2</sub> in the reaction mixture. This carbonyl hydride species can be produced in the absence of H<sub>2</sub> by migration of H from the support to Rh. The dissociation of CO<sub>2</sub> on supported Rh has been shown to be enhanced by the presence of H<sub>2</sub> and impurity boron.

\*Author to whom correspondence should be addressed.

## I. Introduction

Although there has been a tremendous amount of research interest in recent years in catalytic methanation, most of this interest has been focused upon the hydrogenation of CO over various noble metal catalysts. The hydrogenation of CO<sub>2</sub> over these catalysts is at least of equal importance as a reaction relevant to international energy needs; however, there have been considerably fewer detailed studies of this reaction. Such recent studies have included CO<sub>2</sub> hydrogenation over Ni(100)<sup>1</sup>, supported Ni<sup>2-7</sup>, supported Pd<sup>8,9</sup>, supported Pt and Ir<sup>8</sup>, supported Ru<sup>7,8,10-13</sup>, polycrystalline Rh<sup>14,15</sup>, and supported Rh<sup>8,10,16-22</sup>. From prior work on CO<sub>2</sub> hydrogenation several generalizations can be made concerning the reaction.<sup>1-22</sup>

- (1) CO<sub>2</sub> hydrogenation is much more selective toward product formation than is CO hydrogenation, with CH<sub>4</sub> generally being the only hydrocarbon product for the former.
- (2) The activation energy for CO<sub>2</sub> hydrogenation is generally lower than that for CO hydrogenation under analogous conditions.
- (3) The apparent rate of CH<sub>4</sub> formation from CO<sub>2</sub> hydrogenation is generally higher than that from CO hydrogenation under analogous conditions, with CH<sub>4</sub> generally being formed at lower temperatures for the CO<sub>2</sub> reaction.
- (4) CO<sub>2</sub> hydrogenation is effectively poisoned by the presence of small amounts of gas-phase CO.

- (5) CO<sub>2</sub> hydrogenation is generally thought to proceed via dissociation to some form of adsorbed CO and then along the same reaction pathway as that of CO hydrogenation.

In this paper we shall report on recent infrared studies of the hydrogenation of CO<sub>2</sub> over supported Rh catalysts with emphases on a carbonyl hydride intermediate and the dissociation of CO<sub>2</sub> over the catalysts under varying reaction conditions.

## II. Experimental

Supported Rh catalyst films were prepared by procedures used here previously for infrared studies of CO adsorbed on supported Rh<sup>23-25</sup> and the hydrogenation of CO over supported Rh.<sup>26</sup> Briefly, sufficient RhCl<sub>3</sub>·H<sub>2</sub>O (Alfa products, Inc.) was dissolved in one part triply distilled water and added to nine parts spectroscopic-grade acetone containing support material to produce catalysts having final weight percentages of Rh of either 0.5 or 10%. The support materials used were alumina (Degussa Aluminum Oxide C, 100 m<sup>2</sup>g<sup>-1</sup>), titania (Degussa Titanium Oxide P25, 50 m<sup>2</sup>g<sup>-1</sup>), and silica (Cabot Cab-0-sil M-5, 200 m<sup>2</sup>g<sup>-1</sup>). The slurry mixture of RhCl<sub>3</sub>·3H<sub>2</sub>O, support, water, and acetone was carefully sprayed using a specially designed atomizer onto a 25 mm CaF<sub>2</sub> infrared window held at a temperature of ca. 360 K. The solvents rapidly vaporized leaving thin films of RhCl<sub>3</sub>·3H<sub>2</sub>O/support adhered tightly to the window typically at ca. 4 mg cm<sup>-2</sup>. The window containing the catalyst was then mounted in a specially designed Pyrex infrared cell (Figure 1), and the cell was evacuated at 298 K over night. The sample was heated under vacuum (2x10<sup>-6</sup> Torr using an ion pump) for 1 hr at 460 K and generally subjected to hydrogen reduction

cycles at 470 K. The reduction cycles consisted of exposure to successive doses of H<sub>2</sub> or D<sub>2</sub> at 70 Torr for 5, 5, 10, and 20 min, with each cycle being followed by evacuation to at least 10<sup>-5</sup> Torr. The reduced samples were then heated at 460 K under vacuum for an additional 30 min and evacuated to a base pressure of 1x10<sup>-6</sup> Torr.

For a typical kinetics experiment the infrared cell was dosed with 66 Torr of a 1:4 mixture of CO<sub>2</sub>:H<sub>2</sub> and rapidly heated to a prescribed temperature. The cell temperature was monitored by means of the measured voltage across the heating coils; calibration under reaction conditions was checked frequently with a chromel-alumel thermocouple. The production of methane during the reaction and the formation of surface intermediates were followed by infrared spectroscopy. The spectrometer (Perkin-Elmer model 983 with Perkin-Elmer data station) was operated at a resolution of 4.5 cm<sup>-1</sup> in the 2000 cm<sup>-1</sup> region. The infrared beam was blocked from the sample except during a data scan to minimize the additional heating effect of the beam on the sample. The yield of CH<sub>4</sub> produced at any given time in the reaction was determined by means of a calibration curve based upon the integrated intensities of the 3014 and/or 1304 cm<sup>-1</sup> infrared bands for methane as a function of partial pressure of CH<sub>4</sub>. The calibration curve was developed for each sample by evacuation of the cell at the end of the experiment followed by the introduction of CH<sub>4</sub> at known pressures in the presence of the supported Rh catalyst (MKS Baratron capacitance manometer) and associated infrared scans; an example of such a curve is shown in Figure 2.

For experiments involving isotopic labeling, dissociation of CO<sub>2</sub>, introduction of impurity boron, etc., the procedures differed slightly from



the kinetics experiments and will be discussed later in the text. All gases employed in these experiments ( $H_2$ ,  $D_2$ ,  $CO_2$ , and  $CH_4$ ) were of the highest purity obtainable from Matheson; all except  $CO_2$  were passed through liquid nitrogen traps before use.

### III. Results

Typical infrared spectra corresponding to the hydrogenation of  $CO_2$  over 10% Rh/X (X= $TiO_2$ ,  $Al_2O_3$ ,  $SiO_2$ ) and 0.5% Rh/X (X= $TiO_2$ ,  $Al_2O_3$ ) are shown in Figures 3-7. The bands of greatest interest in all of the spectra are those in the 2020-2040  $cm^{-1}$  region which must be assigned to some form of an adsorbed CO species in that they are not removed by evacuation of the cell and the sharp bands at 1304 and 3014  $cm^{-1}$  removed by evacuation of the cell which represent the accumulation of gas-phase  $CH_4$ . The CO band generally occurred at lower frequency for Rh/ $Al_2O_3$  and Rh/ $SiO_2$  than for Rh/ $TiO_2$ . The broad band of low intensity in Fig. 3c is representative of a bridged carbonyl species.<sup>23-27</sup> The extensive band structure in the 1600  $cm^{-1}$  region of spectra 3b,c corresponds to the presence of gas-phase  $H_2O$ , while the broader bands near 1600  $cm^{-1}$  which occur at 298 K (spectrum 3a) are indicative of a hydrated support and possibly also to the presence of carbonates and bicarbonates on the support. The bands in the 1400-2000  $cm^{-1}$  region of spectrum 5a for 10% Rh/ $SiO_2$  are present also for a film containing only  $SiO_2$ . It should be noted that none of the support materials as films catalyzed the production of measurable amounts of  $CH_4$  under the reaction conditions employed in the experiments unless Rh was present. Blank support samples gave only bands characteristic of hydration, carbonates, and bicarbonates; no bands attributable to adsorbed

CO species were ever present.

The infrared spectra of 0.5% Rh/TiO<sub>2</sub> and 0.5% Rh/Al<sub>2</sub>O<sub>3</sub> (Figures 6 and 7) are somewhat different than those for their 10% analogs. The ambient temperature spectra (6a and 7a) show more band structure indicative of hydration, carbonates, and bicarbonates in the 1400-1700 cm<sup>-1</sup> regions than do those in 3a, 4a, and 5a. Furthermore, upon heating the 0.5% Rh/Al<sub>2</sub>O<sub>3</sub> catalyst, bands near 1375 and 1586 cm<sup>-1</sup> characteristic of a formate species<sup>10,17,18,21,22</sup> grew in; these bands were not evident under similar conditions for the 10% catalysts or the blank supports. Also, for the 0.5% supported Rh catalysts the band in the 2020-2040 cm<sup>-1</sup> region is broader and weaker than the corresponding band for the 10% catalysts.

From reproducible infrared spectra for the various supported catalyst films, turnover frequencies (molecules CH<sub>4</sub>/Rh atom/sec) were determined at several temperatures in the range 423-503 K. Comparisons of these turnover frequencies at 483 K for six samples for the hydrogenation of CO<sup>26</sup> and CO<sub>2</sub> are shown in Table I. Table I also shows the CO stretching frequencies for the adsorbed CO species for the various catalyst films. Typical Arrhenius plots using the turnover frequencies for 0.5% Rh/TiO<sub>2</sub> and 0.5% Rh/Al<sub>2</sub>O<sub>3</sub> are shown in Figure 8. We have only examined the Rh/SiO<sub>2</sub> films at 483 K, and thus can not report activation energies for Rh/SiO<sub>2</sub> at this time. Activation energies evaluated from Arrhenius plots for 0.5 and 10% Rh/TiO<sub>2</sub> and Rh/Al<sub>2</sub>O<sub>3</sub> have been presented in Table II together with prior data reported by other laboratories.

In an effort to identify the species responsible for the infrared bands in the 2020-2040 cm<sup>-1</sup> regions of the spectra several other experiments were performed. Figure 9 illustrates the effect of isotopic

substitution on this band. For two analogous experiments in which  $\text{CO}_2$  was hydrogenated (9a) and deuterated (9b) over 10% Rh/TiO<sub>2</sub> the band near 2030  $\text{cm}^{-1}$  shifts to lower frequency upon deuteration by 8  $\text{cm}^{-1}$ . The corresponding shift for 10% Rh/SiO<sub>2</sub> was 5  $\text{cm}^{-1}$ . For 10% Rh/Al<sub>2</sub>O<sub>3</sub> bands of comparable intensity for hydrogenation and deuteration were not obtained in the experiments performed and thus the shift was not measured. In spectrum 9b the bands at 2258 and 2199  $\text{cm}^{-1}$  can be assigned to vibrational modes for CD<sub>4</sub> and CH<sub>3</sub>D, respectively.<sup>28</sup> Bands corresponding to CHD<sub>3</sub> and CH<sub>2</sub>D<sub>2</sub> are masked by broad structure near 2269 and 2255  $\text{cm}^{-1}$ . The small band at 2141  $\text{cm}^{-1}$  in spectrum 9b occurs only for deuteration and disappears upon evacuation of the cell and is thus not due to a surface species, but we can not propose an assignment for this band at this time. It should be added that the D<sub>2</sub> + CO<sub>2</sub> reaction clearly proceeded more rapidly than the H<sub>2</sub> + CO<sub>2</sub> reaction over the supported Rh films at a given temperature.

Figure 10 shows the effects of adding H<sub>2</sub> gas and/or boric acid to 10% Rh/TiO<sub>2</sub> catalysts. In experiments 10a and 10b the catalysts were heated for long periods of time at 523 K under vacuum following reduction to remove as much hydrogen from the support as possible; the catalyst corresponding to 10b had been doped with 4.9% H<sub>3</sub>BO<sub>3</sub> before treatment. For 10c and 10d standard catalyst preparation was used (except H<sub>3</sub>BO<sub>3</sub> was added for 10c). Then CO<sub>2</sub> was introduced alone (10a or 10b) or with an excess of H<sub>2</sub> (10c or 10d). All of the samples were heated at 503 K for 4 hr. From a comparison of the CO species bands near 2030  $\text{cm}^{-1}$ , it is evident that H<sub>2</sub> causes an increase in its intensity for nonboron-doped samples (10a and 10d), but a decrease in its intensity for boron-doped samples (10b and 10c). It is also apparent that the impurity boron species cause(s) a

reduction in the intensity of the  $\text{CH}_4$  band at  $1304 \text{ cm}^{-1}$ . The large bands in the  $1200\text{-}1600 \text{ cm}^{-1}$  regions of spectra 10b and 10c can be attributed to boron oxides<sup>29,30</sup> which may be located primarily on the support.

#### IV. Discussion

##### General

From Table I it is evident that the turnover frequencies for the catalyzed  $\text{CO}_2$  hydrogenation reaction are significantly larger than those for  $\text{CO}$  hydrogenation at a given temperature (483 K) for a given catalyst film with the possible exception of the 10% Rh/ $\text{SiO}_2$  film. The latter result is probably not significant in that  $\text{CH}_4$  yields were lower and infrared background interference was greater for the  $\text{SiO}_2$  samples. In any case these observations are in accord with those of most other laboratories which have compared the rates of the two reactions over supported catalysts. From Table I one further notes that the catalytic activity of supported Rh for the hydrogenation of  $\text{CO}_2$  depends upon the nature of the support, the order being  $\text{TiO}_2 > \text{Al}_2\text{O}_3 > \text{SiO}_2$ ; this observation is also in accord with that elsewhere.<sup>17,21</sup> The turnover frequencies measured in this work for the 0.5% supported Rh catalyst films are substantially higher than those for the analogous 10% Rh films. This observation can most probably be attributed to the fact that the Rh is more highly dispersed in the 0.5% Rh films. It has been postulated that for a 0.5% supported Rh catalyst film, the active sites are isolated  $\text{Rh}^+$  ions; while for a 10% supported Rh catalyst film, the active sites are a mixture of isolated  $\text{Rh}^+$  ions and  $\text{Rh}^0$  metal clusters.<sup>23-27</sup> In our calculation of turnover frequencies, we have assumed that all Rh atoms are potentially active sites. The turnover frequencies for the 10% Rh films thus are at best minimum values, and the

data shown for 0.5% supported Rh are probably more accurate.


The data in Table II indicate that while turnover frequencies for Rh/TiO<sub>2</sub> are greater than those for Rh/Al<sub>2</sub>O<sub>3</sub> at a given temperature, the reverse is true of the activation energies; the activation energy for hydrogenation of CO<sub>2</sub> over 0.5% Rh determined in this work was 24.5 kcal mol<sup>-1</sup> for Rh/TiO<sub>2</sub>, but only 15.6 kcal mol<sup>-1</sup> for Rh/Al<sub>2</sub>O<sub>3</sub>. These results, both numerically and as a trend, are in reasonable agreement with prior results from other laboratories on a variety of Rh catalysts.<sup>14,16,17</sup> The trend was opposite for our 10% supported Rh catalyst films (21.4 and 20.3 kcal mol<sup>-1</sup> for Rh/Al<sub>2</sub>O<sub>3</sub> and Rh/TiO<sub>2</sub>, respectively). Again this may reflect the error in the measurements of turnover frequencies due to varying active cluster sizes which may change with reaction temperature as discussed earlier for the 10% supported Rh catalysts. The significant support effect on the kinetics of the hydrogenation of CO<sub>2</sub> most likely are due to an electronic effect, in that TiO<sub>2</sub> is an n-type semiconductor, as pointed out by Solymosi and coworkers.<sup>17</sup> A partial reduction of the titania surface creating "special active sites" at the Rh-support interface may also be a factor.<sup>31</sup>

It is interesting that infrared bands characteristic of adsorbed formate were observed only for the 0.5% Rh/Al<sub>2</sub>O<sub>3</sub> film following heating above 423 K. Solymosi and coworkers have detected formate in the CO<sub>2</sub> hydrogenation reaction and in the decomposition of formic acid over a variety of supported Rh catalysts even near 300 K; they have shown that the formate species resides on the support rather than on Rh, but that the presence of Rh is necessary for the formation of formate in the hydrogenation of CO<sub>2</sub>.<sup>10,17,18,22,32,33</sup> It would appear from our data that

catalysts containing highly dispersed Rh on alumina (0.5% Rh/Al<sub>2</sub>O<sub>3</sub>) favor the formation of formate. Since formate does not form during the heating of Al<sub>2</sub>O<sub>3</sub> alone in the presence of CO<sub>2</sub> and H<sub>2</sub>, we would postulate that the Rh catalyzes the formation of formate, but in accord with the view of Solymosi, that the formate resides on the support well removed from the Rh-support interface.

#### The CO Intermediate

We performed isotopic labeling studies to insure that the infrared bands near 2030 cm<sup>-1</sup> for these catalysts did not, in fact, correspond to a Rh-H vibrational mode. The band shifted to 1981 cm<sup>-1</sup> when C<sup>18</sup>O<sub>2</sub> was hydrogenated over 10% Rh/Al<sub>2</sub>O<sub>3</sub> indicating that the band did not correspond to a Rh hydride. Figure 9 also clearly shows that this was not the case, because the band shift upon changing from H<sub>2</sub> to D<sub>2</sub> (typically in the range 5-10 cm<sup>-1</sup> for all experiments) was indicative of isotopic substitution two bonds removed from the CO bond. Solymosi and coworkers have suggested that the 2030 cm<sup>-1</sup> band is too low in frequency to correspond to a linear CO species, and most probably instead corresponds to a carbonyl hydride species.<sup>17,18,22,34</sup> Iizuka and coworkers, on the other hand, have pointed out that this band appears in the absence of gas-phase H<sub>2</sub> and have suggested that the band thus corresponds to the usual "linear" CO species at low coverage.<sup>16,35</sup> We concur completely with Solymosi. The band in the 2020-2040 cm<sup>-1</sup> region is due to a carbonyl hydride species of the form shown below. The normal "linear" CO band frequency for supported Rh



catalysts lies in the range 2040 - 2080  $\text{cm}^{-1}$  dependent upon coverage.<sup>23-27</sup> The hydride ligand acts as an electron donor through the metal into the antibonding  $\pi^*$  orbital on CO thus weakening the C-O bond and lowering its stretching frequency. The presence of two hydride ligands should enhance the effect and lower the stretching frequency further. The small isotopic shift observed here (5-10  $\text{cm}^{-1}$ ) upon switching from  $\text{H}_2$  to  $\text{D}_2$  gas is in accord with this explanation because the hydride (deuteride) ligand is two bonds removed from the CO oscillator. The two bands at 2036 and 2028  $\text{cm}^{-1}$  in Figure 9 have the same intensity, so the low frequency of the CO moiety can not be due to low coverage; it must be due to the existence of the carbonyl hydride (deuteride). It should be noted that this band does move toward higher frequency as its intensity increases for the 10% Rh catalysts due to a coverage effect. However, it does not shift in frequency as coverage is increased for 0.5% Rh catalysts. This observation is in line with the 0.5% catalysts containing isolated  $\text{Rh}^+$  ions, such that increasing coverage does not lead to increased dipole-dipole interaction causing shifts to higher frequency of the CO vibrational mode.<sup>27</sup> The existence of a carbonyl hydride band for  $\text{CO}_2$  in the presence of supported Rh, but in the absence of gaseous  $\text{H}_2$ , has been observed here,<sup>36</sup> as well as by Iizuka and coworkers.<sup>16,35</sup> We believe that this is a result of migration of hydrogen from the support to the Rh, an "inverse spillover effect".<sup>36</sup> In support of this hypothesis, we have observed the presence of  $\text{CHD}_3$  and  $\text{CH}_2\text{D}_2$  over 10% Rh/ $\text{TiO}_2$  at 503 K for a mixture of  $\text{CO}_2$  and  $\text{D}_2$  following reduction by  $\text{D}_2$  and extensive heating in vacuum.<sup>36</sup> The H necessary for the formation of  $\text{CHD}_3$  and  $\text{CH}_2\text{D}_2$  must have come from the small amounts of unexchanged H on the support. We have also observed complete exchange of  $\text{CH}_4$  in the presence of

D<sub>2</sub> over 10% Rh/TiO<sub>2</sub> at 503 K to form CH<sub>3</sub>D, CH<sub>2</sub>D<sub>2</sub>, CHD<sub>3</sub>, and CD<sub>4</sub>.<sup>36</sup> All of these experiments demonstrate the mobility of H or D on the supported catalysts.

It should be noted also that our isotopic labeling studies have demonstrated an inverse isotope effect for the hydrogenation of CO<sub>2</sub> over all of the supported Rh films, *ie.* the turnover frequencies at a given temperature were larger for the production of CD<sub>4</sub> from CO<sub>2</sub> + D<sub>2</sub> than for the production of CH<sub>4</sub> from CO<sub>2</sub> + H<sub>2</sub>. This inverse isotope effect has been noted by other laboratories for a variety of supported metal catalysts for CO and CO<sub>2</sub> hydrogenation.<sup>16,37</sup> Wilson<sup>38</sup> and Kellner and Bell<sup>37</sup> have concluded that the overall inverse isotope effect results from a combination of the kinetic and equilibrium isotope effects associated with the various steps of the mechanism.

The data in Table I concerning the carbonyl hydride band frequency for CO and CO<sub>2</sub> hydrogenation are suggestive of a monohydride in all cases for Rh/TiO<sub>2</sub>, but possibly a dihydride for CO<sub>2</sub> hydrogenation over Rh/Al<sub>2</sub>O<sub>3</sub> and Rh/SiO<sub>2</sub>. The role of the carbonyl hydride species in the CO hydrogenation reaction was discussed in more detail elsewhere.<sup>26</sup>

#### The Dissociation of CO<sub>2</sub>

Currently there exists a controversy concerning the dissociation of CO<sub>2</sub> over Rh at ambient temperature.<sup>39-43</sup> Somorjai and coworkers have reported that CO<sub>2</sub> does dissociate on Rh foil and on several different Rh single crystal surfaces with high probability (10<sup>-1</sup>) at 300 K.<sup>39</sup> However, Weinberg has computed the probability of dissociative adsorption of CO<sub>2</sub> on Rh to be only 10<sup>-15</sup> at low pressure and ambient temperature.<sup>40</sup> Goodman and



coworkers<sup>41</sup> have recently measured the activation energy for CO<sub>2</sub> dissociation on Rh(111) to be 17 kcal mol<sup>-1</sup> and have concluded that the probability of dissociation of CO<sub>2</sub> on Rh at 300 K and 760 Torr is only 10<sup>-11</sup>. Very recently Solymosi and Kiss have reported that no dissociation of CO<sub>2</sub> takes place on clean Rh at 300 K, but that dissociation does occur in the presence of H<sub>2</sub> or impurity boron.<sup>42</sup>

From spectrum 10a it is obvious that CO<sub>2</sub> dissociation does occur on 10% Rh/TiO<sub>2</sub> at 503 K in the absence of H<sub>2</sub> gas, for the carbonyl hydride infrared band at 2032 cm<sup>-1</sup> grew to the indicated intensity after 4 hr. The necessary hydrogen for this species migrates to Rh from the support. We have made a similar observation for Rh/Al<sub>2</sub>O<sub>3</sub>. Examination of spectrum 10d reveals that the carbonyl hydride band was much more intense under the same conditions when gas-phase H<sub>2</sub> was present. We have shown previously that the carbonyl hydride band grows in intensity with time, even at 300 K, for 10% Rh/TiO<sub>2</sub> when H<sub>2</sub> gas is present.<sup>43</sup> Thus there can be no doubt that H<sub>2</sub> assists the dissociation of CO<sub>2</sub> on supported Rh. This is probably accomplished by a combination of two effects - reaction with adsorbed O produced from CO<sub>2</sub> decomposition to free active sites and more facile formation of the carbonyl hydride species.

Spectra 10b and 10c correspond to analogous experiments for 10% Rh/TiO<sub>2</sub> in which H<sub>3</sub>BO<sub>3</sub> was added as an impurity. Comparison of spectra 10b and 10a shows that the presence of the impurity boron species (probably in the form of oxides) caused an accentuation of the carbonyl hydride species when no H<sub>2</sub> was present. This is most probably the result of electropositive boron interacting with the O in CO<sub>2</sub> to enhance dissociation and thus more facile formation of the carbonyl hydride species. On the

other hand, a comparison of spectra 10b and 10c reveals that the carbonyl hydride species is suppressed when impurity boron and gas-phase H<sub>2</sub> are present. Also from spectra 10c and 10d it is evident that impurity boron poisons the production of CH<sub>4</sub>. These observations indicate that the impurity boron is poisoning the rate-determining step, probably by blocking active methanation sites. A build-up of carbon on inactive methanation sites due to the presence of H<sub>2</sub> in the reaction cell could then block the formation of additional carbonyl hydride and explain the weak infrared band for the latter.

Unfortunately we can not compute the probability of dissociation of CO<sub>2</sub> over Rh from our data. However, we suspect that the presence of impurities such as H<sub>2</sub>, H from a support, or boron are necessary to make this process facile at low temperature.

#### Mechanism of CO<sub>2</sub> Hydrogenation

Based upon the data accumulated in these laboratories, we would propose that the mechanism of CO<sub>2</sub> hydrogenation over supported Rh catalyst films involves: (1) the dissociation of CO<sub>2</sub> on Rh assisted by the presence of H<sub>2</sub> gas or H from the support to form the Rh carbonyl hydride species, formate on the support, and adsorbed O on Rh; (2) the removal of adsorbed O by H<sub>2</sub> and H to form H<sub>2</sub>O(g) and OH on the support; (3) dissociation of the C-O bond in the Rh carbonyl hydride, to form active C on Rh; and (4) reaction of the active surface C on Rh with H<sub>2</sub> and H(a) to form CH<sub>4</sub> (g). This proposed mechanistic scheme is very similar to one suggested earlier by Solyosi and coworkers.<sup>22</sup> Its most novel feature is the proposed carbonyl hydride intermediate.

The reason for CO<sub>2</sub> hydrogenation proceeding at an apparent faster rate than does CO hydrogenation, even though the mechanisms are thought to be similar, is that the reactions are negative order in CO; there is a lower steady-state concentration of CO for the CO<sub>2</sub> methanation process.<sup>1</sup> We agree with Goodman and coworkers that for CO<sub>2</sub> and CO methanation, there must be a delicate balance of the C(a) formation step and the C(a) surface hydrogen step,<sup>1</sup> such that either the dissociation of the carbonyl hydride or the hydrogenation of active C may be rate limiting, dependent upon reaction conditions. As for which step was rate determining for our catalyst films, we can only propose that for the impurity boron work, the rate determining step was hydrogenation of active C (see last section).

#### Conclusions

The following conclusions can be made from this work:

- (1) Methane was the only hydrocarbon reaction product observed in these studies.
- (2) There is a support effect for CO<sub>2</sub> hydrogenation over supported Rh catalyst films. The turnover frequencies at a given temperature are in the order TiO<sub>2</sub> > Al<sub>2</sub>O<sub>3</sub> > SiO<sub>2</sub>.  
The CO<sub>2</sub> hydrogenation turnover frequencies are larger than CO hydrogenation ones under similar reaction conditions.
- (3) The activation energy for hydrogenation of CO<sub>2</sub> is higher for Rh/TiO<sub>2</sub> than for Rh/Al<sub>2</sub>O<sub>3</sub> for sample films containing low weight percent Rh.
- (4) A formate species is formed upon heating for catalyst films

containing low Rh loading on Al<sub>2</sub>O<sub>3</sub> indicating the possibility of location on the support well removed from the Rh-support interface. The formate species was not observed for catalyst films containing high Rh loading or on blank supports.

- (5) A Rh carbonyl hydride species is formed during CO<sub>2</sub> hydrogenation which is a key observable intermediate in catalytic methanation. This intermediate has been observed for CO hydrogenation over supported Rh films also.<sup>26</sup> The carbonyl hydride can be formed as a result of hydrogen migration from the support in the absence of gas-phase H<sub>2</sub>.
- (6) The presence of H<sub>2</sub>, H(a), and impurity boron all enhance the dissociation of CO<sub>2</sub> over supported Rh. However, impurity boron poisons the methanation reaction.

#### Acknowledgements

We gratefully acknowledge the support of the Office of Naval Research for this work. We also acknowledge stimulating conversations with F. Solymosi, D.W. Goodman, and J.M. White concerning this work. We thank F. Solymosi for access to reference 42 in advance of publication.

## References

- (1) D.E. Peebles, D.W. Goodman, and J.M. White, J. Phys. Chem., **87**, 4378 (1983).
- (2) G.D. Weatherbee and C.H. Bartholomew, J. Catal., **77**, 460 (1982).
- (3) J.L. Falconer and A.E. Zagli, J. Catal., **62**, 280 (1980).
- (4) J. Dalmon and G.A. Martin, J. Chem. Soc. Faraday Trans. 1, **75**, 1011 (1979).
- (5) G.D. Weatherbee and C.H. Bartholomew, J. Catal., **68**, 67 (1981).
- (6) T. Van Herwijnen, H. Van Doesburg, and W.A. Dejong, J. Catal., **28**, 391 (1973).
- (7) T. Inui, M. Funabiki, M. Suehiro, and T. Sezume, J. Chem. Soc. Faraday Trans. 1, **75**, 787 (1979).
- (8) F. Solymosi and A. Erdohelyi, J. Mol. Catal., **8**, 471 (1980).
- (9) E. Ramarosan, R. Kieffer, and A. Kiennemann, J. Chem. Soc. Chem. Commun., 645 (1982).
- (10) F. Solymosi, A. Erdohelyi, and M. Kocsis, J. Chem. Soc. Faraday Trans 1, **77**, 1003 (1981).
- (11) A.E. Zagli and J.L. Falconer, J. Catal., **69**, 1 (1981).
- (12) F.S. Karn, J.F. Shultz, and R.B. Anderson, Ind. Eng. Chem. Prod. Res. Dev., **4**, 265 (1965).
- (13) P.J. Lunde and F.L. Kester, J. Catal., **30**, 423 (1973).
- (14) B.A. Sexton and G.A. Somorjai, J. Catal., **46**, 167 (1977).
- (15) A. Amariglio, M. Lakhdar, and H. Amariglio, J. Catal., **81**, 247 (1983).
- (16) T. Iizuka, Y. Tanaka, and K. Tanabe, J. Catal., **76**, 1 (1982).
- (17) F. Solymosi, A. Erdohelyi, and T. Bansagi, J. Catal., **68**, 371 (1981).
- (18) F. Solymosi, A. Erdohelyi, and M. Kocsis, J. Catal., **65**, 428 (1980).
- (19) Y. Tanaka, T. Iizuka, and K. Tanabe, J. Chem. Soc. Faraday Trans. 1, **78** 2215 (1982).

- (20) T. Iizuka, Y. Tanaka, and K. Tanabe, J. Mol. Catal., **17**, 381 (1982).
- (21) F. Solymosi, A. Erdohelyi, and T. Bansagi, J. Chem. Soc. Faraday Trans 1, **77**, 2645 (1981).
- (22) A. Erdohelyi, M. Kocsis, T. Bansagi, and F. Solymosi, Acta Chim. Acad. Scient. Hung. Tomus, **111**, 591 (1982).
- (23) C.A. Rice, S.D. Worley, C.W. Curtis, J.A. Guin, and A.R. Tarrer, J. Chem. Phys., **74**, 6487 (1981).
- (24) S.D. Worley, C.A. Rice, G.A. Mattson, C.W. Curtis, J.A. Guin, and A.R. Tarrer, J. Chem. Phys., **76**, 20 (1982).
- (25) S.D. Worley, C.A. Rice, G.A. Mattson, C.W. Curtis, J.A. Guin, and A.R. Tarrer, J. Phys. Chem., **86**, 2714 (1982).
- (26) S.D. Worley, G.A. Mattson, and R. Caudill, J. Phys. Chem., **87**, 1671 (1983).
- (27) J.T. Yates, T.M. Duncan, S.D. Worley, and R.W. Vaughan, J. Chem. Phys., **70**, 1219 (1979) and references quoted therein.
- (28) G. Herzberg, "Molecular Spectra and Molecular Structure II. Infrared and Raman Spectra of Polyatomic Molecules", D. Van Nostrand, Inc., New York, 1945.
- (29) S. Semancik, G.L. Haller, and J.T. Yates, Appl. Surface Sci., **10**, 546 (1982).
- (30) L.H. Dubois, J. Chem. Phys., **77**, 5228 (1982).
- (31) M.A. Vannice and C. Sudhakar, J. Phys. Chem., **88**, 2429 (1984).
- (32) F. Solymosi, T. Bansagi, and A. Erdohelyi, J. Catal., **72**, 166 (1981).
- (33) F. Solymosi and J. Kiss, J. Catal., **81**, 95 (1983).
- (34) F. Solymosi and A. Erdohelyi, J. Catal., **70**, 451 (1981).
- (35) T. Iizuka and Y. Tanaka, J. Catal., **70**, 449 (1981).
- (36) M.A. Henderson and S.D. Worley, J. Phys. Chem., submitted.
- (37) For example, see C.S. Kellner and A.T. Bell, J. Catal., **67**, 175 (1981) and references quoted therein.
- (38) T.P. Wilson, J. Catal., **60**, 167 (1979).

- (39) L.H. Dubois and G.A. Somorjai, Surface Sci., **128**, L231 (1983) and numerous references cited therein.
- (40) W.H. Weinberg, Surface Sci., **128**, L224 (1983).
- (41) D.W. Goodman, D.E. Peebles, and J.M. White, Surface Sci., **140**, L239 (1984).
- (42) F. Solymosi and J. Kiss, Surface Sci., in press; Chem. Phys. Letters, in press.
- (43) M.A. Henderson and S.D. Worley, Surface Sci., in press.

TABLE I: Comparison of Turnover Frequencies for Hydrogenation of CO<sup>a</sup> and CO<sub>2</sub> over Supported Rh Catalyst Films at 483 K

Catalyst Film	CO + 3H <sub>2</sub>		CO <sub>2</sub> + 4H <sub>2</sub>	
	Rh(CO)H	TN <sup>b</sup>	Rh(CO)H	TN <sup>b</sup>
10.0% Rh/TiO <sub>2</sub>	2045 <sup>c</sup>	19.1	2042 <sup>c</sup>	81.3
10.0% Rh/Al <sub>2</sub> O <sub>3</sub>	2045	11.2	2025	33.5
10.0% Rh/SiO <sub>2</sub>	2045	13.8	2028	9.2
0.5% Rh/TiO <sub>2</sub>	2043	27.5	2038	803.0
0.5% Rh/Al <sub>2</sub> O <sub>3</sub>	2045	7.3	2020	77.8
0.5% Rh/SiO <sub>2</sub>	2040	5.3	2032	30.4

<sup>a</sup>Reference 26.

<sup>b</sup>Molecules CH<sub>4</sub>/Rh atom/sec x 10<sup>5</sup>.

<sup>c</sup>Frequency in cm<sup>-1</sup>.



TABLE II. Comparison of Activation Energies for Hydrogenation of CO<sub>2</sub> over Supported Rh Catalyst Films from This Work with Selected Values from Other Laboratories

Catalyst	Reaction Conditions	E <sub>a</sub> <sup>a</sup>	Reference
0.5% Rh/Al <sub>2</sub> O <sub>3</sub>	66 Torr, 1:4	15.6	This work
0.5% Rh/TiO <sub>2</sub>	CO <sub>2</sub> : H <sub>2</sub> ,	24.5	This work
10.0% Rh/Al <sub>2</sub> O <sub>3</sub>	Static	21.4	This work
10.0% Rh/TiO <sub>2</sub>		20.3	This work
Rh Foil	700 Torr, 1:3 CO <sub>2</sub> : H <sub>2</sub> , Flow	16	14
5% Rh/Al <sub>2</sub> O <sub>3</sub>	760 Torr, 1:4	16.2	17
1% Rh/TiO <sub>2</sub>	CO <sub>2</sub> :H <sub>2</sub> , Flow	19.4	17
2.3% Rh/Al <sub>2</sub> O <sub>3</sub>	75 Torr, 1:4 CO <sub>2</sub> :H <sub>2</sub> , Flow	17.0	16

<sup>a</sup>Kcal mol<sup>-1</sup>.

### Figure Captions

Figure 1. Schematic of the Pyrex infrared cell/reactor used in this work.

Figure 2. Typical calibration curve for determining the reaction yield of methane.

Figure 3. Infrared spectra of a 10% Rh/TiO<sub>2</sub> film (4.7 mg cm<sup>-2</sup>) following normal sample pretreatment and reduction and then: (a) introduction of 66.2 Torr CO<sub>2</sub> + 4H<sub>2</sub> at 298 K, (b) heating at 503 K for 30 min, (c) heating at 503 K for 4 hr.

Figure 4. Infrared spectra of a 10% Rh/Al<sub>2</sub>O<sub>3</sub> film (3.1 mg cm<sup>-2</sup>) following normal sample pretreatment and reduction and then: (a) introduction of 66.4 Torr CO<sub>2</sub> + 4H<sub>2</sub> at 298 K, (b) heating at 503 K for 1.5 hr, (c) heating at 503 K for 5 hr.

Figure 5. Infrared spectra of a 10% Rh/SiO<sub>2</sub> film (5.1 mg cm<sup>-2</sup>) following normal sample pretreatment and reduction and then: (a) introduction of 66.1 Torr CO<sub>2</sub> + 4H<sub>2</sub> at 298 K, (b) heating at 483 K for 1 hr, (c) 3 hr, (d) 8 hr.

Figure 6. Infrared spectra of a 0.5% Rh/TiO<sub>2</sub> film (4.4 mg cm<sup>-2</sup>) following normal sample pretreatment and reduction and then: (a) introduction of 66.5 Torr CO<sub>2</sub> + 4H<sub>2</sub> at 298 K, (b) heating at 443 K for 2 hr, (c) heating at 443 K for 7 hr, (d) evacuation at 298 K.


Figure 7. Infrared spectra of a 0.5% Rh/Al<sub>2</sub>O<sub>3</sub> film (4.4 mg cm<sup>-2</sup>) following normal sample pretreatment and reduction and then:

(a) introduction of 66.3 Torr  $\text{CO}_2 + 4\text{H}_2$  at 298 K, (b) heating at 453 K for 2 hr, (c) heating at 453 K for 3 hr, (d) heating at 453 K for 16 hr, (e) evacuation at 298 K.


Figure 8. Typical Arrhenius plots for  $\text{CH}_4$  production from 66 Torr  $\text{CO}_2 + 4\text{H}_2$  over 0.5% Rh/ $\text{TiO}_2$  and 0.5% Rh/ $\text{Al}_2\text{O}_3$  films. Activation energies in  $\text{kcal mol}^{-1}$  are indicated.

Figure 9. Infrared spectra of 10% Rh/ $\text{TiO}_2$  films: (a)  $4.7 \text{ mg cm}^{-2}$  film following normal pretreatment, reduction in  $\text{H}_2$ , introduction of 66.2 Torr  $\text{CO}_2 + 4\text{H}_2$ , and heating at 503 K for 2 hr, (b)  $4.2 \text{ mg cm}^{-2}$  film following normal pretreatment, reduction in  $\text{D}_2$ , introduction of 66.0 Torr  $\text{CO}_2 + 4\text{D}_2$ , and heating at 503 K for 2 hr.

Figure 10. Infrared spectra of 10% Rh/ $\text{TiO}_2$  films: (a)  $4.1 \text{ mg cm}^{-2}$  film following reduction, heating at 523 K at  $1 \times 10^{-6}$  Torr for 16 hr, introduction of 12.6 Torr  $\text{CO}_2$ , and heating at 503 K for 4 hr, (b)  $4.4 \text{ mg cm}^{-2}$  film doped with 4.9%  $\text{H}_3\text{BO}_3$ , following reduction, heating at 523 K at  $1 \times 10^{-6}$  Torr for 17.7 hr, introduction of 12.9 Torr  $\text{CO}_2$ , and heating at 503 K for 4 hr, (c)  $4.2 \text{ mg cm}^{-2}$  film doped with 4.9%  $\text{H}_3\text{BO}_3$ , following standard reduction, introduction of 66.2 Torr  $\text{CO}_2 + 4\text{H}_2$ , heating at 503 K for 4 hr, (d)  $4.3 \text{ mg cm}^{-2}$  film following standard reduction, introduction of 66.2 Torr  $\text{CO}_2 + 4\text{H}_2$ , heating at 503 K for 4 hr.




Worley, et al., Fig. 1




ABSORBANCE AT 1304 CM<sup>-1</sup> (x10<sup>2</sup>)


METHANE PRESSURE (TORR)



3  
V. J. et al.




Universal




Wolfs, et al







*subtle etc*




Wolke, et al.



Whitney, et al.



Wiley, et al.



Wolke

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Douda Naval Weapons Support Center Code 5042 Crane, Indiana 47522	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1		

ABSTRACTS DISTRIBUTION LIST, 634

Dr. K. N. Nicholas  
Department of Chemistry  
University of Oklahoma  
Norman, Oklahoma 73019

Dr. Aaron Fletcher  
Code 3852  
Naval Weapons Center  
China Lake, California 93555

Dr. A. Wold  
Department of Chemistry  
Brown University  
Providence, Rhode Island 02912

Dr. J. Cooper  
Code 6130  
Naval Research Laboratory  
Washington, D.C. 20375

Dr. M. C. Baird  
Department of Chemistry  
Queen's University  
Kingston, Canada  
K7L 3N6

Dr. N. N. Lichtin  
Department of Chemistry  
Boston University  
685 Commonwealth Avenue  
Boston, Massachusetts 02215

Dr. R. Eisenberg  
Department of Chemistry  
University of Rochester  
Rochester, New York 14627

Dr. N. Cooper  
Department of Chemistry  
Harvard University  
Cambridge, Massachusetts 02138

Dr. S. D. Worley  
Department of Chemistry  
Auburn University  
Auburn, Alabama 36830

Dr. L. Vaska  
Department of Chemistry  
Clarkson College  
Potsdam, New York 13676

Dr. R. A. Huggins  
Materials Science and  
Engineering Department  
Stanford University  
Stanford, California 94305

**END**

**FILMED**

**2-85**

**DTIC**