REPORT NO. NADC-85029-60

Best Available Copy



20030115214

CORROSION-PREVENTIVE PRIMERS FOR MILITARY EQUIPMENT

Stephen J. Spadafora, Charles R. Hegedus, and David F. Pulley Aircraft and Crew Systems Technology Directorate NAVAL AIR DEVELOPMENT CENTER Warminster, Pennsylvania 18974-5000

1 APRIL 1985

FINAL REPORT AIRTASK NO. AIR-310-310A/001B/4F61-542-000 Work Unit ZM540

Approved for Public Release; Distribution Unlimited

Prepared for NAVAL AIR SYSTEMS COMMAND Department of the Lavy Washington, DC 20361 DTIC SULIS 1665 G

25

85

FILE COP9

REPRODUCTION QUALITY NOTICE

This document is the best quality available. The copy furnished to DTIC contained pages that may have the following quality problems:

- Pages smaller or larger than normal.
- Pages with background color or light colored printing.
- Pages with small type or poor printing; and or
- Pages with continuous tone material or color photographs.

Due to various output media available these conditions may or may not cause poor legibility in the microfiche or hardcopy output you receive.

If this block is checked, the copy furnished to DTIC contained pages with color printing, that when reproduced in Black and White, may change detail of the original copy.

REPORT NUMPERING SYSTEM - The numbering of technical project reports issued by the Naval Air Development Center is arranged for specific identification purposes. Each number consists of the Center acronym, the calendar year in which the number is assigned, the sequence number of the report within the specific calendar year, and the official 2-digit correspondence code of the Command Office or the Functional Directorate responsible for the report. For example: Report No. NADC-78015-20 indicates the fifteeth Center report for the year 1978, and prepared by the Systems Directorate. The numerical codes are as follows:

CODE

OFFICE OR DIRECTORATE

1 8 3 4 1 1

- 00 Commander, Naval Air Development Center.
- 01 Technical Director, Naval Air Development Center
- 02 Comptroller
- 10 Directorate Command Projects
- 20 Systems Directorate
- 30 Sensors & Avionics Technology Directorate
- 40 Communication & Navigation Technology Directorate
- 50 Software Computer Directorate
- 60 Air raft & Crew Systems Technology Directorate
- 70 Planning Assessment Resources
- 80 Engineering Support Group.

PRODUCT FNDORSEMENT - The discussion or instructions concerning commercial products herein do not constitute an endorsement by the Government nor do they convey or imply the license or right to use such products.

~	
	Plank DATE 8 91 1 1985
CAPI, MSC. U.S.	Navy
Accession For	Z
STIS GRAAI DTIC TAB Unannounced 5 5.	
Justification	
By Distribution/	+
Availability Codes]
Dist Avail and/or Spoulal	

Unclassified

AD. A156927

Ś

Π

		REPORT DOCU	MENTATION	PAGE		
1. REPORT SECURITY CLASSIF	FICATION		15. RESTRICTIVE	MARKINGS		
Unclassified		<u>N/A</u>	N/A			
SECURITY CLASSIFICATION		3. DISTRIBUTION / AVAILABILITY OF REPORT				
N/A		Approved	Approved for Public Release;			
b. DECLASSIFICATION / DOWN	LE	Distribution Unlimited				
. PERFORMING ORGANIZATIC	ON REPORT NUMBE	.R(S)	5. MONITORING	ORGANIZATION I	REPORT NUMBER(S)	
NADC-85029-60						
ES. NAME OF PERFORMING O	RGANIZATION	65. OFFICE SYMEOL	7a. NAME OF M	ONITORING ORGI	ANIZATION	
Aircraft and Crew Sys	stems	(if applicable)	1		,	
Technology Directors	ite	6062	[
ADDRESS (City, State, and	ZIP (,ode)		7b. ADDRESS (CT	ty, State, and ZIP	P Code)	
ALANIAL AID DEVEL	ODMENT CENT	760	1		1	
NAVAL AIR DEVEL	UPMENT CENT	ER	1		1	
Warminster, PA 1057	4					
A NAME OF FUNDING / SPON	NSORING	TED. OFFICE SYMBOL	9. PROCUREMEN	T INSTRUMENT IC	DENTIFICATION NUMBER	
CREANIZATION		(if applicable)		-	1	
Naval Air Systems Co	mmand	1	1			
- ADDRESS (CIN State, and	TIP Code)	1	10 SOURCE OF	FUNCING NUMBE	· R5	
	air wuxy		PROGRAM	TEROJECT	TASK AIR 210 WORK UNIT	
Department of the ive	avy		ELEMENT NO.	NO.	NO 3104/0018/ ACCESSION NO.	
Washington, DC			1	1	4F61-542-000 ZM540	
3 TITLE (include Security Cli	asufication)				$\overline{\nabla}$	
6. SUPPLEMENTARY NOTAT	ION			<u>April 1</u>		
17 COSATI C	CODES	18. SUBJECT TERMS	(Continue on revers	e if necessary and	d identify by block number)	
FIELD GROUP	SUB-GROUP	Organic Coating	p _		1	
	L	Corrosion Prote	ction			
	k	Military Equipr	nent			
way of protecting equ primers are composed to cover a broad rang Eleven primers confo Properties such as con primer. The results of primers. This information properties for a speci Mymg Thm N-Value 0	Jipment against 3 of a variety of e of operational irming to militar rrosion protectic f this evaluation ation is presented ific use. A for the second for the second	this process is throw resins, pigments and environments. y and federal specifi in, adhasion, flexibi indicate a wide vari- d to enable the read doctor resist (orgound RPT. DTIC USER:	igh the use or cu isolvents to pro ications were ter ility and chemicr iety of performa ler to choose a m <i>Kayworda</i> ance <i>Conlint</i> , 21. AJSTRACT SI JInclassifier	rrosion-preven duce materials ited on steel an al resistance we nee properties naterial with th 'organi built No ECURITY CLASSIFIE	tive primers. I ness with different properties and aluminum specimens. Fre determined for each for the eleven the most appropriate the costinger instance ;	
228. GAME OF RESPONSIBLE	INDIVIDUAL		220. TELEPHONE	(include Area Cod-	(+) 22C OFFICE SYNIGOL	
DD FORM 1473, 64 MAR	83 A	PR edition may be used u All other editions are (intil exnausted. obsolete.	SECURITY	CLASSIFICATION OF THIS PAGE	

URITY CLASSIFICATION OF THIS PAGE

.

1.

Ż

'

.

.

·

. . .

.

a shara da sa sana sa sana ya sa sa sa sa sa sa

. .

•

an an the second se

SECURITY CLASSIFICATION OF THIS PAGE

.

Ľ

يده بالا يوالي منتخب بالارد الأسادي

1.

•

٦.

TABLE OF CONTENTS

	Page
LIST OF TABLES.	2
LIST OF FIGURES.	2
INTRODUCTION	3
PROCEDURE	3
DRYING TIME	3
ADHESION	3
FLEXIBILITY	6
CORROSION RESISTANCE	6
FLUID RESISTANCE	6
VOLATILE ORGANIC COMPOUNDS CONTENT.	6
RESULTS AND DISCUSSION	6
SUMMARY	26
ACKNOWLEDGEMENT	26

1~

LIST OF TABLES

Table Page 1 Materials List. 4 2 Components of the Primers Evaluated. 5 3 Test Results. 7,

LIST OF FIGURES

Figure Page 1 Comparison of Cross-Hatch Test Results..... 9 2 GE Versus Gardner Impact Test Results 10 3 Results for 5% NaCl Salt Spray Tests 13 4 Steel Specimens (Painted) from 5% Salt-Spray Test 14 5 Steel Panels (Stripped) from 5% Salt-Spray Test 15 6 Aluminum Panels (Painted) from 5% Salt-Spray Test 16 7 Aluminum Panels (Stripped) from 5% Salt-Spray Test 17 8 Results for SO₂/Salt-Spray Tests. 18 9 Steel Panels (Painted) from SO2/Salt-Spray Test. 19 10 Steel Panels (Stripped) from SO2/Salt-Spray Test..... 20 11 Aluminum Panels (Painted) from SO2/Salt-Spray Test 21 12 Aluminum Panels (Stripped) from SO2/Salt-Spray Test 22 Results for the Filiform Corrosion Test. 13 23 Aluminum Panels (Painted) from Filiform Corrosion Test 14 24 15 Aluminum Panels (Stripped) from Filiform Corrosion Test. 25

INTRODUCTION

Corrosion is a major reason for the high cost of maintaining and repairing military equipment. It can be minimized through the application of corrosion-inhibiting primers to all metallic substrates before topcoating. These primers contain reactive pigments such as chromates, phosphates, oxides, etc. that help to passivate metals and neutralize aggressive ions at the primer/metal interface. Many military specifications have been written for the procurement of these materials. Eleven of the more common specifications are given in Table 1. They differ in regard to composition and intended application. This information can be obtained from the specifications. Table 2 lists the binder, resin, and solvent systems of these materials. The purpose of the study is to give those who specification, a single primer was obtained directly from a qualified manufacturer. Their names and product numbers have been withheld from this report, since it is not our intent to endorse any proprietary formulation. The selection of a primer for a particular application should be based on many factors including cost, performance, intended use, and environmental conditions. The optimum material for one application may not be adequate for another. We hope that this report will make the task of choosing the proper material somewhat easier.

PROCEDURE

With the exception of flexibility and filiform corrosion, all of the test properties were conducted on 1010 carbon steel and 2024T3 aluminum alloy. The steel panels were pretreated with a zinc phosphate coating in accordance with specification DOD-P-16232. The aluminum panels were pretreated with a chromate conversion coating in accordance with specification MIL-C-5541 using materials conforming to specification MIL-C-81706. The flexibility tests were conducted on 2024-0 aluminum alloy (annealed) that was anodized in accordance with specification MIL-(A-8625, Type II. Filiform corrosion was performed on Alclad 2024-T3 aluminum alloy panels which vere pretreated with the above chromate conversion coating. The primers were mixed as prescribed by the manufacturer and applied by conventional air spray to a dry-film thickness of 1.0 to 1.5 mis. They were then cured for seven days at room temperature before testing. The physical properties of each primer were determined in accordance with test methods from the American Society for Testing and Materials (ASTM) and Federal Test Method Standard (FTMS) No. 141B.

DRYING TIME (ASTM D1640)

and a second second

The tark-free time is defined as the period of time from application until no tackiness is evident to the touch. At this point, the primer is ready for topcoating. The dry-hard time is defined as the period of time from application until the film cannot be permanently marred using firm thumb pressure. At this point, items that receive only a coat of primer are now ready to be handled.

ADHESION (ASTM D3359, ASTM D2197)

After 24 hours of water immersion, the crosshatch instrument was used to scribe 11 parallel lines (1 mm apurt) through the film and again in a perpendicular direction, so that a grid of 100 squares was formed. A strip of 3M-250 masking tape was then applied over the grid with firm thumb pressure and removed with one quick motion. Standards for evaluation of adhesion, based on the area of primer removed, are given in the test method. Another means of determining adhesion was the Arco Microknife. With this method, parallel cuts were made in the film through to the substrate. These cuts were made closer and closer together until the primer between the cuts was sheared from the panel. The adhesion rating was calculated from a formula that included the shearing force as a variable.

٦

TABLE 1. MATERIALS LIST

Specification	Title
TT-P-664	Primer Coating, Synthetic, Rust-inhibiting, Lacquer-resistant
TT-P-1757	Primer Coating, Zinc Chromate, Low Moisture Sensitivity
MIL-P-23377	Primer Coatings, Epoxy-polyamide, Chemicai and Solvent Resistant
MIL-P-26915	Primer Coating, Zinc Dust Pigmented, for Steel Surfaces
MIL-P-52192	Primer Coating, Epoxy
MIL-P-52995	Primer Coating, Synthetic, Corrosion-inhibiting, Lacquer-resisting, Lead and Chromate-Free
MIL-P-53022	Primer Coating, Epoxy, Corrosion-inhibiting, Lead and Chromate-Free
MIL-P-53030	Primer Coating, Epoxy, Water Reducible, Lead and Chromate-Free
MIL-P-85582	Primer Coatings, Epoxy, VOC Compliant, Chemical and Solvent Resistant
MIL-P-87112	Primer Coating, Elastomeric, Polysulfide, Corrosion-inhibiting
MIL-P-XXXXX*	Primer Coatings, Polyurethane, Elastomeric, Corrosion-inhibiting

.

*One-component, Polyurethane Primer

7

......

TABLE 2. COMPONENTS OF THE PRIMERS EVALUATED

Specification	Binder	Corrosion-Inhibiting Pigments	Solvent
TT-P-664	Phthalic Alkyd	Iron Oxide, Zinc Chromate	Organic
TT-P-1757	Phthalic Alkyd	Zinc Chromate	Organic
MIL-P-23377	Epoxy	Strontium Chromate	Organic
MIL-P-26915	Epoxy	Zinc	Organic
MIL-P 52192	Εροχγ	Iron Oxide, Basic Lead-Silica Chromates	Organic
MIL-P-52995	Phthalic Alkyd	Iron Oxide, Zinc Phosphate, Organo-Zinc Salt	Organic
MIL-P-53022	Ероку	Zinc Phosphate, Organo- Zinc Salt	Organic
MIL-P-53030	Εμοχγ	Iron Oxide, Zinc Phosphate, Organo-Zinc Salt	Water/Organic
MIL-P-85582	Ероху	Barium Chromate	Water/Organic
MIL-P-87112	Polysulfide	Chromates	Organic
MIL-P-XXXXX	Polyurethane	Zinc Chromate	Organic

FLEXIBILITY (FTMS 6226, ASTM D2794, ASTM D1737)

The impact resistance of the primer was measured with both the GE and Gardner instruments. The results are given as the maximum percentage elongation (GE) or inch-pounds of energy (Gardner) that the primer can withstand without cracking. Mandrel-bend tests were conducted over 1/8, 1/4, 1/2, and 1" mandrels. This test was performed at a temperature of -60°F. The smallest mandrel around which the coated panel could be bent without cracking was recorded.

CORROSION RESISTANCE (ASTM B117, ASTM G85, ASTM D2203)

Four sets of primed steel and aluminum panels were scribed in a figure "X" down to bare metal and mounted in 15° racks. Two sets were exposed in a 5% salt-spray cabinet for 1000 hours. Another two sets were exposed in a SO₂/salt-spray cabinet for 400 hours. The panels were then observed for undercutting at the edge of the scribe lines and blistering over the rest of the panel. Filiform tests were conducted only on scribed Alclad aluminum panels that were primed and topcoated with MIL-C-83286 polyurethane topcoat. Two panels for each primer were exposed to 12 <u>N</u> hydrochloric acid vapors for one hour to initiate the corrosion process. Then the panels were thoroughly rinsed with distilled water and placed in a 85% R.H. humidity cabinet for 500 hours at ambient temperature. After this exposure, they were examined for filiform corrosion leading from the scribe lines.

FLUID RESISTANCE

.

The fluid resistance of the primers was evaluated by exposing the coated panels to three types of fluids: hydraulic fluids, lubricating oils, and hydrocarbons. Resistance to hydraulic fluids was determined by immersing the coated panels in specification MIL-H-5606 and MIL-H-83282 hydraulic fluids for 24 hours at 150°F. The primers were then observed for softening or other signs of film degradation. Resistance to iubricating oils was ascertained by immersing the primed panels in MIL-L-23699 lubricating oil for 24 hours at 250°F. Again, the primers were evaluated for film scittening or degradation. Resistance to hydrocarbons was determined by rubbing a cloth rag soaked in methyl ethyl ketone or specification MIL-T-5624, Grade JP-4 aviation fuel back and forth across the surface of the primer about ten times. Complete removal of the coating from the panel represented failure in these tests.

VOLATILE ORGANIC COMPOUNDS CONTENT (ASTM D3960)

The volatile organic compounds (VOC) content of each primer was determined by diluting the material with the recommended thinner to spray viscosity (18 seconds through a Zahn No. 2 cup). The volatile components were then measured, and the results were recorded as the grams of VOC per liter of paint (less water).

RESULTS AND DISCUSSION

The drying-time of the primers evaluated was recorded for both tack-free and dry-hard conditions. These results are listed in Table 3. Tack-free times ranged from 15 minutes to three hours with the majority of materials becoming tack-free in 30 to 45 minutes. Drying-time is a property usually considered during equipment processing. The tack-free time for a primer is generally the minimum period after application before the material can be overcoated with either a sealant or topcost. If the squipment being painted is occupying valuable space in a spray-booth or hangar, shorter tack-free times are desirable.

The dry-hard time is generally the minimum period after application before equipment can be handled without risk of easily damaging the costing. The materials tested had dry-hard times ranging

Spray Viscosity	V.)C Gm/1	566	579	581	542	609	608	621	315	325	532	730
Fuel	JP-4 Resistance	SR	۵.	0	۵.	۵.	SR	٩	٩.	٩.	۵.	۵.
Solvent Resistance	M:EK	œ	۵.	٩	٩	Œ	æ	٩	æ	۹.	<u>i</u>	۵.
Lubricating Out	MIL-1 -236 99 (250 ⁰ F)	٩	æ	æ	ø	۵.	S	e.	£	٩	G.	۵.
Hydraul.c Fluios MIL-H-	5606 and MIL-H-83282 150 ⁰ F	م	G.	٩.	٩.	œ	٩	Q.	Q.	٩	٩.	٩
	Mandret Bend (Inch)	1/8	1/2	1/4	Ā	1/4	1/8	1/2	1/8	1/8	1/8	1/8
exibility Te	Reverse	110	40	40	40	8	40	10	30	80	>160	▶160
FIE	Gardner (inIbs.) Direct	120	10	40	40	8	30	30	8	8	×160	×163
	G.F.	8	1.0	1.0	0.5	8	10	10	8	8	40	8
esion esion	alue ST	2.1	2.7	2.6	1.6	6.1	2.7	2.3	2.7	2.3		3.0
Micro Micro	۹۲ ۲	1.2	2.4	51	2.0	2.5	1.7	1.5	2.1	1.7	3.8	2.2
Adhesic hatch	Vorst 08 .ST	56	58	38	58	58	83	28	58	2B	58	28
Cross	Besci 5B AL	58	56	58	58	58	58	58	58	58	58	28
le (Hou.s)	Dry Hard	0.5	0.1	3.0	2.0	6 .0	0.1	2.5	1.25	2.0	80 A	5.0
Drying Tin	Tack Free	0.25	0.5	0.1	0.5	2.0	0.5	1.25	0.75	0.75	3.0	0.1
		TT-P-664	17-9-1757	MIL P-23377	MIL-P-26915	MIL-P-52192	MIL-P-52995	MIL-P-53022	MILP-53030	MIL-P-8:582	MIL-P-87112	One Comporent Urethane Primer

TABLE 3. TEST RESULTS

.

NADC-85029-60

٦

in the second se

1

SH -- Slight Removal

R --- Removed

S - Softened

P - Pass

from 30 minutes for TT P-664 to eight hours for MIL-P-97112. Most coatings were dry-hard in two to four hours. If critical space and time are being wasted while waiting for a primer to dry, a material with a quicker cure is desirable. For example, at many rework facilities, aircraft are stripped of all paints, and corrosion is removed. The aircraft is then cleaned, and a fresh coat of primer is applied for corrosion protection during the rework process (which may last several months). The next step in the process cannot begin until the primer is dry-hard in order to minimize possible damage to the coating.

Adhesion of the primer to military equipment is of great importance. This is especially true when considering the operational environment of the equipment. In many cases, the climate is harsh and demanding (such as on aircraft carrier). Also, the conditions of use are severe. Army and Marine Corps vehicles may be driven off the road through dirt and water. When not in operation, they are frequently walked on or scraped by tools causing mechanical damage to the coating. In areas where the coating has been chipped, the underlying metal is exposed to the environment, and the corrosion process is initiated. Therefore, a durable and adherent film is necessary.

Adhesion was measured by the wet cross-hatch and microknife methods. The results of these tests are listed in Table 3. Cross-hatch results for all primers on the aluminum specimens was 5B, which indicates excellent adhesion. On steel specimens, all primers exhibited 5B adhesion except MIL-P-85582 and MIL-P-53022 (2B) and MIL-P-23377D (3B). Figure 1 illustrates that the latter results are only fair in comparison to a 5B rating. It must also be considered that this test was performed after 24 hours of immersion in water. Therefore, it was influenced by the water resistance of the primers.

Microknife adhesion results ranged from 1.6 to 3.0 on steel and 1.2 to 3.8 on aluminum (the lower numbers indicate better adhesion). This test was performed at ambient conditions. There is no correlation between these and the cross-hatch results. However, the cross-hatch results showed no difference between many of the coatings, while the microknife results indicated fine differences in the adhesive strength of the primers tested. Fcr instance, TT-P-664 and MIL-P-52192 both had a 5B adhesion on aluminum; but TT-P-664 yielded 1.2 in the microknife, and MIL-P-52192 yielded a 2.5, indicating that the former is more adherent. Cross-hatch and microknife results are empirical and should only be used as an indication of the trend of adhesive strengths of the primers tested.

The impact flexibility of the primers on O-temper, alurninum specimens was measured at ambient conditions by two methods: the GE impact test and the Gardner test. The GE impact test indicates the maximum elongation of the coating before cracking occurs. The Gardner test yields the highest impact energy applied to the specimen before the coating cracks. The results of these tests are presented in Table 3. The GE results range from 0.5% for MIL-P-26915 to 60% for the one component, urethane coating. The Gardner results range from 10 inch-pounds to greater than 160 inch-pounds. These results, in some cases, are lower than specified requirements. This is suspected to be due to the surface characteristics of the specimens. However, all of the primers were applied to the same batch of specimens, and the results can be used on a comparative basis. Figure 2 is a graph comparing the results from the two tests. This graph shows some agreement between the two methods. However, there is more variation in the Gardner results. For instance, there are four primers which have a GE impact of 20% elonyation; but the Gardner results on these materials range from 20 to 110 in-lbs, showing a differentiation between materials.

Impact flexibility is necessary if a coating is on a substrate which is often flexed or impacted. As previously mentioned, ground vehicles are frequently impacted with tools and other hard objects. This property indicates the likelihood of the protective coating being damaged by rough handling.

	12	<u> </u>		
	2.43			
		ू. सिंह देव	14.22	
a proget				52
				5
		-		

	I				
-	L-	. :			
			E		のないのない
	-		Ċ		<u>20. 6 6 2 2</u>
	ED.				
	-	-	-		
	Ī			- 1	





MiL-P-23377D 38

MIL-P-53022 28 Figure 1. Comparison of Cross Hatch Test Results

ľ



Figure 2. G.E. Versus Gardner Impact Test Results

Low-temperature (-60°F) flexibility was measured by performing a 180 degree bend over 1/8, 1/4, 1/2, and 1 inch mandrels with primed, O-temper, aluminum specimens. Table 3 lists the smallest mandrel on which the coated specimen could be bent without cracking. MIL-P-26915 failed over all the mandrels. MIL-P-53022 and TT-P-1757 passed the 1/2 inch mandrel, while MIL-P-20377D passed the 1/4 inch mandrel. All other primers passed the 1/8 inch mandrel. This is an indication of how these primers will perform when ' tixed at low temperatures. Aircraft are exposed to such temperatures during high-altitude flight

The results for the fluid resistance tests appear in Table 3. All eleven primers passed immersion in standard aircraft hydraulic fluids (MIL-H-5606 and MIL-H-83282) at 150°F (66°C). No softening occurred on any of the panels tested, although the one-component, urethane primer and the TT-P-1757 did discolor slightly. Immersion in MIL-L-23699 lubricating oil at 250°F (121°C) softened both MIL-P-52995 and MIL-P-26915 to the point where the coatings could be removed by wiping with a cloth using slight pressure. The MIL-P-26915 was also softened in the vapor phase section of the specimen (exposed above the fluid), such that the coating could be wiped off the panel with slight pressure. Except for some discoloration, all of the other primers were unaffected by the lubricating oil.

The results for the solvent resistance test appear in Table 3. Most of the coatings exhibited good resistance to methyl ethyl ketone (MEK). However, three of the coatings (TT-P-664, MIL-P-52995, and MIL-P-52192) were softened and removed when wiped with a cloth soaked with MEK.

The results for the fuel resistance test appear in Table 3. TT-P-664 and MIL-P-52995 primers had small amounts of the coating removed when wiped with a cloth soaked in JP-4 aviation fuel. The rest of the primers were unaffected.

The fluid resistance, fuel resistance, and solvent resistance tests are designed to test the chemical resistance of a coating. Most of the primers performed well in these tests. MIL-P-52995 failed all three tests and should not be used in any area where chemical resistance is a requirement. TT-P-664 failed both fuel resistance and solvent resistance tests, and MIL-P-52192 failed the solvent resistance test. Therefore, these primers should not be used in areas around fuel tanks where they may be exposed to hydrocarbons. MIL-P-26915 failed the lubricating oil exposure in both the immersed and vapor phase and, therefore, should not be used in any area where lubricating oils are present (such as aircraft engine compartments). Any of the other primers could be used in these tareas, and all of the primers evaluated could be used in areas where hydraulic fluids are present.

The volatile organic compounds (VOC) of the subject primers were measured at standard, airspray viscosity (18 seconds through a Zahn No. 2 cup), and the results appear in Table 3. Most of the primers have a VOC in the range of 525 to 625 grams per liter. The values for MIL-P-53030 and MIL-P-85582 are 315 and 325 grams per liter, respectively. These are low because the two primers are water-borne, while the rest are solvent-borne. The one-component, urethane primer has a VOC of 780 grams per liter.

The VOC of a coating represents the amount of organic vapor emitted to the atmosphere during and after application. Since most organic vapors are hazardous to the environment, their concentration during coating application is often limited. An example of this is South Coast Air Quality Management District Rule 1142 for the Los Angeles area. Water-borne primers or exempt solvents (such as trichloroethane) must be used to meet solvent emission limitations. Where these laws do not exist, any of the primers could be used.

Three corrosion tests were performed during this study: 5% salt-spray, SO₂/salt-spray, and filiform corrosion. Salt-spray and SO₂ tests were performed on both steel and aluminum. Filiform testing was performed only on aluminum. All test specimens were first inspected with the coating intact and then after the coating was chemically removed from the substrate. Similar results were observed on the coated panels and the stripped panels.

The results of the 5% salt-spray tests appear in Figure 3. Steel specimens exposed to 1000 hours of 5% salt-spray are shown in Figures 4 and 5. These results indicate that iron oxide pigment systems generally inhibit corrosion of steel better than other inhibiting systems. Strontium chromate and the zinc phosphate/organo-zinc salt systems also performed well. Coatings with just zinc or zinc chromate inhibitors performed poorly. It should be noted that the inhibitor is only one phase of the corrosion protection of a primer. The resin system provides a physical barrier against the corrosive environment. If the resin cannot withstand the environmental exposure, the coating can fail regardlesss of the pigment system.

Aluminum specimens exposed to 1000 hours of 5% salt-spray appear in Figures 6 (painted) and 7 (stripped). These results show that under salt-spray conditions, chromates provide the best corrosion protection for aluminum, with zinc phosphate and iron oxide systems providing fair protection. Again, this is only true if the resin system can withstand the environmental conditions. It was observed that the zinc pigmented primer (MIL-P-26915) performed well when initially exposed to the salt-spray environment. During this time, white corrosion products (probably zinc oxide) formed on the surface. After 200 hours, these products diminished, indicating a depletion of zinc. During the additional exposure period, corrosion of the substrate occurred.

The final results for the SO₂/salt-spray tests on steel and aluminum specimens were taken after 400 hours of exposure. These results appear in Figure 8, Periodic evaluations of the specimens were performed throughout the test. These evaluations indicated that the specimens which showed signs of corrosion first were the most corroded specimens in the final evaluation. All of the specimens exposed had corrosion in the scribe, indicating the severity of the test conditions. The steel specimens from this test appear in Figures 9 (painted) and 10 (stripped). These results indicate that the zinc phosphate/organo-zinc salt inhibitor system and the iron oxide inhibitor provided the best protection on steel under these conditions. Chromate inhibitors again provided very little protection for steel. The aluminum specimens from the SO2/salt-spray test appear in Figures 11 (painted) and 12 (stripped). These results indicate that the zinc phosphate/organo-zinc salt inhibitor system and the iron oxide inhibitor system and the iron oxide inhibitor provided the best corrosion inhibition on aluminum. Strontium chromate and zinc inhibitors also provided fair protection on aluminum. The rest of the chromate inhibited primers, however, were not very effective in providing protection against the SO₂/salt spray environment. This can be seen dramatically with MIL-P-85582 and MIL-P-87112 primers. These materials provided excellent protection for 1000 hours of regular salt-spray, while both materials performed poorly in less than 400 hours of SO₂/salt-spray exposure.

The results of the filiform corrosion test appear in Figure 13. Filiform corrosion appears as filament-shaped or threadlike corrosion products leading away from the scribe lines. This type of corrosion usually occurs in acidic and humid environments. As these corrosive conditions become more severe, the process can tend to go from filiform to other forms of localized corrosion. Figures 14 (painted) and 15 (stripped) show the filiform test specimens. These results indicate that the chromate inhibitors and zinc provided the best protection against the environment. The zinc phosphate/organo-zinc salt inhibitor system also provided fair protection.



- Excellent: No corrosion in scribe or on the rest of the panel
- Good: Some corrosion in scribe, but no corrosion on the rest of the panel
- Fair: Corrosion in scribe and a few (2-4) spots on the rest of the panel
- Marginal: Corrosion in scribe and roughly a dozen spots over the rest of the panel
- Poor: Heavy corrosion in the scribe and over the rest of the panel

Figure 3. Results for 5% NaCl Salt-Spray Tests

NADC-85029-60

....



Figure 4. Steel Specimens (Painted) From 5% Salt-Spray Test

٦



Figure 5. Steel Panels (Stripped) From 5% Salt-Spray Test

1



Figure 6. Aluminum Panels (Painted) From 5% Salt-Spray Test



Figure 7. Aluminum Panels (Stripped) From 5% Salt-Spray Test



18

2

- Good:
- - Corrosion in the scribe and over less than one-third of the panel Fair:

Corrosion in the scribe and over less than two-thirds, but greater than one-third, of the panel Marginal:

Corrosion in the scribe and over the entire surface of the panel Poor:

Figure 8. Results For SO₂/Selt-Spray Tests



Figure 9. Strial Panel (Psinted) From SO2/Salt-Spray Test

anna a' an**n**a a cuma

1.1

NADC-85029-60

.



Figure 10. Steal Panels (Stripped) From SO2/Salt-Spray Test



Figure 11. Aluminum Panels (Painted) From SO₂/Salt-Spray Test



Figure 12. Aluminum Panels (Stripped) From SO₂/Salt-Spray Test



No corrosion in scribe, no filaments leading away from the scribe, and no corrosicn on the rest of the panel. Excellent:

- Slight corrosion in scribe filaments less than 1/16 inch leading away from the scribe, and no corrosion on the rest of the panel. Good:
- Corrosion in scribe, filaments less than 1/8 inch leading away from the scribe, no corrosion on the rest of the panel. Fair:
- Corrosion in scribe, filaments less than 1/8 inch leading away from the scribe and a few spots of corrosion on the rest of the panel. Marginal:
- Corrosion in scribe, filaments greater than 1/8 inch leading away from the scribe and/or more than a dozen spots of corrosion on the rest of the panel. Poor:

Figure 13. Results For The Filiform Corrosion Test

NADC-85029-60

4..

4



Figure 14. Aluminum Panels (Painted) From Filiform Corrosion Test



Figure 15. Aluminum Panels (Stripped) From Filiform Corrosion Test

1014

ź

ť

Corrosion protection is one of the primary functions of a primer and is, therefore, a property of great importance when selecting a material for a particular application. This selection should be made only after considering the substrate to be protected and the surrounding environment. The application can vary from one piece of equipment to the next. Therefore, a material suited to the particular substrate should be used. Some materials perform better on steel, while others perform better on aluminum. In some cases, both substrates are present; and this requires a material that works well on both. In addition, the severity of the environment dictates the degree of protection that is required. These results are only an indication of the ability of these primers to prevent corrosion. There is little correlation between different corrosion tests, because of the unique conditions of each test. The SO₂/salt-spray test is a better corrosion test for aircraft carrier environments or highly industrialized areas where stack exhaust gases are prevalent. The regular salt-spray test represents general conditions for corrosion. The filiform corrosion test covers highly humid and acidic environments where equipment could be susceptible to this type of corrosion.

SUMMARY

The objective of this investigation was to evaluate various primers available for military equipment and provide comparative performance information to designers and engineers who specify and apply these materials. The eleven primers evaluated varied in performance from poor to excellent in corrosion protection, flexibility, adhesion, and chemical resistance. The corrosion resistance and adhesion varied between steel and aluminum substrates. In addition, these materials differed in composition (affecting not only physical properties but, also, application and cure).

Military equipment is constructed of various materials and is subjected to a wide variety of operational environments. The designer must consider these operational factors when specifying a coating system. He also must consider the application environment and scenario. The information provided in this report can then be used to determine the most effective primer for the intended use. By this process, equipment operational readiness and life-times can be increased.

ACKNOWLEDGEMENT

The authors wish to acknowledge the efforts of Mr. William J. Green for his assistance in performing the tests in this study.

Ľ¢.

DISTRIBUTION LIST

Sec. 1

REPORT NO. NADC-85029-60

AIRTASK NO. AIR-310-310A/001B/4F61-542-000 Work Unit ZM540

No. of Copies

and the California California

NAVAIR (AIR-31A)	1
(AIR-5304)	2
(AIR-5304C)	1
(AIR-004D4)	2
NAVAIREWORKFAC, NAC, Alameda (Code 340)	1
Jacksonville (Code 340)	1
Norfolk (Code 340)	1
North Island (Code 340)	1
Pensacola (Code 340)	i
MCAS, Cherry Point (Code 340)	i
COMNAVAIRLANT (Code 528)	1
COMNAVAIRPAC (Code 7421)	1
DTIC	12
NAVAIRDEVCEN (Code 8131)	3