



MICROCOPY RESOLUTION TEST CHART NATIONAL BUREAU OF STANDARDS-1963-A



AD-A159 760

OFFICE OF NAVAL RESEARCH

Contract N00014-84-K-0534

Technical Report No. 2

Complex Molecular Motions in Bulk Hard Segment

Polyurethanes - A Deuterium NMR Study

by

A. Kintanar and L. W. Jelinski AT&T Bell Laboratories Murray Hill, NJ 07974

and

I. Gancarz and J. T. Koberstein Department of Chemical Engineering Princeton University Princeton, NJ 08544

September 30, 1985

Reproduction in whole or in part is permitted for any purpose of the United States Government

This document has been approved for public release and sale; its distribution is unlimited



THE FILE COPY

	REPORT DOCUMENTAT	ION PAGE	READ INSTRUCTIONS BEFORE COMPLETING FORM
-	REPORT NUMBER	2. GOVT ACCESSION NO.	3 RECIPIENT'S CATALOG NUMBER
	2	100 A18976	
-	· · · · · · · · · · · · · · · · · · ·	HD-1913 / 180	
	TITLE (and Sublitle)	Bulk Hard	S IT THE OF REPORT & PERIOD CC.EF
	Complex Molecular Molions In	torium NMP Study	Technical Report
	Segment Polyurethanes - A Det	lerium wik study	
			5 PERFORMING ORG. REPORT NUMELS
	AUTHOR/a,		S. CONTRACT OR GRANT NUMBER 4
	A. Kintanar, L. W. Jelinski,	I. Gancarz,	N00014-84-K-0534
	J. T. Koberstein	-	N00014-04-K 0554
-	PERFORMING ORGANIZATION NAME AND ADD	RESS	10 PROGRAM ELEMENT PROJECT TAS
	Polymer Materials Program		AREA & WORK UNIT NUMBERS
	Department of Chemical Engine	ering	
	Princeton University, Princet	ton, NJ 08544	
	CONTROL UNG OFFICE NAME AND ADDDDT		
	Denortmont of the Name		September 30, 1985
	Department of the Navy		
	UIIICE OI Naval Kesearch		I S NUMBER OF PAGES
_	ATTINGTON, VITGINIA 22217	Hereni from Controlling Olice	15 SECURITY CLASS (of the second
	INCLUSION NOTICE NAME & PDURESSIN BI	neren noa. Controlling Office;	unclassified
			154. DECLASSIFICATION DOWNGRADING
			SCHEDULE
	Distribution Unlimited	tered in Block 20, if dillerent fro	m Report)
	Distribution Unlimited	tered in Block 20, if different fro	æ Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES	tered in Block 20, if different fro	sen Report)
-	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Meanonalogulos	tered in Block 20, if different fro	ign Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules	tered in Block 20, if different fro	m Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the ebstreet en SUPPLEMENTARY NOTES Submitted to Macromolecules	tered in Block 20, if dillerent fro	m Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde 11 necess)	tered in Block 20, if different fro	m Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse aids II necess) Polyurethanes	lered in Block 20, il dillerent fro any and identify by block number) Deuterium NMR	m Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde 11 necess) Polyurethanes Microphase Separation	tered in Block 20, 11 dillerent fro ary and identify by block number) Deuterium NMR Hard Segments	m Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde II necess) Polyurethanes Microphase Separation	tered in Block 20, if different fro ary and identify by block number) Deuterium NMR Hard Segments	m Repor:)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse olde 11 noccess) Polyurethanes Microphase Separation	er, end identify by block number) Deuterium NMR Hard Segments	næ Repor:)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde 11 necess) Polyurethanes Microphase Separation	itered in Block 20, if different fro ary and identify by block number) Deuterium NMR Hard Segments	m Report)
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde 11 necessor Polyurethanes Microphase Separation ABSTRACT (Continue on reverse olde 11 necessor Solid state deuterium NMR spe	iered in Block 20, if different fro ary and identify by block number) Deuterium NMR Hard Segments	o characterize molecular
	Distribution Unlimited DISTRIBUTION STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse olde II necess) Polyurethanes Microphase Separation ABSTRACT (Continue on reverse olde II necess) Solid state deuterium NMR spe tion in two enecifically dout	tered in Block 20, if different fro any and identify by block number) Deuterium NMR Hard Segments iny and identify by block number) sctroscopy is used t erated polyurethane	o characterize molecular hard segment polymers. Th
000	Distribution Unlimited DISTRIBUTION STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde if necessor Polyurethanes Microphase Separation ABSTRACT (Continue on reverse olde if necessor Solid state deuterium NMR spe tion in two specifically deut hyperbanes consist of 4 41-d	ery and identify by block number) Deuterium NMR Hard Segments my and identify by block number) sctroscopy is used t erated polyurethane diphenylmethane diis	o characterize molecular hard segment polymers. Th ocvanate (MDI) chain extend
000	Distribution Unlimited DISTRIBUTION STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde 11 necessor Polyurethanes Microphase Separation ABSTRACT (Continue on reverse olde 11 necessor Solid state deuterium NMR spe tion in two specifically deut lyurethanes consist of 4,4'-d th [2, 2, 3, 3-d,] buttonedic] (B	ary and identify by block number) Deuterium NMR Hard Segments ctroscopy is used t erated polyurethane diphenylmethane diis DO), and 2.4 toluen	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain
0001	Distribution Unlimited Distribution STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde 11 necessor Polyurethanes Microphase Separation ABSTRACT (Continue on reverse olde 11 necessor Solid state deuterium NMR spe tion in two specifically deut lyurethanes consist of 4,4'-d th [2,2,3,3-d4] butanediol (B tended with [2,2,3,2-d4] butanediol (B	ary and identify by block number) Deuterium NMR Hard Segments inv and identify by block number) ctroscopy is used t erated polyurethane liphenylmethane diis DO), and 2,4 toluen inedial Lineshape	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain and relaxation (T ₂) data we
	Distribution Unlimited DISTRIBUTION STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse olde 11 nocessed Polyurethanes Microphase Separation ABSTRACT (Continue on reverse olde 11 nocessed Solid state deuterium NMR spe tion in two specifically deut lyurethanes consist of 4,4'-d th [2,2,3,3-d4] butanediol (B tended with [2,2,3,3-d4] buta	ary and identify by block number) Deuterium NMR Hard Segments inv and identify by block number) sctroscopy is used t erated polyurethane liphenylmethane diis 3DO), and 2,4 toluen inediol. Lineshape	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain and relaxation (T ₁) data we
000 1 x b	Distribution Unlimited Distribution STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse olde 11 nocessed Polyurethanes Microphase Separation ABSTRACT (Continue on reverse olde 11 nocessed Solid state deuterium NMR spe tion in two specifically deut lyurethanes consist of 4,4'-d th [2,2,3,3-d4] butanediol (B tended with [2,2,3,3-d4] buta tained as a function of tempe	ary and identify by block number) Deuterium NMR Hard Segments inv and identify by block number) ctroscopy is used t erated polyurethane liphenylmethane diis 3DO), and 2,4 toluen anediol. Lineshape erature. The result	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain and relaxation (T ₁) data we s indicate a broad distribu
	Distribution Unlimited DISTRIBUTION STATEMENT (of the observed on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse ende 11 necessor Polyurethanes Microphase Separation ABSTRACT (Continue on reverse ende 11 necessor Solid state deuterium NMR spe tion in two specifically deut lyurethanes consist of 4,4'-d th [2,2,3,3-d4] butanediol (B tended with [2,2,3,3-d4] buta tained as a function of tempe on of motional correlation ti	ary and identify by block number) Deuterium NMR Hard Segments hy and identify by block number) ctroscopy is used t erated polyurethane diphenylmethane diis DO), and 2,4 toluen inediol. Lineshape erature. The result mes, in both materi	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain and relaxation (T ₁) data we s indicate a broad distribu als. In the semicrystallin
ooixbi	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde II necess) Polyurethanes Microphase Separation ABSTRACT (Continue on reverse orde II necess) Solid state deuterium NMR spetion in two specifically deut lyurethanes consist of 4,4'-d th [2,2,3,3-d4] butanediol (B tended with [2,2,3,3-d4] buta tained as a function of tempe on of motional correlation ti	ary and identify by block number) Deuterium NMR Hard Segments iny and identify by block number) ectroscopy is used t erated polyurethane liphenylmethane diis 500), and 2,4 toluen mediol. Lineshape erature. The result mes, in both materi	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain and relaxation (T ₁) data we s indicate a broad distribu als. In the semicrystallin
	Distribution Unlimited DISTRIBUTION STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde if necessor Polyurethanes Microphase Separation ABSTRACT (Continue on reverse ofde if necessor Solid state deuterium NMR spe tion in two specifically deut lyurethanes consist of 4,4'-d th [2,2,3,3-d4] butanediol (B tended with [2,2,3,3-d4] buta tained as a function of tempe on of motional correlation ti	ary and identify by block number) Deuterium NMR Hard Segments inv and identify by block number) ctroscopy is used t erated polyurethane diphenylmethane diis bDO), and 2,4 toluen inediol. Lineshape erature. The result mes, in both materi	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain and relaxation (T ₁) data we s indicate a broad distribu als. In the semicrystallin
	Distribution Unlimited Distribution STATEMENT (of the obstract on SUPPLEMENTARY NOTES Submitted to Macromolecules KEY WORDS (Continue on reverse orde 11 necesson Polyurethanes Microphase Separation ABSTRACT (Continue on reverse orde 11 necesson Microphase Separation ABSTRACT (Continue on reverse orde 11 necesson Solid state deuterium NMR spetion in two specifically deut lyurethanes consist of 4,4'-d th [2,2,3,3-d4] butanediol (B tended with [2,2,3,3-d4] buta tained as a function of tempe on of motional correlation ti FORM, 1473 EDITION O ' NOV 65 IS C S. N C102- * 6601	ary and identify by block number) Deuterium NMR Hard Segments inv and identify by block number) sctroscopy is used t erated polyurethane diphenylmethane diis 3DO), and 2,4 toluen inediol. Lineshape erature. The result mes, in both materi DESOLETE SECURITY CLA	o characterize molecular hard segment polymers. Th ocyanate (MDI) chain extend e diisocyanate (TDI) chain and relaxation (T ₁) data we s indicate a broad distribu als. In the semicrystallin

LUNHITY CLASSIFICATION OF THIS PAGE/When Date Entered)

MDI-BDO polymer, the distribution divides cleanly into two components that are attributable to the crystalline and amorphous regions of the material. In the TDI-BDO polymer, there is only a single broad distribution in keeping with the completely amorphous nature of this material. The results also show that the predominant large-scale motion of the alkyl chain is a gauche-trans conformational hop. The central methylene carbons of the butanediol undergo librations about their equilibrium positions, in addition to the large scale conformational transitions. Above $\sim 60^{\circ}$ C, additional larger-scale diffusion of the entire butanediol moiety occurs within a cone of semiangle $\sim 15^{\circ}$. The results are consistent with the existence of kinked conformations in the alkyl chain of this material.

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Complex Molecular Motions in Bulk Hard Segment Polyurethanes - A Deuterium NMR Study

> Agustin Kintanar Lynn W. Jelinski

AT&T Bell Laboratories Murray Hill, NJ 07974

Irena Gancarz Jeffrey T. Koberstein

Department of Chemical Engineering Princeton University Princeton, NJ 08544



Solid state deuterium NMR spectroscopy is used to characterize molecular motion in two specifically deuterated polyurethane hard segment polymers. The polyurethanes consist of 4,4'-diphenylmethane diisocyanate (MDI) chain extended with [2,2,3,3-d₄] butanediol (BDO), and 2,4 toluene diisocyanate (TDI) chain extended with $[2,2,3,3-d_4]$ butanediol. Lineshape and relaxation (\tilde{T}_1) data were obtained as a function of temperature. The results indicate a broad distribution of motional correlation times, in both materials. In the semicrystalline MDI-BDO polymer, the distribution divides cleanly into two components that are attributable to the crystalline and amorphous regions of the material. In the TDI-BDO polymer, there is only a single broad distribution in keeping with the completely amorphous nature of this material. The results also show that the predominant large-scale motion of the alkyl chain is a gauche-trans conformational hop. The central methylene carbons of the butanediol undergo librations about their equilibrium positions, in addition to the large scale conformational transitions. Above -60 °C, additional larger-scale diffusion of the entire butanediol moiety occurs within a cone of semiangle -15° . The results are consistent with the existence of kinked conformations in the alkyl chain of this material.

ABSTRACT

The morphology and physical properties of polyurethane block copolymers have been areas of considerable interest for at least 20 years. Studies of these thermoplastic elastomers have focussed primarily on the microphase separation of the hard and soft segments into domains, to which the unique properties of these materials may be directly ascribed.

We have recently demonstrated the viability of solid state deuterium (^{2}H) NMR as a technique for evaluating phase separation and phase mixing in polyurethanes,¹ and in another segmented copolymer system, the Hytrel copolyesters.^{2,3} The NMR method is based on differential segmental mobilities of ²H-labeled moieties in the hard and soft domains and at the domain interfaces.

Solid state ²H NMR is a powerful tool for characterizing molecular motion in polymers.^{4,5} In a rigid lattice powder, where the orientation of a selected C-D bond is random and the motions of this bond are slow on the ²H NMR timescale ($\tau_c \ge 10^{-3}$ sec), the ²H NMR spectrum consists of a Pake doublet that has a quadrupole splitting, $\Delta \nu_Q$, of ~128 kHz. The broad spectrum arises from the interaction of the quadrupole moment of the deuteron and the electric field gradient around the nucleus. The electric field gradient tensor is axially symmetric, and has its maximal component along the C-D bond axis. Because of this, the interpretation of ²H NMR lineshapes in the presence of motion is straightforward. The spectra are sensitive to the nature of the motion (e.g. diffusive or discrete hops), the geometry of the motion, and the correlation time of the motion when the correlation time is in the intermediate exchange regime $(10^{-7} \text{ s} < \tau_c < 10^{-4} \text{ s}).^{4.5}$ Therefore, temperature-dependent solid state ²H NMR spectra can provide information concerning the rate, angular range, and nature of the motion. It is clear that information of this type is essential to obtaining a precise correlation of polymer molecular structure and observed macroscopic properties.

-] -

We report here results of a ²H NMR study of molecular motion in two polyurethanes consisting entirely of hard segments. The materials are 4,4'- diphenylmethane diisocyanate (MDI) chain extended with $[2,2,3,3-d_4]$ butanediol (BDO); and 2,4-toluene diisocyanate (TDI) chain extended with $[2,2,3,3-d_4]$ butanediol. The structures are shown below.









The deuterium label is located only on the center methylene carbons of the butanediol residues, and thus our study probes local motions in the vicinity of the label. Earlier studies of poly(butylene terephthalate), which contains the same labeled butanediol moiety, have shown that the predominant motion of the alkyl segment is of a three-bond type resulting in a fast gauche-trans conformational reorientation of the interior methylenes.^{2,6,7} These studies further showed that the terephthalate residues are moving slowly on the ²H

NMR timescale.

In this paper we address the details of molecular motion of the butanediol portion of the polyurethane hard segment. Such experiments are relevant in view of recent SAXS studies on segmented polyurethanes by Koberstein and co-workers.^{8,9} Their experiments suggest that the hard segments exist in kinked conformations, and that the hard segment chains are able to fold back on themselves in the solid state, thereby filling space efficiently. The kinks would likely be located at the butanediol moiety which is the most flexible portion of the hard segment chain.

Furthermore, Dumais et al.¹ have used deuterium NMR spectra of the MDI-BDO material as a control sample for observing and quantifying the interfacial hard segments in a series of polyurethane copolymers containing 70, 60, and 50 wt% MDI-BDO hard segment. They observed that the all-hard segment material exhibits a motionally averaged deuterium NMR lineshape at room temperature, and it was assumed that the molecular motions of the all-hard segment material are similar to those of the hard segment-rich microdomains in the copolymers. However, the details of the hard segment motion were not investigated.

Here we provide experimental data that bear on the following questions related to molecular motion of the butanediol portion of the polyurethane hard segments: (1) What are the predominant modes of molecular motion of the alkyl residues? (2) Are these motions characterized by a single correlation time, or rather by a distribution of characteristic frequencies? (3) How do the dynamics of the butanediol residues in MDI-BDO and TDI-BDO compare? and (4) Are these results consistent with the proposed model of a kinked conformation for the butanediol group?

EXPERIMENTAL SECTION

Sample: The selectively labeled hard segment polyurethane samples were prepared in THF solution according to literature methods,¹⁰ using [2,2,3,3-d₄] butanediol (Merck) as the starting diol and the appropriate diisocyanate (MDI or TDI). The polymer was characterized by DSC measurements, and by solution state ²H NMR spectroscopy.

The DSC measurements of the MDI-BDO sample (heating rate 20°C/min) reveal a small high temperature endotherm at ~213°C which is due to melting of the crystalline component.¹¹ We did not observe a clear glass transition temperature, although this has been reported to be 109°C.¹² The TDI-BDO polymer is known to have a T_e of 101°C.¹²

NMR Measurements: Solution state ²H NMR analyses were performed on both Varian XL-200 and JEOL GX-500 spectrometers. The samples were dissolved in DMSO and spectra were obtained both at room temperature and at 90°C. The results attest to the integrity of the labeling pattern and indicate a number average degree of polymerization of \sim 20 for MDI-BDO and \sim 22 for TDI-BDO.

Solid state ²H NMR spectra were obtained on a home-built spectrometer operating at 8.5 Tesla, corresponding to a ²H resonance frequency of 55.26 MHz. The spectrometer has been described previously.² The sample temperature was regulated by using either a heated air flow or a liquid nitrogen boil-off system. The temperature was measured next to the sample by means of a digital thermometer (Omega 2176A) equipped with a copper-constantan thermocouple. Temperatures are considered accurate and stable to $\pm 1^{\circ}$ C.

Spectra were obtained in quadrature using the quadrupolar echo pulse sequence $(90_{\pm x} - \tau_1 - 90_y - \tau_2)$,¹³ or some variation thereof.¹⁴ The 90° pulse width was typically 3.3 μ sec. 4K data points were collected with a digitization rate of 100 nsec/point. Unless specified otherwise, the delay between the quadrupole pulse pair was set at 30 μ sec, which

- 4 -

was ample time for the probe and receiver to recover after the pulses.

Variations of the quadrupole echo pulse sequence were used for spin-lattice relaxation time determinations and for selective observation of a fast (short T_1) component. The amorphous quadrupole echo pulse sequence¹⁴ was used for progressive saturation T_1 measurements and for selectively observing the fast component. This sequence consists of a train of 90° pulses to saturate the entire spin system, followed by a delay (t_a) , followed by the quadrupole echo pulse pair. The delay (t_a) was varied over several orders of magnitude for the progressive saturation T_1 experiments; and was set at 100 msec ($-5 \times T_1$ of the fast component), otherwise. The amorphous inversion-recovery quadrupole echo pulse sequence¹⁴ was used to measure the spin-lattice relaxation time of the short T_1 component. The pulse sequence consists of a saturating train of 90° pulses, followed by a delay to allow the magnetization of the rapidly relaxing amorphous component to recover, followed by a 180° pulse to invert the fast component magnetization, followed by a variable delay, followed by the quadrupole echo pulse pair.

Data Analysis: Typically 12-20 points were obtained for either progressive saturation or inversion recovery relaxation experiments. Data out to 100 msec $(5 \times T_1 \text{ of fast}$ component) were reasonably linear and were analyzed with a non-linear three-parameter fit routine on a Nicolet 1180E computer system, using the NMC program. In some cases linearity was checked by casting the inversion-recovery data in semi-log form. The intensity at each delay time was obtained from the height of the echo, or from integration of the entire lineshape. The results obtained by either method were the same, within experimental error.

The total equilibrium ²H NMR spectral intensity data were corrected for the variation of the probe signal intensity response with temperature. The probe response was calibrated by obtaining a fixed number of scans on a sample of L-d3 Alamine under equilibrium conditions at a variety of temperatures.

Calculated solid state ²H NMR spectra were obtained according to the methods described by Mehring.¹⁵ The calculated spectra have been corrected for the effects of pulse power fall-off,¹⁶ and for the effects of motions that occur during the quadrupole echo delay time.¹⁷

RESULTS

²H NMR Spectra of MDI-BDO The ²H NMR spectra of the bulk MDI-BDO polymer reflect a very broad distribution of motional correlation times at all temperatures observed $(-59^{\circ}C \text{ to } +95^{\circ}C)$. This is clearly demonstrated in Figure 1, where we show spectra obtained using the amorphous quadrupole echo pulse sequence at several representative temperatures. The top row of lineshapes was obtained with an equilibrium delay time of 2-4 s between the saturating pulse train and the quadrupole echo pulse pair. From separate progressive saturation spin-lattice relaxation time (T_1) experiments (see below), we estimate that we are observing approximately 90% of the deuterons in the MDI-BDO sample at an equilibrium delay time of 2 s at room temperature.

In the second row, we show spectra that were obtained also using the amorphous quadrupole echo pulse sequence, except that the delay between the saturating pulses and the observe pulses is shortened to 100 ms (160 ms for the -45° C spectrum). These lineshapes are plotted on the same vertical scale as the corresponding top row spectra, and it is apparent that there is a considerable loss of intensity due to the saturation of deuterons with relatively long T_1 values. Integration of these spectra shows that at room temperature and above (data up to 123°C, spectrum not shown), approximately 70% of the deuterons contribute to the short T_1 component. At -2° C, the short T_1 component has only -64%

- 6 -

of the intensity of the equilibrium recycle spectrum; and at -45° C, this value has decreased to -48%. The relative intensity data are listed in Table 1. We note that the total intensity (obtained by integration of the spectra, top row, Figure 1) remains approximately constant from -2° to 73° . We observe only a slight decrease in total intensity at 123^{\circ}.

Subtraction of the middle row spectra from the corresponding top row spectra affords the lineshapes of the long T_1 component. These difference spectra are shown in the bottom row. The lineshape at -45°C can be fit to a calculated rigid-lattice Pake doublet with a quadrupole splitting, $\Delta \nu_Q$, of 125 kHz. The difference spectra at -2°C, and 22°C fit somewhat less well to a rigid-lattice pattern, as there is too much intensity at the center of the experimental lineshape, especially at the higher temperature. As the temperature is increased further, to 55° and 73°C, the center of the static-like powder patterns (Figure 1, bottom row) continue to fill in (giving rise to a flat-topped spectrum at 73°C) while the overall breadth at half-height remains the same. This kind of behavior is observed when the methylene groups undergo gauche-trans conformational transitions (such that the C-D bonds hop between two sites separated by a projected (Newman) angle of ~120°) at a rate that is intermediate on the NMR timescale $(10^{-4} s > \tau_c > 10^{-7} s)$.^{2,15} A projected Newman angle of 120° corresponds to a dihedral (jump) angle between sites of ~109°.

Motion of the Fast Component of MDI-BDO: In Figure 2 we show ²H NMR spectra of the fast component only, obtained using the amorphous quadrupole echo pulse sequence with a delay of 100 milliseconds, at various temperatures. The lineshapes indicate that the motionally averaged electric field gradient tensor is axially asymmetric, suggesting that the motional process leading to collapse of the static powder pattern has two-fold symmetry.^{2,15,18} Furthermore, the overall breadth of the room temperature spectrum is ~120 kHz; which implies that the proposed two-fold hopping motion involves a C-D bond

- 7 -

Figure 4. Solid state ²H NMR spectra (55.26 MHz) of the hard segment TDI-BDO polymer obtained using the amorphous quadrupole echo pulse sequence. Top row. Spectra obtained with an equilibrium delay time of 2-4 sec after the saturating pulse train. Middle row: Spectra obtained with a delay time of 100-160 msec. Bottom row: Difference spectra of the equilibrium and fast recycle lineshapes. Spectra within a column (a-e) were obtained at the same temperature. The experimental temperatures are (a) -53, (b) -6, (c) 22, (d) 40, and (e) 77°C.

Figure 5. Plot of the total equilibrium ²H NMR spectral intensity (obtained by integration of the lineshapes) versus the temperature. (a) MDI-BDO, (b) TDI-BDO. The intensity data were corrected for the signal intensity response of the probe as described in the text.

Figure 6. Representative ²H NMR spin-lattice relaxation data of TDI-BDO. (a) Semilogarithmic plot of the magnetization recovery versus the delay time showing the nonexponential nature of the data. The progressive saturation data were obtained using the amorphous quadrupole echo pulse sequence at 22°C. The amorphous delay time was varied from 1 msec to 2 sec, by which time magnetization recovery was complete. (b) Arrhenius plot of the natural logarithm of the spin-lattice relaxation time (of the short T_1 component) versus the reciprocal of the absolute temperature. The data were obtained using the amorphous inversion-recovery quadrupole echo pulse sequence with a 100-160 msec delay after the saturating pulse train.

FIGURE CAPTIONS

Figure 1. Solid state ²H NMR spectra (55.26 MHz) of the hard segment MDI-BDO polymer obtained using the amorphous quadrupole echo pulse sequence. Top row: Spectra obtained with an equilibrium delay time of 2-4 sec after the saturating "comb" of pulses. Middle row: Spectra obtained with a delay time of 100-160 asec. Bottom row: Difference spectra of the equilibrium and fast recycle spectra. Spectra within a column (a-e) were obtained at the same temperature. The experimental temperatures are (a) -45, (b) -2, (c) 22, (d) 55, and (e) 73°C.

Figure 2. Experimental (a-d) and calculated (e-h) solid state ²H NMR spectra of the short T_1 component of the MDI-BDO polymer. Spectra (a-d) were obtained with the amorphous quadrupole echo pulse sequence with an amorphous delay time, t_a of 100 msec at 22, 42, 62, and 83°C, respectively. Spectra (e-h) were calculated as described in the text using quadrupole splittings 120, 118, 107, and 105 kHz respectively.

Figure 3. Representative ²H NMR spin-lattice relaxation data of MDI-BDO. (a) Semilogarithmic plot of the magnetization recovery versus the delay time showing the non-exponential and biphasic nature of the data. The progressive saturation data were obtained using the amorphous quadrupole echo pulse sequence at 22°C. The amorphous delay time was varied from 1 msec to 8 sec, by which time magnetization recovery was complete. (b) Arrhenius plot of the natural logarithm of the spin-lattice relaxation time (of the short T_1 component) versus the reciprocal of the absolute temperature. The data were obtained using the amorphous inversion-recovery quadrupole echo pulse sequence with a 100-160 msec delay after the saturation pulses. at rates very much faster than in the crystalline domain and in the fast limit of the ²H NMR timescale ($\tau_c < 10^{-7} sec$).

The ²H NMR spectra of the amorphous component (obtained with a short delay time) are consistent with the occurrence of gauche-trans conformational transitions as the major motional mode. The motion consists of hops of the C-D bonds between two equally populated sites separated by a dihedral angle of ~114: Observation of this motional mode is consistent with the existence of kinked conformations of the alkyl segment in MDI-BDO and TDI-BDO. Low-amplitude high frequency librations of the methylene groups about their equilibrium position may also occur to account for the small observed narrowing of the quadrupole splitting from the rigid lattice value. This motional model is consistent with the observed magnitude of the T_1 minimum in the amorphous component of MDI-BDO, which indicates that more than one motional mode is contributing to relaxation.

Above $\sim 60^{\circ}$ C, we observe further significant narrowing of the ²H NMR lineshapes which indicates the onset of an additional mode of motion. This motion is modeled by diffusion of the butanediol chain within a cone of small semiangle (10-20[°]). The amplitude of the diffusion and thus the semiangle of the cone is assumed to increase with increasing temperature.

Finally, in the amorphous TDI-BDO polymer we observe the onset of large scale translational motion at rates greater than $10^5 sec^{-1}$ at -20° C above the glass transition temperature ($T_g \sim 41^{\circ}$ C), which results in a decrease in intensity of the quadropole echo.

refocussing results in a scrambling of the quadropole interaction that each spin "sees". Therefore, refocussing is incomplete and we see echoes with reduced intensity. The spectral intensity decreases with increasing temperature because as the motion speeds up, there is an increased probability that more portions of the polymer chain move and therefore more spins are "scrambled".

SUMMARY

These ²H NMR results show the existence of a broad distribution of motional correlation times in the hard segment (butanediol-labeled) polyurethane polymers. In semicrystalline MDI-BDO, the distribution is divided into two major components corresponding to crystalline and amorphous regions of the polymer. In the crystalline region, the C-D bonds may be considered static on the ²H NMR timescale at room temperature. However, relaxation data indicate that there are high frequency librational motions of the labeled methylene groups in these relatively rigid domains. The motional constraints in the crystalline region are not easily relaxed at higher temperatures and the distribution shifts only slowly to higher frequencies with increasing temperature.

In the amorphous regions of MDI-BDO and in the amorphous polymer TDI-BDO, there is a broad range of motional correlation times extending over 5 orders of magnitude. Motion in these domains is considerably faster than in the crystalline domains at room temperature. The correlation times range from $\sim 10^{-5} sec$ to $10^{-9} sec$. The constraints responsible for the distribution of motion in the amorphous domains is likely differences in local packing density. These constraints vary readily with temperature so that the distribution moves easily to lower or higher frequencies of motion. Thus at -50° C, some of the deuterons in the amorphous region are moving as slowly as those in the crystalline regions; while at about 70°C, most of the deuterons in the amorphous domain are moving There is indirect IR spectroscopy evidence that the butanediol chain diffusion occurs at elevated temperatures in MDI-BDO polyurethane.^{23,24} The evidence consists of quantification of the free and hydrogen-bonded NH groups and is based on their different vibrational frequencies and extinction coefficients. The results reveal an increase in the amount of free NH groups starting at about 75°C. Large-amplitude diffusion of the butanediol moiety would require disruption of the hydrogen bonds of the NH groups on one chain with the oxygen atoms on the ester groups of adjacent chains. A recent communication has questioned the validity of these IR experiments, however, noting that the IR lineshape changes may be accounted for by frequency shifts and reduction of the extinction coefficient to a change in the "strength" of the hydrogen bond. It is clear, however, that the stretching of hydrogen bonds due to the proposed diffusion of the butanediol chain in a cone would be expected to modulate the IR properties of the NH region.

Translational Motion in TDI-BDO Above T_g We now address the large decrease in absolute ²H NMR spectral intensity that we observe in the TDI-BDO material above its glass transition temperature. This intensity decrease is likely due to the onset of translational motions of the polymer chain.

An understanding of this effect requires a more thorough understanding of the quadrupole echo sequence. During the first RF pulse, the spin magnetization is tilted away from alignment with the static field (B_o) until it is in a plane perpendicular to B_o . After the pulse, the magnetization precesses in the plane under the influence of the quadropolar interaction. Since every spin "sees" interactions with different magnitudes, the spins dephase. The second RF pulse causes the dephasing to change direction and the spins refocus to form an echo. Translational motion that occurs while the spins are dephasing or

transition of the labeled methylene group. In Fig. 7a, we show in a Newman projection (down the center bond of the butanediol moiety) how this motion occurs. As diagrammed, this motion requires a large-scale reorientation of the ends of the polymer chain which would be energetically unfavorable. Several motional models involving cooperative motion about several bonds have been proposed that avoid this situation. Two of the models, involving motion about three bonds are shown schematically in Fig. 7b. These motions have been shown to occur in poly(butylene terephthalate).^{2,6} Similar motions probably occur in these polyurethane systems as well.

The observed gauche-trans conformational transitions in these polyurethanes are quite similar to those observed in poly(butylene terephthalate). There are, however, some important differences. The spectra we observe here are best fit to a calculated lineshape obtained with a dihedral angle of $\sim 114^{\circ}$; as opposed to the 102° angle that was reported for poly(butylene terephthalate).² We note that there is some uncertainty in the determination of this angle in the present study because of the broad distribution of motional correlation times (vide supra). Moreover, the conformational hops occur at a much faster rate in the polyurethane system than in poly(butylene terephthalate). The present results indicate that the average correlation time for this motional process is in the fast exchange limit above $-2^{\circ}C$. In poly(butylene terephthalate) the fast exchange limit for this motional process occurs at $\sim 85^{\circ}C$. Furthermore, the results for poly(butylene terephthalate) indicate a much narrower distribution of correlation times than what we observe here for MDI-BDO and TDI-BDO.

The most obvious difference between the two systems is the presence of fast butanediol chain diffusion which occurs in the polyurethane hard segment polymers, and results in significantly narrowed spectra at high temperature. The ²H NMR spectra of poly(butylene terephthalate) up to 85°C suggest that little such motion is occuring in this polymer.²

- 16 -

have different lineshapes; again indicating that even in the fast recycle spectra, not all the deuterons are moving at rates in the fast limit of the ²H NMR timescale.¹⁷

The distribution in the characteristic frequencies of motion of the labeled methylene groups in the amorphous regime of the polymer are likely due to variation in the local packing density due to the irregular packing of the polymer in these domains. Alternatively, or in addition to the above reasons, the slower components in the distribution may be attributed to butanediol residues that are in constrained conformations because they are the sites of twists and turns of the polymer chain. We note, however, that the observed broad range of motional correlation times probably represents distributions in the characteristic frequencies of several motional modes (e.g. a large-amplitude two-fold hop and a small-angle vibration). Finally, we note that the constraints resulting in the broad range of correlation times in the amorphous region relax readily with temperature, permitting a facile shift of the entire distribution of motion to higher frequencies.

Details of Molecular Motion in the Fast Component: The ²H NMR spectra of the fast (amorphous) component of the MDI-BDO and TDI-BDO polymer are consistent with the occurrence of gauche-trans isomerization in the butanediol moiety. Librations of the methylene groups are superimposed on this motion, and at high temperatures, diffusion of the entire butanediol chain may also occur.

This motional model is supported by the T_1 data. The magnitude of the T_1 minimum (~20 msec) of the amorphous component in MDI-BDO suggest that more than one motion contributes to relaxation, since we would expect a much higher or lower T_1 value at the minimum if one process were dominant.²²

The predominant motion affecting lineshapes is the large-amplitude two-fold hop of the labeled methylene groups. The motion results from a gauche-trans conformational

explained by the fact that MDI-BDO is semicrystalline while TDI-BDO is completely amorphous. The slower moving deuterons with long T_1 values observed in the MDI-BDO material are likely located in the crystalline domains. In these domains, the packing is ordered and consequently denser, making the large amplitude (two-fold hop) motion less likely to occur. The existence of crystalline regions in MDI-BDO also explains the constant long T_1 component (30%) that is observed over a wide range of temperatures. At low temperatures $(-40^{\circ}C)$ dueterons in both the crystalline and amorphous domain MDI-BDO contribute to the long T_1 component as the motions are slow in both regions. At higher temperatures ($\sim 20^{\circ}$ C), the motional constraints in the amorphous regions are readily relaxed so that essentially all the deutron in this domain contribute to the fast recycle spectrum. However, deuterons in the crystalline domains are still packed tightly and therefore move slowly and contribute to the long T_1 component. Our relative intensity results indicate that our MDI-BDO sample is $\sim 30\%$ crystalline. Although it is difficult to obtain reliable quantitative results from our DSC measurements, 30% crystallinity is not inconsistent with these results. Moreover, it is well known that crystallinity of 30% can be routinely obtained in MDI-BDO.¹¹

It is clear that even in amorphous domains of these polymers, there is a very broad distribution of motional correlation times. This is demonstrated most clearly by the ²H NMR lineshapes of TDI-BDO (Fig. 4). From the lineshapes and the T_1 data, we estimate that the distribution of motional correlation times in the amorphous regions of MDI-BDO and TDI-BDO spans some five orders of magnitude. Even at high temperatures, when the deuterons in the amorphous regions contribute only to the fast recycle (short T_1) spectra, there is still a distribution of motions. This is evident in the imperfections of the fit of the calculated spectra to a single correlation time model. Moreover, ²H NMR spectra obtained with different delays between pulses (not shown)

- 54

temperatures at which intensity losses are not a problem.) In these experiments, the magnetization recovery was reasonably linear up to the longest delay time used (100-160 msec, $\sim 4 \times T_1$). The results are shown in an Arrhenius plot in Fig. 6b. The T_1 data are summarized in Table 2. Note that the T_1 values of the fast component in TDI-BDO and MDI-BDO are quite similar. Thus, in addition to the similarity in the types of motion of the fast component in both polymers, the rates of motion are quite similar as well.

DISCUSSION

Nature of the Distribution of Motional Correlations Times in MDI-BDO and TDI-BDO; The evidence presented in the previous section clearly indicates that there is a broad distribution of motional correlation times in both MDI-BDO and TDI-BDO. The nature of the distribution in the two polymers is quite different, however. First, there are slower motions occurring in MDI-BDO than in TDI-BDO. The spin-lattice relaxation indicate that there are deuterons with much longer T_1 values in MDI-BDO than in TDI-BDO. Second, the distribution of motion in MDI-BDO divides clearly into two major components, while that of TDI-BDO does not. This is indicated by the relative intensities of the equilibrium and fast recycle spectra (Fig. 1, Fig. 4, and Table 1). At low temperatures, both polymer systems have -50% of the deuterons contributing to the short T_1 component. As the temperature is increased, the percentage of deuterons contributing to the fast component increases on both systems. At room temperature the relative intensity in the short T_1 component starts to plateau at 70% in the MDI-BDO system, and remains at this value even above the glass transition. In the TDI-BDO system, however, the relative intensity of the fast recycle spectra increases monotonically to a value of 100% at about 60°C.

The differences in the distribution of motion in the two polymers can readily be

- 13 -

distribution, the butanediol residues undergo the same type of motion in TDI-BDO and MDI-BDO. That is, the predominant motion is a two-fold hop between sites of equal probability separated by a dihedral angle of $\sim 114^{\circ}$. The average correlation time of this motion is in the fast limit of the ²H NMR timescale ($r_c \leq 10^{-7} sec$) above 20°C. Superimposed on the large amplitude motion is a small-amplitude libration of the methylene groups which accounts for the observed motionally narrowed breadth of these spectra (~ 120 kHz) from the rigid-lattice value. The additional narrowing of the spectrum at 77°C is attributed both to larger amplitude librations of the methylene groups about their equilibrium positions and to diffusion of the entire butanediol chain within a narrow cone of semiangle $\sim 10^{\circ}$.²⁰

We also note that the variation of the total spectral intensity with temperature (obtained by integration of the equilibrium delay spectra) appears markedly different in the TDI-BDO polymer than in the MDI-BDO material. This is shown graphically in Fig. 5. It appears that the large scale motions that occur above T_g prevent proper refocussing of the quadrupole echo signal, leading to marked reductions in echo amplitude.

Spin-Lattice Relaxation Times of TDI-BDO: Further evidence that there is a broad distribution of correlation times is provided by progressive saturation T_1 results obtained at room temperature, using a variable delay that spanned some four decades (2 sec to 1 msec). The data, shown in Fig. 6a, clearly describes a nonexponential recovery. There are deuterons in some environments that take up to 1 sec to relax, whereas a good proportion of deuterons are fully relaxed by 100 msec. In contrast, progressive saturation data obtained at 60°C (not shown) indicate that all deuterons obtain equilibrium in 200 msec and the nonexponential nature of the magnetization recovery is not as evident.

We have also obtained T_1 results of the fast component only using the amorphous inversion-recovery quadrupole echo pulse sequence at -55, -17, and 23°C. (These are

short T_1 component increases monotonically until ~20°C above the glass transition when essentially 100% of the deutrons are observed with a delay time of 100 msec. This is in sharp contrast to the behavior of the MDI-BDO material where the fraction of deutrons contributing to the short T_1 component was constant at ~70% from 20° to 73°C.

In the bottom row, we show difference spectra of the corresponding top and middle row lineshapes. These difference spectra represent the lineshapes of the long T_1 component of the distribution. At -53 °C, the spectrum fits reasonably well to a rigid lattice Pake doublet with a quadrupole splitting $\Delta v_Q \sim 125$ kHz. As the temperature is increased, the center of the pattern fills in to give a nearly flat-topped spectrum at 22 °C. AT 77 °C, there is essentially no intensity in the difference spectrum as nearly all the deuterons have very short T_1 values and relax within 100 msec. The overall pattern of change in the difference lineshapes is similar to that of the MDI-BDO polymer, although the changes occur at lower temperatures for the TDI-BDO material. This suggests that as in the MDI-BDO material, the predominant motion of the butanediol residues in TDI-BDO is a two-fold hop between sites separated by a dihedral angle of ~ 114 °C, consistent with a gauche-trans conformational transition of the interior methylenes.

This interpretation is supported by the lineshapes of the short T_1 component (Fig. 4, middle row), obtained with a delay time of 100 msec (160 msec for the -53°C spectrum). At -53°C, the spectrum is nearly flat-topped but retains nearly the same spectral breadth (~120 kHz). As the temperature is increased, the center of the pattern becomes dome-like, indicating that the average rate of the large-amplitude two-fold hop is in the fast limit of the ²H NMR timescale $(\tau_c \leq 10^{-7} sec)$. At the highest temperature (77°C), the spectrum narrows significantly so that the breadth at half-height is ~110 kHz. The ²H NMR spectra of the fast T_1 component in TDI-BDO and MDI-BDO are very similar. In fact at ~20° and ~40°C, the lineshapes from the two materials are virtually identical and fit reasonably well to the same calculated spectrum (Fig. 4 middle row and Fig. 2a,b). Thus, at least at these temperature, and for the fast component of the We have obtained very precise T_1 measurements of the fast component, at a variety of temperatures using the amorphous inversion-recovery quadrupole echo pulse sequence.¹⁴ These experiments represent the rapidly decaying portion of the magnetization recovery curve; which data is reasonably linear out to 100 msec. The T_1 values are summarized in an Arrhenius plot in Figure 3b. The plot shows a T_1 minimum at ~45°C. Since the T_1 minimum occurs when $\omega_0 \tau_c \sim 1$, this suggests that there are motions occuring with an average correlation time of ~2 nsec at this temperature. A number of motional modes could contribute to the efficient spin lattice relaxation. The calculated spectra at this temperature (*vide supra*) require both the large scale conformational transition and a lower-amplitude libration for adequate simulation. The T_1 data are summarized in Table 2.

²*H NMR Spectra of TDI-BDO*: The ²*H NMR spectra of the TDI-BDO polymer also reveals a* broad distribution of correlation times at temperatures from -55° C to 40°C (the glass transition temperature). This is demonstrated in Fig. 4 where we show spectra of TDI-BDO obtained using the amorphous quadrupole echo pulse sequence at several representative temperatures. The top row of lineshapes was obtained with an equilibrium delay time of 2 sec (4 sec for the -53° C spectrum) between the saturating pulse train and the quadrupole echo pulse pair. Separate progressive saturation spin-lattice relaxation time (T_1) experiments (*vide infra*), indicate that we are observing all the deutrons in TDI-BDO with this delay time at room temperature. In the second row, we show lineshapes obtained using the same pulse sequence except the delay time is shortened to 100 ms (160 ms for the -53° C spectrum). These spectra are plotted on the same vertical scale as the top row lineshapes, and as we observed for MDI-BDO polymer, there is again a loss in intensity at the shorter delay time because of saturation of deuterons with long spin-lattice relaxation times. The relative intensity of the short T_1 component is obtained by integration of the top and middle row spectra and the results are summarized in Table 1. The fraction of deuterons contributing to the

- 10 -

The respective calculated spectra were obtained by including a fast, small-amplitude diffusion of the butanediol chain in addition to the aforementioned gauche-trans conformational hops and small-angle librations of the methyle ∞ . The first and third motional modes cause a reduction in the breadth of the spectrum, while the second motional mode affects mainly the lineshape. We obtain reasonably good agreement between the observed and calculated spectra at 62° and 83°C if we assume that the butanediol moiety is diffusing within a cone whose semi-angle increases with increasing temperature, and that the C-D bond hops between two equally populated sites with a dihedral angle of 114°; via a gauche-trans conformational transition. We require cone angles of \sim 12° and \sim 16° to adequately fit the spectra at 62°C and 83°C, respectively (Figure 2c and 2d).²¹

We now consider the lineshapes of the fast component at reduced temperatures. These spectra have already been shown in the middle row of Figure 1a and b. The lineshape at $-2^{\circ}C$ is essentially identical to the room temperature spectrum, indicating that the deuterons contributing to this component are undergoing motion in the fast limit at $-2^{\circ}C$. At $-45^{\circ}C$, however, the pattern has a characteristic flat top; suggesting that the hopping motion has a correlation time in the intermediate exchange regime.

Spin Lattice Relaxation Times of MDI-BDO: Further evidence that there is a broad distribution of motional correlation times in the MDI-BDO material is provided by progressive saturation T_1 results obtained at several temperatures, using a variable delay that spanned some 5 decades (10 sec to 100 μ sec). Representative data are shown in Figure 3a. In all cases, we were unable to adequately fit the entire magnetization recovery curves either to a single or a double exponential decay, even thought the curves appear to be biphasic.

- 9 -

reorientation with a dihedral (jump) angle of $\sim 109^{\circ}$. Such a lineshape can arise from a gauche-trans conformational transition.^{18,19}

Concentrating first on a simulation of the room temperature experimental spectrum, we varied the dihedral (jump) angle from 102° to 118°, and allowed the correlation time to go from the intermediate exchange regime to the rapid motion limit ($r_c \leq 10^{-8}$ s). We assumed a quadrupole splitting of 120 kHz which we determined from the breadth at half height of the spectrum. This decrease from the rigid lattice value of 125 kHz is expected to arise from a fast libration of the methylene groups about their equilibrium positions. (We use *libration* to indicate a low-amplitude, high-frequency molecular motion.) These librational motions consist of a small torsional oscillation ($\pm 10^{\circ}$) of the methylene group about a C-C bond. Using this single correlation time, single angle model, the best calculated lineshape is obtained with a jump angle of $\sim 114^{\circ}$ with a correlation time in the rapid motion limit. Similar conditions obtain for the spectrum is good, given the simplicity of the model. However, note that the simulated spectrum has a small dip in the center and the shoulders are too narrow near the top. These imperfections are attributed to distributions in the frequencies of motion (*vide infra*).

We now address the lineshapes obtained at elevated temperatures. The lineshape obtained at 42°C (Figure 2b) is essentially identical to the room temperature spectrum except for a slight narrowing of \sim 2 kHz. At 62°C, however, we observe further significant narrowing of the overall breadth of the pattern; which becomes even more pronounced at 83°C where the breadth (at half height) of the spectrum is only \sim 105 kHz. This additional narrowing is attributed both to increasingly larger-amplitude librations of the methylene groups about their equilibrium position.²⁰

Figure 7. Schematic representation of mechanisms for trans-gauche conformational transitions in the butanediol residues of MDI-BDO or TDI-BDO. (a) Newman projection showing a discrete isomerization about the central bond in the alkyl moiety. (b) Helfand-type models of motion about three bonds, involving gauche migration $(tt_g^{\pm} \rightleftharpoons g^{\pm}tt)$ and pair-gauche production $(ttt \rightleftharpoons g^{\pm}t_g^{\mp})$.

TABLE 1

Percent of Polyurethane Samples Observed by Different NMR Pulse Delays

MDI-BDO			TDI-BDO		
Temperature (°C)	% in Rapid Motion ^a	% in Slow Motion ^b	Temperature (°C)	% in Rapid Motion ²	% in Slow Motion ^b
-45	48 ^c ,e	52 ^d ,e	-53	48 ^c ,e	52 ^d ,e
-2	64 ^ſ	365	-6	69	31
22	69	31 ^d	22	79	21
55	70	30	40	84	16
73	71	29	78	95	5
123	67	33	93	100	0

(a) Measured with the amorphous quadrupole echo pulse sequence, $t_a = 100$ ms except as noted, estimated uncertainity $\pm 2\%$.

(b) Obtained by difference methods. Quadrupole delay time $t_a = 2$ s, unless noted otherwise.

(c) $t_a = 160 \text{ ms}$

(*d*) $t_a = 4 \text{ s}$

(e) Estimated uncertainty $\pm 8\%$.

(f) Estimated uncertainty $\pm 4\%$.

TABLE 2

MDI-BDO			TDI-BDO		
Temperature (°C)	T ₁ Fast Component (ms) ^b	T ₁ Slow Component (ms) ^c	Temperature (°C)	T ₁ Fast Component (ms) ^b	T ₁ Slow Component (ms) ^c
-32	39		-53	49	
-3	23				
22		2000	-7	28	
23	19.4		22		200
42	18.3		23	21	
62	19.3		40		60
75		900			
83	20.7				

Spin Lattice Relaxation Times^a for Polyurethane Hard Segments

(a) Measured at 55.26 MHz for deuterium.

(b) Measured by inversion-recovery.

(c) Measured by progressive-saturation. Estimated uncertainty $\pm 20\%$.

REFERENCES and NOTES

- Dumais, J. J.; Jelinski, L. W.; Leung, L. M.; Gancarz, I.; Galambos, A.; Koberstein, J. T. Macromolecules 1985, 18, 116.
- 2. Jelinski, L. W.; Dumais, J. J.; Engel, A. K. Macromolecules 1983, 16, 492.
- 3. Jelinski, L. W.; Dumais, J. J.; Engel, A. K. ACS Symposium Series 1984, 247, 55.
- 4. Spiess, H. W. Colloid Polym. Sci. 1983, 261, 193.
- 5. Torchia, D. A. Annu. Rev. Biophys. Bioeng. 1984, 13, 125.
- 6. Jelinski, L. W.; Dumais, J. J.; Engel, A. K. Macromolecules 1983, 16, 403.
- Jelinski, L. W.; Dumais, J. J.; Watnick, P. I.; Engel, A. K.; Sefcik, M. D. Macromolecules 1983, 16, 409.
- 8. Koberstein, J. T.; Stein, R. S. J. Polym. Sci. Polym. Phys. Ed. 1983, 21, 1439.
- 9. Leung, L. M.; Koberstein, J. T. J. Polym. Sci. Polym. Phys. Ed. 298X, XX, 0000.
- 10. Lyman, D. J. J. Polym. Sci. 1960, 45, 49.
- 11. Kajiyama, T.; MacKnight, W. J. Polym. J. 1970, 1, 548.
- Schneider, N. S.; Sung, C. S. P.; Matton, R. W.; Illinger, J. L. Macromolecules 1985, 8, 62.
- Davis, J. H.; Jeffrey, K. R.; Bloom, M.; Valic, M. I.; Higgs, T. P. Chem Phys. Lett. 1976, 42, 390.
- Cholli, A. L.; Dumais, J. J.; Engel, A. K.; Jelinski, L. W. Macromolecules 1984, 17, 2399.

- Mehring, M. "High Resolution NMR in Solids", 2nd ed.; Springer-Verlag; New York, 1983.
- 16. Bloom, M.; Davis, J. H.; Valic, M. I. Can. J. Phys. 1980, 58, 1510.
- 17. Spiess, H. W.; Sillescu, H. J. Magn. Reson. 1981, 42, 381.
- Huang, T. H.; Skarjune, R. P.; Wittebort, R. J.; Griffin, R. G.; Oldfield, E. J. Am. Chem. Soc. 1980, 102, 7377.
- 19. Rosenke, K.; Sillescu, H.; Spiess, H. W. Polymer 1980, 21, 757.
- 20. It is theoretically possible to account for the observed decrease in quadrupole splitting at high temperature by a model of only large amplitude ($\sim \pm 30^{\circ}$) librations of the methylene groups about their equilibrium position. Such a model, however, introduces additional asymmetry into the electric field gradient tensor and results in a lineshape substantially different from that observed experimentally.
- 21. We assume that the rigid lattice quadrupole splitting (125 kHz) was reduced to -120 kHz by librations of the methylene group about their equilibrium positions. The quadrupole splittings were further narrowed by assuming a libration of the entire butanediol chain within a cone of semi-angle θ_L . The reduction factor is given by $(3 \cos^2 \theta_L 1)/2$.
- 22. We have calculated the spin-lattice relaxation time versus the correlation time for a two-fold jump motional model using the expression of Torchia and Szabo.²⁵ For a gauche-trans conformational transformation, we expect a T_1 value of 5 msec at the minimum ($\tau_c \sim 2$ nsec). For a low-amplitude ($\pm 10^\circ$) libration, the predicted T_1 at the minimum is 33 msec. Contributions to relaxation by other motions would decrease the observed T_1 value. Since we observe a minimum T_1 of ~ 20 msec

(42°C), we conclude that fast librations are the dominant motional mode for relaxation at this temperature, with significant contributions from fast $(\tau_c \sim 5 \times 10^{-8} \text{ sec})$ gauche-trans conformational hops.

- 23. MacKnight, W. J.; Yang, M. J. Polym. Sci. 1973, Symposium No. 42, 817.
- 24. Seymour, R. W.; Cooper, S. L. Macromolecules 1973, 6, 48.
- 25. Torchia, D. A.; Szabo, A. J. Magn. Reson. 1982, 49, 107.
- 26. Coleman, M. M.; Skrovanek, D. J.; Howe, S. E.; Painter, P. C. Macromolecules 1985, 18, 299.





1

......

Figure 2



• •

Figure 3



. . .



Figure 5



 $D \xrightarrow{CH_2O^{-}}_{D} \xrightarrow{D}_{D} \xrightarrow{CH_2O^{-}}_{D} \xrightarrow{CH_2O^{-}}_{D}$

.



می از مراجع از می از می







.

- -

-

.

• •



Figure 7

DL/413/83/01 GEN/413-2

TECHNICAL REPORT DISTRIBUTION LIST, GEN

<u>(</u>	No. Copies		No. Copies
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Douda Naval Weapons Support Center Code 5042 Crane, Indiana 47522	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 2770	1 9
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 1911	1 2
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory	1		

Washington, D.C. 20375

Report Documentation page

DL/413/83/01 356A/413-2

ABSTRACTS DISTRIBUTION LIST, 356A

Naval Surface Weapons Center Attn: Dr. J. M. Augl, Dr. B. Hartman White Oak Silver Spring, Maryland 20910

Professor Hatsuo Ishida Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106

Dr. Robert E. Cohen Chemical Engineering Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139

Dr. R. S. Porter Department of Polymer Science and Engineering University of Massachusetts Amherst, Massachusetts 01002

Professor A. Heeger Department of Chemistry University of California Santa Barbara, California 93106

Dr. T. J. Reinhart, Jr., Chief Nonmetallic Materials Division Department of the Air Force Air Force Materials Laboratory (AFSC) Wright-Patterson AFB, Ohio 45433

Professor J. Lando Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106

Professor C. Chung Department of Materials Engineering Rensselaer Polytechnic Institute Troy, New York 12181

Professor J. T. Koberstein Department of Chemical Engineering Princeton University Princeton, New Jersey 08544 Professor J. K. Gillham Department of Chemistry Princeton University Princeton, New Jersey 08540

Professor R. S. Roe Department of Materials Science and Metallurgical Engineering University of Cincinnati Cincinnati, Ohio 45221

Professor L. H. Sperling Department of Chemical Engineering Lehigh University Bethlehem, Pennsylvania 18015

Professor Brian Newman Department of Mechanics and Materials Science Rutgers University Piscataway, New Jersey 08854

Dr. C. E. Hoyle Department of Polymer Science University of Southern Mississippi Hattiesburg, Mississippi 39406

Dr. Stuart L. Cooper Department of Chemical Engineering University of Wisconsin Madison, Wisconsin 53706

Professor D. Grubb Department of Materials Science and Engineering Cornell University Ithaca, New York 14853

Dr. D. B. Cotts SRI International 333 Ravenswood Avenue Menlo Park, California 94205

PLASTEC DRSMC-SCM-O(D), Bldg 351 N Armament Research & Development Center Dover, New Jersey 07801

DL/413/83/01 356A/413-2

.

ABSTRACTS DISTRIBUTION LIST, 356A

Professor C. H. Wang Department of Chemistry University of Utah Salt Lake City, Utah 84112

Professor J. H. Magill Department of Metallurgical and Materials Engineering University of Pittsburgh Pittsburgh, Pennsylvania 15261

Professor F. Rodriguez Department of Chemical Engineering Cornell University Ithaca, New York 14853



11-85

DTIC