


AD-A162 285 CONGRUENT VAPORIZATION IN THE V-SI SYSTEM AS STUDIED BY 1/1  
HIGH TEMPERATURE. (U) STATE UNIV OF NEW YORK AT  
BINGHAMTON DEPT OF CHEMISTRY C E MYERS ET AL.  
UNCLASSIFIED 26 NOV 85 TR-4 N00014-82-K-0501 F/G 7/4 NL





MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

12

UNCLASSIFIED

SECURITY CLASSIFICATION OF

REPORT DOCUMENTATION PAGE

AD-A162 285

2d. DECLASSIFICATION/DOWNGRADING SCHEDULE		1b. RESTRICTIVE MARKINGS	
4. PERFORMING ORGANIZATION REPORT NUMBER(S) TR-4		3. DISTRIBUTION/AVAILABILITY STATEMENT Unlimited	
6a. NAME OF PERFORMING ORGANIZATION C.E. Myers, Chem. Dept., State Univ. of NY, Univ. Ctr., at Binghamton		7a. NAME OF MONITORING ORGANIZATION Office of Naval Research	
6b. OFFICE SYMBOL (if applicable)		7b. ADDRESS (City, State, and ZIP Code) 800 North Quincy Street Arlington, VA 22217	
6c. ADDRESS (City, State, and ZIP Code) Binghamton, NY 13901		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-81-K-0501	
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Same as 7a		10. SOURCE OF FUNDING NUMBERS	
8b. OFFICE SYMBOL (if applicable)		PROGRAM ELEMENT NO.	PROJECT NO.
8c. ADDRESS (City, State, and ZIP Code) Same as 7B		TASK NO. NR625-827	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) Congruent Vaporization in the V-Si System as Studied by High Temperature Knudsen Cell Mass Spectrometry			
12. PERSONAL AUTHOR(S) Clifford E. Myers and Robert J. Kematick			
13a. TYPE OF REPORT Technical	13b. TIME COVERED FROM TO	14. DATE OF REPORT (Year, Month, Day) November 26, 1985	15. PAGE COUNT 5
16. SUPPLEMENTARY NOTATION Proceedings, 33rd Annual Conference on Mass Spectrometry and Allied Topics, American Association for Mass Spectrometry, San Diego, CA May 26-31, 1985			
17. COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	Vanadium silicides, V <sub>3</sub> Si, V <sub>5</sub> Si <sub>3</sub> , vaporization behavior, vaporization thermodynamics activities, free energy of formation, enthalpy of formation, congruent vaporization, Knudsen effusion, mass spectrometry.	
19. ABSTRACT (Continue on reverse if necessary and identify by block number)			
<p>The vaporization behavior of vanadium silicides has been investigated by Knudsen cell mass spectrometry in the temperature range 1800-2000K. It was demonstrated that at about 1900-2000K the congruently vaporizing composition is within the V<sub>3</sub>Si single phase region. Thermodynamic activities relative to the solid elements were obtained by direct comparison. Free energies and enthalpies of phase formation for V<sub>3</sub>Si(s) and V<sub>5</sub>Si<sub>3</sub>(s) were calculated from the experimental data and were found to be in good agreement with data obtained elsewhere.</p>			
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS		21. ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED	
22a. NAME OF RESPONSIBLE INDIVIDUAL		22b. TELEPHONE (Include Area Code)	22c. OFFICE SYMBOL

This report has been approved for public release and sale; its distribution is unlimited.

DTIC FILE COPY

DTIC ELECTED  
DEC 10 1985

OFFICE OF NAVAL RESEARCH  
Contract N00014-82-K-0501  
TECHNICAL REPORT NO. 4

CONGRUENT VAPORIZATION IN THE V-Si SYSTEM AS STUDIED BY  
HIGH TEMPERATURE KNUDSEN CELL MASS SPECTROMETRY

by

Clifford E. Myers and Robert J. Kematick  
Department of Chemistry  
State University of New York  
University Center at Binghamton  
Binghamton, NY 13901

Prepared for Publication

in

Proceedings, 33rd Annual Conference on Mass Spectrometry  
and Allied Topics

American Association for Mass Spectrometry  
San Diego, CA  
May 26-31, 1985

November 26, 1985

Accession For	
NTIS	<input checked="" type="checkbox"/>
DTIC	<input checked="" type="checkbox"/>
Unannounced	<input checked="" type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A1	

Reproduction in whole or in part is permitted for  
any purpose of the United States Government

\*This document has been approved for public release  
and sale; its distribution is unlimited.



85 12 -9 070

CONGRUENT VAPORIZATION IN THE V-Si SYSTEM AS STUDIED BY  
HIGH TEMPERATURE KNUDSEN CELL MASS SPECTROMETRY\*

Clifford E. Myers and Robert J. Kematick  
Department of Chemistry  
State University of New York at Binghamton  
Binghamton, NY 13901

The vanadium silicides are of interest as corrosion resistant materials and for their potential applications in the electronics industry. In addition, their cohesive energies may be used, together with those of other silicides and related compounds, to assess factors affecting the strengths of chemical bonds in these compounds. The compounds in the V-Si system (1) are  $V_3Si$ ,  $V_5Si_3$ ,  $V_6Si_5$ , and  $VSi_2$ . Of these, only  $V_3Si$  has any significant range of homogeneity;  $V_6Si_5$  is only stable above about 1160K (2). Several authors (1,3,4,5) have reviewed critically the published thermochemical data for the system. These reviews do not include a recent study (2) which employed Knudsen cell-mass spectrometry. One result of this last work was a plot of log activity vs composition (activities relative to the respective pure solid elements) for both V and Si at 1650K. The activities of V and Si were observed to cross within the  $V_5Si_3$  phase region which, in consideration of the vapor pressures of pure V and Si at this temperature, led to the tentative conclusion that  $V_5Si_3$  vaporized congruently (i.e. vapor and condensed phase have same composition). The goal of the present work was to test this conclusion.

EXPERIMENTAL

The samples were prepared by arc melting weighed mixtures of the elements and were characterized by X-ray powder diffraction.

Selected residues were analyzed by wet chemical techniques, and these results agreed closely with the compositions inferred from the original weights of V and Si. The mass spectrometer used was a 90° sector, single focusing, high resolution magnetic deflection instrument manufactured by Nuclide Corporation. The sample was placed in a tungsten metal cup within a tungsten metal effusion cell which was heated by radiation from a tungsten helix resistance heating element. The entire furnace assembly was surrounded by tungsten and tantalum radiation shields within a water cooled vacuum enclosure. Temperatures were measured with a tungsten-rhenium thermocouple inserted into the base of the effusion cell; the thermocouple was calibrated by means of an optical pyrometer sighted through the orifice into the interior of the effusion cell. The design of the mass spectrometer was such that the molecular beam from the effusion cell, the path of the ionizing electrons, and the ion beam were all mutually perpendicular. Silicon signals were obtained with ionizing electron energies of 12.5 eV in order to minimize the effects of the mass 28 background. An ionizing energy of 30.0 eV was used for the vanadium data.

## RESULTS

Thermodynamic activities relative to the pure solid elements were obtained as follows. The partial pressure of a species in a Knudsen cell-mass spectrometry experiment is proportional to  $IT$ , where  $I$  is the ion current due to that species and  $T$  is the temperature of the effusing vapor. Hence the thermodynamic activity of a species in the sample is given by  $a = I/I^0$ , where  $I$

is measured for the element above the sample and  $I^\circ$  is measured above the pure element under the same experimental conditions of temperature, orifice area, and electron energy (2). Although  $I$  and  $I^\circ$  are measured in different experiments, the mass spectrometer is sufficiently stable that reproducible results are obtained. In practice, activities at a given temperature were calculated from slopes and intercepts of  $\log IT$  and  $\log I^\circ T$  vs  $1/T$  plots. The activities at a given composition and temperature were used to calculate the free energies of phase formation:

$$(1-x)V(s) + xSi(s) = V_{1-x}Si_x(s)$$

$$\Delta G_f^\circ/R = 2.303 T \log a_V^{(1-x)} a_{Si}^x$$

where  $x$  is the atom fraction of Si. Entropy and heat capacity data for the silicides cited or estimated by Smith (1) were used, together with Smith's data (6) for  $V$  and data from the JANAF Tables (7), to calculate  $\Delta G_f^\circ/R$  as a function of temperature and  $\Delta H_f^\circ, 298.15/R$  from the experimental data. As shown in Table 1, agreement with the results of the earlier mass spectrometric study (2) is quite good. Samples richer in Si than  $V_5Si_3$  were found preferentially to lose Si and samples richer in V than  $V_3Si$  were found preferentially to lose V. Hence there is at least one congruently vaporizing composition in the  $V_3Si$ - $V_5Si_3$  composition range. The results from X-ray powder diffraction were ambiguous in that it was very difficult to identify lines attributable to  $V_3Si$ , even in samples which were well within the  $V_3Si$ - $V_5Si_3$  two-phase region. However, wet chemical analysis before and after vaporization of a significant fraction (19-58%) showed clearly that, at about 1900-2000K, there is only one congruently vaporizing composition which is within the  $V_3Si$  single-phase

region. The precise composition is difficult to fix since, near the congruently vaporizing composition, the partial pressures of V and Si differ only very slightly from those at congruency. Hence, to reach congruency it is necessary to vaporize a major fraction of the sample. It should be noted that this congruent vaporization is for effusion conditions. Hence partial pressures differ from those under static conditions since Si effuses more rapidly than V. It is not yet clear whether the congruently vaporizing composition under static conditions lies within  $V_3Si$  or  $V_5Si_3$ .

#### REFERENCES

1. J. F. Smith, Bull. Alloy Phase Diagrams, 2, 42 (1981).
2. E. K. Storms and C. E. Myers, High Temp. Science, in press.
3. T. G. Chart, Natl. Phys. Lab. (UK) Rep. 18 (1972).
4. T. G. Chart, High Temp. High Press., 5, 241 (1973).
5. P. F. Freund and K. E. Spear, J. Less-Common Met., 60, 185 (1978).
6. J. F. Smith, Bull. Alloy Phase Diagrams, 2, 40 (1981).
7. D. R. Stull and H. Prophet, NSRDS-NBS No. 37 (1971).

\*Supported in part by the U. S. Office of Naval Research.



TABLE 1  
THERMODYNAMIC DATA FOR VANADIUM SILICIDES

	$\Delta G_f^0, 1650K/R$ (kK)	
1/4 $V_3Si$	3.63	Si and V activities (22 a/o Si)
	4.35	Si and V activities, $V_5Si_3 + V_3Si$
	4.40	Storms and Myers (2), $V_5Si_3 + V_3Si$
1/8 $V_5Si_3$	5.49	Si and V activities, $V_5Si_3 + V_3Si$
	5.47	Storms and Myers (2), $V_5Si_3 + V_3Si$
	$\Delta H_f^0, 298.15/R$ (kK)	
1/4 $V_3Si$	5.35	Si and V activities, $V_5Si_3 + V_3Si$
	5.40	Storms and Myers (2), $V_5Si_3 + V_3Si$
	5.18	Smith (1)
1/8 $V_5Si_3$	6.33	Si and V activities, $V_5Si_3 + V_3Si$
	6.31	Storms and Myers (2), $V_5Si_3 + V_3Si$
	6.47	Smith (1)

**END**

**FILMED**

*1-86*

**DTIC**