



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

2

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER ARO 18537.1-CH	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER	
4. TITLE (and Subtitle) Dynamic Orientation Studies of Polymers		5. TYPE OF REPORT & PERIOD COVERED FINAL 81-10 01 thru 84-09-30	
		6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) Richard S. Stein		8. CONTRACT OR GRANT NUMBER(s) DAA29-82-K-0010	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Polymer Research Institute LGRC, Rm. 701, University of Massachusetts Amherst, MA 01003		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS	
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Army Research Office Post Office Box 12211 Research Triangle Park, NC 27709		12. REPORT DATE 86-02-03	
		13. NUMBER OF PAGES Five	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified	
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) NA			
18. SUPPLEMENTARY NOTES The view, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) polymer, dynamic, orientation, small angle x-ray scattering, x-ray diffraction, light scattering, small angle neutron scattering, birefringence, infrared dichroism, crystalline polymers, polyethylene			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Static and dynamic x-ray diffraction, small angle x-ray scattering, small angle light scattering, birefringence, and infrared dichroism studies have been carried out on crystalline polymers (mostly polyethylenes) and their blends. Preliminary small angle neutron scattering studies of their orientation have been made.			

DTIC
SELECTED
FEB 25 1986
S D D

AD-A164 611

DTIC FILE COPY

THE VIEW, OPINIONS AND/OR FINDINGS CONTAINED IN THIS REPORT ARE
THOSE OF THE AUTHOR AND SHOULD NOT BE CONSTRUED AS AN OFFICIAL
DEPARTMENT OF THE ARMY POSITION, POLICY OR DECISION, UNLESS SO
DESIGNATED BY OTHER DOCUMENTATION.

86 2 24 145

DYNAMIC ORIENTATION STUDIES OF POLYMERS

FINAL REPORT

Richard S. Stein

February 2, 1986

U.S. ARMY RESEARCH OFFICE

CONTRACT: SAA29-82-K0010

UNIVERSITY OF MASSACHUSETTS

APPROVED FOR PUBLIC RELEASE
DISTRIBUTION UNLIMITED

INTRODUCTION

The purpose of this investigation was to carry out dynamic wide angle x-ray diffraction (WAXD), small angle x-ray scattering (SAXS), dynamic birefringence, dynamic small angle light scattering (SALS), and dynamic infrared dichroism (IRD) on various types of polyethylene and their blends. These goals were accomplished and have led to several important research publications, as described below.

SUMMARY

The technique of dynamic small angle x-ray scattering was developed in which the x-ray scattering could be observed as a sample was subjected to oscillatory strain. This was done, using a stroboscopic signal averaging type technique, at the National Center for Small Angle Scattering Research at the Oak Ridge National Laboratory. It was possible to observe the dynamic opening and closing of voids as well as the orientation of crystalline lamellae.

Wide angle x-ray diffraction was used to study crystal orientation of radiation crosslinked polyethylene samples which were crystallized from the oriented melt. At low melt orientations, the a-crystal axis was found to orient parallel to the stretch direction, whereas with increasing melt orientation, one progressed to a state of c-axis orientation. A degree of crosslinking - melt orientation superposition principle was discovered in which corresponding states of crystal orientation occurred at corresponding states of melt orientation. Morphological transitions of these samples were studied using the small angle light scattering technique.

The use of the two-dimensional optical multichannel analyzer (OMA) was developed for the quantitative studies of SALS during crystallization and deformation. Techniques for calibration and for data processing were developed. A principal use for this device was in the study of blends of linear low density polyethylene (LLDPE) with high density polyethylene (HDPE) and with conventional low density polyethylene (LDPE). The SALS studies were accompanied by WAXD, SAXS and raman longitudinal acoustic mode (LAM) spectroscopy. It was concluded that LLDPE co-crystallized with HDPE but not with LDPE. However in the latter case, both species reside in the same spherulites. A two-step crystallization occurs where the LLDPE crystallizes first, forming volume filling spherulites. The LDPE the crystallized by a secondary process within the already formed spherulites. These two stages may be readily followed with the OMA.

Dynamic mechanical properties and dynamic birefringence studies were carried out on the above blends. Because of the differing morphological role of the two components of the LLDPE/LDOE blends, they were found to contribute to these measurements in a non-equivalent manner. The properties were dominated by the LLDPE component which formed the "backbone" of the spherulites. It is notable that this reinforcing effect of the LLDPE occurs even when it is present at only 10% concentration. This illustrates a relatively new and important concept in the understanding of polymer morphology - where a small amount of a crystallizable component in a blend can influence the morphology of a major component, and thus have a major influence on properties.

Another application of this principle deals with the use of nucleating agents to



Dist	over and/or Special
A-1	

<input checked="" type="checkbox"/>
<input type="checkbox"/>
<input type="checkbox"/>
codes

control crystal morphology. The SALS technique, using the OMA, was applied to the study of the nucleation of polypropylene (PP) and LLDPE by the soluble organic nucleant, dibenzidyl sorbitol (DBS). It was found that the DBS not only served to nucleate more spherulites and hence, decrease their size, but also changed the internal arrangement of crystals within the spherulites. This observation indicates the possibility of inducing major property changes with small amounts of nucleant.

The OMA was also used to study the spherulite deformation process. Quantitative Hv, Vv, and Hh polarized light scattering data were obtained for uniaxially deformed PE and PP samples. Data revealed not only information about the change in spherulite shape, but also details about the way in which the crystals within the spherulites rearranged. Results were fitted to parameters in models involving such parameters was shown that the deformation modes of PE and PP were quite different. An affine model for internal spherulite deformation was shown to be inadequate, and good progress was made in developing a non-affine model.

The above technique has the advantage that data acquisition is fast, so that measurements may be extended to dynamic studies. Thus, the completed work "opens doors" for new studies for which alternative support is being sought.

Another novel technique pioneered during this study was the use of small angle neutron scattering (SANS) for the study of chain deformation. Such studies were carried out on polystyrene (PS) and PE, where it was found that the molecular extension of high MW PS is affine but that for PE is not. A paper is being prepared considering proposed models for the latter situation. These measurements also are leading to appreciable additional studies of chain extension in crystalline polymers for which support (ONR) has been approved. They also point the way to future dynamic studies which will permit "molecular level" rheology of crystalline polymers.

PUBLICATIONS ENTIRELY OR PARTIALLY SUPPORTED BY THIS PROJECT

D. P. Lefebvre and R. S. Stein,
"Study of the Light-Scattering Pattern of Deformed Low-Density
Polyethylene,"
in preparation

D. P. Lefebvre and R. S. Stein,
"Study of the Light-Scattering Pattern of Deformed Isotactic
Polypropylene,"
in preparation

P. Forgacs and R. S. Stein,
"A Theory for α -Axis Orientation in Polyethylene Crystallized in
the Oriented State,"
in preparation

P. Forgacs and R. S. Stein,
"Crystallization in Oriented Polymers: Relationships Between the
Orientation Functions in the Crystalline Phase, in the Amorphous
Phase, and in the Molten Precursor,"
in preparation

P. Forgacs, P. Young and R. S. Stein,
"Dependence of Crystalline Orientation and Morphology of
Radiation Crosslinked Linear Low-Density Polyethylene on the
Amorphous Orientation Prior to Crystallization,"
in preparation

S. Hu, T. Kyu and R. S. Stein,
"Characterization and Properties of Polyethylene Blends:
II--Linear Low-Density With Conventional Low-Density
Polyethylene,"
J. Polymer Sci. in press

S. Hu, T. Kyu and R. S. Stein,
"Characterization and Properties of Polyethylene Blends:
I--Linear Low-Density With High-Density Polyethylene,"
J. Polymer Sci., in press

K. Baba and R. S. Stein,
"Rheo-Optical and Mechanical Studies of the Crystallization and
Orientation of Ethylene-Propylene Copolymers,"
J. Polym. Sci., Polym. Phys. Ed., in press

R. J. Tabar, P. Leitte-James and R. S. Stein, "Quantitative Small-Angle Light Scattering Studies of the
Melting of Poly(ethylene Terephthalate)", J. Polymer Science, Polymer Physics Ed., 23 2085-2108 (1985)

R. J. Tabar, R. S. Stein, and D. E. Rose,
The Effect of Spherulite Truncation on Small-Angle
Light Scattering,
J. Polymer Science, Polymer Physics Ed., 23, 2059-84 (1985)

R.S. Stein

"Neutron Scattering from Polymers in the 'Nineties"
Neutron Scattering in the 'Nineties, Int. Atomic Energy Agency,
Vienna DN-46/42 335-348 (1985)

R. S. Stein,

"Frontiers of Materials in Research in Polymeric Materials",
PROC. UNIV. TEXAS MATERIALS SYMPOSIUM, H. Steinfink, H.L. Marcus,
R.M. Walser, eds., Univ. Texas. Press, Austin, TX, Sp.Pub. #1, 93-114, (1985)

R. S. Stein and C. C. Han,

"Neutron Scattering From Polymers,"
Physics Today, 38, 74-80 (1985).

R. S. Stein,

"Recent Advances in Rheo-Optical Studies of Polymers in the Solid
State,"
Polym. J., 17, 289-306 (1985).

T. Sun, T. Kyu, J. Sheng, D. Lefebvre, R. S. Stein and R. S.
Porter,

"Optical Characterization of Solid-State Co-Extruded PET,"
J. Appl. Polym. Sci., 30, 251-262 (1985)

S. N. Garg, R. S. Stein, T. K. Su, R. J. Tabar and A. Misra,

"Light-Scattering Studies of Nucleation of Polypropylene,"
KINETICS OF AGGREGATION AND GELATION, F. Family and D. P. Landau
(eds.), North-Holland, Amsterdam, 1984, pp.229-234.

T. P. Russell, D. P. Anderson, R. S. Stein, C. R. Desper, J. J.
Beres and N. S. Schneider,

"Rheo-Optical Investigation of the Transition Behavior of
Polyphosphazenes,"
Macromolecules, 17, 1795-1799 (1984).

P. Young, T. Kyu, S. Suehiro, J. S. Lin and R. S. Stein,

"Dynamic Small-Angle X-Ray Scattering From Crystalline Polymers,"
J. Polym. Sci., Polym. Phys. Ed., 21, 881-892 (1983).

R. S. Stein and G. P. Hadziioannou,

"Recent Advances in the Use of Scattering for the Study of Solid
Polymers,"
POLYMER CHARACTERIZATION, C. D. Craver (ed.), American Chemical
Society, Washington, D.C., 1983, pp.722-756.

R. J. Cembrola, T. Kyu and R. S. Stein,

"Dynamic X-Ray Diffraction Studies of High-Density Polyethylene,"
J. Polym. Sci., Polym. Phys. Ed., 21, 329-352 (1983).

Y. K. Wang, D. A. Waldman, J. E. Lasch, R. S. Stein
and S. L. Hsu,

"Raman Spectroscopic Study of Highly Deformed Polyethylene,"
Macromolecules, 15, 1452-1454 (1982).

R. J. Tabar and R. S. Stein,
"A Two-Dimensional Position-Sensitive Detector for Small-Angle
Light-Scattering,"
J. Polym. Sci., Polym. Phys. Ed., 20, 2041-2049 (1982).

R. S. Stein,
"Small-Angle Light-Scattering From the Polymeric Solid State,"
STATIC AND DYNAMIC PROPERTIES OF THE POLYMERIC SOLID STATE, R. A.
Pethrick and R. W. Richards (eds.), Reidel Publishing Co., Boston, 1982, pp.109-125.

R. S. Stein,
"Optical, X-Ray and Neutron Scattering Studies of Polymer
Morphology,"
PROCEEDINGS OF CHINA-U.S. BILATERAL SYMPOSIUM ON POLYMER
CHEMISTRY AND PHYSICS, Science Press, Beijing, China, 1981, pp.171-185.

R. J. Tabar, A. Wasiak, S. D. Hong, T. Yuasa, and R. S. Stein,
"Small-Angle Light-Scattering by Random Assemblies of Incomplete
Spherulites: Systems with Partial Degree of Volume Filling,"
J. Polym. Sci., Polym. Phys. Ed., 19, 49-58 (1981).

PARTICIPATING SCIENTIFIC PERSONNEL

<u>NAME</u>	<u>PRESENT LOCATION</u>
Richard S. Stein, PI	Professor, University of Massachusetts
Dennis Lafebvre, PD	Industry, FRANCE
Peter Forgacs, PD	Atomic Energy Comm., HUNGARY
Ping Young, GS	PhD, UMASS, Industry, US
Shi-Ru Hu, VS	Academia Sinica, PRC
Thein Kyu, PD	Asst. Prof., U. Akron
Kenichi Baba, VS	Industry, JAPAN
Ronald Tabar, GS	Industry, US
Patrecia Leitte-James, PD	Industry, US
D. Rose, UG	Grad. School, US
Jin Sheng, VS	Academia Sinica, PRC
Satya Garg, PD	Gov't. Lab, US
Ashok Misra, GS, PD	PhD., UMASS, Assoc. Prof., INDIA
Thomas Russell, GS	PhD., UMASS, Industry, US
David Anderson, GS	PhD., UMASS, Gov't. Lab., US
Shoji Suehiro, PD	Asst. Prof., JAPAN
Georges Hadziioannou, PD	Industry, US
Robert Cembrola, GS	PhD., UMASS, Industry, US
Andrej Wasiak, PD	Academy of Science, POLAND
Su Don Hong, GS	PhD., UMASS, Gov't. Lab., US
Cameron Murray, GS	PhD., UMASS, Industry, US

CODE :

PI	Principal Investigator (UMASS Faculty)
GS	Graduate Student
PD	Post-Doctoral Fellow
VS	Visiting Scientist
UG	Undergraduate

END

FILMED

4-86

DTIC