

AD-A171 547

SYNTHESIS OF IONIC CONDUCTING INTERPENETRATING POLYMER  
NETWORKS(U) NATIONAL BUREAU OF STANDARDS GAITHERSBURG  
AD POLYMERS DIV C K CHIANG ET AL. 14 AUG 86 TR-5

1/1


UNCLASSIFIED

N00014-86-F-0020

F/G 7/4

NL





MICROCOPY RESOLUTION TEST CHART

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report 5	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER ①
4. TITLE (and Subtitle) Synthesis of Ionic Conducting Interpenetrating Polymer Networks		5. TYPE OF REPORT & PERIOD COVERED Technical Report 5
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) C. K. Chiang, * B. J. Bauer, R. M. Briber and G. T. Davis * Partially supported by the Office of Naval Research		8. CONTRACT OR GRANT NUMBER(s) N00014-86-F0020
9. PERFORMING ORGANIZATION NAME AND ADDRESS National Bureau of Standards Polymers Division Gaithersburg, MD 20899		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Task No. 14339
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Arlington, VA 22217		12. REPORT DATE August 14, 1986
		13. NUMBER OF PAGES 16
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report)
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)  According to attached distribution list		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)  SEP 4 1986 S A		
18. SUPPLEMENTARY NOTES  Submitted to Polymer Communications		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Epoxy; interpenetrating polymer network; ionic conductivity; poly(ethylene oxide); synthesis		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Epoxy and ionic conducting poly(ethylene oxide)-salt complexes form inter- penetrating polymer networks. The co-continuity of the two phases are tested independently using mechanical and electrical measurements. Examination of the network using transmission electron microscopy suggests that the size scale of the phases ranges from 0.1 to 0.5 microns.		

DD FORM 1473  
1 JAN 73EDITION OF 1 NOV 68 IS OBSOLETE  
S/N 0102-014-6601

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

86 9 3 118

AD-A171 547

MICROFILM COPY

OFFICE OF NAVAL RESEARCH

Contract N00014-86-F0020

Task No. 14339

TECHNICAL REPORT NO. 5

SYNTHESIS OF IONIC CONDUCTING INTERPENETRATING POLYMER NETWORKS

by

C. K. Chiang, B. J. Bauer, R. M. Briber and G. T. Davis,

Prepared for Publication

in

Polymer Communications

National Bureau of Standards  
Institute for Materials Science and Engineering  
Polymers Division  
Gaithersburg, MD

August 14, 1986

Reproduction in whole or in part is permitted for  
any purpose of the United States Government.

This document has been approved for public release  
and sale; its distribution is unlimited.

**Synthesis of Ionic Conducting  
Interpenetrating Polymer Networks**

C. K. Chiang,\* B. J. Bauer, R. M. Briber  
and G. T. Davis\*

Polymers Division  
Institute for Materials Science and Engineering  
National Bureau of Standards  
Gaithersburg, MD 20899

**ABSTRACT**

Epoxy and ionic conducting poly(ethylene oxide)-salt complexes form interpenetrating polymer networks. The co-continuity of the two phases are tested independently using mechanical and electrical measurements. Examination of the network using transmission electron microscopy suggests that the size scale of the phases ranges from 0.1 to 0.5 microns.



Form	<input checked="" type="checkbox"/>
1981	<input type="checkbox"/>
1982	<input type="checkbox"/>
1983	<input type="checkbox"/>
1984	<input type="checkbox"/>
1985	<input type="checkbox"/>
1986	<input type="checkbox"/>
1987	<input type="checkbox"/>
1988	<input type="checkbox"/>
1989	<input type="checkbox"/>
1990	<input type="checkbox"/>
1991	<input type="checkbox"/>
1992	<input type="checkbox"/>
1993	<input type="checkbox"/>
1994	<input type="checkbox"/>
1995	<input type="checkbox"/>
1996	<input type="checkbox"/>
1997	<input type="checkbox"/>
1998	<input type="checkbox"/>
1999	<input type="checkbox"/>
2000	<input type="checkbox"/>
2001	<input type="checkbox"/>
2002	<input type="checkbox"/>
2003	<input type="checkbox"/>
2004	<input type="checkbox"/>
2005	<input type="checkbox"/>
2006	<input type="checkbox"/>
2007	<input type="checkbox"/>
2008	<input type="checkbox"/>
2009	<input type="checkbox"/>
2010	<input type="checkbox"/>
2011	<input type="checkbox"/>
2012	<input type="checkbox"/>
2013	<input type="checkbox"/>
2014	<input type="checkbox"/>
2015	<input type="checkbox"/>
2016	<input type="checkbox"/>
2017	<input type="checkbox"/>
2018	<input type="checkbox"/>
2019	<input type="checkbox"/>
2020	<input type="checkbox"/>

\*Partially supported by the Office of Naval Research.

A1

## INTRODUCTION

The discovery of high ionic conductivity in poly(ethylene oxide)-salt complexes <sup>(1,2)</sup> has led to an extensive search for solid polymeric electrolytes. <sup>(3-5)</sup>

The desirable properties for a solid polymeric electrolyte include both high ionic conductivity and good mechanical strength. Attempts to increase ionic conductivity by lowering the molecular weight or the glass transition temperature result in specimens that are fluids or mechanically weak films. Crosslinking can lead to stronger films, but generally results in a drop in conductivity. The largest research effort previously has been on single phase polymers with capability to dissolve salts and to form polymer-salt complexes. <sup>(6-8)</sup> However, the conductivity of these polymer systems is only on the order of  $1 \times 10^{-6}$  S/cm at room temperature.

To find a polymer system which has both high ionic conductivity and good mechanical properties, we have focused our attention on interpenetrating polymer networks, IPNs. <sup>(9,10)</sup> This paper reports the first attempt to synthesize an ionic conducting IPN made from epoxy and poly(ethylene oxide)-salt complexes. The epoxy forms the phase which has good mechanical properties while the liquid PEO-salt complex phase provides the high ionic conductivity. In an ideal IPN each co-continuous phase provides one of the necessary properties.

## EXPERIMENTAL

Poly(ethylene oxide), MW=400 (Aldrich)<sup>(11)</sup>, and 10 mole %

lithium perchlorate were dissolved in spectro grade acetonitrile to form a 5 wt% solution. The PEO solution was mixed with the epoxy, diglycidylether of bisphenol A (Dow DER-332) (11) and crosslinker, poly(propylene oxide) triamine (Texaco Jeffamine T-403). (11) Acetonitrile was evaporated at room temperature in vacuum. The dried mixture was cured at 95 °C.

The electrical conductivity of the polymers was measured using the AC impedance method. The electrodes were a pair of stainless steel plates pressed against the surface of the polymer films (15mm x 15 mm). The specific conductivity of the sample was deduced by varying the AC frequency from 100 Hz to 13 MHz. The frequency data was also used to examine the relaxation mechanism of the polymer. Compression modulus was measured by placing a series of dead weights on the sample. The displacement of sample was measured 30 seconds after each weight was applied. The modulus of the polymer was computed by a linear least squares fitting of the force versus displacement.

#### RESULTS AND DISCUSSION

The pure epoxy is a rigid solid with a conductivity of less than  $10^{-12}$  S/cm at room temperature. The epoxy containing the PEO-salt complex phase is a opaque white solid. For less than 20 wt% epoxy phase, no free standing film was able to be formed, which would indicate that the epoxy did not form a continuous phase. When the epoxy content is more than 20 wt%

free standing films were formed.

The mechanical properties of these films improve as the percentage of epoxy increases. Figure 1 shows the modulus as a function of epoxy content from 20 wt. % to 50 wt. %. At 50 wt. % epoxy the measured modulus is  $2.5 \times 10^9$  dynes/cm<sup>2</sup>. This agrees with the Young's modulus of a pure epoxy, which is  $2 \times 10^9$  dynes/cm<sup>2</sup>. (12) At about 30 wt% of epoxy the modulus of the polymer sample still has a value approaching that of the pure epoxy. The formation of a free standing film with 20 wt. % or more epoxy is evidence that the epoxy phase is continuous.

At room temperature the PEO-LiClO<sub>4</sub> complex is a viscous liquid. The dissociated Li<sup>+</sup> and ClO<sub>4</sub><sup>-</sup> ions provide ionic conductivity of  $6 \times 10^{-4}$  S/cm. The viscosity of the PEO polymer increases when the salt is incorporated. The viscosity increase is due to the crosslinking effect by the dissolved ions. The AC electrical impedance spectrum of PEO-10 mol% LiClO<sub>4</sub> shows a simple RC response with a small depression angle. The DC electrical conductivity is calculated from the minimum in the complex impedance plot. The ionic conduction follows a free-volume mechanism (13-14).

Figure 2 shows the DC electrical conductivity of the polymers as a function of epoxy content from 20 wt. % to 50 wt.%. The conductivity of the polymer remains nearly constant from pure PEO-LiClO<sub>4</sub> to about 30 wt% epoxy. Further increase in epoxy content leads to an exponential decrease in the conductivity. The AC electrical impedance spectra of the



polymers with up to 35 wt% of epoxy shows a similar RC response as that of the polymer with no epoxy added. This behavior indicates that the samples containing 35 wt % and less epoxy maintain a continuous conducting phase. Above 40 wt. % of epoxy the impedance spectra of the polymers show evidence of distributed relaxation. This type of spectra is often observed in a polycrystalline ionic conductor which contain grain boundaries.<sup>(15)</sup> It can be interpreted that at higher epoxy contents the phase separated epoxy is beginning to restrict the motion of ions.

A sample of 50 wt% epoxy and 50 wt% PEO-salt complex has been examined using transmission electron microscopy (TEM). Phase separation was observed on the size scale of 0.1 to 0.5 microns. The corresponding AC impedance spectrum of the polymer with 50 wt. % epoxy is highly depressed. The AC impedance spectrum indicates that the connection of PEO-salt phases are highly non-uniform since the spectrum did not exhibit two clearly separated RC responses. Also, the conductivity of the IPNs never dropped to the level of pure epoxy.

#### CONCLUSIONS

In conclusion, co-continuous interpenetrating polymer networks are formed between epoxy and PEO-Li salt complexes when the epoxy content varies between 20 wt % to 50 wt % based on electrical and mechanical measurements. The optimum properties for a solid polymeric electrolyte are in the vicinity of 30 wt% epoxy and 70 wt% PEO-LiClO<sub>4</sub> in the present

system.

Forming an IPN will have many advantages over a single phase polymer system. Two aspects should be emphasized: first, that all existing ionic conducting polymer systems could be used, even if they are in liquid form, to construct solid IPN electrolytes. Second, a suitable choice of the support phase could provide good thermal and mechanical properties. The concept presented in this paper involves a new process for preparing solid polymeric electrolytes.

In our experiments the concentration of  $\text{LiClO}_4$  salt was fixed at 10 mole %. Although it was not optimized for the best conductivity, an IPN system with a conductivity of  $1 \times 10^{-4}$  S/cm at room temperature has been obtained. This ionic conductivity is nearly ten times higher than the values reported for systems such as polyphosphazine or polysiloxane containing lithium salts.<sup>(6-8)</sup>


## REFERENCES


1. P. V. Wright, *Brit. Polym.* 7, 319 (1975).
2. M. Armand, J. M. Chabano and M. J. Duclot, *Fast Ion Transport in Solids*, eds. P. Vashishta, J. N. Mundy and G. K. Shenoy, North Holland, Amsterdam, (1979), p.131.
3. D. F. Shriver and G. C. Farrington, *Chem. & Eng. News*, p.42, May 20, 1985.
4. *Papers in Solid State Ionics*, 9/10 (1983).
5. *Papers in Solid State Ionics*, 18/19 (1986).
6. P. M. Blonsky, D. F. Schriver, P. Austin and H. R. Allcock, *J. Amer. Chem. Soc.*, 106, 6854 (1984).
7. P. G. Hall, G. R. Davies, J. E. McIntyre and I. M. Ward, D. J. Bannister and K. M. F. LeBrocq, *Polym. Comm.*, 27, 98 (1986).
8. D. Fish, I. M. Khan and J. Smid, *Makromol. Chem., Rapid Commun.*, 7, 115 (1986).
9. D. A. Thomas and L. H. Sperling, "Polymer Blends", Vol. II, Plenum Press, N.Y., Chapter 11, (1976).
10. H. L. Frish, K. C. Frisch and D. Klempner, *Pure Appl. Chem.*, 53, 1557 (1981).
11. Certain commercial materials and equipment are identified in this article to specify the experimental procedure. In no instance does such identification imply recommendation or endorsement by the National Bureau of Standards or imply that the material and equipment identified are necessarily the best available for the purpose.
12. S. C. Mirsa, J. A. Manson, and L. H. Sperling, "Epoxy Resin Chemistry", ACS Symposium Series, 114, 136 (1979)
13. J. D. Ferry, "Viscoelastic Properties of Polymers", John Wiley & Sons, New York (1961).
14. M. L. Williams, R. F. Landel and J. D. Ferry, *J. Am. Chem. Soc.*, 77, 3701 (1955).
15. C. K. Chiang, J. P. Buthin, A. L. Dragoo, A. D. Franklin and K. F. Young, *J. Electrochem. Soc.*, 129, 2113 (1982).

## FIGURE CAPTIONS

Figure 1. The Modulus of epoxy/PEO-10 mol.% LiClO<sub>4</sub> samples as a function of epoxy content. The straight lines are the least squares fit for data above and below 30 wt%.

Figure 2. The electrical conductivity of epoxy/PEO-10 mol.% LiClO<sub>4</sub> samples as function of epoxy content. The straight lines are the least squares fit for the data above and below 30 wt%.





TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No Cops</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper DTNSRDC Code 2903 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTECH/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST: 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Paul Delahay Department of Chemistry New York University New York, New York 10003	1	Dr. P. J. Hendra Department of Chemistry University of Southampton Southampton SO0 5NH United Kingdom	1
Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 41106	1	Dr. San Perone Chemistry & Materials Science Department Lawrence Livermore National Lab. Livermore, California 94550	1
Dr. D. N. Bennion Department of Chemical Engineering Brigham Young University Provo, Utah 84602	1	Dr. Royce W. Murray Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1
Dr. R. A. Marcus Department of Chemistry California Institute of Technology Pasadena, California 91125	1	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
Dr. J. J. Auburn Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. C. F. Mueller The Electrochemistry Branch Materials Division, Research and Technology Department Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910	1
Dr. Adam Heller Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. G. Goldman Johnson Controls 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. T. Katan Lockheed Missiles and Space Co., Inc. P. O. Box 504 Sunnyvale, California 94088	1	Dr. J. Poehler Electrochimica Corporation 20 Kelly Court Menlo Park, CA 94025-1418	1
Dr. Joseph Singer, Code 302-1 NASA-Lewis 21000 Brookpark Road Cleveland, Ohio 44135	1	Dr. P. P. Schmidt Department of Chemistry Oakland University Rochester, Michigan 48063	1
Dr. B. Brunner EIC Incorporated 55 Chapel Street Boston, Massachusetts 02156	1		
Library P. L. Mallory and Company, Inc. Northwest Industrial Park Ludington, Massachusetts 01860			



TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. H. Richtol Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1	Dr. R. P. Van Duyne Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. A. B. Ellis Chemistry Department University of Wisconsin Madison, Wisconsin 53706	1	Dr. B. Stanley Pons Department of Chemistry University of Alberta Edmonton, Alberta CANADA T6G 2G2	1
Dr. M. Wrighton Chemistry Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139		Dr. Michael J. Weaver Department of Chemistry Michigan State University East Lansing, Michigan 48824	1
Larry E. Piew Naval Weapons Support Center Code 30736, Building 2906 Crane, Indiana 47522	1	Dr. R. David Rauh EIC Corporation 55 Chapel Street Newton, Massachusetts 02158	1
S. Ruby DOE (STOR) 600 E Street Providence, Rhode Island 02192	1	Dr. J. David Margerum Research Laboratories Division Hughes Aircraft Company 3011 Malibu Canyon Road Malibu, California 90265	1
Dr. Aaron Wold Brown University Department of Chemistry Providence, Rhode Island 02192	1	Dr. Martin Fleischmann Department of Chemistry University of Southampton Southampton SO9 5NE England	1
Dr. R. C. Chudacek McGraw-Edison Company Edison Battery Division Post Office Box 28 Bloomfield, New Jersey 07003	1	Dr. Janet Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. A. J. Bard University of Texas Department of Chemistry Austin, Texas 78712	1	Dr. K. A. Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. W. M. Nicholson Electronics Research Center Rockwell International 3370 Miraloma Avenue Anaheim, California 92806	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Donald W. Ernst Naval Surface Weapons Center Code R-33 White Oak Laboratory Silver Spring, Maryland 20910	1	Mr. James R. Moden Naval Underwater Systems Center Code 3632 Newport, Rhode Island 02840	1
Dr. R. Nowak Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Dr. Bernard Spielvogel U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709	1
Dr. John F. Houlihan Shenango Valley Campus Pennsylvania State University Sharon, Pennsylvania 16146	1	Dr. Denton Elliott Air Force Office of Scientific Research Bolling AFB Washington, D.C. 20332	1
Dr. B. F. Shriver Department of Chemistry Northwestern University Evanston, Illinois 60201	1	Dr. David Aikens Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1
Dr. D. H. Whitmore Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Dr. A. P. B. Lever Chemistry Department York University Downsview, Ontario M3J1P3 Canada	1
Dr. Alan Bewick Department of Chemistry The University Southampton, SO9 5NH England		Dr. Stanislaw Szpak Naval Ocean Systems Center Code 6343 San Diego, California 95157	1
Dr. A. Himy NAVSEA-5433 NC #4 2541 Jefferson Davis Highway Arlington, Virginia 20362		Dr. Gregory Farrington Department of Materials Science and Engineering University of Pennsylvania Philadelphia, Pennsylvania 19104	
Dr. John Kincaid Department of the Navy Strategic Systems Project Office Room 901 Washington, D.C. 20376		Dr. Bruce Dunn Department of Engineering & Applied Science University of California Los Angeles, California 90024	

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
M. L. Robertson Manager, Electrochemical and Power Sonics Division Naval Weapons Support Center Crane, Indiana 47522	1	Dr. T. Marks Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. Elton Cairns Energy & Environment Division Lawrence Berkeley Laboratory University of California Berkeley, California 94720	1	Dr. D. Cipris Allied Corporation P. O. Box 3000R Morristown, New Jersey 07960	1
Dr. Micha Tomkiewicz Department of Physics Brooklyn College Brooklyn, New York 11210	1	Dr. M. Philpot IBM Corporation 5600 Cottle Road San Jose, California 95193	1
Dr. Lesser Blum Department of Physics University of Puerto Rico Rio Piedras, Puerto Rico 00931	1	Dr. Donald Sandstrom Washington State University Department of Physics Pullman, Washington 99164	1
Dr. Joseph Gordon, II IBM Corporation K33/281 5600 Cottle Road San Jose, California 95193	1	Dr. Carl Kannevurf Northwestern University Department of Electrical Engineering and Computer Science Evanston, Illinois 60201	1
Dr. Robert Somoano Jet Propulsion Laboratory California Institute of Technology Pasadena, California 91103	1	Dr. Edward Fletcher University of Minnesota Department of Mechanical Engineering Minneapolis, Minnesota 55455	1
Dr. Johann A. Joebstl USA Mobility Equipment R&D Command DRDME-EC Fort Belvoir, Virginia 22060	1	Dr. John Fontanella U.S. Naval Academy Department of Physics Annapolis, Maryland 21402	1
Dr. Judith H. Ambrus NASA Headquarters H.S. RTS-6 Washington, D.C. 20546	1	Dr. Martha Greenblatt Rutgers University Department of Chemistry New Brunswick, New Jersey 08903	1
Dr. Albert R. Landgrebe U.S. Department of Energy H.S. 6B025 Forrestal Building Washington, D.C. 20503	1	Dr. John Wassib Kings Mountain Specialties P. O. Box 1173 Kings Mountain, North Carolina 28086	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>	<u>No. Copies</u>
Dr. J. J. Brophy University of Utah Department of Physics Salt Lake City, Utah 84112	1	
Dr. Walter Roch Department of Physics State University of New York Albany, New York 12222	1	
Dr. Thomas Davis National Bureau of Standards Polymer Science and Standards Division Washington, D.C. 20234	1	
Dr. Charles Martin Department of Chemistry Texas A&M University College Station, TX 77843	1	
Dr. Anthony Sammells Institute of Gas Technology 3424 South State Street Chicago, Illinois 60616	1	
Dr. H. Tachikawa Department of Chemistry Jackson State University Jackson, Mississippi 39217	1	
Dr. W. M. Risen Department of Chemistry Brown University Providence, Rhode Island 02912	1	

END

10-8%

DTIC