


AD-A172 278 PLASMA POLYMER COATINGS TO PREVENT PIPELINE CORROSION
AND REDUCE FRICTION(U) POLAR MATERIALS INC MARTIN'S
CREEK PA G W WALPERT 21 MAY 86 DAAK78-85-C-0188


1/1

UNCLASSIFIED

F/G 11/3

NL





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

AD-A172 278

(12)

PLASMA POLYMER COATINGS TO PREVENT PIPELINE
CORROSION AND REDUCE FRICTION
CONTRACT #DAAK70-85-C-0100


PRINCIPAL INVESTIGATOR: DR. DEREK SHUTTLEWORTH
REPORT PREPARED BY: DR. GEORGE W. WALPERT

DTIC
ELECTE
S SEP 24 1986
A

George Walpert
Dr. George W. Walpert
Polar Materials, Inc.

DATED: 5-21-86

OMC FILE COPY



86 7 1 063

DISCLAIMER NOTICE

**THIS DOCUMENT IS BEST QUALITY
PRACTICABLE. THE COPY FURNISHED
TO DTIC CONTAINED A SIGNIFICANT
NUMBER OF PAGES WHICH DO NOT
REPRODUCE LEGIBLY.**

**SMALL BUSINESS INNOVATION RESEARCH PROGRAM
PHASE 1 – FY 1985
PROJECT SUMMARY**

Topic No. A-59

Military Department/Agency Army

Name and Address of Proposer

Polar Materials Inc.
Ben Franklin Technology Center
Homer Research, Bldg. F
Bethlehem, PA 18016

Name and Title of Principal Investigator

Dr. Derek Shuttleworth, Director

Proposer's Title*

Plasma Polymer Coatings to Prevent Pipeline Corrosion
and Reduce Friction

Technical Abstract* (Limit your abstract to 200 words with no classified or proprietary information/data.)

This program will investigate the preparation of corrosion and friction reduction coatings for pipeline protection prepared by state-of-the-art plasma methods. Plasma techniques can produce coatings of ceramic-like materials with high abrasion resistance. Their chemical unreactivity and uniformity of coverage allows them to function as effective barrier coatings for corrosion protection.

Diagnostic and real-time process control methods will be developed to make the procedures a viable production method.

Anticipated Benefits/Potential Commercial Applications of the Research or Development

This program will have extensive application in corrosion protection of, for example, automotive exhausts and corrosive material pipelines.

List a maximum of 8 Key Words that describe the Project.

Corrosion protection, friction reduction, plasma CVD, plasma polymerization

PREFACE

The work reported herein was done under Procurement Instrument Number DAAK70-85-C-0100, August 22, 1985, awarded in response to SBIR proposal for Topic A-59 in Solicitation DOD85-1. The work was done in the laboratories of Polar Materials, Inc. during the period August 22, 1985 to April 22, 1986. The Principal Investigator was Dr. Derek Shuttleworth until March 1, 1986, at which time Dr. Shuttleworth was replaced as Principal Investigator by Dr. George W. Walpert. Other contributors to the project include Dr. Malcolm L. White, Consultant and Staff member at the Sinclair Center for Surface and Coatings Research at Lehigh University, Dr. H. Ronald Thomas, President of PMI, Terry J. Hafford, Paula J. Battavio, and Robert J. Babacz, staff members at PMI.

The Contracting Officer's Representative was Louis H. Tagliaferre, STREB-GP, who was kept informed of progress throughout the project. The contract was originally scheduled to cover the period August 22, 1985 to February 22, 1986, but a 60-day no-cost extension was requested by letter from Dr. Shuttleworth to Mr. Tagliaferre dated February 13, 1986, and acknowledged by telephone by Mr. Tagliaferre.

The SBIR proposal proposed utilizing part of a Post-Doctoral appointment at Lehigh University to use non-uncursive in situ analytical techniques to characterize the plasma polymerization process and seek relationships between plasma parameters and product characteristics. Unfortunately, recruiting efforts for the post-doctoral fellow were not successful, and this portion of the project was not done. The monies budgeted for the post-doctoral effort were diverted to staff members at Lehigh University for product characterization, test development, and testing.

Classification	<input type="checkbox"/>
Controlled Distribution	<input type="checkbox"/>
Declassification	<input type="checkbox"/>
Declassify Date	
Delivery Address	
Delivery Date	
Delivery Method	
Delivery Point	
Delivery Time	
Delivery Type	
Distribution	<input type="checkbox"/>
Availability Codes	
Avail and/or Dist Special	
A-1	

ABSTRACT

Three different materials, thiophene, hexamethyldisiloxane, and hexamethyldisilazane were deposited on mild steel coupons by low temperature radio-frequency plasma polymerization. Statistically designed experiment matrices were utilized to screen a range of operating conditions and optimize coating properties. For two of the materials, a narrower range of conditions was used to produce coating weights of about 400 micrograms per square centimeters, and these coatings were evaluated for corrosion protection and coating physical properties.

Coatings were produced which yielded 256 hours in air-bubbled salt water to 95% corrosion. Uncoated coupons in the same test rusted to 95% in six hours. The best coating was deposited at a rate of 4 micrograms per square centimeter per minute, but reasonably good coatings were produced at coating rates of 20 to 30 micrograms per square centimeter per minute.

The feasibility of corrosion protection coatings using low temperature plasma polymerization has been established by this project, but much process and product development remains for commercialization. Recommendations for continued development work are discussed in this report.

(*Pipelines; Diagnostic tests; Real time; Process control methods*)

TABLE OF CONTENTS

<u>TITLE</u>	<u>PAGE #</u>
INTRODUCTION	1
EXPERIMENTAL	3
A. PLASMA EQUIPMENT	3
B. MATERIALS	3
C. OPERATING PROCEDURES	3
D. EXPERIMENTAL DESIGN	4
E. EVALUATION TECHNIQUES	5
RESULTS & DISCUSSION	7
A. DATA	7
B. GENERAL	7
C. FILM DENSITY	8
D. COATING PROPERTIES VS. PROCESS CONDITIONS	9
E. ECONOMICS	10
RECOMMENDATIONS	11
REFERENCES	12
APPENDIX	13

INTRODUCTION

This report presents the results of a study to determine the feasibility of using non-equilibrium plasma polymerization to produce coatings for corrosion protection and flow enhancement on the inside of pipes.

The low temperature, or non-equilibrium plasma is currently a procedure of significant importance in semiconductor fabrication (1). This development paves the way for other applications of low temperature plasma by the development of equipment for routine use and by development of some understanding of the principles governing plasma technology. Low temperature plasma, therefore, affords considerable promise as a source of protective coatings for use in a diversity of applications.

An opportunity exists to devise coating procedures in which thin films of high performance material can be deposited at relatively low cost. The challenge and the opportunity is to obtain coatings that are hard, chemically inert, of low permeability to oxygen and water, strongly adhering and low in defects, such as pinholes. Plasma methods afford the capability to produce such films, and represent a higher probability of success than other methods.

A particularly flexible plasma method for the production of thin films is plasma polymerization (2, 3, & 4). In this process, volatile materials are caused to react at essentially room temperature in a gas plasma sustained by high frequency electrical power. The state thus produced is highly reactive, populated by radicals, electrons, ions, metastables and electromagnetic radiation extending into the ultraviolet (5). Energies up to 40 eV are available which is to be compared with typical chemical energies of 3 to 10 eV. Many reaction pathways are opened in an organic gas plasma leading to rearrangement of the starting material and/or deposition of polymeric material on surfaces in the plasma zone (6). Under the appropriate conditions, materials generally not considered to be monomers, eg. benzene, xylene, butane, or even methane gas can be deposited as thin, eg. one micron, coatings which are pinhole-free, conformal, strongly adhering, and crosslinked to the point of being insoluble in common organic solvents.

Such coatings have been produced for the subject study of this report from three starting materials, thiophene, hexamethyldisiloxane and hexamethyldisilazane. Corrosion resistance of the films, and their physical properties have been measured and to some extent these responses related to process conditions.

One of the objectives as stated in the SBIR proposal was to develop coatings for corrosion protection and flow enhancement.

One of the criteria for selecting starting materials was to produce coatings with a range of surface energy, intending to study the effect on resistance to flow. However, informal discussions with Navy investigators on fluid flow projects convinced this author that fluid flow is dominantly controlled by surface topography (and the character of the fluid) and that efforts to enhance flow by surface chemistry offered little probability of success with a cursory effort. In addition, the effort required for the investigation proved to have been underestimated in the SBIR Proposal, and the election was made not to pursue the flow enhancement objective.

EXPERIMENTAL

A. PLASMA EQUIPMENT

A laboratory scale vacuum plasma polymerization reactor of six-inch diameter glass was set up with monomer flow controllers, vacuum gauges, R.F. (radio frequency) power supply, and vacuum pump.

Flow was controlled by Datametrics Type 825 mass flow control valves, Datametrics Type 1511 multi-channel digital display flow controller, and ball-float flow tubes, Air Products E29M150MM1 and E29C150MM2. Pressure was sensed and controlled by a Datametrics Type 1500 digital pressure display and power supply, a Datametrics Type 621 Barocel pressure sensor, an MKS Type 252A exhaust valve controller to maintain constant pressure in a vacuum system, an MKS Type 253A-1-40-1 throttling valve to regulate the removal of gas from a vacuum chamber, and a Varian thermocouple vacuum gauge 804-A. The R.F. power generator, ENI Power Systems Model HF-300, was used with A Heathkit SA2060-A manual impedance matching network. The Varian CD300 mechanical vacuum pump was fitted with a 345 foreline trap filled with molecular sieve material. A Mathis Model TM-100 thickness monitor was set up in the reactor sleeve but eventually malfunctioned, and its use was discontinued.

The cross-shaped glass reactor was equipped with a rotating copper heated stage capable of operating at temperatures up to 400° C. Temperature was initially read on a Eurotherm Model 983 digital indicating controller and then an Omega Model 199KC digital temperature indicator. Both units experienced problems with interference from the pick-up of stray RF power. Temperature was finally read on an Omega Model 7045-K-1500 analog pyrometer. For experimental runs without substrate heating, a stainless steel rotating stage was used. A schematic diagram of the system is shown in Figure 1.

B. MATERIALS

Monomers and gases used included thiophene (Fisher Scientific), hexamethyldisiloxane (HMDSO) and hexamethyldisilazane (HMDSN) (both from Petrarch Systems Inc.), oxygen and argon (both from Air Products). Substrate materials were 0.5 mm thick, smooth finish, steel Type OD O-Panels, ASTM specification D609.3B.

C. OPERATING PROCEDURES

The O-Panels were cut into desired sizes, washed with trichloroethylene, and stored in desiccators. Before each run, they were individually wiped with a Kimwipe and trichloroethylene, air dried, weighed, and loaded into the reactor.

Thiophene, HMDSO, and HMDSN were vacuum degassed at liquid nitrogen-temperature. The gas flow from these monomers were manually controlled by flow tubes.

After the substrates were positioned on the rotating, electrically grounded electrode and loaded in the reactor, pressure was lowered to less than 0.3 Torr, and an autotransformer was manually adjusted to the heated rotating electrode to maintain the desired temperature. Substrates were exposed to an argon plasma (gas flow 28 sccm, pressure 500 mTorr, power 100 w) for two minutes to clean the substrate surfaces. Thiophene runs A59A1 to A13, A59B1 to B13, A59C1 to C3, and A59A55 were exposed to the argon plasma followed by an oxygen plasma (gas flow 25 sccm, pressure 500 mTorr, power 100 w) for one minute.

Monomers at a prescribed rate were introduced into the reactor, pressure was set to a prescribed value, R.F. power turned on, adjusted to the prescribed value and forward power optimized with the matching network to maintain a glow discharge plasma. Every 5 minutes during a run, the R.F. power was turned off, the temperature checked, the autotransformer adjusted if necessary to maintain the desired temperature, and the R.F. power turned back on. (Because of R.F. pick-up by the thermocouple leads, the temperature indicator could only be hooked up to the system and the temperature noted when the plasma was off, although power was supplied to the heater via the autotransformer during the entire run.) At the end of a run, the R.F. power, monomer flow, and heater power were turned off. Pressure was pumped down to less than 0.3 Torr. Samples remained in the reactor under vacuum until the temperature fell below 100° C. Then the system was vented, the samples removed from the system, allowed to cool to room temperature, and weighed.

(Thiophene Experimental Designs I and II, design orders 2, 3, 5, and 8 were run to different thicknesses on the Mathis Thickness monitor to estimate the correlation between the thickness rate calculated from the actual coating formed and the thickness monitor indication. The remaining design orders in thiophene Designs I, II, and III were run to a thickness of 0.25 kiloangstroms on the monitor to the nearest whole minute. A monitor thickness rate in kiloangstroms per minute was calculated. For samples having the better film qualities, run times were calculated to reach a thickness build-up of 500 micrograms per square centimeter using the thickness rate of the actual coating formed.

D. EXPERIMENTAL DESIGN

Two-level fractional factorial experiments were designed to identify the process variables that most significantly influenced development of a good coating and to begin optimizing a set of process conditions.

Preliminary experiments included full factorial designs for thiophene runs with no temperature control, half factorial designs for thiophene and HMDSO runs with temperature control, and half factorial designs for HMDSN with no temperature control. The process variables studied included conditions varying the radio

frequency, power, pressure, flow, and temperature. The design matrices and ranges for the variables are shown in Tables 1-7.

E. EVALUATION TECHNIQUES

The coating properties measured included weight gain of the coupon, scrape adhesion, tensile adhesion, salt exposure (corrosion resistance), pinhole microscope tests, conductance, and abrasion resistance.

Coating thickness (coating weight) in grams per square centimeter was calculated by the coating weight obtained on the O-Panels divided by the coated area.

A Pacific Scientific, Gardner/Neotec Instrument Division, balanced beam scrape-adhesion and mar tester, SG-8101, fitted with a loop stylus, SG-8102 was used for the scrape adhesion test. The Standard Test Method for Adhesion of Organic Coatings, ASTM D2197-68 (reapproved 1979) Method A Scrape Adhesion, was used with the following modifications to the ASTM procedure: sample size, load increments, number of repeated tests, and detection of adhesion end point using an electrical contact. A coated 2.5 x 2.5 cm square O-Panel was tested with 10-g increments to 100g, 100-g increments to 1 kg, and 1-kg increments to a maximum load of 10 kg. End points were repeated as available sample area permitted. Two indications of failure were reported. Scrape Adhesion 1 was the loading for the first discontinuous indication of electrical contact between the stylus and the substrate, and Scrape Adhesion 2 was the loading for continuous contact.

The tensile adhesion test employed a Sebastian I coating adherence tester (The Quad Group). An epoxy-coated pull stud was clipped to a coated O-Panel, cured at 125° C for 2.5 hours, and cooled to room temperature. The bond strength was determined by the amount of force in psi exerted to pull the stud from the sample. The amount of coating left on the sample was noted.

Salt immersion testing was made by suspending a sample above 5% NaCl solution with the lower half immersed while the solution was bubbled with air. Samples were observed periodically for percentage of surface area oxidized to 95% corrosion.

Deviation from the salt immersion procedure was made for some samples from the HMDSN runs. Samples were submersed into the salt solution bubbled with air and placed flat at the bottom of the container. Observed percentages of surface corrosion were corrected to values relating to the partial immersion testing described above by comparing uncoated substrates evaluated by both methods.

Three pinhole measurements were performed using solutions of neutral CuSO₄ (CuSO₄.5H₂O, H₂O), acidified CuSO₄ (CuSO₄, H₂SO₄, H₂O), and Ferroxil (K₃Fe(CN)₆, NaCl). A drop of one solution is placed on a coating surface. Using an Olympus zoom binocular

microscope at 10x magnification, the time was noted for the formation of 5 crystals, and then 10 crystals.

The conductance was measured by placing an 0.05-0.1 ml drop of 3% NaCl solution on the coating, immersing a stainless steel wire electrode into the drop, using the substrate as the other electrode, and reading the conductance within ten seconds at 2kHz with an Extech Model 440 conductivity meter.

The abrasion resistance was measured using the falling sand technique (ASTM D968-51). 100 ml volumes of Ottawa silica sand (-20 +30 mesh) were funneled through a 36" long by three-quarter-inch diameter tube and allowed to impinge on the coated substrate, held at a 45° angle, until there was some area of bare metal showing. The total volume of sand to reach this point was recorded.

Contact angle measurements were taken using a Rame-Hart Model A-100 NRL C.A. goniometer and water as the liquid.

Density measurements were approximated by wetting pieces of flaked film in different solutions having a range of densities (HL aqueous series from Cargille Lab). Film flakes having a higher density than the solution sank while flakes having a lower density floated.

Quality of the deposited films were classified as film (F) or powder (P). The visual appearance further described the films as even or rainbow colored, peeled, or flaked. A particular sample could exhibit more than one appearance characteristic at one time, usually in different areas of the substrate.

RESULTS AND DISCUSSION

A. DATA

Three materials were evaluated by plasma polymerization as candidates for pipeline coatings - thiophene, hexamethyldisiloxane and hexamethyldisilazane. Each were selected because of previous personal experience of the investigators, and because of a reference in the literature citing good quality films from these materials. The evaluation was done by coating coupons in a research reactor and measuring film properties and corrosion protection on the coupons.

For each material, a statistically designed 2-level full factorial experiment (8 runs) was run to study the effects of process conditions: gas flow rate, pressure, and RF power input. When the temperature-controlled grounded electrode became available, half-factorial designs of 8 runs were made, including substrate temperature as the fourth variable. For the hexamethyldisilazane runs done at ambient temperature, the four variables in the 8-run half factorial were HMDSN flow, oxygen flow, pressure, and power. Design details are shown in Tables 1-7.

For each of the preliminary factorial designs, a visual evaluation of coating quality was made, coating weight was measured and coating rate determined. Coating properties were measured with a scrape adhesion test, and in some cases, a measure of film integrity was made using a drop of copper sulfate solution (the Priest Test). Based on these results, a second factorial design was run at different ranges for the process variables, or selected runs from the first design were repeated at the same process conditions, but different duration to achieve a targeted coating weight, or for selected runs, process conditions were modified slightly and rerun. A total of eleven "sets" were done, comprising 98 individual coating trials. The printout for all of the run data is shown in the Appendix as Tables 8 to 18.

Tables 19, 20, and 21 present a condensation of the data where coating weight and coating rates have been averaged for all the coupons in each run and test data are tabulated by run rather than by coupon. These tables were used for analysis of effects of process variables and for observations upon which the conclusions were based.

B. GENERAL

The interpretation of the massive amount of data accumulated for this program, the distillation of results and the formulation of conclusions is severely hindered by a large amount of variability. Individual coupons within a run gained different coating weight per unit of area despite the rotating electrode sample holder, replicate runs yielded variable results, and test results on duplicate samples from a given run were not reproducible. Statistical test for significance of the first

order effects of process variables show very few to have significance at the 90% confidence level. The objective to relate coating properties to process conditions was only partially achieved, and to this extent only because the massive amount of data enabled some judgemental conclusions based on consistency of the direction of first order effects.

Since the conclusion of the experimental work on this contract, the research reactor on which this work was done has been equipped with a pulse generator to enable pulsing the RF power input in the range of one millisecond period to one second period. Early indications are that pulsing at about 100 milliseconds results in faster coating rates, better film properties, better consistency and more reproducibility. Any continuation of the investigation should definitely include pulsed power as a parameter for study.

The attempt to understand the source of variability has brought into question the design of the research reactor used for this study. Emphasis on electrical isolation of the RF power electrodes resulted in spaces of stagnant gas which have been observed to be the predominant sources of powder. In a configuration specifically designed to coat the inside of pipe with the active electrode centered in the pipe, the pipe itself as both the counterelectrode and the vacuum chamber wall, and reaction gases flowing between them, there would be no stagnant space. The anticipated effect is for higher quality and more uniform coatings. Continuation of the project should go directly to the coating of lengths of pipe, or at least a research reactor designed to simulate the condition of pipe coating.

The compelling observation to be derived from the data is that a number of runs produced reasonably good corrosion-protection coatings. Table 23 shows the test results of the coatings from 15 of the trials, 9 thiophene and 6 hexamethyldisiloxane. The first row in the table is an arbitrary set of acceptance criteria for this stage of development and the entries within each family of coating are by decreasing corrosion resistance as measured by bubbling salt spray. Those properties deficient with respect to the selection criteria are underlined. Run number A59B93 resulted in coupons meeting all acceptance criteria. There is no consistency among the other runs for properties failing to meet the acceptance criteria. The results listed in this table lead to the conclusions that suitable coating properties are achievable, but that continuation of the development mandates upgrading repeatability, upgrading the design of equipment, procedures, and characterization methods.

C. FILM DENSITY

Flakes of coating from some of the coupons which came from the reactor with the film flaking off were used to determine coating density. For these flakes, densities of 1.4 to 1.7 grams per cubic centimeter were observed. At the conclusion of the

experimentation on this contract, a means to remove good coatings, eg. coating from trials resulting in good salt spray results, had not been devised. It is the consensus of the investigators on this project for plasma polymerized coatings, that there is a relationship between coating density and oxygen and water permeability, and that for coatings as thin as are targeted, film density of about 2 will be required. The identification of process conditions to produce this density without internal stresses that lead to crazing and flaking should be an objective of any continuation of this project.

D. COATING PROPERTIES vs. PROCESS CONDITIONS

The first order effect for each process variable on coating rate and film properties in each experimental design matrix is shown in Table 24. A test for significance was done judgmentally by inspection of computer generated cumulative probability charts for each design matrix. Meaningful effects on the table are underlined. In general, the variability in the process and/or in the measuring procedures obscures any well-defined relationship between process conditions and coating properties. However, some trends are indicated. Increased monomer feed rate (flow) within the range studied in the program produced positive results, ie. faster coating rates, better scrape adhesion results, and lower electrical conductivity. The first order effects of pressure were predominantly not significant, but in many instances, the sign of the effect was opposite the sign of the effect of flow. The important parameter may be residence time, a parameter inversely proportional to flow rate and directly proportional to reactor volume and pressure. The concept is interesting, and useful in optimizing trade-off considerations for coating properties vs. economics. When the effects of temperature are judged to have significance, they are mostly negative, ie. detrimental, and the preponderance of temperature effects even where not judged to be significant are negative. If this effect is real, it is contrary to the expected effect based on published literature, which indicates that elevated temperature is required to achieve films with integrity and good corrosion protection. The ability to operate at ambient temperature would obviously be an advantage in a manufacturing process.

The range of process variables utilized for plasma polymerization is limited by regions of the operating conditions that produce powder rather than deposit film. As was observed in paragraph B, entitled General, the design of the research reactor used for this project was a particular offender in producing powder. With a reactor more carefully designed to simulate the process of coating the inside of pipes, the range of the variables studied could be extended and, along with the better reproducibility expected, a better relationship between process conditions and film properties could be obtained.

E. ECONOMICS

The process for coating the inside of pipes was not well enough defined in this program to enable a detailed economic study. Some limiting costs can be estimated. Coating run #A59A89, for instance, provided 216 hours of bubbling salt water protection at a coated weight of 360 micrograms per square centimeter, applied at 10 watts with an electrode area of approximately 650 square centimeters in a 66 minute coating run. For a 21-foot length of 4-inch schedule 40 pipe, assuming 50% material conversion, 50% power efficiency, using chemically pure thiophene at \$15 per pound and 5 cents per kilowatt hour for power, the material cost would be 6 cents, and the power cost would be 13 cents. To design a coating plant for reasonable capital cost and reasonable operating cost is an entirely feasible prospect.

RECOMMENDATIONS

The investigation of plasma polymerized coatings for corrosion protection of the inside of pipes should be continued with a multi-pronged effort:

1. The design of a coating reactor to simulate the inside of a pipe. A section of pipe as the reaction chamber would be appropriate, suitably modified with a demountable (vacuum tight) wall segment for obtaining samples of coating for analysis and characterization. The ends of the pipe section would be ground flat for a vacuum tight "O" ring seal to an electrically insulating end plate including the monomer inlet and electrode mount in one end and the vacuum port and electrode mount on the other end. If controlled elevated temperature continues to be of interest, then an electrically heated jacket for the pipe may be provided.
2. Using the reactor described above, and a starting set of process conditions extracted from the work covered in this report, concentrate on achieving reproducibility of the process and the characterization test procedures.
3. With reproducibility achieved, develop the relationship between process conditions and coating performance.
4. Conduct a screening study to select promising material systems for corrosion protection plasma coating. The thiophene, siloxane and silazane starting materials used in this study were selected considering literature references, availability, cost, and safety considerations. Recent work by this author using all-hydrocarbon coatings of multi-component monomers, and two-layer coatings using fluorinated hydrocarbon top layers have shown promise for corrosion protection. Several members of each "family" of coatings should be screened for this application.
5. With the understanding of the process and an optimum materials package from steps 3 and 4 above, develop parameters for the design of a commercial plant and details of the economics of plasma polymerization coating for corrosion protection of fluid-flow pipes.

REFERENCES

1. Applications of Metallurgical Coatings, R. F. Bunshah & D. M. Mattox, Physics Today, May 1980
2. Deposition Technologies for Films & Coatings, R. F. Bunshah et al, Noyes, 1982
3. Plasma Processing of Materials, Committee Report, Nat. Materials Advisory Board, 1985
4. Thin Film Processes, A. P., New York, (1978), Eds. J. L. Vossen & W. Kern
5. The Application of Plasmas to the Synthesis and Surface Modification of Polymers, D. T. Clark, D. Shuttleworth, & A. Dilks, in "Polymer Surfaces", Ed. D. T. Clark & W. J. Feast, Wiley, London, 1979
6. Plasma Polymerization 1979-80, D. Shuttleworth in Macromolecular Chemistry, Vol. 2, Royal Society of Chemistry, London, 1982

APPENDIX

TABLE #

TITLE

1	THIOPHENE EXPERIMENTAL DESIGN I
2	THIOPHENE EXPERIMENTAL DESIGN II
3	THIOPHENE EXPERIMENTAL DESIGN III
4	THIOPHENE EXPERIMENTAL DESIGN IV
5	HMDSO EXPERIMENTAL DESIGN I
6	HMDSN EXPERIMENTAL DESIGN I
7	HMDSN EXPERIMENTAL DESIGN II
8	DATA FOR THIOPHENE DESIGN I
9	DATA FOR THIOPHENE DESIGN II
10	DATA FOR RUNS AT CONDITIONS MODIFIED FROM THIOPHENE DESIGNS I AND II
11	DATA FOR SELECTED RUNS FROM THIOPHENE DESIGNS I AND II AT 500 MICROGRAMS PER SQUARE CENTIMETER
12	DATA FOR THIOPHENE DESIGN III
13	DATA FOR THIOPHENE DESIGN IV
14	DATA FOR THIOPHENE DESIGN III-A AT 500 MICROGRAMS PER SQUARE CENTIMETER
15	DATA FOR SELECTED RUNS FROM THIOPHENE DESIGN IV AT 500 MICROGRAMS PER SQUARE CENTIMETER
16	DATA FOR HMDSO DESIGN I
17	DATA FOR HMDSN DESIGN I
18	DATA FOR HMDSN DESIGN II
19	SUMMARY OF AVERAGED DATA OF RUNS IN THIOPHENE DESIGN I, II, III, AND IV
20	SUMMARY OF AVERAGED DATA OF SELECTED RUNS FROM THIOPHENE DESIGNS III AND IV
21	SUMMARY OF AVERAGED DATA OF RUNS IN HMDSO DESIGN I
22	SUMMARY OF AVERAGED DATA OF RUNS IN HMDSN DESIGNS I AND II
23	PROPERTIES OF THE 15 BEST CORROSION PROTECTION COATINGS
24	FIRST ORDER EFFECTS OF PROCESS VARIABLES

FIG. 1 VACUUM PLASMA POLYMERIZATION REACTOR AND SYSTEM

TABLE 1
THIOPHENE EXPERIMENTAL DESIGN I

Design Order	Run Number	Flow sccm	Press mTorr	Power w	Run Order
1	A59A9	-	-	-	8
2	A59A2	+	-	-	2
3	A59A4	-	+	-	4
4	A59A7	+	+	-	6
5	A59A1	-	-	+	1
6	A59A6	+	-	+	5
7	A59A8	-	+	+	7
8	A59A3	+	+	+	3
<hr/>					
Variables		-	+		
<hr/>					
Flow		2.1	29		
Press		250	500		
Power		10	50		

TABLE 2
THIOPHENE EXPERIMENTAL DESIGN II

Design Order	Run Number	Flow sccm	Press mTorr	Power w	Run Order
1	A59B9	-	-	-	8
2	A59B3	+	-	-	3
3	A59B4	-	+	-	4
4	A59B7	+	+	-	6
5	A59B2	-	-	+	2
6	A59B6	+	-	+	5
7	A59B8	-	+	+	7
8	A59B1	+	+	+	1
 Variables					
Flow - 2.1 29					
Press 500 1000					
Power 50 100					

Note 1: The following additional thiophene runs were made.

Run Number	Flow sccm	Press mTorr	Power w	Run Order
A59C1	3	250	50	1
A59C2	3	500	100	2

Note 2: The better samples from Thiophene Experimental Designs I and II were repeated to a coating thickness of approximately 0.5mg/sqcm. The flow (-) values were changed from 2.1 to 3 sccm.

TABLE 3
THIOPHENE EXPERIMENTAL DESIGN III

Design Order	Run Number	Power w	Press mTorr	Flow sccm	Temp deg C	Run Order
1	A59A59	-	-	-	-	3
2	A59A57	+	-	-	+	2
3	A59A67	-	+	-	+	8
4	A59A65	+	+	-	-	6
5	A59A66	-	-	+	+	7
6	A59A55	+	-	+	-	1
7	A59A61	-	+	+	-	4
8	A59A63	+	+	+	+	5

Variables	-	+
Power	10	50
Press	250	500
Flow	3	29
Temp	50	150

TABLE 3
THIOPHENE EXPERIMENTAL DESIGN III

Design Order	Run Number	Power w	Press mTorr	Flow sccm	Temp deg C	Run Order
1	A59A59	-	-	-	-	3
2	A59A57	+	-	-	+	2
3	A59A67	-	+	-	+	8
4	A59A65	+	+	-	-	6
5	A59A66	-	-	+	+	7
6	A59A55	+	-	+	-	1
7	A59A61	-	+	+	-	4
8	A59A63	+	+	+	+	5

Variables	-	+
Power	10	50
Press	250	500
Flow	3	29
Temp	50	150

TABLE 4
THIOPHENE EXPERIMENTAL DESIGN IV

Design Order	Run Number	Power w	Press mTorr	Flow sccm	Temp deg C	Run Order
1	A59B72	-	-	-	-	5
2	A59B70	+	-	-	+	3
3	A59B75	-	+	-	+	8
4	A59B71	+	+	-	-	4
5	A59B68	-	-	+	+	1
6	A59B74	+	-	+	-	7
7	A59B69	-	+	+	-	2
8	A59B73	+	+	+	+	6

Variables	-	+
Power	50	100
Press	250	500
Flow	3.9	29
Temp	150	250

Note 1: The better samples from Thiophene Experimental Designs III and IV were repeated to a coating thickness of approximately 500 ug/sqcm.

TABLE 5
HMDSO EXPERIMENTAL DESIGN I

Design Order	Run Number	Power w	Flow sccm	Press mTorr	Temp deg C	Run Order
1	A59S0128	-	-	-	-	8
2	A59S0124	+	-	-	+	4
3	A59S0123	-	+	-	+	3
4	A59S0129	+	+	-	-	9
5	A59S0130	-	-	+	+	10
6	A59S0126	+	-	+	-	6
7	A59S0127	-	+	+	-	7
8	A59S0125	+	+	+	+	5
0	A59S0120, A59S0121 A59S0131, A59S0132	1/2	1/2	1/2	1/2	1,2 11,12

Variables	-	+	1/2
Power	50	200	95
Flow	3.5	30	7.8
Press	350	1000	675
Temp	150	250	200

TABLE 6
HMDSN EXPERIMENTAL DESIGN I

Design Order	Run Number	Power w	Flow HMDSN sccm	Flow O2 sccm	Press mTorr	Run Order
1	86428, 864213	-	-	-	-	8, 13
2	86414	+	-	-	+	4
3	86413	-	+	-	+	3
4	86429	+	+	-	-	9
5	864210	-	-	+	+	10
6	86416	+	-	+	-	6
7	86417	-	+	+	-	7
8	86415	+	+	+	+	5
0	86381, 86382 864211, 864212	1/2	1/2	1/2	1/2	1, 2 11, 12

Variables	-	+	1/2
Power	50	200	125
Flow HMDSN	3.5	29	8
Flow O2	2	5	3
Press	250	1000	625

Note 1: The following runs were made with the pressure valve left open; ie, minimum pressure for the flow rates with the system vacuum pump.

Run Number	Power w	Flow HMDSN sccm	Flow O2 sccm
864214, 864215	200	3.5	2
864316	200	2.4	2

TABLE 7
HMDSN EXPERIMENTAL DESIGN II

Design Order	Run Number	Power w	Flow HMDSN sccm	Flow O2 sccm	Press mTorr	Run Order
1	86445	-	-	-	-	5
2	86457	+	-	-	+	7
3	86446	-	+	-	+	6
4	864510	+	+	-	-	10
5	86459	-	-	+	+	9
6	86443, 864813	+	-	+	-	3, 13
7	86444	-	+	+	-	4
8	86458	+	+	+	+	8
9	86431, 86432 864511, 864512	1/2	1/2	1/2	1/2	1, 2 11, 12

Variables	-	+	1/2
Power	50	200	125
Flow HMDSN	2.4	3.5	3
Flow O2	0	2	2
Press	175	250	213

TABLE 8
DATA FOR THIOPHENE DESIGN I

Design Order	Run Number	Power w	Press. Set mT	Press. Obt mT	Flow1 Set secm	Flow1 Obt secm	Flow2 Set secm	Flow2 Obt secm	Time min	Sample Number	Weight Gain. g
1	A59A9	10	250	250	10	2.1	12	12	12	1	0.0002
										2	0.0003
										3	0.0002
										4	0.0001
2	A59A2	10	250	250	150	29	15	15	15	1	0.0032
										2	0.0034
										3	0.0043
										4	0.0038
3	A59A4	10	500	500	10	2.1	40	40	40	1	0.0020
										2	0.0016
										3	0.0019
										4	0.0017
4	A59A7	10	500	500	150	135	20	29	29	1	0.0135
										2	0.0150
										3	0.0118
										4	0.0099
5	A59A1	50	250	250	10	2.1	10	10	10	1	0.0008
										2	0.0004
										3	0.0001
										4	0.0002
6	A59A6	50	250	250	150	29	2	2	2	1	0.0007
										2	0.0008
										3	0.0006
										4	0.0009
7	A59A8	50	500	500	10	2.1	45	45	45	1	0.0005
										2	0.0004
										3	0.0004
										4	0.0004
8	A59A3	50	500	500	150	29	6	6	6	1	0.0069
										2	0.0062
										3	0.0052
										4	0.0061

TABLE 8

Wt Rate g/min	Thickness g/sqcm	Thick Rate g/sqcm/min	T-mon rate Amp/min	Qual
1.7E-05	3.2E-05	2.7E-06	21.2	F
2.5E-05	4.8E-05	4.0E-06		F
1.7E-05	3.2E-05	2.7E-06		F
8.3E-06	1.6E-05	1.3E-06		F
2.1E-04	5.1E-04	3.4E-05	22.9	F
2.3E-04	5.4E-04	3.6E-05		F
2.9E-04	6.9E-04	4.6E-05		P
2.5E-04	6.0E-04	4.0E-05		P
5.0E-05	3.2E-04	8.0E-06	5.45	P
4.0E-05	2.6E-04	6.4E-06		P
4.0E-05	2.6E-04	6.4E-06		P
4.2E-05	2.7E-04	6.8E-06		P
4.7E-04	2.1E-03	7.4E-05	8.97	P
5.2E-04	2.4E-03	8.3E-05		P
4.1E-04	1.9E-03	6.5E-05		P
3.4E-04	1.6E-03	5.5E-05		P
8.0E-05	1.3E-04	1.3E-05	18.6	F
4.0E-05	6.4E-05	6.4E-06		F
1.0E-05	1.6E-05	1.6E-06		F
2.0E-05	3.2E-05	3.2E-06		F
3.5E-04	1.1E-04	5.6E-05	364	F
4.0E-04	1.3E-04	6.4E-05		F
3.0E-04	9.6E-05	4.8E-05		F
4.5E-04	1.4E-04	7.2E-05		F
1.1E-05	8.0E-05	1.8E-06	5.91	F
8.9E-06	6.3E-05	1.4E-06		F
8.9E-06	6.3E-05	1.4E-06		F
8.9E-06	6.3E-05	1.4E-06		F
1.2E-03	1.1E-03	1.8E-04	47.3	P
1.0E-03	9.6E-04	1.6E-04		P
8.7E-04	8.4E-04	1.4E-04		P
1.0E-03	9.6E-04	1.6E-04		P

TABLE 8

Comments and Observations

Film
Film
On glass, film
On glass, film
Slight powder
Slight powder
Piece jumped to top electrode during run
On glass, slight powder
Powder; press, drop, took 10 min to line out
Powder; press, drop, took 10 min to line out
On glass, powder; press, drop, took 10 min to line out
On glass, powder; press, drop, took 10 min to line out
Powder; flow dropped to 130
Powder; flow dropped to 130
On glass, powder, some film; flow dropped to 130
On glass, powder, some film; flow dropped to 130
Piece jumped to top electrode during run
Piece jumped to top electrode during run
On glass, film
On glass, film
(Film, small amt powder
Film, small amt powder
On glass, film, small amt powder
On glass, film, small amt powder
Film, small amt powder
Film, small amt powder
On glass, film
On glass, film
Loose powder
Loose powder
On glass, loose powder
On glass, loose powder

TABLE 8

Scratch 1	Scratch 2	Pull Test	Acid Sery	CuSO ₄ 10cry	Neut Sery	CuSO ₄ 10cry	Ferroxil Sery	CuSO ₄ 10cry
0	0			0	0	0.1	0.2	>0.1
50	100							
1000	5000			1.8	3.5	0.6	0.2	0.5
500	1500	20						
100	2000		>0.5		2.5		>0.4	
500	5000		0.2	0.3	2.2		>0.2	
100	900	1140						
100	2000							
200	500	30						
100	400							
200	400		0.2		0.1	0.2	0	0
0	700							
1000	5000		0.2	0.4	>1.2		0.1	0.2
0	4000							
0	5000							
0	800		0.2	0.5	>0.4		>0.2	
0	600							
10	1000							
50	900							

Note for microscope tests time to 5 and 10 crystals is in min and > means time to less than 5 crystals.

TABLE 8

Notes

Ac CuSO₄ formed 500+ crystals in 27 sec

Scratch test 2 questionable
Scratch test 2 questionable

Scratch test 2 questionable

Ferroxil formed 50+ crystals in 10 sec

Stud not affix to coating for Pull test
Scratch test 2 questionable
Scratch test 2 questionable
Scratch test 2 questionable
Stud not affix to coating for Pull test

TABLE 9

Design Order	Run Number	Power w	Press. Set	mT Obt	Flow1 Set	Flow1 Obt	Flow2 sccm	Time min	Sample Number	Weight Gain. g
1	A59B9	50	500	500	10	2.1	74	1	0.0006	
						74		2	0.0007	
						74		3	0.0012	
						74		4	0.0005	
2	A59B3	50	500	500	150	29	4	1	0.0041	
						4		2	0.0039	
						4		3	0.0037	
						4		4	0.0036	
3	A59B4	50	1000	510	10	2.1	17	1	0.0012	
						17		2	0.0012	
						17		3	0.0009	
						17		4	0.0012	
4	A59B7	50	1000	1000	140 135	20	7	1	0.0067	
						7		2	0.0063	
						7		3	0.0046	
						7		4	0.0048	
5	A59B2	100	500	500	10	2.1	25	1	0.0004	
						25		2	0.0005	
						25		3	0.0003	
						25		4	0.0003	
6	A59B6	100	500	500	150	29	2	1	0.0011	
						2		2	0.0011	
						2		3	0.0010	
						2		4	0.0011	
7	A59B8	100	1000	<1000	10	2.1	42	1	0.0007	
						42		2	0.0006	
						42		3	0.0018	
						42		4	0.0022	
8	A59B1	100	1000	1000	150	29	3	1	0.0038	
						3		2	0.0038	
						3		3	0.0034	
						3		4	0.0034	

TABLE 9

Wt Rate g/min	Thickness g/sccm	Thick Rate g/sccm/min	T-mon rate Ans/min	Gual
8.1E-06	9.6E-05	1.3E-06	3.38	F
9.5E-06	1.1E-04	1.5E-06		F
1.6E-05	1.9E-04	2.6E-06		F
6.8E-06	8.1E-05	1.1E-06		F
1.0E-03	6.4E-04	1.6E-04	76.8	P
9.8E-04	6.4E-04	1.6E-04		P
5.2E-04	6.0E-04	1.5E-04		F
9.0E-04	5.6E-04	1.4E-04		P
7.1E-05	1.9E-04	1.1E-05	14.5	P
7.1E-05	1.9E-04	1.1E-05		P
5.3E-05	1.4E-04	8.5E-06		P
7.1E-05	1.9E-04	1.1E-05		P
9.6E-04	1.0E-03	1.5E-04	38.6	F
9.0E-04	1.0E-03	1.4E-04		P
6.6E-04	7.0E-04	1.0E-04		P
6.3E-04	7.7E-04	1.1E-04		P
1.6E-05	6.5E-05	2.6E-06	9.72	F
2.0E-05	8.0E-05	3.2E-06		F
1.2E-05	4.8E-05	1.9E-06		F
1.2E-05	4.8E-05	1.9E-06		F
5.5E-04	1.6E-04	8.8E-05	172	F
5.5E-04	1.8E-04	8.8E-05		F
5.0E-04	1.6E-04	8.0E-05		F
5.5E-04	1.8E-04	8.8E-05		F
1.7E-05	1.1E-04	2.7E-06	5.61	F
1.4E-05	9.7E-05	2.3E-06		F
4.3E-05	2.9E-04	6.9E-06		F
5.2E-05	3.5E-04	8.4E-06		F
1.3E-03	6.0E-04	2.0E-04	116	P
1.3E-03	6.0E-04	2.0E-04		P
1.1E-03	5.4E-04	1.8E-04		P
1.1E-03	5.4E-04	1.8E-04		P

TABLE 9

Comments and Observations

Film
Film
On glass, film
On glass, film
Partial powder
Partial powder
On glass, partial powder
On glass, partial powder
Powder
Powder
On glass, powder
On glass, powder
Thick powder; flow unstable
Thick powder; flow unstable
On glass, thick powder; flow unstable
On glass, thick powder; flow unstable
Film
Film
On glass, film
On glass, film
Film, small amt powder
Film, small amt powder
On glass, film
On glass, film
Film, small amt powder; press, took 20 min to line out
Film, small amt powder; press, took 20 min to line out
On glass, film; press, took 20 min to line out
On glass, film; press, took 20 min to line out
Powder
Powder
On glass, powder
On glass, powder

TABLE 9

Scratch 1	Scratch 2	Pull Test	Acid Scrib	Cu504 Scrib	Neut Scrib	Cu834 Scrib	Ferricill Scrib
			0.2	0.4	0.1	0.2	0.1
0	500						
0	300						
100	200						
100	600		0.1	0.2	0.7		0.1
100	300						0.5
100	200		0.1	0.2	0.3		0
10	1000						0.1
			0.2		>0.3		>0.2
10	150						
0	10						
0	200		0.1	0.2	0.2	0.3	0.1

TABLE 9

Notes

Stud not affix to coating for Pull test

Stud not affix to coating for Pull test

Scratch test B questionable

TABLE 10
DATA FOR RUNS AT CONDITIONS MODIFIED
FROM THIOPHENE DESIGNS I AND II

Design Order	Run Number	Power w	Press. Set	Flow1 mT	Flow2 Set	Flow2 Obt	Time sec	Sample Number	weight g
5	A5503	50	250	150	15		3	6	0.0005
							6	6	0.0005
							6	6	0.0004
							6	6	0.0005
5	A5505	100	500	450	15		6	10	0.0014
							10	10	0.0005
							10	9	0.0005
							10	4	0.0005

TABLE 10

wt Rate s/min	Thickness c/sccm	Thick Rate c/sccm/min	T-mon rate Ans/min	Qual
6.3E-05	7.6E-05	1.3E-05	43.7	F
8.3E-05	7.8E-05	1.3E-05		F
6.7E-05	6.6E-05	1.1E-05		F
8.3E-05	7.8E-05	1.3E-05		F
4.0E-05	6.4E-05	6.4E-06	25.6	F
2.0E-05	3.2E-05	3.2E-06		F
3.0E-05	4.8E-05	4.8E-06		F
5.0E-05	8.0E-05	8.0E-06		F

TABLE 10

Comments and Observations

Film: press, crop to 120

Film: press, crop to 120

On glass, film: press, crop to 120

On glass, film: press, crop to 120

mostly film: press, crop, took 6 min to line out

mostly film: press, crop, took 6 min to line out

On glass, mostly film: press, crop, took 6 min to line out

On glass, mostly film: press, crop, took 6 min to line out

TABLE 10

Scratch 1	Scratch 2	Pull Test	Acid Scry	CuSO ₄ 10cry	Neut Scry	CuSO ₄ 10cry	Ferroxil Scry	CuSO ₄ 10cry
0	100		0.2	0.3	0.2	0.3	>0.7	
0	500							
10	500							
80	500							
0	500							
10	900		1.8		3.0		>0.3	
20	1000							

TABLE 10

Notes

Scratch test 2 questionable

Scratch test 2 questionable

Stud not affix to coating for Pull test

Stud not affix to coating for Pull test

TABLE 11
DATA FOR SELECTED RUNS FROM THIOPHENE DESIGNS I AND II
AT 500 MICROGRAMS PER SQ. CENTIMETER

Design Order	Run Number	Power w	Press. mT Set	Flow1 Set	Flow2 Set	Flow3 Set	Time sec	Temp °C	Sample Number	Weight Gain. g	
1	A55A13	10	250	220	15	3	120	>82	1	0.0034	
							120		2	0.0032	
							120		3	0.0033	
							120		4	0.0033	
							120		5	0.0045	
							120		6	0.0039	
5	A55A11	50	250	153	15	3	120	>88	1	0.0011	
							120		2	0.0082	
							120		3	0.0081	
							120		4	0.0087	
							120		5	0.0037	
							120		6	0.0039	
5	A55B03	50	250	250	15	3	38	>82	1	0.0010	
							38		2	0.0010	
							38		3	0.0012	
							38		4	0.0010	
							38		5	0.0013	
							38		6	0.0012	
6	A55A10	50	250	250	150	29	12	>82	1	0.0034	
							12		2	0.0040	
							12		3	0.0037	
							12		4	0.0038	
							12		5	0.0052	
							12		6	0.0056	
7	A55C04	50	500	400	15	3	120	>82	1	0.0025	
							120		2	0.0022	
							120		3	0.0024	
							120		4	0.0024	
							120		5	0.0037	
							120		6	0.0038	
1	A55B13	50	500	310	15	3	120	>127	1	0.0036	
							120		2	0.0034	
							120		3	0.0036	
							120		4	0.0033	
							120		5	0.0045	
							120		6	0.0048	
5	A55B11	100	500	500	15	3	124	>138	1	0.0018	
							124		2	0.0022	
							124		3	0.0020	
							124		4	0.0018	
							124		5	0.0026	
							124		6	0.0023	
6	A55B10	100	500	500	150	143	25	13	?	1	0.0066
							13		2	0.0069	
							13		3	0.0075	
							13		4	0.0073	
							13		5	0.0069	
							13		6	0.0101	
7	A55B12	100	1000	1000	15	3	120	>138	1	0.0039	
							120		2	0.0042	
							120		3	0.0047	
							120		4	0.0040	
							120		5	0.0055	
							120		6	0.0060	

TABLE 11

wt Rate g/min	Thickness cm/sec	Thick Rate cm/sec/g/min	T-mon rate Ans/min	Qual
2.8E-05	5.4E-04	4.5E-06	68.0	F
2.7E-05	5.2E-04	4.3E-06		F
2.8E-05	5.3E-04	4.4E-06		F
2.8E-05	5.3E-04	4.4E-06		F
3.5E-05	4.7E-04	3.9E-06		F
3.2E-05	4.1E-04	3.4E-06		F
1.6E-05	3.0E-04	2.5E-06	62.7	F
1.8E-05	3.5E-04	2.9E-06		F
1.8E-05	3.4E-04	2.8E-06		F
3.2E-05	4.3E-04	3.6E-06		F
3.1E-05	3.8E-04	3.2E-06		F
3.2E-05	4.1E-04	3.4E-06		F
2.6E-05	1.6E-04	4.2E-06	20.2	F
2.6E-05	1.6E-04	4.2E-06		F
3.2E-05	1.9E-04	5.0E-06		F
2.6E-05	1.6E-04	4.2E-06		F
2.6E-05	1.6E-04	4.2E-06		F
3.2E-05	1.9E-04	5.0E-06		F
2.8E-04	5.4E-04	4.5E-05	156	F
3.3E-04	6.4E-04	5.3E-05		F
3.1E-04	5.9E-04	4.9E-05		F
3.2E-04	6.1E-04	5.1E-05		F
4.3E-04	5.4E-04	4.5E-05		F
4.7E-04	5.8E-04	4.8E-05		F
2.1E-05	4.0E-04	3.3E-06	39.6	F
1.8E-05	3.5E-04	2.9E-06		F
2.0E-05	3.8E-04	3.2E-06		F
2.0E-05	3.8E-04	3.2E-06		F
3.1E-05	3.8E-04	3.2E-06		F
3.2E-05	4.0E-04	3.3E-06		F
3.0E-05	5.8E-04	4.8E-06	57.0	F
2.8E-05	5.4E-04	4.5E-06		F
3.2E-05	6.1E-04	5.1E-06		F
2.8E-05	5.3E-04	4.4E-06		F
3.8E-05	4.7E-04	3.9E-06		F
4.0E-05	4.9E-04	4.1E-06		F
1.5E-05	2.9E-04	2.3E-06	9.90	F
1.8E-05	3.5E-04	2.8E-06		F
1.6E-05	3.2E-04	2.6E-06		F
1.5E-05	2.9E-04	2.3E-06		F
2.3E-05	2.9E-04	2.3E-06		F
1.9E-05	2.4E-04	1.9E-06		F
5.1E-04	1.1E-03	8.1E-05	125	F
5.3E-04	1.1E-03	8.5E-05		F
5.8E-04	1.2E-03	9.2E-05		F
5.6E-04	1.2E-03	9.0E-05		F
5.3E-04	7.2E-04	5.5E-05		F
7.8E-04	1.0E-03	8.0E-05		F
3.2E-05	6.2E-04	5.2E-06	31.2	F
3.5E-05	6.7E-04	5.6E-06		F
3.9E-05	7.6E-04	6.3E-06		F
3.3E-05	6.4E-04	5.3E-06		F
4.6E-05	5.6E-04	4.7E-06		F
5.0E-05	6.2E-04	5.2E-06		F

TABLE 11

Comments and Observations

Film: slow press. drop (250-206-197); flow unstable
 Film: press. drop; flow unstable
 Film rainbow with cold hue
 Film rainbow with cold hue, slightly powdery
 Film: some brown powder; flow unstable; press. drop to 206
 Film: some brown powder; flow unstable; press. drop to 206
 Film: some brown powder; flow unstable; press. drop to 206
 Film: some brown powder; flow unstable; press. drop to 206
 Film: some brown powder; flow unstable; press. drop to 206
 Film: some brown powder; flow unstable; press. drop to 206
 Part film + powder; press. + RF power reverse unstable
 Part film + powder; press. + RF power reverse unstable
 Part film + powder; press. + RF power reverse unstable
 Part film + powder; press. + RF power reverse unstable
 Part film + powder; press. + RF power reverse unstable
 Part film + powder; press. + RF power reverse unstable
 Film. small amt brown powder
 Thick powder; flow unstable
 Thick powder; flow unstable
 Thick powder; flow unstable
 Thick powder; flow unstable
 Thick powder; flow unstable; sample dropped
 Thick powder; flow unstable
 Deep brown powder, some film
 Deep brown powder, some film

TABLE 11

Scratch	Scratch	Ball	Solid CuSO ₄	Neut CuSO ₄	Ferricxit	Salt
1	2	Test	5Cry 10Cry	5Cry 10Cry	5Cry 10Cry	%
2000	5000		>0.7	>4.5	>5.9	
2000	5000	0				
					>0.8	
3000	6000	0	>0.3	>2.6		
900	10000					
						1
500	5000					
500	5000		0.2	0.4	0.1	0.2
						48
10	6000					
500	5000	0				
400	5000	10				
900	2000		1.0	1.3		
			0.5	0.7	1.4	>0.2
(1
1000	6000					
500	7000					
			3.3	2.6		>6.0
						1
10000	10					
7000						
			1.1	2.8		>4.0
						1
50	5000					
200	4000	10	1.8	1.8		>1.7
						48
1000	10000					
1000	6000	810				
			2.9	0.6	1.2	>3.5
						5

TABLE 11

Notes

Ac CuSO₄ & Ferr wrinkled coating; Ferr formed in blob

Coating wrinkled 40 min into SS test
Ferroxil wrinkles coating

Ac CuSO₄ eats coating in 2 min

Coating flaked off 40 min into SS test
Scratch tests 1 & 2 questionable
Scratch tests questionable; stud not affix to coating

20% rust after 1 da

Scratch test 2 questionable

Scratch test 2 questionable
Ac CuSO₄ wrinkled coating

(Coating wrinkled 40 min into SS test
Stud not affix to coating for Pull test

Coating wrinkled and flaked 40 min into SS test
Scratch test questionable
Scratch test questionable

Ferr formed white then 500+ yellow crys in 23 min
Most of coating flaked 1 h into SS test

20% rust after 1 da

Scratch tests questionable
Scratch tests questionable

Coating flaked off 5 h into SS test

TABLE 12
DATA FOR THIOPHENE DESIGN III

Design Order	Run Number	Power w	Press, mT		Flow set		Flow obs		Flow secm		Temp, deg C	Time min.
			set	obs	set	obs	set	obs	secm	set		
1	A59A55	10	250	248	15	15	3	50	56	10	10	
2	A59A57	50	250	248	15	14.6	2.9	150	147	3	3	
3	A59A67	10	500	485	15	15	3	150	146	6	6	
4	A59P65	50	500		15	15	3	50	58	4	4	
5	A59A66	10	250	249	150	150	29	150	148	5	5	
6	A59A55	50	250	249	150	150	29	50	57	3	3	
7	A59P61	20	500		150	150	29	50	50	13	13	
8	A59P63	50	500		150	148	28	150	160	3	3	

TABLE 12

Sample Number	Weight Gain, g	Wt Rate g/min	Thickness s/sccm	Thick Rate t/sccm/min	T-mon Rate Ans/min	Dual itv
1	0.0002	2.0E-05	3.2E-05	3.2E-06	31.9	F
2	0.0002	2.0E-05	3.2E-05	3.2E-06	31.9	F
3	0.0002	6.7E-05	5.4E-05	1.6E-05	98.3	F
4	0.0001	3.3E-05	2.6E-05	9.2E-06	98.3	F
5	0.0001	1.2E-05	1.6E-05	2.0E-06	32.9	F
6	-0.0002				32.9	
7	0.0002	5.0E-05	3.2E-05	8.0E-06	67.0	F
8	0.0001	2.5E-05	1.6E-05	4.0E-06	67.0	F
9	0.0001	2.0E-05	1.6E-05	3.2E-06	58.2	F
10	0.0001	2.0E-05	1.6E-05	3.2E-06	58.2	F
11	0.0005	1.7E-04	8.1E-05	2.7E-05	245	F
12	0.0005	3.0E-04	1.4E-04	4.8E-05	245	F
13	0.0002	1.5E-05	3.2E-05	2.5E-06	22.7	F
14	0.0004	3.1E-05	6.4E-05	4.9E-06	22.7	F
15	0.0011	3.7E-04	1.6E-04	6.0E-05	503	F
16	0.0009	3.0E-04	1.4E-04	4.8E-05	503	F

TABLE 12

Comments and Observations	Scratch	
	1	2
4		
Eliminate oxygen pretreat: use thin copper plate	4	
Press area to 440	4	
Press 326 during run(?); sample 2, cloudy, some powder	4	400
Flow needed adjustment	4	10
	20	700
unable to set power at 10 w; film looked cloudy	4	10
Solid film with thin layer of powder over it	10	500

TABLE 13
DATA FOR THIOPHENE DESIGN IV

Design Order	Run Number	Power w	Press. mT set obs	Flow set obs	Flow set obs	Flow set obs	Temp. deg C set obs	Time min
1	A59E72	50	250 249	15 15	3	150 146	40 40	
2	A59E70	100	250 249	15 15	3	250 254	22 22	
3	A59E75	50	500 500	15 15	3	250 246	35 35	
4	A59E71	100	500 500	15 15	3	150 156	45 45	
5	A59E66	50	250 250	150 150	29	250 246	10 10	
6	A59E74	100	250 253	150 150	29	150 155	15 15	
7	A59E69	50	500 500	150 150	29	150 146	10 10	
8	A59E73	100	500 498	150 150	29	250 251	10 10	

TABLE 13

Sample Number	Weight Gain, g	wt Rate, g/min	Thickness, μ/scm	Thick Rate, $\mu/\text{scm}/\text{min}$	Dual ity
1	0.0004	1.0E-05	6.4E-05	1.6E-06	F
2	0.0004	1.0E-05	6.4E-05	1.6E-06	F
1	0.0001	4.5E-06	1.6E-05	7.3E-07	BF
2	0.0000				BF
1	0.0000				F
2	0.0003	8.6E-06	4.9E-05	1.4E-06	F
1	0.0002	4.4E-06	3.2E-05	7.1E-07	F
2	0.0003	6.7E-06	5.0E-05	1.1E-06	F
1	0.0012	8.0E-05	2.0E-04	1.3E-05	F
2	0.0011	7.3E-05	1.8E-04	1.2E-05	F
1	0.0015	1.0E-04	2.4E-04	1.6E-05	F
2	0.0017	1.1E-04	2.7E-04	1.8E-05	F
1	0.0048	3.2E-04	7.7E-04	5.1E-05	P
2	0.0051	3.4E-04	8.1E-04	5.4E-05	P
1	0.0015	1.0E-04	2.4E-04	1.6E-05	F
2	0.0021	1.4E-04	3.3E-04	2.2E-05	F

TABLE 13

Comments and Observations	Scratch 1	Scratch 2	Notes and Observations
Rotate platform by hand: press fluctuated	4	10	
Blue hue (oxidation?); press fluc.: rotate platform by hand	4		
Press fluctuated	4	50	
Rotate platform by hand	4	20	
	40	2500	
Press fluctuated	250	7000	
Gold film under powder	2000	4500	Scratch tests questionable
	300	6000	
Press fluctuated	70	3000	

TABLE 14
DATA FOR THIOPHENE DESIGN III-A
AT 500 MICROGRAMS PER SQ. CENTIMETER

TABLE 14

Sample Number	Weight Gain, g	Wt Rate g/min	Thickness g/sccm	Thick Rate g/sccm/min	T-mov Rate Ang/min	Dual ity
1	0.0038	3.2E-05	6.1E-04	5.1E-06		F
2	0.0039	3.2E-05	6.2E-04	5.2E-06		
3	0.0037	3.1E-05	5.9E-04	4.9E-06		
4	0.0038	3.2E-05	6.1E-04	5.1E-06		
5	0.0053	4.4E-05	5.5E-04	4.6E-06		
6	0.0057	4.8E-05	5.9E-04	4.9E-06		
1	0.0004	1.1E-05	6.5E-05	1.8E-06		
2	0.0005	1.4E-05	7.9E-05	2.2E-06		
3	0.0003	8.3E-06	4.7E-05	1.3E-06		
4	0.0003	8.3E-06	4.7E-05	1.3E-06		
5	0.0004	1.1E-05	4.3E-05	1.2E-06		
6	0.0006	1.7E-05	6.1E-05	1.7E-06		
1	0.0025	2.1E-05	4.0E-04	3.3E-06		
2	0.0024	2.0E-05	3.8E-04	3.2E-06		
3	0.0023	1.9E-05	3.7E-04	3.1E-06		
4	0.0027	2.2E-05	4.3E-04	3.6E-06		
5	0.0038	3.2E-05	4.0E-04	3.3E-06		
6	0.0033	2.8E-05	3.4E-04	2.8E-06		
1	0.0024	2.9E-05	3.8E-04	4.6E-06		
2	0.0020	2.4E-05	3.2E-04	3.9E-06		
3	0.0022	2.7E-05	3.5E-04	4.2E-06		
4	0.0023	2.8E-05	3.7E-04	4.4E-06		
5	0.0036	4.3E-05	3.7E-04	4.5E-06		
6	0.0035	4.2E-05	3.7E-04	4.4E-06		
1	0.0024	3.6E-05	3.8E-04	5.8E-06		
2	0.0016	2.4E-05	2.6E-04	3.9E-06		
3	0.0020	3.0E-05	3.2E-04	4.8E-06		
4	0.0021	3.2E-05	3.4E-04	5.1E-06		
5	0.0043	6.5E-05	4.4E-04	6.7E-06		
6	0.0040	6.1E-05	4.2E-04	6.3E-06		
1	0.0027	1.9E-04	4.3E-04	3.1E-05		
2	0.0027	1.9E-04	4.3E-04	3.1E-05		
3	0.0028	2.0E-04	4.5E-04	3.2E-05		
4	0.0027	1.9E-04	4.3E-04	3.1E-05		
5	0.0040	2.9E-04	4.2E-04	3.0E-05		
6	0.0036	2.6E-04	3.6E-04	2.6E-05		
1	0.0035	2.8E-05	5.6E-04	4.5E-06		
2	0.0028	2.2E-05	4.5E-04	3.6E-06		
3	0.0037	3.0E-05	5.9E-04	4.7E-06		
4	0.0037	3.0E-05	5.9E-04	4.7E-06		
5	0.0066	5.3E-05	6.8E-04	5.4E-06		
6	0.0049	3.9E-05	5.0E-04	4.0E-06		

TABLE 14

Comments and Observations
Press fluctuated
Press drop to 220, rose slowly and fluctuated
Press drop to 448, rose slowly and fluctuated
Press drop to 364, rose slowly and fluctuated
Press fluctuated; thiophene ran out
Press fluctuated
Press fluctuated; coatings, fine layer powder over film

TABLE 14

TABLE 14

Abrasions
ml. sec/c

200

700

300

200

400

200

100

TABLE 14

NOTES AND
Observations

full test. stud came off when olio removed

full test. stud came off when loading in tester

salt test failed 120 h @95%

full test (in excess of). some film left

at CuSO₄. 800+ dry (6sec); N CuSO₄, same (15 sec)

salt test failed 45 h @95%

Scratches >10000 (max)

full test (in excess of). > half film left

at CuSO₄. needle-like crys form around edges

salt test failed 150 h @95% (test interrupted)

full test (in excess of). some film left

Ferroxil begins dry up 19 min (cry around edges)

salt test failed 245 h @95% (test interrupted)

full test (in excess of), some film left

Ferroxil begins dry up 22 min (cry around edges)

salt test failed 216 h @95% (test interrupted)

full test (in excess of). half film left

at CuSO₄ 3 dry (27 min)

salt test failed 72 h @95%

full test (in excess of). some film left

salt test failed 120 h @95%

TABLE 15
DATA FOR SELECTED RUNS FROM THIOPHENE DESIGN IV
AT 500 MICROGRAMS PER SQ. CENTIMETER

TABLE 15

Sample Number	Weight Gain, g	Wt Rate, g/min	Thickness, μ/secm	Thick Rate, $\mu/\text{secm}/\text{min}$	T-mon Rate, Ans/min	Dual rate
1	0.0166	1.4E-04	2.6E-03	2.2E-05		
2	0.0144	1.2E-04	2.3E-03	1.9E-05		
3	0.0165	1.4E-04	2.6E-03	2.2E-05		
4	0.0154	1.3E-04	2.4E-03	2.0E-05		
5	0.0234	2.0E-04	2.4E-03	2.0E-05		
6	0.0279	2.3E-04	2.9E-03 ¹⁵	2.4E-05 ²¹		
7	0.0010	8.3E-06	1.6E-04	1.3E-06	55.0	
8	0.0007	5.8E-06	1.1E-04	9.3E-07	59.0	
9	0.0010	8.3E-06	1.6E-04	1.3E-06	59.0	
10	0.0007	5.8E-06	1.1E-04	9.3E-07	59.0	
11	0.0013	1.1E-05	1.3E-04	1.1E-06	55.0	
12	0.0015	1.2E-05	1.6E-04	1.2E-06	55.0	
13	0.0029	5.6E-05	4.6E-04	6.9E-06		
14	0.0038	7.3E-05	6.2E-04	1.2E-05		
15	0.0030	5.8E-05	4.6E-04	9.2E-06		
16	0.0033	6.3E-05	5.2E-04	1.0E-05		
17	0.0029	7.5E-05	4.0E-04	7.7E-06		
18	0.0042	8.7E-05	4.6E-04	8.9E-06		
19	0.0023	5.5E-05	3.7E-04	8.8E-06		
20	0.0023	5.5E-05	3.7E-04	8.8E-06		
21	0.0026	6.2E-05	4.2E-04	9.9E-06		
22	0.0022	5.2E-05	3.5E-04	8.4E-06		
23	0.0054	1.3E-04	5.5E-04	1.3E-05		
24	0.0029	6.9E-05	3.0E-04	7.1E-06		
25	0.0039	1.3E-04	6.4E-04	8.2E-06		
26	0.0045	1.6E-04	7.2E-04	8.5E-06		
27	0.0038	1.3E-04	6.1E-04	8.1E-06		
28	0.0039	1.3E-04	6.4E-04	8.2E-06		
29	0.0082	2.8E-04	8.4E-04	8.9E-06		
30	0.0047	1.6E-04	4.9E-04	1.7E-05		
31	0.0037	1.4E-04	6.0E-04	2.3E-05		
32	0.0051	2.0E-04	8.1E-04	3.1E-05		
33	0.0033	1.3E-04	5.2E-04	8.0E-06		
34	0.0036	1.4E-04	5.7E-04	8.2E-06		
35	0.0059	2.3E-04	6.0E-04	2.3E-05		
36	0.0052	2.0E-04	5.5E-04	2.1E-05		

TABLE 15

Comments and Observations
Press drop to 92; increased flow to 150 to bring press up to 150; coatings, black film
Press drop to 350, rose slowly and fluctuated; thickness monitor working
Press drop to 57 and stayed; when flow increased to 150, press increased to 500; trouble retaining powder
Press drop to 227, rose and fluctuated
(
Press drop to 209, rose, and fluctuated
Press fluctuated; film, dark purple, black

TABLE 15

TABLE 15

Abrasion
mi. sand

>5000

600

200

400

200

400

TABLE 15Notes and
Observations

Pull (in exc of), small amt; scratch, film flakes
 Pull (load to failure), no film left
 Re CuSO₄, 1 cry 9m 30s; both CuSO₄, drop dried

Salt test failed 128h @100% (test interrupted 2x)
 Black film makes salt test (B93-5) hard to judge
 Pull test (in excess of), some film left

Ferroxil, copper cry, then blue (B153, 12:01)

Salt test failed 32 h @ 95% (test interrupted)
 Pull test (in excess of), some film left
 Pull test same; scratch >10000 (max)

Salt test failed 72 h @95% (test interrupted)
 Pull (in exc of), some left; scratch >10000 (max)

Salt test failed 120 h @95%
 Pull (in exc of), small amt; scratch >10000 max

W CuSO₄, Ferrox: drop dried, cry around edges

Salt test failed 72h @98% (test interrupted twice)
 Pull (in exc of), some left; scratch >10000 (max)
 Film flakes off, bare metal spots (all B94's)
 Ferroxil, 3 cry after 11m 30s

Salt test failed 24 h @98% (test interrupted)

TABLE 15

Design Order	Run Number	Sample Number	XPS Binding Energies wrt C1s at 284.7	C1s chp	C1s	S2p	N1s	C1s
7	A59A87	4	532.2	1.7	163.7			0.434
3	A59B96	4	532.0	0.4	164.1 / 168	399.3		0.437
6	A59B95	2	531.9	1.4	163.5			0.440

TABLE 15

XPS Atomic Fractions		
O1s	S2p	N1s
0.419	0.147	
0.425	0.047	0.091
0.375	0.185	

TABLE 16

TABLE 16

Sample Number	Weight Gain, g	Wt Rate g/min	Thickness g/sccm	Rate g/sccm/min	Duality
1	0.0013	4.3E-05	1.4E-04	4.5E-06	F
2	0.0011	3.7E-05	1.1E-04	3.8E-06	F
3	0.0007	2.3E-05	1.1E-04	3.7E-06	F
4	0.0006	2.0E-05	9.6E-05	3.2E-06	F
5	0.0003	1.0E-05	8.4E-05	2.8E-06	F
6	0.0004	1.3E-05	1.1E-04	3.7E-06	F
7	0.0018	6.0E-05	1.9E-04	6.2E-06	F
8	0.0023	7.7E-05	2.4E-04	7.9E-06	F
9	0.0012	4.0E-05	1.9E-04	6.4E-06	F
10	0.0013	4.3E-05	2.1E-04	6.9E-06	F
11	0.0007	2.3E-05	2.0E-04	6.5E-06	F
12	0.0005	1.7E-05	1.4E-04	4.6E-06	F
13	0.0000				N
14	0.0001	3.3E-06	1.0E-05	3.4E-07	F
15	0.0000				N
16	0.0000				F
17	0.0001	3.3E-06	2.8E-05	9.2E-07	F
18	-0.0002				F
19	0.0029	9.7E-05	3.0E-04	1.0E-05	F
20	0.0029	9.7E-05	3.0E-04	1.0E-05	F
21	0.0020	6.7E-05	3.3E-04	1.1E-05	F
22	0.0022	7.3E-05	3.6E-04	1.2E-05	F
23	0.0011	3.7E-05	3.0E-04	1.0E-05	F
24	0.0012	4.0E-05	3.3E-04	1.1E-05	F
25	0.0008	2.7E-05	8.4E-05	2.8E-06	F
26	0.0011	3.7E-05	1.1E-04	3.8E-06	F
27	0.0007	2.3E-05	1.1E-04	3.7E-06	F
28	0.0007	2.3E-05	1.1E-04	3.7E-06	F
29	0.0006	2.0E-05	1.6E-04	5.5E-06	F
30	0.0003	1.0E-05	8.4E-05	2.8E-06	F
31	0.0036	1.2E-04	3.6E-04	1.2E-05	F
32	0.0024	8.0E-05	2.5E-04	8.3E-06	F
33	0.0015	5.0E-05	2.4E-04	8.0E-06	F
34	0.0012	4.0E-05	1.9E-04	6.4E-06	F
35	0.0006	2.0E-05	1.6E-04	5.5E-06	F
36	0.0008	2.7E-05	2.2E-04	7.4E-06	F
37	0.0034	1.1E-04	3.6E-04	1.2E-05	F
38	0.0034	1.1E-04	3.6E-04	1.2E-05	F
39	0.0024	8.0E-05	3.9E-04	1.3E-05	F
40	0.0033	1.1E-04	5.4E-04	1.8E-05	F
41	0.0016	5.3E-05	4.5E-04	1.5E-05	F
42	0.0010	3.3E-05	2.8E-04	9.2E-06	F
43	0.0008	2.7E-05	8.4E-05	2.8E-06	F
44	0.0015	5.0E-05	1.6E-04	5.2E-06	F
45	0.0007	2.3E-05	1.1E-04	3.7E-06	F
46	0.0069	2.3E-04	1.1E-03	3.7E-05	F
47	0.0002	6.7E-06	5.7E-05	1.9E-06	F
48	0.0007	2.3E-05	2.0E-04	6.5E-05	F

TABLE 16

Comments and Observations
Film, rainbow; Press fluctuates between 334-363, then lines out; Salt test (1) failed @97%; Pull (3) 5% film left; Micro. (4) CuSO ₄ , very small Cu crys; Ferroxil, blue crys
Film, rainbow; Salt (1) failed @100%; Pull (4) 0% film left; Micro. (3) CuSO ₄ , Cu crys; Ferroxil, blue crys
Film, rainbow; Pull (3) stud not affix to sample; Micro. (4) CuSO ₄ , Cu crys; Ferroxil, blue crys; Salt (2) failed @95-95%
Film, silver with faint lime rainbow; Flow needed periodic adjustment; Salt (1) failed @95%; Pull (3) 20% film left?; Micro. (4) CuSO ₄ , brown, small Cu crys; Ferroxil, blue crys, 100+ faint, small brown spots
Film, rainbow; Press fluctuated between 976-1020 continuously; Salt (1) failed @98%; Pull (3) 30-40% film left; Micro. (4) CuSO ₄ , Cu, gold, silver, brown crys; Ferroxil, blue crys
Film, silver, transparent & peels around edges; temp mon failed after 10 min; Salt (2) failed @95% Pull (3) stud not affix to sample; Micro. (4) within sec large area turns Cu from CuSO ₄ , blue from Ferroxil, film wrinkles; film can be easily scraped off with needle
Film, silver with white sticky, powder-like surface; Salt (1) failed @98%; Pull (4) 99% film left; Micro. (3) CuSO ₄ , gold, Cu, rust crys; Ferroxil, blue crys, soln tends to roll on sample surface
Film, rainbow w gold hue; changed temp mon 12 min into run; white foam on samples; Salt (2) failed @95%; Pull (3) stud came off; Micro. (4) CuSO ₄ , Cu crys (Neut; small crys, also brown, rust); Ferroxil, blue crys

TABLE 16

Scratch i	Scratch E	Pull psi	Salt h	Acid Scry 10crys	DuSO4 Scry 10crys	Neut Scry 10crys	DuSO4 Scry 10crys	Ferroxil Scry 10crys	Conductance MS	Abrasion mi sand
			80							300
4	700	0		0.3	0.8	0.4	0.7	2.0	8.4	560
			48							400
20	400	90		0.4	0.5	0.4	0.6	2.6	9.1	34
			120							400
4	40			0.1	0.1	0.2	0.2	4.8	9.5	200
			144							200
100	500	140		3.8	5.1	0.4	1.6	15.0		9
			144							400
4	500	190		1.2	1.9	0.3	0.8	7.0	15.0	700
			6							2100
			98							400
300	700	410		0.5	1.0	0.9	1.6	0.4	0.8	310
			56							400
4	1000			0.3	0.6	0.4	0.7	0.2	0.4	456

TABLE 16

TABLE 16

Sample Number	Weight Gain.g	Wt Rate g/min	Thickness g/sqcm	Rate g/sqcm/min	Qual ity
1	0.0022	7.3E-05	2.3E-04	7.6E-06	F
2	0.0021	7.0E-05	2.2E-04	7.2E-06	F
3	0.0015	5.0E-05	2.4E-04	8.0E-06	F
4	0.0013	4.3E-05	2.1E-04	6.9E-06	F
5	0.0006	2.0E-05	1.6E-04	5.5E-06	F
6	0.0007	2.3E-05	2.0E-04	6.5E-06	F
1	0.0017	5.7E-05	1.8E-04	5.9E-06	F
2	0.0012	4.0E-05	1.2E-04	4.1E-06	F
3	0.0011	3.7E-05	1.8E-04	5.9E-06	F
4	0.0010	3.3E-05	1.6E-04	5.3E-06	F
5	0.0005	1.7E-05	1.4E-04	4.6E-06	F
6	0.0005	1.7E-05	1.4E-04	4.6E-06	F
1	0.0023	7.7E-05	2.4E-04	7.9E-06	F
2	0.0013	4.3E-05	1.4E-04	4.5E-06	F
3	0.0005	1.7E-05	8.1E-05	2.7E-06	F
4	0.0016	5.3E-05	2.6E-04	8.5E-06	F
5	0.0002	6.7E-06	5.7E-05	1.9E-06	F
6	0.0002	6.7E-06	5.7E-05	1.9E-06	F
1	0.0027	9.0E-05	2.8E-04	9.3E-06	F
2	0.0041	1.4E-04	4.2E-04	1.4E-05	F
3	0.0017	5.7E-05	2.7E-04	9.1E-06	F
4	0.0044	1.5E-04	7.2E-04	2.4E-05	F
5	0.0019	6.3E-05	5.4E-04	1.8E-05	F
6	0.0014	4.7E-05	3.9E-04	1.3E-05	F
1	0.0020	6.7E-05	2.1E-04	6.9E-06	F
2	0.0023	7.7E-05	2.4E-04	7.9E-06	F
3	0.0010	3.3E-05	1.6E-04	5.3E-06	F
4	0.0014	4.7E-05	2.2E-04	7.5E-06	F
5	0.0008	2.7E-05	2.2E-04	7.4E-06	F
6	0.0007	2.3E-05	2.0E-04	6.5E-06	F

TABLE 16

Sample Number	Weight Gain, g	Wt Rate g/min	Thickness μ/secm	Rate $\mu/\text{secm}/\text{min}$	Qual ity
1	0.0022	7.3E-05	2.3E-04	7.6E-06	F
2	0.0021	7.0E-05	2.2E-04	7.2E-06	F
3	0.0015	5.0E-05	2.4E-04	8.0E-06	F
4	0.0013	4.3E-05	2.1E-04	6.9E-06	F
5	0.0006	2.0E-05	1.6E-04	5.5E-06	F
6	0.0007	2.3E-05	2.0E-04	6.5E-06	F
1	0.0017	5.7E-05	1.8E-04	5.9E-06	F
2	0.0012	4.0E-05	1.2E-04	4.1E-06	F
3	0.0011	3.7E-05	1.8E-04	5.9E-06	F
4	0.0010	3.3E-05	1.6E-04	5.3E-06	F
5	0.0005	1.7E-05	1.4E-04	4.6E-06	F
6	0.0005	1.7E-05	1.4E-04	4.6E-06	F
1	0.0023	7.7E-05	2.4E-04	7.9E-06	F
2	0.0013	4.3E-05	1.4E-04	4.5E-06	F
3	0.0005	1.7E-05	8.1E-05	2.7E-06	F
4	0.0016	5.3E-05	2.6E-04	8.5E-06	F
5	0.0002	6.7E-06	5.7E-05	1.9E-06	F
6	0.0002	6.7E-06	5.7E-05	1.9E-06	F
1	0.0027	9.0E-05	2.8E-04	9.3E-06	F
2	0.0041	1.4E-04	4.2E-04	1.4E-05	F
3	0.0017	5.7E-05	2.7E-04	9.1E-06	F
4	0.0044	1.5E-04	7.2E-04	2.4E-05	F
5	0.0019	6.3E-05	5.4E-04	1.8E-05	F
6	0.0014	4.7E-05	3.9E-04	1.3E-05	F
1	0.0020	6.7E-05	2.1E-04	6.9E-06	F
2	0.0023	7.7E-05	2.4E-04	7.9E-06	F
3	0.0010	3.3E-05	1.6E-04	5.3E-06	F
4	0.0014	4.7E-05	2.2E-04	7.5E-06	F
5	0.0008	2.7E-05	2.2E-04	7.4E-06	F
6	0.0007	2.3E-05	2.0E-04	6.5E-06	F

TABLE 16Comments and
Observations

Film, rainbow w gray hue; temp kept decreasing thru run; Salt (1) failed @98%; Pull (3) 80% film left; Micro. (4) CuSO₄. Cu crys. within 45 sec brown streaks cover 30-40% of drop; Ferr, blue crys. within 5 sec brown streaks cover 10-60% drop, brown spots form 5 & 10 crys in 0.1 min
Film, rainbow w gray hue; flow @ 90; Salt (1) failed @98%; Pull (3) stud came off;
Micro. (4) CuSO₄, Cu crys; Ferroxil, blue crys

Film, rainbow w gray hue; Pull (3) stud came off;
Micro. (4) CuSO₄, Cu & small silver crys; Ferroxil, blue crys, only 5 formed; Salt (1) failed @95%; salt spray sample not crusted with rust like other samples in this matrix series

Film, silver w faint lime rainbow; Salt (2) failed @98%; Pull (3) 80% film left; Micro. (4) CuSO₄, Cu, silver, rust spots; Ferroxil, blue crys

Film, silver w faint lime rainbow; Salt (1) failed @98%; Pull (3) 10 or 90% film left?;
Micro. (4) CuSO₄, very small silver crys, a couple rust, Cu ones; Ferroxil, blue crys (1 in 25 min)

TABLE 16

Scratch	Scratch	Pull	Salt	Acid	CuSO ₄	Neut	CuSO ₄	Ferroxil	Conductance	Permeability	
1	2	psi	h	5crys	10crys	5crys	10crys	5crys	10crys	MS	ml sand
			48								400
4	1000	0		0.1	0.2	0.1	0.1	0.9	1.8		39
			72								400
4	50			0.2	0.4	0.6	0.8	7.1	12.9		930
			168								300
4	1200			0.7	1.1	0.4	0.6	14.1			240
			144								200
(10	300	20	0.3	0.6	0.3	1.8	19.0			300
			152								20
20	500	30		0.3	0.7	0.7	1.5				350

TABLE 17
DATA FOR HMDSN DESIGN I

Std OrdNumber	Run Number	Power set	Power obt	Flow HMDSN	Flow 02	Press set	Press obt	Time min	Sample Number	Weight Gain, g	Rate d/sqcm/min	Qual ity
1	86428	50	15	2	250	15	A			5E-04	5.3E-06	F
										6E-04	6.4E-06	F
										8E-04	8.5E-06	F
										1.0E-03	1.1E-05	F
										4E-04	4.3E-06	F
										8E-04	8.5E-06	F
2	86414	200	15	2	1000	15	A			2.0E-03	2.1E-05	F
										2.2E-03	2.4E-05	F
										2.5E-03	2.7E-05	F
										1.7E-03	1.8E-05	F
										1.6E-03	1.7E-05	F
										1.7E-03	1.8E-05	F
3	86413	50	150	2	1000	15	A			9E-04	9.6E-06	F
										7E-04	7.5E-06	F
										1.0E-03	1.1E-05	F
										1.7E-03	1.8E-05	F
										1.8E-03	1.9E-05	F
										1.8E-03	1.9E-05	F
4	86429	200	160	150	2	250	305			1.5E-03	1.6E-05	F
										1.7E-03	1.8E-05	F
										2.2E-03	2.4E-05	F
										2.7E-03	2.9E-05	F
										2.4E-03	2.6E-05	F
										2.7E-03	2.9E-05	F
5	864210	50	15	5	1000	15	A			1.6E-03	1.7E-05	F
										1.4E-03	1.5E-05	F
										1.6E-03	1.7E-05	F
										1.8E-03	1.9E-05	F
										1.8E-03	1.9E-05	F
										2.0E-03	2.1E-05	F
6	86416	200	170	15	5	250	15			6E-04	6.4E-06	F
										9E-04	9.6E-06	F
										1.0E-03	1.1E-05	F
										1.1E-03	1.2E-05	F
										8E-04	8.5E-06	F
										1.0E-03	1.1E-05	F
7	86417	50	150	5	250	300	15			1.4E-03	1.5E-05	F
										1.1E-03	1.2E-05	F
										1.4E-03	1.5E-05	F
										2.3E-03	2.4E-05	F
										1.8E-03	1.9E-05	F
										1.9E-03	2.0E-05	F
8	86415	200	147	150	5	1000	15			2.5E-03	2.7E-05	F
										4.7E-03	5.0E-05	F
										4.1E-03	4.4E-05	F
										4.0E-03	4.3E-05	F
										3.9E-03	4.2E-05	F
										4.1E-03	4.4E-05	F
0	86381	125	90	3	625	30	A			5.2E-03	2.8E-05	F
										5.7E-03	3.0E-05	F
										3.3E-03	1.8E-05	F
										5.0E-03	2.7E-05	F
										4.9E-03	2.6E-05	F

TABLE 17

O	86382	125	90	3	625	30	F	4.9E-03	2.6E-05	F		
						15	A	1.7E-03	1.8E-05	F		
						15	B	2.2E-03	2.4E-05	F		
						15	C	2.8E-03	3.0E-05	F		
						15	D	2.9E-03	3.1E-05	F		
						15	E	2.8E-03	3.0E-05	F		
						15	F	2.6E-03	2.8E-05	F		
O	864211	125	90	3	625	15	A	1.8E-03	1.9E-05	F		
						15	B	1.7E-03	1.8E-05	F		
						15	C	1.6E-03	1.7E-05	F		
						15	D	2.8E-03	3.0E-05	F		
						15	E	2.6E-03	2.8E-05	F		
						15	F	2.5E-03	2.7E-05	F		
O	864212	125	90	3	625	15	A	1.9E-03	2.0E-05	F		
						15	B	2.0E-03	2.1E-05	F		
						15	C	1.8E-03	1.9E-05	F		
						15	D	2.9E-03	3.1E-05	F		
						15	E	2.9E-03	3.1E-05	F		
						15	F	2.4E-03	2.6E-05	F		
1	864213	50	15	2	250	15	A	9E-04	9.6E-06	F		
						15	B	7E-04	7.5E-06	F		
						15	C	8E-04	8.5E-06	F		
						15	D	1.2E-03	1.3E-05	F		
						15	E	1.1E-03	1.2E-05	F		
						15	F	1.0E-03	1.1E-05	F		
	864214	200	183	15	2	172	185	30	A	3.1E-03	1.6E-05	F
						30	B	1.6E-03	8.5E-06	F		
						30	C	3.5E-03	1.9E-05	F		
						30	D	7E-04	3.7E-06	F		
						30	E	9E-04	4.8E-06	F		
						30	F	1.3E-03	6.9E-06	F		
	864315	200	179	15	2	196	216	35	A	9E-04	4.1E-06	F
						35	B	1.1E-03	5.0E-06	F		
						35	C	9E-04	4.1E-06	F		
						35	D	3.2E-03	1.5E-05	F		
						35	E	3.6E-03	1.6E-05	F		
						35	F	3.0E-03	1.4E-05	F		
	864316	200	181	10	2	188	188	60	A	4.5E-03	1.2E-05	F
						60	B	4.0E-03	1.1E-05	F		
						60	C	3.7E-03	9.9E-06	F		
						60	D	1.1E-03	2.9E-06	F		
						60	E	9E-04	2.4E-06	F		
						60	F	1.2E-03	3.2E-06	F		

TABLE 17

Glass Stage	Comments and Observations	Scratch 1	Scratch 2	Pull psi
G	Film rainbow; rotating stage			
G	not running; Pull B&E stud	4	2000	
G	came off, 0-5% film left on sample			
S		20	2000	
S				
G	Film on glass silver w aqua rainbow, on stage silver &	4	1500	
G	uneven film, easily scratch;			
S	Pull A&E stud came off, 0-20% film left	20	2000	
S				
G	Film on glass silver, rainbow, on stage silver, oily; Pull C& E 80-100% film left, Pull F not wiped w TCE, stud came off	4	100	20
S		4	4	780
S		4	4	
G	Film dull gray; Trouble setting power; Pull B 95% film left, Pull D stud came off, 90% film left	4	400	190
S		800	1500	
S				
G	Film slight lime color; Pull A stud came off, Pull E 10% film left	50	4000	
S		150	4000	20
S				
G	Film green & pink rainbow; Trouble matching power; Pull C 20-30% film left, Pull E stud came off, 30% film left	4	500	20
S		10	300	
S				
G	Film on glass slight rainbow, on stage silver; Pull B 60-70% film left, Pull D stud came off	4	300	50
S		10	800	
S				
G	Film dull gray; Trouble matching power; Pull B&D stud came off, 90-100% film left	4	1500	
S		30	1000	
S				
G	Film silver; Pull B 70-80% film left, Pull F 10% film left	200	900	20
S				

TABLE 17

S		500	700	450
G	Film silver; Pull B 20% blue			
G	film left, Pull E 10% blue	4	1000	80
G	film left			
S				
S		500	1500	0
S				
G	Film on glass slightly lime			
G	colored rainbow, on stage dull	100	500	0
G	gray; Pull B 10% blue film			
S	left, Pull E stud came off,			
S	i-5% film left	400	800	
S				
G	Film on glass slight lime			
G	color, on stage dull gray;	500	700	
G	Pull B stud came off, 20% blue			
S	film left, Pull D stud came	400	500	
S	off, 95% film left			
S				
G	Repeat Std Ord 1; film			
G	rainbow; Pull B 60% film left,	4	2500	120
G	Pull E 10-20% film left			
S				
S		4	2000	450
S				
G	Film on glass crazed, slight			
G	lime rainbow, on stage flaky			
G	rainbow; Press open; Pull C 0%	10	500	440
S	film left, Pull E 60% film			
S	left, both Pulls cream film	4	90	120
S	peels off			
G	Repeat run 864214; film flaky			
G	rainbow; Press open; stage not			
G	at ground potential; Pull C	4	500	2920
S	30% film left, Pull F 60% film			
S	left, film similar to 864214,			
S	samples D-F more flaky film	4	20	2920
G	Film rainbow; Press open;	40	900	100
G	Pull A 5% film left; Pull D			
G	stud came off			
S		10	2000	
S				
S				

TABLE 18
DATA FOR HMDSN DESIGN II

Std Ord	Run Number	Power set	Power obt	Flow HMDSN	Flow 02	Press set	Press obt	Time min	Sample Number	Weight Gain, g	Rate g/sqcm/min	Qual ity
1	86445	50		10	0	175			60 A	1.0E-03	2.7E-06	F
									60 B	1.0E-03	2.7E-06	F
									60 C	1.0E-03	2.7E-06	F
									60 D	1.2E-03	3.2E-06	F
									60 E	1.1E-03	2.9E-06	F
									60 F	9E-04	2.4E-06	F
2	86457	200	160	10	0	250			60 A	2.8E-03	7.5E-06	F
									60 B	3.0E-03	8.0E-06	F
									60 C	4.2E-03	1.1E-05	F
									60 D	5E-04	1.3E-06	F
									60 E	6E-04	1.6E-06	F
									60 F	5E-04	1.3E-06	F
3	86446	50		15	0	250			60 A	1.9E-03	5.1E-06	F
									60 B	1.9E-03	5.1E-06	F
									60 C	2.0E-03	5.3E-06	F
									60 D	2.2E-03	5.9E-06	F
									60 E	2.2E-03	5.9E-06	F
									60 F	2.3E-03	6.1E-06	F
4	864510	200	178	15	0	175	198		60 A	5.1E-03	1.4E-05	F
									60 B	4.5E-03	1.2E-05	F
									60 C	5.4E-03	1.4E-05	F
									60 D	1.6E-03	4.3E-06	F
									60 E	1.8E-03	4.8E-06	F
									60 F	1.8E-03	4.8E-06	F
5	86459	50		10	2	250			60 A	1.1E-03	2.9E-06	F
									60 B	1.2E-03	3.2E-06	F
									60 C	1.1E-03	2.9E-06	F
									60 D	1.1E-03	2.9E-06	F
									60 E	1.1E-03	2.9E-06	F
									60 F	1.1E-03	2.9E-06	F
6	86443	200	169	10	2	175	183		30 A	6E-04	3.2E-06	F
									30 B	7E-04	3.7E-06	F
									30 C	7E-04	3.7E-06	F
									30 D	6E-04	3.2E-06	F
									30 E	5E-04	2.7E-06	F
									30 F	5E-04	2.7E-06	F
6	864813	200	169	10	2	175	194		60 A	4.4E-03	1.2E-05	F
									60 B	3.4E-03	9.1E-06	F
									60 C	4.1E-03	1.1E-05	F
									60 D	1.2E-03	3.2E-06	F
									60 E	1.2E-03	3.2E-06	F
									60 F	1.4E-03	3.7E-06	F
7	86444	50		15	2	175	191		60 A	2.5E-03	6.7E-06	F
									60 B	2.5E-03	6.7E-06	F
									60 C	2.3E-03	6.1E-06	F
									60 D	2.5E-03	6.7E-06	F
									60 E	2.4E-03	6.4E-06	F
									60 F	2.4E-03	6.4E-06	F
8	86458	200	179	15	2	250			60 A	3.5E-03	9.3E-06	F
									60 B	2.8E-03	7.5E-06	F
									60 C	3.4E-03	9.1E-06	F
									60 D	1.1E-03	2.9E-06	F
									60 E	1.0E-03	2.7E-06	F

TABLE 18

O	86431	125	12.5	2	213	60 F	1.0E-03	2.7E-06 F
						60 A	3.5E-03	9.3E-06 F
						60 B	4.8E-03	1.3E-05 F
						60 C	4.5E-03	1.2E-05 F
						60 D	2.2E-03	5.9E-06 F
						60 E	2.4E-03	6.4E-06 F
						60 F	2.1E-03	5.6E-06 F
O	86442	125	12.5	2	213	60 A	2.1E-03	5.6E-06 F
						60 B	1.9E-03	5.1E-06 F
						60 C	1.4E-03	3.7E-06 F
						60 D	1.6E-03	4.3E-06 F
						60 E	2.0E-03	5.3E-06 F
						60 F	1.2E-03	3.2E-06 F
O	864511	125	12.5	2	213	60 A	4.4E-03	1.2E-05 F
						60 B	2.2E-03	5.9E-06 F
						60 C	4.6E-03	1.2E-05 F
						60 D	2.0E-03	5.3E-06 F
						60 E	2.1E-03	5.6E-06 F
						60 F	2.3E-03	6.1E-06 F
O	864512	125	12.5	2	213	60 A	4.9E-03	1.3E-05 F
						60 B	4.6E-03	1.2E-05 F
						60 C	4.3E-03	1.2E-05 F
						60 D	2.4E-03	6.4E-06 F
						60 E	2.3E-03	6.1E-06 F
						60 F	2.3E-03	6.1E-06 F

TABLE 18

Glass Stage	Comments and Observations	Scratch 1	Scratch 2	Pull psi
G	Film on glass rainbow, flaky;			
G	on stage more flaky, silver			
G	Pull(C) 30% film left, may have	4	100	9280
S	been loaded improperly, Pull			
S	(F) 70% film left			
S		4	40	2570
G	Film rainbow streaky, flaky	4	30	150
G	gold; Pull(A) 95% film left,			
G	Pull(D) 5% film left			
S		4	30	1380
S				
S				
G	Film silver w slight lime	200	400	410
G	rainbow; Pull(A) 95% film left,			
G	Pull(D) stud came off			
S		90	400	
S				
S				
G	Film on glass gold w pink			
G	stripes; on stage gold, crazed	4	700	8810
G	& flaky, silver underneath;			
S	Pull(B) 90% film left, Pull(E)			
S	50% film left	20	600	7760
S				
G	Film rainbow; Pull(C) no film			
G	left, Pull(E) 50% film left			
G		4	500	10
S				
S		4	1000	0
S				
G	Film green, pink rainbow;			
G	Pull(B,E) stud came off	4	100	
G				
S		4	800	
S				
G	Repeat; film on glass pink,			
G	green rainbow; on stage same			
G	w gold, crazed around edges;	4	300	
S	Pull(C,F) stud came off, no			
S	film left			
S		10	300	
G	Film silver w very slight lime	100	500	
G	rainbow; Pull(A,D) stud came			
G	off, 0-10% film left			
S		100	800	
S				
S				
G	Film on glass rainbow, silver	4	10	2750
G	where coat flaked; on stage			
G	silver, more flaky coat;			
S	Scratch 2(A) 300 on rainbow,	20	2000	830
S	1/4 of sample; Pull(A,D) 40%			

TABLE 18

S	film left				
G	Film on glass silver, rainbow;	10	500	460	
G	on stage pale gold, crazed,				
G	flaky; Pull(A) 20% film left,				
S	Pull(E) 30% film left				
S		40	200	9870	
S					
G	Film on glass silver, flaky;	4	400	4920	
G	on stage pale gold, flaky;				
G	flaky rainbow when removed				
S	from vacuum; Pull(A) 60% film				
S	left, Pull(E) 30% film left;	4	300	5900	
S	Scr2(E) 70, 400 opposite edges				
G	Film silver w faint lime	200	3000		
G	rainbow, flaky around edges;				
G	Pull(A) stud came off, Pull(E)				
S	80% film left				
S		4	10	2480	
S					
G	Film on glass silver w faint	200	1000		
G	lime rainbow, flaky at edges;				
G	on stage same w gold, crazed,				
S	flaky; Pull(A) stud came off,				
S	no film left, Pull(E) 90% film	4	20	1480	
S	left				

TABLE 19
SUMMARY OF AVERAGED DATA OF RUNS IN THIOPHENE
DESIGN I, II, III, AND IV

SAMPLE #	DESIGN ORDER	PWR WATTS	FLOW SCCM	PRESS. mTorr	TEMP °C	TIME min.	FILM QUAL	WT.GN. mg	RATE mg/min	THKNS. $\mu\text{g/cm}^2$	THK.B RATE $\mu\text{g/cm}^2/\text{min}$	SCR. 1.9	SCR. 2.9	PULL psi	S.S. hrs	CuSO ₄ min	FERR min	
A59A9	1	10	2.1	250		12	F	0.2	17	32	2.7	50	100			<1	<1	
A59A2	2	10	29	250		15	F/P	3.7	245	590	39	1000	5000	20		3.5	<1	
A59A4	3	10	2.1	500		40	P	1.7	43	280	7	500	5000	1140		2.5	<1	
A59A7	4	10	20	500		29	P	12.5	435	2000	69							
A59A1	5	50	2.1	250		10	F	0.4	38	60	6	200	500	30		<1	<1	
A59A6	6	50	29	250		2	F	0.8	375	120	60	1000	5000			<1	<1	
A59A8	7	50	2.1	500		45	F	0.4	9	65	1.4	50	900			<1	<1	
A59A3	8	50	29	5000		6	P	6.1	1020	965	161					<1	<1	
A59B9	1	50	2.1	500		74	F	0.8	10	122	1.6		500			<1	<1	
A59B3	2	50	29	500		4	F/P	2.8	950	610	153							
A59B4	3	50	2.1	510		17	P	1.1	67	178	11							
A59B7	4	50	20	1000		7	P	5.6	803	868	124							
A59B2	5	100	2.1	500		25	F	0.4	15	63	3	100	600			<1	<1	
A59B6	6	100	29	500		2	F	1.1	540	175	88	10	1000			<1	<1	
A59B8	7	100	2.1	1000		42	F	1.3	32	212	5		200			<1	<1	
A59B1	8	100	29	1000		3	P	3.6	1200	570	190							
A59C1	5	50	3	150		6	F	0.5	79	75	13	80	500			<1	<1	
A59C2	5	100	3	450		10	F	0.4	35	56	6	20	1000			3	<1	
A59A13	1	10	3	220		120	F	3.6	60	517	43	2000	9000			1	4.5	5.9
A59A11	5	50	3	153		120	F	2.8	23	368	3.1	900	10000			1	2.6	<1
A59C3	5	50	3	250		38	F	1.1	28	170	4.4	500	5000			48	<1	2.2
A59A10	6	50	29	250		12	F	4.3	357	583	49	500	5000	10	1	1.4	<1	
A59C4	7	50	3	400		120	F	2.9	24	380	3.2	500	7000			1	3.3	6.0
A59B13	1	50	3	310		120	F/P	3.9	33	537	4.5		10000	10	1	2.8	4.0	
A59B11	5	100	3	500		124	F	2.2	18	297	2.4	50	5000	10	48	1.8	1.7	
A59B10	6	100	25	500		13	P	7.6	582	1053	81							
A59B12	7	100	3	1000		120	P	4.7	39	645	5.4	1000	10000	810	5	2.9	3.5	
A59A59	1	10	3	248	56	10	F	0.2	20	32	3		4					
A59A57	2	50	3	248	147	3	F	0.2	50	41	14		4					
A59A67	3	10	3	485	146	8	F	0.1	12	16	2		4					
A59A65	4	50	3	500	58	4	F	0.2	37	24	6		4	400				
A56A66	5	10	29	249	148	5	F	0.1	20	16	3		4	10				
A59A55	6	50	29	249	57	3	F	0.7	240	110	33		20	700				
A59A61	7	20	29	500	50	13	F	0.2	23	48	4		4	10				
A59A63	8	50	29	500	160	3	F/P	1.0	335	16	5		10	900				
A59B72	1	50	3	249	146	40	F	0.4	10	6.4	1.6		4	10				
A59B70	2	100	3	249	254	22	F	0.1	5	16	0.7		4					
A59B75	3	50	3	500	246	35	F	0.3	9	49	1.4		4	50				
A59B71	4	100	3	500	156	45	F	0.3	6	41	0.9		4	20				
A59B68	5	50	29	250	240	15	F	1.1	76	190	12.5		40	2500				
A59B74	6	100	29	253	155	15	F	1.6	105	255	17		250	7000				
A59B69	7	50	29	500	140	15	F/P	5.0	330	790	52.5		3000	4500				
A59B73	8	100	29	498	251	15	F	1.8	120	285	19		70	3000				

TABLE 20
SUMMARY OF AVERAGED DATA OF SELECTED RUNS
FROM THIOPHENE DESIGNS III AND IV

SMPL. #	DES ORDR	PWR WTS	FLOW SCCM	PRESS mTorr	TEMP °C	TIME min.	FILM QTY	WT.GN. mg	RATE		THKNS		THK RT	CuSO ₄ min	FERR min	COND mS	ABRAS ml/sand		
									μg/ min.	μg/cm ² / min.	μg/cm ²	SCR 1.9	SCR 2.9	PULL psi	S.S. hrs.				
A59A86	1	10	3	248	54	120	F	4.4	36	595	5.0	700	3000	0	126	1.2	9.8	14	200
A59A85	2	50	3	248	149	36	F	0.4	12	57	1.6	4	20	300	48	(1	3.7	800	700
A59A90	3	10	3	499	150	120	F	2.8	24	387	3.2	900	8000	1280	152	19.1	17.4	30	300
A59A88	4	50	3	498	76	83	F	2.7	32	360	4.3	700	3000	1060	245	6.9	20.2	10	200
A59A89	5	10	28	248	148	66	F	2.7	41	360	5.5	10	5000	1070	216	3.8	23.7	30	400
A59A84	6	50	29	248	68	14	F	3.1	220	420	30	800	7000	160	72	90	1.6	22	200
A59A87	7	20	29	499	47	125	F/P	4.2	34	562	4.5	90	3000	150	120	23.2	4.5	14	100
A59B93	1	50	20	230	155	120	F	19.0	159	2533	21	2000	3000	1850	128	13.8	9.2	5	>5000
A59B96	3	50	3	500	248	120	F	1.3	886	138	1.2	10	1000	410	32	7.2	(1	55	600
A59B92	4	100	2	71	134	52	F	3.6	69	490	9.4	700	10000	860	72	3.2	1.7	9	200
A59B91	5	50	29	250	238	42	F	3.0	70	393	9.4	2000	10000	50	120	8.6	11.7	20	400
A59B95	6	100	29	250	151	29	F	4.9	167	657	22.6	5000	10000	650	72	8.3	12.8	57	200
A59B94	8	100	29	498	252	26	F	4.5	172	608	23.4	9000	10000	20	24	4.8	38.3	20	400

TABLE 21
SUMMARY OF AVERAGED DATA OF RUNS IN HMDSO DESIGN I

SMPL. #	DES ORDR	PWR WTS	FLOW SCCM	PRESS mTorr	TEMP °C	TIME min.	FILM QTY	WT.GN. mg	RATE		THKNS THK RT		CuSO ₄ min	FERR min	COND mS	ABRAS ml/sand
									μg/ min.	μg/ cm ² / min.	SCR 1.9	SCR 2.9	PULL psi	S.S. hrs.		
S0128	1	50	3.5	350	147	30	F	0.7	24	108	3.6	4	700	0	80	<1 8.4 580 200
S0124	2	196	3.5	350	242	30	F	1.3	43	195	6.5	20	400	90	48	<1 9.1 34 400
S0123	3	50	30	350	251	30	F	0.1	3.3	11	0.4	4	40		120	<1 9.5 200 400
S0129	4	160	30	350	181	30	F	2.1	68	320	10.7	100	500	140	144	5.1 15 9 200
S0130	5	50	3.5	1000	250	30	F	0.7	23	109	3.7	4	500	190	144	1.9 15 700 400
S0126	6	187	3.5	1000	155	30	F/P	1.7	56	237	7.9	50	1000		6	2100
S0127	7	50	30	1000	159	30	F/P	2.5	84	397	13.2	300	700	410	98	1.6 <1 310 400 100
S0125	8	154	30	1000	263	30	F	1.8	60	285	9.5	4	1000		56	<1 <1 456 400
S0120	M	95	7	675	161	30	F	1.4	47	210	7.0	4	1000		48	<1 1.8 39 400
S0121	M	95	7	675	205	30	F	1.0	34	153	5.1	4	50		72	<1 12.9 930 400
S0122	M	95	8	675	204	30	F	1.0	34	140	4.6	4	1300		168	<1 14.1 240 300
S0131	M	95	8	675	204	30	F	2.7	90	438	14.6	10	300	20	144	<1 19.0 20 200
S0132	M	95	8	675	200	30	F	1.5	51	208	6.9	20	500	30	152	1.5 350 300

TABLE 22
SUMMARY OF AVERAGED DATA OF RUNS IN HMDSN DESIGNS I AND II

SAMPLE #	DESIGN ORDER	PWR <u>WATTS</u>	FLOW <u>HMDSN</u>	SCDM <u>O₂</u>	PRESS. <u>mTorr</u>	TIME <u>min.</u>	FILM <u>QUAL</u>	WT.GN. <u>mg</u>	RATE <u>mg/min</u>	THKNS, <u>mg/cm²</u>	THK.RATE <u>mg/cm²/min</u>	SCR. <u>1_g</u>	SCR. <u>2_g</u>	PULL <u>psi</u>	S.S. <u>hrs</u>
86428	1	50	3.5	2	250	15	F	0.68		109	7.3	20	2000		
864213	1	50	3.5	2	250	15	F	1.0		152	10.1	4	2500	450	
86414	2	200	3.5	2	1000	15	F	2.0		312	20.8	20	2000		
86413	3	50	29	2	1000	15	F	1.3		210	14.5	4	100	780	
86429	4	160	29	2	305	15	F	2.2		352	23.5	800	1500	190	
864210	5	50	3.5	5	1000	15	F	1.7		270	18	150	4000	20	
86416	6	170	3.5	5	250	15	F	0.9		144	9.6	10	300	20	
86417	7	50	29	5	300	15	F	1.7		264	17.6	10	800	50	
86415	8	147	29	5	1000	15	F	3.9		621	41.4	30	1000		
86382	M	125	8	3	625	15	F	2.5		400	26.7	500	1500	80	
864211	M	125	8	3	625	15	F	2.2		348	23.2	400	800		
864212	M	125	8	3	625	15	F	2.3		372	24.8	500	700		
86381	X	125	8	3	625	30	F	4.8	773	25.8	500	700	450		
864214	X	200	3.5	2	185	30	F/F	1.9		296	9.9	10	500	440	
864215	X	200	3.5	2	216	35	F/F	2.1		339	9.7	4	500	2920	
864316	X	200	2.4	2	188	60	F	2.6		411	6.9	10	2000	100	
86445	1	50	2.4	0	175	60	F/F	1.03		166	2.7	4	100	9280	
86457	2	160	2.4	0	250	60	F/F	1.93		309	5.2	4	30	1380	
86446	3	50	3.5	0	250	60	F	2.08		333	5.6	200	400	410	
864510	4	178	3.5	0	198	60	F/C	3.37		539	9.0	4	700	8810	
86459	5	50	2.4	2	250	60	F	1.18		179	3.0	4	1000	10	
864813	6	169	2.4	2	194	60	F/C	2.62		418	7.0	10	300		
86444	7	50	3.5	2	191	60	F	2.43		389	6.5	100	800		
86458	8	179	35	2	250	60	F/F	2.13		341	5.7	20	2000	2750	48
86431	M	125	3.0	2	213	60	F/C	3.25		520	8.7	40	200	9870	
86442	M	125	3.0	2	213	60	F/F	1.70		272	4.5	4	400	4920	
864511	M	125	3.0	2	213	60	F/F	2.93		469	7.8	200	3000	248J	6
864512	M	125	3.0	2	213	60	F/F	3.47		556	93	200	1000	1480	8

TABLE 23
PROPERTIES OF THE 15 BEST CORROSION PROTECTION COATINGS

SAMPLE #	CTG. WT. <u>mg/cm²</u>	CTG. RATE <u>mg/cm²/min</u>	SCRATCH #1	SCRATCH #2	PULL psi	SALT SPRAY hrs.	CuSO ₄ min	FERR. min	COND. <u>MS</u>	ABRASION ml sand
CRITERIA		10	400	1000	100	100				400
A59A88	360	<u>4.3</u>	700	3000	1060	245	6.9	20.2	10	<u>200</u>
A59A89	360	<u>5.5</u>	<u>10</u>	5000	1070	216	3.8	23.7	30	400
A59A90	387	<u>3.2</u>	900	8000	1280	152	19.1	17.4	30	<u>300</u>
A59B93	2533	21	2000	3000	1850	128	13.8	9.2	5	5000
A59A87	562	<u>4.5</u>	<u>90</u>	3000	150	120	23.2	4.5	14	<u>100</u>
A59B91	393	<u>9.4</u>	2000	10000	<u>50</u>	120	8.6	11.7	20	400
A59A84	420	30	800	7000	160	<u>72</u>	90	1.6	22	<u>200</u>
A59B95	657	22.6	5000	10000	650	<u>72</u>	8.3	12.8	57	<u>200</u>
A59B92	490	<u>9.4</u>	700	10000	860	<u>72</u>	3.2	1.7	9	<u>200</u>
A59S0132	208	<u>6.9</u>	<u>20</u>	<u>500</u>	<u>30</u>	152	1.5		350	<u>300</u>
A59S0122	140	<u>4.6</u>	<u>4</u>	1300	<u>0</u>	168	<1	14	240	<u>300</u>
A59S0129	320	10.7	<u>100</u>	<u>500</u>	140	144	5.1	15	9	<u>200</u>
A59S0130	109	<u>3.7</u>	<u>4</u>	<u>500</u>	190	144	1.9	15	700	400
A59S0131	438	14.6	<u>10</u>	<u>300</u>	<u>20</u>	144	<1	19	20	<u>200</u>
A59S0127	397	13.2	<u>300</u>	<u>700</u>	410	<u>98</u>	1.6	<1	310	400

TABLE 24
FIRST ORDER EFFECTS OF PROCESS VARIABLES

DESIGN NO.	VAR	DESN	VAR	UNITS	VAR RANGE	THICK RATE	FIRST ORDER		SALT SPRAY	ON CuSO ₄	RESPONSES			
							SCR1	SCR2			PULL	SOL	FERR	COND
THIOPH I	POWER	C	WATTS	10/50	27.7	-75	-925	-282		-1.275	-0.15			
	FLOW	A	SCCM	2.1/29	78	300	875	-288		0.125	0			
	PRESS	B	mT	250/500	32	-425	-1175	272		-0.325	-0.05			
THIOPH II	POWER	C	WATTS	50/100	25.8	27.5	450			0.23	0.10			
	FLOW	A	SCCM	2.1/29	107	-22.5	50			-0.28	-0.05			
	PRESS	B	mT	500/1000	-5.6	-27.5	-350			-0.28	-0.10			
THIOPH III	POWER	A	WATTS	10/50	11.5	5.5	495							
	FLOW	C	SCCM	3/29		5	5.5	302						
	PRESS	B	mT	250/500		-9	-2.5	149						
	TEMP	D	°C	50/150	-5.5	-2.5	-49							
THIOPH IV	POWER	A	WATTS	50/100	-7.6	-680	741							
	FLOW	C	SCCM	3/29	24.1	836	4229							
	PRESS	B	mT	250/500	10.5	695	-486							
	TEMP	D	°C	150/250	-9.6	-785	-1494							
THIOPH III-A	POWER	A	WATTS	10/100	6.4	76	-1245	-102	-27	17.7	-5.8	219	100	
	FLOW	C	SCCM	3/29	8.4	-225	745	-172	-6	-27.6	-1.5	-164	-100	
	PRESS	B	mT	250/500	-5.6	169	1245	384	49	-6.2	4.4	-170	-150	
	TEMP	D	°C	50/250	-6.5	-219	225	463	-2	-19.3	4.1	233	250	
HMDSO I	POWER	A	WATTS	50/200	3.4	-34.5	240	-92.5	-47	0.48	-2.3	202	-100	
	FLOW	B	SCCM	3.5/30	3.0	82.5	-90	67.5	35	1.08	-1.7	-610	100	
	PRESS	C	mT	350/1000	3.3	57.5	390	92.5	-22	-0.63	-6.5	686	0	
	TEMP	D	°C	150/250	-3.8	-105.5	-240	-67.5	10	-1.03	2.5	-402	200	
HMDSN I	POWER	A	WATTS	50/200	9.1	172	-525	-216						
	FLOW	B	SCCM	3.5/29	10.0	164	-1225	189						
	OXYGEN	C	SCCM	2/5	4.8	-159	125	-276						
	PRESS	D	mT	250/1000	8.8	-157	625	79						
HMDSN II	POWER	A	WATTS	50/180	2.3	-67.5	183	810						
	FLOW	B	SCCM	2.4/3.5	2.2	75.5	618	325						
	OXYGEN	C	SCCM	0/2	-0.1	-19.5	718	-4280						
	PRESS	D	mT	175/250	-1.4	27.5	383	-3385						

FIGURE 1
VACUUM PLASMA POLYMERIZATION REACTOR AND SYSTEM

