

AD-A180 186


SPATIALLY SELECTIVE PHOTOELECTROCHEMISTRY(U) EIC LABS  
INC NORWOOD MA R D RAUH ET AL MAR 87 TR-13  
N00014-79-C-0700

1/1

UNCLASSIFIED

F/G 20/12 NL





MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

**DTIC FILE COPY**

12

**AD-A180 186**

**REPORT N00014-79-C-0700(F)**

**SPATIALLY SELECTIVE PHOTOELECTROCHEMISTRY**

**DTIC  
ELECTE  
MAY 15 1987**  
**S D**  
D

**R. David Rauh, Principal Investigator**

**EIC Laboratories, Inc.  
111 Downey Street  
Norwood, Massachusetts 02062**

**March, 1987**

**FINAL REPORT FOR PERIOD 1 AUGUST 1979 - 31 OCTOBER 1986  
CONTRACT NO. N00014-79-C-0700**

**Prepared for**

**OFFICE OF NAVAL RESEARCH  
Department of the Navy  
800 North Quincy Street  
Arlington, Virginia 22217**

**Approved for Public Release - Distribution Unlimited**

**Reproduction in whole or in part is permitted for  
any purpose of the United States Government**

87 5 13 110

8a. NAME OF FUNDING / SPONSORING ORGANIZATION Office of Naval Research		8b. OFFICE SYMBOL (if applicable) N00014	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-79-C-0700	
8c. ADDRESS (City, State, and ZIP Code) 800 North Quincy Street Arlington, VA 22217-5000		10. SOURCE OF FUNDING NUMBERS		
		PROGRAM ELEMENT NO. NR	PROJECT NO. 359	TASK NO. 723
		WORK UNIT ACCESSION NO. -		
11. TITLE (Include Security Classification) (U) SPATIALLY SELECTIVE PHOTOELECTROCHEMISTRY				
12. PERSONAL AUTHOR(S) R. David Rauh et al.				
13a. TYPE OF REPORT Final Report	13b. TIME COVERED FROM 8/01/79 to 10/31/86		14. DATE OF REPORT (Year, Month, Day) 1987 March	15. PAGE COUNT 6
16. SUPPLEMENTARY NOTATION				
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP	Key Words: Photoelectrochemistry; Semiconductor; Etching; Electroplating; Imaging; Laser; GaAs	
19. ABSTRACT (Continue on reverse if necessary and identify by block number)				
<p>↓</p> <p>This program has dealt with applications of photoelectrochemistry to semiconductor technology. Light localized etching and electroplating have been demonstrated for n-GaAs, including imaging with a computer-controlled focused laser light source and crystallographically enhanced photoelectrochemical etching using conventional photoresist masks. These studies have resulted in new processes for high aspect ratio etching in compound semiconductors, and in fabrication of sawtooth Eschelle-type diffraction gratings for spectroscopy and integrated electro-optics.</p> <p>↑</p>				
20. DISTRIBUTION / AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED	
22a. NAME OF RESPONSIBLE INDIVIDUAL Dr. Robert J. Nowak			22b. TELEPHONE (Include Area Code) (202) 696-4409	22c. OFFICE SYMBOL N00014

## SUMMARY

The purpose of this program has been to explore applications of photoelectrochemistry to semiconductor technology. Two general applications have been considered: 1) photoelectrochemistry as a tool for nondestructive evaluation of semiconductor bulk and surface properties, and light-localized electrochemical imaging processes or semiconductors, including etching and metal deposition.

Photoelectrochemical Nondestructive Evaluation. A computer controlled laser spot scanner was developed which allowed the profiling of the photoelectrochemical activity of a semiconductor with  $\sqrt{1}$   $\mu\text{m}$  spatial resolution [5,9]. Research was conducted to demonstrate stabilizing electrolytes which could be used nondestructively with III-V compounds and Si, e.g.,  $\text{CH}_3\text{CN}/\text{I}^-/\text{I}_3^-$  [1,3] and  $\text{CH}_3\text{CN}/\text{Cu}^+/\text{Cu}^{+2}$  [4] were used with n-GaAs, and nickelocene in propylene carbonate [1] and methyl viologen in methanol for n-Si. Laser scanning was used to map out defects in thin film electrodes [5,9]. Liquid junctions were also employed for the rapid assessment of minority carrier diffusion lengths in Si [8]. A novel "photoelectrochemical vidicon" imaging device was demonstrated in which a near infrared image was projected onto a Si photoelectrode while a low power He-Ne laser raster scanned the surface. The projected image was replicated on an oscilloscope in real time as photovoltage or photocurrent vs. position due to image induced redox concentration gradients at the electrode surface [3].

Electroplating. Direct photoelectrochemical imaging of microscopic metal film patterns was achieved on p-GaAs and p-Si electrodes in contact with electroplating baths [2,7]. Reductive electroplating was confined to the areas of illumination. Resolution of  $\sqrt{10}$   $\mu\text{m}$  was achieved, limited primarily by nondirectional growth of the metal nuclei. The photoelectrochemical mechanism of plating various metals was described. Also demonstrated was "negative" photoelectrochemical plating on n-type semiconductors, in which illumination prevented electroplating while it proceeded in dark portions of the electrode surface [7]. In this way, the general applicability of the photoelectrochemical plating process was described.

Additional research was conducted on removing the necessity for an electrochemical cell in the imaging process [6]. This approach relied on complementary oxidation and reduction reactions occurring at the illuminated and dark portions of the semiconductor surface. High quantum yield light localized electroless plating of electropositive metals (Zn, Cd, etc.) was achieved on both p-Si and p-GaAs by using Zn, ohmically contacted to a nonilluminated region of the surface, as an internal bias agent. On illumination of the semiconductor/plating electrolyte junction, an internal cell was set up in which metal was plated onto the illuminated regions and dissolved from the sacrificial Zn source.

<input checked="" type="checkbox"/>
<input type="checkbox"/>
<input type="checkbox"/>

Availability Codes	
Dist	Avail and/or Special
A-1	



Focused Laser Etching [9,10]. The computer controlled laser scanning instrument developed on this project [9] was used in the direct etching of microscopic patterns on semiconductors. During this period, we demonstrated and parameterized the high rate photoassisted etching of  $n^+$ -GaAs using a scanning focused laser and 10% aqueous KOH electrolyte [10]. In particular, we were interested in the relationship between intensity and resolution of holes developed using a diffraction limited focused spot of diameter  $<1 \mu\text{m}$ . We determined that the hole diameters are a function of total delivered energy rather than intensity, at least in the intensity regime investigated. This limits the depth of features that can be produced using high rate laser etching processes. The process still can be used for lower energy etching of shallow patterns, such as character sets for identification of individual integrated circuits.

High Aspect Ratio Etching. Experiments were carried out to determine the utility of using photoelectrochemistry for etching deep structures in n-GaAs. In one series of experiments, the (100) surfaces of n-GaAs single crystals were lithographically patterned in with  $10 \mu\text{m}$  wide grooves pointed in the [011], [010], and [011] crystallographic direction [11,12]. Photoelectrochemical etching of these channels showed that deep, vertical walled structures could be produced with a great deal of process control [12]. Undercutting of the mask occurred in crystals of low doping, which fosters rapid surface diffusion of photo-generated holes. Marked crystallographic effects were observed as well [11-13]. Photogenerated holes reacted more readily with the nucleophilic (111) As face than the (111) Ga face, an effect which enables the photoelectrochemical etching of sawtooth structures in the GaAs surface. The latter process was shown to be a new technique for fabricating deep low pitch Eschelle diffraction gratings for high performance spectrometers [12].

### Participants

#### Principal Investigator

Dr. R. David Rauh

#### Senior Scientists

Dr. Robert A. Boudreau  
Dr. Michael M. Carrabba  
Dr. Margaret E. Langmuir  
Dr. Ronald H. Micheels  
Dr. Timothy L. Rose

#### Staff Scientists

Mr. Allan D. Darrow II  
Ms. Catherine A. Kavassalis  
Mr. Robert A. LeLievre  
Mr. David H. Longendorfer  
Ms. Nguyet M. Nguyen  
Ms. Maureen A. Parker  
Ms. Rebecca L. Schiff

## Technical Reports

1. Margaret E. Langmuir, Ronald H. Micheels and R. David Rauh, "Non-aqueous Electrochemical Photovoltaic Cells Based on n-GaAs and n-Si," Proc. Third International Conf. on Photochemical Conversion and Storage of Solar Energy, Boulder, CO (1980).
2. R. H. Micheels, A. D. Darrow II and R. David Rauh, "Photoelectrochemical Deposition of Microscopic Metal Film Patterns on Si and GaAs," Appl. Phys. Lett. 39, 418 (1981).
3. Ronald H. Micheels and R. David Rauh, "An IR Sensitive Real-Time Imaging Technique Based on a Photoelectrochemical Cell," Appl. Phys. Lett. 40, 433 (1982).
4. M. E. Langmuir, M. A. Parker and R. D. Rauh, "Photoelectrochemical Cells Based on n-GaAs and the Cu(II)/Cu(I) Redox Couple in Acetonitrile," in Photoelectrochemistry: Fundamental Processes and Measurement Techniques, The Electrochemical Society, Inc., Pennington, NJ, 1982), p. 315.
5. M. E. Langmuir, R. H. Micheels, R. A. Boudreau and R. D. Rauh, "Laser Spot Scanning of Photoelectrochemical Cells," Ref. 4, p. 598.
6. T. L. Rose, D. H. Longendorfer and R. D. Rauh, "Photoelectrochemical Deposition of Metals onto p-Silicon using an Internal Cell," Appl. Phys. Lett. 42, 193 (1983).
7. T. L. Rose, R. H. Micheels, D. H. Longendorfer and R. D. Rauh, "Photoelectrochemical Deposition of Metal Patterns on Semiconductors," Materials Research Society Symposium Proceedings, Vol. 17, Beam Diagnostics and Photochemical Processing of Semiconductor Devices (New York: Elsevier Science Publishing Co., 1983), p. 265.
8. Ronald H. Micheels and R. David Rauh, "Use of a Liquid Junction for the Measurement of Diffusion Length in Silicon Ribbon," J. Electrochem. Soc. 131, 217 (1984).
9. Catherine A. Kavassalis, David H. Longendorfer, Robert A. LeLievre and R. David Rauh, "Localized Photoprocesses at Semiconductor-Electrolyte Interfaces Using a Programmable Laser Spot Scanner," Materials Research Society Symposium Proceedings, Vol. 29, Laser Controlled Chemical Processing of Surfaces, (New York: Elsevier Science Publishing Co., 1984), p. 151.
10. R. D. Rauh and R. A. LeLievre, "Microphotoelectrochemical Etching of n-GaAs Using a Scanned Focused Laser," J. Electrochem. Soc. 132, 2811 (1985).
11. Michael M. Carrabba, Nguyet M. Nguyen and R. David Rauh, "Orientation Dependence of Photoelectrochemical Etching in n-GaAs," J. Electrochem. Soc. 134, 260 (1987).

12. Michael M. Carrabba, Nguyet M. Nguyen and R. David Rauh, "Photoelectrochemical Fabrication of Sawtooth Gratings in n-GaAs," Applied Optics **25**, 4516 (1986).
13. Michael M. Carrabba, Nguyet M. Nguyen and R. David Rauh, "Effects of Doping and Orientation on Photoelectrochemically Etched Features in n-GaAs," J. Electrochem. Soc. (in press).
14. Michael M. Carrabba, Nguyet M. Nguyen and R. David Rauh, "Crystallographic Effects on the Photoelectrochemical Etching of Gratings in Compound Semiconductors," in Photon Beam and Plasma Stimulated Chemical Processes at Surfaces, V. M. Donnelly, I. P. Herman and M. Hirose, eds. (Elsevier Science Publishing Co., New York, 1987).



TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 1113 800 North Quincy Street Arlington, Virginia 22217-5000	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Doua Naval Weapons Support Center Code 50C Crane, Indiana 47522-5050	1	Naval Weapons Center Attn: Dr. Ron Atkins Chemistry Division China Lake, California 93555	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko, Code L52 Port Hueneme, California 93401	1	Scientific Advisor Commandant of the Marine Corp Code RD-1 Washington, D.C. 20380	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
DTNSRDC Attn: Dr. H. Singerman Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375-5000	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1

END

6-87

DTIC