

AD-A101 256

EVALUATION OF RESINS CURED BY ULTRAVIOLET RADIATION AND 1/1
IN CONJUNCTION W/ (U) ARMY LAB COMMAND WATERTOWN MA
MATERIAL TECHNOLOGY LAB M S SENNETT ET AL. MAR 87


UNCLASSIFIED

MTL-TR-87-15

F/G 11/9

NL





MICROCOPY RESOLUTION TEST CHART
 NATIONAL BUREAU OF STANDARDS-1963-A

AD-A181 256

DTIC FILE COPY

2

MTL TR 87-15

AD

EVALUATION OF RESINS CURED BY ULTRAVIOLET RADIATION AND IN CONJUNCTION WITH FIBER OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR OF COMPOSITE MATERIALS

MICHAEL S. SENNETT and STANLEY E. WENTWORTH

POLYMER RESEARCH DIVISION

March 1987

DTIC
SELECTED
JUN 09 1987
S D
D

Approved for public release; distribution unlimited.



US ARMY
LABORATORY COMMAND
MATERIALS TECHNOLOGY
LABORATORY

U.S. ARMY MATERIALS TECHNOLOGY LABORATORY
Watertown, Massachusetts 02172-0001

87 6 8 012

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER MTL TR 87-15	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) EVALUATION OF RESINS CURED BY ULTRAVIOLET RADIATION AND IN CONJUNCTION WITH FIBER OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR OF COMPOSITE MATERIALS	5. TYPE OF REPORT & PERIOD COVERED Final Report	
	6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) Michael S. Sennett and Stanley E. Wentworth	8. CONTRACT OR GRANT NUMBER(s)	
9. PERFORMING ORGANIZATION NAME AND ADDRESS U.S. Army Materials Technology Laboratory Watertown, Massachusetts 02172-0001 ATTN: SLCMT-OMP	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS D/A Project: 1L161101A91A	
11. CONTROLLING OFFICE NAME AND ADDRESS U.S. Army Laboratory Command 2800 Powder Mill Road Adelphi, Maryland 20783-1145	12. REPORT DATE March 1987	
	13. NUMBER OF PAGES 8	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) UV curing Field repair Fiber optics Composite materials Low energy curing Curing		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) <p style="text-align: center;">(SEE REVERSE SIDE)</p>		

Block No. 20

ABSTRACT

Several commercially available resins designed to be cured with ultra-violet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems. (KEYWORDS →

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

INTRODUCTION

This project is related to an ongoing effort to address the problems associated with the repair of composite materials that are becoming increasingly widespread in military applications. In particular, this project is concerned with field repair of such materials, to be conducted under highly variable conditions with a minimum of support services and equipment. Current repair technology for advanced composite materials involves the use of thermally cured resins and associated equipment to apply heat and pressure as required to fabricate a patch. Low energy curing resin systems, those that cure at ambient temperature or upon exposure to light or other radiation, have attracted interest as alternatives to thermally cured systems now employed. The use of ultraviolet (UV) radiation to cure glass-reinforced composites has been demonstrated,¹ but in the case of graphite- and Kevlar-reinforced materials, the opacity of the reinforcing fiber is an impediment to full exposure of the resin to the curing radiation. It was felt that using optical fiber waveguides, radiation could be introduced within the plies of a composite material, thus effecting a uniform cure throughout an essentially opaque material. This approach has been endorsed by a committee of the National Materials Advisory Board.²

MATERIALS

Resins

Ultraviolet curable resin systems are commercially available and are designed principally for use as inks, coatings, and adhesives. This program was initiated without concern for the structural properties of these materials on the grounds that once feasibility of curing resins in a graphite-reinforced composite material had been demonstrated, suitable modifications of existing resins or development of new resins for structural applications could be undertaken.

The commercially available UV curable resins generally fall into one of two categories. The first type consists of acrylates or epoxy resins modified by reaction with acrylic or methacrylic acid to produce acrylate esters which cure by means of a free radical mechanism. The features of these systems are very fast cures (typically seconds for thin layers) and limited thermal stability of the uncured resin. The optimum wavelength radiation to induce the curing reaction is typically 365 nm. The second type of resin is an unmodified cycloaliphatic epoxy resin with a photoinitiator such as $[\text{Ar}_2\text{I}]^+\text{BF}_4^-$ added. These systems exhibit excellent uncured thermal stability (typically stable up to 100°C) and require radiation in the region of 225 nm to effect rapid cure. Sensitizing dyes, such as acridine orange, can be added to change the optimum curing wavelength. These photoinitiators work by generating a so-called superacid, such as HBF_4 , in situ when irradiated and cure takes place by a cationic mechanism. Owing to the relatively long lifetime of an ionic species, the cure reaction continues to some extent in these resins after irradiation is stopped.³ Another feature of the cationic curing mechanism is a sensitivity to organic bases which poison the initiator and prevent cure. As a result, nitrogen containing epoxy resins, such as

1. GILLMAN, H. D., and EICHELBERGER, J. L. *The Application of Ultraviolet Cure Resins for Repair of Composites*. Pennwalt Corp., Contract N62269-77-M7197, Final Report, November 1977, NTIS Accession No. AD-A055731.
2. National Academy Press, *Report of the Committee on Room Temperature Curing Resin Systems*, NMAB-412, March 1984.
3. CRIVELLO, J. V., and LAMM, J. H. W. *Diaryliodonium Salts. A New Class of Photoinitiators for Cationic Polymerization*. *Macromol.*, v. 10, no. 6, 1977, p. 1307.

tetraglycidylmethylenedianiline (TGMDA) or diglycidylorthotoluidine [$\text{CH}_2(\text{C}_6\text{H}_4)\text{N}(\text{OCH}_2\text{CHOCH}_2)_2$], cannot be used with cationic initiators. Epoxies based on DGEBA (diglycidyl ether of bisphenol A), such as EPON 828, can be successfully cured by this method.

The resins used with their cure mechanism and approximate compositions are shown in Table 1.

Table 1. ULTRAVIOLET CURABLE RESINS STUDIED

Resin Name (Manufacturer)	Composition	Cure Type
Alcocure EBDMA (Alcolac)	Methacrylic acid ester of DGEBA, 98%.	Free radical
Uniset UV-900 (Amicon)	Urethane acrylate, 40-50% Acrylic monomers, 40-50% Initiators, <5%.	Free radical
Cel-Rad 3600 (Celanese)	Diacrylate ester of bisphenol A.	Free radical
Masterbond UV-10 (Masterbond)	100% UV reactive polymer probably an acrylate.	Free radical
Tactix 742 (Dow)	Triglycidyl ether of tris- (hydroxyphenyl)methane. A trifunctional epoxy resin.	Ionic using FX512*
Cyrcure 6110 (Union Carbide)	Cycloaliphatic epoxy resin.	Ionic using FX512*

*Cationic cure initiator, diphenyliodoniumtetrafluoroborate or closely related derivative 60%, with butyrolactone, 40% (manufactured by 3M Company).

Fiber Optics

Several companies produce optical fibers that are transparent to UV radiation, most based on fused silica. Two representative samples were obtained from Spectran Corporation for use in this study.

EVALUATION

Experiments were conducted to determine the suitability of some of the commercially available UV curing resins for use in graphite-reinforced composite systems. The experiments included determination of the effect of different UV sources on the cure behavior of the neat resins, the effect of increasing resin opacity using carbon black dispersed in the resins, and the behavior of the resin when used with small patches of graphite reinforcing cloth. Both surface irradiation and radiation introduced via optical fibers were used in various experiments.

Epoxy Resins Cured Using Cationic Initiators - Surface Irradiation

A key feature of these resin systems revealed by the experiments is their sensitivity to both the wavelength and intensity of the radiation used. Exposure to a 6500W Xenon Suprasil flash lamp (3 min @ 2 flash/sec, 100 μs /pulse) which did not provide significant UV radiation below 250 nm, was not sufficient to fully cure

a 1-ml sample of resin (Cyracure 6110 + FX512 4%). Similarly, one-hour exposure to 2-5W vacuum UV (Pen-Ray) Hg lamp did not cure the mixture. Exposure to a 100W (33W/in.) high pressure Hg lamp for 40 minutes cured the mixture to a leathery consistency. A 550W (122W/in.) high pressure Hg lamp was able to completely cure a 1-ml sample in 5 to 10 minutes (including approximately 5 minutes warm-up time). Cure times on the order of seconds are reported by the manufacturers using a 200W/in. medium pressure Hg lamp and thin films (inks, coatings) of the resin formulation. In view of the reported tendency of cationically cured resins to continue curing after irradiation was stopped,³ it was anticipated that the cationic cure system would be most suitable for use in graphite-reinforced composites. In these systems, the cure might be expected to propagate into areas receiving little or no direct irradiation. Repeated experiments showed that this is not the case. In experiments where a neat sample of a resin formulation was partially masked, no cure occurred in the unexposed fraction of the sample while the exposed fraction cured completely. In experiments where a patch of graphite cloth saturated with resin was irradiated, cure took place only at the irradiated surface. There was no evidence of propagation of the cure through the patch. Based on the sensitivity of the cationic curing resins to the intensity of the incident radiation, the possibility that the concentration of active (initiator) species was critical to cure behavior was investigated. Epoxy formulations containing 25% and 50% cationic initiator by weight were prepared and cured in pans that were partially masked from the UV lamp (100W or 33W/in. Hg lamp). No cure into the unirradiated portion of the sample was observed in any case, indicating that either lack of molecular mobility due to crosslinking or termination reactions dominate the system. This observation precludes the possibility of extensive propagation of cure away from the radiation source. Experiments done to determine if the presence of elemental carbon affected the cure showed that low concentrations (approximately 10% w/w) did not prevent cure and such formulations are specified for use as black lithography inks by the manufacturer of the curing agent. Formulations of 50% carbon black (a thick paste) with the resin would not cure. This resin/filler ratio approximates that found in fiber-reinforced composites.

Resins Cured By Free Radical Mechanism - Surface Irradiation

These materials are much less sensitive to the wavelength and intensity of the incident radiation than the cationically cured resins. A 2-5W Pen-Ray Hg lamp was not capable of fully curing a neat 1-2 ml sample of resin, but a 100W (33W/in.) Hg lamp fully cured such a sample with a few minutes exposure (Masterbond UV-10 resin). These resins can also be cured using a 6500W Xenon flash lamp (Germasil or Suprasil). Exposure of 15 seconds @ 2 flash/second (100 μ s/pulse) was sufficient to completely cure small samples of neat resin. A sample of resin was also cured after exposure to strong sunlight through a glass window for two days. No further curing takes place in partially cured samples without irradiation. Experiments in which samples were partially masked showed that no cure occurred in unexposed areas of the resins. Inclusion of small quantities (approximately 10% wt) of carbon black did not prevent curing, but when patches of graphite cloth were saturated with resin and irradiated, curing occurred only at the exposed surface.

Thermal and Mechanical Analysis of Cured Resins

Preliminary efforts to characterize the cured resins have employed differential scanning calorimetry (DSC) and torsional braid analysis (TBA) techniques. For Masterbond UV-10, DSC analysis of photocured samples showed that cure was 96% complete after 15 seconds exposure to 2 flash/second of a 6500W Xenon Suprasil flash lamp. After 120 seconds exposure to the same radiation, the cure was 99% complete. A broad T_g centered around 76°C was observed for both samples. TBA analysis of a sample of MB UV-10 cured on a glass braid using a 100W (33W/in) Hg lamp for one hour showed the onset of softening at 25°C. This method also showed that even after this extensive irradiation period, ultimate T_g is not achieved for samples cured on glass braids. Heating the sample through 200°C caused the softening onset temperature to rise about 35°C. The observation of low softening temperatures may reflect the fact that the resins being tested are formulated mainly for use as coatings and as such require some flexibility at ambient temperatures. Table 2 shows the results of TBA analysis of all the resins in the test. Several of these materials exhibited softening temperatures adequate for many types of service, supporting the idea that photocurable resin systems can be made viable for repair applications. If a very high ultimate T_g is critical, it may be necessary to use heat in conjunction with another curing mechanism (such as UV initiation) or to revert to thermally induced cure altogether.

Table 2. TBA ANALYSIS OF ULTRAVIOLET CURABLE RESINS

Resin	Scan	Onset of Softening (°C)
Alcocure EBDMA	1	77
	2	77
Uniset UV-900	1	0
	2	0
Cel-Rad 3600	1	0
	2	0
Masterbond UV-10	1	25
	2	35
Tactix 742 + 4% FX512	1	48
	2	77
	3	114
	4	132
Cyracure 6110 + 6.9% FX512	1	86
	2	86

TBA conditions: 1.5 °C/minute from -40 through 200°C.
All samples cured on a glass braid using a 100W
(33W/in.) medium pressure Hg lamp for 30-60 minutes.
Maximum temperature reached during cure was 60°C.

It should be noted that the long irradiation times used to cure the glass braid composites for the TBA experiment are not typical of these resins, and were not necessary to cure neat samples of the resins or flat glass-reinforced test patches. The reasons for this observation are not fully understood, but it may be that the very small cross section that the TBA braid presents to the UV source results in inadequate radiation flux for rapid cure.

Fiber Optics

No conclusions can be drawn at this time about the suitability of optical fibers for curing composite materials or photoinitiated resins in general. It was not possible to get sufficient energy into a fiber to effect cure at a fiber end with the equipment available. It is necessary to gather and focus diffuse light from a source into an intense spot on the fiber end. Special UV transparent optics are needed to avoid attenuation of the desired wavelengths. These optics were unavailable to us. It is most probable that neat photocurable resins can be cured using optical fibers since high energy transmission applications, such as laser steel cutting, have been demonstrated with these fibers. The unanswered questions concern the nature of the cure at a fiber end, specifically the distance cure can propagate from a fiber end and the shape of the irradiated/cured area. In the absence of resins that can propagate the cure reaction through an opaque material, the need to answer these questions is not acute.

The recent introduction of fiber optics transparent to infrared radiation is a development that may eliminate the requirement that a resin propagates cure away from the radiation source. Infrared radiation could potentially be introduced via optical fibers into a composite patch to initiate a conventional thermal cure. The principal advantage of this approach (as opposed to surface heating) is the ability to heat the patch uniformly and quickly. Efforts are now underway to investigate the potential of this method.

CONCLUSIONS

Current light curing resin technology is not applicable to graphite-reinforced composite materials. This conclusion can almost certainly be extended to include all reinforcing fibers/materials that significantly reduce transmission of the radiation used to induce cure in the material. In the case of the epoxy resins cured by cationic mechanism, it is not completely clear why the curing reaction will not propagate from an irradiated portion of a sample into a portion that has not been directly exposed. One likely possibility is that loss of molecular mobility as cure advances severely limits the extent of such an auto-cure process by preventing migration of monomer to the reactive sites in the growing polymer matrix. Another possibility is that the commercial resins contain impurities that terminate the reaction. In any event, it is considered unlikely that minor changes in formulation or cure conditions will render current photocuring technology suitable for use with composite materials using opaque reinforcing media.

FUTURE RESEARCH

Although currently available commercial UV curable resins are not suitable for use with graphite-reinforced composite materials, it may be possible to design a resin that would work in such an application. By incorporating into a resin a component that liberates a large quantity of heat, for example, it might be possible to photoinitiate fast thermal cure in epoxy resins. Another more exotic approach might be to incorporate a material that undergoes thermal decomposition with fluorescence and can effect an internal photocure.

Further study of the mode of propagation of cure through a resin may lead to suggestions for reactive additives which can propagate a photochemically induced cure reaction from irradiated to unirradiated regions in a resin, or through an opaque, but porous, material saturated with resin.

ACKNOWLEDGMENTS

The authors wish to thank Martin Drexhage and Richard Brown of the Air Force Geophysics Laboratory, Hanscom Field, Massachusetts, for their assistance with the fiber optic experiments. TGA and DSC analyses were performed by Walter Zukas and Bernard LaLiberte, respectively, of MTL. Xenon flash lamp cures were performed by Dana Granville and Seth Ghiorse of the Composites Development Division of MTL. High intensity UV lamps were loaned by Arthur Kaplan of Natick Research and Development Center, Natick, Massachusetts.

DISCLAIMER

The identification of commercial materials by name should not be considered as an endorsement of these products by the United States Government. It is done only for purposes of materials description. In addition, the findings reported herein reflect only on these studies and have no bearing on the adequacy of these materials for their intended uses.

DISTRIBUTION LIST

No. of
Copies

To

-
- 1 Office of the Under Secretary of Defense for Research and Engineering,
The Pentagon, Washington, DC 20301
- Commander, U.S. Army Laboratory Command, 2800 Powder Mill Road, Adelphi,
MD 20783-1145
- 1 ATTN: SLCIS-IM-TL
- Commander, Defense Technical Information Center, Cameron Station, Building 5,
5010 Duke Street, Alexandria, VA 22304-6145
- 2 ATTN: DTIC-FDAC
- 1 Metals and Ceramics Information Center, Battelle Columbus Laboratories,
505 King Avenue, Columbus, OH 43201
- Commander, Army Research Office, P.O. Box 12211, Research Triangle Park,
NC 27709-2211
- 1 ATTN: Information Processing Office
- Commander, U.S. Army Materiel Command, 5001 Eisenhower Avenue,
Alexandria, VA 22333
- 1 ATTN: AMCLD
- Commander, U.S. Army Materiel Systems Analysis Activity,
Aberdeen Proving Ground, MD 21005
- 1 ATTN: AMXSY-MP, H. Cohen
- Commander, U.S. Army Electronics Research and Development Command,
Fort Monmouth, NJ 07703
- 1 ATTN: AMDSD-L
- 1 AMDSD-E
- Commander, U.S. Army Missile Command, Redstone Arsenal, AL 35898
- 1 ATTN: AMSMI-RKP, J. Wright, Bldg. 7574
- 1 AMSMI-TB, Redstone Scientific Information Center
- 1 AMSMI-RLM
- 1 Technical Library
- Commander, U.S. Army Armament, Munitions and Chemical Command, Dover, NJ 07801
- 2 ATTN: Technical Library
- 1 AMDAR-QAC-E
- 1 AMDAR-LCA, Mr. Harry E. Pebly, Jr., PLASTECH, Director
- Commander, U.S. Army Natick Research, Development, and Engineering Center,
Natick, MA 01760
- 1 ATTN: Technical Library
- Commander, U.S. Army Satellite Communications Agency, Fort Monmouth, NJ 07703
- 1 ATTN: Technical Document Center

No. of
Copies

To

Commander, U.S. Army Tank-Automotive Command, Warren, MI 48090
1 ATTN: AMSTA-ZSK
2 AMSTA-TSL, Technical Library

Commander, White Sands Missile Range, NM 88002
1 ATTN: STEWS-WS-VT

President, Airborne, Electronics and Special Warfare Board, Fort Bragg,
NC 28307
1 ATTN: Library

Director, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground,
MD 21005
1 ATTN: AMDAR-TSB-S (STINFO)

Commander, Dugway Proving Ground, Dugway, UT 84022
1 ATTN: Technical Library, Technical Information Division

Commander, Harry Diamond Laboratories, 2800 Powder Mill Road, Adelphi, MD 20783
1 ATTN: Technical Information Office

Director, Benet Weapons Laboratory, LCWSL, USA AMCCOM, Watervliet, NY 12189
1 ATTN: AMSMC-LCB-TL
1 AMSMC-LCB-R
1 AMSMC-LCB-RM
1 AMSMC-LCB-RP

Commander, U.S. Army Foreign Science and Technology Center, 220 7th Street, N.E.,
Charlottesville, VA 22901
1 ATTN: Military Tech

Commander, U.S. Army Aeromedical Research Unit, P.O. Box 577, Fort Rucker,
AL 36360
1 ATTN: Technical Library

Director, Eustis Directorate, U.S. Army Air Mobility Research and Development
Laboratory, Fort Eustis, VA 23604-5577
1 ATTN: SAVDL-E-MOS (AVSCOM)

U.S. Army Aviation Training Library, Fort Rucker, AL 36360
1 ATTN: Building 5906-5907

Commander, U.S. Army Agency for Aviation Safety, Fort Rucker, AL 36362
1 ATTN: Technical Library

Commander, USACDC Air Defense Agency, Fort Bliss, TX 79916
1 ATTN: Technical Library

Commander, U.S. Army Engineer School, Fort Belvoir, VA 22060
1 ATTN: Library

No. of
Copies

To

- Commander, U.S. Army Engineer Waterways Experiment Station, P.O. Box 631,
Vicksburg, MS 39180
1 ATTN: Research Center Library
- Technical Director, Human Engineering Laboratories, Aberdeen Proving Ground,
MD 21005
1 ATTN: Technical Reports Office
- Commandant, U.S. Army Quartermaster School, Fort Lee, VA 23801
1 ATTN: Quartermaster School Library
- Naval Research Laboratory, Washington, DC 20375
1 ATTN: Dr. C. I. Chang - Code 5830
2 Dr. G. R. Yoder - Code 6384
- Chief of Naval Research, Arlington, VA 22217
1 ATTN: Code 471
- 1 Edward J. Morrissey, AFWAL/MLTE, Wright-Patterson Air Force, Base, OH 45433
- Commander, U.S. Air Force Wright Aeronautical Laboratories,
Wright-Patterson Air Force Base, OH 45433
1 ATTN: AFWAL/MLC
1 AFWAL/MLLP, M. Forney, Jr.
1 AFWAL/MLBC, Mr. Stanley Schulman
- National Aeronautics and Space Administration, Marshall Space Flight Center,
Huntsville, AL 35812
1 ATTN: R. J. Schwinghammer, EH01, Dir, M&P Lab
1 Mr. W. A. Wilson, EH41, Bldg. 4612
- U.S. Department of Commerce, National Bureau of Standards, Gaithersburg,
MD 20899
1 ATTN: Stephen M. Hsu, Chief, Ceramics Division, Institute for Materials
Science and Engineering
- 1 Committee on Marine Structures, Marine Board, National Research Council,
2101 Constitution Ave., N.W., Washington, DC 20418
- 1 Librarian, Materials Sciences Corporation, Guynedd Plaza 11, Bethlehem Pike,
Spring House, PA 19477
- 1 The Charles Stark Draper Laboratory, 68 Albany Street, Cambridge, MA 02139
- Wyman-Gordon Company, Worcester, MA 01601
1 ATTN: Technical Library
- Lockheed-Georgia Company, 86 South Cobb Drive, Marietta, GA 30063
1 ATTN: Materials and Processes Engineering Dept. 71-11, Zone 54

No. of
Copies

To

-
- 1 General Dynamics, Convair Aerospace Division, P.O. Box 748, Fort Worth, TX 76101
1 ATTN: Mfg. Engineering Technical Library
- 1 Mechanical Properties Data Center, Belfour Stulen Inc., 13917 W. Bay Shore Drive,
Traverse City, MI 49684
- 1 Mr. R. J. Zentner, EAI Corporation, 198 Thomas Johnson Drive, Suite 16,
Frederick, MD 21701
- 1 Dr. James Economy, IBM Corporation, K42-282, Monterey and Cottle Road,
San Jose, CA 95114
- 1 Professor George B. Butler, Department of Chemistry, University of Florida,
Gainesville, FL 32601
- 1 Professor Nathan D. Field, Department of Chemical Engineering, The City
College of the City University of New York, 38th Street & Convent Avenue,
New York City, NY 10031
- 1 Professor John K. Gillham, Department of Chemical Engineering, Princeton
University, Princeton, NJ 08540
- 1 Professor Morton H. Litt, Department of Macromolecular Science, Case
Western Reserve University, Cleveland, OH 44106
- 1 Dr. Stanley M. Barkin, Staff Scientist, National Materials Advisory Board,
National Academy of Sciences, 2101 Constitution Avenue, N.W., Washington,
DC 20418
- 1 Dr. John T. Quinlivan, The Boeing Company, P.O. Box 3707, M.S. 4456,
Seattle, WA 98124
- 1 Professor Garth L. Wilkes, Department of Chemical Engineering, Virginia
Polytechnic Institute & State University, Blacksburg, VA 24061
- 1 Mr. Ted Reinhart, Chief, Composites, Adhesives, & Fibrous Materials Branch,
Air Force Wright Aeronautical Laboratories (AFSC), Wright-Patterson Air
Force Base, OH 45433
- 1 Dr. Nibert Bikales, Director, Polymers Program, National Science Foundation,
1800 G Street, N.W., Washington, DC 10550
- 1 Dr. Norman J. Johnston, Head, Polymer Section, Langley Research Center,
Langley Station, Hampton, VA 23665
- 1 Dr. Bruno Fanconi, Leader, Structure and Properties Group, Polymer Sciences
and Standards Division, National Bureau of Standards, Room A 209, Building 224,
Washington, DC 20234
- Director, U.S. Army Materials Technology Laboratory, Watertown, MA 02172-0001
2 ATTN: SLCMT-IML
2 Authors

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION

Key Words
UV curing
Fiber optics
Low energy curing

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION

Key Words
UV curing
Fiber optics
Low energy curing

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION

Key Words
UV curing
Fiber optics
Low energy curing

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION

Key Words
UV curing
Fiber optics
Low energy curing

AD

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD

UNCLASSIFIED
UNLIMITED DISTRIBUTION

Key Words
UV curing
Fiber optics
Low energy curing

AD

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD

U.S. Army Materials Technology Laboratory,
Watertown, Massachusetts 02172-0001
EVALUATION OF RESINS CURED BY ULTRAVIOLET
RADIATION AND IN CONJUNCTION WITH FIBER
OPTIC SYSTEMS FOR USE IN THE FIELD REPAIR
OF COMPOSITE MATERIALS - Michael S. Sennett and
Stanley E. Wentworth

Technical Report MTL TR 87-15, March 1987, 8 pp -
tables, D/A Project IL161101A91A

Several commercially available resins designed to be cured with ultraviolet radiation were evaluated with respect to their potential for use in the field repair of composite materials. Thermal and mechanical properties of cured resins were evaluated by DSC and TBA techniques. Some cured resins exhibited physical properties which may be suitable for repair applications. None of the tested materials was able to cure when impregnated in woven graphite cloth which strongly attenuates the curing radiation. This prevented the use of fiber optics to cure these systems.

AD

UNCLASSIFIED
UNLIMITED DISTRIBUTION

Key Words
UV curing
Fiber optics
Low energy curing

END

7-87

DTIC