



AD-A191 005

OFFICE OF NAVAL RESEARCH Contract N00014-82-K-0280

Task No. NR413E001

TECHNICAL REPORT NO. 16

Construction of Pierced Hemispherical Grids

by



JII

Patrick A. Taylor

Prepared for Publication in

Journal of Vacuum Science and Technology A

Surface Science Center Department of Chemistry University of Pittsburgh Pittsburgh, PA 15260

28 January 1988

Reproduction in whole or in part is permitted for any purpose of the United States Government

This document had been approved for public release and sale; its distribution is unlimited

120 7 1931 - 22

REPORT DOCUMENTATION PAGE			READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER		2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
	16		
4. TITLE (and Subtitie	*)	<u></u>	5. TYPE OF REPORT & PERIOD COVERE
Construc	ction of Pierced Hem	ispherical	
Grids			
			- PERFORMING ORG. REPORT NUMBER
7. AUTHOR(3)		·	8. CONTRACT OR GRANT NUMBER(+)
· Patrick A.	Taylor		NOO014-82-K-0280
9. PERFORMING ORG	ANIZATION NAME AND ADDRE	55	10. PROGRAM ELEMENT. PROJECT, TASK
Surface Scie	ence Center. Chemist	rv Department.	AREA & WORK UNIT NUMBERS
University of	of Pittsburgh, Pitts	burgh, PA 15260	1
11 000000		· · · · · · · · · · · · · · · · · · ·	12 050007 0475
CONTROLLING OF	FICE NAME AND ADDRESS		1/29/88
			13. NUMBER OF PAGES
		. <u></u>	8
14. MONITORING AGE	ENCY NAME & ADDRESS(II diffe	rent from Controlling Office)	15. SECURITY CLASS. (of this report)
			UNCLASSIFIED
			154, DECLASSIFICATION DOWNGRADING
16. DISTRIBUTION ST	ATEMENT (of this Report) ATEMENT (of the abetract enter	ed in Block 20, if different fra	Am Report)
16. DISTRIBUTION ST	ATEMENT (of this Report)	ed in Block 20, if different fro	ver Report)
16. DISTRIBUTION ST	ATEMENT (of this Report) ATEMENT (of the abetract enter	ed in Block 20, if different fro	Am Report)
16. DISTRIBUTION ST	ATEMENT (of this Report) ATEMENT (of the abstract enter Y NOTES	ed in Block 20, if different fra	san Report)
16. DISTRIBUTION ST	ATEMENT (of this Report) ATEMENT (of the abetract enter y NOTES	ed in Block 20, il different fro	Am Report)
16. DISTRIBUTION ST	ATEMENT (of this Report) ATEMENT (of the abstract enter Y NOTES	ed in Block 20, il different fra	Schebble
16. DISTRIBUTION ST 17. DISTRIBUTION ST 18. SUPPLEMENTARY 19. KEY WORDS (Cont	ATEMENT (of this Report) ATEMENT (of the abetract enter Y NOTES	ed in Block 20, il dillerent fro end identify by block number	xn Report)
16. DISTRIBUTION ST 17. DISTRIBUTION ST 18. SUPPLEMENTARY 19. KEY WORDS (Cont	ATEMENT (of this Report) ATEMENT (of the abstract enter Y NOTES	ed in Block 20, if different fro and identify by block number,	Am Report)
16. DISTRIBUTION ST 17. DISTRIBUTION ST 18. SUPPLEMENTARY 19. KEY WORDS (Cont Electron Op	ATEMENT (of this Report) ATEMENT (of the abstract enter Y NOTES	ed in Block 20, il different fro and identify by block number,	Schebble
 16. DISTRIBUTION ST 17. DISTRIBUTION ST 18. SUPPLEMENTARY 19. KEY WORDS (Cont Electron Op Ion Optics Gride fabr 	ATEMENT (of this Report) ATEMENT (of the abstract enter y NOTES Inue on reverse eide if necessary tics	ed in Block 20, il different fro and identify by block number,	Am Report)
 16. DISTRIBUTION ST 17. DISTRIBUTION ST 18. SUPPLEMENTARY 19. KEY WORDS (Conr Electron Op Ion Optics Grids, fabr 	ATEMENT (of this Report) ATEMENT (of the abstract enter Y NOTES Inue on reverse eide if necessary tics ication	ed in Block 20, if different fro and identify by block number.	Schebble
 16. DISTRIBUTION ST 17. DISTRIBUTION ST 18. SUPPLEMENTARY 19. KEY WORDS (Cont. Electron Op Ion Optics Grids, fabr 20. ABSTRACT (Cont.) 	ATEMENT (of this Report) ATEMENT (of the abetract enter Y NOTES inue on reverse elde if necessary tics ication	ed in Block 20, il different fro and identify by block number, and identify by block number)	The this report we describe
 16. DISTRIBUTION ST 17. DISTRIBUTION ST 18. SUPPLEMENTARY 19. KEY WORDS (Cont. Electron Op Ion Optics Grids, fabr 20. ABSTRACT (Cont. an easy way of any shap material ma 	ATEMENT (of this Report) ATEMENT (of the abstract enter NOTES inue on reverse eide if necessary tics ication nue on reverse eide if necessary to construct hemisp e through the grids y be either stainles	ed in Block 20, if different fro and identify by block number, bherical grids and without distortin as steel or tungst	In this report we describe a procedure to cut holes g the grid itself. The grid en. The grid is made from a
 16. DISTRIBUTION ST 17. DISTRIBUTION ST 19. SUPPLEMENTARY 19. KEY WORDS (Cont Electron Op Ion Optics Grids, fabr 20 ABSTRACT (Conti an easy way of any shap material ma high transp. The grids a Once attach orid 	ATEMENT (of this Report) ATEMENT (of the abstract enter NOTES Unue on reverse elde if necessary tics ication nue on reverse elde If necessary to construct hemisp e through the grids y be either stainles arency 100x100 scree re shaped and spot w ed to the ring, hole	ed in Block 20, if different fro and identify by block number, bherical grids and without distortin as steel or tungst en mesh woven with welded onto stainl es of any shape ma	In this report we describe a procedure to cut holes g the grid itself. The grid en. The grid is made from a 0.001" diameter wire. ess steel annular rings. y be pierced through the

2

ストリアファン

date submitted:Jan.15, 1988 submitted to:J.Vac.Sci.Tech A Shop Notes

Construction of Pierced Hemispherical Grids.

Patrick A. Taylor

Surface Science Center, Department of Chemistry, University of Pittsburgh, Pittsburgh, Pennsylvania 15260

Apple An Fat Asson ς. $A_{i,j+1}$ A-1

Construction of Pierced Hemispherical Grids

Patrick A. Taylor Surface Science Center, Department of Chemistry, University of Pittsburgh, Pittsburgh, PA 15260

(received

A. Introduction

In this report we describe an easy way to construct hemispherical grids and a procedure to cut holes of any shape through the grids without distorting the grid itself. The grid material may be either stainless steel or tungsten. The grid is made from a high transparency 100x100 screen mesh woven with 0.001" diameter wire ¹. The grids are shaped and spot welded onto stainless steel annular rings. Once attached to the ring, holes of any shape may be pierced thorough the grid.

B. Construction of Grids

The procedure used to shape the hemispherical grids is similar to that described by Shaw and Bennett 2 and by Koch 3 . The construction of a hemispherical grid, described below, can serve as a model for any shaped grid.

The grid is pressure formed into a hemisphere. This is accomplished by pressing the tungsten mesh (W) between a brass mandrel (M) and an annular stainless steel plate (P),

-1-

as shown in Fig. 1. Brass is used for the mandrel because of its poor spot welding abilities. The whole assembly is held together with machine clamps (A) as the tungsten mesh is tacked in ~10 places to the stainless steel plate with a spot welder (S) (spot weld energy: 40 watt seconds). Once the grid is tacked on the plate, the grid and plate (W,P) are removed from the mandrel (M). The excess mesh is cut off and the wire ends are spot welded to the steel plate (spot weld energy: 25 watt seconds).

C. Piercing the Grids

To construct the holes, the center point of the hole is located and marked with a metal punch on the brass mandrel (M). The shape of the hole is then scratched into the brass with a scribe. The stainless steel plate (P) with the hemispherical grid is clamped to the mandrel in the proper orientation with respect to the hole. The entire assembly is placed in an aqueous salt solution (~100g NaCl in 2!) under a microscope, as shown in Fig. 2. The plate-mandrel (P-M) assembly acts as one spot welder electrode (S_1). The second electrode is constructed from 0.020" tungsten wire, with one end of the wire ground or cut to a point of approximately twice the mesh wire diameter; the other end is attached to a long piece of copper braid or wire, which

-2-

in turn is connected to the spot welder. This assembly allows the second electrode (S_2) to be maneuverable.

While viewing under the microscope, the point of the second electrode is placed on a wire of the tungsten mesh which intercepts the scribed guideline on the mandrel, as shown in the inset of Fig. 2. An electrical pulse of sufficient energy is used to cut the tungsten mesh (energy: 25 watt seconds). In this fashion the hole is cut out using the scribed guideline as a template to shape the hole. The salt solution is used to protect the brass mandrel from the heat produced during the cutting and may contribute to the electrical contact between the electrodes, the mesh, and the mandrel. Before removing the grid from the mandrel, the edges of the hole should be checked for any wires accidentally spot welded to the mandrel. Cutting the hole in air causes severe pitting of the brass mandrel and makes its subsequent use difficult.

Depending on the pressure applied between the wire mesh and the mandrel by the tip of electrode S_2 , the number of wires cut may vary. Usually the wire cut by the electrical arc is not limited to the point of contact, and the wires are cut up to the point where they intercept a perpendicular wire.

Once the hemispherical grid is removed from the mandrel some relaxation of the grid occurs, which distorts the sphericity. This very slight distortion from perfect

-3-

sphericity causes no discernible problems in the electrical properties of the grids. If one is concerned, however, electroplating or a heat treatment prior to piercing the grid may prevent this relaxation. If heat treatment is the preferred route, caution must be taken to use a vacuum compatible material for the mandrel used during the heat treatment (brass may not be used).

D. Acknowledgements

The procedures described here represent the accumulated knowledge passed down through our laboratory. The help and experience of Dr. Craig Klauber and Dr. Mark Alvey greatly contributed to the development of these techniques. The helpful comments on preparing this manuscript by Professor J.T. Yates, Jr. are also appreciated. The support of this work by the Office of Naval Research is also acknowledged.

E. References

- Wire weaves for grids may be obtained from Unique Wire Weaving Co., Inc., 762 Ramsey Avenue, Hillside, N.J. 07205.
- ² D.A. Shaw and D.A. Bennett, Review Sci. Instrum., 43 (1972) 1706.
- ³ J. Koch, Review Sci. Instrum., 45 (1974) 1212.

-4-

Figure Captions

- Figure 1. The pressure forming of hemispherical grids. Key: A-machine clamp; P-stainless steel annular ring plate; R-radius of hemispherical grid; S-spot welder; W-tungsten wire mesh.
- Figure 2. Assembly used to cut holes in hemispherical tungsten grids under an aqueous NaCl solution (energy: 25 watt seconds). Key: S₁-fixed spot welder electrode (mandrel-grid); S₂-movable spot welder electrode (tungsten needle).

Construction of Hemispherical Grid



Taylor

12123242

Figure 1



Taylor

Figure 2

DL/413/83/01 GEN/413-2

ALLE DOVIDE RASS

TECHNICAL REPORT DISTRIBUTION LIST, GEN

<u>c</u>	No. opies		No. Copies
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Douda Naval Weapons Support Center Code 5042 Crane, Indiana 47522	1	Naval Weapons Center Attn: Dr. Ron Atkins Chemistry Division China Lake, California 935 55	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 2770	1 9
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19 11	1 2
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1 -	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1
Dr. William Tolles Superintendent	1		

Superintendeat Chemistry Division, Code 5100 Naval Research Laboratory Washington, D.C. 20375