

AD-A193 704

ANOMALOUS DIFFUSION IN A WATER VAPOUR PERMEABLE  
WATERPROOF COATING(U) DEFENCE RESEARCH ESTABLISHMENT  
OTTAWA (ONTARIO) R J OSCZEYSKI ET AL. NOV 87

1/1


UNCLASSIFIED

DREO-TN-88-3

F/G 11/3

ML





MICROCOPY RESOLUTION TEST CHART  
NBS 1963-A

1



National  
Defence

Défense  
nationale



AD-A193 784

# ANOMALOUS DIFFUSION IN A WATER VAPOUR PERMEABLE, WATERPROOF COATING

by

K.J. Osczevski and P.A. Dolhan

DTIC  
ELECTE  
MAY 24 1988  
S D

DISTRIBUTION STATEMENT A  
Approved for public release  
Distribution Unlimited

DEFENCE RESEARCH ESTABLISHMENT OTTAWA

TECHNICAL NOTE 88-3

Canada

November 1987  
Ottawa

88 5 28 082

1



National  
Defence      Défense  
                  nationale

# ANOMALOUS DIFFUSION IN A WATER VAPOUR PERMEABLE, WATERPROOF COATING

by

R.J. Osczevski and P.A. Dolhan  
*Environmental Protection Section  
Protective Sciences Division*

DTIC  
ELECTE  
MAY 24 1988  
S      D  
    D

DISTRIBUTION STATEMENT  
Approved for public release  
Distribution Unlimited

DEFENCE RESEARCH ESTABLISHMENT OTTAWA  
TECHNICAL NOTE 887-3

PCN  
051LC

November 1987  
Ottawa

88 5 23 082

ABSTRACT

Different test methods give widely varying values of water vapour resistance for materials with hydrophilic coatings. An experiment was performed confirming that anomalous diffusion occurs in such materials, providing a mechanism by which to explain the various test results.

RÉSUMÉ

Des matériaux possédant des revêtements hydrophiliques donnent des valeurs de perméabilité à la vapeur d'eau qui varient énormément en fonction de la procédure expérimentale utilisée. Une expérience fut faite afin de confirmer que le processus de diffusion dans ce type de matériel dévie de la normalité. Le mécanisme de diffusion obtenu est utilisé pour expliquer les résultats tirés des autres méthodes expérimentales.



(iii)

Accession For	
NWS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT . . . . .	(iii)
1.0 INTRODUCTION . . . . .	1
2.0 METHOD . . . . .	1
3.0 RESULTS AND DISCUSSION . . . . .	2
4.0 CONCLUSION . . . . .	3
5.0 REFERENCES . . . . .	4

## 1.0 INTRODUCTION

An earlier study had been carried out to evaluate several methods of measuring the water-vapour resistance of coated, waterproof, but water-vapour permeable fabrics. The results, which are reported elsewhere (1), were inconsistent. It was found that the resistance values of individual fabrics and the ranking of the fabric within the series of fabrics varied from method to method. When the results and methods were examined, it became apparent that the fabrics with hydrophilic coatings had water-vapour resistance values which were humidity-dependent. The water-vapour resistance of such fabrics was high when the fabric was tested using a method in which the fabric was in relatively dry air. Conversely, the water-vapour resistance was low when the fabric was tested by a method in which the fabric was adjacent to a wet surface.

This paper reports the experiment carried out to examine the effect of relative humidity on the water-vapour resistance of a water-vapour permeable coated fabric. Only one experiment was carried out because, upon its completion, it was discovered that other workers had independently formulated and tested the same hypothesis with similar results. (C. A. B. de)

## 2.0 METHOD

Three plexiglass rings, 11.6 mm thick were made to fit the test area of the DREO (3) apparatus. A schematic diagram is shown in Figure 1. The circular hole in each was filled with polyester batting to reduce air movement. The fibre volume was less than 1%. The resistances of these batting-filled rings, and of combinations are given in Table I. The mean resistance of a spacer ring is  $11.6 \pm 0.5$  mm of equivalent still air (E.S.A.) which agrees nicely with the average ring thickness.




Figure 1: Cross-Sectional Schematic Diagram of Plexiglass Rings & Fabric Positions

TABLE I

Resistances of Spacer Rings

Ring No.	Resistance (mm E.S.A.) $\pm$ S.D.
1	12.0 $\pm$ 0.2
2	11.1 $\pm$ 0.7
3	11.6 $\pm$ 1.1
1 + 2	23.7 $\pm$ 4.5
1 + 2 + 3	35.6 $\pm$ 0.7
2 + 3	23.0 $\pm$ 5.9

The test sample was a three layer laminate of camouflage-printed polyester/cotton fabric, a polytetrafluoroethylene film (Goretex II), and a nylon tricot. It was 0.41 mm thick and had a mass of 0.17 kg per square metre. Goretex II has a hydrophilic coating applied to the porous PTFE film to protect it from sweat poisoning.

The effect of relative humidity (RH) on the sample resistance was determined by measuring the total resistance of the spacer rings plus the sample, with the sample at various locations in the stack. When the sample was between the dry side of the apparatus and the stack of three rings, the



RH at the level of the sample was at a minimum (Position 1). When it was between the stack of three rings and the water reservoir of the apparatus, the RH was at a maximum (Position 4). When the sample was between rings 1 and 2 and between 2 and 3 (Position 2,3) the RH was at some intermediate value which could be determined approximately from the relative resistances of the sample and the rings. It was assumed that the RH at the dry and wet ends was 0% and 100% respectively, and that the apparatus resistance was divided evenly between its wet and dry faces. The sample was conditioned to 65% RH before testing.

### 3.0 RESULTS AND DISCUSSION

The results are listed in Table II.

TABLE II

Resistance of Sample at Calculated Average Relative Humidities

Position	RH (%)	Resistance (mm air eq)
1	30	45 ± 15
2	44	45 ± 14
3	59	26 ± 15
4	88	3 ± 5
No spacers	50	17 ± 1

There is an obvious decrease of resistance to water vapour diffusion with an increase in relative humidity. Such behaviour has been previously noted by Fourt and Harris (4). In their experiments, the resistance of cellophane varied from 1.6 mm when tested over water at about 75% RH, to 48 mm when measured over a dessicant at an RH of about 40%. The dependence of diffusion rates on concentration is well established for many polymers (5). Similar behaviour has been reported for human skin (6) and keratin (7). This diffusion is referred to as non-Fickian or anomalous

diffusion. The diffusion constant appears to depend on the concentration of the vapour in the material. This may be a simplification of the process, as molecules do not spend all of their time diffusing, but are adsorbed by the molecules of the barrier for periods of time (8). Keighley (9) noted that the "breathability" of certain rainwear fabrics appeared to increase in wet conditions. It is possible that other hydrophilic materials, such as leather are similarly affected.

#### 4.0 CONCLUSION

The results confirm, for materials with hydrophilic coatings, the value of water-vapour diffusion resistance obtained from direct measurement will depend on the RH at which the measurement is made. Care should be taken when attempting to apply the results of such measurements to conditions which differ from those of the test.

#### 5.0 REFERENCES

1. Dolhan P.A. A comparison of apparatus used to measure water vapour resistance, submitted to J. of Coated Fabrics.
2. Farnworth B., Lotens W.A., Wittgen P.P.M.M. The variation of water vapour resistance of microporous and hydrophilic films with relative humidity, submitted to Textile Res. J.
3. Farnworth B., Dolhan P.A. An apparatus to measure the water-vapour resistance of textiles, J. Text. Inst. Vol. 75, No. 2, 1984, p. 142.
4. Fourt L., Harris M. Diffusion of water vapour through textiles, Text. Res. J., May 1947, p. 256.
5. Crank J. Diffusion in fibre-forming substances in "Moisture In Textiles", Hearle J., Peters R., editors Butterworths Scientific Publications, 1960.

6. Spruit D., Malten K. Humidity of the air and water vapour loss of the skin, *Dermatologica* Vol. 138, 1969, p. 418.
7. King G. Permeability of keratin membranes to water vapour, *Trans. Faraday Soc.* Vol. 41, 1945, p. 479.
8. Weisz P.B. The non-Fickian dogs, *Chemtech*, March 1981, p. 134-135.
9. Keighley J.H. Breathable fabrics and comfort in clothing, *J. Coated Fabrics*, Vol. 15, p. 89, October 1985.

## DOCUMENT CONTROL DATA

(Security classification of title, body of abstract and indexing annotation must be entered when the overall document is classified)

1. ORIGINATOR (the name and address of the organization preparing the document. Organizations for whom the document was prepared, e.g. Establishment sponsoring a contractor's report, or tasking agency, are entered in section 8.) DEFENCE RESEARCH ESTABLISHMENT OTTAWA Department of National Defence Ottawa, Ontario, Canada K1A 0Z4		2. SECURITY CLASSIFICATION (overall security classification of the document including special warning terms if applicable)  UNCLASSIFIED	
3. TITLE (the complete document title as indicated on the title page. Its classification should be indicated by the appropriate abbreviation (S,C,R or U) in parentheses after the title.)  ANOMALOUS DIFFUSION IN A WATER VAPOUR PERMEABLE, WATERPROOF COATING (U)			
4. AUTHORS (Last name, first name, middle initial)  OSCZEVSKI, Randall J. and DOLHAN, Patricia A.			
5. DATE OF PUBLICATION (month and year of publication of document)  NOVEMBER 1987	6a. NO. OF PAGES (total containing information. Include Annexes, Appendices, etc.)  8	6b. NO. OF REFS (total cited in document)  9	
7. DESCRIPTIVE NOTES (the category of the document, e.g. technical report, technical note or memorandum. If appropriate, enter the type of report, e.g. interim, progress, summary, annual or final. Give the inclusive dates when a specific reporting period is covered.)  TECHNICAL NOTE			
8. SPONSORING ACTIVITY (the name of the department project office or laboratory sponsoring the research and development. Include the address.)			
9a. PROJECT OR GRANT NO. (if appropriate, the applicable research and development project or grant number under which the document was written. Please specify whether project or grant)  051LC		9b. CONTRACT NO. (if appropriate, the applicable number under which the document was written)	
10a. ORIGINATOR'S DOCUMENT NUMBER (the official document number by which the document is identified by the originating activity. This number must be unique to this document.)  DREO TECHNICAL NOTE NO. 88-3		10b. OTHER DOCUMENT NOS. (Any other numbers which may be assigned this document either by the originator or by the sponsor)	
11. DOCUMENT AVAILABILITY (any limitations on further dissemination of the document, other than those imposed by security classification)  <input checked="" type="checkbox"/> Unlimited distribution <input type="checkbox"/> Distribution limited to defence departments and defence contractors; further distribution only as approved <input type="checkbox"/> Distribution limited to defence departments and Canadian defence contractors; further distribution only as approved <input type="checkbox"/> Distribution limited to government departments and agencies; further distribution only as approved <input type="checkbox"/> Distribution limited to defence departments; further distribution only as approved <input type="checkbox"/> Other (please specify):			
12. DOCUMENT ANNOUNCEMENT (any limitation to the bibliographic announcement of this document. This will normally correspond to the Document Availability (11). However, where further distribution (beyond the audience specified in 11) is possible, a wider announcement audience may be selected.)			

13. ABSTRACT ( a brief and factual summary of the document. It may also appear elsewhere in the body of the document itself. It is highly desirable that the abstract of classified documents be unclassified. Each paragraph of the abstract shall begin with an indication of the security classification of the information in the paragraph (unless the document itself is unclassified) represented as (S), (C), (R), or (U). It is not necessary to include here abstracts in both official languages unless the text is bilingual).

Different test methods give widely varying values of water vapour resistance for materials with hydrophilic coatings. An experiment was performed confirming that anomalous diffusion occurs in such materials, providing a mechanism by which to explain the various test results.

14. KEYWORDS, DESCRIPTORS or IDENTIFIERS (technically meaningful terms or short phrases that characterize a document and could be helpful in cataloguing the document. They should be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location may also be included. If possible keywords should be selected from a published thesaurus. e.g. Thesaurus of Engineering and Scientific Terms (TEST) and that thesaurus-identified. If it is not possible to select indexing terms which are Unclassified, the classification of each should be indicated as with the title.)

WATER VAPOUR  
MOISTURE TRANSFER  
DIFFUSION  
COATED FABRICS  
RAINWEAR  
TEST METHODS

END

DATE

FILMED

7-88

Dtic