BILL ALL LOUGH

LOW-TEMPERATURE PUMPABILITY OF U.S. ARMY DIESEL ENGINE OILS

INTERIM REPORT BFLRF No. 229

By

E.A. Frame A.F. Montemayor E.C. Owens Belvoir Fuels and Lubricants Research Facility (SwRI) Southwest Research Institute San Antonio, Texas

Under Contract to

U.S. Army Belvoir Research, Development and Engineering Center Materials, Fuels and Lubricants Laboratory Fort Belvoir, Virginia

Contract No. DAAK70-87-C-0043

1

ELECTE

AUG 2 3 1988

Approved for public release; distribution unlimited

December 1987

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Trade names cited in this report do not constitute an official endorsement or approval of the use of such commercial hardware or software.

DTIC Availability Notice

Qualified requestors may obtain copies of this report from the Defense Technical Information Center, Cameron Station, Alexandria, Virginia 22314.

Disposition Instructions

Destroy this report when no longer needed. Do not return it to the originator.

Unclassified SECURITY CLASSIFICATION OF THIS PAGE					
	REPORT DOCU	MENTATION	PAGE		
a. REPORT SECURITY CLASSIFICATION		16. RESTRICTIVE M	ARKINGS		
Unclassified		None			
a. SECURITY CLASSIFICATION AUTHORITY	_	3. DISTRIBUTION/A	VAILABILITY OF REPO	ORT elease	
かんな あ. DECLASSIFICATION/DOWNGRADING SCHEDULE		distribut	ion unlimite	ed	
<u>N/A</u>					
PERFORMING ORGANIZATION REPORT NUMBER(S)		5. MONITORING OR	GANIZATION REPORT	NUMBER(S)	
Interim Report BFLRF No. 229	_				
a NAME OF PERFORMING ORGANIZATION Belvoir Fuels and Lubricants	6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONI	TORING ORGANIZATI	ON	
Research Facility (SWRI)	<u> </u>	7. 4000555 (6)	Casta and ZIR Codel		
c. ADDRESS (City, State, and ZIP Code) Southwest Research Institute 6220 Culebra Road		76. ADDRESS (City,	State, and ZIP Code)		
San Antonio, TX 78284					
B. NAME OF FUNDING/SPONSORING ORGANIZATION U.S. Army Belvoir	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT DAAK70-82-	C-0001; DAAK	FICATION NUMBER	07, WD 9;
Engineering Center	STRBE-VF	DAAK70-87-	·C0043		
c. ADDRESS (City, State, and ZIP Code)		10. SOURCE OF FUI	NDING NUMBERS	TASK	
Fort Belvoir, VA 22060-5606		ELEMENT NO.	NO.	NO.	ACCESSION NO.
		62733A	1L762733AH2	P VLL	<u> </u>
2. PERSONAL AUTHOR(S) Frame, Edward A.; Montemayor, 3a. TYPE OF REPORT 13b. TIME CO Interim FROMJULY	Alan F.; and O VERED V 82 TO Dec 87	wens, Edwin	C. T (Year, Month, Day) mber	15. PAGE	
6. SUPPLEMENTARY NOTATION		- <u>- 1907 Beee</u>			
17. COSATI CODES	18. SUBJECT TERMS (C	Continue on reverse if ne	cessary and identify b	y block number	
FIELD GROUP SUB-GROUP MIL-L-2104D Borderline Oil Pumpability Temperature 15W-40 Oil 0il Pumpability VI Improver					
15W-40 Oil Oil Pumpability VI Improver Diesel Engine DDC 6V-53T. GM 6.2L. VTA 903-T. LDT-465					
Diesel Engine DDC 6V-53T, GM 6.2L, VTA 903-T, LDT-465 Borderline oil-pumpability temperatures (BPT's) were determined for U.S. Army diesel engines by prophing experiments approximate a product of the provided to the prov					
cranking experiments conducted in a cold box. The variables investigated included: four different diesel engine types; four different oil viscosity grades; and three different viscosity index improver chemical types. In general, for a given oil, the decreasing order of engine severity (i.e., highest					
BPT) was: the Continental LDT-465-1C and the Cummins VTA-903T were the most severe, and were approximately equivalent. The GM 6.2L engine was the next least severe with the DDC 6V-53T engine being the overall least severe. The different viscosity index improver chemistries of					
specially blended test oils inclu- polymethacrylate (PMA). The	uded: olefin cop PMA-containin	olymer (OCP) ng 15W-40 oi), styrene-iso Is had superi	prene polyn ior low-ten	ner (SI), and perature oil
SI VII had similar to slightly	better low-temp	perature pump	pability perfo	ormance th	an the OCP-
			<u> </u>) (************************************	(Continued)
		21. ABSTRACT SE	CURITY CLASSIFICA	TION	
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT	IPT. 🗍 DTIC USERS	Unclassi			
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT SUNCLASSIFIED/UNLIMITED SAME AS R 22a. NAME OF RESPONSIBLE INDIVIDUAL Mr. F.W. Schaekel	IPT. 🗆 DTIC USERS	22b. TELEPHONE (703) 664	(Include Area Code) -3576	Zc. OFFICE ST	/mbol /F

120.420.01.01

1.5.1.1

313515

Unclassified SECURITY CLASSIFICATION OF THIS PAGE

19. ABSTRACT (Continued)

containing oils. The BPT's determined by ASTM D 3829 did not completely predict engine-derived BPT's. Predicted BPT's (D 3829) were either higher or lower than engine-derived BPT's depending on the individual engine involved. The linear regression correlation coefficients (R-squared) resulting from the two different BPT values ranged from 0.61 to 0.88. Based on the engine-derived BPT's, recommendations for revised low-temperature use limits for MIL-L-2104D oils were made.

Unclassified SECURITY CLASSIFICATION OF THIS PAGE

FOREWORD

This work was conducted at the Belvoir Fuels and Lubricants Research Facility (SwRI), San Antonio, TX under Contract Nos. DAAK70-82-C-0001, DAAK70-85-C-0007 and DAAK70-87-C-0043 during the period July 1982 through December 1987. The work was funded by the U.S. Army Belvoir Research, Development and Engineering Center, Ft. Belvoir, VA, with Mr. F.W. Schaekel (STRBE-VF), as the Contracting Officer's Representative and Mr. T.C. Bowen (STRBE-VF) as the project technical monitor.

Accession For
NTIS GRAAT
1 10 TO TAR
Guerra and The
F Stateste Ston
By
p fritu's co/
Franket Lity Coles
Avell weeter
Dist oper in
n I I

ACKNOWLEDGMENTS

The authors wish to acknowledge the assistance provided by Mr. T.C. Bowen, the project technical monitor at Belvoir, and Mr. S.J. Lestz, Director of the Belvoir Fuels and Lubricants Research Facility at Southwest Research Institute. Recognition is made of the following people who helped in the conduct of the low-temperature engine oil pumpability determinations: Mr. R. Pena, Mr. E. Bass, and Mr. R.A. Alvarez. A special thanks is sent to the Rohm and Haas Company for its cooperation in supplying many of the test oils for this program.

TABLE OF CONTENTS

OTEXT

.

⁶.4.².4.8².4.8².4.5².4.6³.

CPUT

Section	on		Page
Ι.	INTE	RODUCTION AND BACKGROUND	1
	А. В.	Introduction ••••••••••••••••••••••••••••••••••••	1
11.	OBJ	ECTIVE/APPROACH ·····	3
III.	EQU	IPMENT/PROCEDURE	3
	A. B. C. D. E. F.	Test Engines Test Cell Description Instrumentation Test Lubricants Test Procedure Typical Oil Pressure Traces	3 4 6 11 11
IV.	RES	ULTS ·····	13
	A. B. C. D. E.	LDT-465-1C Engine GM 6.2L Engine DDC 6V-53T Engine Cummins VTA-903T Engine Summary	13 22 26 34 39
۷.	CON	CLUSIONS ·····	42
٧١.	REC	OMMENDATIONS ·····	43
VII.	LIST	OF REFERENCES	44
APPE	NDIC	ES	
	A. B. C. D. E. F.	Test Cell Configuration Test Procedure Low-Temperature Oil Pumpability in the LDT-465-1C Engine Low-Temperature Oil Pumpability in the GM 6.2L Engine Low-Temperature Oil Pumpability in the DDC 6V-53T Engine Low-Temperature Oil Pumpability in the	49 57 63 73 81
	-	Cummins VTA-903-T Engine	89

v

LIST OF ILLUSTRATIONS

1.0

1. a' 1. a' 1. a' 1. a' 1

1.7.5

Figure		<u>Page</u>
1	Cummins Engine Used to Crank LDT-465-1C Engine ·····	5
2	Rocker Arm Oiling Indicating System, GM 6.2L Engine ·····	7
3	Cooldown Cycle (84CP) Schematic ·····	12
4	Typical Oil Pressure Traces ·····	12
5	LDT-465-1C Engine in Cold Box ·····	15
6	Lubrication System Diagram for LDT-465-1C Engine ·····	16
7	Typical LDT-465-1C Oil Pressure Trace ·····	17
8	Regression of LDT-465 BPT on MRV BPT ·····	20
9	GM 6.2L Engine Lubrication System ••••••	22
10	Typical GM 6.2L Oil Pressure Trace ·····	23
11	Regression of GM 6.2 BPT on MRV BPT ·····	25
12	Lubricating System Diagram for DDC 6V-53T Engine ·····	28
13	Typical Pressure Trace for DDC 6V-53T Engine ·····	2 9
14	Regression of DDC6V BPT on MRV BPT ·····	31
15	Regression of DDC6V BPT on Pour Point ·····	33
16	Cummins VTA-903T Engine Oil Flow Diagram ••••••••••••••••••••••••••••••••••••	34
17	Typical Oil Pressure Trace for VTA-903T Engine ·····	35
18	Regression of C903 BPT on MRV BPT ·····	38
19	BPT Ranges for Viscosity Classes by Engine Type ·····	39

LIST OF TABLES

Table		Page
1	Lubricant Properties	8
2	Compositions of Special Oil Blends SF/CD Performance Level	9
3	Low-Temperature Pumpability Test Oils	10
4	Engine Specifications for the Continental LDT-465-1C Engine ·····	14
5	Effect of Pistons on Borderline Pumpability Temperature, LDT-465-1C Engine, Fast-Cool Procedure ••••••••••••••••••••••••••••••••••••	17
6	Cooling Cycle EffectLDT-465-1C Engine ·····	18
7	Extended Soak Time Effect LDT-465-1C Engine, 82CP ·····	18
8	Oil Borderline Pumpability Temperature (BPT) in LDT-465-1C Engine	19
9	BPT Regression AnalysisLDT-465-1C Engine	20
10	Used Oil Properties After One Pump Test LDT-465-1C 15W-40 Oils · · · · · · · · · · · · · · · · · · ·	21
11	Engine Specifications for the GM 6.2L Engine ••••••••••••••••••••••••••••••••••••	22
12	Oil Borderline Pumpability Temperature (BPT) in GM 6.2L Engine ••••••••••••••••••••••••••••••••••••	24
13	BPT Regression AnalysisGM 6.2L Engine ·····	26
14	Used Oil Viscosity of 15W-40 Oils After One Pump TestGM 6.2L Engine	26
15	Engine Specifications for the DDC 6V-53T Engine •••••••	27
16	Oil Borderline Pumpability Temperature (BPT) in DDC 6V-53T Engine	30
17	BPT Regression AnalysisDDC 6V-53T Engine ·····	32
18	Engine BPT Regression Analysis on Pour Point ·····	32
19	Used Oil Viscosity of 15W-40 Oils After One Pump TestDDC 6V-53T Engine ·····	33
20	Engine Specifications for the Cummins VTA-903T Engine •••••••	34

LIST OF TABLES (Cont'd)

<u>Table</u>		Page
21	Oil Borderline Pumpability Temperature (BPT) in Cummins VTA-903 Engine ·····	37
22	BPT Regression AnalysisVTA-903T Engine ·····	38
23	BPTs of Special Blend 15W-40s ·····	40
24	Summarized Results: Limiting BPTs ·····	41
25	Range of BPTs Within 15W-40 Oil Class · · · · · · · · · · · · · · · · · ·	41
26	Shear Effects for One Pumpability Test ••••••••••••••••••••••••••••••••••••	42

I. INTRODUCTION AND BACKGROUND

A. Introduction

Under cold ambient conditions, lubricants will increase in viscosity to the point that they will not flow into the oil pump, or flow through the oil galleries. This form of oil starvation is especially critical to engines that require prompt and copious lubrication to the turbocharger. Heavy-duty diesel engines used primarily in commercial transport fleets generally do not experience low-temperature lubricant pumpability problems. These decreased problems are because of (1) less frequent cold starts, as equipment is often idled instead of shut down during cold-ambient periods and (2) use of supplementa-ry electric engine block heaters in cold-weather locations. Diesel engine low-temperature pumpability is of concern to the U.S. Army because the combat-tactical fleet, which is powered primarily by diesel engines, must be ready to operate immediately at a wide variety of ambient temperatures throughout the world.

In a continuing effort to improve low-temperature operability, multiviscosity MIL-L-2104D diesel engine oils (15W-40) were introduced into the military supply system in early 1984.(1)* A need existed to better define the low-temperature use limits for multiviscosity and single-grade oils and apply these limits in the various lubrication orders for equipment.

B. Background

The vast majority of all previous work involving low-temperature oil pumpability was conducted in spark-ignition engines. In 1948, Appledoorn identified engine oil pumpability problems in winter with oils having high wax content and/or high viscosity at 0°F (-18°C).(2) Meyer conducted cranking determinations of military gasoline and diesel engines at arctic temperatures using oil that conformed to MIL-O-10295.(3) Moyer investigated oil pumpability of single and multigrade oils using an engine oil pump mounted in a pan.(4) Selby determined the viscosity/shear characteristics of reblends of the test oils from Moyer's work.(5) In 1967, the cold-cranking simulator was adopted to define low-temperature viscosity limits, and the extrapolated viscosity at 0°F (-18°C) was incorporated into the Society of Automotive Engineer's SAE Crankcase Oil Viscosity

^{*}Underscored numbers in parentheses refer to the list of references at the end of this report.

Classification System (SAE J300a).(<u>6-8</u>) The cold-cranking simulator is intended to correlate with engine cranking, which is a high shear rate process; however, oil flow, which is a low shear rate process, was not addressed by a bench test at this time.

In the early 1970's, interest in oil pumpability accelerated due to increased gasoline engine warranty claims that were believed to be related to low-temperature oil properties. The SAE requested that American Society for Testing and Materials (ASTM) develop an oil pumpability bench test. This task was investigated by ASTM D2 RDD VII-C, Engine Oil Pumpability Task Force. The technical literature of the 1970's abounds with papers concerning the investigation and definition of low-temperature oil pumpability.(9-18) Studies were conducted in gasoline engines, viscometers, and benchscale pumpability equipment.

In 1975, ASTM published the results of an extensive gasoline-engine based oil pumpability study. (19) Two oil pumpability failure modes were observed. Air binding occurred when the oil had sufficient gelation structure to prevent adequate oil flow to the oil pump. Air entering the oil pump caused both intermittent and continuous oil-pressure loss. Air binding was characteristic of relatively short, large diameter oil pickup tubes. The other pumpability failure mode was the flow-limited condition in which the oil was too viscous for an adequate flow rate. Oil pickup tubes with a relatively long length and small diameter were most sensitive to flow-limited failures. (19, 20)

At this point, research was directed towards developing a laboratory bench test that would respond to both air-binding and flow-limited oils. Several techniques were evaluated by the ASTM Test Method Task Force. A low shear rate apparatus, the minirotary viscometer (MRV), was selected as the test method that best related to the engine performance data (21) and was approved as ASTM Method D 3829.(22) The MRV requirements for winter-grade engine oils were incorporated into SAE Viscosity Classification System J-300 SEP80.(23) ASTM D 3829 (MRV) defines maximum values for yield stress (<105 Pa) and apparent viscosity (30 Pa·S). The yield stress is related to the air-binding tendency of the oil and is defined as the minimum stress required for oil flow, which is a measure of the gelation strength of the oil. The apparent viscosity limit is related to the flow-limited type of pumpability failure.

Despite the newly adopted low-temperature viscosity specification J-300 SEP80, severe engine oil pumpability failures occurred in spark-ignition engines during the winters of

1980 through 1983.(24-31) The oil pumpability related engine failures precipitated a new round of research to determine why the MRV test method was inadequate.(24-31) The sensitivity of some oils to cool-down rate was found to be the reason for the failure of the MRV test to identify oils with poor low-temperature performance.(24-26,31)

In 1987, MacAlpine and May reported that basestock pour points or residual wax contents alone do not predict low-shear viscometric properties of formulated engine oils under slow-cool conditions. The wax composition was reported to be a key factor with both normal and non-normal paraffins contributing to low-temperature viscosity increases.(32) The Stable Pour Point Test, Cycle C (FTM 791b, Method 203) was found to identify many, but not all, of the low-temperature problem oils.(31) The Stable Pour Point was included in the SAE Viscosity Classification System with requirements for 10W and 5W graded oils (SAE J300APR84).(31) Additional work is continuing on revising and defining cooling cycles for the MRV apparatus.

II. OBJECTIVE/APPROACH

The objective of this program was to define the minimum temperatures at which multiviscosity and straight-grade lubricants procured under military engine oil specifications may be used in U.S. Army diesel engines and still provide adequate lowtemperature lubrication. The approach was to determine the low-temperature oil pumpability characteristics of several U.S. Army engines using a variety of engine oils. This determination was accomplished by placing the subject engine in a cold box, charging it with test oil, and then cooling at prescribed conditions to the test temperature. The engine was then cranked at idle speed (without firing), and the time to a constant oil pressure was determined. An underlying assumption was that in the field, an Army engine will be started and idled by a slave engine and/or starting aids. The program was designed to ensure that the idling engine will be properly lubricated at low temperatures.

III. EQ'JIPMENT/PROCEDURE

A. Test Engines

Representative two- and four-cycle diesel engines were selected from the U.S. Army fleet for this work. The diesel engines investigated were:

- Teledyne-Continental Motors LDT-465-1C
- GM 6.2L

ß

COZZZZEN

- Cummins VTA-903-T
- DDC 6V-53T

Of the various LD-465 configurations available, the engine with the longest pickup tube was selected. Additional descriptions of each engine are presented in later sections.

B. <u>Test Cell Description</u>

A refrigerated box was used to cool the test engines to the desired test temperatures. The box was able to attain test temperatures as low as -40° F (-40° C) and maintain them $\pm 2^{\circ}$ F. The refrigeration equipment was controlled using a Honeywell UDC-500 controller and a Honeywell DPC-7700 set point programmer. This equipment allowed specification of cooling rates as described later.

Initially a 50-horsepower motoring dynamometer was used to motor the test engines at the desired speeds. This system proved to be difficult to use since the torque available at low speeds (800 to 1000 rpm) was very limited. As a result of this problem, and a fuel-dribble problem, discussed later, the pistons and connecting rods were removed from the first test engine (the Continental LDT-465-1C). This action lowered the motoring friction and made the use of the motoring dynamometer possible. Eventually, this approach was questioned since the connecting-rod lubrication system was eliminated with this approach. The pistons and connecting rods were reinstalled and an enginepowered motoring system was used. This design consisted of a driving engine, a clutch, a 12-speed truck transmission, and a driveshaft through the cold-box wall connecting the transmission to the flywheel of the test engine (Fig. 1). The clutch on the transmission was actuated with an air cylinder such that air pressure was required to disengage the clutch. A needle valve was used to control the air bleed rate from the cylinder and thus control the engagement rate of the clutch. Cranking speeds of 150 to 1000 rpm were possible using this cranking apparatus. Speeds lower than 150 rpm caused excessive torsional vibrations in the driveshaft and were avoided.

The fuel system of the first engine tested (the Continental LDT-465-1C) was plumbed to circulate fuel through the injection system for lubrication. However, dribble from the



Figure 1. Cummins engine used to crank LDT-465-1C engine

injectors (even in the no-rack position) caused exhaust fumes to fill the refrigerated box. As a result, each of the fuel systems in the test engines was disabled in order to prevent exhaust fumes from being present in the box. Appendix A contains details of the measures taken to disable the fuel systems.

The normal engine-mounted water pump was used to circulate a 50/50 volumetric blend of antifreeze and water in the cooling passages of the engine. A 1000-watt immersion heater was plumbed in the cooling line to facilitate warmup of the engine for purposes of oil flush. Circulation ran from the engine to the water pump to the heater and back to the engine. Four 250-watt infrared heating lamps were placed under the oil sumps of the engines. These lamps provided rapid heat up of the oil sump without disturbing the internal oil-pan geometry with heating coils. A Honeywell UDC-500 controller was used to control the temperature in the cold box. The controller received its set point from a Honeywell DCP-7700 set point programmer, which allowed controlled cool-down curves with respect to time. Since initial tests with the cold box revealed a tendency to freeze the evaporator coils on humid days, a defrost cycle was added to eliminate the icing. The defrost was set to initiate at midnight and last for 30 minutes. This defrost cycle effectively eliminated the icing problem but only introduced a slight perturbation into the cool-down cycle. Since the oil sump had significant thermal mass, the perturbation in the cool-down cycle had minimal impact on the bulk oil temperature.

Each engine was instrumented for oil-sump temperature, oil-suction pressure (in the oil pickup tube), oil-gallery pressure, turbocharger oil pressure (where applicable), engine speed, and in some cases, rocker-arm oiling indication/pressure. The air temperature in the cold box was also measured.

Rocker arm oiling was measured in one of two ways. In the case of the Cummins VTA-903T and DDC 6V-53T engines, a 15-psig pressure transducer was plumbed directly to the rocker shaft. This configuration was possible since both engines use a pressurized rocker shaft. In the case of the GM 6.2L engine, however, a pressurized push rod lubricates the rocker arm by drip feed. In order to obtain an indication of rocker arm oiling, a vacuum system was used to indicate the presence of oil in the rocker arm. Fig. 2 shows the rocker arm oiling indication system for the 6.2L engine. A detailed description of the test set up and installation is given in Appendix A.

D. Test Lubricants

A wide variety of diesel engine lubricants was evaluated during this program. The oils included special oils blended to a given viscosity, qualified products from MIL-L-2104D qualified products list, and commercially available oils. A variety of viscosity index improver (VII) additives were represented in the test oil matrix. Oils that exhibit cooling-cycle sensitivity (problem oils) were not included in the matrix. Since MIL-L-2104D oil specification includes a stable pour point requirement, it was felt that most problem oils would be eliminated from the military supply system. Also, future low-





temperature specifications will include cooling cycles and procedures to identify and eliminate "problem oils." Each drum of test lubricant was stored in an electrically heated water bath for at least 24 hours prior to testing and for the duration of testing. The temperature of the lubricant was maintained at 180°F (82°C) in order to provide all test lubricants with uniform temperature histories and destroy any previous temperature history.

The properties of the 15W-40 oils used in this program are presented in TABLE 1. Oil No. 1 is a MIL-L-2104D qualified product that was recently used in a field validation test (FVT) of 15W-40 oils at Ft. Bliss, TX.(33) Oil No. 2 is the MIL-L-2104D, 15W-40 grade Army reference oil and was used in the recent 15W-40 FVT at Ft. Knox, KY.(33) Oil Nos. 1 and 2 contain different olefin-copolymer VII systems. Oil Nos. 3 through 8 are special blends supplied by Rohm and Haas Company. Included are two of each oil based on olefin copolymer (OCP), polymethacrylate (PMA) and styrene-isoprene (SI) VI improvers, with each polymer-type oil formulated to the upper limit of SAE 15W in one case, and to the lower limit of SAE 15W in the second case. The oils supplied by Rohm and Haas are "well-behaved", that is, they have no major soak-time sensitivity. Compositions of the PMA and OCP special-blend oils are presented in TABLE 2. The oils were formulated with a detergent-inhibitor package to API SF/CD performance levels.

TABLE 1. Lubricant Properties (15W-40 Test Oils)

Lubricant No. <u>Description</u>	ASTM Method	l Qualified <u>MIL-L-2104D</u>	2 Qualified <u>MIL-L-2104D</u>	3 <u>0CP-L</u>	4 OCP-H	SI-H	6 SI-L	7 PMA-L	8 <u>PMA-H</u>	9 Comm. PMA	10 Comm. SI
<u>Properties</u>											
K. Vis., 40°C, cSt	D 445	107.47	99.06 	101.51	111.86	107.01	98.39 14 51	88.48	97.87	95.42 14.20	98.98 14 34
K. Vis., 100°C, cSt	D 445	13.66	13.51	14.90	14.6) 134	12.01	14.21	20.01	155	153	134
Viscosity Index	D 22/U	28.6	29.8	29.8	28.9	29.3	30.2	28.9	28.3	27.4	28.8
Pour Point, ^o C	D 97	-24	-26	-27	-27	-23	-25	-28	-28	-33	24
Borderline Pumpabil-									0	0	
ity, Temp ^o C	IJ 3829	-25.2	-27.3	-27.7	-26.3	-25.8	-28.6	-30.1	-28.2	67-	9.12-
Apparent Viscosity,	D 2602		4		0010	0366		1950	2200	1200	750
cp at -15°C		2900	2830	0661	3400	1626	0007	0027		0070	00.72
cp at -20°C		2000	*OZ	4100	67 50	6800	0065	4200	001/	0080	2000
cn at -25°C		CIN	GN	8500	13900	CIN	CN	0006	1 2600	nn g	
Total Acid No.	D 664	3.0	2.6	2.9	2.8	2.8	2.6	2.9	3.0	5.5	2.6 2.6
Total Base No.	D 664	7.0	5.4	5.6	- 5.6	5.6	5.1	5.3	5.5	6.2	8.0
Sulfated Ash, wt%	D 874	16.0	1.09	0.92	0.92	0.90	0.92	0.90	0.89	1.04	0.97
Element, wt%	Method										
Ва	ICP	< 0.005	< 0.005	<0.005 2.005	<0.005	< 0.005	<0.005	0.005	< 0.005	<0.005	< 0.005
Ca	ICP	<0.005	0.15	u.20	17.0	0.18	0.17	0710	07.0	17.0	17.0
Mg	ICP	0.15	< 0.05	<0.005	< 0.005	<0.005	<00°0	0.00.0	<0.00 0.005	<00°0	<0.00 2 2 2
zň	ICP	0.13	0.16	0.15	0.15	0.16	0.16	0.15	c1.0	0.16	0.13 0.13
٩	ICP	0.11	0.14	0.13	0.13	0.11	0.12	0.13	0.13	0.13	0.12
S	XRF	0.51	0.55	0.48	0.47	0.41	0.43	0.44	0.47	0.94	0.40
Z	CLM	0.07	0.05	0.09	0.09	0.09	0.10	0.06	0.06	0.11	0.12

JY KOY

110.010.010.010.010

8

* ND = Not Determined.

Oil Composition, wt%	Oil No. 3 Low 15W (OCP-L)	Oil No. 4 High 15W (OCP-H)	Oil No. 7 Low 15W (PMA-L)	Oil No. 8 High 15W (PMA-H)
Dispersant PMA VII	0	0	7.5	5.7
Nondispersant OCP VII	12.2	9.0	0	0
Ashless Dispersant	2.5	2.5	0	0
Detergent-Inhibitor				
Package	9.1	9.1	9.1	9.1
Basestock 10	35.8	0	25.6	0
Basestock 20	40.4	70.0	57.8	63.0
Basestock 35	0	9.4	0	22.2

TABLE 2. Compositions of Special Oil Blends SF/CD Performance Level

Because the OCP VII was a nondispersant type, ashless dispersant was included in the formulation of oil Nos. 3 and 4. Oil No. 9 is a commercially available 15W-40 product that is branded and sold by a major diesel engine manufacturer. Oil No. 10 is a well-regarded commercial oil (CD) from a major petroleum company.

The properties of the other (non-15W-40) oils investigated during this program are presented in TABLE 3. Oil No. 11 is a qualified MIL-L-2104D grade 30 product of 76 VI that is near the specification minimum limit. Considering low-temperature viscosity properties, oil No. 11 is actually a 25W-30 grade. Oil No. 12 is the MIL-L-2104D grade 30 (actually 20W-30) reference oil, and oil No. 13 is the grade 10W MIL-L-2104D reference oil.

Oil No. 14 is a 10W-30 special blend oil supplied by Rohm and Haas that contains an OCP VII and is similar in composition to 15W-40 oils No. 3 and 4. This 10W-30 is blended to the lower limit of SAE 10W. Oil Nos. 15 through 17 are commercially available products that contain synthetic basestock material. Oil No. 16 is a qualified MIL-L-46152 grade 5W-30 oil that contains polyalphaolefin basestocks. Oil No. 17 is a recent revision of oil No. 15 and has been qualified under MIL-L-2104D as a 15W-40 product. The basestocks of oil Nos. 15 and 16 are blends of polyol ester and polyalphaolefin materials.

TABLE 3. Low-Temperature Pumpability Test Oils

						:		1
Lubricant No. Viscosity Grade		11 SAE 30	12 SAE 30	13 10W	14 10W-30	15 5W-30	16 5W~30	17 5W-40
Description	A C T U	MIL-L-21	04D Qualified	Products	OCP-L		Synthetic Oils	
Properties	Method							
K. Vis., 40°C, cSt	D 445	124.17	95.82	39.95	64.19	56.0	61.97	85.95
K. Vis., 100°C, cSt	D 445	11.62	11.08	6.25	10.59	10.0	10.26	15.21
Viscosity Index	D 2270	76	101	103	155	167	1.54	188
API Gravity, ⁰	D 287	23.9	26.8	29.0	30.7	31.0	35.2	31.3
Pour Point, ^o C Borderline Pumnahil-	76 (1	-21	4 7-	رر-	17-	0+-	1(->	66-
ity Temp, ^o C	D 3829	-17.3	-22.4	-33.8	-28.3	-32.0	0+->	0+->
Apparent Viscosity,	D 2602							
cp at -150C	5250	1425	*0N	870	1170	ŊŊ	DN	
		at - 5°C	at -5°C					1
cp at -20°C		QZ	QN	3050	2150	1650	3900 at -30°C	QN
cp at -25°C		9600	3150	6400	6000	2550	2250	2300
	ť	at -10°C	at -10ºC	u (÷	с с	, c	3 5
Total Acid No.	D 664	5°5'	7.6 -	(' 7 '	7.4	D .0		
Total Base No.	D 664	10.9	7.4	1.3	 	6.3 	8.0	2.61
Sulfated Ash, wt%	D 874	1.1	16.0	0.40	0.89	1.10	00.1	1.42
Elements, wt%	Method							
Ba	ICP	< 0.005	< 0.005	<0.005	<0.005	<0.005	<0.005	< 0.005
Ca	ICP	0.27	< 0.00 <	<00.0>	0.21	0.27	<00.0<	91 . 0
Mg	ICP	0.08	cc1.0	0.15	<0.05	<00.0>	0.1/	(1.)
Zn	ICP	0.13	0.13	0.13	(1.)	0.13 2.13	0.11	010
L 0	VDE	0.12	0.12 150	0.46	0.14	0.33	0.56	0.20
γZ	CLM	0.04	0.00	0.06	0.09	0.14	0.05	0.07
*Note: ND - Not de	termined							

Note:

ND = Not determined ICP = Inductively coupled plasma XRF = X-ray fluorescence CLM = Chemiluminescence method

E. <u>Test Procedure</u>

The test procedure used for the lubricant pumpability determinations is described in Appendix B.

The timetable shown in the procedure was intended to provide each run with the same amount of cold-soak time, while still allowing adequate time to change lubricant and prepare for the next day's run. In some instances, the cold soak was extended over a weekend to investigate the effect of longer cold-soak periods. Normal cold-soak time was 20 hours total, with over-the-weekend tests consisting of 68-hour cold-soak periods.

Initially, in the LDT-465-1C engine, a fast-cooling cycle (82CP) was used. The oil was cooled quickly (approximately 2 hours) to the test temperature and held at test temperature approximately 18 hours until the pumpability test was started. This procedure was changed as information on the critical nature of oil cooling rate on pumpability of some engine oils became available in the literature. The new slower oil cooling procedure (84CP) used was essentially the "Sioux Falls" cycle (SFC) that included a programmed stepwise cooldown.(25) In the 84CP cooling procedure, the oil was cooled as fast as possible to a point 14°F above the desired pumpability test temperature and held there for 8 hours. During the next 8 hours, the temperature was slowly reduced 14°F to the desired test temperature and then held there 1.5 hours prior to attempting to pump the oil. During the 8-hour slow cooldown, the temperature is reduced 1°F over 2 hours, 2°F over the next 2 hours, 4°F over the next 2 hours, and 7°F over the last 2 hours. A schematic of the staged programmed cooling cycle is presented in Fig. 3.

F. Typical Oil Pressure Traces

When engine oil is pumped at low temperature in an engine, the amount of engine oil flowing is indicated by the oil pressure. Typical oil pressure traces are presented in Fig. $4.(\underline{19})$ A satisfactory condition is defined as adequate oil pressure within some minimum amount of time. Unsatisfactory oil pumping performance can be classified in the following four categories:

- flow limited
- typical borderline



Figure 3. Cooldown cycle (84CP) schematic



Figure 4. Typical oil pressure traces

- air binding
- no pump

In the flow-limited condition, adequate oil pressure develops; however, it does not occur within the minimum time due to inadequate oil flow. Typical borderline pump condition is characterized by initial adequate oil pressure; followed by inadequate pressure as the pump cannot move enough of the viscous oil and then recover to acceptable pressure as the system warms and oil viscosity reduces. A specialized type of borderline pumping is the air-binding condition, where the oil gel structure does not allow sufficient oil to flow to the oil pump pickup. As the oil is pumped away without total resupply, the oil pump intermittently sucks air that appears as sharp spikes on the oil pressure trace. The "no pump" condition occurs when the oil is too thick to be pumped at all. All of these conditions were observed within the matrix of oils and Army engines investigated during this program.

IV. RESULTS

A. LDT-465-1C Engine

The first engine to be investigated for low-temperature oil pumpability was the Continental LDT-465-1C used to power many of the U.S. Army tactical 2.5- and 5-ton trucks. The initial tests were run without engine pistons installed to reduce the breakaway torque requirements. Later tests were run with the pistons installed when a better cranking system was installed. A description of the LDT-465-1C engine is presented in TABLE 4. A photograph of the test engine installed in the cold box is Fig. 5. A schematic of the LDT-465-1C engine lubrication system is presented in Fig. 6, along with locations of the pressure pickup instrumentation. Turbocharger oil pressure was obtained from the oil feed line to the turbocharger; engine oil pressure was obtained from the midpoint of the oil pickup tube that runs between the front and rear sections of the oil pan.

Borderline pumping conditions for this engine at 600 rpm idle were defined as a minimum oil pressure of 40 psi at 1.0 minute and thereafter. The oil pressure limit was

	LDT-465-1C Engine
Model:	LDT-465-1C
Engine Type:	Four-Cycle, Compression Ignition, M.A.N. Combustion System, Turbocharged
Cylinders:	6 Inline
Displacement:	7.83 L (478 cubic inches)
Bore:	11.58 cm (4.65 inches)
Stroke:	12.37 cm (4.87 inches)
Compression Ratio:	22:1
Fuel Injection:	Bosch Rotary Distributor w/Density Compensation
Rated Power:	145-156 kW (194-209 BHP) at 2800 rpm
Rated Torque:	597 NM (429 lb-ft) at 2000 rpm
Idle Speed:	600 rpm (motoring speed for pumpability tests)

 TABLE 4. Engine Specifications for the Continental

selected based on the minimum oil pressure at idle listed in the Army training manual for the LDT-465-1C engine.(34) Gallery and turbocharger oil pressure were developed at the same time in this engine; thus, all borderline pumping determinations were made based on the gallery oil pressure. In general, the engine exhibited flow-limited behavior at temperatures well below the borderline pumping temperature (BPT) and air binding at temperatures near the BPT. Fig. 7 shows a typical oil pressure trace at borderline conditions in the LDT-465-1C engine.

A comparison was made between the BPTs obtained with and without pistons installed in the LDT-465-1C engine. As shown in TABLE 5, the BPTs were essentially equivalent with or without the pistons present.

The effect of the cooling cycle on the BPT of four different test oils was determined. As shown in TABLE 6, no major differences in BPT were observed for these four oils when tested using the fast- or slow-programmed cooling cycles. The two multigrade oils had slightly higher BPTs when using the slow-cool method. Thus, the slow-cool method was equivalent or possibly just slightly more severe than the fast-cool method. The programmed slow-cool cycle was used for all subsequent tests in different engines.

The effect of an extended cold soak on oil BPT in the LDT-465-1C engine was determined. The extended weekend soak consisted of following the normal slow-cooling cycle up to the point at which the cranking test would normally be made. At this point,



Figure 5. LDT-465-1C engine in cold box



Section Contraction

Figure 6. Lubrication system diagram for LDT-465-1C engine

48 hours were added to the cold soak before testing began, which increased the total extended soak test time to 68 hours. As shown in TABLE 7, the extended cold soak had no major effect on oil BPT.



222222

EXXXX2



TABLE 5. Effect of Pistons on Borderline Pumpability Temperature, LDT-465-1C Engine, Fast-Cool Procedure

		15 W -4	40 Oils	
	PM	A VII	OCP	· VII
	Oil No. 7	Oil No. 8	Oil No. 3	Oil No. 4
With Pistons Installed	-20°F(-29°C)	-17°F(-27°C)	-10°F(-23°C)	-6°F(-21°C)
Without Pistons	-18°F(-28°C)	-16°F(-27°C)	-10°F(-23°C)	-5°F(-21°C)

01111	N	Fast Cool	Programmed Slow Cool
<u>011 No.</u>	Description	<u>82CP</u>	<u>84CP</u>
1	15W-40	-8°F(-22°C)	-4°F(-20°C)
12	SAE 30	-4°F(-20°C)	-4°F(-20°C)
13	10 W	-22°F(-30°C)	-22°F(-30°C)
4	15 W- 40 OCP-H	-6°F(-21°C)	-4°F(-20°C)

TABLE 6. Cooling Cycle Effect—LDT-465-1C Engine

TABLE 7. Extended Soak Time Effect LDT-465-1C Engine, 82CP

		Time to 40 psi Oil Gallery Pressure, min			
<u>Oil No.</u>	Description	Normal Soak (20 Hr)	Extended Soak (68 Hr)		
13	10W at -24°F(-31°C)	1.63	1.70		
7	15W-40, PMA-L at -18°F(-28°C)	0.65	0.75		

The results of low-temperature oil pumpability evaluations in the LDT-465-1C engine are presented in TABLE 8. Since the two cooling procedures (slow and fast programmed) yielded essentially the same BPTs, all data are presented. Some of the oils were received later in the program and were not evaluated in this engine and are reported as not tested. Appendix C contains plots of test temperature versus time to minimum required oil pressure for the LDT-465-1C engine. For the multigrade oils, the only points plotted were for tests of new unsheared oils. To conserve oil, multigrade oils were re-run to help in locating the approximate BPT. However, the actual BPT was always confirmed using new, unsheared multigrade oil. For the 15W-40 oils, Oil No. 1, which contains an OCP VII system, and special blend Oil No. 4 (OCP-H) were the most severe oils with each having a BPT of -4° F (-20°C). For blends of equivalent lowtemperature viscosities, those containing PMA VII additive had substantially lower BPTs than the oils formulated with OCP VII. Oil No. 11 (75 VI) had the most severe SAE 30 grade BPT at $+6^{\circ}$ F(-14°C), while the straight 10W grade (Oil No. 13) had a BPT of -22° F (-30°C). Overall, the BPTs developed in the LDT-465-1C were more severe (higher

Oil No.	Oil Description	Cooling Cycle	BPT, °F(°C)	MRV/BPT,
	15W-40 Oils			
1 2 3 4 5 6 7 8 9 10	MIL-L-2104D (OCP) MIL-L-2104D (OCP) OCP-L OCP-H SI-H SI-L PMA-L PMA-H Commercial PMA Commercial SI	84CP 82CP 82CP 84CP NT NT 82CP 82CP NT NT	-4(-20) -8(-22) -10(-23) -4(-20) NT NT -20(-29) -17(-27) NT NT	-13(-25) -16(-27) -18(-28) -16(-27) -15(-26) -18(-28) -22(-30) -19(-28) -20(-29) -17(-27)
	30-Grade Oils			
11 12	MIL-L-2104D 75 VI MIL-L-2104D Others	84CP 84CP	+6(-14) -4(-20)	+1(-17) -8(-22)
13 14 15 16	10W MIL-L-2104D 10W-30, OCP-L 5W-30, Synthetic 5W-30, Synthetic	84CP 82CP NT 84CP	-22(-30) -12(-24) NT <-33(-36)	-29(-34) -19(-28) -26(-32) < -40(-40)
NT OCP SI PMA	 Not tested. Olefin copolymer VII. Styrene-Isoprene VII. Polymethacrylate VII. 			

TABLE 8. Oil Borderline Pumpability Temperature (BPT) in LDT-465-1C Engine

temperature) than the BPTs calculated from the MRV (ASTM D 3829). A plot of the linear regression of engine-derived BPT on MRV BPT is presented in Fig. 8, and a summary of the regression analysis is in TABLE 9. In Fig. 8, the two pairs of dotted lines represent the 95-percent confidence and prediction limits. Based on this linear regression, which has a correlation coefficient (R-squared) of 0.86, approximately 86 percent of the variability in the engine-derived BPT is explained by the MRV BPT. In general, the engine-derived BPT was approximately 6°F higher than the MRV BPT.





TABLE 9. BPT Regression Analysis--LDT-465-1C Engine

Regression Analysis - Linear model: Y = a+bX Dependent variable: LDT465BPT

Independent variable: MRVBPT

Parameter Intercept Slope	Estimate 6.1732 0.985736	-	tandard <u>Error</u> 2.44399 0.13843	T Value 2.52587 7.12082	Prob. Level 0.0354826 9.99193E-5			
	Analysis of Variance							
	Sum of	-	Mean		Prob.			
Source	Squares	Df	Square	F-Ratio	Level			
Model	572.21982	<u> </u>	572.21982	50.70613	0.00010			
Error	90.280183	8	11.285023					
Total (Corr.) 662.50000 9		9						
Correlation Coefficient = 0.92937 Std. Error of Est. = 3.35932		937	R-squared = (0.86				

The 15W-40 multigrade oils experienced shear during the pumping test. TABLE 10 shows the effect of a single pump test on oil properties. The oils lost between 0.2- to 2.2-centistokes viscosity at 100°C, and most oils had slightly lower MRV BPTs after experiencing one pump test. Cold-cranking simulator viscosities were slightly reduced in most, but not all cases. These data illustrate the importance of conducting engine pumpability tests with fresh, unsheared test oils.

TABLE 10. Used Oil Properties After One Pump Test-LDT-465-1C 15W-40 Oils Oil No. 7 1 2 8 3 OCP-L OCP OCP PMA-L Description OCP-H PMA-H Oil Properties K. Vis, 40°C, cSt New 107.47 99.06 101.51 111.86 88.48 97.87 Used 86.00 103.40 83.28 94.94 99.78 99.43 Δ 7.69 0.37 15.51 8.46 5.20 2.93 K. Vis, 100°C, cSt 14.90 14.65 15.02 14.58 New 13.66 13.31 Used 12.81 13.37 13.96 13.98 13.07 12.72 Δ 1.28 0.85 0.24 2.18 1.06 0.60 BPT, °C New -25.2 -27.3 -27.7 -26.3 -30.1 -28.2 Used -31.0 -26.4 -27.8 -26.0 -26.3 -28.1 Δ +0.1+0.9 -0.4 +0.8 -1.0 +0.4 CCS,* -15°, cp 3400 New 2900 2830 1950 1950 3300 3150 Used 2100 3200 3400 3300 1850 Δ -100 -250 +500 +470 +150 -100 CCS, -20°C, cp 4100 6750 4200 7150 New 7000 ND** Used <u>6790</u> 3450 6000 4000 6800 Δ -10 -650 -750 -200 -350 *Cold cranking simulator

**ND=No. determined

#`1_#*4_#`6_#`6_#*6_#_6_#`6

B. GM 6.2L Engine

Low-temperature oil pumpability was investigated in the GM 6.2L engine used to power the U.S. Army HMMWV and CUCV vehicles. All tests were run with the pistons installed and followed the 84CP (slow programmed) cooling cycle. A description of the 6.2L engine is presented in TABLE 11. A schematic of the 6.2L engine lubrication system and the locations of BFLRF oil pressure instrumentation are shown in Fig. 9.(35) Gallery oil

TABLE 11. Engine Specifications for the GM 6.2L Engine







pressure was measured at the front of the right-hand side valve lifter gallery, the furthest point from the oil pump. Rocker-arm oiling time was determined for this engine at the right rear rocker arm.

#18187848384284828442844284428442

Borderline pumping conditions for the 6.2L engine at 800-rpm idle were defined as a minimum oil pressure of 30 psi at 1.0 minute and thereafter. According to the 1984 GMC pickup truck owner's manual, oil pressure at normal operating temperatures with proper engine cooling should be 30-40 psi. If 30 psi is adequate oil pressure during normal operation, it should also be adequate for cold-temperature idle and was selected as the limit. While an oil pressure of less than 30 psi may be acceptable at idle, the oil pressure trace curve is essentially a straight vertical line between 10 and 40 psi, as shown in Fig. 10. This means that the oil BPT as determined by oil pressure at 1.0





minute would be the same for any oil pressure limit between 10 and 40 psi. The 6.2L engine was generally flow limited at temperatures below the BPT and exhibited some very limited air-binding at temperatures near the BPT, as shown in Fig. 10.

<u>ᡧ᠈ᠵᢣ᠈ᡷ᠈ᡷ᠈ᡷ᠈ᡷ᠈ᡷ᠈ᡷ᠈ᡷ᠈ᡷ᠈ᡷ᠅ᡛᡵᡭᡃᡛᡵᡭᡃᡛᡵᡭ᠘ᡱᡭ᠘ᡛᡵᡭ᠔ᡛᡷᡭᡇᡱ</u>᠅ᡛᡵᡭ᠈ᡛᡵᡭ᠈ᡛᡵ᠋ᡭ᠈ᡛᡵᡭ᠈ᡛᡵᡭ᠈ᡛᡵᡭ᠈ᡛᡵᡭ᠈ᡛᡵᡭ᠈ᡛᡵᢥᡵᡛᡵᢤᡵᡀ᠈᠈ᡛᡵ᠅ᡵᡛ᠈᠈ᡷᢧ᠈᠈ᢢᢧ᠈᠂ᡵᢑ᠈

The results of the borderline oil pumpability temperature determinations in the 6.2L engine are presented in TABLE 12. Plots of test temperature versus time to the minimum required oil pressure are provided in Appendix D. In this engine, the most severe 15W-40 oil was Oil No. 5 (special blend SI-H) with a BPT of -9°F (-23°C), while

Oil <u>No.</u>	Oil Description	BPT, °F(°C)	MRV BPT, 	Rocker Arm Oiling Time, minutes
	15 W- 40 Oils			
1 2 3 4 5 6 7 8 9 10	MIL-L-2104D (OCP) MIL-L-2104D (OCP) OCP-L OCP-H SI-H SI-L PMA-L PMA-L Commercial PMA Commercial SI	-12(-24) -17(-27) -16(-27) -11(-24) -9(-23) -15(-26) NT NT NT NT -11(-24)	-13(-25) -16(-27) -18(-28) -16(-27) -15(-26) -18(-28) -22(-30) -19(-28) -20(-29) -17(-27)	12 14 12 13 13 13 NT NT NT 12
	30 Grade Oils			
11 12	MIL-L-2104D (75 VI) MIL-L-2104D	+2(-17) -5(-21)	+1(-18) -8(-22)	12 12
	Others			
13 14 15 16	10W, MIL-L-2104D 10W-30, OCP-L 5W-30, Synthetic 5W-30, Synthetic	-28(-33) -22(-30) NT <-22(-30)	-29(-34) -19(-28) -26(-32) <-40(-40)	13 14 NT >14
NT = OCP = SI = PMΛ =	Not tested. Olefin copolymer VII. Styrene-Isoprene VII. Polymethacrylate VII.			

 TABLE 12. Oil Borderline Pumpability Temperature (BPT)
 in GM 6.2L Engine

Oil No. 11 (75 VI) had the highest BPT of the SAE 30 grades at +2°F (-17°C). The straight-grade 10W had a BPT of -28°F (-33°C). Of particular interest was the rather long rocker-arm oiling times observed for this engine. At borderline pumpability temperature, rocker-arm oiling time was consistently between 12 and 14 minutes. Overall, the BPT, as determined by MRV, was a better predictor of engine-determined BPT in this engine than in the LDT-465-1C engine. Fig. 11 shows a plot of the linear regression of engine-derived BPT on MRV BPT, which had a correlation coefficient (R-squared) of 0.88. The regression analysis summary is presented in TABLE 13. By this analysis, the engine-derived BPTs were approximately 2.5°F higher temperature than the BPT by ASTM D 3829.



The used oil kinematic viscosity at 100°C was determined after one pumpability test for the 15W-40 oils tested to determine shear degradation of the oils. As shown in TABLE 14, viscosity loss at 100°C ranged from 0.5 to 1.5 cSt after one pumping test,

Regression Dependent v	Analysis - Linear m variable: DD62BPT	odel: Y = a	a+bX	Independent vari	able: MRVBPT		
Parameter Intercept Slope	Estimate 2.53391 1.02305	5 2 0	tandard Error .14021 .127284	T Value 1.18396 8.03759	Prob. Level 0.266756 2.13206E-5		
Analysis of Variance							
<u>Source</u> Model Error	Sum of Squares 569.56195 79.347143	<u>Df</u> 1 9	Mean <u>Square</u> 569.56195 8.816349	F-Ratio 64.60292	Prob. Level 0.00002		
Total (Corr.) 648.90909 10							
Correlation Std. Error o	Coefficient = 0.936 f Est. = 2.96923	868	R-squared =	• 0.88			

TABLE 13. BPT Regression Analysis-GM 6.2L Engine

TABLE 14. Used Oil Viscosity of 15W-40 Oils After One Pump Test--GM 6.2L Engine

		K. Vis, 100°C, cSt		
<u>Oil No.</u>	Description	New	Used	Loss
1	OCP	13.66	12.75	0.91
2	OCP	13.31	12.85	0.46
3	OCP-L	14.90	13.38	1.52
4	OCP-H	14.65	13.12	1.53
6	SI-L	14.51	13.63	0.88
7	SI-H	13.97	13.62	0.35

which was very similar to the observed viscosity loss in the LDT-465-1C engine. Overall, the 6.2L diesel engine was less severe than the LDT-465-1C with respect to low-temperature oil pumpability.

C. DDC 6V-53T Engine

The next engine to be investigated for low-temperature oil pumpability was the DDC 6V-53T, which is representative of a two-cycle diesel engine series used to power many
of the U.S. Army combat vehicles. For all tests, the slow-cooling procedure (84CP) was used, and pistons were installed. A description of the DDC 6V-53T engine is presented in TABLE 15. Fig. 12 contains a schematic of the engine lubricating system with the locations of the oil pressure pickups used in the tests. (36) Gallery oil pressure was obtained from the left rear main oil gallery; turbocharger oil pressure was obtained from the right from the oil line feeding it; and rocker-arm oil pressure was obtained from the right front cylinder (1R).

Model:	5063-5395
Engine Type:	Two-Cycle, Compression Ignition, Direct Injection,
	Turbo-supercharged
Cylinders:	6, V-Configuration
Displacement:	5.21 L (318 cubic inches)
Bore:	9.8 cm (3.875 inches)
Stroke:	11.4 cm (4.5 inches)
Compression Ratio:	18.7:1
Fuel Injection:	DD Unit Injectors, N-70
Rated Power:	224 kW (300 BHP) at 2800 rpm
Rated Torque:	858 NM (633 lb-ft) at 2200 rpm
Idle Speed:	600 rpm (motoring for pumpability tests)

TABLE 15. Engine Specifications for the DDC 6V-53T Engine

Borderline oil-pumping conditions for the 6V-53T engine at 600 rpm idle were defined as a minimum turbocharger oil pressure of 30 psi at 1.0 minute and thereafter. The 6V-53T oil qualification test procedure has an oil-pressure limit of 30 psi at operating speeds and temperatures. (<u>37</u>) The same 30-psi limit was selected for this program to provide a margin of safety at cold idle conditions. As with the 6.2L engine, the oil pressure trace for the 6V-53T engine is nearly a vertical line between initial pumping and 50 psi; thus, the BPT as determined by minimum oil pressure at 1.0 minute would be nearly the same for any oil pressure limit between 5 and 50 psi. A typical oil pressure trace for a pumpability test is shown in Fig. 13. In the 6V-53T, at BPT conditions, the gallery had almost immediate oil pressure, while pressure to the turbocharger developed slightly later. Air binding was observed in the gallery pressure trace and, to a lesser extent, in the turbocharger trace at BPT conditions. A sudden spike of loss in turbocharger oil pressure, followed by an immediate recovery in oil pressure, was a typical oil-pumpability characteristic of this engine at low temperatures.



Figure 12. Lubricating system diagram for DDC 6V-53T engine





The results of the oil pumpability tests in the 6V-55T engine are presented in TABLE 16. Plots of test temperature versus time to the minimum required idle oil pressure are in Appendix E. In this engine, the most severe 15W-40 oil was Oil No. 1 (OCP) with a BPT of $-11^{\circ}F$ (24°C), vhile Oil No. 11 (75 VI) (an SAE 30 grade) had the highest BPT at $+1^{\circ}F$ ($-17^{\circ}C$). The SAE 10W grade (Oil No. 13) is not recommended for use in this engine series; however, it was evaluated for information only and found to have a BPT of $-30^{\circ}F$ ($-34^{\circ}C$). Rocker-arm oiling times at BPT conditions were between 2 and 3 minutes for most of the oils. Fig. 14 shows a plot of the linear regression of enginederived BPT on the BPT from the MRV. The correlation coefficient (R-squared) for this regression was only 0.61 (TABLE 17). The 6V-53T engine has a very powerful oil pump,

Oil <u>No.</u>	Oil Description	BPT ºF(ºC)	MRV BPT, 	Rocker-Arm Oiling Time, minutes	Pour Point, °F(°C)
	15 W -40 Oils				
1 3 4 5 6 7 8 9 10	MIL-L-2104D (OCP) MIL-L-2104D OCP-L OCP-H SI-H SI-L PMA-L PMA-H Commercial PMA Commercial SI	-11(-24) -16(-27) -16(-27) -13(-25) -21(-29) -19(-28) -24(-31) -21(-29) -24(-31) -20(-29)	-13(-25) -16(-27) -18(-28) -16(-27) -15(-26) -18(-28) -28(-33) -19(-28) -22(-30) -17(-27)	2.0 2.8 2.5 2.4 3.7 2.4 3.0 3.5 3.8 3.0	-11(-24) -15(-26) -17(-27) -17(-27) -9(-23) -13(-25) -18(-28) -18(-28) -27(-33) -11(-24)
	30-Grade Oils				
11 12	MIL-L-2104D (75 V MIL-L-2104D Others	(I) -13(-25) -15(-26)	-1(-17) -8(-22)	4.0 2.8	-6(-21) -11(-24)
13 14 15 16	10W, MIL-L-2104D 10W-30, OCP-L 5W-30, Synthetic 5W-30, Synthetic	-30(-34) NT NT < -30(-34)	-29(-34) -19(-28) -26(-32) < -40(-40)	3.1 NT ND	-27(-33) ND ND ND
NT OCP SI PMA ND	 Not tested. Olefin copolymer VII. Styrene-Isoprene VII. Polymethacrylate VII Not determined. 	•			

TABLE 16. Oil Borderline Pumpability Temperature (BPT) in DDC 6V-53T Engine

as it was able to pump oils through the system at temperatures near or below their pour point where the oils are a semisolid slush. For example, Oil No. 11 (75 VI SAE 30 grade) had a pour point of $-6^{\circ}F(-21^{\circ}F)$, and an engine-derived BPT of $-13^{\circ}F(-25^{\circ}C)$. Pour point was examined as a predictor of engine-derived BPT as shown in the linear regression analysis in TABLE 18 and plotted in Fig. 15. The correlation coefficient (Rsquared) of 0.48 revealed no strong relationship between pour point and the BPT in the 6V-53T engine.



8.500 L L L

Figure 14. Regression of DDC6V BPT on MRV BPT

The used oil kinematic viscosity at 100° C was determined for the 15W-40 oils after one 6V-53T pumpability test to determine shear degradation of the oils (TABLE 19). The observed viscosity loss ranged from 0.23 to 1.74 centistokes, which was very similar to the loss observed in the LDT-465-1C and GM 6.2L engines. Overall, the 6V-53T engine was less severe with respect to low-temperature oil pumpability than either the LDT-465-1C or GM 6.2L engines.

TABLE 17. BPT Regression Analysis—DDC 6V-53T Engine

Regression Analysis - Linear model: Y = a+bX Dependent variable: DD6VBPT

111141

Independent variable: BPT

Parameter	Estimate	:	Standard	T Value	Prob.
Intercept Slope	-9.56656 0.544196	-	2.39082 0.130281	-4.00136 4.17709	2.08133E-3 1.54412E-3
		Analys	is of Variance		
	Sum of	-	Mean		Prob.
Source	Squares	Df	Square	F-Ratio	Level
Model	213.91087		213.91087	17.44808	0.00154
Error	134.85836	11	12.25985		
Total (Corr.)	348.76923	12			
Correlation Co Std. Error of Es	efficient = 0.78 st. = 3.50141	3154	R-squared =	0.61	

 TABLE 18. Engine BPT Regression Analysis on Pour Point

Regression Analysis - Linear model: Y = a+bX Dependent variable: DD6VBPT

Independent variable: POURPT

Parameter Intercept Slope	Estimate -9.65686 0.587304		Standard Error 3.07507 0.185876	T Value -3.14037 3.15965	Prob. Level 9.40248E-3 9.08487E-3
		Analys	is of Variance		
	Sum of		Mean		Prob.
Source	Squares	Df	Square	F-Ratio	Level
Model	165.93600	1	165.93600	9.98339	0.00908
Error	182.83323	11	16.62120		
Total (Corr.)	348.76923	12			
Correlation Co Std. Error of Es	efficient = 0.689) st. = 4.07691	765	R-squared = (0.48	



187-238-284-245

Table 19. Used Oil Viscosity of 15W-40 Oils AfterOne Pump Test--DDC 6V-53T Engine

		K. Vis, 100°C, cSt		
Oil No.	Description	New	Used	Loss
1	OCP	13.66	12.67	0.99
2	OCP	13.31	12.68	0.63
3	OCP-L	14.90	13.16	1.74
4	OCP-H	14.65	13.17	1.48
6	SI-L	14.51	14.26	0.25
5	SI-H	13.97	13.80	0.17
7	PMA-L	15.02	13.76	1.26
8	РМА-Н	14.58	13.70	0.88
10	Comm, SI	14.34	14.11	0.23
9	Comm. PMA	14.20	13.49	0.71

D. Cummins VTA-903T Engine

The final engine to be investigated for low-temperature oil pumpability was the Cummins VTA-903T engine used to power U.S. Army M2 and M3 combat vehicles. All tests were run following the slow cooling procedure (84CP) with the pistons installed. TABLE 20 contains a description of the VTA-903T engine, while Fig. 16 is a block diagram of the engine lubrication system.(38) Gallery oil pressure was measured at the right rear of the engine block while turbocharger oil pressure was measured at the

TABLE 20. Engine Specifications for the Cummins VTA-903T Engine

Model:	VTA-903T
Engine Type:	Four-Cycle, Compression Ignition, Direct Injection
Cylinders:	8, V-Configuration
Displacement:	14.8 L (903 cubic inches)
Bore:	14.0 cm (5.5 inches)
Stroke:	12.1 cm (4.75 inches)
Compression Ratio:	15.5:1
Fuel Injection:	Cummins PT
Rated Power:	373 kW (500 BHP) at 2600 rpm
Rated Torque:	1369 NM (1010 lb-ft) at 2400 rpm
Idle Speed:	800 rpm (motoring for pumpability tests)





oil delivery line leading to the turbocharger. Rocker-arm oil pressure was measured at left front of the engine (cylinder No. 5).

Borderline oil-pumping conditions for the VTA-903T engine at 800-rpm idle were defined as a minimum turbocharger oil pressure of 10 psi at 1.0 minute and thereafter.(<u>38</u>) As observed in other engines, the turbocharger oil-pressure trace was nearly a straight vertical line from initial pressure development to 30 psi; thus, the BPT determined at 1.0 minute would be nearly the same for any pressure limit between 1 and 30 psi. A typical oil pressure trace for this engine at borderline pumping conditions is shown in Fig. 17. The VTA-903T engine had the following general oil pumpability characteristics:



at a given temperature, oil pressure developed at the turbocharger after gallery pressure; at BPT gallery, oil pressure was immediate and turbocharger oil pressure showed indications of air binding. In fact, gallery oil pressure developed immediately for all test conditions examined. For example, using SAE 10W grade oil at -38°F (-39°C) resulted in immediate gallery oil pressure, while turbocharger oil pressure took in excess of 15 minutes to develop. At BPT, it generally took 3.5 to 4.5 minutes to develop 1.0 psi rocker-arm oil pressure. The BPTs determined in the VTA-903T engine are presented in TABLE 21. Appendix F contains plots of test temperature versus time to minimum required idle oil pressure. Special 15W-40 blend OCP-H (Oil No. 4) was the most severe 15W-40 oil with a BPT of -6°F (-21°C). As observed in the other engines, the 15W-40 oils formulated with PMA-VII had the lowest BPTs. Oil No. 11 (75 VI SAE 30-grade) had the highest BPT at +7°F (-14°C). BPT of the SAE 10W grade was -21°F (-29°C), while the synthetic 5W-40 product had a BPT of -35°F (-37°C). At BPT conditions, rocker-arm oiling times were between 3.5 and 4.5 minutes. Fig. 18 shows a plot of the linear regression of engine-derived BPT on BPT from the MRV (ASTM D 3829). The correlation coefficient (R-squared) for this regression was 0.76 as shown in TABLE 22. Overall, the VTA-903T engine was similar in low-temperature oil pumpability severity to the LDT-465-1C engine. These two engines were the most severe (highest BPTs) of the four engines investigated.

Oil <u>No.</u>	Oil Description	врт, °f(°с)	MRV BPT, 	Rocker-Arm Oiling Time, minutes
	15W-40 Oils			
1	MIL-L-2104D (OCP)	-7(-22)	-13(-25)	4.0
2	MIL-L-2104D (OCP)	-9(-23)	-16(-27)	ND
3	OCP-L	-10(-23)	-18(-28)	4.5
4	OCP-H	-6(-21)	-16(-27)	3.5
5	SI-H	-9(-23)	-15(-26)	3.8
6	SI-L	NT	-18(-28)	NT
7	PMA-L	-18(-28)	-22(-30)	4.3
8	РМА-Н	-13(-25)	-19(-28)	4.4
9	Commercial PMA	-14(-26)	-20(-29)	3.8
10	Commercial SI	NT _	-17(-27)	NT
	30 Grade Oils			
11	MIL-L-2104D (75 VI)	+7(-14)	+1(-17)	3.6
12	MIL-L-2104D	-4(-20)	-8(-22)	4.3
	Others			
13	10 W , MIL-L-2104D	-21(-29)	-29(-34)	4.2
14	10 W -30, OCP-L	-18(-28)	-19(-28)	4.1
15	5W-30, Synthetic	-38(-39)	-26(-32)	3.1
16	5 W-30 , Synthetic	-38(-39)	< -40(-40)	4.0
17	5W-40, Synthetic	-35(-37)	< -40(-40)	3.7

TABLE 21. Oil Borderline Pumpability Temperature (BPT) In Cummins VTA-903 Engine

NT = Not tested. OCP = Olefin copolymer VII. SI = Styrene-Isoprene VII. PMA = Polymethacrylate VII. ND = Not determined.



TABLE 22. BPT Regression Analysis--VTA-903T Engine

Regression Analysis - Linear model: Y = a+bX Dependent variable: C903BPT

Independent variable: BPTF

Parameter Intercept Slope	Estimate 8.1315 1.20777	S 3 0	tandard <u>Error</u> .81331 .206853	T Value 2.1324 5.8388	Prob. Level 0.0563444 1.12715E-4
		Analysi	s of Variance		
	Sum of	,	Mean		Prob.
Source	Squares	Df	Square	F-Ratio	Level
Model	1013.6912		1013.6912	34.0916	0.00011
Error	327.07804	11	29.73437		
Total (Corr.)	1340.7692	12			
Correlation Co Std. Error of E	oefficient = 0.869 Est. = 5.45292	9512	R-squared =	0.76	

Borderline oil-pumpability temperatures (BPTs) were determined by engine cranking experiments conducted in a cold box. The variables investigated included: four different engine types; four different oil viscosity grades; and three different viscosity index improver chemistries. Fig. 19 shows the limiting BPTs for each engine grouped by oil viscosity class. In general, for a given oil, the decreasing order of engine severity (i.e., highest BPT) was: the LDT-465-1C and the VTA-903T were the most severe and were approximately equivalent. The GM 6.2L engine was the next least severe, and the DDC 6V-53T engine was the overall least severe. Note that the 6V-53T engine tended to



Figure 19. BPT ranges for viscosity classes by engine type

group all the 15W-40 and 30-grade oils between -13° (-25°) and $-16^{\circ}F$ (-27°C) due to its very strong oil pump.

TABLE 23 contains the engine-derived BPTs for the special blend 15W-40 oils that were formulated to the upper and lower 15W specification limits. The different VII chemistries of the special blend test oils included: olefin copolymer (OCP), styreneisoprene polymer (SI), and polymethacrylate (PMA). The PMA-containing 15W-40 oils had superior low-temperature oil pumpability performance in each engine in which they were evaluated. Oils formulated with SI VII had similar to slightly better lowtemperature pumpability performance than the OCP-containing oils. TABLE 24 contains a summary of the limiting engine-derived BPTs for the engine/oil matrix. The limiting BPT for each oil type is boxed in TABLE 24. For 15W-40 grade oils, the most severe condition was an oil formulated with OCP VII operated in the LDT-465-1C engine. For the SAE 30 grade oils, the 75 VI product was limiting in the VTA-903T engine. This same engine was limiting for the single SAE 10W grade oil investigated.

0.1			ВРТ	, ^o F(^o C)	
<u>No.</u>	Description	VTA-903T	DDC6V-53T	GM 6.2L	LDT-465-1C
3	OCP-L	-10(-23)	-16(-27)	-16(-27)	-10(-23)
6	SI-L	NT	-19(-28)	-15(-26)	NT
7	PMA-L	-18(-28)	-24(-31)	NT	-20(-29)
4	оср-н	-6(-21)	-13(-25)	-11(-24)	-4(-22)
5	SI-H	-9(-23)	-21(-29)	-9(-23)	NT
8	РМА-Н	-13(-25)	-21(-29)	NT	-17(-27)

TABLE 23. BPTs of Special Blend 15W-40s

The BPT range (R) for a given VII type and engine is defined as the engine-derived BPT for the oil blended to the upper limits of the viscosity grade (BPT_{UL}) less the engine-derived BPT of the oil blended to the lower limit of the grade (BPT_{LL}). The equation is: R = BPT_{UL} - BPT_{LL}.

		Temperature	oF(OC)	
	LDT-465-1-C	GM 6.2 L	DDC 6V-53T	VTA-903T
1 5₩- 40				
OCP	- 4(-20)	-11(-24)	-11(-24)	- 6(-21)
PMA	-17(-27)	NT	-21(-29)	-13(-25)
SI	- 8(-22)	-11(-24)	-19(-28)	- 9(-23)
30				
95 VI	- 4(-20)	- 5(-21)	-15(-26)	- 4(-20)
75 VI	+ 6(-14)	+ 2(-17)	-13(-25)	+ 7(-14)
10 W	-22(-30)	-28(-33)	-30(-34)	-21(-29)
5 W-3 0	-33(-36)	<-22(-30)	< -30(-34)	-38(-39)
5 ₩- 40	NT	NT	NT	-35(-37)

TABLE 25 shows the range of engine-derived BPTs for 15W-40 oils grouped by engine type and VII chemistry. For oils blended with OCP VII to the lower and upper 15W-40 viscosity limits, the BPTs in the LDT-465-1C engine increased by 6° F over the 15W-40 viscosity grade. The 15W-40 BPT ranges varied from 2° to 6° F, with no consistent trends with respect to VII chemical type or engine type.

TABLE 25. Range of BPTs Within 15W-40 Oil Class						
	Temperature Range, ^o F					
Engine Type VII Chemistry	LDT-465-1C	<u>GM 6.2L</u>	DDC 6V-53T	VTA-903T		
OCP	6	6	5	4		
РМА	3	ND*	3	5		
SI	ND	6	2	ND		

*ND = Not Determined

The BPTs determined by ASTM D 3829 did not completely predict engine-derived BPTs. The linear regression correlation coefficients (R-squared) resulting from the two different BPT values ranged from 0.61 to 0.88.

verences surrive appoint thesester workers p

The shear effects of a single pumpability test for three engine types are summarized in TABLE 26 for 15W-40 oils. Each engine produced approximately the same viscosity shear loss. Of the particular VII additives represented, the SI material experienced the least viscosity shear loss. The shear data apply to these particular oils only, and should not be extrapolated or generalized to other oils of the same VII chemistry.

		K. Vis Loss at 100°C, cSt (15W-40 Oils)			
No.	Description	LDT-465-1C	<u>GM 6.2L</u>	DDC 6V-53T	
1	MIL-L-2104D (OCP)	0.85	0.91	0.99	
3	OCP-L	2.18	1.52	1.74	
4	OCP-H	1.28	1.53	1.48	
7	PMA-L	1.06	1.26	ND*	
8	РМА-Н	0.60	0.88	ND	
6	SI-L	ND	0.88	0.25	
5	SI-H	ND	0.35	0.17	
*ND =	Not Determined				

TABLE 26. Shear Effects for One Pumpability Test

V. CONCLUSIONS

The following conclusions are made based on the results of the low-temperature oil pumpability tests:

• Each engine had a unique set of low-temperature oil pumpability characteristics. The LDT-465-1C and the VTA-903T engines were the most severe in terms of low-temperature oil pumpability performance, i.e., they required a higher temperature for a given oil to pump adequately. The GM 6.2L engine was the next least severe, while the DDC 6V-53T engine was the overall least severe. The 6V-53T engine was able to pump oils at temperatures below their pour point.

• The limiting engine-derived BPTs for various viscosity grades were as follows:

for 15W-40s, the limiting BPT was -4°F (-20°C), for SAE 30 grade, the limiting BPT was +7°F (-14°C), and for SAE 10W grade, the limiting BPT was -21°F (-29°C)

- The PMA-containing 15W-40 oils had superior low-temperature oil pumpability performance in each engine in which they were evaluated.
- The 15W-40 oils formulated with SI VII had similar to slightly better lowtemperature pumpability performance than the OCP-containing oils.
- The BPTs determined by ASTM D 3829 (MRV) did not adequately predict engine-derived BPTs. The linear regression correlation coefficients (Rsquared) resulting from the two different BPT values ranged from 0.61 to 0.88, and the data had rather large confidence bands.
- Each engine produced approximately the same viscosity shear loss during a single pumpability test. Of the particular VII additives represented, the SI material experienced the least viscosity shear loss. The shear data apply to these particular oils only, and should not be extrapolated or generalized to other oils of the same VII chemistry.

VI. RECOMMENDATIONS

The following recommendations for low-temperature use limits for U.S. Army dieselpowered ground vehicles are offered based on the BPTs developed during this program. Low-temperature use limits were defined as +5°F warmer than the highest enginederived BPT. The 5°F was added to the BPT to provide a margin of safety. It is recommended that the low-temperature use limit for MIL-L-2104D grade 15W-40 can be safely lowered to $0^{\circ}F$ (-18°C), and the use limit for SAE grade 30 can be safely lowered to +10°F (-12°C). It is recommended that the grade 10W low-temperature use limit of -15°F (-26°C) be retained.

Additional research is recommended since BPTs from ASTM D 3829 do not adequately predict BPTs from heavy-duty diesel engines. A mathematical model needs to be developed that could be used to predict the expected BPT of any diesel engine/lubricant combination that the Army might encounter. Variables such as engine geometry (oil pickup tube length and diameter, main oil gallery dimensions etc), engine hardware characteristics such as oil pump flow rate and engine oil properties would form the basis for this predictive model. Once the preliminary model is formed based on the currently available engine-derived BPTs, the critical engine geometries and characteristics of other available diesel engines should be considered. If any engines are identified that have geometric or flow properties that fall outside the range of the engines used in the current program, additional low-temperature engine pumpability determinations would be recommended.

Finally, low-temperature oil pumpability requirements should be determined for other vehicle components such as powershift transmissions and power steering units. The effects of operation at low-temperature, high-viscosity conditions should be determined for gearboxes, transmissions, and other vehicle components that do not pump their lubricant.

VII. LIST OF REFERENCES

- 1. Military Specification MIL-L-2104D, Lubricating Oil, Internal Combustion Engine, Tactical Service, dated 1 April 1983.
- 2. Appledoorn, J.K., "Motor Oil Viscosity Pumpability of Oil," Chicago, IL, API Meeting, Nov 1948.
- 3. Meyer, W.E., De Carolis, J.J. and Stanley, R.L., "Engine Cranking at Arctic Temperatures," SAE Meeting, Cleveland, OH, Oct 1954.
- 4. Moyer, R.G., "Low Temperature Pumpability of Oil," <u>Journal of ASLE</u>, pp. 165-168, Apr 1962.

- 5. Selby, T.W., "Viscosity and the Cranking Resistance of Engines at Low Temperatures," Sixth World Petroleum Congress Proceedings, Section VI, Frankfurt, Germany, pp. 241-258, June 1963.
- 6. "Evaluation of Laboratory Viscometers for Predicting Cranking Characteristics of Engine Oils at 9°F and -20°F," CRC Report No. 409, Apr 1968.
- 7. McMillan, M.L., "Engine Oil Viscosity Classifications Past, Present, and Future," SAE Transactions, Vol. 86, Paper No. 770373, 1977.
- 8. Stewart, R.M. and Seil: T.W., "The Relationship Between Oil Viscosity and Engine Performance A Literature Search," SAE Paper No. 770372.
- 9. Smith, Jr., M.F. and Graham, J.P., "Pumpability of Multigrade Oils at Low Temperatures," SAE Transactions, Vol. 80, SAE Paper No. 710139, 1971.
- 10. Boone, E.F., Crouse, W.W. and McLaughlin, J.H., "Low Temperature Fluidity of Multigrade Motor Oils," SAE Paper No. 710140, 1971.
- 11. Stewart, R.M. and Spohn, C.R., "Some Factors Affecting the Cold Pumpability of Crankcase Oils," SAE Transactions, Vol. 81, SAE Paper No. 720150, 1972.
- 12. McMillan, M.L. and Murphy, C.K., "The Relationship of Low-Temperature Rheology to Engine Oil Pumpability," SAE Paper No. 730478, 1973.
- Stewart, R.M. and Smith, Jr., M.F., "Proposed Laboratory Methods for Predicting the Low-Temperature Pumpability Properties of Crankcase Oils," SAE Paper No. 730479, 1973.
- 14. Nolf, A.R., "Engine Oil Pumpability and Related Properties," SAE Paper No. 730480, 1973.
- 15. Tao, F.F. and Waddey, W.E., "Low-Shear Viscosity and Cold Flow Mechanism-Engine Oils," SAE Paper No. 730481, 1973.
- 16. Spohn, C.R. and Stewart, R.M., "Cold Pumpability Characteristics of Engine C'Is Predicted by a Bench Test," SAE Paper No. 740541, 1974.

- 17. Alexander, D.L. and Rein, S.W., "Viscometer for Predicting Low-Temperature Pumpability of Engine Oils," SAE Paper No. 770632, 1977.
- 18. Stewart, R.M., "Engine Pumpability and Crankability Tests on Commercial 'W' Graded Engine Oils Compared to Bench Test Results," SAE Paper No. 780369, 1978.
- 19. "Low-Temperature Pumpability Characteristics of Engine Oils in Full-Scale Engines," ASTM Data Series Publication 57, 1975.
- 20. McMillan, M.L., Stewart, R.M., Smith, Jr., M.F. and Rein, S.W., "Low-Temperature Engine Oil Pumpability in Full-Scale Engines," SAE Paper No. 750691, 1975.

- 21. Shaub, H., Smith, Jr., M.F. and Murphy, C.K., "Predicting Low Temperature Engine Oil Pumpability With the Mini-Rotary Viscometer," SAE Paper No. 790732, published in SAE SP-460 and ASTM STP-621-S4, 1979.
- 22. ASTM D 3829, "Standard Method for Predicting the Pumpability of Engine Oils," approved for publication on August 31, 1979, published in ASTM Handbook in October 1979.
- 23. McMillan, M.L. and Stambaugh, R.L., "The Development of a Viscosity Classification System Based on Engine Performance - A Review of SAE and Related ASTM Activities," Paper EL/4/3, Presented at CED International Symposium, June 1981.
- 24. Stewart, R.M., Smith, Jr., M.F., Shaub, H. and Selby, T.W., "Summary of ASTM Activities on Low Temperature Engine Oil Pumpability," SAE Paper No. 821206, 1982.
- 25. Stambaugh, R.L. and O'Mara, J.H., "Low Temperature Flow Properties of Engine Oils," SAE Transactions, Vol. 91, Paper 821247, 1982.
- 26. Smith, Jr., M.F., "Better Prediction of Engine Oil Pumpability Through a More Effective MRV Cooling Cycle," SAE Paper No. 831714, 1983.
- 27. Clevenger, J.E. and Richards, H.F., "Low-Temperature Rheology of Multigrade Engine Oils - Formulary Effects," SAE Paper No. 831716, 1983.
- 28. Schmidt, G.M., Olsen, M.T. and Michael, M.I., "Low Temperature Fluidity of Lubricating Oils Under Slow Cool Conditions," SAE Paper No. 831718, 1983.
- 29. Johnson, R.S., "A Laboratory Engine Test Study of Motor Oil Flow Properties in Winter Service," SAE Paper No. 841387, 1984.
- 30. Stambaugh, R.L., "Low-Temperature Pumpability of Engine Oils," SAE Paper No. 841388, 1984.
- 31. Henderson, K.O., Manning, R.E., May, C.J. and Rhodes, R.B., "New Mini-Rotary Viscometer Temperature Profiles That Predict Engine Oil Pumpability," SAE Paper No. 850443, 1985.
- 32. MacAlpine, G.A. and May, C.J., "Compositional Effects on the Low-Temperature Pumpability of Engine Oils," SAE Paper No. 870404, 1987.
- 33. Butler, W.E., Alvarez, R.A., Frame, E.A., Owens, E.C. and Bowen, T.C., "Field Evaluation of All-Season Tactical Engine Oil OD/HDO 15W-40 at Ft. Knox, KY and Ft. Bliss, TX," Interim Report BFLRF No. 217, conducted under Contract No. DAAK70-85-C-0007, Belvoir Fuels and Lubricants Research Facility (SwRI), San Antonio, TX, July 1986.
- 34. U.S. Army Publication TM.9-2815-210-35.

35. Reilly, D.J., "The New GM 6.2L V8 Diesel Engine - Designed by Chevrolet," SAE Paper No. 820115, 1982.

36. U.S. Army Publication TM.9-2815-212-35.

- 37. Federal Test Method Standard No. 791-C, Method No. 355.
- 38. Cummins Diesel V/VT-903 and VTA-903 C.I.D. Engine Shop Manual, 1980.



<u></u>

C

Test Cell Configuration



A refrigerated box was used to cool the test engines to the desired test temperatures. The cold box initially used in the program employed a 3-horsepower electrically powered single-stage compressor and was capable of attaining temperatures as low as -35° F (-37°C). The test engine was bolted to a bedplate and the cold box assembled around it. A sheet of polyethylene film was then cut and taped to the bedplate to act as a vapor barrier. Next, a 2-inch (5-cm) layer of polystyrene foam was cut and placed on the floor to serve as an insulator. Lastly, another layer of polyethylene film was taped down to act as a spill retainer and additional vapor barrier. The refrigeration equipment was controlled in a on-off mode using a Honeywell UDC-500 controller and a Honeywell DPC-7700 set point programmer. The box, which was equipped with a 4-foot wide access door, was able to attain test temperatures as low as -35° F (-37°C) and maintain them $\pm 2^{\circ}$ F.

A second refrigerated box was used later in the program. This box had a 5-horsepower dual-stage compressor and was capable of attaining test temperatures as low as -40° F (-40°C). This box had one completely removable wall that facilitated the changeout of engines without disassembly of the entire box. The floor of this box was insulated in the same manner as the other. Changeout of the box revealed that moisture had migrated through the vapor barrier and into the bedplate foundation. This moisture caused extensive rusting of the bedplate and deterioration of the foundation due to freeze-thaw effects. When the second box was installed, great care was taken to seal the vapor barriers better and fit the insulation to the bedplate. In addition, insulation was placed on the support legs of the test engine to minimize heat infiltration into the cold box and minimize sweating of the baseplate.

B. Engine Cranking System

Initially a 50-horsepower motoring dynamometer was used to motor the test engines at the desired speeds. This system proved to be difficult to use since the torque available at low speeds (800 to 1000 rpm) was very limited. The dynamometer control system tended to blow fuses at these low cranking speeds. As a result of this problem, and a fuel-dribble problem, discussed later, the pistons and connecting rods were removed from the first test engine (the Continental LDT-465-1C). After this initial attempt, a special

cranking system was designed to provide reliable and repeatable motoring of the test This design consisted of a driving engine, a clutch, a 12-speed truck engine. transmission, and a driveshaft connecting the transmission to the test engine. The driving engine was initially a Cummins NTC-350 diesel engine. The clutch on the transmission was actuated with an air cylinder such that air pressure was required to disengage the clutch. A needle valve was used to control the air bleed from the cylinder and thus control the engagement of the clutch. The driving and driven engines were placed back-to-back and the transmission operated in high-range reverse. The speed of the driven engine was controlled by an air cylinder on its rack. The driveshaft between the transmission and the test engine passed through a hole in the side of the cold box. Although the passthrough was insulated with rubber curtains on the inside and outside surfaces of the cold box, the passthrough was an unavoidable source of moisture and heat intrusion into the cold box. During the test program, it became necessary to change the driving engine to a Detroit Diesel 6V-53T engine because the Cummins NTC-350 engine was needed for another test program. The change had little or no impact on the test since both engines were capable of providing the same range of test speeds. Later in the program, the Cummins NTC-350 engine was reinstalled as the driving engine. Test speeds of 175 to 1000 rpm were possible using this cranking apparatus. Speeds lower than 150 rpm caused excessive torsional vibrations in the driveshaft and were avoided by running the driving engine higher than these rpm's before engaging the clutch. The driving engines were run at very modest power levels in relation to their maximum powers. Fuel for the driving engine was provided from a 55-gallon drum in the test cell. Driving engines were provided with a water-out thermocouple to indicate when the engine was warmed up and ready for use.

C. Instrumentation

Contraction of the second

South the trace of the second

A Honeywell UDC-500 controller was used to control the temperature in the cold box. The controller received its set point from a Honeywell DCP-7700 set point programmer, which allowed controlled cool-down curves with respect to time. Initial tests with the cold box revealed a tendency to freeze the evaporator coils on humid days. A defrost cycle was added to eliminate the icing. The defrost was set to initiate at midnight and last for 30 minutes. This defrost cycle effectively eliminated the icing problem but introduced a slight perturbation into the cool-down cycle. Since the oil sump has

significant thermal mass, the perturbation in the cool-down cycle had minimal impact on the bulk oil temperature.

Each engine was instrumented for oil-sump temperature, oil-suction pressure (in the oil pickup tube), oil-gallery pressure, turbocharger oil pressure (where applicable), engine speed, and in some cases, rocker-arm oiling indication/pressure. The air temperature in Temperatures were measured using type J the cold box was also measured. thermocouples. The oil sump and air temperatures were indicated using a digital readout and recorded during the cool-down period using an ice-point reference and millivolt recorder. The recording of the air and oil temperatures proved to be important since it indicated if any interruptions in the cool-down cycle had occurred. Thus, any runs that were suspect because of evaporator icing, power failure, a door left ajar, etc., were eliminated. Oil pressures were measured using Sensotec amplified pressure transducers placed as close to the measured fluid as possible. In the case of gallery and turbo pressures, the transducers were screwed directly to the block or supply hose. In the case of the oil suction pressure, a 0.25-inch copper line was brazed to the pickup tube and run to the exterior of the engine in order to attach-the pressure transducer. Each of the pressure transducers was recorded on a stripchart recorder during the pumping part of the experiment.

Engine speed was measured using a 60-tooth gear and a magnetic pickup. The output of the magnetic pickup was routed to a digital frequency meter in order to monitor engine speed. The frequency was also routed to a frequency-to-voltage converter and thence to the chart recorder. This pathway provided immediate feedback to the operator controlling motoring speed and a record of speed.

Rocker arm oiling was measured in one of two ways. In the case of the Cummins VTA-903T and DDC 6V-53T engines, a 15-psig pressure transducer was plumbed directly to the rocker shaft. This was possible since both engines use a pressurized rocker shaft. In the case of the GM 6.2L engine, however, a pressurized push rod lubricates the rocker arm by drip feed. In order to obtain an indication of rocker arm oiling, a vacuum system was used to indicate the presence of oil in the rocker arm. A small electrically powered vacuum pump was used to provide vacuum to the system. The vacuum was piped to a Tconnection with needle valves on both arms. One needle valve opened to atmosphere and the other opened to another T-connection. This T-connection had a vacuum gauge (0 to 15 inches of water) on one leg and a tube to the engine on the other. The tube to the engine was large (0.25 inch) until just before the rocker arm. At the rocker arm, a 1/16-inch stainless steel tube was connected and immersed in the pool of oil in the rocker arm. In practice, the rocker arm was drained of oil and washed with solvent before the test. The vacuum pump was turned on and the valves adjusted to provide a mid-scale reading on the vacuum gauge. With the rocker arm drained and clean, only air was sucked through the 1/16-in tube. When rocker-arm oiling occurred, oil was sucked into the small tube and the indicated vacuum increased. This method proved to be very dependable in indicating rocker-arm oiling. A visual method was used to confirm the rocker-arm oiling apparatus. A change in capacitance method was also tried, but the dielectric difference between oil and air was insufficient to provide reliable indications of rocker-arm oiling.

E. <u>Other Details</u>

The normal engine-mounted water pump was used to circulate a 50/50 volumetric blend of commercial antifreeze and water in the cooling passages of the engine. A 1000-watt immersion heater was plumbed in the cooling line to facilitate warmup of the engine for purposes of oil flush. Circulation ran from the engine to the water pump to the heater and back to the engine.

The fuel system of the first engine tested (the Continental LDT-465-1C) was plumbed to circulate fuel from a small container to the injector pump with return fuel being routed back to the container. This cycle caused problems in that dribble from the injectors (even in the no-rack position) caused exhaust fumes to fill the refrigerated box. This was initially cured by removing the pistons, connecting rods, and fuel injectors and routing fuel only to the injector pump (for lubrication). This approach was desirable since a motoring dynamometer was used for a short time to motor the engine. The removal of the pistons and connecting rods lowered the motoring friction and made the use of the motoring dynamometer possible. Later in the program, this approach was deemed unrealistic since the connecting-rod lubrication system was eliminated with this approach. The alternate approach was to reinstall the pistons and connecting rods, let the fuel lines to the injectors drain into the fuel supply can, and switch to the engine-powered motoring system already described. Each of the fuel systems in the test engines was disabled to prevent exhaust fumes from being present in the box. The Cummins

903T fuel system was disabled by removing the fuel injector pushrod and removing the fuel injection pump. The GM 6.2L fuel system was disabled by utilizing the built-in fuel shutoff solenoid. The DDC 6V-53T fuel system was disabled by wiring the rack control in the no-fuel position.

Four 250-watt infrared heating lamps were placed under the oil sumps of the engines. These lamps provided rapid heatup of the oil sump without disturbing the internal oil-pan geometry with heating coils. A 1000-watt heating element was placed in the cooling water circulation path to facilitate engine warm-up.

Each test lubricant was stored in an electrically heated drum for at least 24 hours prior to testing and for the duration of testing. The temperature of the lubricant was maintained at 180°F (82°C) in order to provide all test lubricants with uniform temperature histories and destroy any previous temperature history.

APPENDIX B

Test Procedure

The following test procedure was used for the lubricant pumpability determinations:

After a pumping attempt,

- Raise oil temperature to 110°F (43°C) by turning on heating lights, turning on water heater (meters should read 1000 watts), and motoring at 800 rpm. This was done in order to facilitate drainage.
- 2. Turn off lights and heater.
- 3. Drain oil and save in used oil drum.
- 4. Remove filters and reinstall housings. This was done to minimize used oil hangup in the engine.
- 5. Fill with hot test oil (180°F). This is a flush using the next test lubricant.
- 6. Motor at 800 rpm for 10 minutes. This is a flush run.
- 7. Drain oil and dispose. This lubricant is a mix of old and new lubricant and is therefore disposed.
- 8. Fill with hot test oil (180°F). This is new test lubricant.
- 9. Motor at 800 rpm for 10 minutes. This is another flush run.
- 10 Drain oil and save in used oil drum.
- 11. Install filters. This is in preparation for the test run.

10:30 am

- 12. Fill with measured amount of hot test oil (180°F).
- 13. Motor at 800 rpm for 1 minute.
- 14. Program set point programmer for desired cooling curve.

15. Start cooling, recording temperatures at a chart speed of 2 cm/hr. Check to make sure air and oil-sump temperatures are recording properly.

8:00 am (next day)

- 16. Install all pens in chart recorder. Turn on speed recorder. Shift transmission into neutral and warm cranking engine to 170°F (77°C) water-out temperature. Disengage clutch and shift into reverse. Remove box and sump indicating pens to avoid interference w/others. Turn on remaining pens on recorder and set speed to 2 cm/min. Check to make sure all pens are functioning correctly. Engage clutch and blip oil gallery pen simultaneously.
- 17. Motor engine at test speed for 15 minutes.
- 18. Turn off chart recorder and cap all pens.
- 19. Turn off cooling.
- 20. Turn on heating lights.
- Turn on water heater and motor at 800 rpm until oil temperature reaches 110°F (43°C). Oil temperature will rise approximately 2°F (-17°C) per minute. Check speed occasionally and maintain 800 rpm.
- 22. Stop engine, turn off lights and heaters, open box.
- 23. Drain oil and oil filters. Four-ounce sample of used oil to chemical laboratory. Label sample with AL No., cranking temperature, and date. Save drained oil in used oil drum.
- 24. Sponge up any fluid that has condensed or spilled on floor.
- 25. If the next lubricant is the same as the last lubricant, go to step 12. If the next lubricant is a different lubricant, go to step 4.

Quantities of lubricant used in each engine were 38.2 lb (17.3 kg) for the LDT-465-1C engine, 38.2 lb (17.3 kg) for the Cummins VTA-903T, 11.6 lb (5.3 kg) for the GM 6.2L engine, and 43.0 lb (19.5 kg) for the DDC 6V-53T engine. The time table shown in the procedure was intended to provide each run with the same amount of cold-soak time, while still allowing adequate time to change lubricant and prepare for the next day's run. In some instances, the cold soak was extended over a weekend to investigate the effect of longer cold-soak periods. Normal cold-soak time was 20 hours total, or 68 hours over the weekend.

APPENDIX C

fat defails take alle all

1.1.1

Low-Temperature Oil Pumpability in the LDT-465-1C Engine
















APPENDIX D

Low-Temperature Oil Pumpability in the GM 6.2L Engine











APPENDIX E

Low-Temperature Oil Pumpahility in the DDC 6V-53T Engine













APPENDIX F

ŧ⋰ⅎ₽ℴℽⅎ₽⅀₩₽₽ℴ^ℴ₽₩₽₽ġ₽ℴ₩₽₽₽₩₽₽ĸ₩₽₽ĸĔ₽₽ĸĔ₽₽ĸĔ₽₽ĸĔ₽₽ĸĔ₽₽ċĔ₽₽ĊĔ₽

Low-Temperature Oil Pumpability in the Cummins VTA-903-T Engine









7.4

. . . .







DISTRIBUTION LIST			
DEPARTMENT OF DEFENSE DEFENSE TECHNICAL INFORMATION CTR CAMERON STATION 12 ALEXANDRIA VA 22314 DEFENSE ADVANCED RES PROJ AGENCY	DIRECTOR US ARMY MATERIEL SYSTEMS ANALYSIS ACTIVITY ATTN: AMXSY-CM (MR NIEMEYER) 1 ABERDEEN PROVING GROUND MD 21005-5006 DIRECTOR APPLIED TECHNOLOGY DIRECTORATE		
DEFENSE SCIENCES OFC I 1400 WILSON BLVD ARLINGTON VA 22209 DEPARTMENT OF THE ARMY	U.S. ARMY R&T ACTIVITIES (AVSCOM) ATTN: SAVDL-ATL-ATP (MR MORROW) 1 FORT EUSTIS VA 23604-5577 HQ, 172D INFANTRY BRIGADE (ALASKA) ATTN: AFZT-DI-L 1		
CDR U.S. ARMY BELVOIR RESEARCH, DEVELOPMENT & ENGINEERING CTR ATTN: STRBE-VF 10 STRBE-BT 2 FORT BELVOIR VA 22060-5606 HQ, DEPT OF ARMY ATTN: DALO-TSE (COL BLISS) 1 DALO-TSZ-B (MR KOWALCZYK) 1 SARD-TN (DR CHURCH) 1 SARD-TR (MR APPEL) 1 WASHINGTON DC 20310-0005 CDR US ARMY MATERIEL COMMAND ATTN: AMCDE-SS 1 AMCSM-WST 1 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001	DIRECTORATE OF INDUSTRIAL OPERATIONS FORT RICHARDSON AK 99505 CDR THEATER ARMY MATERIAL MGMT CENTER (200TH)-DPGM DIRECTORATE FOR PETROL MGMT ATTN: AEAGD-MMC-PT-Q (MR CARLONE) 1 APO_NY 09052 CDR US ARMY GENERAL MATERIAL & PETROLEUM ACTIVITY ATTN: STRGP-F (MR ASHBROOK) 1 STRGP-FE, BLDG 85-3 (MR GARY SMITH) 1 STRGP-FT 1 NEW CUMBERLAND PA 17070-5008		
CDR US ARMY TANK-AUTOMOTIVE CMD ATTN: AMSTA-RG 1 AMSTA-TSL (MR BURG) 1 AMSTA-MTC (MR GAGLIO), AMSTA-MC, AMSTA-MV 1	CDR US ARMY COLD REGION TEST CENTER ATTN: STECR-TA 1 APO SEATTLE 98733 HQ, DEPT OF ARMY ATTN: DAEN-DRM 1		
AMSTA-RGP (MR RAGGIO) 1 AMSTA-MLF (MR KELLER) 1 WARREN MI 48397-5000 DIRECTOR US ARMY AVIATION RESEARCH & TECHNOLOGY ACTIVITIES (AVSCOM) ATTN: SAVRT-R (MR ANDRE) 1 AMES RESEARCH CENTER (MAIL STOP 207-5) MOFFETT FIELD CA 94035-1099	WASHINGTON DC 20310 CDR US ARMY TANK-AUTOMOTIVE CMD PROGR EXEC OFF CLOSE COMBAT PM ABRAMS, ATTN: AMCPM-ABMS PM BFVS, ATTN: AMCPM-BFVS PM 113 FOV, ATTN: AMCPM-M113 PM M60, ATTN: AMCPM-M60 WARREN MI 40397-5000		

7

BFLRF No. 229 Page 1 of 5

CDR US ARMY LABORATORY COMMAND ATTN: AMSLC-TP-AL (LTC SCHRADER) ADELPHI MD 20783-1145	1	C A
CDR US ARMY FORCES COMMAND ATTN: AFLG-REG AFLG-POP FORT MCPHERSON GA 30330	1 1	4 S D A
CDR US ARMY RES & STDZN GROUP (EUROPE) ATTN: AMXSN-UK-RA (DR OERTEL) BOX 65 FPO NEW YORK 09510	1	A T C T
CDR US ARMY YUMA PROVING GROUND ATTN: STEYP-MT-TL-M (MR DOEBBLER) YUMA AZ 85364-9103	1	A F C U A C
CDR US ARMY RESEARCH OFC ATTN: SLCRO-EG (DR MANN) SLCRO-CB P O BOX 12211 RSCH TRIANGLE PARK NC 27709-2211	1 1	C U A N N
CDR US ARMY TANK-AUTOMOTIVE CMD PROGR EXEC OFF COMBAT SUPPORT PM LIGHT TACTICAL VEHICLES ATTN: AMCPM-TVL PM MEDIUM TACTICAL VEHICLES ATTN: AMCPM-TVM PM HEAVY TACTICAL VEHICLES ATTN: AMCPM-TVH WARREN MI 40397-5000	1 1 1	H V A C U A
PROJ MGR, MOBILE ELECTRIC POWER ATTN: AMCPM-MEP-TM 7500 BACKLICK ROAD SPRINGFIELD VA 22150	1	Fi C C U
PROJ OFF, AMPHIBIOUS AND WATER CRAFT ATTN: AMCPM-AWC-R 4300 GOODFELLOW BLVD ST LOUIS MO 63120	1	A Bi Ti

CDR, US ARMY TROOP SUPPORT COMMAND ATTN: AMSTR-ME AMSTR-S AMSTR-E AMSTR-WL 4300 GOODFELLOW BLVD ST LOUIS MO 63120-1798	1 1 1 1
DIR AMC PACKAGING, STORAGE, AND CONTAINERIZATION CTR ATTN: SDSTO-TE-S TOBYHANNA PA 18466-5097	1
CDR TRADOC COMBINED ARMS TEST ACTIVITY ATTN: ATCT-CA FORT HOOD TX 76544	1
CDR US ARMY DEPOT SYSTEMS CMD ATTN: AMSDS-RM-EFO CHAMBERSBURG PA 17201	1
CDR US ARMY LEA ATTN: DALO-LEP NEW CUMBERLAND ARMY DEPOT NEW CUMBERLAND PA 17070	1
HQ, EUROPEAN COMMAND ATTN: J4/7-LJPO (LTC WEINER) VAIHINGEN, GE APO NY 09128	1
CDR US ARMY FOREIGN SCIENCE & TECH CENTER ATTN: AIAST-RA-ST3 (MR BUSI) AIAST-MT-1 FEDERAL BLDG CHARLOTTESVILLE VA 22901	1 1
CDR US ARMY GENERAL MATERIAL & PETROLEUM ACTIVITY ATTN: STRGP-PW (MR PRICE) BLDG 247, DEFENSE DEPOT TRACY TRACY CA 95376-5051	1

BFLRF No. 229 Page 2 of 5 PROJ MGR, LIGHT ARMORED VEHICLES ATTN: AMCPM-LA-E 1 WARREN MI 48397

CDR US ARMY ORDNANCE CENTER & SCHOOL ATTN: ATSL-CD-CS

ABERDEEN PROVING GROUND MD 21005

CDR

AMC MATERIEL READINESS SUPPORT ACTIVITY (MRSA) ATTN: AMXMD-MO (MR BROWN) LEXINGTON KY 40511-5101

HQ, US ARMY T&E COMMAND ATTN: AMSTE-TO-O AMSTE-TE-T (MR RITONDO) ABERDEEN PROVING GROUND MD 21005-5006

CDR

US ARMY ARMAMENT RESEARCH, DEVELOPMENT & ENGRG CTR ATTN: AMSMC-LC AMSMC-SC DOVER NJ 07801-5001

CDR

CONSTRUCTION ENG RSCH LAB ATTN: CERL-EM CERL-ES (MR CASE) P O BOX 4005 CHAMPAIGN IL 61820

HQ

US ARMY TRAINING & DOCTRINE CMD ATTN: ATCD-SL-5 1 FORT MONROE VA 23651-5000

CDR

US ARMY QUARTERMASTER SCHOOL ATTN: ATSM-CD ATSM-PFS (MR ELLIOTT) FORT LEE VA 23801

CDR

COMBINED ARMS COMBAT DEVELOPMENT ACTIVITY ATTN: ATZL-CAT-E FORT LEAVENWORTH KS 66027-5300 DIR

1

1

1

1

1

1

1

1

1

1

1

DIR	
US ARMY MATERIALS TECHNOLOGY	
LABORATORY	
ATTN: SLCMT-M	1
SLCMT-MCM-P (DR FOPIANO)	1
WATERTOWN MA 02172-2796	
DIRECTOR	
US ARMY RSCH & TECH ACTIVITIES	
(AVSCOM)	
PROPULSION DIRECTORATE	
ATTN: SAVDL-PL-D (MR ACURIO)	1
21000 BROOKPARK ROAD	
CLEVELAND OH 44135-3127	
CDR	

US ARMY TRANSPORTATION SCHOOL ATTN: ATSP-CD-MS (MR HARNET) 1 FORT EUSTIS VA 23604-5000

PROJ MGR, PATRIOT PROJ OFFICE ATTN: AMCPM-MD-T-C U.S. ARMY MISSILE COMMAND REDSTONE ARSENAL AL 35898

HQ, US ARMY ARMOR CENTER AND FORT KNOX ATTN: ATSB-CD FORT KNOX KY 40121

CDR

US ARMY LOGISTICS CTR ATTN: ATCL-MS (MR A MARSHALL) 1 ATCL-C 1 FORT LEE VA 23801-6000

PROJECT MANAGER PETROLEUM & WATER LOGISTICS ATTN: AMCPM-PWL 4300 GOODFELLOW BLVD ST LOUIS MO 63120-1798

CDR

US ARMY FIELD ARTILLERY SCHOOL ATTN: ATSF-CD FORT SILL OK 73503-5600

CDR

US ARMY ENGINEE	R SCHOOL
ATTN: ATZA-TSM-	• (•
ATZA-CD	
FORT BELVOIR VA	22060-5606

BFLRF No. 229 Page 3 of 5

1

1

1

1

1

CDR US ARMY INFANTRY SCHOOL ATTN: ATSH-CD-MS-M FORT BENNING GA 31905-5400

CDR

US ARMY ARMOR & ENGINEER BOARD ATTN: ATZK-AE-AR 1 FORT KNOX KY 40121

1

1

1

1

1

1

1

1

1

1

CDR

US ARMY AVIATION CTR & FT RUCKER ATTN: ATZQ-DI 1 FORT RUCKER AL 36362

DEPARTMENT OF THE NAVY

CDR

NAVAL AIR PROPULSION CENTER ATTN: PE-33 (MR D'ORAZIO) PE-32 (MR MANGIONE) P O BOX 7176 TRENTON NJ 06828

CDR

NAVAL S	EA SYSTE	MS CMD	
ATTN: C	ODE 05M	4	
WASHING	GTON DC	20362-5101	

CDR

DAVID TAYLOR RESEARCH CTR ATTN: CODE 2830 (MR SINGERMAN) CODE 2759 (MR STRUCKO) CODE 2831 ANNAPOLIS MD 21402-5067

JOINT OIL ANALYSIS PROGRAM -TECHNICAL SUPPORT CTR BLDG 780 NAVAL AIR STATION PENSACOLA FL 32508-5300

CDR

NAVAL SHIP ENGINEERING CENTER ATTN: CODE 6764 PHILADELPHIA PA 19112

PROJ MGR, M60 TANK DEVELOPMENT ATTN: USMC-LNO US ARMY TANK-AUTOMOTIVE COMMAND (TACOM) WARREN MI 48397

DEPARTMENT OF THE NAVY HQ, US MARINE CORPS ATTN: LPP LMM/2 LMW WASHINGTON DC 20380	1 1 1
CDR NAVAL RESEARCH LABORATORY ATTN: CODE 6170 CODE 6180 CODE 6110 (DR HARVEY) WASHINGTON DC 20375-5000	1 1 1
CDR NAVAL FACILITIES ENGR CTR ATTN: CODE 1202B (MR R BURRIS) 200 STOVAL ST ALEXANDRIA VA 22322	1
COMMANDING GENERAL US MARINE CORPS DEVELOPMENT & EDUCATION COMMAND ATTN: DO74 QUANTICO VA 22134	1
OFFICE OF THE CHIEF OF NAVAL RESEARCH ATTN: OCNR-126 (DR ROBERTS) ARLINGTON VA 22217-5000	j
CDR NAVY PETROLEUM OFC ATTN: CODE 43 (MR LONG) CAMERON STATION ALEXANDRIA VA 22304-6180	1
DEPARTMENT OF THE AIR FORCE	
CDR USAF 3902 TRANSPORTATION SQUADRON ATTN: LGTVP (MR VAUGHN) OFFUTT AIR FORCE BASE NE 68113	1
CDR	

US AIR FORCE WRIGHT AERONAUTICAL LAB ATTN: AFWAL/POSL (MR JONES)

AFWAL/MLSE 1 AFWAL/MLBT (MR SNYDER) 1 WRIGHT-PATTERSON AFB OH 45433-6563

BFLRF No. 229 Page 4 of 5 CDR

<u>``8.4`8.6⁸8`8`8`8`8\$\$`8`8`8`8`8`8`8</u>*8*8*8*8*8*8*

SAN ANTONIO AIR LOGISTICS CTR

ATTN: SAALC/SFT (MR MAKRIS) SAALC/MMPRR KELLY AIR FORCE BASE TX 78241

"al. "al. "al. 4a b. V. B. L. B. A.

1

1

1

1

HQ AIR FORCE SYSTEMS CMD ATTN: AFSC/DLF (DR DUES) ANDREWS AFB MD 20334

CDR

WARNER ROBINS AIR LOGISTIC CTR ATTN: WRALC/MMTV ROBINS AFB GA 31098

OTHER GOVERNMENT AGENCIES

1

1

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION LEWIS RESEARCH CENTER CLEVELAND OH 44135

US DEPARTMENT OF ENERGY ATTN: MR ECKLUND MAIL CODE CE-151 FORRESTAL BLDG. 1000 INDEPENDENCE AVE, SW WASHINGTON DC 20585

> BFLRF No. 229 Page 5 of 5