

DTIC FILE COPY



2

Naval Research Laboratory

Washington, DC 20375-5000

NRL Report 9134

AD-A193 535

Three-Dimensional Stresses in a Half Space Caused by Penny-Shaped Inclusions

H. Y. YU

*Geo-Centers Inc.
Fort Washington, MD 20744*

AND

S. C. SANDAY

*Composites and Ceramics Branch
Materials Science and Technology Division*

DTIC
ELECTE
OCT 11 1988
S D
D cy

August 19, 1988

Approved for public release; distribution unlimited.

130 1 2 237

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
1a REPORT SECURITY CLASSIFICATION UNCLASSIFIED			1b RESTRICTIVE MARKINGS		
2a SECURITY CLASSIFICATION AUTHORITY			3 DISTRIBUTION AVAILABILITY OF REPORT		
2b DECLASSIFICATION/DOWNGRADING SCHEDULE			Approved for public release; distribution unlimited.		
4 PERFORMING ORGANIZATION REPORT NUMBER(S) NRL Report 9134			5 MONITORING ORGANIZATION REPORT NUMBER(S)		
6a NAME OF PERFORMING ORGANIZATION Naval Research Laboratory		6b OFFICE SYMBOL (if applicable) Code 6370	7a NAME OF MONITORING ORGANIZATION		
6c ADDRESS (City, State, and ZIP Code) Washington, DC 20375-5000			7b ADDRESS (City, State, and ZIP Code)		
8a NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research		8b OFFICE SYMBOL (if applicable)	9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER		
8c ADDRESS (City, State, and ZIP Code) Arlington, VA 22217			10 SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO 61153N	PROJECT NO RR0220441	TASK NO
					WORK UNIT ACCESSION NO DN280-063
11 TITLE (Include Security Classification) Three-Dimensional Stresses in a Half Space Caused by Penny-Shaped Inclusions					
12 PERSONAL AUTHOR(S) Yu, * H.-Y. and Sanday, S.C.					
13a TYPE OF REPORT Interim		13b TIME COVERED FROM _____ TO _____		14 DATE OF REPORT (Year, Month, Day) 1988 August 19	15 PAGE COUNT 18
16 SUPPLEMENTARY NOTATION *Geo-Centers, Inc., Fort Washington, MD 20744					
17 COSATI CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	Elastic solution Inclusion	Orthotropic misfit Image stress	Half space
19 ABSTRACT (Continue on reverse if necessary and identify by block number) Elastic stress fields caused by isotropic penny-shaped inclusions and axisymmetric ellipsoidal inhomogeneties in a semi-infinite solid are investigated. The analytical solution for these problems is obtained by applying Hankel transformations and Eshelby's solution for ellipsoidal inclusions. This new approach can also be applied to other axisymmetric-potential function-related problems in the half space.					
20 DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21 ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED		
22a NAME OF RESPONSIBLE INDIVIDUAL S. C. Sanday			22b TELEPHONE (Include Area Code) (202) 767-2264	22c OFFICE SYMBOL Code 6370	

CONTENTS

INTRODUCTION	1
BASIC APPROACH	1
SOLUTION FOR σ_{ij}	7
ELASTIC STRAIN ENERGY	11
THE ELLIPSOIDAL INHOMOGENEITY	11
SURFACE DISTORTION AND DILATATION FIELD	12
SUMMARY	12
REFERENCES	13

Accession For	
NTIS	<input checked="" type="checkbox"/>
CRA&I	
DTIC	<input type="checkbox"/>
TAG	
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	



THREE-DIMENSIONAL STRESSES IN A HALF SPACE CAUSED BY PENNY-SHAPED INCLUSIONS

INTRODUCTION

Elastic fields caused by inclusions in infinite media have been extensively investigated by several authors [1-5] after Eshelby's work [6-8]. Other research efforts have addressed the half-space problem with an inclusion located near the free surface [9-12]. In these studies, the following methods were used: Galerkin vector [9], Papkovitch-Neuber displacement potential [10], image stress caused by two cuboidal inclusions with uniform eigenstrains [11], and Green's function in the half space [12]. Mura has recently reviewed these research efforts [13].

When the elastic moduli of an ellipsoidal subdomain of a material differs from those of the remainder (matrix), the subdomain is called an ellipsoidal inhomogeneity. Cracks, voids, and precipitates are examples of these inhomogeneities. A material containing inhomogeneities is assumed to be free from any stress field unless an external stress field σ_{ij}^a is applied. On the other hand, a material containing inclusions is subjected to an internal stress caused by the eigenstrain e_{ij}^T even if it is free from any external loads. The definition of eigenstrains has been given by Mura [13] and is the same as the stress-free-transformation strain described by Eshelby [6].

The solutions for ellipsoidal inhomogeneities can be reduced to the penny-shaped or elliptical crack case by setting the elastic constants λ and μ for the inhomogeneities equal to zero. The solution of the three-dimensional problems for these cracks has received considerable attention [14-19]. The stress field of a penny-shaped crack in the half space can be solved by obtaining the relevant system of integral equations for the problem formulated by Erdogan and Gupta [20] for the stress analysis of multilayered composites with a flaw.

In the present study, Eshelby's method for ellipsoidal inclusions [6-8] and Hankel's transformation method, used to obtain the elastic solutions of a circular dislocation loop in an unbounded media [21] and in the half space [22], are used for the analysis of the elastic solution of axisymmetric inclusions and axisymmetric-ellipsoidal inhomogeneities in the half space. The method provides a novel way for obtaining the image stresses of an ellipsoidal inclusion in the half space. It is used to find a more general solution of an ellipsoidal inclusion with anisotropic eigenstrain. Existing solutions are shown to be special cases of the present result. This method can also be used to obtain the stress field of a penny-shaped crack in the half space.

BASIC APPROACH

In this report, we consider an axisymmetric ellipsoidal inclusion Ω_1 in a half space (Fig. 1). In general, the inclusion Ω_1 is given by

$$\frac{x_1^2}{a_1^2} + \frac{x_2^2}{a_2^2} + \frac{x_3^2}{a_3^2} \leq 1. \quad (1)$$




Fig. 1 — Ellipsoidal inclusion with principal half axis $a_1 = a_2, a_3$ in a half space

Symmetry with respect to the x_3 -axis is then defined by $a_1 = a_2$, and the anisotropic eigenstrain of the inclusion

$$e_{ij}^T = \delta_{ij}(e + b\delta_{i3}) \quad i, j = 1, 2, 3, \quad (2)$$

where δ_{ij} is Kronecker delta. (Note that the usual summation convention does not apply to any of the expressions in this report.) Equation (2) states that only normal eigenstrains appear, and $e_{11}^T = e_{22}^T = e$ and $e_{33}^T = e + b$.

For the inclusion Ω_1 defined by Eq. (1) with the uniform eigenstrain described by Eq. (2) with $a_3 = 0$, the stress field in the unbounded medium outside Ω_1 is obtained by using Eshelby's method [6-8]. The result is given by

$$\begin{aligned} \sigma_{ij} = & \frac{\mu b}{4\pi(1-\nu)} [x_3\phi_{,ij3} - (1-2\nu)(\delta_{i3} + \delta_{j3} - 1)\phi_{,ij} - 2\nu\delta_{ij}\phi_{,33}] \\ & - \frac{\mu(1+\nu)e}{2\pi(1-\nu)} \phi_{,ij}. \end{aligned} \quad (3)$$

where the numerical suffixes, $i, j = 1, 2, 3$, following a comma denote differentiation with respect to the Cartesian coordinates x_1, x_2, x_3 , e.g. $\phi_{,ij} = \partial^2\phi/\partial x_i\partial x_j$, and ϕ is the Newtonian potential function that is given by

$$\phi = \pi a_1^2 a_3 \int_{\lambda_0}^{\infty} \frac{U}{\Delta} ds, \quad (4)$$

where

$$U = 1 - \left[\frac{x_1^2 + x_2^2}{a_1^2 + s} + \frac{x_3^2}{a_3^2 + s} \right],$$

$$\Delta = (a_1^2 + s)(a_3^2 + s)^{1/2},$$

and λ_0 is the largest root of $U = 0$ outside of Ω_1 and $\lambda_0 = 0$ inside of Ω_1 . For inclusions with uniform dilatation eigenstrain only ($b = 0$), Eq. (3) is valid for any a_3 value. The detailed expression of ϕ for both the oblate spheroid ($a_1 > a_3$) and the prolate spheroid ($a_1 < a_3$) are given by Yu [23]. Equation (3) can be transformed into cylindrical coordinates (r, θ, z) as follows:

$$\begin{aligned} \sigma_{rr} &= -\frac{\mu b}{4\pi(1-\nu)} \left[\phi_{,zz} + z\phi_{,zzz} + \frac{1-2\nu}{r} \phi_{,r} + \frac{z}{r} \phi_{,rz} \right] \\ &\quad + \frac{\mu(1+\nu)e}{2\pi(1-\nu)} \left[\frac{\phi_{,r}}{r} + \phi_{,zz} \right], \\ \sigma_{\theta\theta} &= -\frac{\mu b}{4\pi(1-\nu)} \left[2\nu\phi_{,zz} - \frac{1-2\nu}{r} \phi_{,r} - \frac{z}{r} \phi_{,rz} \right] - \frac{\mu(1+\nu)e}{2\pi(1-\nu)} \frac{\phi_{,r}}{r}, \\ \sigma_{zz} &= -\frac{\mu b}{4\pi(1-\nu)} [\phi_{,zz} - z\phi_{,zzz}] - \frac{\mu(1+\nu)e}{2\pi(1-\nu)} \phi_{,zz}, \\ \sigma_{rz} &= \frac{\mu b}{4\pi(1-\nu)} [z\phi_{,rzz}] - \frac{\mu(1+\nu)e}{2\pi(1-\nu)} \phi_{,rz}, \\ \sigma_{r\theta} &= \sigma_{z\theta} = 0. \end{aligned} \quad (5)$$

Equations (5) are obtained with the aid of the following relationships:

$$\nabla^2\phi = 0,$$

$$x_1\phi_{,2} = x_2\phi_{,1},$$

and

$$\phi_{,r} = \frac{1}{r} (x_1\phi_{,1} + x_2\phi_{,2}), \quad (6)$$

where the letter suffixes following a comma denote differentiation with respect to the cylindrical coordinates r , θ , and z , e.g. $\phi_{,rz} = \partial^2 \phi / \partial r \partial z$.

For a circular-edge dislocation loop with the z -axis as the axis of symmetry in an unbounded medium (Fig. 2), the stress field is found by Kroupa [21] by using Hankel transformations. For $z > 0$, Kroupa's solution can be rewritten as

$$\begin{aligned}\sigma_{rr} &= -\frac{\mu b'}{2(1-\nu)} a [(I_0^{-1})_{,zz} + z(I_0^{-1})_{,zzz} + \frac{1-2\nu}{r} (I_0^{-1})_{,r} + \frac{z}{r} (I_0^{-1})_{,rz}], \\ \sigma_{\theta\theta} &= -\frac{\mu b'}{2(1-\nu)} a \left[2\nu(I_0^{-1})_{,zz} - \frac{1-2\nu}{r} (I_0^{-1})_{,r} - \frac{z}{r} (I_0^{-1})_{,rz} \right], \\ \sigma_{zz} &= -\frac{\mu b'}{2(1-\nu)} a [(I_0^{-1})_{,zz} - z(I_0^{-1})_{,zzz}], \\ \sigma_{rz} &= \frac{\mu b'}{2(1-\nu)} a [z(I_0^{-1})_{,rz}], \\ \sigma_{r\theta} &= \sigma_{z\theta} = 0,\end{aligned}\tag{7}$$

where

$$\begin{aligned}I_m^n &= \int_0^\infty t^n J_m(rt/a) J_1(t) e^{-zt/a} dt, \\ I_m^n &= -a(I_m^{n-1})_{,z}, \\ &= -ar^{m-1}(r^{-m+1} I_{m-1}^{n-1})_{,r} \quad (m = 0, 1, 2, \dots; n = -1, 0, 1, 2, \dots),\end{aligned}$$

and J_m is the Bessel function of the m th order, a is the radius of the circular dislocation loop, and b' is the Burger's vector. Equation (7) is obtained by the method of Hankel transformation as used for cylindrically symmetric problems of the theory of elasticity in Sneddon's book [24] and subjected to the following boundary conditions:

$$\begin{aligned}u_z(r, 0) &= \frac{1}{2} b' \quad \text{for } 0 \leq r < a, \\ &= 0 \quad \text{for } r > a, \\ \sigma_{rz}(r, 0) &= 0 \quad \text{for } 0 \leq r < \infty.\end{aligned}\tag{8}$$

For the penny-shaped inclusion without shear and dilatation eigenstrains (penny-shaped prismatic inclusion), which is the axisymmetric inclusion when a_3 approaches zero, the equivalent eigenstrains




Fig. 2 — Circular edge dislocation loop in infinite solid

are $e_{11}^T = e_{22}^T = 0$, $e_{33}^T \neq 0$. If we reduce Eq. (5) for a penny-shaped prismatic inclusion, that is, $a_3 \rightarrow 0$ and $e = 0$, it is interesting to note the similarity between Eqs. (5) and (7). By putting

$$\phi = kI_0^{-1} \quad (a_3 \rightarrow 0), \quad (9)$$

where $k = 2\pi b'a/b$, and $a_1 = a$, the elastic solutions of both the penny-shaped prismatic inclusion (Eq. 5) and the circular-edge dislocation loop (Eq. 7) are identical. This suggests that the method used to investigate the elastic solution of a circular-edge dislocation loop in the half space [22] can be applied to solve the elastic field caused by an axisymmetrical inclusion in the half space. This approach is reasonable since the solution of the axisymmetrical inclusion can be obtained by the integration of the results of a penny-shaped prismatic inclusion and the fact that if the inclusion has the same elastic moduli as the matrix, the stress field is the same as that of a small dislocation loop when both the dislocation loop and the inclusion are infinitesimally small [8]. For example, a small inclusion of volume V and an eigenstrain e_{33}^T in the x_3 direction has the same stress field as that of a prismatic interstitial dislocation loop of area A and Burgers vector b_1 provided that $Ve_{33}^T = Ab_1$.

Consider the half space $x_3 = z > 0$ (Fig. 1), an axisymmetric inclusion with the center at the point $(0, 0, c)$ in such a way that its axis of symmetry (z -axis) is perpendicular to the plane of the free surface $z = 0$. In order that the plane $z = 0$ be a free surface, no force must act on it, thus the stress components at $z = 0$ must satisfy the boundary conditions

$$(\sigma_{rz})_{z=0} = 0, \quad (10)$$

$$(\sigma_{zz})_{z=0} = 0,$$

and the equilibrium condition

$$\sum_{j=1}^3 \sigma_{ij,j} = 0. \quad (11)$$

Similar to the work of Bastecka [22], the stress σ_{ij} outside the axisymmetric ellipsoidal inclusion centered at the point $(0, 0, c)$ but in the half space $z > 0$ is

$$\sigma_{ij} = \sigma_{ij}^I + \sigma_{ij}^{II} + \sigma'_{ij}, \quad (12)$$

which will satisfy the required boundary conditions (Eq. 10) and the equilibrium condition (Eq. 11). This converges to zero for x_1 and x_2 approaching $\pm \infty$ and x_3 approaching ∞ . In Eq. (12), the term σ_{ij}^I is the stress caused by the axisymmetric inclusion Ω_1 (and outside of it) centered at the point $(0, 0, c)$; σ_{ij}^{II} is the stress caused by the image inclusion Ω_2 centered at the point $(0, 0, -c)$ (Fig. 3) with eigenstrain

$$(e_{ij}^T)^{II} = -(e_{ij}^T)^I = -\delta_{ij}(e + b\delta_{i3}). \quad (13)$$




Fig. 3 — Semi-infinite solid containing an ellipsoidal inclusion Ω_1 and its image Ω_2

Equation 13 shows that σ'_{ij} is an additional stress that satisfies the boundary condition

$$(\sigma'_{zz})_{z=0} = -(\sigma'_{zz} + \sigma''_{zz})_{z=0} = 0; \quad (14a)$$

$$(\sigma'_{rz})_{z=0} = -(\sigma'_{rz} + \sigma''_{rz})_{z=0}. \quad (14b)$$

The solutions for the stresses σ'_{ij} and σ''_{ij} are obtained by translating the origin of coordinates in Eq. (3) and Eq. (5) to points $(0, 0, c)$, and $(0, 0, -c)$ respectively. The Newtonian potential function ϕ' and ϕ'' for the solutions of σ'_{ij} and σ''_{ij} respectively are given by

$$\begin{aligned} \phi' &= \pi a_1^2 a_3 \int_{\lambda_1}^{\infty} \frac{U_1}{\Delta} ds, \\ \phi'' &= \pi a_1^2 a_3 \int_{\lambda_2}^{\infty} \frac{U_2}{\Delta} ds, \end{aligned} \quad (15)$$

where

$$U_1 = 1 - \left[\frac{x_1^2 + x_2^2}{a_1^2 + s} + \frac{(x_3 - c)^2}{a_3^2 + s} \right],$$

$$U_2 = 1 - \left[\frac{x_1^2 + x_2^2}{a_1^2 + s} + \frac{(x_3 + c)^2}{a_3^2 + s} \right],$$

$$\Delta = (a_1^2 + s)(a_3^2 + s)^{1/2},$$

and where

λ_1 is the largest root of $U_1 = 0$ for exterior points of Ω_1 ,

$\lambda_1 = 0$ for interior points of Ω_1 , and

λ_2 is the largest root of $U_2 = 0$.

SOLUTION FOR σ'_{ij}

Substituting Eqs. (5) and (15) into Eq. (14) gives

$$(\sigma'_{zz})_{z=0} = 0; \quad (16a)$$

$$(\sigma'_{rz})_{z=0} = \frac{\mu}{2\pi(1-\nu)} \left[cb \phi''_{,rzz} - 2(1+\nu)e \phi''_{,rz} \right]_{z=0}, \quad (16b)$$

where for $z = 0$, $\phi_{,rzz}^I = \phi_{,rzz}^{II}$ and $\phi_{,rz}^I = -\phi_{,rz}^{II}$. Now, in the limit when a_3 approaches zero, that is, for the penny-shaped inclusion ($a_1 = a_2 = a$), we can substitute Eq. (9) into Eq. (16b) to obtain

$$\begin{aligned} (\sigma'_{rz})_{z=0} = & -\frac{\mu bc}{2\pi(1-\nu)} \frac{k}{a^3} \int_0^\infty t^2 J_1(\rho t) J_1(t) e^{-ct/a} dt \\ & -\frac{\mu(1+\nu)e}{\pi(1-\nu)} \frac{k}{a^2} \int_0^\infty t J_1(\rho t) J_1(t) e^{-ct/a} dt, \end{aligned} \quad (16c)$$

where $\rho = r/a$.

For the axisymmetric problem, by the appropriate expression of the elastic displacements as the derivatives of certain function $\psi(r, z)$ in cylindrical coordinates, the equilibrium and Beltrami equations are replaced by a single equation [24]

$$\nabla^4 \psi(r, z) = 0, \quad (17)$$

whose general solution is carried out by the method of integral transformations. The function ψ is replaced by its Hankel transform of zeroth order,

$$G(\zeta, z) = \int_0^\infty r \psi(r, z) J_0(\zeta r) dr, \quad (18)$$

and it can be shown that $G(\zeta, z)$ is generally given by the expression

$$G(\zeta, z) = (A + Bz)e^{-\zeta z} + (C + Dz)e^{\zeta z}, \quad (19)$$

where A, B, C and D are unknown functions of ζ , which are determined from the boundary conditions. The stress components are expressed by means of the function $G(\zeta, z)$.

In the present case, we consider the solution to converge to zero for z approaching ∞ . Thus we set $C = D = 0$. To determine A and B from the first boundary condition (Eq. 16a), we obtain the following relationship

$$A = -\frac{\mu}{\lambda + \mu} \frac{B}{\zeta}, \quad (20)$$

where $\lambda = 2\mu\nu/(1 - 2\nu)$ is Lamé's constant. From the second boundary condition (Eq. 16b), as modified in Eq. (16c), we have

$$\begin{aligned} (\sigma'_{rz})_{z=0} = & f(r) \\ = & \int_0^\infty \zeta F(\zeta) J_1(\zeta r) d\zeta, \end{aligned} \quad (21)$$

where

$$F(\zeta) = -2(\lambda + \mu)\zeta^2 B(\zeta), \quad (22)$$

and

$$f(r) = -\frac{\mu bc}{2\pi(1-\nu)} \frac{k}{a^3} \int_0^\infty t^2 J_1(\rho t) J_1(t) e^{-ct/a} dt$$

$$-\frac{\mu(1+\nu)e}{\pi(1-\nu)} \frac{k}{a^2} \int_0^\infty t J_1(\rho t) J_1(t) e^{-ct/a} dt. \quad (23)$$

By letting $t = a\zeta$, Eqs. (21) and (23) give

$$F(\zeta) = -\frac{k\mu}{2\pi(1-\nu)} [cb\zeta + 2(1+\nu)e] J_1(a\zeta) e^{-c\zeta}. \quad (24)$$

By substituting Eqs. (24), (22), and (20) into Eq. (19), the function $G(\zeta, z)$ is found that can then be substituted in the expressions for the stress σ'_{ij} [24, §51]. After substituting the relationship again,

$$\phi'' = k(I_0^{-1})'' = k \int_0^\infty t^{-1} J_0(\rho t) J_1(t) e^{-t(z+c)/a} dt, \quad (25)$$

these stresses σ'_{ij} are as follows.

$$\sigma'_{rr} = -\frac{\mu bc}{2\pi(1-\nu)} \left[2\phi_{,zzz}'' + z\phi_{,zzzz}'' + \frac{2(1-\nu)}{r} \phi_{,rz}'' + \frac{z}{r} \phi_{,rzz}'' \right]$$

$$+ \frac{\mu(1+\nu)e}{\pi(1-\nu)} \left[2\phi_{,zz}'' + z\phi_{,zzz}'' + \frac{2(1-\nu)}{r} \phi_{,r}'' + \frac{z}{r} \phi_{,rz}'' \right],$$

$$\sigma'_{\theta\theta} = -\frac{\mu bc}{2\pi(1-\nu)} \left[2\nu\phi_{,zzz}'' - \frac{2(1-\nu)}{r} \phi_{,rz}'' - \frac{z}{r} \phi_{,rzz}'' \right]$$

$$+ \frac{\mu(1+\nu)e}{\pi(1-\nu)} \left[2\nu\phi_{,zz}'' - \frac{2(1-\nu)}{r} \phi_{,r}'' - \frac{z}{r} \phi_{,rz}'' \right], \quad (26)$$

$$\sigma'_{zz} = \frac{\mu bc}{2\pi(1-\nu)} \left[z\phi_{,zzzz}'' \right] - \frac{\mu(1+\nu)e}{\pi(1-\nu)} \left[z\phi_{,zzz}'' \right],$$

$$\sigma'_{rz} = \frac{\mu bc}{2\pi(1-\nu)} \left[\phi_{,rzz}'' + z\phi_{,rzzz}'' \right] - \frac{\mu(1+\nu)e}{\pi(1-\nu)} \left[\phi_{,rz}'' + z\phi_{,rzz}'' \right],$$

$$\sigma'_{r\theta} = \sigma'_{rz} = 0.$$

When $e = 0$ and $\phi'' = k(I_0^{-1})''$, Eq. (26) reduces to the same results obtained by Bastecka [22] for a circular-edge dislocation loop in the half space. In Cartesian coordinates, $\Sigma\zeta$, (26) becomes

$$\begin{aligned} \sigma'_{ij} = & -\frac{\mu b c}{2\pi(1-\nu)} \left[(1-2\nu)(\delta_{3i} + \delta_{3j} - 1)\phi_{,ij3}'' - \phi_{,ij3}'' \right. \\ & \left. + 2\nu\delta_{ij}\phi_{,333}'' - x_3\phi_{,ij33}'' \right] \\ & + \frac{\mu(1+\nu)e}{\pi(1-\nu)} \left[(1-2\nu)(\delta_{3i} + \delta_{3j} - 1)\phi_{,ij}'' - \phi_{,ij}'' \right. \\ & \left. + 2\nu\delta_{ij}\phi_{,33}'' - x_3\phi_{,ij3}'' \right]. \end{aligned} \quad (27)$$

It can be shown that σ'_{ij} satisfies the equation of equilibrium, that is,

$$\sum_{j=1}^3 \sigma'_{ij,j} = 0. \quad (28)$$

Therefore, for points outside Ω_1 , the stress field caused by the presence of a penny-shaped inclusion in the half space can be obtained by Eqs. (3), (12), and (27). Thus,

$$\begin{aligned} \sigma_{ij} = & \frac{\mu b}{4\pi(1-\nu)} \{ (x_3 - c)(\phi_{,ij3}^I - \phi_{,ij3}^{II}) - (1-2\nu)(\delta_{3i} + \delta_{3j} - 1)(\phi_{,ij}^I - \phi_{,ij}^{II} + 2c\phi_{,ij3}^{II}) \\ & - 2\nu\delta_{ij}(\phi_{,33}^I - \phi_{,33}^{II} + 2c\phi_{,333}^{II}) + 2cx_3\phi_{,ij33}^{II} \} \\ & - \frac{\mu(1+\nu)e}{2\pi(1-\nu)} \{ \phi_{,ij}^I + \phi_{,ij}^{II} - 2(1-2\nu)(\delta_{3i} + \delta_{3j} - 1)\phi_{,ij}^{II} - 4\nu\delta_{ij}\phi_{,33}^{II} \\ & + 2x_3\phi_{,ij3}^{II} \}. \end{aligned} \quad (29)$$

For points inside Ω_1 , the elastic stress σ_{ij}^* is given by

$$\begin{aligned} \sigma_{ij}^* & = \sigma_{ij} - \sigma_{ij}^{**} \\ & = (\sigma_{ij}^I - \sigma_{ij}^{**}) + \sigma_{ij}^{II} + \sigma_{ij} \end{aligned} \quad (30)$$

where $-\sigma_{ij}^{**}$ is the uniform stress that exists in the inclusion caused by the uniform eigenstrain e_{ij}^T (Eq. 2). The stress $(\sigma_{ij}^I - \sigma_{ij}^{**})$ is the uniform stress inside the inclusion Ω_1 when the medium is infinite. The solution is expressed explicitly by Mura ([13], Eq. 11.20). Equations (5), (12), and (26) give the stress field in cylindrical coordinates.

Seo and Mura's results [12] for the elastic field in a half space caused by an ellipsoidal inclusion with uniform dilatational eigenstrain (obtained by using Mindlin's solution [25] for Green's function in the half space) can be obtained as a special case by taking $b = 0$ (and $a_1 = a_2$) in Eqs. (29) and (30). Mindlin and Cheng's results [9] for a sphere can also be obtained as a special case by taking $a_1 = a_2 = a_3$ and $b = 0$ in Eq. (29).

ELASTIC STRAIN ENERGY

The elastic strain energy can be expressed as

$$\begin{aligned} W &= -\frac{1}{2} \int_{\Omega_1} \sigma_{ij}^* e_{ij}^T d\bar{V}, \\ &= -\frac{1}{2} \int_{\Omega_1} \sum_{i=1}^3 \sigma_{ii}^* e d\bar{V} - \frac{1}{2} \int_{\Omega_1} \sigma_{33}^* b d\bar{V}, \end{aligned} \quad (31)$$

where $\sum_{i=1}^3 \sigma_{ii}^*$ is the dilation stress field in the inclusion. It is given by

$$\begin{aligned} \sum_{i=1}^3 \sigma_{ii}^* &= -\frac{2\mu(1+\nu)e}{(1-\nu)} \left[2 - \frac{1}{\pi} (1+\nu)\phi_{,33}'' \right] \\ &\quad - \frac{2\mu(1+\nu)b}{(1-\nu)} \left[1 + \frac{1}{4\pi} (\phi_{,33}' - \phi_{,33}'' + 2c\phi_{,333}''') \right]. \end{aligned} \quad (32)$$

when $b = 0$, the strain energy obtained is the same as that obtained by Seo and Mura [12].

THE ELLIPSOIDAL INHOMOGENEITY

When an inhomogeneity contains an eigenstrain, it is called an inhomogeneity inclusion. Eshelby [6] first pointed out that the stress-field changes caused by an inhomogeneity when the remotely applied stress is σ_{ij}^a can be simulated by the eigenstress caused by an inclusion, if the eigenstrain e_{ij}^T is properly chosen. This eigenstrain is sometimes referred to as the equivalent eigenstrain, or the equivalent stress-free transformation strain. For a given uniformly applied stress σ_{ij}^a and a uniform eigenstrain e_{ij}^{T*} , the normal components of the equivalent eigenstrains e_{ij}^T are given by [23]

$$\begin{aligned} (\lambda - \lambda^*)e^c + \lambda e^T + 2\mu e_{ij}^T + 2(\mu^* - \mu) \sum_{kl=11}^{33} S_{ijkl} e_{kl}^T \\ = \lambda^* e^{T*} + (\lambda - \lambda^*)e^a + 2\mu^* e_{ij}^{T*} + 2(\mu - \mu^*)e_{ij}^a \end{aligned} \quad (33)$$

where $ij = 11, 22, 33$ and kl denotes summation over 11, 22, 33 only; e^T , e^{T*} and e^a are the sum of three normal components of strains e_{ij}^T , e_{ij}^{T*} , and e_{ij}^a respectively;

$$e^c = \frac{1-2\nu}{4\pi(1-\nu)} (I_1 e_{11}^T + I_2 e_{22}^T + I_3 e_{33}^T) + \frac{\nu}{1-\nu} e^T. \quad (34)$$

In this equation, μ, λ are the elastic constants of the matrix; μ^*, λ^* are the elastic constants of the inhomogeneity; and I_1, I_2, I_3 , and S_{ijkl} are constants whose values depend on the shape of the inclusion as given by Eshelby [6-8]. Some detailed expressions for these constants for the inclusions of special shapes are given by Mura [13]. Therefore, by solving the set of three simultaneous equations in Eq. (33), the equivalent eigenstrains e_{11}^T, e_{22}^T , and e_{33}^T are obtained once the uniform eigenstrain e_{ij}^{I*} and uniformly applied stress e_{ij}^a are given. If both e_{ij}^{I*} and e_{ij}^a are axisymmetric for an axisymmetrical inclusion, the resultant equivalent eigenstrain e_{ij}^T is also axisymmetric and can be represented in the form of Eq. (2). Then the results of Eqs. (3), (5), (12), (26), (27), (29), and (30) can be applied accordingly to solve the stress field and strain energy of an axisymmetrical inhomogeneous inclusion in the half space.

SURFACE DISTORTION AND DILATATION FIELD

The roughness of solid surfaces is a second-order effect, but it has profound practical consequences in many fields of engineering and pure science. In many practical situations, the presence of inclusions or inhomogeneities under an external load will change the surface profile. The displacement of the free surface ($z = 0$) solved by the present method is:

$$u_r = \frac{bc}{\pi} (\phi,_{rz})_{z=0} - \frac{(1 + \nu)e}{\pi} (\phi,_{r})_{z=0},$$

$$u_z = \frac{b}{2\pi} [(\phi,_{z})_{z=0} - c(\phi,_{zz})_{z=0}] + \frac{e}{\pi} (\phi,_{z})_{z=0}.$$
(35)

The presence of inclusions or inhomogeneities under an external load will also produce a dilatational field. The dilatational field in the matrix obtained in the present study is:

$$\frac{\Delta V}{V} = -\frac{(1 - 2\nu)b}{4\pi(1 - \nu)} [\phi,_{zz}^I - \phi,_{zz}^{II} + 2c\phi,_{zzz}^{II}]$$

$$+ \frac{(1 - 2\nu)(1 + \nu)e}{\pi(1 - \nu)} \phi,_{zz}^{II}.$$
(36)

The important relationships between the dilatation field and the equilibrium-concentration distribution for dilute solutions in stressed solid are given by Li [26].

SUMMARY

The stress field in the half space ($z \geq 0$) caused by a penny-shaped inclusion Ω_1 centered at $(0, 0, c)$ with eigenstrain $e_{ij}^T = \delta_{ij}(e + b\delta_{i3})$ is found by the superposition of the following three stress fields: (a) the stress field of the inclusion Ω_1 centered at $(0,0,c)$ with eigenstrain e_{ij}^T in an infinite medium; (b) the stress field of the image inclusion Ω_2 centered at $(0, 0, -c)$ with eigenstrain $-e_{ij}^T$; and (c) the additional fictitious stress field that makes all stress fields satisfy the equilibrium and boundary conditions.

The stress field of the penny-shaped prismatic inclusion in an infinite medium obtained by Eshelby is compared with the stress field of a prismatic loop in an infinite medium as obtained by Kroupa [21]. A relationship is found between the potential function ϕ of the inclusion and the integral function I_0^{-1} , which involves the product of the Bessel functions J_m for the solution of the prismatic loop.

The fictitious stress field is solved first for the two-dimensional problem by using the Hankel transformation method and then it is transformed into the three-dimensional case by use of the relationship between ϕ and I_0^{-1} .

The solution of the elastic field in the half space with ellipsoidal inclusions with uniform dilatational eigenstrains obtained by Seo and Mura (1979) has been rearranged into three terms corresponding to the stress field of the inclusion Ω_1 in an infinite medium centered at $(0,0,-c)$ with eigenstrain $\delta_{ij}e$, the stress field of the image inclusion Ω_2 centered at $(0,0,-c)$ with eigenstrain $-\delta_{ij}e$, and the additional fictitious stress field. It has also been shown that when $a_1 = a_2$, Seo and Mura's results are a special case of the present solution.

REFERENCES

1. L.J. Walpole, "The Elastic Field of an Inclusion in an Anisotropic Medium," *Proc. R. Soc. London A300*, 270-289 (1967).
2. N. Kinoshita and T. Mura, "Elastic Fields of Inclusions in Anisotropic Media," *Phys. Status Solidi A5*, 759-768 (1971).
3. R.J. Asaro and D.M. Barnett, "The Nonuniform Transformation Strain Problem for an Anisotropic Ellipsoidal Inclusion," *J. Mech. Phys. Solids 23*, 77-83 (1975).
4. T. Mura and D.C. Cheng, "The Elastic Field Outside an Ellipsoidal Inclusion," *J. Appl. Mech. 44*, 591-594 (1977).
5. Y.P. Chiu, "On the Stress Field Due to Initial Strains in Cuboid Surrounded by an Infinite Elastic Space," *J. Appl. Mech. 44*, 587-590 (1977).
6. J.D. Eshelby, "The Determination of the Elastic Field of an Ellipsoidal Inclusion and Related Problems," *Proc. R. Soc. London A241*, 376-396 (1957).
7. J.D. Eshelby, "The Elastic Field Outside an Ellipsoidal Inclusion," *Proc. R. Soc. London A252*, 561-569 (1959).
8. J.D. Eshelby, "Elastic Inclusion and Inhomogeneities," in *Prog. Solid Mech. 2*, I.N. Sneddon and R. Hill, eds. (North-Holland, Amsterdam, 1961), pp. 89-140.
9. R.D. Mindlin and D.H. Cheng, "Thermoelastic Stress in the Semi-Infinite Solid," *J. Appl. Phys. 21*, 931-933 (1950).
10. D.L. Guell and J. Dundurs, "Further Results on Center of Dilatation and Residual Stresses in Joined Elastic Half-Space," *Dev. Theor. Appl. Mech. 3*, 105-115 (1967).
11. Y.P. Chiu, "On the Stress Field and Surface Deformation in a Half Space with a Cuboidal Zone in Which Initial Strains Are Uniform," *J. Appl. Mech. 45*, 302-306 (1978).
12. K. Seo and T. Mura, "The Elastic Field in a Half-Space Due to Ellipsoidal Inclusions with Uniform Dilatational Eigenstrains," *J. Appl. Mech. 46*, 568-572 (1979).
13. T. Mura, *Micromechanics of Defects in Solids* (Martinus-Nijhoff, The Hague, 1982).

14. I.N. Sneddon and M. Lowengrub, *Crack Problems in the Classical Theory of Elasticity* (Wiley, New York, 1969).
15. M.K. Kassir and G.C. Sih, *Three-Dimensional Crack Problems: A New Selection of Crack Solutions in Three-Dimensional Elasticity* (Mechanics of Fracture, Vol. 2, Noordhoff, 1975).
16. M.K. Kassir and G.C. Sih, "Three-Dimensional Stress Distribution Around an Elliptical Crack Under Arbitrary Loading," *J. Appl. Mech.* **33**, 601-611 (1966).
17. J.R. Willis, "The Stress Field Around an Elliptical Crack in an Anisotropic Medium," *Int. J. Eng. Sci.* **6**, 253-263 (1968).
18. L.M. Keer and T. Mura, "Stationary Crack and Continuous Distribution of Dislocations," Proc. 1st Intl. Conf. Fracture I, 1966, pps. 99-115.
19. H. Sekine and T. Mura, "The Elastic Field Around an Elliptical Crack in an Anisotropic Medium Under an Applied Stress of Polynomial Forms," *Int. J. Eng. Sci.* **17**, 641-649 (1979).
20. F. Erdogan and G. Gupta, "The Stress Analysis of Multi-Layered Composites with a Flaw," *Int. J. Solids Struc.* **7**, 39-61 (1971).
21. F. Kroupa, "Circular Edge Dislocation Loop," *Czech. J. Phys.* **B10**, 284-293 (1960).
22. J. Bastecka, "Interaction of Dislocation Loop with Free Surface," *Czech. J. Phys.* **B14**, 430-442 (1964).
23. H.-Y. Yu, "Some Interactions Between Microstructure Defects," Ph.D. Dissertation, University of Rochester, 1977.
24. I.N. Sneddon, *Fourier Transforms* (McGraw Hill, New York, 1951).
25. R.D. Mindlin, "Force at a Point in the Interior of a Semi-Infinite Solid," *Midwestern Conf. Solid Mech.*, 1953, pp. 56-59.
26. J.C.M. Li, "Physical Chemistry of Some Microstructural Phenomena," *Met. Trans.* **9A**, 1353-1380 (1978).