

DTIC FILE COPY

4

AD-A199 642

OFFICE OF NAVAL RESEARCH
CONTRACT NO. N00014-86-K-0772
TECHNICAL REPORT NO. 24

X-Ray Diffraction Studies of Homologous Series of
4-Alkyl-4' Cyanostilbene

by

Sarama Bhattacharjee and Leonid V. Azaroff

Liquid Crystalline Polymer Research Center
University of Connecticut
Storrs, CT 06268

DTIC
SELECTED
SEP 30 1988
S D

Published
in

Molecular Crystals and Liquid Crystals

September 26, 1988

REPRODUCTION IN WHOLE OR IN PART IS PERMITTED FOR ANY
PURPOSE OF THE UNITED STATES GOVERNMENT.

THIS DOCUMENT HAS BEEN APPROVED FOR PUBLIC RELEASE
AND SALE; ITS DISTRIBUTION IS UNLIMITED.

88 9 30 051

REPORT DOCUMENTATION PAGE

1a REPORT SECURITY CLASSIFICATION Unclassified		1b RESTRICTIVE MARKINGS None	
2a SECURITY CLASSIFICATION AUTHORITY		3 DISTRIBUTION/AVAILABILITY OF REPORT Approved for Public Release, Distribution Unlimited	
3b DECLASSIFICATION/DOWNGRADING SCHEDULE		4 PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report No. 24	
4 PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report No. 24		5 MONITORING ORGANIZATION REPORT NUMBER(S)	
6a NAME OF PERFORMING ORGANIZATION University of Connecticut	6b OFFICE SYMBOL (if applicable)	7a NAME OF MONITORING ORGANIZATION Office of Naval Research	
6c ADDRESS (City, State, and ZIP Code) Storrs, CT 06268		7b ADDRESS (City, State, and ZIP Code) 800 North Quincy Avenue Arlington, VA 22217	
8a NAME OF FUNDING/SPONSORING ORGANIZATION	8b OFFICE SYMBOL (if applicable) ONR/DARPA	9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-86-K-0772	
8c ADDRESS (City, State, and ZIP Code) 800 North Quincy Avenue Arlington, VA 22217		10 SOURCE OF FUNDING NUMBERS	
		PROGRAM ELEMENT NO	PROJECT NO
		TASK NO	WORK UNIT ACCESSION NO
11 TITLE (Include Security Classification) "X-Ray Diffraction Studies of Homologous Series of 4-Alkyl-4' Cyanostilbene" (Unclassified)			
12 PERSONAL AUTHOR(S) Sarama Bhattacharjee and Leonid V. Azaroff			
13a TYPE OF REPORT Interim Technical	13b TIME COVERED FROM TO 09/23/88	14 DATE OF REPORT (Year, Month, Day) 1988/09/23	15 PAGE COUNT 11
16 SUPPLEMENTARY NOTES Published in <u>Molecular Crystals and Liquid Crystals</u> , 144, pgs. 317-322 (1987) LCPRC86-4 (LCPRC Publication No.)			
17 COSATI CODES		18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB GROUP	
			4-alkyl-4'-cyanostilbene, moving film technique, X-ray diffraction, smectic, partial bilayer nematic. (A) (V)
19 ABSTRACT (Continue on reverse if necessary and identify by block number) Various members of the series 4-alkyl-4'-cyanostilbene (n=4,...11) have been examined by x-ray diffraction using monodomain samples aligned in .2 T magnetic field. A moving*film technique has been employed with Fe K radiation (=1.937 A) to record the zero level and upper levels in reciprocal space. Lower members (n=4,5,6) form only a nematic phase; higher members (n=10,11) form only a smectic-A phase; while intermediate members (n=7,8,9) form both nematic and smectic-A phases. The equatorial reflections were used to establish effective side-chain separations while meridional reflections permitted the calculation of effective molecular lengths and layer thickness, respectively, in the nematic and smectic phases. These were found to be longer than the calculated molecular length in its most extended conformation. For the smectic-A phases, this implies some type of bilayer structure like that reported for other liquid-crystal compounds having polar end groups.			
20 DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS		21 ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a NAME OF RESPONSIBLE INDIVIDUAL Dr. Kenneth J. Wynne		22b TELEPHONE (Include Area Code) (202) 696-4410	22c OFFICE SYMBOL ONR

X-RAY DIFFRACTION STUDIES OF HOMOLOGOUS SERIES OF 4-ALKYL-4' CYANOSTILBENE

Sarama Bhattacharjee and Leonid V. Azaroff

Institute of Materials Science

University of Connecticut

Storrs, CT 06268


Various members of the series 4-alkyl-4'-cyanostilbene ($n=4, \dots, 11$) have been examined by x-ray diffraction using monodomain samples aligned in .2 T magnetic field. A moving-film technique has been employed with Fe K α radiation ($\lambda=1.937 \text{ \AA}$) to record the zero level and upper levels in reciprocal space. Lower members ($n=4, 5, 6$) form only a nematic phase; higher members ($n=10, 11$) form only a smectic-A phase; while intermediate members ($n=7, 8, 9$) form both nematic and smectic-A phases. The equatorial reflections were used to establish effective side-chain separations while meridional reflections permitted the calculation of effective molecular lengths and layer thickness, respectively, in the nematic and smectic phases. These were found to be longer than the calculated molecular length in its most extended conformation. For the smectic-A phases, this implies some type of bilayer structure like that reported for other liquid-crystal compounds having polar end groups.

Key Words: 4-alkyl-4'-cyanostilbene, x-ray diffraction smectic, nematic, moving-film technique, partial bilayer.

INTRODUCTION

It has been known for some time that certain cyano derivatives form smectic-A phases in which the layer spacing d , as measured by x-ray or neutron diffraction, is considerably larger than the molecular length^{1,2}.

In order to investigate whether other cyano compounds show the same behavior, an x-ray diffraction study was undertaken using compounds in the series 4-alkyl-4'-cyanostilbene:



where n ranges from $n=4$ to $n=11$.

EXPERIMENTAL PROCEDURE

The compounds of the homologous series of 4-alkyl-4'-cyanostilbene (alkyl chain length $n=9$ to 11) had been synthesized by Cox et al.³ and were used without further purification.

The x-ray measurements were performed using a Buerger precession camera equipped with a magnet ($H=2$ T) and heating arrangement⁴. The samples were placed in Lindemann-glass capillaries having square (1 mm^2) cross sections oriented at right angles to the magnetic field lines and the incident x-ray beam (at the zero camera setting). The temperature of the sample was maintained within $\pm 2^\circ\text{C}$ as determined by a thermocouple placed adjacent to the sample. Mn-filtered Fe radiation ($\lambda=1.937 \text{ \AA}$) was used to obtain optimal dispersion of the diffraction maxima which were recorded on a flat film using Laue as well as precession geometry. The centers of the diffraction maxima were determined by a film reader (as well as by locating their maximum optical densities with a Quantimet image analyzer.)

RESULTS AND DISCUSSION

The transition temperatures of 4-alkyl-4'-cyanostilbenes are listed in Table 1. X-ray diffraction (Laue) photographs typical of magnetically aligned nematic and smectic-A phases are reproduced in Fig. 1. The smectic layer spacings d and the intermolecular distances along the director in the nematic phase were calculated from the inner reflections along the meridian using the Bragg equation. These measured d values

are listed in Table 2 as are the side-to-side spacings D ($=1.155 \lambda/2 \sin \theta$) calculated by assuming short-range order (hexagonal) packing.⁵ For comparison purposes, Table 2 also lists the molecular length L calculated in its most extended conformation, projected on the axis of minimum moment of inertia, using standard bond lengths, angles, and Van-der-Waal's radii.

Several features are noteworthy. The interlayer spacings d for the smectic-A phases having $n = 9, 10$, and 11 are about 50% longer than the calculated molecular lengths L . (Column headed d/L in Table 2.) This has been observed previously⁶ for compounds having polar end groups and can be explained by assuming a bilayer molecular array. It is noteworthy that d/L declines slightly but progressively as the molecular length (n) shortens, suggesting a lessening in the parallelism of adjacent molecules. A corresponding increase in the average side-to-side spacing D is more difficult to discern because of the breadth of the equatorial arcs.

The mean incremental length of the inter-layer spacing is 1.05 \AA per methyl group added which suggests that the methyl chain forms an angle of 34° with the long axis of the rigid core. This can be compared to 28° for *p*-*n*-alkoxybenzoic acid,⁷ 30° for *p*-*n*-alkoxycinnamic acid,⁸ and 29° for 4,4' di-*n*-alkyl azoxybenzene.⁹ Since these compounds have symmetrical alkyl chains on both sides of the aromatic core, the following model emerges for the smectic-A phases studied here. The aromatic cores pack with their long axis nearly normal to the smectic layers. The alkyl tails form an angle of 34° with this axis but are free to rotate about the layer normal. The relatively sharp meridional reflection 001 and the absence of higher-order 00 l reflections suggests a highly regular (planar) array of the rigid cores but a considerably less

regular electron density distribution at the inter-layer boundaries. The relatively large amount of arcing and the breadth of the equatorial reflection, plus the total absence of higher-order reflections, strongly supports a rather 'loose' short-range order among the parallel molecules having chains pointing in opposite directions. (The diffraction photographs in Fig. 1 have cylindrical symmetry about the magnetic field direction as verified by upper-level precession photographs.)

The dimeric alignment of parallel neighbors having oppositely directed alkyl chains appears to persist in the nematic phase as well. In fact, the existence of an inner reflection along the meridian (Fig. 1b) clearly indicates a long-range correlation of nearly parallel dimers along the nematic director. There is no side-to-side correlation (layering) and, again, the electron density distribution along the director is fairly periodic for the aromatic cores and less so for the terminal portions (alkyl tails) since higher-order reflections are totally absent. The disk-like intensity distribution about the 001 reciprocal-lattice point is what one expects from parallel periodic chains having no interchain correlations.¹¹ The d/L ratio (Table 2) in the nematic phases declines slightly from that in the smectic phases due to the 'looseness' of the nematic packing but provides supporting evidence for the relatively high degree of alignment attained.

Acknowledgements

The authors express their profound thanks to Dr. Robert J. Cox for providing the liquid crystal compounds used in this study.

Literature

1. J. E. Lydon and C. J. Coakley, *J. Physique Colloq.* 36, C1-45 (1975).
2. W. L. McMillan, *Phys. Rev.* A7, 1419 (1973).
3. R. J. Cox and N. J. Ciecak, *Mol. Cryst. Liq. Cryst.* 37, 263 (1976).
4. L. V. Azaroff and C. A. Schuman, *Mol. Cryst. Liq. Cryst.* 22, 309 (1985).
5. A. de Vries, *Mol. Cryst. Liq. Cryst.* 131, 125 (1985).
6. A. J. Leadbetter, J. C. Frost, J. P. Gaughan, G. W. Gray and A. Mosely, *J. Physique*, 40, 375 (1979).
7. A. Blumstein and L. Patel, *Mol. Cryst. Liq. Cryst.* 48, 151 (1978).
8. R. F. Bryan, A. J. Leadbetter, A. I. Mehta and P. A. Tucker, *Mol. Cryst. Liq. Cryst.* 104, 257 (1984).
9. E. H. Pape, *Mol. Cryst. Liq. Cryst. Lett.* 102, 271 (19).
10. G. V. Vani and K. Vijayan, *Mol. Cryst. Liq. Cryst.* 42, 249 (1977).
11. W. W. Adams, L. V. Azaroff and A. K. Kulshreshtha, *Z. Kristallogr.* 150, 321 (1979).

Table 1

Transition temperatures³ between crystal (C), smectic-A (S_A), nematic (N), and isotropic liquid (I) phases.

(In deg. C with a dash indicating absence and a dot presence of phase.)

n	C	S_A	N	I
4	. 70.5	--	.	82.3 .
5	. 55.1	--	.	101.0 .
6	. 51.2	--	.	86.1 .
7	. 59.5	. 64.6	.	95.0 .
8	. 51.1	. 78.7	.	89.4 .
9	. 56.2	. 94.4	.	96.7 .
10	. 47.2	. 95.1	--	.
11	. 65.5	. 100.2	--	.

Table 2

Comparison of measured and calculated spacings

n	d	L	d/L	D
4	26.77 Å	19.34 Å	1.38	5.16 Å
5	28.76	20.39	1.41	5.09
6	31.04	21.44	1.45	5.13
7	(32.39)*	22.49	--	--
8	(34.49)*	23.54	--	--
9	36.59	24.59	1.49	5.12
10	38.78	25.64	1.51	5.10
11	40.82	26.69	1.53	5.18

*Since samples for $n = 7$ and 8 were not available, these values were interpolated assuming an incremental length of 1.05 \AA per CH_2 group added.

Figure Legends

Fig. 1. Normal-beam x-ray diffraction photographs of magnetically aligned 4-nonyl-4'-cyanostilbene. (Crystal monochromatized Fe $K\alpha$ radiation.)

- a. Nematic phase (hexyl).
- b. Smectic-A phase (nonyl).

D/1113/87/2

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 1113 800 N. Quincy Street Arlington, Virginia 22217-5000	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Duda Naval Weapons Support Center Code 50C Crane, Indiana 47522-5050	1	Naval Weapons Center Attn: Dr. Ron Atkins Chemistry Division China Lake, California 93555	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko, Code LS2 Port Hueneme, California 93401	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12 high quality	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
DTNSRDC Attn: Dr. H. Singerman Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375-5000	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1