

Distribution List for Annual and Final Reports

AD-A210 507

- 1. Put a cover page (Form DD 1473) on your report and attach a copy of the distribution list. Mail one copy of the report to each person on the contractor subset list attached on which your name appears. The other subset list is for your information only. Please don't forget to attach this distribution list to your report - otherwise the folks below think they have mistakenly received the copy meant for the Molecular Biology Program and forward it to us.

Mail two copies to (include a DTIC Form 50 with these two copies too)

Administrator
 Defense Technical Information Center
 Building 5, Cameron Station
 Alexandria, VA 22314

Mail one copy to each of the following:

- Dr. Michael Marron (e) Director
 ONR Code 1141 Chemical and Biological Sci Div
 Molecular Biology Program Army Research Office
 800 N. Quincy Street P. O. Box 12211
 Arlington, VA 22217-5000 Research Triangle Park, NC 27709
- (b) Administrative Contracting Officer (f) Life Sciences Directorate
 ONR Resident Representative Air Force Office of Scientific Research
 (address varies - see copy of your grant) Bolling Air Force Base
 Washington, DC 20332
- (c) Director, (g) Director
 Applied Research Directorate Naval Research Laboratory
 ONR Code 12 Technical Information Div, Code 2627
 800 N. Quincy Street Washington, DC 20375
 Arlington, VA 22217-5000
- (d) Director
 Office of Naval Technology
 Code 22
 800 N. Quincy Street
 Arlington, VA 22217-5000

DTIC
 DTIC FILE COPY
 01 03 1989
 D

5

REPORT DOCUMENTATION PAGE				Form Approved OMB No 0704-0188	
1a REPORT SECURITY CLASSIFICATION (U)			1b RESTRICTIVE MARKINGS NA		
2a SECURITY CLASSIFICATION AUTHORITY NA			3 DISTRIBUTION / AVAILABILITY OF REPORT Distribution Unlimited		
2b DECLASSIFICATION / DOWNGRADING SCHEDULE NA			4 PERFORMING ORGANIZATION REPORT NUMBER(S) NA		
6a NAME OF PERFORMING ORGANIZATION University of South Alabama			6b OFFICE SYMBOL (If applicable) NA	7a NAME OF MONITORING ORGANIZATION Office of Naval Research	
6c ADDRESS (City, State, and ZIP Code) Department of Biological Sciences Mobile, AL			7b ADDRESS (City, State, and ZIP Code) 800 N. Quincy Street Arlington, VA 22217-5000		
8a NAME OF FUNDING / SPONSORING ORGANIZATION Office of Naval Research		8b OFFICE SYMBOL (If applicable) ONR	9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-88-K-0428		
8c ADDRESS (City, State, and ZIP Code) 800 N. Quincy Street Arlington, VA 22217-5000			10 SOURCE OF FUNDING NUMBERS	PROGRAM ELEMENT NO 61153N	PROJECT NO RR04106
				TASK NO 4412050	WORK UNIT ACCESSION NO
11 TITLE (Include Security Classification) (U) Polypeptide Inhibitors of Mineral Scaling and Corrosion					
12 PERSONAL AUTHOR(S) Sikes, C. Steven, Wheeler, A.P., and Little, Brenda J. (B.J.L., NORDA, NSTL, MS)					
13a TYPE OF REPORT Annual		13b TIME COVERED FROM 7/88 TO 6/89		14 DATE OF REPORT (Year, Month, Day)	15 PAGE COUNT
16 SUPPLEMENTARY NOTATION					
17 COSATI CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD 06	GROUP 03	SUB-GROUP	Polypeptide, peptide, scaling, corrosion, inhibitors, calcium carbonate, calcium phosphate		
19 ABSTRACT (Continue on reverse if necessary and identify by block number) <p>In the first year of the project, the work has been focused on 1) synthesis of polypeptides, 2) evaluation of their activities as inhibitors of calcium carbonate and phosphate crystallization, and 3) measurement of their activities as inhibitors of corrosion of mild steel. A set of polyaspartate molecules of specific molecular sizes and other aspartate-enriched peptides were made by automated solid phase methods. Polyaspartate molecules with 1 to 3 serine residues at the N-terminus were phosphorylated post-synthesis using monochlorophosphoric acid. The polyaspartate molecules were very effective inhibitors of calcium carbonate but not calcium phosphate crystallization. Polyaspartate was most effective as an inhibitor of CaCO₃ crystal growth at a length of about 15 residues, but a length of about 35 residues was required for maximum inhibition of crystal nucleation.</p> <p>The polyaspartate molecules with terminal phosphoserine residues were extra-</p>					
20 DISTRIBUTION / AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21 ABSTRACT SECURITY CLASSIFICATION (U)		
22a NAME OF RESPONSIBLE INDIVIDUAL M. Marron			22b TELEPHONE (Include Area Code) 202-696-4760	22c OFFICE SYMBOL ONR	

ordinarily active inhibitors of both calcium carbonate and phosphate formation. A thermal method of synthesis of polyaspartate based on peptide bond formation in dry powders of aspartic acid at around 200°C was developed to produce larger sample sizes required in corrosion experiments. Bulk thermal polyaspartate at 0.1 mg/ml ennobled the corrosion potential of mild steel electrodes somewhat with a reduction in corrosion rate from about 7 to 2 milli-inches per year. By use of scanning electron microscopy, the polyaspartate was seen to be bound to electrode surfaces after brief exposures, where it appeared to inhibit both anodic and cathodic reactions at doses used in practice for corrosion inhibition.

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution	
Availability Codes	
Avail and/or	
Dist	Special
A-1	



DATE: 1 July 1989

ANNUAL REPORT

CONTRACT: N00014-88-k-0428

R&T CODE: 4412050

PRINCIPAL INVESTIGATOR: C. Steven Sikes

CO-INVESTIGATORS: A.P. Wheeler and Brenda J. Little

CONTRACTOR: The University of South Alabama

CONTRACT TITLE: Polypeptide Inhibitors of Mineral Scaling and Corrosion

START DATE: 1 July 1988

RESEARCH OBJECTIVES:

The overall purpose of the project is to understand better the interactions of peptide inhibitors of mineral scaling and corrosion with metal surfaces, including relationships between mineral deposition and corrosion. The peptides are based on natural protein inhibitors of mineral formation and generally are enriched in aspartic acid and phosphoserine. Specifically, the project involves 1) synthesis of polypeptides, 2) evaluation of their activities as inhibitors of calcium carbonate and phosphate crystallization, and 3) evaluation of their activities as inhibitors of corrosion of mild steel.

PROGRESS (YEAR 1):

Synthesis of Polypeptides.

Automated solid-phase synthesis. A peptide synthesizer (Applied Biosystems, Model 430A) was used to prepare peptides. A family of polyaspartate molecules ranging in size from Asp₅ to Asp₆₀ was synthesized by repetitive couplings of t-Boc-L-aspartic acid residues with B-carboxyl protection by O-benzyl linkage. A C-terminal residue of 0.5 mmole was preloaded on a resin of a polymer of styrene cross-linked with 1% of divinylbenzene. The C-terminal amino acid was linked to the resin via a phenylacetamidomethyl (PAM) group. Peptide bond formation was promoted by use of dicyclohexyl carbodiimide (DCC) and formation of symmetric anhydrides of the incoming amino acid. At the appropriate times during a synthesis, a subsample of the peptide-resin was taken to provide the desired size of the polyaspartate, then the synthesis was allowed to continue to produce the next larger size, and so forth until all desired sizes had been synthesized and collected.

The same procedure was followed in synthesizing a family of aspartate₁₅ alanine_x molecules ranging from Asp₁₅Ala₂ to Asp₁₅Ala₁₀. In this case, t-Boc-L-alanine residues were used. For peptides containing serine or glycine residues, t-Boc-L-serine-O-benzyl and t-Boc-L-glycine were used.

In all cases, coupling efficiency of each residue was checked by automated sampling of peptide resin for measurement of unreacted free amine by the ninhydrin method. Coupling efficiencies routinely were greater than 99% per cycle of synthesis.

Following synthesis, peptide-resin was repeatedly washed with methanol then dried and weighed. Then peptides were cleaved from the resin using a modification of the trifluoromethyl sulfonic acid (TFMSA) procedure, with precautions taken to prevent aspartimide formation. For 100 mg samples, peptide-resins in a scintillation vial were treated for 10 minutes with 150ul of anisole to swell the resin, making it more accessible for reaction. Then 1.0 ml of neat trifluoroacetic acid (TFA) was added with magnetic stirring and allowed to react for 10 minutes. Next, 100 ul of concentrated TFMSA (Aldrich Chemical Co.) were added with cooling using an ice bath, followed by cleavage of the peptide from the resin at room temperature for 30 minutes. For cleavage of other amounts of peptide-resin, the amounts of reagents used were changed proportionally.

Following cleavage, 20 ml of methyl butyl ether (MBE) (Aldrich) were added to the vial to insure precipitation of the peptide, which already was relatively insoluble in the acidic reaction medium due to the acidic nature of the peptides. After stirring for 1-2 minutes, the entire slurry was passed through a 4.25 cm glass fiber filter (Fisher G4) using a filter funnel and vacuum pump at 15 psi. This removed the TFA, TFMSA, anisole, and any soluble reaction products, leaving the cleaved peptide and resin on the filter. After washing on the filter with 100 ml of MBE, the peptide was extracted into a clean, dry flask with 10 ml of Na_2CO_3 (0.02 M, pH 10.2), using 5 successive rinses of 2 ml, with at least 1 minute extraction on the filter prior to applying the vacuum each time. Using this procedure, the filtrate containing the solubilized peptides had pH values >5 . The filtrate was then dialyzed twice with stirring against 2 liters of distilled water for 2 hours using dialysis tubing (Spectrapor, nominal MW cutoff of 1000 daltons). The dialysate was frozen and lyophilized, yielding white flakes or powders. The average yield of the peptides was 40%.

Following isolation, purity of the peptides was checked by high performance liquid chromatography (Varian 5500 LC) using gel permeation columns designed for separations of peptides (Toya Soda 2000 SW and 3000 PWXL). Single, sharp peaks at the appropriate MW were obtained. Because the peptides were isolated partially as sodium salts, the sodium content was determined by atomic absorption (Perkin Elmer model 360). Sodium levels typically were less than 5% by weight. Amounts of peptides reported were corrected for sodium content. Concentrations of peptides in aqueous stock solution were based on lyophilized dry weight but were also checked by comparison of UV spectra.

Post-synthesis phosphorylation. Because phosphate linkages to proteins are not stable during cleavage steps of solid-phase synthesis and because phosphate is known to be critical to the activity of the protein inhibitors of mineral formation, we evaluated several methods of preparation of phosphopeptides. These included direct polymerization of

phosphoserine by use of DCC, and phosphorylation of polyserine by use of diphenyl phosphochloridate followed by catalytic hydrogenolysis to remove phenyl protecting groups. Both of these approaches gave unsatisfactory results. However, a successful method based on the use of monochlorophosphoric acid was employed, with production of peptides with essentially 100% phosphorylation of serine residues.

In this approach, serine residues attached at the N-terminus of polyaspartate molecules were phosphorylated manually using the following procedure and in proportions consistent with the molar amounts of serine residues. For example, phosphorus oxychloride, POCl_3 , was added as 117 ml (1.25 moles) to 45 ml (2.5 moles) of water. This solution was stirred for one hour, allowing formation of monochlorophosphate (ClH_2PO_3). Next, an amount of peptide to provide 0.25 moles of serine residues was added with stirring and occasional heating at 60°C for two hours. The reaction was ended by dropwise addition of 18 ml (1 mole) of H_2O to degrade any unreacted monochlorophosphate to orthophosphate. Any polyphosphates that may have formed during the reaction were destroyed by addition of 75 ml of 1N HCL and heating in a boiling water bath for at least 20 minutes. Upon cooling, peptides were crystallized in 95 percent ethanol and methyl butyl ether at 3°C overnight. Crystals were washed repeatedly with ethanol. The extent of phosphorylation of peptides was monitored spectrophotometrically upon formation of the phosphomolybdate complex.

Thermal polymerization. Because the measurements of activity of the peptides as corrosion inhibitors, as well as other procedures, including pilot-scale studies in some cases, require relatively large amounts of materials (from 1 gram on up) and because available solid-phase synthesis becomes prohibitively expensive at that level, we looked into the feasibility of bulk thermal polymerization of aspartic-enriched polyamino acids. This approach to polypeptide synthesis originated in the study of the possible abiotic origin of proteins.

In a typical synthesis, L-aspartic acid (500 g) was placed in a two-liter, round-bottom reaction vessel, originally designed as the evaporator vessel in a rotary evaporator apparatus. The reaction vessel was partially submerged in cooking oil in a deep-fryer set at $190^\circ\text{C}/(+2^\circ\text{C})$. The reaction vessel was coupled by ground glass fitting to a condenser vessel, which in turn was fitted to a rotator shaft driven by a rheostated electric motor. The fittings were sealed with tape and fastened with hose clamps. A stream of nitrogen was continuously purged into the condenser vessel to eliminate O_2 and the possibility of charring. The reaction was allowed to continue for up to 24 hours at which time no further visible evolution of water vapor was observed. The water is produced as a result of the dehydration reaction of peptide bond formation and serves as a good indicator of the progress of the reaction.

Polyaspartate molecules of approximately 5000 daltons (determined by gel permeation) were produced. They were purified by dissolving at pH 6 in water followed by dialysis to remove unreacted aspartic acid, although the bulk product is also usable without further purification.

Samples as large as 1 kilogram were prepared essentially at the cost of the amino acids (e.g., Sigma L-aspartic acid, \$25.70/kg). A number of interesting materials were produced.

Assays to verify the identity of each of the molecules produced by both solid-phase and thermal methods included amino acid analysis, peptide sequencing studies, amine measurement by alkalimetric titration and ninhydrin reaction, carboxyl measurement by alkalimetric titration, phosphate analysis, and ultraviolet and infrared spectroscopy.

Evaluation of Polypeptides Enriched in Aspartic Acid and Phosphoserine as Inhibitors of Crystallization.

A number of assays have been developed to measure the ability of the peptides to inhibit mineral formation. These include methods for assessing effects on both crystal nucleation and crystal growth. The general results were that at a molecular size of about 15 residues, polyaspartate was most effective as an inhibitor of CaCO_3 crystal growth. However, the optimum size for inhibition of CaCO_3 crystal nucleation by polyaspartate was about 35 residues. In addition, the presence of an hydrophobic domain of alanine residues attached at the N-terminus of polyaspartate molecules of 15 residues enhanced the effectiveness of the molecules as inhibitors of crystal nucleation relative to control polyaspartates of appropriate sizes. This type of data is useful in formulating hypotheses about the nature of the crystal nuclei and the crystal growth sites and in designing effective inhibitors.

Perhaps the most interesting discovery of the past year was the remarkable positive effect that even a single phosphoserine residue can have on the activity of a polyaspartate as an inhibitor of crystallization. For example, as shown in Figure 1, the polyaspartate molecules that had one to three phosphoserine residues on the end were far more effective inhibitors of CaCO_3 formation as indicated by the length of time prior to crystallization, shown by stabilization of pH of the metastable solution at about pH 8.3. Note also that the most effective molecule measured was $\text{HO}-(\text{Asp})_{20}-(\text{pSer})_1\text{-H}$ followed by $\text{HO}-(\text{Asp})_{20}-(\text{pSer})_3$ and $\text{HO}-(\text{Asp})_{20}-(\text{pSer})_2\text{-H}$. Thus, surprisingly, a single phosphoserine residue at the end of the molecule was the best arrangement, and adding more phosphoserines diminished the activity of the molecules.

Similarly, as seen in Figure 2, the polyaspartate molecules having one to three phosphoserine residues on the end were by far the most effective as inhibitors of calcium phosphate formation. In these experiments, $\text{HO}-(\text{Asp})_{20}-(\text{pSer})_2\text{-H}$ was clearly the most effective molecule, followed by $\text{HO}-(\text{Asp})_{20}-(\text{pSer})_1\text{-H}$, with $\text{HO}-(\text{Asp})_{20}-(\text{pSer})_3\text{-H}$ having much less activity, although still considerably more than simple $\text{HO}-(\text{Asp})_{20}\text{-H}$ or $\text{HO}-(\text{Asp})_{25}\text{-H}$ molecules. However, as shown in Table 1, the serine residues of the $\text{HO}-(\text{Asp})_{20}-(\text{pSer})_3\text{-H}$ molecules were incompletely phosphorylated due to limitations of the method of phosphorylation. In any event, it is clear that having one or two phosphoserine residues at the end of a polyanionic peptide greatly enhances inhibitory activity, and in all cases the presence of phosphoserine improved the performance of peptides as inhibitors of crystallization. Furthermore, the polyaspartate-phosphoserine molecules are among the best known inhibitors of both calcium carbonate and calcium phosphate crystallization. This breadth of activity is itself unusual.

Figure 1. Effects of Phosphorylation of Synthetic, Polyanionic Peptides on Calcium Carbonate Crystallization.

In all cases, the concentration of peptides was 0.05 ug/ml.

In these experiments, a solution supersaturated with respect to CaCO_3 is prepared by separately pipetting 0.3 ml of 1.0 M CaCl_2 dihydrate and 0.6 ml of 0.4 M NaHCO_3 into 29.1 ml of artificial seawater (0.5 M NaCl , 0.011 M KCl). Inhibitors normally are added after the calcium but before the bicarbonate. The reaction vessel is a 50 ml, 3-necked, round-bottom flask partially immersed in a thermostated water bath at 20°C. The reaction vessel is closed to the atmosphere to minimize exchange of CO_2 . The reaction is started by adjusting the pH upward to 8.3 by titration of μl amounts of 1 N NaOH by digital pipette. The initial concentrations are 10 mM of Ca^{2+} and 8 mM of dissolved inorganic carbon (DIC). The reaction is monitored by pH electrode and recorded by strip chart. After a period of stable pH during which crystal nuclei form, the pH begins to drift downward until the reaction ceases due to depletion of reactants and the lowering of pH.




Figure 2. Effects of Phosphorylation of Synthetic, Polyanionic Peptides on Calcium Phosphate Crystallization.

In all cases, the concentration of the peptides was 30 ug/ml.

A solution supersaturated with respect to calcium phosphate is prepared by separately pipetting 0.1 ml of 1.32 M CaCl_2 dihydrate and 0.1 ml of 0.90 M NaH_2PO_4 into 29.8 ml of distilled water. This yields initial concentrations of 4.4 mM Ca^{2+} and 3.0 mM dissolved inorganic phosphorus (DIP). Inhibitors normally are added after the calcium but before the phosphate. The reaction vessel is a 50 ml, round-bottom, 3-necked flask partially immersed in a thermostated water bath at 20°C. The reaction vessel is closed to the atmosphere. The reaction begins upon mixing the reactants with an initial pH of 7.4.




Table 1. Comparison of phosphorylated and non-phosphorylated serine-containing peptides as inhibitors of calcium carbonate and phosphate formation.

Peptide	%Ser as PSer	Calcium Carbonate Assay ^a		Calcium Phosphate Assay ^b	
		(ug/ml)	Induction Period (minutes)	(ug/ml)	Period to Apatite formation (minutes)
Control			5.86 ± 0.76 ^c		20.7 ± 2.09 ^c
PolySer(mw5100)		0.05	4.00 ± 0.28	10	same as control
PolyPSer	23.0	0.05	113 ± 50.6	10	33.5 ± 8.74
(AspSerGly) ₁₀		0.10	9.10 ± 1.20	10	same as control
(AspPSerGly) ₁₀	30.0	0.10	7.50 ± 2.10	10	28.0 ± 1.70
(AspSer) ₁₀		0.05	33.5 ± 2.12	10	same as control
(AspPSer) ₁₀	29.0	0.05	205 ± 14.4	10	31.0 ± 2.80
Asp ₂₀		0.05	87.5 ± 19.0	30	59.7 ± 6.40
Asp ₂₀ Ser		0.05	65.0 ± 11.1	30	47.3 ± 3.05
Asp ₂₀ ^{PSer}	97.6	0.05	583 ± 5.80	30	601 ± 103
Asp ₂₀ Ser ₂		0.05	48.8 ± 16.2	30	54.5 ± 3.50
Asp ₂₀ ^{PSer} ₂	99.8	0.05	254 ± 39.9	30	> 20 hours
Asp ₂₀ Ser ₃		0.05	31.3 ± 11.1	30	53.0 ± 0.75
Asp ₂₀ ^{PSer} ₃	59.0	0.05	326 ± 88.0	30	185 ± 9.30

a. CaCO₃ pH-drift assay: 10mM Ca²⁺, 8mM dissolved inorganic carbon, 30ml artificial seawater, 20°C., initial pH = 8.30.

b. CaPO₄ pH-drift assay: 4.4mM Ca²⁺, 3mM dissolved inorganic phosphorus, 30 ml distilled water, 20°C., initial pH = 7.40.

c. Mean values ± standard deviations, n = 3 to 70.

Evaluation of Thermal Polyaspartate as a Corrosion Inhibitor.

A sample of polyaspartate prepared by the thermal polycondensation reaction was chosen for the initial measurements of corrosion inhibition. Because a single experiment of this type may require up to 1 gram of material, and we had 100's of grams of thermal polyaspartate, it was sensible to use this material in these studies. In addition, the results for a generic polyaspartate can serve as a basis for comparison to results for other molecules.


At a dose of 0.1 mg/ml of bulk thermal polyaspartate, which for this sample was equivalent to about 40 ug/ml of pure thermal polyaspartate, the corrosion potential of mild steel electrodes was ennobled somewhat (Figure 3). This was accompanied by a reduction in corrosion current from about 17 to 5 microamps per cm^2 , which translated to a reduction in corrosion rate from about 7 to 2 milliinches per year.

Scanning electron microscopy confirmed that the polyaspartate was bound to the surface of the electrode after brief exposures. Analysis by EDAX showed some calcium and chlorine associated with the polyaspartate.

The results to date demonstrate that the material is surface-reactive and appears to inhibit both anodic and cathodic reactions of mild steel surfaces at doses of polymers that are used in practice for corrosion inhibition.

Figure 3. The effect of thermal polyaspartate on the corrosion potential of a mild steel electrode.

The concentration of bulk thermal polyaspartate was 0.1 mg/ml in artificial seawater. Potentials were measured relative to a saturated calomel electrode.



Work Plan (Year 2):

A main objective is to evaluate the phosphopeptides as corrosion inhibitors. To do this, we will first have to prepare larger amounts of the materials by thermal polymerization, followed by derivatization. Because serine residues do not survive thermal synthesis, asparagine residues, which are thermally stable, will be added to provide a reactive NH_2 group as a site of phosphorylation or phosphonation.

We recently received support from the State of Alabama to purchase a corrosion monitoring system for the laboratory at South Alabama. With this instrument, we will be able to screen the corrosion inhibiting activity of experimental compounds, and then select the most promising for more detailed mechanistic studies by Dr. Little at the Naval Space Technology Laboratory.

We also plan to synthesize sulfopeptides by methods analogous to those for preparing phosphopeptides. The literature suggests that sulfate or sulfonate containing polymers may be very effective inhibitors.

A general goal of the project is to understand more about the relationships between mineral deposition and corrosion, including microbially-accelerated corrosion. To begin a study of these relationships, experiments are planned in which supersaturated, spontaneously mineralizing solutions are used with and without the presence of the peptides, which inhibit both mineral deposition and corrosion.

Similarly, experiments are scheduled in which corrosion-accelerating microbes will be present in the experimental solution, including calcifying bacteria in some cases. This will allow us to begin exploring the relationship between microbially-induced corrosion and mineral deposition.

Inventions (Year 1):

A United States patent application, "Inhibition of mineral deposition by phosphorylated and related polyanionic peptides" (serial #07/334,456), by C. Steven Sikes was filed on April 7, 1989. This application covers the materials themselves and their use as inhibitors of crystallization. As we develop the data on corrosion inhibition, we will need to prepare an application in that field of use.

Publications and Reports (Year 1):

We organized and hosted a symposium, "Surface reactive peptides and polymers," that was held in April 1989 in Dallas as part of the 197th national meeting of the American Chemical Society. Our work was presented along with 26 other papers, scheduled for publication as an ACS book. The booklet of abstracts is enclosed.

1. Little, Brenda J. and C. Steven Sikes. 1989. Corrosion inhibition by thermal polyaspartate. Abstract, ACS 197th annual meeting.

2. Sikes, C. Steven and M.L. Yeung. 1989. Peptides enriched in aspartate and phosphoserine as inhibitors of calcium carbonate and phosphate crystallization. Abstract, ACS 197th annual meeting.
3. Wheeler, A.P. and K.C. Low. 1989. CaCO₃ crystal-binding properties of polyanionic proteins and peptides. Abstract, ACS 197th annual meeting.
4. Sikes, C. Steven and A.P. Wheeler. 1990. Surface reactive peptides and polymers: from discovery to commercialization. ACS Books, in preparation.
5. Wheeler, A.P., C.S. Sikes, and K.C. Low. 1988. Absorption of oyster shell organic matrix synthetic analogs to calcium carbonate crystals. Abstract, American Zoologist 57, 133A.

Training Activities: The following students and post-doctoral associates have assisted in the project during year 1.

- | | | |
|----------------------|--------|--|
| 1. Donachy, Julie E. | Ph.D. | Research Associate |
| 2. Dickey, Joan | D.D.S. | Research Associate |
| 3. Yeung, Miranda | M.S. | Technologist, from Hong Kong |
| 4. Ding, Jane | B.S. | Surgeon from China working as a technologist |
| 5. Garris, John | B.S. | beginning M.S. student |

Women or minorities - 4

Non-citizens - 2 (1 from Hong Kong, 1 from China)

Awards/Fellowships: None.

AMZEL, L. Mario
Department of Biophysics
Johns Hopkins School of Medicine
725 North Wolfe Street
Baltimore, MD 21205

ANDERSEN, Niels H.
Department of Chemistry
University of Washington
Seattle, WA 98195

ARNOLD, Frances H.
Dept of Chemical Engineering
California Institute of Technology
Pasadena, CA 91125

AUGUST, J. Thomas
Department of Pharmacology
Johns Hopkins Medical School
725 North Wolfe Street
Baltimore, MD 21205

BEVERIDGE, David L.
Department of Chemistry
Wesleyan University
Hall-Altwater Laboratories
Middletown, CT 06457

BRAMSON, H. Neal
Department of Biochemistry
Univ of Rochester Medical Center
601 Elmwood Avenue
Rochester, NY 14642

BRUICE, Thomas C.
Department of Chemistry
University of California-Santa
Barbara
Santa Barbara, CA 93106

CASE, Steven T.
Department of Biochemistry
Univ of Mississippi Medical Center
2500 North State Street
Jackson, MS 39216-4505

CHANG, Eddie L.
Bio/Molecular Engineering
Naval Research Laboratory
Code 6190
Washington, D.C. 20375-5000

CHRISTIANSON, David W.
Department of Chemistry
University of Pennsylvania
231 South 34th Street
Philadelphia, PA 19104-6323

CORDINGLEY, John S.
Department of Molecular Biology
University of Wyoming
Box 3944 University Station
Laramie, WY 82071

DeGRADO, William F.
E. I. du Pont de Nemours & Co
Central R & D, Experimental Station
P. O. Box 80377
Wilmington, DE 19880-0328

EVANS, David R.
Department of Biochemistry
Wayne State Univ School of Medicine
540 E. Canfield Street
Detroit, Michigan 48201

FEIGON, Juli F.
Department of Chem & Biochemistry
UCLA
405 Hilgard Avenue
Los Angeles, CA 90024-1569

FICHT, Allison R.
Dept of Med Biochem & Genetics
Texas A&M University
College Station, TX 77843

FRAUENFELDER, Hans
Department of Physics
University of Illinois
Urbana, IL 61801

GABER, Bruce
Naval Research Laboratory
Bio/Molecular Engineering Branch
Code 6190
Washington, DC 20375

GETZOFF, Elizabeth D.
Scripps Clinic & Research Foundation
Department of Molecular Biology
10666 North Torrey Pines Road
La Jolla, CA 92037

GOODMAN, Eugene M.
Biomedical Research Institute
University of Wisconsin
P. O. Box 2000
Kenosha, WI 53141

HO, Pui Shing
Department of Biochemistry and
Biophysics
Oregon State University
Corvallis, OR 97331

HOGAN, Michael E.
Baylor Center for Biotechnology
4000 Research Forest Drive
The Woodlands, TX 77381

HONIG, Barry
Columbia University
Dept of Biochem and Molec Biophys
630 West 168th St.
New York, NY 10032

HOPKINS, Paul B.
Department of Chemistry
University of Washington
Seattle, WA 98195

KAHNE, Daniel
Department of Chemistry
Princeton University
Princeton, NJ 08544

KEMP, Robert G.
Chicago Medical School
Dept of Biological Chemistry
3333 Green Bay Rd.
North Chicago, IL 60064

KHORANA, Gobind H.
Department of Biology
MIT
77 Massachusetts Ave.
Cambridge, MA 02139

KIM, Sangtae
Chemical Engineering
University of Wisconsin
1415 Johnson Drive
Madison, WI 53706

LANSBURY, Peter T.
Department of Chemistry
MIT
Cambridge, MA 02139

LAURSEN, Richard A.
Chemistry Department
Boston University
590 Commonwealth Avenue
Boston, MA 02215

LENZ, Robert W.
Chemical Engineering Department
University of Massachusetts
Amherst, MA 01003

LEWIS, Randolph V.
Molecular Biology Department
University of Wyoming
University Station Box 3944
Laramie, WY 82071

LINDSAY, Stuart M.
Department of Physics
Arizona State University
Temp, AZ 85278

LOEB, George I.
David W. Taylor Research Center
Code 2841
Annapolis, MD 21402-5067

MASILAMANI, Divakar
Biotechnology Department
Allied-Signal Inc.
P. O. Box 1021R
Morristown, NJ 07960

McCONNELL, Harden M.
Stanford University
Department of Chemistry
Stanford, CA 94305

McELROY, William D.
Department of Chemistry
University of California - San Diego
La Jolla, CA 92093-0601

MERTES, Kristin Bowman
University of Kansas
Dept of Chemistry
Lawrence, Kansas 66045

NAGUMO, Mark
Bio/Molecular Engineering Branch
Naval Research Laboratory
Code 6190
Washington, DC 20375-5000

OLIVERA, Baldomero M.
Department of Biology
University of Utah
Salt Lake City, UT 84112

PABO, Carl O.
Department of Biophysics
Johns Hopkins University
School of Medicine
Baltimore, MD 21205

PRENDERGAST, Franklyn G.
Dept of Biochemistry & Molec Biol
Mayo Foundation
200 First St. SW
Rochester, MN 55905

PUGH, Jr., Edward N.
Department of Psychology
University of Pennsylvania
3815 Walnut Street
Philadelphia, PA 19104-6196

RACKOVSKY, Shalom R.
Department of Biophysics
University of Rochester
School of Medicine and Dentistry
Rochester, NY 14642

RAJAN, K. S.
Illinois Institute of Technology
Research Institute
10 W. 35th St.
Chicago, IL 60616

REINISCH, Lou
Laser Biophysics Center
Uniformed Services University
4301 Jones Bridge Road
Bethesda, MD 20814

RICH, Alexander
MIT Department of Biology
Cambridge, MA 02139

RICHARDS, J. H.
California Institute of Technology
Division of Chemistry and Chemical
Engineering
Pasadena, CA 91125

ROTHSCHILD, Kenneth J.
Department of Physics
Boston University
590 Commonwealth Avenue
Boston, MA 02215

SCHULTZ, Peter G.
Department of Chemistry
University of California-Berkeley
Bekeley, CA 94720

SEEMAN, Nadrian
Department of Chemistry
New York University
New York, NY 10003

SELSTED, Michael E.
UCLA
Dept of Medicine
37-055 CHS
Los Angeles, CA 90024

SIGMAN, David S.
UCLA School of Medicine
Dept of Biological Chemistry
Los Angeles, CA 90024
SIKES, Steven C.
Department of Biological Sciences
University of South Alabama
Mobile, AL 36688

SINSKEY, Anthony J.
Laboratory of Applied Microbiology
MIT Department of Biology
Cambridge, MA 02139

STEWART, James M.
Department of Chemistry
University of Maryland
College Park, MD 20742

STEWART, John M.
Department of Biochemistry
University of Colorado
Health Science Center
Denver, CO 80262

TURNER, Douglas H.
Department of Chemistry
University of Rochester
Rochester, NY 14627

URRY, Dan W.
Laboratory of Molecular Biophysics
University of Alabama
P. O. Box 311
Birmingham, AL 35294

WAITE, J. Herbert
College of Marine Studies
University of Delaware
Lewes, DE 19958

WARD, Keith B.
Naval Research Laboratory
Code 6030
Washington, DC 20375

WARSHEL, Arieh
Department of Chemistry
University of Southern California
University Park
Los Angeles, CA 90089-0482

WATT, Gerald D.
Dept of Chemistry & Biochemistry
University of Colorado
Campus Box 215
Boulder, CO 80309-0215