

AD-A243 642



✓
②

Office of Naval Research

DTIC
ELECTE
DEC 24 1991
S D

Grant: N00014-91-J-1625

R&T Code: 4132051--01

Technical Report No. 3

Organometallic NLO Polymers. Accordion Main-Chain NLO Polymers of Ferrocene

by

Michael E. Wright and Matthew S. Sigman

*Department of Chemistry & Biochemistry, Utah State University,
Logan, Utah 84322-0300*

Accepted for Publication in


Polym. Preprints 1992, 33(1), pp 0000

December 13, 1991

Reproduction in whole, or in part, is permitted for any purpose of the United States Government.

This document has been approved for public release and sale; its distribution is unlimited.

91-18884



91 1225 072

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188		
1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS			
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release: distribution unlimited			
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE						
4. PERFORMING ORGANIZATION REPORT NUMBER(S)			5. MONITORING ORGANIZATION REPORT NUMBER(S)			
6a. NAME OF PERFORMING ORGANIZATION Utah State University		6b. OFFICE SYMBOL (if applicable)	7a. NAME OF MONITORING ORGANIZATION			
6c. ADDRESS (City, State, and ZIP Code) Chemistry and Biochemistry Dept. Logan, UT 84322-0300			7b. ADDRESS (City, State, and ZIP Code)			
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research		8b. OFFICE SYMBOL (if applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER			
8c. ADDRESS (City, State, and ZIP Code) 800 N Quincy St. Arlington, VA 22217-5000			10. SOURCE OF FUNDING NUMBERS			
			PROGRAM ELEMENT NO N00014-91	PROJECT NO J-1625	TASK NO 4132051	WORK UNIT ACCESSION NO
11. TITLE (Include Security Classification) Technical Report #3: "Organometallic NLO Polymers. Accordion Main-Chain NLO Polymers of Ferrocene"						
12. PERSONAL AUTHOR(S) Michael E. Wright and Matthew S. Sigman						
13a. TYPE OF REPORT Preprint		13b. TIME COVERED FROM 4/15/91 TO 4/15/92		14. DATE OF REPORT (Year, Month, Day) Dec. 13, 1991	15. PAGE COUNT	
16. SUPPLEMENTARY NOTATION Polym. Preprints 1992, 33(1), pp 0000						
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number) Polymers, Ferrocene, Nonlinear optical materials, Second harmonic generation, Single-crystal, X-ray diffraction, polyesters, condensation polymers, Knoevenagel condensation, Bis(cyanoacetate)			
FIELD	GROUP	SUB-GROUP				
			19. ABSTRACT (Continue on reverse if necessary and identify by block number) Bis(ferrocene) NLO-phore monomers were prepared. The new bis(ferrocene) monomer was successfully copolymerized with bis(cyanoacetate) comonomers using a Knoevenagel polycondensation technique. The polymers were characterized by spectroscopic, thermal analysis, and GPC data. The polymers had average molecular weights in the range of 5000 to 25,000.			
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS				21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL Dr. Kenneth J. Wynne			22b. TELEPHONE (Include Area Code) (703) 696-4409	22c. OFFICE SYMBOL		

DD Form 1473, JUN 86

Previous editions are obsolete.

SECURITY CLASSIFICATION OF THIS PAGE

S/N 0102-LF-014-6603


ORGANOMETALLIC NLO POLYMERS. ACCORDION MAIN-CHAIN NLO POLYMERS OF FERROCENE

Michael E Wright* and Matthew S. Sigman

Department of Chemistry & Biochemistry,
Utah State University, Logan, Utah 84322-0300

Introduction


In the previous paper¹ we presented the synthesis of linear organometallic main-chain NLO polymers. Our research has continued to focus on ferrocene based NLO polymers because of the outstanding results obtained by Marder and coworkers using crystalline ferrocene complexes.² The ability to selectively functionalize the cyclopentadienyl rings of ferrocene has given us the ability to prepare elaborate organometallic NLO-phores.^{1,3} Lindsay and coworkers recently presented the synthesis of a new class of main-chain organic NLO polymers.⁴ For this new class of NLO polymers, the aligning process need not reorient the entire polymer chain, but rather, only fold the polymer backbone into the accordion shape.




In this paper we present the synthesis and characterization of organometallic polymers with the potential of adopting the accordion macrostructure. As we saw in the previous paper, the use of the Knoevenagel condensation appears to be the most effective manner to prepare polymers of good molecular weight and tractability.

Results & Discussion


Monomer Synthesis & Characterization. Selective mono-transmetalation of the ferrocene complex $(\eta^5\text{-C}_5\text{H}_5\text{SnBu}_3)_2\text{Fe}^0$ followed by reaction with one-half mol-equiv of dimethyldichlorosilane afforded the bridged ferrocene system in 45% isolated yield (eq 1). Separation of $(\eta^5\text{-C}_5\text{H}_5\text{SnBu}_3)(\eta^5\text{-C}_5\text{H}_4\text{SiMe}_2)\text{Fe}^0$ from SnBu_3 , which is also a product in the reaction, proves to be very difficult. The separation is made even more difficult by the necessity to deactivate the alumina column by treatment with ether prior to use. It turns out the most efficient route to 1 is to use the bis-ferrocenyl compound contaminated with SnBu_3 (~10 mol-%, the exact ratio was determined in ¹H NMR spectra). The SnBu_3 does not appear to have any deleterious effects on the yield in the final transmetalation step. Monomer 1 is isolated in a 30% overall yield starting from $(\eta^5\text{-C}_5\text{H}_5\text{SnBu}_3)_2\text{Fe}^0$.



The bis(cyanoacetate) monomers 2 were prepared by reaction of the appropriate diol with an excess of ethyl cyanoacetate in the presence of a catalytic amount of $\text{Ti}(\text{OC}_2\text{H}_5)_4$ (eq 2).⁷ At the completion of the reaction the monomers are purified by crystallization from ethyl acetate/hexanes. Monomers 2a-c are white crystalline materials which can be stored at ambient temperature for months without decomposition.




Copolymer Synthesis & Characterization. Our initial strategy to prepare the accordion copolymers was to carry out a polycondensation of monomer 3 with various diols. This method appeared highly desirable because it has proven very successful for main-chain organic NLO polymers prepared thus far. Monomer 3 is treated with hexanediol in the presence of $\text{Ti}(\text{OC}_2\text{H}_5)_4$ (2 mol-%) at 150 °C for 16 h. The product of the reaction is found to be intractable in all solvents. Elemental analysis data is close to that anticipated for the polymeric product; however, the lack of solubility is not consistent with other results we will present later.



The results above suggest that the reaction conditions required to carry out the Lewis acid catalyzed transesterification polycondensation are having deleterious effects on the ferrocene monomer and/or the polymeric product. It is at this point we changed our strategy and decided to construct the polymer backbone through the Knoevenagel condensation reaction. For the ferrocenecarboxaldehydes we find this reaction to proceed in very high yields and can be accomplished using very mild reaction temperatures (25 - 50 °C). This reaction also possesses good functional group tolerance because of the mild base (i.e. K_2CO_3 or DMAP) used. This latter point will become important in future generations of NLO polymers being prepared in our laboratory.

Scheme 1



The copolymerization of monomers 1 and 2 is carried out by heating a THF solution to 50 °C in the presence of excess potassium carbonate for 12 h (Scheme 1). Spectroscopic analysis of the crude polymer indicates a mixture of *E*- and *Z*-isomers are formed in the polymerization reaction. The *E/Z* ratio is found to vary in the range of 5 to 10. When the copolymers are purified by precipitation into methanol the *E*-isomer is enriched to ~95%. Evidently the copolymer which contains ratio of *Z*-isomers exhibits higher solubility.

The accordion main-chain organometallic polymers are soluble in most organic solvents (e.g. benzene, chloroform, dichloromethane, and tetrahydrofuran) and for 4c we are able to cast free-standing films. Gel permeation chromatography of the polymers show that comonomer 2c afforded the highest molecular weight polymer ($M_n = 25,000$). Films of polymer 4c are elastic and can be stretched by nearly 100% of their original length before tearing. The lower molecular polymers form films which are much more brittle.

Concluding Remarks

In this study we have demonstrated the feasibility of preparing accordion organometallic NLO polymers. The key to our success in obtaining the novel polymers was the utilization of a Knoevenagel polycondensation technique. The mild reaction conditions averted deleterious reactions which we seem to incur when heating ferrocenyl NLO-phore monomers in the presence of Lewis acids.

Experimental Section

Preparation of Copolymer 4. A solution of THF (4 mL) containing $((\eta^5-C_5H_4CHO)Fe(\eta^5-C_5H_4)_2SiMe_3$ (0.200 g, 0.413 mmol), $CNCH_2CO_2(CH_2)_nO_2CCH_2CN$ (0.104 g, 0.413 mmol), and K_2CO_3 (0.35 g, 0.62 mmol) was heated at 50 °C for period of 12 h. The mixture was filtered through Celite and the solvents removed under reduced pressure. The crude product was dissolved in chloroform and precipitated in methanol. The copolymer was collected and washed with cold methanol (3 x 25 mL) and then dried under reduced pressure at 65 °C for 24 h.

Copolymer 4c. 1H (CDCl₃) δ 8.06 (s, 2 H), 4.92 (t, *J* = 1.9 Hz, 4 H), 4.59 (t, *J* = 1.9 Hz, 4 H), 4.49 (t, *J* = 1.7 Hz, 4 H), 4.25 (t, *J* = 6.5 Hz, 4 H), 4.14 (t, *J* = 1.7 Hz, 4 H), 1.72 (m, 4 H), 1.39 (m, 8 H), 0.49 (s, 6 H, SiCH₃); ^{13}C NMR (CDCl₃) δ 163.1 (CO₂), 158.3 (=CH), 116.7 (CN), 97.6 (=C(CN)), 75.1 (Cp CH), 74.2 (Cp CH), 74.16 (*ipso*-Cp CH), 73.9 (Cp CH), 73.5 (*ipso*-Cp), 71.8 (Cp CH), 66.1 (OCH₂), 29.0, 28.4, 25.7 (CH₂'s), -1.4 (SiCH₃). IR (CH₂Cl₂) ν_{CN} 2222, $\nu_{C=O}$ 1718, and $\nu_{C=C}$ 1593 cm⁻¹. Anal. Calcd for (C₂₈H₄₄Fe₂N₂O₄Si)_n: C, 62.05; H, 5.53; N, 3.84%. Found: C, 61.70; H, 5.44; N, 3.76%.

Acknowledgment. The authors express their sincere gratitude to the donors of the Petroleum Research Fund, administered by the American Chemical Society for partial funding of this research through an undergraduate summer fellowship to MSS. Support of this work by the Office of Naval Research is greatly appreciated. We wish to thank the Utah State University Research Office and the NSF (grant CHE-9002379) for funding the purchase of the single-crystal X-ray diffractometer.

References and Notes

- For part 2 in the series see: Wright, M. E.; Toplikar, E. G. *Polym. Prepts*, preceding paper in this issue.
- Marder, S. R.; Perry, J. W.; Tiemann, B. G.; Schaefer, W. P. *Organometallics* 1991, 10, 1896 and references cited therein.
- Wright, M. E. *Organometallics* 1990, 9, 853.
- Lindsay, G. A.; Fischer, J. W.; Henry, R. A.; Hoover, J. M.; Kubin, R. F.; Seltzer, M. D.; Stenger-Smith, J. D. *Polym. Preprints* 1991, 32(2), 91.

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail. and/or Special
A-1	

