

## **OFFICE OF NAVAL RESEARCH**

1990 - 1991



for

Grant No. N00014-89-J-2-3237

# "THE IMPURITY RELATED STUDIES OF

## HIGH $T_C$ SUPERCONDUCTING MATERIALS"

Stanley Tsai

Department of Physics, Lincoln University

of the Commonwealth System of Higher Education

Lincoln University, PA 19352

Reproduction in whole, or in part, is permitted for any purpose of the United States Government.



Statement A per telecon Dr. Wallace Smith ONR/Code 1132 Arlington, VA 22217-5000 Second Fire

11001

Still Callor

12012.11.

6198 A-1

Impurity Effect of S on Superconductivity in  $YBa_2Cu_3SO_{6-\delta}$ 

J. T. Wang, S. Tsai, W. Williams, and S. C. SubbaRao Lincoln University, Lincoln University, PA 19352

A. Kebede and J. E. Crow<sup>\*</sup> Temple University, Philadelphia, PA 19122

In 1986, Bednorz and Muller found the superconductivity in the 30K range in La-Ba-Cu-O compound.<sup>1,2</sup> Soon after this discovery, C. W. Chu and etc. announced their tremendous finding of superconductivity of 90-93K with a sharp transition region (1K) in Y-Ba-Cu-O compound.<sup>2</sup> Scientists worldwide have much focused on searching new superconductors of higher transition temperature,  $T_c$  and the studies of physics and chemistries of these high  $T_c$  superconductors. The highest transition temperature  $T_c$  achieved so far is believed 125K in Tl-Ca-Ba-Cu-O compounds.<sup>3</sup> Although, many models have been proposed to elucide the mechanism of the high  $T_c$  superconductivity in oxide compounds, no guidelines can really direct ones to enhance the superconductors. It seems that the empirical methods are still the way to approach these goals.

In the superconductors of oxides, oxygen atoms play a key role of the superconductivity<sup>1</sup>. From the x-ray and neutron diffraction<sup>4</sup> it was known that in the orthorhombic phase the oxygens are ordered along the <u>b</u> axis so as to form a one dimensional Cu-O "chain" and a disordering of the oxygen vacancies along <u>a</u> axis. It is popularly agreed that the Cu-O chains play an important role in the high  $T_c$  superconductivity. The lack of the isotope effect on the superconductivity in Y-Ba-Cu-O compounds may suggest that the pairing mechanism is not a standard electron-phonon

NWW 3/31/92

<sup>\*</sup> J. E. Crow's current address is Physics Department, Florida State University.

interaction<sup>5</sup>. According to Anderson (RVB) the hole amplitude drives true electron-pair amplitude via the hole-pair amplitude which has the same symmetry as a bound electron pair.<sup>6</sup> If so, a sufficient concentration of  $Cu^{+3}$  is required.<sup>5</sup> Varma et.al<sup>5.7</sup> proposed that the charge transfer exciton  $Cu^{3+}O^{2-} \rightarrow Cu^{2+}O^{-}$  is the source of the effective electronelectron attraction.<sup>5.7</sup> And Mattheis et.al.<sup>8</sup> from their band structure calculations concluded that the superconducting properties of these oxides are mainly governed by the Cu-3d and O-2p electrons.<sup>5</sup> Chemical doping is one of the practical methods to confirm these proposed models, by knowing the precise locations of the impurities, and their ion structures. Much work has been focused on the doping of the  $Cu^+$  sites by positively charged ions, such as  $Zn^+$ ,  $Ni^+$ ,  $Fe^+$  and on  $Y^+$ ,  $Ba^+$  sites by rare earth ions. Fewer studies on the effects of the substitution for  $O^-$  sites have been conducted. Our paper is in attempt devoted to the study of the change of the physical properties when  $S^-$  ions substitutes for  $O^-$  ons in Y-Ba-Cu-O compounds.

#### **Experiment Results**

Sample preparation: Several Y-Ba-Cu-S(O) samples have been synthesized by means of the use of different chemical components and heat treatments. Some samples were made from the mixture of  $Y_2O_3$ ,  $BaCO_3$ , CuS and CuO, and some from the mixture of  $Y_2O_3$ ,  $BaCO_3$ ,  $CuSO_4$  and CuO. The original oxides sulphide or sulphates were dried in a hot vacuum. According to the stoichiometric of the final compound  $YBa_2Cu_3SO_6$ . The appropriate amount of components were weighed and ground and mixed thoroughly. The powder is then pressed into pellets. The pellets are subject to two heat treatment processes: (a) samples were heated in air at 950°C for 24 hours or longer and cooled to room temperature in air, then ground, pressed into pellets again and (b) sintered in a furnace with  $O_2$  flowing. The furnace temperature increases from room temperature to 950°C within five (5) hours, and stays at 950°C for 16 hours, cools down to 500°C within five (5) hours, stays at 500°C for 16 hours and finally cools down to room temperature within five (5) hours. The heat treatments processes may differ from sample to sample. The samples and their heat treatments processes are listed below:

Sample 1: Components used are:  $Y_2O_3$ ,  $BaCO_3$ , CuS, and CuO; and heat treatment, processes are: (a) once then process (b) twice.

Sample 2: Components used are:  $Y_2O_3$ ,  $BaCO_3$ , CuS, and CuO; heat treatment processes (a) once, then processes are: (b) three (3) times.

Sample 3: Components used are:  $Y_2O_3$ ,  $BaCO_3$ ,  $CuSO_4$ , and CuO; and heat treatment processes are: (a) twice then process (b) once.

The electrical resistance measurements were carried out by means of standard fourprobe technique with indian soldering points on the samples of rectangular bars of about 10 x 2 x 1  $mm^3$  cut from pellets. The data acquisitions were accomplished by Keithley's instruments and HP computer system. Fig. 1 and Fig. 2 show the temperature-dependence of the resistivity of sample 1 and sample 2. In the temperature range from 300K down to liquid heliumm temperature the resistances of sample 1 and sample 2 were performed. From the electrical resistance point of view, before the superconductivity transition temperature sample 1 exhibits, insulator like electrical property. Shown in Fig. 1, the resistance increases when the temperature decreases. The onset temperature is about 94K. The zero resistance temperature is about 30K. Therefore, the transition region is wide. For sample 2, shown in Fig. 2, the resistance decreases monotonously as the temperature decreases. The onset temperature is also about 94K and transition region is very narrow, about three (3) or four (4) degrees. The "zero-R" state is at about 90K. The susceptibility measurements for those three (3) samples have been carried out at Quantum Design Sample Property Measurement System. Fig. 3 shows the temperature-dependence of susceptibility at magnetic strength of 2000g for sample 1. The embedded is the data of susceptibility of this sample

(3)

from 400K to the temperature before transition temperature and the solid curve is the best fit by Curie-like law  $\chi = \chi_0 + \frac{c}{T+T^*}$  Meissner effect starts at the temperature around 91k. Fig. 4 shows the temperature-dependence of susceptibility at magnetic strength of 2000g for sample 2. The embedded graph is the data of susceptibility of sample 2 vs. temperate from 400K down to temperature before the transition temperature and the solid curve is the best fit by curie-like law. Fig. 5 is the similar plot for sample 3. From Fig. 3 (sample 1) it is obvious that the Meissner effect starts at about 90K, at 77K the susceptibility is about -0.04 (emu/mol), and the curie-like parametors are:  $\chi_0 = 2.17 \times 10^{-4}$  emu/mol,  $C = 9.29 \times 10^{-3}$  emu/mol,  $T^* = 51.4K$  and magnetic moment  $\mu_p = .273\mu_B$ . For sample 2 from Fig. 4 the transition (Meissner effect takes place) is sharp at about 90K. At 77K the susceptibility is about 0.09 (emu/mol) which is almost double the value of sample 1 (0.04), and the curie-like parameters are :  $\mu_0$  = 4.78 x 10<sup>-4</sup> emu/mol, c = 0.08 emu/mol.  $T^*$  = 17.7K, and the magnetic moment  $\mu_p$  = .798  $\mu_B$ . For sample 3, the resistance measurement hasn't been done yet. However, the d.c. susceptibility measurement shows Meissner effect also, it seems that at temperature around 75K, the susceptibility becomes negative and the transition is broadened. The curie-like parameters are:  $\chi_0 = 3.549 \times 10^{-4}$  emu/mole, c = 5.34 x 10<sup>-2</sup> emu/mole, T<sup>\*</sup> = 8.2K and magnetic moment  $\mu_p$  =.654  $\mu_B$ . From the observations reported about, we may conclude that the transition temperatures  $T_c$  are not strongly affected by the impurity S that is in agreement with the prediction by non-BCS theory9. Whereas, the other models responsible for the high T<sub>c</sub> superconductivity somewhat involve the electronic structure of the compound YBa2Cu3SO6. For instance, the charge-transfer excitations would enable us to expect three d-d transitions, and the lowest one would be the  $3d(3z^2 - r^2)$  to  $3d(x^2 - y^2)$  excitation within the  $e_g$  orbitals<sup>10</sup>. The substitution of S for O may lead to some variations in the electrical and magnetic properties of  $YBa_2CuO_7$ . The susceptibility studies of  $YBa_2CuSO_6$  do show the effects of S in the compound<sup>9</sup>.

### Acknowledgement

This work is supported partially by ONR grant No. N00014-89-J-3237 at Lincoln University and the usage of Physics Lab facilities at Temple University.

#### REFERENCES

- 1. J. G. Bednorz and K. A. Muller, Z. Phys. B64, 189 (1986).
- C. W. Chu, P. H. Hor, R. L. Meng, L. Gao. Z. J. Huang, and Y. Q. Wang, Phys. Rev. Lett. 58, 405 (1987)
- 3. J. R. Thompson, J. Brynestad, D. M. Kroeger, Y. G. Kim, S. T. Sekula, D. K. Christen, and E. D. Specht, Phys. Rev. B 39, 6652 (1989).
- Ivan K. Schuller, D. G. Hinks, J. D. Jorgensen, L. Soderholm, M. Beno, K. Zhang<sup>\*</sup>,
  C. U. Segre<sup>\*</sup>, Y. Bruynseraede<sup>\*\*</sup>, and J. P. Locquet<sup>\*\*</sup>, in Stuart A. Wolf, and
  Vladimir Z. Kresin (edt.), "Novel Superconductivity", proceeding of International
  Workshop, 647 (1987).
- J. M. Tarascon, L. H. Greene, B. G. Bagley, W. R. McKinnon, P. Bardoux, and G. W. Hall, in Stuart A. Wolf and Vladimir Z. Kresin (edt.), "Novel Superconductivity", proceeding of International Workshop, 705 (1987).
- P. W. Anderson, G. Baskaran, Z. Zou, and T. Hsu, Phys. Rev. Lett. 58, 2791 (1987).
- 7. C. M. Varma, S. Schmitt-Rink, and E. Abrahams, Solid State Commun. 62, 681 (1987).
- 8. L. F. Mattheis and D. R. Hamann, Solid State Commun.

- 9. I. Felner, I. Nowik, Y. Yeshurun, Phys. Rev. B 36, No. 7 (1987).
- H. P. Geserich, G. Scheiber, J. Geerk, H. C. Li, W. Weber, H. Romberg, N. Nucker, J. Fink, and B. Gegenheimer, in "High T<sub>c</sub> Superconducting", edited by Harald W. Weber. 195 (1988).



(7)



FIGURE 2.



(9)



3

FIGURE 4.





