

AD-A248 614



AD-E501508
Copy 38 of 80 copies

2

DTIC
ELECTE
APR 4 1992
S C D

IDA DOCUMENT D-1115

SURVEY OF RESEARCH INTO ELECTROMAGNETIC AND
OTHER WAVE EFFECTS ON MECHANICAL BEHAVIOR AND
PROCESSING OF MATERIALS

George Mayer
Benjamin Tao

January 1992

Prepared for
Defense Advanced Research Projects Agency

Approved for public release; distribution unlimited.

92-09488



INSTITUTE FOR DEFENSE ANALYSES
1801 N. Beauregard Street, Alexandria, Virginia 22311-1772

92 4 13 093

IDA Log No. HQ 92-40803

DEFINITIONS

IDA publishes the following documents to report the results of its work.

Reports

Reports are the most authoritative and most carefully considered products IDA publishes. They normally embody results of major projects which (a) have a direct bearing on *decisions affecting major programs*, (b) *address issues of significant concern to the Executive Branch, the Congress and/or the public*, or (c) *address issues that have significant economic implications*. IDA Reports are reviewed by outside panels of experts to ensure their high quality and relevance to the problems studied, and they are released by the President of IDA.

Group Reports

Group Reports record the findings and results of IDA established working groups and panels composed of senior individuals addressing major issues which otherwise would be the subject of an IDA Report. IDA Group Reports are reviewed by the senior individuals responsible for the project and others as selected by IDA to ensure their high quality and relevance to the problems studied, and are released by the President of IDA.

Papers

Papers, also authoritative and carefully considered products of IDA, address studies that are narrower in scope than those covered in Reports. IDA Papers are reviewed to ensure that they meet the high standards expected of refereed papers in professional journals or formal Agency reports.

Documents

IDA Documents are used for the convenience of the sponsors or the analysts (a) to record substantive work done in quick reaction studies, (b) to record the proceedings of conferences and meetings, (c) to make available preliminary and tentative results of analyses, (d) to record data developed in the course of an investigation, or (e) to forward information that is essentially unanalyzed and unevaluated. The review of IDA Documents is suited to their content and intended use.

The work reported in this document was conducted under contract MDA 903 89 C 0003 for the Department of Defense. The publication of this IDA document does not indicate endorsement by the Department of Defense, nor should the contents be construed as reflecting the official position of that Agency.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public Reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE January June 1992	3. REPORT TYPE AND DATES COVERED Final--May 1989-November 1991	
4. TITLE AND SUBTITLE Survey of Research Into Electromagnetic and Other Wave Effects on Mechanical Behavior and Processing of Materials			5. FUNDING NUMBERS C - MDA 903 89 C 0003 T - A-131, A-140	
6. AUTHOR(S) George Mayer, Benjamin Tao			8. PERFORMING ORGANIZATION REPORT NUMBER IDA Document D-1115	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Institute for Defense Analyses 1801 N. Beauregard St. Alexandria, VA 22311-1772			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) DARPA 3701 N. Fairfax Dr. Arlington, VA 22207-1714			11. SUPPLEMENTARY NOTES	
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) In an effort to assess trends in the general areas of energy effects on materials, a survey was conducted for the period 1960-1990 of the open literature sources with special focus on electromagnetic and other wave phenomena. This survey has not treated nuclear, laser, or photoplastic effects. The statistics and trends in activity have been examined in four main areas: electric fields and currents, ultrasonics, microwaves, and magnetic fields. These energies have been found to affect the structure and mechanical properties of materials, and the changes, some of them substantial, are a main subject of this survey. In addition, beneficial effects, ranging from minor to significant, have been measured during the processing of materials with these energies. It is expected that future understanding and exploitation of these effects will be essential to the widespread development and use of future DoD systems such as electromagnetic guns, toward achieving economics of manufacturing through microwave processing of ceramic armor components and thick-section structural composites, and in other applications.				
14. SUBJECT TERMS electroplasticity, magnetoplasticity, materials, microwave effects, microwave processing, electric field effects, electric current effects, magnetic field effects, acoustic wave effects, sonic effects, ultrasonic effects			15. NUMBER OF PAGES 94	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT SAR	

IDA DOCUMENT D-1115

**SURVEY OF RESEARCH INTO ELECTROMAGNETIC AND
OTHER WAVE EFFECTS ON MECHANICAL BEHAVIOR AND
PROCESSING OF MATERIALS**

George Mayer
Benjamin Tao

January 1992

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DWAC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or
A-1	Special

Approved for public release; distribution unlimited.



INSTITUTE FOR DEFENSE ANALYSES

Contract MDA 903 89 C 0003
DARPA Assignment A-131 and A-140

ABSTRACT

In an effort to assess trends in the general areas of energy effects on materials, a survey was conducted for the period 1960-1990 of the open literature sources with special focus on electromagnetic and other wave phenomena. This survey has not treated nuclear, laser, or photoplastic effects. The statistics and trends in activity have been examined in four main areas: electric fields and currents, ultrasonics, microwaves, and magnetic fields. These energies have been found to affect the structure and mechanical properties of materials, and the changes, some of them substantial, are a main subject of this survey. In addition, beneficial effects, ranging from minor to significant, have been measured during the processing of materials with these energies. It is expected that future understanding and exploitation of these effects will be essential to the widespread development and use of future DoD systems such as electromagnetic guns, toward achieving economics of manufacturing through microwave processing of ceramic armor components and thick-section structural composites, and in other applications.

CONTENTS

Abstract	iii
Figures	vii
I. INTRODUCTION.....	I-1
II. EFFECTS OF ELECTRIC CURRENTS AND FIELDS ON MATERIALS.....	II-1
A. Electroplasticity.....	II-1
B. Processing and Miscellaneous Effects	II-6
C. Survey Results	II-7
III. ULTRASONIC EFFECTS ON MATERIALS.....	III-1
A. Effects on Structure and Mechanical Properties	III-1
B. Processing and Miscellaneous Effects	III-3
C. Survey Results	III-5
IV. MICROWAVE EFFECTS ON MATERIALS	IV-1
A. Microwave Sintering.....	IV-1
B. Other Processing and Miscellaneous Effects.....	IV-5
C. Survey Results	IV-5
V. MAGNETIC FIELD EFFECTS ON MATERIALS	V-1
A. Effects on Structure and Mechanical Properties	V-1
B. Processing and Miscellaneous Effects.....	V-3
C. Survey Results	V-4
VI. CONCLUSIONS	VI-1
References	R-1

FIGURES

1.	Published Research on Electric Current and Field Effects on Materials by Country (1960-1989)	II-8
2.	Published Research on Electric Current and Field Effects on Materials by Decade	II-8
3.	Areas of Literature Emphasis (1960-1989)	II-9
4.	Published Research on Ultrasonic Effects on Materials by Country (1960-1989)	III-6
5.	Published Research on Ultrasonic Effects on Materials by Decade	III-6
6.	Areas of Literature Emphasis (1960-1989)	III-7
7.	Published Research on Microwave Effects on Materials by Country (1960-1989)	IV-6
8.	Published Research on Microwave Effects on Materials by Decade	IV-6
9.	Areas of Literature Emphasis (1960-1989)	IV-7
10.	Published Research on Magnetic Field Effects on Materials by Country (1960-1989)	V-4
11.	Published Research on Magnetic Effects on Materials by Decade	V-5
12.	Areas of Literature Emphasis (1960-1989)	V-5

I. INTRODUCTION

During the past several decades, the expanding use of energetic phenomena has been demonstrated in widespread applications, from concepts involving electromagnetic guns to microwave communications (and cooking), the use of magnetic fields in medicine and in materials processing, and the employment of ultrasonic methods for nondestructive evaluation of critical defense components and in many other end uses.

Machines and devices have been developed to generate electrical, magnetic, ultrasonic, and other wave phenomena over a broad range of waveforms, frequencies, and amplitudes. Lagging somewhat behind these practical developments has been the mechanistic understanding of the effects of such waves upon the structure, properties, and processing of materials.

In order to assess the trends in activity in the general areas of energy effects on materials, a survey has been conducted for the period 1960-1990 of open literature sources. The emphasis has been on the effects of energetic phenomena on mechanical behavior of materials and on the use of such energies in materials processing.

The survey has not treated nuclear, laser, or photoplastic effects. The statistics and trends in activity have been examined in four main areas: electric fields and currents, ultrasonics, microwaves, and magnetic fields.

The major areas searched for this review included both the scientific fundamental information bases and those dealing with technological applications.

Lower level energetic methods employing electromagnetics, ultrasonics, and optical characterization procedures fall into the category of nondestructive evaluation. These levels of effects were judged to not substantively perturb or otherwise alter existing properties, defect structures, or microstructures and are not powerful enough to be considered for forming or other like processes. Work along the lines of nondestructive evaluation has not been included in the survey.

Probably more was known about the interaction of ultrasonic energy with and its influence on structure and properties of materials (prior to 1960) than was the case with the

other three areas surveyed. In terms of detailed, fundamental mechanistic understanding, more has been achieved with the electroplastic effect than with the other areas reviewed.

The following sections summarize the results of the survey according to the four areas: the effects of electric fields and currents, ultrasonic waves, microwaves, and magnetic fields upon the mechanical properties and processing of materials.

II. EFFECTS OF ELECTRIC CURRENTS AND FIELDS ON MATERIALS

A. ELECTROPLASTICITY

The main emphasis in this part of the review has been on the effects of electric fields and currents on the mechanical behavior of metallic materials (Refs. 1-187). Focus has been on the role of atomic and subatomic species, point and line defects, and the alteration of yield and flow behavior of metals and alloys. Engineering strength levels have been determined for some alloys (nonferrous light and heavy alloys, refractory metals, ferrous alloys and others) over a range of temperatures. Research is at fairly early stages on mechanical failure phenomena, including fatigue and creep. Both continuous and pulsed currents and fields have been explored.

The effect of electric current pulses on plastic flow of materials is generally known as electroplasticity. While other factors such as Joule heating and skin, pinch, and magnetostrictive effects influence the enhanced plastic deformation of metal subjected to an electric current, the major influence in the electroplastic effect is due to electron-dislocation interactions (Ref. 139). One part of this interaction is known as electron drag. Electrons, especially when moving at high speeds and low temperatures, exert a drag on dislocations. The electron drag coefficient, B_e , is defined as:

$$B_e = \frac{f/l}{V_d} = \frac{\tau b}{V_d} \quad (\text{II-1})$$

where f/l is the force per unit length on the dislocation,

τ is the resolved shear strength,

b is the Burgers vector of the dislocation,

and V_d is the dislocation velocity.

A second part of the electron-dislocation interaction, first proposed in 1963 by Troitskii and Likhtman, is one in which directed electrons affect dislocation movement (Ref. 139). This theory was the result of observations of significantly lower flow stresses in zinc crystals which were uniaxially deformed while simultaneously exposed to an electron beam oriented parallel to the slip plane. Troitskii concluded that drift electrons exert a "push" or force on the dislocations. This "push" has been termed the electron wind. Thus, when an electric current passes through a metal, the electron wind aids in the movement of dislocations during plastic deformation of the material (Ref. 139). In the same work, it has been shown that the electron wind contribution to the total electron-dislocation interaction comprises a majority of the effect.

There are two theoretical estimates of the electron wind force. The first is based on considerations of the specific dislocation resistivity, and the second is based on kinetic or quantum mechanical considerations of the interaction between conduction electrons and dislocations (Ref. 145). Whether there are significant differences in the results of these two approaches has yet to be addressed. The electron wind force per unit dislocation length (F_{ew}) is calculated from the following in respective order:

$$F_{ew} = p_d e n_e j / N_d \quad (II-2)$$

and

$$F_{ew} = \alpha b p_f (j/e - n_e V_d) \quad (II-3)$$

where p_d/N_d (p_d is specimen resistivity; N_d is dislocation density) is the specific dislocation resistivity,

e is the electron charge,

n_e is the electron density,

j is the current density,

α is a constant ranging between 0.1 and 1.0,

b is the Burgers vector,

p_f is the Fermi momentum,

and V_d is the dislocation velocity.

From these terms for the electron wind force, one may determine the electron wind push constant ($K_{ew} = F_{ew}/j$) and the electron wind push coefficient ($B_{ew} = K_{ew}en_eF_{ew}/V_e$).

The increase in plastic strain Γ due to the electron wind-dislocation interaction was considered by Conrad et al. for two situations: (1) when the running time t_r between barriers to dislocation movement was much longer than the waiting time t_w at each barrier, and (2) when $t_w \gg t_r$ (Ref. 146). For $t_r \gg t_w$:

$$\Gamma_j/\Gamma = \frac{B_e(B_e\tau_a^*b - B_{ew}^2V_e)}{\tau_a^*b(B_e^2 - B_{ew}^2)} \quad (II-4)$$

where τ_a^* is the effective externally applied stress and v_e is the electron drift velocity. The subscript j refers to the value during the current application; the omission of a subscript refers to the absence of a current. For $t_w \gg t_r$,

$$\ln\Gamma_j/\Gamma = \ln(\Gamma_{oj}/\Gamma_o) - \left[\frac{Gj^* - G^*}{kT} \right] + \left[\frac{(Aj^* - A^*) b\tau_a^*}{kT} \right] + \ln 2 \cosh \left[\frac{A^*F_{ew}}{kT} \right] \quad (II-5)$$

where $\Gamma_o = N_{D,m}bsv^*$ (pre-exponential factor),

$N_{D,m}$ is the mobile dislocation density,

s is the average distance moved per successful fluctuation,

v^* is the frequency of vibration of the dislocation,

G^* is the Helmholtz free energy of activation,

A^* is the activation area,

and kT has its usual meaning.

The effects of current density (j) on the ratio of the strain rate with a current ($\dot{\epsilon}_j$) to the strain rate prior to a pulse ($\dot{\epsilon}_o$) was determined experimentally by Conrad et al. It is defined as:

$$\dot{\epsilon}_j / \dot{\epsilon}_o = (j/j_c)^n \quad (\text{II-6})$$

where j_c is the critical current density (of the order of 10^3 - 10^4 A/cm²), and n is about 3 (for tests on Al, Ag, Cu, Ni, Nb, Fe, W, and Ti) (Ref. 145).

The critical current density is found to vary for different metals as a function of the electron density:

$$j_c = Cn_e^q \quad (\text{II-7})$$

where C is a constant that decreases with temperature, and q is of the order of $2/3$ at 300 K and $2/5$ at 77 K.

In studying electroplasticity in zinc crystals, Troitskii et al. measured a 10-40% reduction in load drop when a current with a density of 10^3 A/mm², pulse duration of 50 μ s, and a pulse frequency of 0.1 Hz were applied at temperatures ranging from 78-300 K (Ref. 139). In studying electroplastic deformation of amalgamated zinc before brittle fracture, Troitskii recorded that plastic deformation to fracture increased by 100-120% at 77 K and by 50-60% at 293 K using concurrently applied current pulses of $\approx 10^3$ A/mm² (Ref. 29). There were increases in the true values of the normal and shear strains by 30% at 77 K and by 35% at 293 K. The current also caused an increase of the critical normal strains by 50-60% and a reduction of critical shear strains by 12-15%. Sprecher et al., with $j = 5500$ A/mm² at a plastic strain of 0.8%, measured a drop in flow stress in metals. These ranged from 1% in tungsten to 36% in aluminum (Ref. 139).

Spitsyn and Troitskii also conducted extensive experiments on the electroplastic effect on steady state creep rates of monocrystalline metals (Ref. 4); the creep rates were shown to increase. The following are the results: lead (load, $P = 1.2$ N/mm²), 30%; zinc (0.3 N/mm²), 106%; indium (0.45 N/mm²), 49%; and tin (1.5 N/mm²), 15% (Ref. 4). The type of current applied during the tests also affected the rate; a pulsed current (every 50 Hz) had the greatest effect. The next largest was due to a direct current, and an alternating current (50 Hz) had the smallest effect. The studies were done using $j \approx 7$ -8 A/mm² at 77 K.

Effects of electric currents on fatigue were studied by Conrad et al. (Ref. 146). Using simultaneous current pulses of 1.3×10^{-4} A/cm² for 100 μ s with 2 per second, the

fatigue life (N_f) of copper during a rotating bending test at 300 K increased by a factor of 1.2 - 3.0. There was an increase in the number of cycles needed for microcrack initiation and a decrease in macrocrack growth rate. Thus, both initiation and propagation phases in fatigue were extended, resulting in longer fatigue life for copper. Transgranular cracking seemed to be promoted by the current pulsing as opposed to intergranular cracking. Conrad et al. attributed the longer microcrack initiation time to increased homogenization of slip, while the decrease in macrocrack growth rate was attributed to a decrease in K_{eff} (K is the stress intensity factor; $K = \sigma\sqrt{a} f(a/w)$. σ is stress, a is crack length, $f(a/w)$ is a factor which is a function of specimen geometry, and w is the specimen thickness) due to the presence of a thicker oxide film (SEM analysis revealed increased oxidation due to electropulsing) which affected crack closure.

Electric (d.c.) field effects have been studied in less detail than the effects of electric currents. During the superplastic deformation of 7475 aluminum alloy in a d.c. electric field of 2 kV/cm, Conrad et al. observed a decrease in flow stress (σ) at all strain levels (ϵ), which reduced the rate of strain hardening ($\theta = d\sigma/d\epsilon$) and increased the strain rate hardening exponent ($m = d\ln\sigma/d\ln\dot{\epsilon}$) (Ref. 146). The amount of cavitation produced by the deformation was also reduced, with the reduction increasing with field strength. Grain growth retardation was observed in an electric field. The effects on the 7475 alloy were not entirely clear. The field may have affected diffusion, specifically the generation and/or migration of vacancies. Soviet work done by Kishkin and Klypin reported that an electric field ($E = 100$ V/cm) applied during the creep of copper and cobalt at high homologous temperatures caused an increase of an order of magnitude in the steady state creep rate (Ref. 145).

Some investigations have been conducted on the phase transformation of metals. Electric pulsing (10^5 A/cm², 60-95 microsecond durations, and 4.2-8.7 pulses per second) of amorphous iron-based alloys resulted in alpha-iron precipitation at temperatures below (150°C below) those where bulk crystallization occurred (Ref. 146). This enhanced rate of precipitation might result from an increase in electromigration caused by the electric current. The application of electric fields (1-2 kV/cm) applied during quench hardening and tempering of 4340 steel produced a slightly increased rate of austenization, a large increase in hardenability, and a slight retardation in the tempering rate. After 3 minutes of austenization in a 1 kV/cm field, the same level of hardness was achieved as for 5 minutes of austenization without a field. The hardenability of the steel doubled after austenization and quenching in an electric field as compared to processing without a field. An increase of

20°C was needed to achieve the same hardness during tempering in a 2 kV/cm field than without.

The study of electroplasticity has not been confined to metallic materials (Refs. 188-200). In 1984 Kulichenko and Smirnov studied the effects of electric fields in the polymers PMMA (polymethylmethacrylate), PS (polystyrene), and PVC (polyvinylchloride) (Ref. 200). The external field gradually lowered the stress applied during deformation. The possibility that the electric field caused heating of the sample during the flow of an electric current was discounted, as an estimate showed that such heating resulted in only a fraction of a degree increase in temperature. While the authors offered two possible models of the effect, it was concluded that further study was necessary before a valid theory could be formulated.

B. PROCESSING AND MISCELLANEOUS EFFECTS

In addition to mechanical property effects, a full range of other effects have had some limited study. Thermoelectric effects have been examined (Refs. 201-208). Work has been done on the effect of fields and currents on the magnetic phases of metallic materials, with much of it focused on the positive or negative shift in the Curie temperature of magnetic phases in ferroelectric and antiferroelectric materials (Refs. 209-237). Some initial work has been done on the effects of electric currents and fields on electrical properties of materials (Refs. 238-280) as well as the effects on the magnetic properties of materials when fields were applied during processing (Refs. 281-297). Solidification and growth of metallic materials in currents and fields has been examined. During electro-pulsing of copper, a doubling of rates of recovery and recrystallization were observed (Refs. 298-333). Conrad et al. have determined that the enhanced rates of recrystallization observed were the result of the current's effect on the rate of subgrain formation and coalescence; it increased the rate of annihilation of residual dislocations (Ref. 146). Annealing in a field resulted in an opposite effect. The annealing temperatures of copper and aluminum in an electric field were moderately higher than without a field. Optical properties affected by electric fields and currents such as luminescence, optical absorption, fluorescence, and photoconductivity have been the subjects of limited study in the last few years (Refs. 334-358). The effect of electric fields on the rate and mechanism of polymerization of polymers has also been briefly considered, where the rate was greater or lesser, depending on the polymer (Refs. 359-362). Sakurada et al. noted increases in the rate of ionic polymerization and the degree of polymerization in electric fields, which has

been attributed to the second Wien effect (Ref. 361). Akbulut et al. reported that the rate of formation of polymers at high conversions decreases in an electric field (Ref. 361). Electrochemical effects are believed to be responsible. Electrical field and current effects during the growth and the deposition of thin films and coatings have been explored (Refs. 363-377). Electrophoretic chromium carbide alloy coatings were influenced by electric field strength on their rate of formation and chemical composition (Ref. 372). The growth rate of gallium arsenide thin films was 1.45 $\mu\text{m}/\text{minute}$ in a zero potential, while it was 1.8 $\mu\text{m}/\text{minute}$ in a negative potential of 1 kV when grown on a substrate oriented in a $\langle 111 \rangle$ direction (Ref. 377). The density of growth hillocks and pits was also reduced. Electric field effects on adhesive bonds and joints have had some isolated study (Refs. 378-380). Additional work is needed to clarify the mechanisms governing these effects and to quantify them.

C. SURVEY RESULTS

As in other areas of this survey, the contribution of Soviet investigators make up much of the research in the area of the effects of electric currents and fields. In the area of electroplasticity, Soviet scientists accounted for about 70% of the published research (Refs. 1-128). Troitskii and his colleagues were responsible for about 40% of these (Refs. 1-49). U.S. literature comprised nearly 20% of the papers surveyed, (Refs. 129-163) and Conrad and his colleagues represented about half of these (Refs. 129-146). Figure 1 shows the overall breakdown for this section by country.

The amount of interest has been climbing steadily in the last few decades. Figure 2 reveals the levels of effort between 1960 and 1989.

In Figure 3, a breakdown of the different areas explored is shown.




Figure 1. Published Research on Electric Current and Field Effects on Materials by Country (1960-1989)




Figure 2. Published Research on Electric Current and Field Effects on Materials by Decade

Electroplasticity	(200, 52%)
Solidification and Other Phase Transformations	(65, 17%)
Electric and Magnetic Properties	(60, 17%)
Other	(55, 14%)

Figure 3. Areas of Literature Emphasis (1960-1989)

III. ULTRASONIC EFFECTS ON MATERIALS

A. EFFECTS ON STRUCTURE AND MECHANICAL PROPERTIES

An analysis of the open literature on ultrasonic effects on materials finds a marked increase in interest during the past two decades in studying the effects of this form of energy on properties and processing of a wide range of materials. The greatest emphasis is on the category of microstructure/mechanical property relations, which range from simple correlations of the applied ultrasonic energy with resultant mechanical properties, to much more detailed studies of dislocation structures and defect interactions as more sophisticated tools and methods of analysis became available (Refs. 381-445). During the past ten years, identification of micromechanisms underlying the enhancement or degradation of mechanical properties by ultrasonic waves has been of main interest. Efforts have been devoted to clarifying the effects of energy on the static and dynamic behavior and properties of (mainly) metals and alloys, including yield strength, microhardness, and creep.

The main effect which is observed as the result of ultrasonic treatment of metals is an increased concentration of dislocations (Ref. 407). This increase affects the plastic deformation and mechanical properties of metals. It has been observed that ultrasonic treatment increases the hardness of metals rapidly. Bazelyuk et al. reported a 19% increase in microhardness in Kh16N11M3 stainless steel ($\text{Cr}_{16}\text{N}_{11}\text{Mo}_3$ stainless steel) after 5 minutes of ultrasonic excitation (20 kHz and a maximum amplitude of alternating mechanical stresses of 12 N/mm^2) (Ref. 390). After this maximum treatment time, the microhardness decreased rapidly, indicating work-softening. After 10 minutes of treatment the microhardness decreased 12.5% from the original value (Ref. 390). Bazelyuk et al. attributed this loss of strength to an increase in the concentration of vacancies, causing dislocation annihilation and rearrangements, and easing formation of polygonal subgrains (Ref. 390). Vasudevan and Muralidhar also observed an increase in hardness of solution heated-treated aluminum alloys of 40% after 5 minutes of treatment with 35 watts/cm^2 at room temperature (Ref. 412). Increased rates and higher values were found at higher temperatures. The same amount of hardening by natural aging would have taken 24 hours (Ref. 412). The amount of hardening asymptotically approached a horizontal line for most treatment temperatures. The authors attributed this to a large increase of the dislocation

density which allowed greater amounts of finer precipitation at nucleating centers. These centers acted as pinning points for dislocations. However, at 180°C for alloy Al-Zn-Mg and at 160°C for alloy Al-Cu-Mg, the hardness dropped rapidly after 1 minute of exposure, similar to the results reported by Bazelyuk et al. (Ref. 412). The yield stress for metals subjected to ultrasonic treatment increased, with the resulting improvements varying. After a cyclic heat treatment (50 cycles) between 650°C and 20°C followed by an ultrasonic treatment of 5 minutes and a peak value of mechanical stress of 12 N/mm², the yield strength of Kh16n11m3 stainless steel increased by 33% (Ref. 390). Treatment of Al-Zn-Mg alloy with an ultrasonic energy of 35 watt/cm² at 150°C for 10 hours resulted in a 218% increase in yield strength (Ref. 412). The elongation dropped from 25% to 12% during the same treatment.

The effect of ultrasonic energy applied during the *simultaneous* application of a load has also been studied. A 40% drop in tensile strength (Ref. 430) has been obtained in zinc single crystals exposed to ultrasonic emissions (25 watts maximum power at 800 kHz). Upon removal of the ultrasonic load, the tensile load returned to its previous value. Some have attributed this softening of the metal to a simple superposition of the alternating ultrasonic stress onto the externally applied stress. In the same 1989 paper, Green suggested three variables as possible underlying reasons for this effect, all of which were components of an equation defining stress (σ) during a standard tensile test:

$$\sigma = \frac{st - \epsilon_p l}{A/K + 1/E^*} \quad \text{(III-1)}$$

where

s is the crosshead speed,

t is the time,

ϵ_p is the plastic strain,

l is the specimen length,

A is the specimen's cross-sectional area,

K is the compliance of the load cell spring and frame of the tensile machine,

and E^* is the effective Young's modulus of the specimen.

In order for the observed stress drop to occur, one or more of the following things must happen: (1) $\dot{\epsilon}$ increases, (2) E^* decreases, and/or (3) ϵ_p increases.

The length of the specimen grows as the crosshead moves at a rate of s . Yet, if the ultrasonic emissions cause the length to increase beyond the limit which is a function of s , then the force on the load cell would decrease. For E^* to decrease, many factors would have to be responsible. One factor is the reduction of E^* as a linear function of increased tensile stress, for which Green has derived an expression. The increase in ϵ_p as a cause seems to be more generally accepted. It might be caused by the ultrasonic energy interacting with dislocations, multiplying and activating them. The resulting movement of dislocations would increase plastic strain. More comprehensive details of this proposed reason for the stress drop are not yet available.

The acceleration of the rate of creep during exposure to ultrasonic emissions during testing has also been observed. Initial creep rates grew exponentially as the ultrasonic stress amplitude increased (Ref. 388). Ultrasonic treatment of aluminum *before* creep testing yielded a different result. After a treatment at 260°C at an ultrasonic stress amplitude of 0.96 N/mm², the creep rate from zero to 7 minutes varied cyclically. The rate after 30 seconds of exposure decreased 62% (Ref. 412). After 2 minutes, the rate had increased by 40% from the original (Ref. 412). At 4 minutes, the rate had again dropped by 62% of the original (Ref. 412). Thus, selective treatment of these aluminum alloys can allow an improvement in the creep rate.

Fatigue testing using ultrasonic oscillations has been performed to gain further understanding of fatigue based upon dislocation concepts (Refs. 431-445). The results have been used to test fatigue theories which have been based upon conventional fatigue testing.

B. PROCESSING AND MISCELLANEOUS EFFECTS

Early attention was attracted to the use of ultrasonics for the processing of materials through the practical success shown by its application to wire-drawing of hard-to-form metallic materials in the 1950s by AT&T (Refs. 446-449). Ultrasonic die activation allowed a reduction in drawing force which varied with drawing rate. A maximum of 75% reduction in force at below 10 feet per minute drawing speed down to a 5 to 10% decrease in force at drawing rates approaching 1000 feet per minute with copper and steel wire have been demonstrated (Ref. 437). A follow-up to this research showed the advantages of tube drawing by axial oscillation of the plug. Reductions in average drawing force were 4-30%

for aluminum alloys, 1-14% for steel, and 2-12% for titanium alloys (Ref. 437). A smooth drawing (absence of slip-stick) resulted from the process, especially for titanium; such results were unlikely with conventional techniques.

Along other technological avenues, ultrasonics have been explored for welding and other bonding processes, largely in metals during the 1970's; but, in the 1980's, more in polymers and in special configurations and complex materials, such as laminates (Ref. 450-481). Reduced costs and energy conservation in reference to adhesive bonding have been demonstrated in the use of ultrasonic bonding of reinforced metal (aluminum/titanium) composites employed in aircraft structures (Ref. 475). Ultrasonic welding has been studied for use in thermoplastic processing. Thermoplastics, which offer some advantages over thermosets, are limited in part complexity because of their forming processes. Ultrasonic welding offered the strongest bonds between thermoplastics (Ref. 458). Ultrasonics have been utilized for cleaning a wide variety of materials (Refs. 482-489), including metallic alloys (Ref. 489), beer kegs (Ref. 482), electronic substrates (Ref. 488), and precision glassware (Ref. 484). It has also been considered for the application of de-inking certain wastepapers which cannot be de-inked using conventional chemical methods (Ref. 486). In the areas of casting and solidification, ultrasonics were applied to metal processing (Refs. 490-499) in the 1970's during such methods as ingot solidification in continuous casting which resulted in a uniform and fine grain structure (Ref. 498). Ultrasonic excitation during the atomization of metal powders resulted in high dispersion and homogeneity, a spherical particle shape, and low (<0.02%) oxygen content (Ref. 495).

More recently, ultrasonics have been used in polymer, composite, and concrete processing (Refs. 500-509). Ultrasonic treatment has been shown to be a decisive factor in structure formation of cement paste (Ref. 509) while ultrasonic treatment of cold-solidifying plastic solutions can be used in the manufacture of plastic-metal composites (Ref. 493). The use of ultrasonics in this manner can reduce production time by factors of 2-5. Ultrasonic oscillations have also been shown to strengthen composite materials (Ref. 503). Transversal reinforcement with microparticles of polymer composites can increase the transverse tensile strength by factors of 1.8-2.5 and stiffness by 40-60%. The widespread use of this method, however, is hampered by the increase in static forces necessary to embed the microparticles. The superposition of ultrasonic vibrations on the static force can improve this transverse reinforcement method. Tomashevskii et al. concluded the ultrasonic vibrations can intensify the reinforcement process significantly while simultaneously reducing the effect of the materials resistance forces to the embedment

of the microparticles by a factor of three-fourths without a reduction in composite quality. Ultrasonics have been utilized during the past several years during the deposition of plated and other protective layers (Refs. 510-512), e.g., during electrolytic deposition of lustrous nickel. The ultrasonic treatment increased the hardness of the coating (Ref. 511). An ultrasonically assisted coating of aluminum with zinc resulted in a homogeneous layer, while a coating without an ultrasonic treatment was inhomogeneous (Ref. 512). Another important area of application has been in machining (Refs. 513-530). Ultrasonics have been used in the accelerated grinding and drilling of ceramics with a minimum of residual stresses; such removal methods are difficult to do by conventional means due to the hardness of most ceramics (Ref. 522). Ultrasonics displayed high removal rates and low machine wear (<0.5%) in the machining of graphite electrodes, (Ref. 524) and ultrasonic knives are being used to cut composite helicopter blades (Ref. 513). Finally, the effect of ultrasonic energy on the electrical and optical properties of materials have been the subject of scattered studies (Refs. 531-541).

C. SURVEY RESULTS

With these technological applications has come a variety of new equipment for processing and testing, as well as several monographs which have reviewed both the fundamentals and the applications of ultrasonics (Refs. 542-553). Several Russian authors have published books on the theory of ultrasonics. An article on a machine to be used for the ultrasonic welding of aluminum cans has been published (Ref. 547). Setting up a microprocessor assembly line using ultrasonics has also been described (Ref. 553).

It is interesting to note that the Soviet researchers again accounted for a large percentage of the work done in this area, about half of it (Refs. 381-411). Figure 4 shows the level of effort by country on the research into ultrasonic effects on materials.

The level of work in this area has also grown steadily, as shown in Figure 5.

Figure 6 shows the areas of emphasis of research.




Figure 4. Published Research on Ultrasonic Effects on Materials by Country (1960-1989)




Figure 5. Published Research on Ultrasonic Effect on Materials by Decade

Mechanical/Structural Effects	(65, 38%)
Bond/Weld	(32, 18%)
Other Processing	(24, 14%)
Machining/Coat/Clean	(29, 18%)
Miscellaneous	(22, 12%)

Figure 6. Areas of Literature Emphasis (1960-1989)

IV. MICROWAVE EFFECTS ON MATERIALS

The number of reported studies on the effects of microwaves on materials processing and properties has increased during the past decade. However, no references were cited in the decade from 1960-1970. Because of the unique heating characteristics of microwaves, most of the attention in the scientific and technical literature has been on the processing aspects of microwave interactions with materials. In the early 1970's, the first use of microwaves for drilling fine holes in ceramic wafers was reported (Refs. 554-555). Microwave micropiercing of ceramic wafers is preferable to conventional machining techniques because of the brittleness of ceramics. The microwaves dielectrically heat, melt, and vaporize these materials; conventional drilling may cause problems such as chipping. Early effects of microwaves on semiconductors were cited in the Soviet literature (Refs. 556-557) and on optical materials in the United States (Refs. 558-559). Two references to biological effects were also reported in this time frame in the nonmedical literature (Refs. 560-561).

Chabinsky (Ref. 561a) has reviewed present uses and future projections of microwaves in materials processing. For ceramics, a wide variety of applications in drying, slip casting, calcining and sintering were foreseen over the 5-year period from 1988-1993. Interesting and potentially important uses for microwaves in remediation (rubber, oil, asphalt) and in pollution control (disulfurization of coal, breakdown of hazardous materials) were addressed. In the medical/biological area, expanded uses were predicted in the areas of sterilization and waste treatment, and in the broad area of elastomers, polymers and composites, forming, drying, and curing were anticipated to be improved to commercially significant levels. For polymeric materials, McGrath and his colleagues (Ref. 561b) have demonstrated orders-of-magnitude time savings in processing with equivalent or improved mechanical properties (compared with conventional thermal treatments).

A. MICROWAVE SINTERING

The first published use of microwaves for sintering of ceramics was in France in the later 1970's (Ref. 562). During the 1980's, most of the reported literature on

microwaves focused on sintering behavior of structural ceramics, along with others on piezoelectric and photovoltaic materials (Refs. 563-594).

The interaction of microwaves with materials is dependent on the dielectric and magnetic properties of the material being processed. This results in a strong dependence of power absorption on frequency, particle size of the material, shape, temperature, and density. An electromagnetic wave, E , which is dependent on space, time, and materials properties, may be defined as

$$E = f(x, y, z, t, \epsilon, \mu) \quad (\text{Ref. 594}) \quad (\text{IV-1})$$

where

x , y , and z are distance coordinates in space,

t is time,

ϵ is permittivity, and

μ is permeability.

In terms of wave-material interactions, the properties of a material that are most important are the permittivity and the permeability. These are:

$$\text{Permittivity: } \epsilon^* = \epsilon' - j\epsilon'' = \epsilon_0 (\epsilon''_{\text{eff}}) \quad (\text{IV-2})$$

$$\text{Permeability: } \mu^* = \mu' - j\mu'' = \mu_0 (\mu'_{\text{f}} - j\mu''_{\text{eff}}) \quad (\text{IV-3})$$

where: ϵ' = dielectric constant

ϵ'' = loss factor

ϵ'_r = relative dielectric constant

ϵ''_{eff} = effective relative loss factor = $\epsilon''_r + \sigma/\epsilon_0\omega$

ϵ''_r = relative loss factor

σ = conductivity

μ' = permeability

μ'' = magnetic loss factor

μ'_r = relative permeability

μ''_{eff} = effective relative magnetic loss factor.

The wavelength, λ , of the electromagnetic wave decreases according to (Ref. 561d)

$$\lambda = \frac{\lambda_0}{\sqrt{\epsilon_r}} \quad (\text{for } \epsilon'' \text{ eff} \ll \epsilon_r') \quad (\text{IV-4})$$

and the field is attenuated

$$E = E_0 e^{-\alpha z} \quad (\text{propagation in Z-direction}) \quad , \quad (\text{IV-5})$$

where α : attenuation constant

$$\alpha = \frac{\sigma}{2} \left\{ \frac{\mu}{\epsilon} \right\}^{1/2} \quad , \quad \text{when } \frac{\sigma}{f\epsilon} < 1 \quad . \quad (\text{IV-6})$$

When the attenuated wave transfers thermal energy into the material, heating occurs, and power is dissipated according to (Ref. 561b)

$$P = K f \epsilon^2 \epsilon' \tan \delta \quad , \quad \text{where:} \quad (\text{IV-7})$$

P = power, in watts/cm³

E = electric field in volts/cm

f = frequency in Hz

K = constant = 55.61×10^{-14}

$\tan \delta$ = dielectric loss tangent = ϵ''/ϵ' .

Because several approximations and assumptions were made in the development of these relations (e.g., assume that thermal equilibrium exists), the latter equation simply shows general relationships between the variables. For example, it is assumed that no chemical reactions take place, and that thermal equilibrium exists. The loss tangent is also defined for a nonionic material.

If convection and conduction losses are ignored, the heating rate is defined as

$$\frac{dT}{dt} = \frac{KfE^2 \epsilon' (T) \tan \delta(T)}{\rho c_v} \quad (IV-8)$$

where:

ρ = density

c_v = specific heat (it is stressed that ϵ' and $\tan \delta$ are dependent on both temperature and frequency).

The thermal energy deposited into the material is limited by the depth of penetration of the electromagnetic field into the material. This depth has been derived by Metaxas and Meredith (Ref. 561f) to be

$$D = \frac{1}{2\omega} \left\{ \frac{2}{\mu_o \mu' \epsilon_o \epsilon'} \right\}^{1/2} \left[\left(1 + \left[\frac{\epsilon''}{\epsilon'} \right]^2 \right)^{1/2} - 1 \right]^{-1/2} \quad (IV-9)$$

where ω is frequency, in Hertz.

On a practical level, for a particular material, the size of the part determines the frequency at which it can be processed. At RF frequencies (several MHz to several hundred MHz), sizes are of the order of a meter. At microwave frequencies (GHz range) the sizes diminish to 20 cm or less. The latter is still of quite practical significance for commercial or military parts.

Bruce (Ref. 561g) has discussed several practical problems which may arise in microwave processing, such as thermal runaway, but these can be effectively avoided.

Microwave sintering is generally an improvement over conventional methods. It has the potential to provide homogeneous heating throughout the object as opposed to infrared heating where heat absorption starts at the surface (Ref. 594). Very close control over the heating process is also possible with microwaves, and very high temperatures (1500-2000°C) are achievable (Ref. 594). Microwaves have been shown to enhance

densification rates and lower the sintering temperature, which may result in lower energy utilization. Microwave plasma sintering of magnesia-doped alumina powder resulted in a sintering density in excess of 99% of theory in less than 2 minutes, and 99.9% in less than 10 minutes of processing (Ref. 593). Microwave sintering also reduced grain growth which may enhance a ceramic's mechanical properties (Ref. 585). The practical use of microwaves for the production of ceramic components is now being intensely studied in the United States.

B. OTHER PROCESSING AND MISCELLANEOUS EFFECTS

There has been growing interest in the use of microwaves during polymer and composite processing (Refs. 595-610). An increase in mechanical properties of 10% after an entire polymerization cycle of an epoxy matrix composite under the influence of microwaves has been reported (Ref. 601). The microwave processing of some polymeric materials decreased processing time from 1/3 to less than 1/10 of the original, provided homogeneous heating, and resulted in major energy savings in comparison with the conventional thermal process (Ref. 561b). The procedures are not fully understood yet, which has slowed use by industry. Microwaves have also been used to join ceramics, such as ceramic-glass-ceramic seals (Ref. 600). Isolated use has also been reported on the treatment of ores (Ref. 611) and of nuclear materials by microwaves (Ref. 612). The future use of microwaves seems to be limited only by the imagination of the user.

C. SURVEY RESULTS

Unlike other areas of this survey, Soviet work reported in the open literature on microwave effects has been extremely limited. This was quite surprising, since major new equipment for microwave processing is now available from the Soviet Union (Ref. 612a). The United States produced half of the surveyed literature. The breakdown by country is shown in Figure 7.

The interest on microwave effects has dramatically increased in the last three decades, as seen in Figure 8.

As mentioned, there has been a body of work (not included in this survey) on optical and biological effects. The areas of research included are shown in Figure 9. Much of this work has been on fabrication processes, with about 60% of that being on ceramic sintering.




Figure 7. Published Research on Microwave Effects on Materials by Country (1960-1989)




Figure 8. Published Research on Microwave Effects on Materials by Decade

Sintering	(33, 56%)
Other Fabrication	(20, 34%)
Miscellaneous	(6, 10%)

Figure 9. Areas of Literature Emphasis (1960-1989)

V. MAGNETIC FIELD EFFECTS ON MATERIALS

The interest in magnetic field effects up to 1989, as reported in the open literature, can be described as moderate. Most of the referenced work deals with the effect of magnetic energy on mechanical behavior of metals (including metallic glasses) and alloys, and on polymers; none of it is comprehensive, and some is conflicting (Refs. 613-662). Recently, some effort has been directed towards the effect of electromagnetic fields upon the wear of materials (Refs. 657-662).

A. EFFECTS ON STRUCTURE AND MECHANICAL PROPERTIES

The magnetoplastic effect has been the main focus of the literature in this survey. Depending on the material and test conditions, several different mechanisms are proposed to be responsible for the effect. The cause of the magnetoplastic effect, however, is not yet fully understood or agreed upon.

Much of the study of magnetoplasticity has been done on both single and polycrystalline ferromagnetic metals. The changes in plastic flow in such metals have been attributed to the effect of the magnetic field on domain boundaries, which elastically interact with dislocations (Ref. 645). In a field of 0.25 Tesla, it was determined that there was a 10% increase in the flow stress in nickel (Ref. 656). Conversely, a 15% reduction in yield stress has been observed in nickel when placed in a variable magnetic field parallel to the extension axis (Ref. 632). The explanation attributed the cause to the oscillation of domain boundaries which unpinned dislocations and facilitated their movement along slip planes. High purity, polycrystalline iron placed in a high-intensity, constant magnetic field showed a 500% increase in creep rate (Ref. 657). Yield strength has, however, also been reported to increase in a magnetic field. Kononenko and Pustovalov reported that repeated loading of monocrystalline nickel up to its yield strength in a constant magnetic field at 4 °K resulted in domain structures and dislocations being formed and pinned (Ref. 656). The result was a maximum increase in yield strength of 20% (Ref. 656). An investigation by Bolshutkin, Denenko, and Ill'ichev studied the effect of full saturation of magnetization of polycrystalline nickel at 3.4 Tesla. They observed an increase of 10% in the flow strength of nickel, as was previously noted (Ref. 656). They also observed an increase in the

deformation hardening coefficient and deforming stress as the field increased. They attributed these changes to magnetostriction and Joule heating in the nickel by eddy currents, as well as to the domain-dislocation interaction (Ref. 656).

Studies of magnetoplasticity have been also conducted on nonmagnetic metals. In 1981, Lebedev and Krylovskiy observed an increase in the yield point of aluminum and lead in a magnetic field at low temperature (Ref. 645). They concluded that this was the result of an increase in electronic frictional force of dislocations. Tensile tests were performed at 4 °K with a force of 0.04 N for 25 seconds in a 3 Tesla field. For 1-2% deformation, the change in stress ($\delta\sigma = \sigma(H) - \sigma(0)$) grew and then fell rapidly (Ref. 645). The maximum increases of $\delta\sigma$ for aluminum, lead, and indium were 0.6, 0.45, and 1.3%, respectively (Ref. 645). For 4-5% deformation, the $\delta\sigma$ values became zero; the magnetic field had no effect beyond deformation greater than 5% (Ref. 645). The resistivity (ρ), which gradually rose as deformation increased, was used to estimate the electron relaxation time (t) as

$$t = \rho / A v_F \quad (V-1)$$

where A is a constant of the material, and v_F is the Fermi velocity (Ref. 645). The term ωt (ω is the cyclotron frequency) can be calculated using,

$$\omega = 2\pi v_c \quad (\text{Ref. 730}) \quad (V-2)$$

where v_c (109 Hertz) = 2.80H, and H is the magnetic field in kilogauss.

Lebedev and Krylovskiy's calculations showed that ωt fell an order of magnitude, from 10^2 to 10 at a deformation of 5% (Ref. 645). They then used theoretical models which define the change in mechanical characteristics under conditions of the superconductive transitions as a function of the electronic system of the crystal to show that the change in stress was associated with growth of the coefficient of electronic frictional resistance in the magnetic field (Ref. 645). The influence of the field, which is dependent on ωt , decreased as the amount of deformation grew, and was no longer effective on the plastic stress at $\omega t \approx 1$ (Ref. 645).

Experimentation on the magnetic effect on wear has been performed (Refs. 657-662). Some researchers reported increased wear resistance, while others have claimed increased wear rate. The effects and mechanisms of magnetic fields on wear are not yet understood, and they may be of importance for electromagnetic gun design.

Another change that takes place in a magnetic field at low temperatures that may affect mechanical properties of materials is the f.c.c. --> b.c.c. martensitic transformation. Fultz and Morris studied the effects of this transformation and determined that the changes in strength were of little engineering consequence. They were, however, useful in understanding the f.c.c. --> b.c.c. martensitic transformation (Ref. 646). In the magnetic field, a reduction in flow stress at small strains was recorded; but at large strains, an increase in work hardening and flow stress was noted. Reduction in elongation of the specimens was also observed.

B. PROCESSING AND MISCELLANEOUS EFFECTS

The effects of magnetic fields on the structure of materials, including polymers (filled and unfilled), during crystallization have been noted (Refs. 679-682). A magnetic field applied during the polymerization of an EDT-10 epoxy resin increased the degree of structural ordering and promoted the formation of crystalline regions in the amorphous material (Ref. 666). Molchanov et al. reported greater hardness and homogeneity in thermoplastics and thermosets subjected to a 0.8 Tesla field during processing. The hardness of Kapron increased from 4 N/mm² to 38 N/mm² (Ref. 679).

Another area of study has dealt with the effect of magnetic fields applied during annealing of materials (especially metallic glasses) on their electric and magnetic properties (Refs. 663-665, 667, 678, 683-704). Magnetic fields have been shown to improve the magnetic properties of such materials. Magnetic phase transitions also have been observed in strong magnetic fields (Refs. 705-708).

Other processes using magnetic fields have also been explored (Refs. 709-721). Application during vacuum metallization with closed field sputtering equipment reduced the source temperature and increased coating speed (Ref. 716). Magnetic fields have been used to orient macromolecules, which could improve the final quality of the polymers and reduce the production cost (Ref. 717). Isolated reports of the magnetic effect on optical properties of materials were also noted (Refs. 722-730). Finally, pulsed magnetic metal forming (Ref. 731) may offer new opportunities for welding and mechanical bonding of

similar and dissimilar metals and alloys, and for swaging of superconducting wires. With activities increasing in the use of electromagnetic power systems and other devices during the past few years, new interest in the fundamental behavior of materials in these environments can be expected.

C. SURVEY RESULTS

As mentioned, magnetoplasticity was the focus in the literature in the last three decades. Overall, the Soviet researchers once again accounted for much of the work done, slightly less than half. U.S. contributions were nearly 20%. Figure 10 reveals the level of effort by country.

As with microwave effects, the amount of research on magnetic effects on materials also grew rapidly in the last three decades, as seen in Figure 11.

Figure 12 shows the areas of emphasis, as revealed by the literature search.




Figure 10. Published Research on Magnetic Field Effects on Materials by Country (1960-1989)




Figure 11. Published Research on Magnetic Effects on Materials by Decade

Magnetoplasticity	(50, 43%)
Solidification and Other Processing	(33, 28%)
Magnetic & Electric Properties	(22, 19%)
Miscellaneous	(12, 10%)

Figure 12. Areas of Literature Emphasis (1960-1989)

VI. CONCLUSIONS

This survey has determined that there has been a marked increase of activity and interest in the effects of electrical, magnetic, microwave, and acoustic energies on materials, especially in the last decade. While ultrasonic effects had been the focus of many studies prior to 1960, major scientific and technological activity has occurred in the area of electroplasticity, especially by Troitskii and Conrad. Indeed, the mechanisms of electroplasticity are better understood than the underlying bases of the other phenomena in this review.

Potential uses of electrical energy for materials processing have been shown to be advantageous. The effect of a high density current pulse (10^3 A/mm², 50 μ s duration) has been demonstrated to have a large effect (10-40%) on load drop during tensile tests of zinc crystals (Ref. 29). The high density current pulse resulted in a large increase in plastic deformation (100-120%) during the same tests.

What this can mean in terms of practical consequences is that, since cavitation is retarded, processes such as superplastic forming can be extended to larger uniform deformations (Ref. 145). It is also expected, since cavitation often provides limits to deformation processing operations such as deep drawing, swaging, and extrusion, that the application of electric currents should be of significance in deformation processing by eliminating the need for intermediate annealing during processing. This has been found to be true (Ref. 139), but additional processing procedures should be explored for materials that are normally difficult to form by deformation, such as refractory metals and alloys.

Likewise, the concurrent application of high density current pulses (1.3×10^{-4} A/cm²) during cyclic tests extended the fatigue life of copper by two- to three-fold (Ref. 146). What is particularly notable is that these pulses were only active 10^{-4} of the entire test time (Ref. 146). An additional benefit of the effects of electrical currents superimposed upon mechanical load cycling might be realized in electromagnetic guns. In this case, the fatigue lives of such guns can be expected to be much longer than the original design predictions, because both crack initiation and growth rate should be extended.

Finally, the industrial significance of the large effects of electric currents on the hardenability of steels also needs to be evaluated.

Ultrasonic treatment of stainless steels and aluminum alloys has resulted in increased hardness (20-40%) after only short exposures (30 seconds-5 minutes); the same amounts of hardening by natural aging would have taken much longer (\approx 24 hours) (Ref. 412). Similarly, large increases (218%, 10 hours) in yield strength have been recorded as well as creep rate reductions (\approx 60%, 30 seconds) (Ref. 412). Here again, the potential industrial savings to be gained through these treatments, in terms of energy and materials conservation, should be assessed.

Special attention has been given to wire drawing, as ultrasonic energy has been shown to reduce the drawing force (5-75% for drawing rates of 10-1000 feet per second) for copper and steel wires (Ref. 437). Tube drawing revealed similar results (1-30% reduction in force) for aluminum, steel, and titanium alloys. It also resulted in a smooth drawing (absence of stick-slip) which is not possible by conventional means.

Ultrasonic processing of other materials (other than metals) has been performed. Ultrasonic modification of cold-solidified plastic solutions during the processing of metal-plastic composites may reduce processing time by factors of 2-5 (Ref. 493). Ultrasonics have been demonstrated to be able to assist in machining a variety of products ranging from ceramics (Ref. 522) to graphite electrodes (Ref. 524) and composite helicopter blades (Ref. 513). Ultrasonic welding and other bonding methods assisted by ultrasonics have been in use for some years.

The ability of microwaves to provide rapid heating and very high temperatures (1500-2000 °C) provides such methods with the potential for use in a multitude of processes, such as sintering of ceramics. Microwave processing provides homogeneous heating, fast sintering times (1-10 minutes), and good control of the heating process. In addition, microwave sintering reduces grain growth, which may enhance the ceramic's mechanical characteristics (Ref. 585).

In addition to sintering effects, microwaves have been demonstrated to improve the mechanical properties (by 10%) of epoxy matrix composites during polymerization (Ref. 601). This effect is not as marked as the time savings achieved in processing of polymer-based materials. Microwave processing of some polymeric materials in 1/10 the normal time has been reported (Ref. 561b). The advent of equipment of greater versatility,

both in the United States and from the Soviet Union, should speed the practical industrial uses of microwave processing.

The magnetoplastic phenomenon is not yet fully understood, which impedes its possible applications to processing. Nonetheless, improvements in yield strength (20%) in single crystals of nickel in a magnetic field were reported, as was improved hardenability (Ref. 656). In the processing of polymers and magnetic metals, magnetic fields have provided enhanced structural ordering.

It was not surprising to find that Soviet research on the effects of electrical, magnetic, and acoustic waves on materials predominated in the world's open literature on these topics. In contrast, reports of microwave effects on materials from the Soviet Union were sketchy, at best. It appears likely, from the appearance of sophisticated Soviet microwave processing equipment in the commercial marketplace, that much work had been going on that was not published in the open literature. With increased access to scientific information becoming available in parts of the former Soviet Union, one can expect new light to be shed on the fundamentals of microwave effects on properties and processing of materials.

Enhancements resulting from processing with electrical, magnetic, microwave, and acoustic energies have been demonstrated to different degrees. Not only may these energies promote favorable structures and mechanical properties in metals, as has been known, but they may also offer new processing techniques for polymers, ceramics, and composites. In view of the fact that industry presently utilizes only a small portion of these enhancing energies, future efforts should focus on converting more of these effects from laboratory observations to industrial realities.

REFERENCES

A. ELECTRICAL CURRENT AND FIELD EFFECTS

1. O. A. Troitskii, N. E. Kir'tanchev, and S. A. Klevtsur, "Electroplastic Deformation of Metals", *Probl. Prochn.*, Vol. 15, No. 5, 1983, 101-105.
2. O. A. Troitskii, and M. M. Moiseenko, "Electroplastic Deformation of Zinc, Cadmium, and Lead Crystals", *Izv. Akad. Nauk. SSSR Met.*, No. 1, 1987, 162-163.
3. O. A. Troitskii, V. G. Ryzhkov, and N. V. Sokolov, "Pulsed Current Generator for Studying the Electroplastic Deformation of Metals", *Elektron. Obrab. Mater.*, No. 3, 1979, 81-83.
4. O. A. Troitskii, and V. I. Spitsyn, "Influence of Electric Current and a Pulsed Magnetic Field on the Creep Rate of a Metal", *Soviet Physics - Dokl.*, 19, (6), 1974, 380-382.
5. O. A. Troitskii, V. Spitsyn, A. Kop'ev, V. Ryzhkov, and N. Sokolov, "Flattening Mill for Ultrafine Spring Strip and Tungsten, Employing Ultrasound and Electroplastic Effect", *Dokl. Akad. Nauk SSSR*, Vol. 236, No. 4-6, 1977, 861-862.
6. O. A. Troitskii, "Electroplastic Deformation of Metal", *Strength of Materials*, Vol. 8, No. 12, 1976, 1466-1471.
7. O. A. Troitskii, "Electroplastic Effect in Metals", *Priroda*, No. 10, 1970, 28-33.
8. O. A. Troitskii, "Electroplastic Effects in a Metal Single Crystal Deformed in an Electron Beam", *Soviet Physics - Solid State*, Vol. 13, No. 1, 1971, 146-148.
9. O. A. Troitskii, "Instrumental Effects in Investigations of Electroplastic Deformation", *Industrial Laboratory - USSR*, Vol. 50, No. 1, 1984, 87-89.
10. O. A. Troitskii, "Rate and Temperature Dependence of the Electroplastic Effect", *Phys. Me. Metallogr.*, Vol. 32, No. 2, 1971, 178-183.
11. O. A. Troitskii, and P. U. Kalymbetov, "Dependence of the Electroplastic Effect on the Applied Stresses For Zinc Crystals", *Izv. Akad. Nauk SSSR Met.*, No. 3, 1981, 85-88.
12. O. A. Troitskii, A. M. Roshchupkin, V. I. Stashenko, et al., "A Development of the Concept of the Direct Physical Action of Current in the Electroplastic Effect", *Fizika Metallov i Metallovedenie*, Vol. 61, 1986, 990-995.

13. O. A. Troitskii, and E. Linke, "Electron Emission During Electroplastic Deformation of Metals", *Fiz. Met. i Metalloved*, Vol. 52, No. 5, 1981, 1084-1090.
14. O. A. Troitskii, and L. G. Maistrenko, "Electroplastic Deformation in Metals", *Soviet Material Science*, Vol. 8, No. 6, 1972, 686-688.
15. O. A. Troitskii, and M. M. Moiseenko, "A Method of Electroplastic Deformation of Metal", *Zavod. Lab*, (9), 1985, 57-60.
16. O. A. Troitskii, and M. M. Moiseenko, "Effect of the Current Pulse Duration on Active Deformation of Zinc Single Crystals", *Elektronnaya Obrabotka Materialov*, No. 2, 1985, 24-26.
17. O. A. Troitskii, and M. M. Moiseenko, "Electroplastic Strain Method For Metals", *Zavod. Laboratory*, Vol. 51, No. 9, 1985, 57-60.
18. O. A. Troitskii, and P. U. Kalymbetov, "Applied Stress Dependence of the Electroplastic Effect", *Izv. Akad. Nauk SSSR Met.*, (3), 1981, 85-88.
19. O. A. Troitskii, and V. I. Spitsyn, "Electroplastic Deformation of Metals", *Priroda*, 1977, 30-43.
20. O. A. Troitskii, and V. I. Spitsyn, "Investigation of the Electroplastic Deformation of a Metal by the Method of Stress Relaxation and Creep", *Soviet Physics - Dokl.*, 21 (2), 1976, 111-113.
21. O. A. Troitskii, and V. I. Stashenko, "Investigation of Electroplastic Deformation of Metals By the Stress Relaxation Method", *Fiz. Met. and Metalloved*, Vol. 47, No. 1, 1979, 180-187.
22. O. A. Troitskii, I. L. Skobtsov, and A. V. Men'shikh, "Electroplastic Deformation of a Metal Preceding Brittle Rupture", *Fizika Metallov i Metallovedenie*, Vol. 33, 1972, 393-399.
23. O. A. Troitskii, P. U. Kalymbetov, and V. I. Spitsyn, "Electron-Plastic Effect in Counter Pulses", *Dokl. Akad. Nauk SSSR*, 253, (1), 1980, 96-100.
24. O. A. Troitskii, T. K. Chormonov, and P. U. Kalymbetov, "Electroplastic Effect in Irradiated Zinc Crystals", *Dokl. Akad. Nauk SSSR*, Vol. 260, No. 4-6, 1981, 880-883.
25. O. A. Troitskii, V. I. Spitsyn, and M. M. Moiseenko, "Effect of Electrical Pulse Series on the Metal Plastic Deformation", *Doklady Akademii Nauk SSSR*, Vol. 274, No. 3, 1984, 587-590.
26. O. A. Troitskii, V. I. Spitsyn, and V. I. Stashenko, "Effect of the Main Current Parameters on the Size of the Electron-Plastic Effect", *Dokl. Akad. Nauk SSSR*, Vol. 256, No. 5, 1981, 1134-1137.
27. O. A. Troitskii, V. I. Spitsyn, M. M. Moiseenko, V. P. Lyashenko, et al., "Electroplastic Deformation of Tungsten", *Dokl. Akad. Nauk SSSR*, Vol. 295, No. 4-6, 1987, 1114-1119.

28. O. A. Troitskii, and M. M. Moiseenko, "The Rate Dependence of the Electroplastic Effect", *Izv. Akad. Nauk SSSR, Met.*, (2), 1985, 179-183.
29. O. A. Troitskii, V. I. Spitsyn, and P. I. Glazunov, "Electroplastic Deformation of Metal Before Brittle Fracture", *Soviet Physics - Doklady*, Vol. 16, 1972, 666-669.
30. O. A. Troitskii, V. Spitsyn, and P. U. Kalymbetov, "The Electroplasticity Effect in Oppositely Moving Pulses", *Dokl. Akad. Nauk SSSR*, Vol. 253, No. 1-3, 1980, 96-100.
31. O. A. Troitskii, V. I. Spitsyn, A. A. Gavrish, et al., "X-Ray Diffractometric and Physical-Mechanical Investigation into Copper Subject to Electroplastic Drawing", *Izv. Akad. Nauk. SSSR Met.*, No. 4, 1978, 120-124.
32. O. A. Troitskii, V. I. Spitsyn, V. I. Gol'danskii, et al., "Phase Composition and Structure of Stainless Steel Wire After Electroplastic Drawing", *Dokl. Akad. Nauk. SSSR*, Vol. 268, No. 4-6, 1983, 871-874.
33. O. A. Troitskii, and V. I. Stashenko, "The Effect of a Pulsed Current on Zinc Single Crystal During Creep", *Fiz. Met. Metalloved*, Vol. 56, No. 5, 1983, 1021-1030.
34. O. A. Troitskii, and V. I. Stashenko, "Influence of Form and Method of Applying Impulse Current on the Plastic Deformation of Zinc Crystals", *Dokl. Akad. Nauk SSSR*, Vol. 267, No. 3, 1982, 638-640.
35. O. A. Troitskii, "Effect of the Electron State of a Metal on Its Mechanical Properties and the Phenomenon of Electroplasticity", *Strength of Materials*, Vol. 9, No. 1, 1977, 35-45.
36. O. A. Troitskii, "Pressure Shaping by the Application of High Energy", *Material Science and Engineering*, Vol. 75, 1985, 37-50.
37. O. A. Troitskii, "Strengthening of Metal Crystals Subjected to Cyclic Loading Under the Simultaneous Action of an Electric Current", *Sov. Mater. Sci.*, Vol. 15, No. 2, 1979, 176-178.
38. O. A. Troitskii, "Strengthening of Metallic Crystals Subject to Preliminary Loading With Current", *Izv. Akad. Nauk. SSSR Met.*, No. 4, 1979, 160-163.
39. O. A. Troitskii, V. I. Spitsyn, N. V. Sokolov, and V. G. Ryzhkov, "Electroplastic Drawing of Stainless Steel", *Soviet Physics - Dokl.*, Vol. 22, No. 12, 1977, 769-770.
40. O. A. Troitskii, V. I. Spitsyn, N. V. Sokolov, et al., "Electroplastic Drawing of Magnetically Hard Steel Wire", *Izv. Akad. Nauk. SSSR Met.*, No. 2, 1979, 113-114.
41. O. A. Troitskii, V. I. Spitsyn, and V. G. Ryzhkov, "Electroplastic Drawing of Steel, Copper, and Tungsten", *Dokl. Akad. Nauk SSSR*, Vol. 243, No. 1-3, 1978, 330-333.

42. O. A. Troitskii, V. I. Staschenko, and A. S. Kozyrev, "Reduction in the Tendency of Fine Copper Wire to Break During Electroplastic Drawing", *Elektron. Obrab. Mater.*, No. 3, 1981, 38-40.
43. O. A. Troitskii, A. Roshchupkin, I. Bataronov, and M. Moiseenko, "Electric Current Effect on Metal Surface Layers", *Physica Status Solidi B*, Vol. 151, No. 1, 1989, 121-126.
44. O. A. Troitskii, V. Stashenko, Y. Yanovskii, and L. Ulyanov, "Estimation of the Effect of Electric Current on the Dislocation Mobility in Cadmium", *Russian Metallurgy*, No. 2, 1981, 148-153.
45. O. A. Troitskii, "Effect of Pulsed Electric Current on the Brittle and Quasibrittle Fracture of Zinc", *Metallofizika*, Vol. 44, 1973, 11-16.
46. O. A. Troitskii, "Increase in the Plastic Deformation Rate of a Metal Under the Effect of Electric Current Pulses", *Vysokoskorostnaya Deform. Mater. Nauch.-Tekh. Soveshch. Teor. Prakt. Vysokoskorostnoi Deform.*, 1971, 50-54.
47. O. A. Troitskii, V. I. Spitsyn, and V. I. Stashenko, "The Effect of an Electric Current on the Relaxation of Stresses in Crystals of Zinc Cadmium, and Lead", *Soviet Physics Dokl.*, 23, (7), 1978, 509-511.
48. O. A. Troitskii, and A. Rozno, "Effect of Electric Currents on Plastic Deformation of Metals", *Fizika Metallov i Metallovedenie*, Vol. 30, No. 4, 1970, 824-829.
49. O. A. Troitskii, I. Skobtsov, and A. Men'shikh, "Electroplastic Deformation of a Metal Preceding Brittle Rupture", *Fizika Metallov i Metallovedenie*, Vol. 33, 1972, 392-399.
50. Y. Golovin, "Mechanisms of Failure of Crack-Containing Metals Under the Effect of the Electromagnetic Field", *Fiz. Khim. Orab. Mater.*, Vol. 17, No. 8, 1983, 6.
51. A. A. Klypin, and A. A. Luchina, "Effects of Contact Between Differing Metals on Creep of Copper and Aluminum", *Russian Metallurgy*, (2), 1985, 133-142.
52. Y. Baranov, A. Tananov, S. Koryagin, G. Nikolaishvili, and I. Matsegorin, "Substructure Changes in Copper Under the Effect of Pulsed Electric Current", *Physics and Chemistry of Materials Treatment*, Vol. 24, No. 4, 1990, 403-407.
53. A. I. Dertagin, and V. A. Zavalishin, "Role of Thermoelectric Phenomena in the Electroplastic Effect", *Fiz. Met. and Metalloved.*, Vol. 58, No. 4, 1984, 782-785.
54. V. N. Dorovskii, A. M. Iskol'dskii, and E. I. Romenskii, "Dynamics of Pulsed Current Heating of a Metal and Electrical Explosion Conductors", *Zhurnal Prikladnoi Mekhaniki i Tekhnicheskoi Fiziki*, No. 4, 1983, 10-25.
55. V. M. Finkel, V. M. Ivanov, and Y. I. Golovin, "Crack Healing in Metals Crossed by Electric and Magnetic Fields", *Problemy Prochnosti*, No. 4 (166), 1983, 54-58.
56. Y. M. Gel'fgat, M. Z. Sorkin, and A. E. Mikel'son, "Distribution of Componentes in a Melt of Immiscible Metals in Crossed Electromagnetic Fields," *Magneto hydrodynamics*, Vol. 13, No. 1, 1977, 99-101.

57. K. M. Klimov, "Electroplasticity of Metals", *Doklady Akademii Nauk SSSR*, Vol. 219, No. 2, 1974, 323-324.
58. K. M. Klimov, and I. I. Novikov, "Problem of Eletron-Plastic Effect", *Problemy Prochnosti*, No. 2 (176), 1984, 98-103.
59. K. M. Klimov, and I. I. Novikov, "The Effect of Instrumentation Parameters on the Magnitude of the Recorded Electroplastic Effect in Metals", *Izv. Akad. Nauk. SSSR Met.*, (1), 1987, 158-161.
60. K. M. Klimov, G. D. Shnyrev, and I. I. Novikov, " 'Electroplasticity' of Metals", *Soviet Physics - Dokl.*, 19 (11), 1975, 787-788.
61. K. M. Klimov, I. I. Novikov, and G. D. Shnyrev, "Electroplasticity of Refractory Metals and Alloys During the Roll-Forming of a Wire into a Ribbon", *Physio-Mechanical and Thermophysical Properties of Metals*, 1976, 184-189.
62. V. M. Kontorovich, "Dynamic Equations of the Elasticity Theory in Metals", *Uspekhi Fizicheskikh Nauk*, Vol. 142, No. 2, 1984, 265-307.
63. A. N. Kulichenko, and B. I. Smirnov, "Influence of an Impurity on the Electroplastic Effect in Alkali Halide Crystals", *Fiz. Tverd. Tela*, Vol. 25, No. 5, 1983, 1523-1525.
64. V. I. Nikolaev, and B. I. Smirnov, "Electroplastic Effect in Ferroelectric NaNO_2 Single Crystals", *Fiz. Tverd. Tela*, Vol. 27, No. 11, 1985, 3369-3372.
65. Y. A. Ossipyany, and V. S. Bobrov, "The Electron Dislocation Interaction and Electronic Effects at Low Temperature Deformation", *Crystal Research and Technology*, Vol. 19, No. 6, 1984, 827-838.
66. L. N. Sokolov, A. I. Andrusenko, and V. N. Efimov, "Apparatus for Determining the Mechanical Properties of Current Conducting Materials in an Electroplastic State", *Industrial Laboratory - USSR*, Vol. 50, No. 1, 1984, 105-107.
67. L. N. Sokolov, A. I. Efimov, and V. N. Andrusenko, "Effect of Electro-Pulse Softening of Metals", *Russian Metallurgy*, No. 6, 1986, 180-185.
68. V. I. Spitsyn, "Electroplastic Effect in Metals", *Vestnik Akademii Nauk SSSR*, No. 11, 1974, 10-15.
69. A. I. Tananov, N. N. Beklemishev, B. N. Zhurkin, V. S. Akinshin, and A. E. Gorskii, "Methods of Evaluating the Mechanical Properties of Metallic Materials Subjected to Electric Effects", *Industrial Laboratory - USSR*, Vol. 49, No. 7, 1983, 744-753.
70. A. V. Zaretskii, A. Osip'yan, and V. F. Petrenko, "Mechanism of the Electroplastic Effect in ZnSe ", *Fiz. Tverdogo Tela*, Vol. 21, No. 5, 1978, 1442-1450.
71. N. N. Beklemishev, N. I. Koryagin, and G. S. Shapiro, "The Effect of a Locally Inhomogeneous Pulsed Electromagnetic Field on the Ductility and Strength of Conducting Materials", *Izv. Akad. Nauk SSSR Met.*, (4), 1984, 184-187.

72. N. N. Beklemishev, E. N. Vedenyapin, and G. S. Shapiro, "The Law for the Deformation of Conducting Materials Under the Action of a High Frequency Electric Current", *Problemy Prochnosti*, (1), 1984, 106-109.
73. G. N. Belozerskiy, A. A. Gavrish, V. V. Dudolayev, et al., "Investigation of Stainless Steel Wire During and After Electroplastic Drawing," *Russian Metallurgy*, No. 5, 1983, 197-200.
74. V. Finkel, Y. Golovin, V. Ivanov, A. Sletkov, and V. Ivanov, "Hardening of Metal at the Crack Tip Due to a Current Pulse", *Fiz. Khim. Obrab. Mater.*, (2), 1981, 42-45.
75. V. E. Gromov, N. M. Seloverstov, E. V. Semakin, and L. I. Gurevich, "Equipment for Pulse Loading Crystals While Passing a Current Through the Sample", *Zavod. Lab.*, Vol. 44, No. 3, 1978, 358-361.
76. K. M. Klimov, and I. I. Novikov, "Effect of Electrostimulated Deformation on the Fine Structure and Mechanical Properties of Polycrystalline Molybdenum", *Dokl. Akad. Nauk. SSSR*, Vol. 260, No. 6, 1981, 1361-1362.
77. V. P. Lebedev, and V. I. Khotkevich, "The Effect of Electrical Impulses on the Low Temperature Deformation of Aluminum", *Fizika Met. i Metalloved*, 1982, 353-360.
78. V. D. Mutovin, K. M. Klimov, et al., "Production of Tungsten Rolled Product by Electroplastic Rolling of Wire", *Izv. Akad. Nauk. SSSR Met.*, No. 4, 1978, 125-129.
79. V. Bolotov, and V. Stuchinskij, "Determination of Specific Times of Inhomogeneous Profile Formation For Vacany Defects in Silicon at the Interface Under the Effect of an Electric Field", *Fizika Tekh. Poluprovodn*, Vol. 22, No. 8, 1988, 1405-1407.
80. P. Kuchinskij, V. Lomako, and A. Petrunin, "Strong Electric Field Effect on Velocity of Introduction and Spatial Distribution of Radiation-induced Defects in Silicon", *Pisma Zh. Tekh. Fizika*, Vol. 11, No. 5, 1985, 309-311.
81. A. Mamontov, V. Peshev, and I. Chernov, "Effect of an Electric Field on the Accumulation and Annealing of Radiation-induced Defects in Gallium Arsenide", *Fizika Tekh. Poluprovodn.*, Vol. 16, No. 12, 1982, 2126-2128.
82. B. Vekhter, M. Kaplan, and I. Novosel'skii, "Effect of an Electric Field on Elastic Properties of $DyVO_4$ ", *Fizika Tverd. Tela*, Vol. 21, No. 5, USSR, 1979, 1386-1391.
83. A. Derendovski, "Effect of Electric Current on Cavitation Erosion and on the Microscopic Substructure of Metal", *Dokl. Akad. Nauk SSSR*, Vol. 183, No. 6, 1968, 1292-1294.
84. V. Kazakov, A. Kuznetsov, G. Poromenskaya, A. Prokhorov, and S. Vladimirov, "A Study of the Effect of Electric Current Processing on the Structure and Properties of Cold Deformed AlMg₅P Alloy", *Tekhnologiya Legkikh Splavov*, No. 1, 1984, 42-45.

85. N. Beklemishev, Y. Baranov, Y. Doronin, A. Valyutin, and A. Tananov, "Effect of Pulsed Electric Current on Mechanical Characteristics of Structural Metallics Materials", *Physics and Chemistry of Materials Treatment*, Vol. 24, No. 4, 1990, 399-402.
86. V. Borisov, Y. Golovin, and V. Ivanov, "Electric Current Effects on Strength of Steel Plates with Stress Concentrators", *Problemy Prochnosti*, No. 2 (176), 1984, 92-95.
87. L. Novogrudskii, "Evaluation of the Strength of Structural Materials at Cryogenic Temperatures Under the Effect of Electric Current Pulses", *Problemy Prochnosti*, No. 12, 1985, 78-81.
88. Y. Taran, A. Prigunova, V. Glachak, S. Petrov, and I. Belkov, "Effect of Electric Current on Structural Transformations in Complexly Doped Aluminum-silicon Melts", *Melts*, Vol. 1, No. 4, 1988, 377-382.
89. E. V. Kalabukhova, V. Maevskii, B. Shanina, and B. Krulikovskii, "Investigation of the Process of Reorientation of Mn^{2+} Vacancy Complexes in NaCl by the Electric Field Effect in ESR", *Fizika Tverdogo Tela*, Vol. 20, No. 3, 1978, 715-719.
90. K. Klimov, and I. Novikov, "Effect of Electric Current Pulses on Tensile Strain of Thin Metal Wires", *Izvestiya Akademii Nauk SSSR, Metally*, No. 3, 1983, 155-159.
91. M. Korzhuev, and A. Laptev, "Effects Involving Electric-current-induced Changes in the Composition of Samples of Superionic $Cu^{2-x}Se$ ", *Zhurnal Tekhnicheskoi Fiziki*, Vol. 59, No. 4, 1989, 62-67.
92. V. Lobanov, and M. Aleksankin, "Effect of External Electric Field on the Electronic Structure of Molecules and Their Cation-Radicals", *Teoreticheskaya i Eksperimentalnaya Khimiya*, Vol. 16, No. 4, 1980, 477-486.
93. K. Valiev, V. Mokerov, and A. Rakov, "Effects of an Electric Field on Electronic Structure in Single Crystals of Vanadium Pentoxide", *Fizika Tverdogo Tela*, Vol. 15, No. 2, 1973, 361-367.
94. L. Zuev, V. Gromov, and V. Gurevich, "The Effect of Electric Current Pulses on the Dislocation Mobility in Zinc Single Crystals", *Physica Status Solidi A.*, Vol. 121, No. 2, 1990, 437-443.
95. L. Zuev, V. Gromov, and V. Sergeev, "The Effect of an Electric Field on the Charged Defects in Crystals of NaCl Structure", *Acta Crystallographica, Section A*, Vol. A31, pt. S3, 1975, S269.
96. S. Abasov, E. Jalal Kyzy, M. Alieva, and M. Kurbanov, "Effect of an Electric Field on the Mechanical Strength of Gallium Selenide Single Crystals", *Dokl Akad. Nauk Az. SSSR*, Vol. 39, No. 9, 1983, 32-35.
97. E. Belozerova, and A. Svetashov, "Electric Field Effect on Dislocation Mobility and Mutiplication During Ultrasound Vibration of Differently Orientated Alkali Halide Crystals", *Fizika Tverdogo Tela*, Vol. 27, No. 4, 1985, 1996-2000.

98. V. Boroditskiy, V. Maltsev, I. Nikiforov, E. Shneider, and Y. Zakharov, "Effect of an Electric Field on the Degree of Mosaicity of Barium Titanate Crystals", *Kristallografiya*, Vol. 20, No. 2, 1975, 366-370.
99. V. Gromov, and L. Gurevich, "Effect of Electric Current Impulses on the Dislocation Mobility in Zinc at 77 K", *Izv. Vyssh. Uchebn. Zaved., Fizika*, Vol. 33, No. 3, 1990, 35-39.
100. V. Gromov, L. Gurevich, V. Kurilov, and T. Erilova, "Effect of Electric Current Pulses on the Mobility and Multiplication of Dislocations in Zinc", *Problemy Prochnosti*, No. 10, 1989, 48-53.
101. S. Koftsov, N. Kopylov, V. Drozd, O. Trofimov, and V. Aleskovskii, "Effect of an Electric Field on the Structure of Titanium Oxide Layers", *Dokl. Akad. Nauk SSSR*, Vol. 262, No. 2, 1982, 375-377.
102. T. Rykova, D. Mikhailov, and B. Kasatkin, "Effect of an Electric Field on the Structure and Properties of Chalcogenide Glasses", *Tezisy Dokl. Vses. Simp. Elektr. Svoistvam Str. Stekla.*, 4th, 1977, 148-150.
103. A. Suvorov, and G. Kukavadze, "Mobility of Displaced Atoms and Their Complexes in a Crystal Lattice of Tungsten Under the Effect of an Electric Field", *Monokrist. Tugoplavkikh Redk. Metal., Mater. Vses. Soveshch.*, 3rd, 1971, 108-111.
104. T. Travina, L. Golik, M. Elinson, V. Ignatkin, and V. Lyakhovitskaya, "Effect of an Electric Field on the Movement of Interphase Boundaries in the Ferroelectric SbSI", *Fizika Tverdogo Tela*, Vol. 11, No. 3, 1969, 622-628.
105. L. Zuev, V. Gromov, and A. Narozhnyi, "Effect of an Electric Field on the Mobility of Dislocations in Sodium Chloride Crystals Determined by Stress Relaxation and Direct Methods", *Dinamika Dislokatsii*, 1975, 76-82.
106. L. Zuev, V. Gromov, and V. Sergeev, "Electric Field Effect on the Kinetics of Expansion of Screw Dislocation Semiloops in Sodium Chloride Crystals", *Fizika Tverdogo Tela*, Vol. 17, No. 10, 1975, 3000-3005.
107. L. Zuev, V. Gromov, V. Sergeev, and A. Narozhnyi, "Mechanism of Electric Field Effect on Dislocation Mobility in Alkali Halide Crystals", *Izv. Vyssh. Uchebn. Zaved., Fizika*, Vol. 18, No. 5, 1975, 16-21.
108. L. Zuev, and V. Segeev, "Breaking Away of Dislocations from Pinning Centers Under the Effect of Pulses", *Vzaimodeistvie Defektov Kristal. Reshetki i Svoistva Met.*, 1981, 34-37.
109. A. Badluyev, V. Gaman, and V. Minayev, "Strong Electric Field Effects in thin-film Structures Metal-Chalcogenide Glass-metal", *Izvestiya Vysshikh Uchebnykh Zavedenii Fizika*, No. 8, 1979, 64-71.
110. N. Novikov, and L. Novogrudskii, "Device for the Investigation of the Effect of Electric Current on Mechanical Properties of Metals in the Temperature Range 4.2-300 Degrees K", *Industrial Laboratory*, Vol. 45, No. 4, 1979, 479-480.

111. V. Petrakov, N. Sorokin, S. Chizhikov, M. Shaskolskaya, and A. Blistanov, "Effect of Electric Fields on Elastic Properties of KH_2PO_4 and LiNbO_3 Crystals", *Izvestiya Akademii Nauk SSSR Seriya Fizicheskaya*, Vol. 39, No. 5, 1975, 974-977.
112. B. Vekhter, M. Kaplan, and I. Novoselskii, "Electric Field Effect on Elastic Properties of DyVO_4 ", *Fizika Tverdogo Tela*, Vol. 21, No. 5, 1979, 1386-1391.
113. O. Bobrikova, and V. Stas, "Effect of an Electric Field on the Accumulation of A, E Centers in Silicon", *Fizika i Tehnika Poluprovodnikov*, Vol. 22, No. 1, 1988, 143-145.
114. E. Rozin, M. Shipko, and I. Zheludev, "Electric Field Treatment Effect on Structure and Properties of Ca-Substituted Hexagonal Ferrites", *Fizika Tverdogo Tela*, Vol. 28, No. 3, 1986, 902-905.
115. Y. Brazhkin, A. L. Korobov, and V. E. Lyamov, "Electric-Field Effect on Electro-Mechanical Properties of SrTiO_3 ", *Fizika Tverdogo Tela*, Vol. 23, No. 5, 1981, 1545-1548.
116. A. N. Kulichenko, and B. I. Smirnov, "Electric-Field Effect on the Resistance of an Alkali-Halide Crystal to Deformation", *Fizika Tverdogo Tela*, Vol. 23, No. 4, 1981.
117. M. Brovman, "Effect of Electric Current on the Plastic Deformation Process", *Problemy Prochnosti.*, Vol. 6, 1981, 107-110.
118. G. Karpenko, O. Kuzin, V. Tkachev, and V. Rudenko, "Effect of Electric Current on Low-cycle Fatigue of Steel", *Dokl. Akad. Nauk SSSR*, Vol. 227, No. 1, 1976, 85-86.
119. L. Novogrudskii, V. Stepanenko, and O. Znachkovskii, "Special Features of Deformation and Fracture of 12Kh18N10Ti and 13Kh13AG19 Steels Under the Effect of Electric Current Pulses and Cooling to 4.2 K", *Strength of Materials*, Vol. 17, No. 4, 1985, 511-514.
120. A. Klypin, "Effect of Electric Current on Metal Creep", *Problemy Prochnosti*, Vol. 5, No. 9, 1973, 35-39.
121. V. Strizhalo, L. Novogrudskii, and O. Znbachkovskii, "Strain Resistance of Structural Alloys Under the Effect of Electric Current Pulse and Cryogenic Temperatures", *Problemy Prochnosti*, No. 5, 1985, 105-107.
122. G. Pisarenko, V. Strizhalo, and L. Novogrudskii, "Resistance of Metallic Materials to the Plasticizing Effect of Electric Current Pulses", *Problemy Prochnosti*, Vol. 21, No. 7, 1989, 21-24.
123. N. Tyapunina, and A. Kolomiitsev, "Effects of an Electric Field on the Starting Stress and Range of Dislocations in NaCl Crystals", *Kritallografiya*, Vol. 17, No. 6, 1972, 1258-1260.
124. M. Kirbardin, "Effect of Low Electric Current on the Heterogeneity of Plastic Deformation Distribution", *Fizika Met. i lkh Soedin*, No. 3, 1975, 178-184.

125. N. Novikov, and L. Novogrudskii, "Effect of an Electric Current Pulse on the Mechanical Characteristics of Stable Austenitic Steel 03Kh13N9G19AM2 During Static Extension", *Problemy Prochnosti*, No. 7, 1979, 91-94.
126. N. Zagoruiko, V. Savenko, and N. Bekkauer, "Effect of Strong Electric Fields on the Behavior of Linear and Point Defects During Microplastic Deformation of Ionic Crystals", *Deposited Doc.*, 1977, 396-377.
127. N. Zagoruiko, and E. Shchukin, "Effect of an Electric Field on the Plastic Flow of Sodium Chloride Crystals", *Kristallografiya*, Vol. 13, No. 5, 1968, 908-909.
128. V. Davydov, and A. Petrov, "Electric Field Effect on Characteristics on Indium Antimonide MOS Structures", *Physica Status Solidi Applied Research*, Vol. 98, No. 1, 1986, 253-261.
129. Army Research Office, *A Study into the Mechanism(s) for the Electroplastic Effect in Metals and Its Application to Metalworking*, AD-A163785; ARO-18184.12-MS, H. Conrad, Dec. 1985.
130. Army Research Office, *The Electroplastic Effect in Metals*, AD-A141526; ARO-18184.5-MS, H. Conrad, H., A. F. Sprecher, and S. L. Mannan, May 1984.
131. H. Conrad, A. F. Sprecher, and S. L. Mannan, "The Electroplastic Effect in Metals", *Journal of Metals*, Vol. 35, No. 8, 1983, 62.
132. H. Conrad, A. F. Sprecher, and S. L. Mannan, "The Electroplastic Effect in Metals", *The Mechanics of Dislocations*, 1983, 28-31.
133. H. Conrad, A. F. Sprecher, and S. L. Mannan, "On the Temperature Rise Associated with the Electroplastic Effect in Titanium", *Scripta Metallurgica*, Vol. 17, 1983, 796-772.
134. Air Force Office of Scientific Research, *A Study of the Electroplastic Effect in Metals*, AD-A075267; AFOSR-79-0988TR, H. Conrad, and K. Okazaki, July 1979.
135. H. Conrad, K. Okazaki, and M. Kagawa, "A Study of the Electroplastic Effect in Metals", *Scripta Metallurgica*, Vol. 12, No. 11, 1978, 1063-1068.
136. H. Conrad, K. Okazaki, and M. Kagawa, "Additional Results on the Electroplastic Effect in Metals", *Scripta Metallurgica*, Vol. 13, No. 4, 1979, 277-280.
137. H. Conrad, K. Okazaki, and M. Kagawa, "An Evaluation of the Contributions of Ski, Pinch and Heating Effects to the Electroplastic Effect in Titanium", *Material Science and Engineering*, Vol. 45, No. 2, 1980, 109-116.
138. H. Conrad, K. Okazaki, and Kagawa, "Effects of Strain Rate, Temperature and Interstitial Content on the Electroplastic Effect in Titanium", *Scripta Metallurgica*, Vol. 13, No. 6, 1979, 473-477.

139. H. Conrad, A. F. Sprecher, and S. L. Mannan, "Overview NO. 49 - On the Mechanisms for the Electroplastic Effect In Metals", *ACTA Metallurgica*, Vol. 34, No. 7, 1986, 1145-1162.
140. Army Research Office, *Effect of Electric Field on the Superplasticity of 7475 Al*, ARO-23090.12-MS, H. Conrad, 1989.
141. Army Research Office, *Effect of Electric Fields and Currents on Microstructure, Properties and Processing of Metals and Alloys*, ARO-26825.12-MS, H. Conrad, and A. Sprecher, July 1, 1990.
142. Air Force Office of Scientific Research, *A Study of the Electroplastic Effect in Metals*, AFOSR-TR-79-0988, H. Conrad and K. Okazaki, July 31, 1979.
143. H. Conrad, A. F. Sprecher, and S. L. Mannan, *Electroplastic Effect in Metals*, ARO-18184.5-MS, May 11, 1984.
144. H. Conrad, A. F. Sprecher, and S. L. Mannan, *Mechanisms for the Electroplastic Effect in Metals*, Report, ARO-23090.1-MS, 1986.
145. H. Conrad, A. F. Sprecher, W. D. Cao, and X. P. Lu, "Electroplasticity - The Effect of Electricity on the Mechanical Properties of Metals", *Journal of Materials*, 1990, 28-33.
146. H. Conrad, *A Study into the Mechanism(s) For the Electroplastic Effect in Metals and Its Applications to Metalworking, Processing and Fatigue*, Project Report, ARO-23090-MS, March 10, 1989.
147. P. D. Goldman, L. R. Motowidlo, and J. M. Galligan, "The Absence of an Electroplastic Effect in Lead at 4.2 K", *Scripta Metallurgica*, Vol. 15, No. 4, 1981, 353-356.
148. M. A. Meyers, S. K. Varma, and L. R. Cornwell, "Comments on 'The Electroplastic Effect in Aluminum'", *Scripta Metallurgica*, Vol. 14, No. 9, 1980, 1033-1036.
149. A. F. Sprecher, "The Electroplastic Effect in Metals", *Diss. Abstr. Int.*, Vol. 46, No. 2, 1985, 248.
150. S. K. Varma, and L. R. Cornwall, "The Electroplastic Effect in Aluminum", *Scripta Metallurgica*, Vol. 13, No. 8, 1979, 733-738.
151. S. Bhaduri, and F. F. Y. Wang, "Effects of Electric-Field and Chemical Environment on Fracture-Behavior of Single-Crystal Silicon", *American Ceramic Society Bulletin*, Vol. 59, No. 8, 1980, 826.
152. G. Caso, M. Schwabel, and F. Van Derck, "Effects of Electric Fields on Slow Crack Growth in Glass", *Journal of the American Ceramic Society*, Vol. 73, No. 1, 1990, 43-48.
153. M. Schwabel, *The Effect of Electric Field on Crack Propagation in Glass*, Thesis, Alfred University, 1978.

154. A. Mamontov, and V. Peshev, "Effect of Electric Field on Build-up and Annealing of E5-centers in GaAs", *Fizika i Tekh. Poluprovodnikov*, Vol. 17, No. 7, 1983, 1310-1311.
155. K. McHenry, "Electric Field Effects on Subcritical Crack Growth in PZT", *Fracture Mechanics of Ceramics*, Vol. 5, Plenum Press, New York, NY, 1983, 337-352.
156. R. Munson, K. McHenry, and B. Koepke, "Electric Field Effects on Crack Propagation in PZT", *American Ceramic Society Bulletin*, Vol. 58, No. 3, 1979, 342.
157. L. Murr, and M. Sattler, "A Critical Evaluation of the Effect of Electric Fields on the Residual Structure of Vapor-deposited Metal Films", *Journal of Applied Physics*, Vol. 49, No. 2, 1978, 929-931.
158. A. Neiman, and W. Rothwell, "Creep in Vacuum of MgO Single Crystals and the Electric Field Effect", *Journal of Applied Physics*, Vol. 36, 1965, 2309-2316.
159. S. Bhaduri, *Effects of Electric Field and Ambient Environments on Slow Crack Growth in Soda-lime Silica Glass and Single Crystal Silicon*, Thesis, State University of New York, 1981.
160. W. Cao, *Effect of Electric Current and Field on the Behavior of Metallic Materials*, Thesis, North Carolina State University, 1989.
161. A. Wheeler, S. Coriell, G. Mcfadden, and D. Hurler, "Effect of an Electric Field on the Morphological Stability of the Crystal-melt Interface on a Binary Alloy", *Journal of Crystal Growth* 88, 1988, 1-15.
162. D. Taylor, R. Newnham, and W. Carlson, "The Effect of Electric Field on Mechanical Strain and Stress in Flawed Electroceramics", *Ferroelectric*, Vol. 87, 1988, 81-84.
163. P. Asle, "Effect of Electric Currents on Ball Bearing Damage in Vacuum and in Air", *Lubrication Engineering*, Vol. 23, 1967, 363-371.
164. M. Berveiller, and A. Zaoui, "Generalisation of the Inclusive Problem and Application to Electroplasticity Problems of Heterogeneous Materials", *J. Mec.*, Vol. 19, No. 2, 1980, 343-361.
165. A. San Martin, D. M. Nghiep, P. Paufler, et al., "The Electroplastic Effect in V_3Si ", *Scripta Metallurgica*, Vol. 14, No. 10, 1980, 1041-1045.
166. R. S. Timsit, "Remarks on Recent Experimental Observations of the Electroplastic Effect", *Scripta Metallurgica*, Vol. 15, (4), 1981, 461-464.
167. T. Yamada, J. Ozaki, and T. Kataoka, "Electroplastic Effect in Ca^{2+} -doped KCl Single Crystal", *Philos. Mag. A, Phys. Condensed Matter Deffects Mechanical Properties*, Vol. 58, No 2, 1988, 385-395.

168. M. Braunovic, "The Effect of an Electric Current on the Stress Relaxation of Aluminum Wire Conductors", *Strength of Metals and Alloys*, Vol. 1, Pergamon Press Ltd., Headington Hill Hall, Oxford, U.K., 1985, 619-624.
169. T. Garosshen, and L. Motowidlo, *Dislocation Drag Mechanism -- Electron Drag on Mobile Dislocations in Copper* *Strength of Metals and Alloys*, Vol. 1, Pergamon Press Ltd., Headington Hill Hall, Oxford, U.K., 1979, 499-503.
170. J. L. Johnson, and J. Schreurs, "High Current Brushes. VIII. -- Effect of Electrical Load", *Wear* 78, (1-2), 1982, 219-232.
171. A. San Martin, K. Kleinstuck, N. H. Quen, and P. Paufler, "Influence of a Direct Current and a Temperature Gradient on the Creep Rate in V₃Si", *Phys. Status Solidi A*, Vol. 80, No. 2, 1983, K171-4.
172. M. Amin, H. Osman, S. Hamza, N. El-nashar, and S. Moghazy, "The Effect of Electric Field on the Creep Characteristics of Low-density Polyethylene (LDPE)", *Polymer Bulletin*, Vol. 21, No. 1, 1989, 113-118.
173. I. Benguigui, "Effect of Electric Field on Ferro and Antiferroelectric Ceramics. I.", *Deformation and Phase Transitions*, Vol. 49, No. 510, 1969, 889-893.
174. J. Courdille, and J. Dumas, "Electric Field Effect on the Elastic Constant Near the Gadolinium Molybdate Phase Transition", *Physical Review B*, Vol. 8, No. 3, 1973, 1129-1131.
175. G. Danan, F. Ladan, F. Molleot, and R. Planel, "Longitudinal Electric Field Effects on Gallium Arsenide-Aluminum Arsenide Type-II Superlattices", *Applied Physics Letters*, Vol. 51, No. 20, 1987, 1605-1607.
176. L. Dobaczewski, "Anisotropy and Isotropy of Electric Field Effects for the EL2 and E3 defects in GaAs", *Mater. Sci. Forum*, Vol. 38-41, 1989.
177. A. Ishibashi, and A. Katsuki, "Effects of Electric Current on Shear Stress and Tool Wear in Metal Cutting", *Kyushu Daigaku Kogaku Shuho*, Vol. 42, No. 6, 1970, 911-918.
178. N. Koprinarov, and K. Nitzsche, "Effect of Transverse Electric Fields on the Structure and Electronic Properties of Vapor-deposited Metal Films", *Wiss. Z. - Tech. Hochsch. Ilmenau*, Vol. 30, No. 2, 1984, 147-155.
179. J. Laforte, L. Phan, and J. Druez, "Effects of an Electric Field on the Microstructure and Mechanical Properties of Glaze and Rime", *Proceedings of the 6th International Conference on Port and Ocean Engineering Under Arctic Conditions*, Univ. Laval, Quebec, Canada, 1981, 1057-1066.
180. Z. Lechowski, "Reversible Variation of Insulating Material Structure Caused by Electric Field Effect", *Energetyka*, Vol. 38, No. 5, 1984, 208-210.
181. G. Lormand, J. Rouais, M. Lallemand, and C. Eyraud, "Displacement of the Grain Boundaries of a Metal Under the Effect of an Electric Field", *Mem. Sci. Rev. Metall.*, Vol. 64, No. 1, 1967, 59-65.

182. Y. Masuda, and A. Baba, "Electric Field-induced Strain Effects of Pb(Zr, Ti)O₃ Family Ceramics", *Japanese Journal of Applied Physics, Supplement*, Vol. 26, 1987, 132-135.
183. H. Prashad, "Analysis of the Effects of Electric Current on Contact Temperature and Residual Stresses Leading to Slip Bands Initiation and Formation", *BHEL Journal*, Vol. 11, No. 1, 1990, 39-47.
184. J. Rouais, G. Lormand, and C. Ryraud, "Displacement of the Grain Boundaries of a Metal Under the Effect of an Electric Field", *Bull. Soc. Fr. Ceramics*, Vol. 80, 1968, 53-59.
185. A. Sibille, "Electric Field Effects on Radiation Defects Annealing in p-InP", *Solid State Communications*, Vol. 46, No. 9, 1983, 673-675.
186. K. Tsumuraya, T. Hasegawa, and Y. Ohno, "Effect of Electric Current on Aging of an Aluminum-2.5 wt.% Copper Alloy", *Keikinzo*, Vol. 24, No. 2, 1974, 85-88.
187. S. Ueda, M. Koizumi, and R. Ikuta, "Effect of Electric Current Forms on the Hardness of Anodized Aluminum", *Aruminyumu Hyomen Shori Kenkyu Chosa Hokoku*, Vol. 80, 1974, 36-37.
188. S. A. Abasov, M. A. Kurbanov, T. M. Veliev, and M. M. Kuliev, "Strong Electric-Field Effect on Mechanical Longevity of Polyethethylene", *Fizika Tverdogo Tela*, Vol. 24, No. 3, 1982, 693-695.
189. B. Ksenofontov, and V. Kuleshov, "Effect of an Electric Field on the Structure of an Acrylamide-methylenebisacrylamide Copolymer", *Plast. Massy*, No. 9, 1984, 20-21.
190. E. Illina, "State of Defects in Polymer Films Under the Effects of an Electric Field and Solutions of Electrolytes", *Vestsi Akad. Navuk BSSR*, No. 2, 1983, 27-30.
191. V. Vinetskiĭ, and G. Chaika, "New Mechanism for the Effect of an Electric Field on Defect Formation in Nonmetallic Crystals", *Radiats. Fizika Poluprovodn. Rodstvennykh Mater.*, 1980, 456-459.
192. A. Yarkov, and R. Petrishcheva, "Effect of an Electric Current on the Strength of Hardened Concrete", *Izv. Vyssh. Uchebn. Zaved.*, 1977, 69-72.
193. N. Rotych, V. Kononenko, R. Rotych, and G. Ioshchenko, "Effect of an Electric Current and Magnetic Fields on Properties of Cement Stone", *Izv. Vyssh. Uchebn. Zaved., Khim. Khim. Tekhnol.*, Vol. 33, No. 5, 1990, 99-102.
194. K. Natesaiyer, "The Effect of Electric Currents on Alkali-silica Reaction in Concrete", Cornell University, Ithaca, NY, 1990.
195. G. Venugopal, S. Krause, and G. Wnek, "Effects of Electric Fields on Polymer Blend Morphologies", *Polymer Preprints, Division of Polymer Chemistry, American Chemicals Society*, Vol. 31, No. 1, ACS, Books and Journals Division Washington, D. C., 1990, 377-378.

196. S. Moriya, K. Adachi, and T. Kotaka, "Effect of Electric Field on the Morphology of a Poly(ethylene Oxide)-Polystyrene Blend", *Polymer Communications*, Vol. 26, No. 8, Guildford, 1985, 235-237.
197. S. S. Badirkhanova, U. A. Kabulov, M. A. Kurbanov, and S. A. Abasov, "The Variation of Polyethylene Mechanical Properties Under the Effect of Discharges at Different Temperatures", *Izv. Akad. Nauk Azerb. SSR, Fiz.-Tkh. Mat.*, Vol. 6, No. 6, 1985, 81-84.
198. V. Y. Ushakov, A. L. Robezhko, and V. F. Vazhov, "The Role of Inhomogeneity in Polymers in the Development of Failure Under the Influence of an Electric Field", *Fiz. Tverd. Tela*, Vol. 27, No. 8, 1985, 2361-2366.
199. V. Y. Ushakov, A. L. Robezhko, and V. F. Vazhov, "Role of Inhomogeneity of Polymers in the Process of Damage Caused By Electrical Fields", *Soviet Phys. Solid State*, Vol. 27, No. 8, 1985, 1416-1420.
200. A. N. Kulichenko, and B. I. Smirnov, "Electroplastic Effect in Polymers", *Soviet Physics - Solid State*, Vol. 26, No. 3, 1984, 570-571.
201. K. Rajeshwar, R. Rosenvold, and J. Dubow, "Electric Field Effects in the Thermal Decomposition of Solids," *Nature*, Vol. 301, 1983, 48-49.
202. V. Zavorotnyj, and Y. Poplavko, "Electric Field Effect on Thermal Diffusivity of TGS", *Fizika Tverdogo Tela*, Vol. 27, No. 12, 1985, 3681-3682.
203. H. Ott, and B. Luthi, "Crystal Electric Field Effects on Thermal Expansion of TmSb", *Physical Review Letters*, Vol. 36, No. 11, 1976, 600-602.
204. K. Mackenzie, and N. Hadipour, "Effect of Electric Fields on the Thermal Decomposition of Calcium Carbonate", *Thermochim. Acta*, Vol. 35, No. 2, 1980, 227-237.
205. A. Kabanov, and E. Zingel, "Effect of an Electric Field on the Thermal Decomposition of Solid Substances", *Usp. Khim.*, Vol. 44, No. 7, 1975, 1194-1216.
206. H. Chaya, Jr., *The Effect of Electric Field on the Thermal Decomposition of Potassium Azide*, dissertation, Princeton University, Princeton, New Jersey.
207. A. Guy, "Effect of Simultaneous Electric Current on Thermal Conductivity", *Proceedings of the Sixteenth International Conference*, Plenum Publishing Co., New York, NY, 1983, 405-408.
208. R. Gairola, and B. Semwal, "The Effect of Electric Field on Thermal Conductivity of a Ferroelectric Crystal II", *Journal of the Physical Society of Japan*, Vol. 43, No. 3, 1977, 954-960.
209. I. G. Ismailzade, O. A. Samedov, D. Bernar, and Z. Lukas, "Stationary Electric-Field Effect on Phase-Transitions in $Cd_2Nb_2O_6$ and $CdZnNb_2O_6S$ ", *Fizika Tverdogo Tela*, Vol. 27, No. 9, 1985, 2822-2824.

210. G. M. Konstantinov, M. F. Kupriyanov, V. A. Servuli, A. A. Lebedinskii, S. M. Zaitsev, and E. G. Fesenko, "Effect of an Electric Field on the Morphotropic Phase Transition in the System of PZT Solid Solutions", *Soviet Phys. Tech. Phys.*, 34, (7), 1989, 760-763.
211. I. Ismailzade, P. Hagenmuller, R. Ismarlov, J. Ravez, and O. Sanedov, "Effect of Constant Electric Fields on Phase Transitions in NaNbO_3 and $\text{Na}_{0.98}\text{Li}_{0.02}\text{NbO}_3$ ", *Inorganic Materials*, Vol. 22, No. 5, 1986, 745-747.
212. I. Ismailzade, and O. Samedov, and N. Ehyubova, "Effect of Constant Electric Field on Successive Structural Phase Transitions in Spontaneous-polarized Crystals", *Neorganicheskie Materialy*, Vol. 25, No. 9, 1989, 1513-1517.
213. L. Kamzina, F. Salaev, N. Krajnik, S. Dorogovtsev, and G. Smolenskij, "Effect of Constant Electric Fields and Impurities on Smeared and Distinct Phase Transitions in $\text{Cd}_2\text{Nb}_2\text{O}_7$ ", *Fizika Tverd. Tela*, Vol. 25, No. 9, 1983, 2846-2849.
214. F. Smutny, and M. Polomska, "Effects of Electric Field on the II-III Phase Transition in Lithium Ammonium Sulphate and Its Deuterated Analogue", *Physi. Status Solidi A*, Vol. 82, No. 1, 1984, K33-K36.
215. I. Ismailzade, P. Hagenmuller, R. Ismarlov, J. Ravez, and O. Sanedov, "Effect of Constant Electric Field on Phase Transitions in NaNbO_3 and $\text{Na}_{0.98}\text{Li}_{0.02}\text{NbO}_3$ ", *Inorganic Materials*, Vol. 22, No. 5, 1986, 745-747.
216. I. Ismailzade, N. Eyubova, I. Aliev, and O. Samedov, "Effect of Constant Electric Fields on Phase Transitions in KNO_3 Crystals," *Izvestiya Akademii Nauk SSSR, Neorganicheskie Materialy*, Vol. 23, No. 5, 1987, 819-821.
218. I. Ismailzade, P. Khagenmyuller, O. Samedov, Z. Ravez, and R. Ismailov, "Effect of Constant Electric Fields on the Phase Transition in NaNbO_3 and $\text{NaO}_9\text{Li}_2\text{NbO}_3$ Crystals", *Izvestiya Akademii Nauk SSSR, Neorganicheskie Materialy*, Vol. 22, No. 5, 1986, 846-848.
219. K. Mackenzie, and G. Hosseini, "Effect of Electric Field on the Transformation of Gamma to Alpha Alumina", *Transactions and Journal of the British Ceramic Society*, Vol. 77, No. 6, 1978, 172-176.
220. H. Okubo, M. Fukui, and R. Abe, "Effect of Electric Field on the IC-C Phase Transition in K_2SeO_4 ", *Japanese Journal of Applied Physics, Supplement*, Vol. 24, 1985, 769-771.
221. Y. Vershinin, and A. Pleshanov, "Effect of Electric Field on Phase Transitions in a System with a Real Equation of State", *Power Engineering*, Vol. 27, No. 4, 1989, 152-156.
222. A. Bondar, and S. Ryabchenko, "Features of Electric Field Effect in NQR and Phase Transition in Crystals of Pyrargyrite", *Journal of Molecular Structure*, Vol. 83, 1982, 85-88.

223. H. Cummins, S. Qiu, J. Dutta, M. Wicksted, and S. Shapiro, "Effect of Transverse Electric Field on the Incommensurate Phase of NaNO_2 ", *Proceedings of a NATO Advanced Research Workshop*, Plenum Publishing Co., New York, NY, 1987, 91-104.
224. J. Kobayashi, M. Ozeki, T. Kimura, Y. Tsutsumi, et al., "Effects of the Electric Field on the Structure of Incommensurate Phases of $(\text{NH}_4)_2\text{SO}_4$ Group Crystals", *Ferroelectric Letters Section*, Vol. 8, No. 2, 1988, 41-48.
225. G. Leonidova, and N. Netesova, "Effect of an Electric Field on the Ferroelectric Phase Transition in Triglycine Sulphate at High Pressures", *Fizika Tverdogo Tela*, Vol. 10, No. 8, 1968, 2526-2527.
226. L. Shuvalov, A. Shirokov, N. Ivanov, and A. Baranov, "Effect of an Electric Field on Phase Transitions in $\text{Na}(\text{D}_x\text{H}_{1-x})_3(\text{SeO}_3)_2$ Crystals", *Krystallografiya*, Vol. 18, No. 1, 1973, 133-137.
227. K. Toyoda, K. Ishikawa, and H. Kameyama, "Effect of Electric Field on Ferroelectric Phase Transition in SbSI ", *Journal of the Physical Society of Japan*, Vol. 27, No. 1, 1969, 261.
228. M. Brainin, and B. Smolyak, "Effect of an Electric Field on Work of New Phase Formation", *Zh. Fizika Khim.*, Vol. 54, No. 4, USSR, 1980, 962-965.
229. A. Bykhovskii, and A. Glushchenko, "Effect of an Electric Field on the Spread, Phase Composition, and Structure of Surface Layers of Coatings on Metals", *Vopr. Fizika. Formobraz i Faz. Prevrashch.*, 1983, 62-70.
230. I. Ismailzade, O. Samedov, N. Eyubova, and I. Aliev, "The Effect of Constant Electric Fields on the Phase Transitions in Potassium Nitrate Crystals", *Izvestiya Akademii Nauk SSR, Neorganicheskie Materialy*, Vol. 23, No. 5, USSR, 1987, 819-821.
231. I. Perro, "Use of the Resonance Spectral Method to Determine the Effect of an Electric Field on Phase Composition in Ferroelectric Solid Solutions", *Aktuak. Probl. Segnetoelektrich Faz. Perekhodov*, 1983, 34-43.
232. V. Zilbervarg, and N. Trufanov, "Effect of an Electric Field on Phase Transitions in Superionic Conductors", *Deposited Doc.*, 1982, 2970-2982.
233. G. Konstantinov, M. Kupriyanov, V. Servuli, A. Lebedinskii, et al., "Effect of an Electric Field on Morphotropic Phase Transition in the Solid Solution Systems Based on ZTL", *Zhurnal Tekhnicheskoi Fiziki*, Vol. 59, No. 7, 1989, 80-85.
234. I. Ismailzade, O. Samedov, D. Bernar, and Z. Lukas, "Stationary Electric Field Effect on Phase Transitions in $\text{Cd}_2\text{Nb}_2\text{O}_6\text{S}$ and $\text{CdZnNb}_2\text{O}_6\text{S}$ ", *Fizika Tverdogo Tela*, Volume 27, No. 9, Leningrad, USSR, 1985, 2822-2824.
235. D. Shemwell, and C. Cantrell, "Effect of Static Electric Fields on Phase Conjugation in Silicon", *Journal of Applied Physics*, Vol. 56, No. 5, 1984, 1309-1313.

236. R. De Vekey, and A. Majumdar, "Effect of Electric Field on Phase Separation of Glass", *Nature*, Vol. 225, No. 5228, 1970, 172-173.
237. M. Date, "Effect of Electric Field on the Phase Transition in Vinylidene Fluoride-trifluoroethylene Copolymers", *IEEE Transactions on Electrical Insulation*, Vol. E1-21, No. 3, 1985, 539-542.
238. J. Gilli, J. Pinton, P. Sixou, A. Blumstein, and O. Thomas, "The Effect of an Electric Field on a Thermotropic Polymer: Optical Memory Effect", *Molecular Crystals and Liquid Crystals*, 1, (3-4), 1985, 123-130.
239. N. Meyer, E. Moseklide, and M. Joergensen, "High Electric Field Effects in Zinc Oxide Single Crystal 2-6 Semiconductor Compounds", *International Conference*, A. Benjamin, Inc., New York, NY, 1967.
240. Y. A. Ossipyan, and V. F. Petrenko, "Motion of Charged Dislocations in Semiconductors AII B VI", *Journal of Phys. Colloq.*, Vol. 40, No. C-6, Pt. 6, 1979, C6/161-167.
241. E. Sonder, K. F. Kelton, J. C. Pigg, and R. A. Weeks, "The Effect of Electric Current on the Conductivity of MgO Single Crystals at Temperatures Above 1300 K", *Journal of Applied Physics*, 49, (12), 1978, 5971-5976.
242. M. M. Elzaidia, and M. M. Eldin, "The Effect of Electric-Field on the D.C. Conductivity of Mixed Amorphous-Crystalline Selenium", *Indian Journal of Technology*, Vol. 19, No. 5, 1981, 214-216.
243. J. Dusseau, and L. Ensuque, I. Saroeun, and T. Lepetre, "High Electric Field Effect in Silicon-Boron Compounds Such As B₁₄Si", *Phys. Status Solidi*, Vol. 47, No. 1, 1978, K11-K15.
244. I. Nekrashevich, and I. Bakuto, "The Electrical Breakdown and Strengthening of Dielectric", *Dokl. Akad. Nauk. Belorussk*, Vol. 12, No. 2, 1968, 126-130.
245. M. Amin, L. Balloomal, H. Osman, and S. Abdel Ghani, "Effect of Electric Field and Annealing on the Electrical Conductivity of Neutron Irradiated Triglycine Sulfate Single Crystal", *Indian Journal of Pure and Applied Physics*, Vol. 24, No. 6, 1986, 297-299.
246. S. Bhatt, G. Baluni, U. Naithani, and B. Semwal, "Effect of Electric Field on Dielectric and Acoustical Properties of Ferroelectric Solids", *Indian Journal of Pure and Applied Physics*, Vol. 26, No. 5, 1988, 356-360.
247. R. Dimmich, and F. Warkusz, "Simple Model of the Electric Field Effect in Thin Metallic Films", *Thin Solid Films*, Vol. 79, No. 2, 1981, 173-184.
248. S. Takayanagi, "Crystalline Electric Field Effects on the Resistivity of PrCu₅ and PrCu₆", *Journal of the Physical Society of Japan*, Vol. 53, No. 2, 1984, 676-681.
249. M. Angadi, and S. Shivaprasad, "Effect of DC Electric Field on Resistance of Thin Manganese and Palladium Films", *Vacuum*, Vol. 32, No. 1, 1982, 51-52.

250. S. Bakanowski, J. Crow, N. Berk, and T. Mihalisin, "Crystalline Electric Field Effects on the Resistivity of PrAl_2 ", *Solid State Communications*, Vol. 17, No. 9, 1975, 1111-1114.
251. J. Duthie, and V. Heine, "Theory of Screening Effects on Crystalline Electric Field in Metallic Rare Earth Materials", *Journal of Physics F*, Vol. 9, No. 7, 1979, 1349-1355.
252. C. Fong, R. Gallup, L. Esaki, and L. Chang, "The Electronic Properties of the Miniband and the Effect of External Electric Fields in Superlattices", *Superlattices and Microstructures*, Vol. 7, No. 2, 1990, 147-151.
253. I. Inculet, and W. Greason, "Effect of Electric Fields and Temperature on Electrification of Metals in Contact with Glass and Quartz", *Proceedings of the Third Conference on Static Electrification*, Institute of Physics, London, U.K., 1971, 23-32.
254. Y. Kawaguchi, and S. Kawaji, "High Electric Field Effect on Negative Magnetoresistance in Si (001) n-inversion Layers", *Physica B & C*, Vol. 117-118B+C, pt. 2, 1983, 658-660.
255. A. Kiveris, and P. Pipinys, "Effect of an Electric Field on the Conductivity of Zinc Sulfide Single Crystals", *Litovskii Fizicheskii Sbornik*, Vol. 17, No. 1, 1977, 99-106.
256. P. Martin, J. Sampsell, and J. Garland, "Electric Current Distortion Effects in Polycrystalline Copper", *Physical Review B*, Vol. 15, No. 12, 1977, 5598-5611.
257. Y. Pikus, V. Teterya, and V. Shnyukov, "Effect of Constant Electric Field on the Conductivity of Oxides of Alkaline Earth Metals", *Radiotekhnika i Elektronika*, Vol. 14, No. 1, 1969, 184-187.
258. T. Shirakawa, M. Miyayama, Y. Nakamura, and H. Yanagida, "Effect of Electric Field on the Surface Electrical Resistance of CuO-ZnO Hetero-contact", *Journal of Materials Science Letters*, Vol. 10, No. 7, 1991, 381-383.
259. J. Sivar Kumar, U. Subba Rao, K. Satyanarayana, and K. Narasimha Reddy, "Effects of Electric Field on Dielectric Properties of $\text{SnO}_2\text{Sb}_2\text{O}_3$ and Their Mixed Thin Films", *Crystal Research and Technology*, Vol. 26, No. 1, 1991, 103-108.
260. G. Abdullaev, V. Gadzhiev, and B. Tagiev, "Effect of an Electric Field on the Electrical Conductivity of Doped Gallium Selenide and Telluride Single Crystal", *Issled. Po Fizika Poluprovodnikov*, 1975, 53-62.
261. B. Mikhailovskii, G., Pikus, V. Perekhvatov, V. Telega, and V. Shnyukov, "Effect of an Electric Field on the Composition and the Electronic Properties of the Surface of Barium Oxide Crystals", *Poverkhnost*, No.11, 1989, 86-91.
262. V. Pronichkin, V. Polishchuk, and A. Ignatov, "Effect of an Electric Field on the Crystallization and Electric Properties of Cadmium Sulfide Thin Layers", *Poverkhnost*, No. 1, 1987, 142-144.

263. S. Mizushima, and Y. Fujibayashi, "Perpendicular Electric Field Effect on Electric Resistivity of Thin Graphite Crystals", *Carbon*, Vol. 15, No. 6, 1977, 423.
264. V. Valyukenas, A. Orlyukas, A. Sakalas, and V. Mikolaitis, "Effect of External Electric Field on Electroconductivity of Alpha-AgSbS₂ Crystals", *Fizika Tverdogo Tela*, Vol. 21, No. 8, 1979, 2449-2450.
265. R. Weeks, J. Narayan, and E. Sonder, "Effect of Electric Fields on Electrical Conductivity in Mg and Aluminum Oxide Systems", *Transactions-American Geophysical Union*, Vol. 59, No. 4, 1978, 397.
266. R. Weeks, E. Sonder, K. Kelton, and J. Pigg, "Electric Field Effects on Conductivity of MgO Single Crystals", *American Ceramics Bulletin*, Vol. 56, No. 3, 1977, 303.
267. I. Kurova, and E. Ponarina, "The Effect of Electric Field on the Conductivity of Al-Si-H Films with High Hydrogen Content", *Vestnik Moskovskogo Universiteta Seriya Fizika I Astronomiya*, Vol. 30, No. 1, 1989, 90-92.
268. A. Elshafie, and A. Abdel-aal, "Effect of the Electric Field on the D.C. Conductivity of Bulk Glassy Te₅₀As₅₀ - XSX Alloys", *Thermochimica Acta*, Vol. 155, 1989, 97-102.
269. M. Brodzeli, G. Dekanozishvili, I. Eligulashvili, M. Kandelaki, and O. Modebadze, "Effect of Electric Field and Temperature on the Switching Process in Borate-Vanadium Glasses", *Akademiia Nauk Gruzinskoi SSR, Soobshcheniia*, Vol 91, 1978, 605-608.
270. R. Pethig, and H. Pohl, "Reversal of the Usual Electric Field on the Nomadic Polarization in Polymeric Solids", *Journal of Physics D*, Vol. 10, No. 1, 1977, 105-109.
271. S. Osaki, S. Uemura, and Y. Ishida, "Effects of Static Electric Field Upon Dielectric Properties of Poly(vinylidene flouride) and Poly(vinyl flouride)", *Journal of Polymer Sciences, Part A-2*, Vol. 9, pt. A-2, No. 4, 1971, 585-594.
272. A. Bradwell, R. Cooper, and B. Varlow, "Conduction of Polythene With Strong Electric Field and the Effect of Prestressing on the Electric Strength", *Proceedings of the Institution of Electrical Engineers*, Vol. 118, No. 1, 1971, 247-254.
273. S. Nishida, Y. Wakashima, and H. Inayoshi, "Measurements of Transverse Electric Field Effects on D.C. Conduction in Epoxy Resin", *Japanese Journal of Applied Physics*, Vol. 12, No. 1, 1973, 147-148.
274. B. Avdeenko, A. Glot, and I. Chernenko, "Effect of Electric Field and Heat treatment on the Conductivity of Zinc Oxide Ceramics", *Izvestiya Akademii Nauk SSR, Neorganicheskie Materialy*, Vol. 17, No. 2, 1981, 378-379.
275. A. Peterson, and A. Filippov, "Effect of the Electric Field and of Defects in Solid (Epoxy) Insulation on Its Long-term Dielectric Strength", *Pisma Zhurnal Tekhnicheskoi Fiziki*, Vol. 6, No. 7-8, USSR, 1980, 408-411.

276. Y. Gokhshtein, V. Lyubimov, and L. Karnaukhov, "Effect of Electric Field on Physicochemical Properties of ZrO_2 -CaO Ceramic Electrodes", *Dokl. Akad. Nauk SSR*, Vol. 239, No. 3, 1978, 632-635.
277. P. Bhat, K. Bhatia, and B. Vaid, "High Electric Field Effects in Amorphous Semiconducting $(As_2S_3)_{1-x}(PbS)_x$ ", *Solid State Electronics*, Vol. 22, No. 3, 1979, 283-284.
278. V. Iarinovskii, I. Shirshov, O. Snitko, and V. Tiagai, "Influence of a Transverse Electric Field on the Thermally Stimulated Conductivity of CdS Single Crystals", *Soviet Physics - Semiconductors*, Vol. 1, 1968, 1290-1294.
279. H. Gatos, and S. Kawaji, Massachusetts Institute of Technology, *Electric Field Effect on the Magnetoresistance of Indium Arsenide Surfaces in High Magnetic Fields*, TR-7; AD-650287, 1967.
280. T. Gasymov, and L. Gurevich, "Electrical Conductivity of Semiconductors at Low Temperatures in a Strong Electric Field and the Effect of a Magnetic Field on the Conductivity", *Fizika I Tekhnika Poluprovodnikov*, Vol. 1, 1967, 774-783.
281. G. Nieuwenhuys, "Crystalline Electric Field Effects in UpT_2Si_2 and URu_2Si_2 ", *Physics Review B: Condensed Matter*, Vol. 35, No. 10, 1987, 5260-5263.
282. B. B. Krichevstov, V. V. Pavlov, and R. V. Pisarev, "Linear Effects of an Electric Field on the Magnetization Processes in Iron Garnet Films", *Soviet Physics Solid State*, 31, (7), 1989, 1142-1148.
283. A. Matyash, I. Takzej, and A. Kostyshin, "Electric Field Effect on Static Magnetization of Al-O SUP - Centers in Quartz", *Fizika Tverdogo Tela*, Vol. 28, No. 4, 1986, 962-965.
284. T. Perekali, "Effect of Electric Field on Magnetic Anisotropy of Ferrite Garnet", *Fizika Tverdogo Tela*, Vol. 16, No. 1, 1974, 199-201.
285. B. Vekhter, and M. Kaplan, "Effect of an Electric Field on Magnetic Properties of a Dysprosium Vanadate ($DyVO_4$) Jahn-Teller Crystal", *Fizika Tverdogo Tela*, Vol. 22, No. 10, 1980, 2977-2983.
286. E. Babkin, and N. Cherkunova, "Electric Field Effect on the Magnetic Anisotropy of Magnetite", *Fizika Tverdogo Tela*, Vol. 26, No. 6, 1984, 1818-1822.
287. T. Ivanova, L. Klyushkin, and V. Rudyak, "Effect of Electric Fields and Mechanical Stresses on Switching and Domain Structure Realignment in $NaH_3(SeO_3)_2$ ", *Ferroelectrics*, Vol. 98, 1989, 59-67.
288. E. Eknadiosyants, A. Pinskaya, and V. Borodin, "Effect of Electric Fields on Domain Structure of Ferroelectric of $BaTiO_3$ Type", *Izvestiya Akademii Nauk Ssr, Seriya Fizicheskaya*, Vol. 48, No. 6, 1984, 1111-1115.
289. A. Chyla, and A. Pochaba, "A Study of the Effect of Electric Field on Domain Structure Formation in Seignette's Salt", *Acta Physica Polonica A*, Vol. A40, No. 1, 1971, 109-110.

290. A. Brik, I. Matyash, G. Takzei, and A. Kostyshin, "Effect of an Electric Field on the Static Magnetization of Al-O- Centers in Quartz", *Fizika Tverdogo Tela*, Vol. 28, No. 4, 1986, 962-965.
291. A. Balagurov, I. Datt, B. Savenko, and L. Shuvalov, "Effect of Electric Field on the Domain Structure of KD_2PO_4 ", *Izvestiya Akademii Nauk SSR, Seriya Fizicheskaya*, Vol. 43, No. 8, 1979, 1740-1744.
292. J. Reffle, and H. Hoffman, "Electric Field Effect on Surface Magnetization", *Journal of Magnetism and Magnetic Materials*, Vol. 6, North-Holland Publishing Co., Amsterdam, Netherlands, 1977, 201-203.
293. G. Rado, "Linear Electric Field Effects in Magnetic Anisotropy and Ferromagnetic Resonance", *Journal of Magnetism and Magnetic Materials*, Vol. 15-18, pt. 2, North-Holland Publishing Co., Amsterdam, Netherlands, 1980.
294. Northeastern University, *A Study of the Effects of Crystalline Electric Fields on Ferromagnets - Final Report, Oct. 1963-Oct. 1965*, AFCRL-66-56; AD-629018, W. Hauser, 1965.
295. B. Krichevtsov, V. Pavlov, and R. Pisarev, "Linear Effects of Electric Filed on the Magnetization Processes in Ferrite-garnet Films", *Fizika Tverdogo Tela*, Vol. 31, No. 7, 1989, 77-88.
296. B. Dunlap, "Crystalline Electric Field Effects on the Paramagnetic Susceptibility of Polycrystalline Materials", *Journal of Magnetism and Magnetic Materials*, Vol. 37, 1983, 211-214.
297. A. Chzhan, N. Drokin, and P. Kim, "Electric Field Effect on Magnetization of $CdCr_2Se_4$ Films", *Fizika Tverd. Tela*, Vol. 28, No. 5, 1986, 1583-1585.
298. H. Conrad, N. Karam, and S. Mannan, "Effect of Prior Cold Work on the Influence of Electric Current Pulses on the Recrystallization of Copper", *Scripta Metallurgica*, Vol. 18, No. 3, 1984, 275-280.
299. K. Vashchenko, D. Chernega, S. Vorobev, and Y. Gotvyanskii, "Effect of Electric-current Action During Cast-Iron Crystallization on the Properties of Castings", *Liteinoe Proizvod*, No. 2, 1973, 27-29.
300. V. Sizykh, V. Isupov, and V. Kirillov, "Effect of Strong Electric Field on Lead Magniobate Single Crystals", *Fizika Tvergado Tela*, Vol. 29, No. 3, 1987, 783-786.
301. H. Conrad, N. Karam, S. Mannan, and A. Sprecher, "Effect of Electric Current Pulses on the Recrystallization Kinetics of Copper", *Scripta Metallurgica*, Vol. 22, No. 2, 1988, 235-238.
302. H. Conrad, and A. Sprecher, "Effect of an Electric Field on the Recovery and Recrystallization of Al and Cu", *Scripta Metallurgica*, Vol. 23, No. 6, 1989, 821-824.

303. B. Zvonkov, E. Kolosov, and R. Rubtsova, "Effect of Electric Current on the Recrystallization of Indium Antimonide", *Izvestiya Akademii Nauk SSR, Neorganicheskie Materialy*, Vol. 19, No. 3, 1983, 478-479.
304. Z. Xu, Z. Lai, and Y. Chen, "Effect of Electric Current on the Recrystallization Behavior of Cold Worked alpha.-titanium", *Scripta Metall.*, Vol. 22, No. 2, 1988, 187-190.
305. M. Roulleau, and J. Capus, "Electric Field Effect on the Phenyl Salicylate Crystallization Rate", *C. R. Hebd. Seances Acad. Sci., Ser. C*, Vol. 265, No. 18, 1967, 961-964.
306. A. Odobescu, "Effect of an Electric Field on the Kinetics of Selenium Crystallization From Amorphous and Liquid States", *Sb. Tr. Molodykh Uch. Kishinev. Politekh. Inst.*, 1969, 128-136.
307. A. Nosov, D. Nosova, and G. Shuppe, "Mechanism of the Effect of an Electric Field on the Growth of Crystal Whisker", *Radiotekh. Elektron.*, Vol. 30, No. 8, 1985, 1606-1610.
308. K. Mackenzie, R. Smits, and P. Melling, "Calcination of Titania. III. Effects of Electric Fields on Crystal Growth in Anatase", *Trans. J. Br. Ceramic Society*, Vol. 73, No. 6, 1974, 185-189.
309. E. Lyudvik, and A. Lyudivk, "Effect of an Electric Field on Epitaxial Growth of Iron Films", *Nauch. Priborostr. Dlya Fizika Issled*, Ch. 2, 1975, 21-25.
310. E. Lyubimov, E. Lyubushkin, V. Pavilainen, and A. Pekarev, "Effect of an Electric Field on Initial Growth Stages of Polycrystalline Silicon Films on an Insulating Substrat", *Sb. Nauch. Tr. po Probl. Mikroelektron. Mosk. In-t Elektron Tekhn.*, No. 21, 1975, 19-23.
311. A. Krylov, and V. Romanenko, "Effect of an Electric Current on the Distribution of Impurities in Bismuth Under Different Methods of Crystallization", *Izvestiya Akademii Nauk SSR, Neorganicheskie Materialy*, Vol. 16, No. 9, 1980, 1543-1545.
312. H. Iwanaga, T. Yoshiie, T. Yamaguchi, and N. Shibata, "Effects of an Electric Field on the Growth of Cadmium Sulfide Crystals", *Journal of Crystal Growth*, No. 49, No. 3, 1980, 541-546.
313. V. Gordeev, A. Pustogarov, Y. Kucherov, G. Kudinov, and V. Sukhinin, "Effect of Electric Current on the Recrystallization Texture of Metals", *Izv. Sib. Otd. Akad. Nauk USSR, Ser. Tekh. Nauk*, No. 3, USSR, 1984, 137-139.
314. L. Golub, D. Ivanchuk, and A. Smulskii, "Effect of Electric Current on the Solidification of Aluminum-silicon Alloys", *Nauch. Tr. Mosk. In-t Stali i Splavov*, No. 148, USSR, 1983, 27-30.
315. H. Conrad, Z. Guo, M. Fisher, W. Cao, and A. Sprecher, "Effects of Electric Current Pulses on the Recrystallization of Metals", *Recryst. '90*, Mineral and Metallic Materials Society, Warrendale, PA, 1990, 301-306.

316. S. Belan, I. Bolotov, and L. Komarova, "Effect of Electric Current on the Crystallization of Amorphous Selenium", *Nekot. Vop. Sferolitn. Krist.*, 1970, 16-24.
317. T. Yoshiie, H. Iwanaga, T. Yamaguchi, and N. Shibata, "Effect of an Electric Field on the Polarity of Growth Direction in CdSe and ZnO Crystals", *Journal of Crystal Growth*, Vol. 51, No. 3, 1981, 624-626.
318. J. Warner, and J. Verhoeven, "The Effect of an Electric Field on the Solidification of Off-eutectic Tin-lead Composite Alloys", *Journal of Materials Science*, Vol. 8, No. 12, 1973, 1817-1822.
319. K. Vashchenko, D. Chernega, S. Vorobev, N. Lysenko, and Y. Yakochuk, "Effect of Electric Current on the Solidification of Cast Iron", *Metallovedenie i Termicheskaya Obrabotka Metallov*, Vol. 16, No. 3, 1974, 62-65.
320. S. Semin, "Effect of an Electric Current on the Nucleation Kinetics of Binary Metallic Systems with Miscibility Gap", *Magnitnaya Gidrodinamika*, Vol. 16, No. 4, USSR, 1980, 77-83.
321. A. Lychev, and A. Chereminsin, "Electric Field Effect on Crystallization Kinetics", *Soviet Physics Journal*, Vol. 22, No. 2, 1979, 162-165.
322. K. Kurien, and M. Ittyachen, "Effect of Electric Field on the Growth of Barium Molybdate Crystals in Silica Gel", *Journal of Materials Science*, Vol. 15, No. 7, 1980, 1724-1729.
323. Y. Kanter, and I. Neizvestnyi, "The Effect of the Electric Field on Heterogeneous Nucleation in Germanium Melt", *Physics, Chemistry, and Mechanics of Surfaces*, Vol. 2 No. 7, 1985, 2006-2015.
324. H. Iwanaga, T. Yoshiie, T. Yamaguchi, and N. Shibata, "Effects of an Electric Field on the Growth of CdS Crystals", *Journal of Crystal Growth*, Vol. 49, No. 3, 1980, 541-546.
325. I. Geller, B. Kolomiets, and A. Popov, "Crystallization of Selenium Under the Effect of Electric Fields of Various Frequencies", *Izvestiya Akademii Nauk SSR, Neorganicheskie Materialy*, Vol. 9, No. 1, 1973, 127-128.
326. A. Lychev, Y. Rudenko, and A. Cheremisin, "Effect of an Electric Field on Crystallization", *Soviet Physics Journal*, Vol. 20, No. 4, 1977, 441-444.
327. M. Labes, and A. Symanski, "Influence of Electric Fields on the Rate of Growth of Molecular Solids", *Mech. For the Effect of Elec. and Magnetic Fields on Biol. Systems*, Sep. 1970.
328. B. Vonkov, E. Kolosov, and R. Rubtsova, "Electric Current Effect on InSb Crystallization", *Izv. Akad. Nauk SSSR, Neorg. Mater.*, Vol. 19, No. 3, 1983, 478-479.
329. John Hopkins University, Dept. of Chemical Engineering, *Initial Studies of Electric Field Effects on Ceramic Powder Formation in Flames*, CONF-900704-6, J. Katz, and C. Hung, Dec. 1989.

330. Army Research Office, *Effect of Electric Current Pulses on the Recrystallization of Copper*, ARO-18184.3-MS, H. Conrad, N. Karam, and S. Mannan, January 7, 1983.
331. F. Lu, and S. Hsu, "Study of the Crystallization Behavior of Poly(vinylidene Fluoride) From the Melt Under the Effect of an Electric Field", *Macromolecules*, Vol. 19, No. 2, 1986, 326-329.
332. V. Dmitrevskii, V. Merkulov, and A. Petrov, "Effect of Electric Field on the Glass Transition Temperature of Polymers", *Izv. Vyssh. Ucheb. Zaved., Fizika*, Vol. 13., No. 7, USSR, 1970, 157-158.
333. H. Marand, and R. Stein, "Isothermal Crystallization of Poly(vinylidene fluoride) in the Presence of High Static Electric Fields II. Effect of Crystallization Temperature", *Journal of Polymer Science, Part B: Polymer Physics*, Vol. 27, No. 5, 1989, 1089-1106.
334. P. Gies, and R. Gerhardt, "Strong Electric Field Effect on the Optical Response Properties of a Metal Surface in p-Polarized Light", *Europhysics Letters*, Vol. 1, No. 10, 1986, 513-519.
335. P. Perov, and M. Elinson, "Effect of Strong Electric Fields on the Optical Properties of Thin Films", *Czech. Conference Electron. Vac. Phys.*, 1969, 413-418.
336. D. Kolendritskii, Y. Piryatinskii, and V. Slobodyanik, "Effect of an Electric Field on the Fluorescence of Impurity-containing Anthracene Crystals", *Tezisy - Vses. Soveshch. Lyumin., 24th*, Akad. Nauk Beloruss. SSR, Inst. Fizika, Minsk, USSR, 1977, 101-103.
336. L. Gaudart, "Effect of Electric Field on the Photoelectric Effect of Thin Gold Layers", *C. R. Acad. of Science*, Vol. 267B, No. 18, Paris, France, 1968, 970-973.
337. B. Rumyantsev, and E. Frankevich, "Effect of an Electric Field on the Delayed Fluorescence of Anthracene", *Optika i Spektroskopiya*, Vol. 25, No. 6, 1969, 938-942.
338. R. Perrenoud, R., M. Aegeter, and J. Rossel, "Effect of an Electric Field on the Phosphorescence of KI at Low Temperature", *Helvetica Physica Acta*, Vol. 44, No. 5, 1971, 604.
339. M. Morita, Y. Kuwamoto, K. Ono, and K. Murata, "Electric Field Effects on the Luminescence in Ferroelectric Cr^{3+} Compounds", *Journal of Luminescence*, Vol. 12-13, 1976, 799-804.
340. M. Menes, "Electric Field Effects on the UV Absorption of NaI, KI, and RbI", *Physical Review B*, Vol. 10, No. 10, 1974, 4469-4479.

341. W. Liptay, B. Dumbacher, and H. Weisenberger, "The Effect of an Electric Field on the Optical Absorption of Molecules. VII Electro-optical and Dielectric Measurements on Some Dyes", *Zeitschrift fur Naturforschung A*, Vol. 23a, No. 10, 1968, 1601-1612.
342. D. Kilendritskii, M. Kurik, Y. Piryatinskii, and V. Slobodyanik, "Effect of an Electric Field on the Fluorescence of Impurity Anthracene Crystals", *Zhurnal Eksperimentalnoi i Teoreticheskoi Fizika*, Vol. 74, No. 4, 1978, 1264-1271.
343. N. Duruy, C. Brunel, and A. Izreal, "The Effect of Electric Field Inhomogeneity on the Electrical and Luminescence Characteristics of DC Electroluminescent ZnS:Mn, Cu Thin Films Device", *Fourth Display Research Conference Eurodisplay '84 Proceedings*, Soc. Electr. Electron and Radioelectr., Paris, France, 1984, 239-242.
344. W. Bala, and B. Mirowski, "Electric Field Effects on Luminescence of ZnS: Cu, Mn, Cl Layers", *Prace Przemyslowego Instytutu Elektroniki*, Vol. 9, No. 2, 1968, 143-149.
345. P. Augustovs, and K. Shvarts, "The Effect of External Electric Field and Light Intensity on Photorefraction in LiNbO₃", *Larvijas PSR Zinatnu Akademijas Vestis, Fizikas un Tehnisko Zinatnu Serija*, No. 5, 1978, 10-12.
346. T. Yokogawa, T. Saitoh, and T. Narusawa, "Effects of Electric Field on ZnSe/ZnS Strained-layer Superlattices", *Journal of Crystal Growth*, Vol. 101, No. 1-4, 1990, 550-553.
347. M. Yamawaki, and C. Hamaguchi, "Effect of Electric Fields on Luminescence in GaAs", *Physica Status Solidi (B): Basic Research*, Vol. 112, No. 1, 1982, 201-210.
348. A. Nouailhat, R. Perrenoud, M. Aegerter, and J. Rossel, "Electric Field Effect on the Luminescence of Kl;Tl", *Journal of Luminescence*, Vol. 6, No. 4, 1973, 245-255.
349. S. Salomon, *Effects of Electric Field on Recombination Emission and Far Infrared Emission of Impurities in InSb and N-type Ge*, Purdue University (thesis), 1969.
350. V. Mushinskii, and M. Karaman, "Optical Absorption of Gallium Selenide and Gallium Telluride Single Crystals and Solid Solutions Based on Them", *Sbornik Nauchnykh Statey Yestestvennyye i Matematicheskiye Nauki*, 1969, 71-84.
351. V. Kovbasyuk, "Field Effect in the Photoconductivity of Pure Silicon in the Infrared", *Ukrain. Phys. Journal*, Vol. 12, No. 3, 1967, 404-413.
352. B. French, *Effect of a Uniform Electric Field Upon Optical Absorption of Gallium Arsenide*, University of California (thesis), 1967.
353. M. Chester, and P. Wendland, "Electric Field Effects on Indirect Optical Transitions in Silicon", *Physical Review, 2nd Series, Section A*, Vol. 140, 1965, A1384-A1390.

354. Brown University, Department of Physics, *Electric Field Effect on Optical Transition to the $n=1$ Exciton in Cuprous Oxide*, AROD-6412:11-P, S. Brahm, and M. Cardona, July 20, 1968.
355. M. Kerimov, and B. Suleimanov, "Effect of Electric Field Strength of the Intensity Distribution of Electrostimulated Thermoluminescence of Polyethylene", *Physica Status Solidi A*, Vol. 94, No. 1, 1986, K51-K54.
356. A. Nouailhat, R. Perrenoud, M. Aegerter, and J. Rossel, "Static Electric Field Effect on the Thermoluminescence of KI:TL Irradiated at Low Temperature", *Helvetica Physica Acta*, Vol. 45, No. 6, 1972.
357. I. Oksman, T. Shchavelkina, V. Smirnov, and G. Talalakin, "Problem of the Electroluminescence of GaAs Single Crystals", *Soviet Physics - Semiconductors*, Vol. 2, 1968, 761-763.
358. Princeton University, *Optical Response of Semiconductors in Electric Fields: Excitonic Effects*, AFOSR-TR-71-3113, F. Weinstein, J. Dow, and B. Lao, July 12, 1971.
359. K. Ueno, K. Hayashi, and S. Okamura, "Radiation-induced Ionic Polymerization. VI. Effect of High Electric Field on Polymerization of Styrene", *Nippon Hoshasen Kobunshi Kenkyu Kyokai Nempo*, Vol. 8, 1967, 65-70.
360. F. Andruzzi, P. Cerrai, M. Di Maina, and P. Giusti, "Polymerization of beta-methyl-p-methoxystyrene(anethole). IV. Effect of an Electric Field on Polymerization in the Presence of Iodine", *Chim. Ind.*, Vol. 52, No. 2, Milan, Italy, 1970, 146-150.
361. U. Akbulut, R. Birke, and J. Fernandez, "Electric Field Effects in Polymerization of a-Methylstyrene", *Makromol. Chem.*, Vol. 179, No. 10, 1978, 2507-2513.
362. G. Fleischer, O. Herbath, and H. Schwind, "Effect of Constant Electric Fields on Radical Polymerisation. II. Results", *Plaste und Kautschuk*, Vol. 25, No. 2, 1978, 67-71.
363. D. Cu, M. Friedrich, and W. Patz, "Effect of Normal Electric Field on Growth of Gold Films on NaCl Cleavage Surfaces", *Thin Solid Films*, Vol. 43, No. 3, 1977, 337-342.
364. E. Nechiporenko, V. Krivoruchko, V. Sagalovich, and V. Podtykan, "Effect of an Electric Field on the Growth of Deposits During the Pyrolysis of Molybdenum Carbonyl", *Izvestiya Akademii Nauk SSR, Neorganicheskie Materialy*, Vol. 5, No. 6, 1969, 1025-1029.
365. K. Chopra, "Effect of an Electric Field on the Growth of Single-crystal Metal Films", *Rost Kristallov, Akad. Nauk SSSR*, Vol. 8, 1968, 141-145.
366. F. Aliev, I. Ivanova, D. Ismailov, and R. Shafizade, "Effect of the Electric Field on Formation of Copper Selenide Films", *Fizika Khim. Obrab. Mater.*, No. 1, 1985, 126-128.

367. R. Zhilinskas, and L. Yakuchenis, "Effect of Electric Fields on the Growth of Aluminum Films", *Fizika Metallov i Metallovedenie*, Vol. 26, No. 4, 1968, 764-765.
368. C. Takenaka, and K. Nakajima, "Effect of Electric Current on the LPE Growth of InP", *Journal of Crystal Growth*, Vol. 108, No. 3-4, 1991, 519-524.
369. L. Pranevicius, J. Dudonis, and V. Titas, "Effect of an Electric Field on the Formation of Dielectric Films During Ion Implantation", *Soviet Physics - Collection*, Vol. 16, No. 4, 1976, 68-71.
370. Y. Murayama, "Effects of Electric Field on the Orientation and Particle Arrangement of Gold Deposits Evaporated in Vacuo", *Thin Solid Films*, Vol. 12, No. 2, 1972, 287-290.
371. R. Hrach, and M. Chvalkovska, "Modelling of Electric Field Effects on the Growth of Thin Metallic Films", *Jemna Mechnika a Optika*, Vol. 26, No. 6, 1981, 159-160.
372. L. Apininskaya, V. Furman, and N. Vergeles, "Effect of Electric Field Strength on the Rate of Deposition and Composition of Electrophoretic Chromium Carbide Alloy Coatings", *Soviet Powder Metallurgy and Metal Ceramics*, Vol 16, No. 4, 1977, 50-52.
373. Y. Murayama, and K. Kashiwagi, "Effects of Electric Fields on the Growth Processes of Gold Films Formed on NaCl Surfaces by R. F. Ion Plating", *Proceedings of the 7th International Vac. Congress*, International Union for Vac. Science, Technology, and Applications, Brussels, Belgium, 1977, 1721-1724.
374. J. Lebas, "Effect of an Electric Field on the Growth of Very Thin Films", *Thin Solid Films*, Vol. 10, No. 1, 1972, 91-97.
375. E. Dominguez, G. San Miguel, and C. Martin, "Effect of Electric Field on the Formation of KCl Thin Films", *Thin Solid Film*, Vol. 11, No. 2, 1972, 243-248.
376. V. Koleshko, A. Kovalevskii, and V. Khomich, "Effect of Electric Field on Formation and Properties of Mo Films", *Izv. Akad. Nauk SSSR, Neorg. Mater.*, Vol. 15, No. 7, 1979, 1225-1228.
377. L. Lavrenteva, G. Ikonnikova, O. Ivleva, and L. Krasilnikova, "Effect of an Electric Field on Growth of Layers of Gallium Arsenide in the GaAs-AsCl₃-H₂ System", *Soviet Physics - Crystallography*, Vol. 24, No. 2, 1979, 199-201.
378. N. Kazakov, V. Novikove, and A. Ekimove, "Electric Field Effect on Quality of Diffusion Joint of Piezoceramics With Metals", *Avtom. Svarka*, Vol. 5, 1983, 71-72.
379. I. Onishi, I. Okamoto, and M. Imachi, "Adhesion of Metals. I. Effect of Electric Field Applied During Bonding Process on Adhesive Strength", *Technol. Rep. Osaka University*, Vol. 17, No. 769-800, 1967, 377-384.

380. U. Mehrotra, K. Pandey, S. Pandey, and J. Nanda, "Effect of Feeble Electric Field and Surface Treatment on Adhesive Joints", *Labdev Journal of Science and Technology, Part A.*, Vol. 10A, No. 2, 1972, 87-90.
381. V. N. Kestelman, "Modification of Polymeric Materials", *Developments in Civil Engineering*, Vol. 5, Elsevier Science Publishing Co., Amsterdam, Netherlands, 1982, 369-374.

B. ULTRASONIC WAVE EFFECTS

382. D. I. Shtakel'berg, G. A. Man'kova, and G. I. Boldyrev, "Ultrasonic Control of the Physical and Mechanical Properties of the Clay-Water System", *Glass and Ceramics*, Vol. 41, No. 11-12, 1984, 497-499.
383. G. N. Pachevskaia, and E. V. Sitnikova, "Dependence of Heating Zone Width on the Dissipation Properties of the Material During Ultrasonic Processing of a Rod", *Fiziko-Khimicheskaia Mekhanika Materialov*, Vol. 9, No. 6, 1973, 111-113.
384. N. F. Vildanova, M. G. Gaidukov, N. I. Nokskoca, and V. A. Pavlov, "Influence of Ultrasonic Processing on the Microstructure and Creep Characteristics of the Cast Alloy AL27", *Fizika Metallov i Metallovedenie*, Vol. 39, 1975, 367-374.
385. A. E. Ansyutina, "Effect of Ultrasonic Processing on the Structure and Properties of Magnesium Alloy Billets", *Izvest Akad. Nauk. SSSR Metally*, 1970, 76-81.
386. V. S. Biront, and L. N. Goncharova, "Investigation of Supercooled Solid Solution Decomposition in Aluminum Alloy AV", *Tekhnol. Legk. Splavov*, (5), 1978, 50-52.
387. E. G. Konovalov, I. G. Dovgyallo, and A. L. Skrpinichenko, "Change in Structure of Copper Due to the Ultrasonic Effect", *Metallovedenie i Term Obrabotka Met Nauka i Tekhnika*, 1965, 102-104.
388. V. F. Kazantsev, and V. G. Badalyan, "Investigation of the Ultrasonic Effect on the Transient Creep Process", *Phys. Met. Metallogr.*, Vol. 55, No. 1, 1983, 174-176.
389. A. V. Belotskii, V. N. Vinnichenko, I. M. Mukha, S. V. Prikhodko, and V. G. Tinyaev, "Strengthening of Cemented Carbides by Ultrasonic Oscillations. III. Influence of Ultrasonic Treatment on the Stressed State of Tungsten-Cobalt", *Poroshk. Metall.*, (8), 1984, 84-88.
390. G. Y. Bazelyuk, R. G. Gontareva, O. I. Kozyrskii et al., "Combined Action of Cycling Heat Treatment and Ultrasonic Emission on the Structural Condition and Mechanical Properties of Kh16N11M3", *Strength of Materials*, Vol. 12, No. 9, 1980, 1139-1145.
391. M. D. Tyavlovskii, "Influence of Structure and Ultrasonic Vibrations on the Mechanical Properties of Steel in Dynamic Deformation", *Metalloved. i Term. Obrab. Met.*, Vol. 23, No. 6, 1981, 35-37.

392. I. A. Gindin, I. M. Neklyudov, O. I. Volchok, et al., "Effect of Neutron Irradiation on the Mechanical Properties of Cu Previously Subjected to the Effects of Ultrasound", *Ukr. Fizika Zh.*, Vol. 27, No. 4, 1982, 620-622.
393. M. D. Tyavlovskii, "Effect of Complex Dynamic Loading on the Impact Toughness of Steel in Different Structural States", *Metalloved i Term. Obrab. Met.*, Vol. 24, No. 4, 1982, 59-60.
394. O. I. Volchok, I. A. Gindin, L. A. Kornienko et al., "Influence of Ultrasonic Action on the Mechanical Properties and Structure of 15KH2MFA Steel", *Problemy Prochnosti*, Vol. 14, No. 4, 1982, 122-125.
395. O. V. Abramov, R. I. Entin, E. V. Kisterev et al, "Effect of Ultrasonic Treatment on the Long-term Strength of Welded Joints Made From Medium Carbon Construction Steels", *Problemy Prochnosti*, Vol. 18, No. 6, 1986, 105-107.
396. Z. N. Protsenko, B. P. Podafa, and O. G. Zarubitskii, "Effect of Ultrasonic on the Microhardness and Structure of Aluminised Layers on ZhS6k Alloy", *Physics and Chemistry Mater. Treat.*, Vol. 21, No. 1, 1987, 93-94.
397. A. Pushkar, "Changes in the Properties and Substructure of Mild Steel Under Ultrasonic Loading", *Problemy Prochnosti*, No. 7, 1986, 47-49.
398. E. V. Kismerev, A. A. Sjevchenok, and O. V. Abramov, "Effect of Ultrasonic Treatment on the Structure of 30Kh3 Steel", *Izvestiya Vysshikh Uchebnykh Zavedenii, Chernaya Metallurgiya*, No. 9, 1986, 88-90.
399. M. S. Neurubai, "Effects of Ultrasonic Vibrations on the Mechanical Properties of Difficult-to-Deform Materials", *Metal Science and Heat Treatment*, Vol. 29, No. 3-4, 1987, 254-258.
400. I. K. Leselidze, E. S. Lapiashvili, and M. T. Asatiani, "Structure and Mechanical Properties of Copper After Ultrasonic Treatment and Neutron Irradiation", *Physics of Metals and Metallography*, Vol. 61, No. 6, 1986, 171-173.
401. T. Y. Bazelyuk, I. G. Polotskii, O. N. Kashevskaya, et al., "Influence of Ultrasonics on Mechanical Properties of the Dispersion-hardened Alloy AK4-1", *Fizika Met. i Metalloved*, Vol. 42, No. 4, 1976, 861-863.
402. N. N. Dmitriev, O. V. Abramov, V. P. Kudel'kin, et al., "The Influence of Ultrasonic Treatment on the Mechanical Properties of Nickel-based Alloys", *Izv. Akad. Nauk. SSSR Met.*, No. 5, 1977, 205-210.
403. I. G. Polotskii, V. F. Belostotskii, and G. A. Nikitova, "The Effect of Ultrasonics on the Mechanical Properties and Structure of Solid Solutions of Nickel-Chromium and Nickel-Molybdenum", *Metallofizika*, No. 69, 1977, 66-70.
404. S. V. Kovsh, V. A. Kotko, I. G. Polotskii et al., "Influence of Ultrasonics on the Dislocation Structure and Mechanical Properties of Molybdenum", *Fizika Met. i Metalloved.*, Vol. 35, No. 6, 1973, 1199-1205.

405. A. Puskar, "Effect of High Frequency Cyclic Loads on Mechanical Properties and Dislocation Structure of Mild Steel", *Fizika Met. i Metalloved.*, Vol. 36, No. 4, 1973, 844-848.
406. E. G. Konovalov, E. G., I. G. Dovgyallo, and V. I. Bord, "One Effect of Ultrasonics on Copper", *Problemy Prochnosti*, Vol. 6, No. 5, 1974, 55-58.
407. N. F. Vil'danova, N. I. Noskova, and V. A. Pavlov, "Influence of Ultrasonic Vibrations on the Mechanical Properties and Fine Structure of Aluminum and an Aluminum-Magnesium Alloy", *Physics of Metals and Metallography*, Vol. 36, No. 1, 1973, 119-123.
408. E. G. Konovalov, and M. D. Tyavloskii, "Effect of Ultrasonic Oscillations of the Mechanical Properties of D16T Alloy Under Dynamic Bending", *Russian Ultrasonic*, Vol. 4, No. 3, 1974, 122-125.
409. N. N. Dmitriev, O. V. Abramov, V. P. Kudel'kin et al., "Effect of Ultrasonic Treatment on the Mechanical Properties of Nickel-based Alloys", *Izvestiya Akademii Nauk SSR, Metally*, No. 5, 1977, 205-210.
410. L. I. Gurskii, and S. I. Petrenko, "Changes in the Dislocation Structure of Metals Under the Action of Ultrasound", *Akademiia Nauk BSSR, Doklady*, Vol. 14, 1970, 1082-1085.
411. I. A. Gindin, G. N. Malik, and N. K. Nechvolod, "Effect of Ultrasonic Radiation on the Region of Action of Dislocation Depletion Mechanism with a Step Creep of LiF Single Crystal", *Ukrayin Fizika Zh.*, Vol. 13, No. 11, 1968, 1823-1827.
412. R. Vasudevan, and C. S. Muralidhar, "Effect of Ultrasonic Vibrations on the Age Hardening Characteristics of Some Aluminum-based Alloys", *Scandinavian Journal of Metallurgy*, Vol. 16, No. 4, 1987, 164-170.
413. L. S. Palatnik, I. K. Tartakovskaya, A. A. Kozma, L. A. Khukova, and V. F. Pusan, "Examination of the Influence of Ultrasonic and Thermal Effects on the Structure of Thin Gallium Layers", *Izvestiya Akademii Nauk SSSR Met.*, No. 1, 1983, 52-57.
414. I. M. Mukha, and V. N. Vinnichenko, "Strengthening of Hard Alloys by Ultrasonic Vibrations. I.", *Poroshk. Metall.*, (10), 1982, 88-91.
415. A. M. Dankov, and N. A. Levanovich, "Influence of Ultrasonic Treatment on the Durability of Gear Wheels in Bending", *Vestn. Mashinostr.*, (11), 1987, 60-63.
416. A. P. Zdebskii, N. I. Deryugina, A. N. Annaniyazov, G. Garyagdyev, G. Korradi, and K. Polgar, "Optically and Acoustically Stimulated Changes in the Electromechanical Properties of LiNbO₃:Mg Crystals", *Pisma Zh. Tekh. Fizika*, Vol. 14, No. 23-24, 1988, 2171-2174.
417. K. Nogami, O. Sakurai, N. Mizutani, and M. Kato, "Effect of Starting Solution on Microstructure of Spherical SiO₂ Particles Prepared by Ultrasonic Spray Pyrolysis", *Journal of the Ceramic Society of Japan*, Vol. 95, No. 7, 1987, 682-685.

418. W. Wisniewska, "Ultrasonic Effect on Polyamide-6 Fibers", *Polimery*, Vol. 19, No. 11, 1974, 539-545.
419. K. Terao, T. Kuno, and M. Mizuno, "Heat Treatment by Ultrasonic Heating", *Bulletin of the JSME*, Vol. 23, No. 182, 1980, 1275-1282.
420. B. G. Belov, "Effect of Ultrasound on Diffusion in a Gel-liquid System", *Akust. Zh.*, Vol. 16, No. 4, 1970, 603-607.
421. H. Koganei, S. Tanaka, and T. Sukurai, "Changes in Mechanical Properties of Ultrasonically Fatigued Metals", *Journal of the Society of Materials Science*, Vol. 24, No. 263, 1975, 753-760.
422. J. Styk, J. Adamka, and Z. Izdinska, "Effect of Ultrasonic Treatment on Fatigue Properties of Notched Welds", *Zvaranie*, Vol. 36, No. 2, 1987, 42-44.
423. T. H. Noh, and S. S. Chun, "The Effect of Ultrasonic Vibrations on the Precipitation Hardening of 7075 Al Alloy", *Journal of Korean Institute of Met.*, Vol. 18, No. 5, 1980, 424-431.
424. J. K. Kim, and S.S. Chun, "Study of the Effect of Ultrasonics on Boronizing of Steel", *Journal of Korean Institute of Met.*, Vol. 18, No. 6, 1980, 598-607.
425. Y. Tanaka, M. Ido, U. Umdeki, and S. Honda, "Plastic Deformation of Metal Surface Induced by Ultrasonic Hammering", *Bulletin of the Japan Society of Precision Engineering*, Vol. 9, No. 4, 1975, 99-104, 110.
426. M. C. Jon, W. P. Mason, and D. N. Beshers, "Internal Friction During Ultrasonic Deformation of Alpha-brass", *Journal of Applied Physics*, Vol. 47, No. 6, 1976, 2337-2349.
427. H. Koganei, S. Tanaka, and T. Sakurai, "Mechanical Properties of Carbon Steel Fatigued Ultrasonically", *Transactions of the Iron and Steel Institute of Japan*, Vol. 17, No. 4, 1977, 179-186.
428. W. Czerwinski, and A. Basinski, "Influence of High Frequency Ultrasounds on the Structure of Polyethylene Terephthalate Fibers", *Polimery*, Vol. 23, No. 1, 1978, 12-15.
429. Air Force Systems Command, Foreign Technology Division, (Academy of Sciences of the Belorussian SSR), *Ultrasonic Creep Test Stand For High Temperature Materials, and Ultrasonic Effects on Copper and Aluminum Alloy Microstructure*, FTD-TT-65-1408; TT-6760506; AD-645836, 1966.
430. R. E. Green, Jr., "Interaction of High Intensity Ultrasonic Waves With Solids", High Intensity Electro-magnetic and Ultrasonic Effect on Inorganic Materials Behavior and Processing, *U.S. Army Research Office Workshop*, Raleigh, NC, July 18-19, 1989.
431. V. Ocelik, P. Palcek, P. Diko, J. Miskuf, and P. Duhaj, "Propagation of Fatigue Crack in Amorphous $Fe_4ONi_4OB_2O$ at High Frequency Loading", *Key Engineering Materials*, Vol. 40-41, Trans. Tech. Publishers, Aedermannsdorf, Switzerland, 1990, 369-373.

432. A. N. Bobryshev, E. N. Kapustyanskii, and V. I. Solomatov, "Fatigue of Epoxy Composites with a Fine Filler at High Loading Frequencies", *Mekh. Kompoz. Mater.*, (3), 1988.
433. N. J. Wells, and L. D. Roth (Westinghouse Research Center) and O. Buck (Iowa State University), and J. K. Tien (Columbia University), *Ultrasonic Fatigue: Proceedings of the First International Conference on Fatigue and Corrosion Fatigue up to Ultrasonic Frequencies*, Champion, PA, Oct. 25-30 1981.
434. S. E. Stanzl, and E. K. Tschegg, "Fatigue Crack Growth and Threshold Behavior at Ultrasonic Frequencies", *Fracture Mechanics, 14th Symposium, Vol. 2, Testing and Applications*, American Society for Testing and Materials Applications, Philadelphia, PA, 1983, 3-18.
435. H. M. Forst, Action of Ultrasound on a Viscoelastic Solid, University of Vermont, Dissertation.
436. A. Pushkar, "Metal-Metal Composites Loaded at Ultrasonic Frequencies", *Ultrasonic Fatigue Conference*, Metallurgical Society/AIME, Warrendale, PA, 1982, 315-320.
437. R. Mitsche, and S. Stanzl, "Fatigue Stressing at 20 kHz as a Means of Materials Testing and Quality Control", *Zeitschrift für Metallkunde*, Vol. 62, No. 12, 1971, 863-866.
438. S. Stanzl, "The Low Temperature Behavior of Metallic Materials on Fatigue Testing With Ultrasonic. 20 kHz", *Metall.*, Vol. 33, No. 2, 1979, 159-164.
439. C. L. Daugste, S. L. Skalozub, and Y. S. Urzhumtsev, "Electron-Acoustic Apparatus For Investigating the Acoustocreeep and Acoustic Fatigue of Rigid Polymeric Materials", *Mekh. Polim.*, Vol. 7, No. 6, 1971, 1125-1127.
440. V. Ocelik, "Fracture Toughness Testing of Metallic Glass", *Metallic Materials*, Vol. 24, No. 4, 1986, 223-227.
441. B. Weiss, R. Stickler, S. Schider, and H. Schmidt, "Corrosion Fatigue Testing of Implant Materials (Nb, Ta, Stainless Steel) at Ultrasonic Frequencies", *Ultrasonic Fatigue: Proceedings of the 1st International Conference on Fatigue and Corrosion Fatigue Up to Ultrasonic Frequencies*, Metallurgical Society of AIME, Warrendale, PA, 1982, 387-411.
442. B. Weiss, "Deformation Caused by Ultrasonic Vibrations, Pt. 3. Technical Significance of the Ultrasonic Process", *Aluminum*, Vol. 49, No. 2, 1973, 165-169.
443. A. Pushcar and I. Durmis, "Cyclic Microductility and Durability of Carbon Steels", *Problemy Prochnosti*, No. 11, 1986, 12-15.
444. Y. Filya, "Relationship Between the Structure of Aluminum Structural Alloys and Characteristics of Muticycle Fatigue in Ultrasonic Frequency Loading Under Room and Low Temperature Conditions", *Problemy Prochnosti*, No. 5, 1987, 33-38.

445. A. Tulyanon, and K. Salama, "Ultrasonic Fatigue in Copper and Aluminum", *1976 Ultrasonics Symposium Proceedings*, IEEE, New York, NY, 1976, 644-648.
446. N. E. Atanasiu, "Intensification of Tube Drawing by Axial Ultrasonic Oscillation of the Plug", *Ultrasonics*, Vol. 18, No. 6, 1980, 255-260.
447. N. Maropis, *The Application of Vibrational Energy to the Drawing of Metallic Materials*, AeroProjects, Inc., West Chester, PA, 1966.
448. N. Atanasiu, "Drawing of Aluminum Alloy Tubes Using Ultrasonics: An Analytic Determination Compared with Experimental Data", *Mem. Etud. Sci. Rev. Metall.*, Vol. 77, No. 11, 1980, 993-1002.
449. K. M. Olsen, R. F. Jack, and E. O. Fuchs, "Wire Drawing in Ultrasoically Agitated Liquid Lubricants", *Wire and Wire Products*, October 1965.
450. V. L. Lanin, and M. D. Tyavlovskij, "Effect of Ultrasonic Wave Frequency on Strength of Glas Cermaics Soldered with Ultrasonics", *Vesci Akademii Navuk BSSR. Seryja Fizika-tehnicnykh Navuk*, (4), 1983, 69-73.
451. S. Matsuoka, "Effect of Ultrasonic Vibration on Joining of Aluminum to Ceramics", *Koon Gakkaishi*, Vol. 14, No. 4, 1988, 150-158.
452. K. Miyazawa, S. Matsuoka, T. Fujii, and T. Suga, "Ultrasonic Bonding of Ceramic to Metal", *Proceedings of the MRS International Meeting on Advanced Materials*, Vol. 8, Materials Research Society, Pittsburgh, PA, 1989, 275-280.
453. M. Naka, and I. Okamoto, "Ultrasonic Soldering and Brazing of Ceramics to Metal", *Proceedings of the MRS International Meeting on Advanced Materials*, Vol. 8, Materials Research Society, Pittsburgh, PA, 1988, 79-84.
454. R. G. Oswald, W. R. deMiranda, and C. W. White, "Changes in Strength and Resistance of Aluminum to Gold Ultrasonic Bonds After Temperature, Electrical, and Environmental Stress", *Proceedings of the International Microelectronic Symposium*, 1975, 324-339.
455. S. J. Horowitz, D. J. Jerry, and R. E. Cote, "Alloy Element Additions to Gold Thick Film Conductors: Effects on Indium/Lead Soldering and Ultrasonic Aluminum Wire Bonding", *27th Electronic Components Conference*, IEEE, New York, NY, 1977, 358-366.
456. A. B. Strong, D. P. Johnson, and B. A. Johnson, "Variable Interactions in Ultrasonic Welding of Thermoplastic Composites", *SAMPE Q*, Vol. 21, No. 2, 1990, 36-41.
457. K. T. Guseinov, and L. N. Ushichenko, "Study of Physicochemical Properties of Polymeric Materials During Ultrasonic Welding", *Izv. V.U.Z. Mashinostr.*, (4), 1989, 122-125.
458. A. Benatar, and T. G. Gutowski, "Ultrasonic Welding of Advanced Thermoplastic Composites", *Eng. Plast.*, Vol. 2, No. 1, 1989, 45-62.

459. R. K. Yafarov, and I. V. Zuev, "Calculation of Main Parameters for Ultrasonic Microwelding", *Svar. Proizvod.*, (4), 1983, 14-15.
460. S. Matsuoka, "Ultrasonic Welding of Amorphous Alloys", *Journal of Japanese Society of Technology*, Vol. 26, No. 288, 1985, 94-98.
461. M. Hammerschmidt, H. Kreye, and B. Meinck, "The Weldability of Metallic Alloy Glasses", *Metalloberfalche*, Vol. 34, No. 1, 1980, 23-27.
462. A. Polakovic, and Z. Augustinovicova, "Preparation of Aluminum-graphite Dispersion System by Ultrasound", *Compos. Met. Mater., Slov. Akad. Vied, Ustav, Kovovych Mater.*, Bratislava, Czech., 1978.
463. H. Richter, "Phenomena During the Joining of Metallic Materials by Ultrasonic Welding", *Schweissen und Schneiden*, Vol. 22, No. 2, 1970, 70-73.
464. W. F. McDonald, and M. W. Urban, "Modification of the PPTA Fiber Surfaces by Ultrasonic Waves", *Proceedings of the ACS Division of Polymeric Materials: Science and Engineering*, Vol. 59, ACS, Books and Journals Division, Washington, D.C., 1988, 306-310.
465. R. Sievers, "Modern Welding Process for Thermoplastic Resins", *Kunststofftechnik*, Vol. 8, No. 11, 1969, 419-422.
466. I. B. Krikshtopaitis, "Attaching Electrodes to Thin Films (using Ultrasonic Cavitation)", *Prib. Tekh. Eksp.*, Vol. 17, No. 6, pt. 2, 1974, 195-196.
467. S. Gallagan, "Laying the Groundwork for Ultrasonic Welding", *Plastics Engineering*, Vol. 41, No. 8, 1985, 35-37.
468. K. Frei, "Ultrasonic Welding of Thermoplastic Materials", *Bulletin de L'Association Suisse des Electriciens*, Vol. 64, No. 16, 1973, 991-997.
469. U. Becker, and G. Strese, "Welding of Plastics", *Kunststoffe*, Vol. 59, No. 10, 1969, 679-684.
470. G. Flodd, *Ultrasonic Energy, A Process for Laminating and Bonding Nonwoven Web Structures*, INDA Tech. Symposium Nonwovens, Washington, D. C., May 22-23, 1984.
471. M. Nonwovens, *New Ultrasonic Process for Bonding/laminating Unveiled*, Branson Ultrasonics, No. 16, 1987.
472. A. V. Kulemin, and Y. V. Kholopov, "The Diffusion Processes Taking Place During the Ultrasonic Welding of Copper to Aluminum", *Automat. Weld.*, Vol. 33, No. 6, 1980, 11-13.
473. T. C. Eakins, "Results of Solar Cell Welded Interconnection Development", *Proceedings of the 7th Intersociety Energy Conversion Engineering Conference*, American Chemical Society, Washington, D.C., 1972, 651-660.
474. MJR, "Ultrasonics Solder ALuminum Without Flux", *Des. Eng.*, Vol. 18, No. 6, 1972, 49.

475. J. Devine, and R. G. Vollmer, "Ultrasonic Bonding Arrives", *ManTech Journal*, Vol.3, No. 1, 1978, 11-14.
476. G. G. Harman, and K. O. Leedy, "An Experimental Model of the Microelectronic Ultrasonic Wire Bonding Mechanism", *Proceedings of the 10th Annual Conference on Reliability Physics*, IEEE, New York, NY, 1972, 49-56.
477. J. L. Harthoorn, "Joint Formation in Ultrasonic Welding Compared with Fretting Phenomena for Aluminum", *Ultrasonics International 1973 Conference Proceedings*, IPC Science and Technology Press, Guildford, U. K., 1973, 43-51.
478. G. E. Littleford, "Ultrasonic Welding-trends and Developments", *Fastening*, 1979, 21-22.
479. H. Reichel, and G. Klauke, "Ultrasonic Processing of Plastics and Metals", *Elektrotechnische Zeitschrift Ausgabe B*, Vol. 27, No. 10, 1975, 241-242.
480. R. Mayer, "Ultrasonic Soldering", *Verbindungstechnik*, Vol. 5, No. 3, Germany, 1973, 27-31.
481. B. E. Paton, M. D. Gabovich et al., "Welding with Alloying and Ultrasonic Processing by Means of an Ion Beam", *Dokl. Akad. Nauk. SSSR*, Vol. 273, No. 1-3, 1983, 104-106.
482. S. Caza, "Latest Ultrasonic Gives Low Cost Cleaning Inside and Out", *Brewing and Distilling International*, Vol. 11, No. 11, 1981, 33, 37.
483. General Electric Company, *Ultrasonic Cleaner Evaluation*, GEPP-TIS=526, T. J. Gillespie, 1980.
484. A. Patridge, "Precision Cleaning for Precision Glassware", *Glass*, Vol. 66, No. 1, 1989, 17-18.
485. W. E. K. Gibb, and A. D. McLachlan, "Ultrasonic Cleaning of Optical Surfaces", *National Bureau of Standards, Special Publication, No. 435, Laser Induced Damage in Optical Materials, Proceedings of 7th Annual Sym.*, 1976, 90-97.
486. L. L. Turai, *Ultrasonic Deinking of Wastepaper*, 1982 Pulping Conference, Tappi, Atlanta, GA, 1982, 387-390.
487. C. Iancu, P. Nicolae, and O. Dragan, "Studies Concerning the Use of Ultrasonic Energy in the Process of Cleaning Sintered Products", *Cercetari Metalurgice*, Vol. 24, Institute de Cercetari Metalurgice, 1983, 353-357.
488. R. Keeler, "Ultrasonic Defluxing: Waves of the Future?" *Electron. Packag. Prod.*, Vol. 28, No. 3, 1988, 52-54.
489. Anon, "Ultrasonic Cleaning - A Vast Choice", *Finishing Industries*, Vol. 5, No. 12, 1981, 26, 29.
490. A. I. Somov, O. V. Chernyi, V. T. Petrenko, and N. F. Andrievskaya, "Influence of Ultrasonics on Directional Solidification of Aluminum-nickel Alloys", *Fizika i Khim. Obrab. Mater.*, No. 4, 1975, 36-39.

491. A. S. Okhotin, V. F. Lapchinskii, and G. S. Shonin, (Akademiia Nauk SSSR, Institut Kosmicheskikh Issledovanii), *Some Results of Studies in Space Technology in the USSR*, COSPAR, 19th Plenary Meeting, Philadelphia, PA, June 8-19, 1976.
492. Y. Kanno, and T. Suzuki, "Synthesis of Fine Spherical ZrO₂-SiO₂ Particles by Ultrasonic Spray Pyrolysis", *Journal of Materials Science Letters*, Vol. 7, No. 4, 1988, 386-388.
493. I. Benevolensky, I. Pichugin, and V. Kestleman, "Ultrasonic Modification of Cold-Solidified Plastic Materials", *5th International Conference on Modified Polymers, Programme and Preprint of Short Contributions*, Vol. 2, IUPAC, Oxford, U. K., 1979, 157-160.
494. A. K. Abd El-Latif, "Ultrasonically Assisted Stabilization of Optical Glass", *American Ceramic Society Bulletin*, Vol. 53, No. 2, 1974, 180-182.
495. S. M. Sheykhaliyev, and S. I. Popel, "Obtaining Metallic Powders by Ultrasonic Atomization of Melts", *Materials Science and Met.*, Joint Publications Research Service, Arlington, VA, 1984, 27.
496. D. H. Ro, and H. Sunwoo, "Comparative Study of Conventional and Ultrasonic Gas Atomization of Aluminum Alloys", *Progress in Powder Metallurgy*, Vol. 39, Metal Powder Industries Federation, Princeton, N. J., 1984, 109-124.
497. O. V. Abramov, "Crystallization of Metals in an Ultrasonic Field", *Izdatelstvo Metallurgii*, 1972.
498. V. I. Dobatkin, G. I. Eskin, and S. I. Borovikova, "Features of Ultrasonic Action on the Process of Ingot Solidification During Continuous Casting", *Fizika i Khim. Obrab. Mater.*, No. 6, 1973, 37-41.
499. N. N. Dmitriev, O. V. Rutes, S. V. Maslenkov, V. P. Kudelk, and E. N. Milenin, "Influence of Ultrasonic Treatment of Liquid Melt on Microchemical Inhomogeneity and Plasticity of Alloys", *Fizika and Khim. Obrab. Mater.*, No. 2, 1979, 165-166.
500. L. J. Graham, L. A. Ahlberg, F. Cohen-Tenoudji, and B. R. Tittman, "Processing Resin Matrix Composites Using High Intensity Ultrasound", *IEEE 1986 Ultrasonics Symposium - Proceedings*, IEEE, New York, NY, 1986, 1013-1016.
501. N. J. Tessier, D. Kieruan, A. Madenjian, and G. Moulder, "Pultrusions with an Epoxy Matrix Improved by Ultrasonics", *Review Plast. Mod.*, Vol. 38, No. 371, 1987, 647-650.
502. M. Muran, and M. Srnanek, "Tribological Characteristics of Aluminum-Graphite Composite Material", *Met. Mater.*, Vol. 23, No. 2, 1985, 107-110.
503. V. T. Tomashevskii, V. N. Shalygin, D. A. Romanov, and S. Y. Sitnikov, "Transversal Reinforcement of Composite Materials Using Ultrasonic Vibrations", *Mechanics of Composite Materials*, Vol. 23, No. 6, 1988, 769-772.

504. A. Polakovic, "Experimental Equipment For Introduction of Insoluble Solid Particles Into Metallic Melts by Help of Ultrasound", *Kovove Mater.*, Vol. 11, No. 6, 1973.
505. L. P. Ivanova, and A. A. Borzykh, "Influence of Ultrasound on the Properties of Thermoplastic Slips", *Glass and Ceramics*, Vol. 31, No. 1-2, 1974, 112-113.
506. G. A. Kardeaschew, K. A. Salaskin et al., "Effect of Ultrasonics on the Processing of Some Polymers", *Plaste und Kautschuk*, Vol. 24, No. 1, 1977, 46-51.
507. F. S. Entelis, and M. A. Nakhamk, "Study of the Process of Ultrasonic Treatment of Plastic Ceramic Bodies", *Glass and Ceramics*, Vol. 29, No. 1-2, 1972, 107-110.
508. A. A. Borzykh, V. M. Zhmyleva, N. V. Solomin, and A. S. Shatalin, "Using Ultrasonics in the Molding of Thermoplastic Suspensions", *Glass and Ceramics*, Vol. 36, No. 9-10, 1979, 574-575.
509. I. N. Akhcerdov, and M. A. Shalimo, *Ultrasonic Vibration in Concrete Technology*, Bureau of Reclamation, Washington, D.C., 1971.
510. C. K. Hwangbo, M. R. Jacobson, H. A. Macleod, and R. H. Potoff, "Ultrasound-assisted Deposition of Dielectric Films", *Proceedings of SPIE - The International Society for Optical Engineering*, Vol. 678, SPIE, Bellingham, WA, 1986, 141-150.
511. D. Meyer, and N. Nowack, "Investigations on the Electrolytic Deposition of Lutrous Nickel in an Ultrasonic Field", *Metalloberfalche*, Vol. 38, No. 12, 1984, 524-526.
512. Showa Aluminum Co., *Corrosion Resistant Aluminum Materials Obtained by Subjecting Aluminum to Ultrasonic Wave Treatment*, Japanese J50084427 (patent), November 30, 1973.
513. Anon, "Desitech CNC Ultrasonic Profiling Machine is the First Module in Westland Helicopters' New, Super-efficient Spar Production Cell", *Aircraft Engineering*, Vol. 58, No. 6, 1986, 26-27.
514. M. Geiger, G. van der Heyd, and R. Muller, "Ultrasonic Cutting of PU Mouldings Reinforced With Milled Glass Fibers", *Kunstst. Ger. Plast.*, Vol. 79, No. 6, 1989, 500-501.
515. H. Iwanek, G. Grathwohl, R. Hamminger, and N. Brugger, "Machining of Ceramics by Different Methods", *Proceedings of the 2nd International Symposium of Ceramic Materials and Components for Engines*, Verlag Deutsche Kermische Gesellschaft, Bad Honnef, W. Germany, 1986, 417-423.
516. P. Boch, and B. Rogeaux, "Vibratory Assistance to the Pressing of Ceramic Powders", *British Ceramic Proc.*, 38, 1986, 91-100.
517. Y. A. Kurdin, A. S. Smirnov, I. I. Polyakov, and N. I. Vertokhvostova, "Nonabrasive Ultrasonic Machining of Ceramics", *Glass and Ceramic*, Vol. 39, No. 5-6, 1983, 293-295.

518. G. Grathwohl, H. Iwanek, and F. Thuemmler, "Machining of Ceramics, With Particular Reference to Ultrasonic Erosion", *Materialwissenschaft und Werkstofftechnik*, Vol. 19, No. 3, 1988, 81-86.
519. National Bureau of Standards, *The Science of Ceramic Machining and Surface Finishing*, NBS-SP-348, S. J. Schneider, Jr., and R. W. Rice, May 1972.
520. G. I. Babavants, L. B. Nezhevenko et al., "Ultrasonic Machining of Diamond Powders Used For Polishing Copper", *Soviet Journal of Superhard Materials*, Vol. 8, No. 3, 1986, 48-50.
521. K. Hatano, "Brittle Material Processing Reported, Science and Technology, Japan", *Developments in Manufacturing Process Technology*, Joint Publication Research Service, Arlington, VA, 1988, 62-70.
522. Tamaura, "Drill for Ceramic Materials", *Ceram. Ind.*, Vol. 2, No. 5, 1986, 6.
523. A. K. Zimin, A. V. Savel'ev, and V. M. Chutko, "Use of Ultrasonic Processing for the Fabrication of Optical Components Having a Complicated Surface Shape", *Opt.-Mekh. Prom.-st.*, Vol. 53, No. 1, 1986, 57-58.
524. B. Kellock, "Benefit of Ultrasonic Electrode Production", *Machinery and Production Engineering*, Vol. 145, No. 3714, 1987, 44-45.
525. L. I. Bondarenko, and V. T. Soziev, "Ultrasonic Finish Turning of Machine Rolls", *Chemical and Petroleum Engineering*, Vol. 23, No. 9-10, 1988, 455-459.
526. J. Devine, "Ultrasonically Assisted Metal Removal, Fabrication of Composite Materials", *American Society for Metals*, Metals Park, Ohio, 1985, 329-334.
527. L. T. Buchek, and I. G. Tereshchenko, "Effect of Application of Ultrasound During Pressing on the Structure of Tungsten Carbide Base Materials", *Poroshk. Metall.*, Vol. 21, No. 9, 1982, 35-38.
528. S. P. Kundas, M. D. Travlovskii, and V. V. Bozhenkov, "Study of the Process of Hot Ultrasonic Flattening of Molybdenum Wires in a Vacuum", *Tsvetnye Metally*, No. 2, 1985, 74-77.
529. G. I. Eskin, P. N. Shvetsov, and A. I. Ioffe, "Relationship Between Cavitation and Decontamination During Ultrasonic Processing of Aluminum and its Magnesium Alloys", *Akademiia Nauk SSSR, Izvestiia, Metally*, 1972, 69-74.
530. V. I. Petukhov et al., "Ultrasonic Extrusion of Al", *Kuznechno-Shtamp Proizv.* (3), 1972, 5-7.
531. A. I. Baranov, and V. M. Rudyak, "Effect of Ultrasonic Vibrations of Polarization Switching Processes in Triglycine Sulfate Crystals at Different Temperatures", *Bulletin of the Academy of Science USSR Phys. Ser.*, Vol. 31, No. 11, 1967, 1808-1810.
532. D. A. Andreev, I. P. Ipatova, and A. V. Subashiev, "Scattering of Light by Phonon Zero Sound in Semiconductors", *Soviet Physics, Semiconductors*, Vol. 12, No. 8, 1978, 921-924.

533. J. Uchil, H. G. Shanbhogue, and G. K. M. Thutupalli, "Optical Properties and Durability of Thin Films Deposited on Vibrating Substrates at Ultrasonic Frequencies", *Thin Solid Films*, Vol. 170, No. 1, 1989, 27-34.
534. A. P. Zdebskii, S. S. Ostaoenko, A. U. Savchuk, and M. K. Sheinkman, "Ultrasonically Stimulated Transformation of the Luminescence and Acoustic Characteristics of CdS Single Crystals", *Pisma v Zh. Tekh Fizika*, Vol. 10, No. 19-20, 1243-1247.
535. N. S. Mitchell, B. M. Armstrong, H. S. Gamble, and J. Wakefield, "Low Resistance Polysilicon Interconnects with Self-Aligned Metal", *Journal of Vacuum Science and Technology*, Vol. 4., No. 3, 1986, 755-757.
536. A. P. Zdebskii, V. L. Korchnaya et al., "Ultrasonically Induced Changes in the Electrical and Luminescence Characteristics of InGaAs:Si Light-emitting Diodes", *Pisma v Zh. Tekh. Fizika*, Vol. 12, No. 1-2, 1986, 31-33.
537. A. P. Zdebskii, M. I. Lisyanskii et al., "Effect of Ultrasonic Processing on the Voltage-current and Noise Characteristics of GaAs Tunnel Diodes", *Pisma Zh. Tekh. Fizika*, Vol. 13, No. 15-16, 1987, 1009-1013.
538. G. Madore, and J. D. N. Cheeke, "Ultrasonic Effects in the Hopping Conductivity Regime of p-InSb at Low Temperatures", *Solid State Communications*, Vol. 49, No. 4, 1984, 331-333.
539. N. G. Einspruch, "Ultrasonic Effects in Semiconductors", *Solid State Physics, Advances in Research and Applications*, Vol. 17, Academic Press, New York, NY, 1965, 217-268.
540. H. R. Carleton, H. Kroger, and E. W. Prohofskey, "Ultrasonic Effects in Piezoelectric Semiconductors", *IEEE Proceedings*, Vol. 53, 1965, 1452-1464.
541. Air Force Systems Command, Foreign Technology Division, (Novocherkassk Polytechnic Institute), FTD-MT-65-485; AD-655021.
542. B. A. Agranat, and M. N. Dubrovin et al., "Fundamentals of Ultrasound Physics and Technology", *Izdatelstvo Vysshiaia, Shkola*, Moscow, USSR, 1987.
543. A. Shoh, "Future Prospects of Ultrasonics In Industry", *Ultrasonics International 1977*, IPC Science and Technology Press, Guildford, U. K., 1977, 75-90.
544. K. F. Graff, "Process Applications of Power Ultrasonic - A Review", *Ultrasonics Symposium Proceedings*, IEEE, New York, NY, 1974, 628-641.
545. V. G. Averianova, and P. E. Diachenko, and I. N. Mizorokhi, *Some Problems in Ultrasonic Processing of Materials*, Consultants Bureau Enterprises, Inc., New York, NY, 1964.
546. Department of Energy, Battelle Pacific Northwest Labs, Richland, WA, *Preliminary Overview of Innovative Industrial-Materials Processes*, PNL-4505, G. J. Hane, S. G. Hauser, D. E. Blahnik, D. E. Eakin, and W. E. Gurwell, 1983.

547. E. W. Bliss Co., Hastings, MI, "Budget Priced Machine Makes Welded 3-Piece Cans From Prefinished Aluminum", *Modern Metals*, Vol. 23, No. 2, 1967, 72.
548. V. I. Babitskii, "Theory of Percussive Vibrational Systems: Approximate Methods", *Izdatel'stvo Nauka*, Moscow, USSR, 1978.
549. A. A. Korichev, N. K. Simonov, V. V. Smorodinov, P. P. Chervinskiy, and K. K. Frolov, "New Types of Power Supplies for Ultrasonic Processing Equipment", *Izv. Vysshikh Uch. Zaved.: Elektromekhanika*, No. 9, 1984, 106-113.
550. B. A. Agranat, M. N. Dubrovin, N. N. Khavskii, and G. I. Eskin, "Fundamentals of Ultrasonic Physics and Technology", *Izdatel'stvo Vysshaia Shkola*, Moscow, USSR, 1987.
551. Taga Electric Co. Ltd., *Ultrasonic Processing Device*, S. Mishiro, November 30, 1983.
552. I. V. Petushko, "Design of Ultrasound Processing Units", *Soviet Electrical Engineering*, Vol. 58, No. 1, 1987, 76-80.
553. Bonnie Barmmer, Branson Ultrasonics Corporation, "Ultrasonics and Microprocessors Team-Up For Efficient Assembly", *Assembly Engineering*, Vol. 30, No. 11.

C. MICROWAVE EFFECTS

554. N. Taniguchi, K. Suimomura, and T. Miyazaki, "On the Electromagnetic Microwave Machining of Ceramic Wafers", *Bulletin of the Japanese Society of Precision Engineering*, Vol. 7, No. 2, 1973, 55-56.
555. K. Taniguchi, K., T. Shimomura, N. Miyazaki, and A. Tsuchiya, "A Study of Electromagnetic Microwave Machining Piercing Characteristics of Alumina Ceramics", *Rep. Inst. Phys. and Chem. Res.*, Vol. 48, No. 1, 1972, 11-19.
556. R. S. Brazis, J. K. Furdyna, and J. K. Pozela, "Microwave Effects in Narrow-Gap Semiconductors -- 2", *Physica Status Solidi (A) Applied Research*, Vol. 53, No. 1, 1979, 11-41.
557. V. N. Chupis, and L. I. Kats, "Impact Ionization Induced in Semiconductors by a Microwave Field in the Presence of an Arbitrarily Orientated Static Magnetic Field", *Soviet Physics, Semiconductors*, Vol. 17, No. 7, 1983, 814-817.
558. D. R. Elle, D. J. Fehringer, R. J. Vetter, and P. L. Ziemer, "Microwave Effects on Thermoluminescence and Thermally Stimulated Exoelectro. Emission", *IEEE Transactions on Microwave Theory and Techniques*, Vol. MTT-21, No. 12, 1973, 836-837.
559. J. M. Beall, and W. T. Anderson, "Circuit Response of GaAs MMIC and Bias Networks to Ionized Radiation Transients", *Proceedings - IEEE Military Communications Conference 1988*, IEEE, New York, NY, 1986.

560. A. F. Chamness, H. R. Scholes, S. W. Sexauer, and J. W. Frazer, "Metal Ion Content of Specific Area of the Rat Brain After 1600 MHz Radio Frequency Irradiation", *Journal of Microwave Power*, Vol. 11, No. 4, 1976, 333-338.
561. F. W. Cope, "Superconductivity -- A Possible Mechanism for Non-thermal Biological Effects of Microwaves", *Journal of Microwave Power*, Vol. 11, No. 3, 1976, 267-270.
- 561a. I. R. Chabinsky, "Applications of Microwave Energy, Past, Present, and Future, Brave New Worlds", Materials Research Society Symposium Proceedings: Microwave Processing of Materials, Vol. 124, 1988, 17-29.
- 561b. J. E. McGrath, "The Microwave Processing of Polymeric Materials", Final Report, U.S. Air Force Contract F33615-85-C-5153, July 1991.
- 561c. A. C. Metaxas and R. J. Meredith, "Industrial Microwave Heating", P. Peregrinus Ltd. (London) 1983, 27.
- 561d. W. H. Hayt, Jr., "Engineering Electromagnetics" (4th ed.), McGraw-Hill, New York, 1981, 392.
- 561e. A. C. Metaxas, and R. J. Meredith, *ibid.*, 72.
- 561f. A. C. Metaxas, and R. J. Meredith, *ibid.*, 80.
- 561g. R. W. Bruce, "New Frontiers in the Use of Microwave Energy: Power and Metrology", Materials Research Society Symposium Proceedings: Microwave Processing of Materials, Vol. 124, 1988, 6-7.
562. P. Colomban, and J. C. Badot, "Production of Superionic Conducting Anisotropic Ceramics ($\text{Na}^+ \text{Be TaAl}_2\text{O}_3$) by Microwave Heating", *Mater. Res. Bulletin*, Vol. 13, No. 2, 1978, 135-140.
563. Oak Ridge National Laboratory, Department of Energy, *Initial Results of a High-Power Microwave Sintering Experiment at ORNL*, CONF-860743-1, H. D. Kimrey, T. L. White, T. S. Bigelow, and P. F. Becher, 1986.
564. S. Das, and T. R. Curlee, "Microwave Sintering of Ceramics: Can We Save Energy?", *American Ceramic Society Bulletin*, Vol. 66, No. 7, 1987, 1093-1094.
565. M. E. Brodwin, and D. L. Johnson, "Microwave Sintering of Ceramics", 1988 *IEEE MTT-s International Microwave Symposium Digest: Microwaves- Past, Present, and Future*, IEEE, New York, NY, 1988, 287-288.
566. D. L. Johnson, W. B. Sanderson, J. M. Knowlton, E. L. Kemer, and M. Chen, "Advances in Plasma Sintering of Ceramics", *Ceramurgia*, Vol. 17, No. 5, 1987, 196-198.
567. D. W. Paul, Queen's University of Belfast, "Solid Phase Compaction of Polymeric Powders", *Dissertation Abstracts International*, Vol. 49, No. 10, 1989, 399.

568. T. T. Blake, R.D. Blake, and J. J. Petrovic, "Microwave Sintering of Al_2O_3 and Al_2O_3 -- SiC Whisker Composites", *Ceramic Engineering and Science Proceedings*, Vol. 8, No. 7-8, 1987, 861-871.
569. Oak Ridge National Laboratory, *Microstructure Evolution in Microwave Sintered Alumina*, CONF-880504-9, M. A. Janney, and H. D. Kimrey, 1988.
580. Oak Ridge National Laboratory, *Device for Microwave Sintering Large Ceramic Articles*, PAT-APPL-7-077 580, H. D. Kimrey, July 24, 1987.
581. Los Alamos National Laboratory, Department of Energy, *Microwave Sintering of Alumina-SiC Composites at 2.45 and 60 GHz*, LA-UR-88-597; CONF-880118-2, J. D. Katz, R. D. Blake, and J. J. Petrovic, 1988.
582. Oak Ridge National Laboratory, Department of Energy, *Techniques for Ceramic Sintering Using Microwave Energy*, CONF-871210-1, H. D. Kimrey, M. A. Janney, and P. F. Becher, 1987.
583. Army Research Office, *Microwave Sintering of Ceramics*, ARO-17377.1-MS, D. L. Johnson, and M. E. Brodwin, 1984.
584. C. E. Holcombe, T. T. Meek, and N. L. Dykes, "Unusual Properties of Microwave-sintered Ytria-2 wt.% Zirconia", *Journal of Material Science Letters*, Vol. 7, No. 8, 1988, 881-884.
585. Electric Power Research Institute, *Microwave Sintering of Ceramics*, EPRI-EM-5890, July 15, 1988.
586. M. E. Brodwin, and D. L. Johnson, "Microwave Sintering of Ceramics", *1988 IEEE MTT International Microwave Symposium Digest*, Vol. 1, IEEE, New York, NY, 1988, 287-288.
587. G. Desgardin, M. Aliouat, L. Mazo, and B. Raveau, "Microwave Sintering of Perovskite Type Materials for Capacitors", *Revue Generale Electr.*, No. 5, 1988, 33-37.
588. J. Wilson, and S. M. Kunz, "Microwave Sintering of Partially Stabilized Zirconia", *Journal of American Ceramic Society*, Vol. 17, No. 1, 1988, C40-C41.
589. H. D. Kimrey, M. A. Janney, and P. F. Becher, "Techniques for Sintering Using Microwave Energy", *12th International Conference on Infrared and Millimeter Waves*, IEEE, New York, NY, 1987, 136-137.
590. T. T. Meek, T. T., C. E. Holcombe, and N. Dykes, "Microwave Sintering of Some Oxide Materials Using Sintering Aids", *Journal of Material Science Letters*, Vol. 6, No. 9, 1987, 1060-1062.
591. M. Alliouat, L. Mazo, G. Desgardin, and B. Raveau, "Microwave Sintering of Lead-based Perovskite Ceramics for Capacitors", *Mater. Letters*, Vol. 5, No. 9, 1987, 328-332.
592. T. T. Meek, "Proposed Model for the Sintering of a Dielectric in a Microwave Field", *Journal of Material Science Letters*, Vol. 6, No. 6, 1987, 638-640.

593. E. L. Kemer, and D. L. Johnson, "Microwave Plasma Sintering of Alumina", *American Ceramic Society Bulletin*, Vol. 64, No. 8, 1985, 1132-1136.
594. W. R. Tinga, "Fundamentals of Microwave-Materials Interactions and Sintering", *Materials Research Society Symposium Proceedings: Microwave Processing of Materials*, Vol. 124, 1988, 33-44.
595. A. Gourdenne, D. LePen, and D. Douibi, "Curing Under Microwaves of Hollow Silica Beads - Epoxy Prepolymer Blends", *Polymer Preprints, Division of Polymer Chemistry*, American Chemical Society, Vol. 27, No. 2, ACS, Washington, D.C., 1986, 401-402.
596. I. J. Chabinsky, "Microwave Energy-enhanced Slip-casting System", *Ceramic Engineering and Science Proceedings*, Vol. 7, No. 11-12, 1986, 1229-1232.
597. T. T. Meek, and R. D. Blake, Department of Energy, *Ceramic Substrate Material*, Patent # GB 2173783 A, March 18, 1986.
598. T. T. Meek, R. D. Blake, J. D. Katz, J. R. Bradberry, and M. H. Brooks, "Cation Diffusion in Glass Heated Using 2.45 GHz Radiation", *Journal of Material Science Letters*, Vol. 7, No. 9, 1988, 928-931.
599. Y. P. Chen, J. F. Pollard, J. D. Graybeal, and T. C. Ward, "The Effect of Temperature and Cure on Dielectric Behavior of Epoxy Resin at Microwave Frequencies", *Polymer Preprints*, Vol. 29, No. 1, 1988, 207-209.
600. R. D. Blake, and T. T. Meek, *Method for Producing Ceramic-Glass-Ceramic Seals by Microwave Heating*, Patent # US 4606748, October 10, 1984.
601. Centre d'Etudes et de Recherches, *Polymerization of Epoxy Matrix Composites Using Pulsed Microwaves*, CERT-3/1324-MO; ETN-88-92162, H. Jullien, M. Delmotte, F. Thuillier, et al., Dec. 1986.
602. M. G. Hamlyn, A. L. Bowden, G. Jones, and S. M. Jackson, "Microwave Firing Process for Earthenware Ceramics", *Mikrowellen Mag.*, Vol. 15, No. 8, 1989, 605-607.
603. F. M. Thuillier, and H. Jullien, "Microwave Effects on Epoxy Resin/Carbon Black Composites", *Revue Generale de l'Electricite*, No. 5, App. Energie des Micro-ondes, France, 1987, 27-32.
604. A. Bialski, R. St. J. Manley, H. P. Schreiber, and M. P. Wertheimer, "Composite Materials with Microwaves - Plasma Treated Components: Treatment - Property Correlation", *Proceedings of the 10th Annual Microwave Power Symposium*, International Microwave Power Institute, Edmonton, Alberta, Canada, 1975, 222-226.
605. J. F. Kinstle, "Advances in Radiation Curing", *American Chemical Society, Division of Organic Coatings and Plastics Chemistry, Preprints*, Vol. 43, ACS, Washington, D.C., 1980, 126-129.

606. C. Gibson, I. Matthews, and A. Samuel, "Microwave Enhanced Diffusion in Polymeric Materials", *Journal of Microwave Powder and Electromagnetic Energy*, Vol. 23, No. 1, 1988, 17-28.
607. H. Jullien, and H. Valot, "Polyurethane Curing by a Pulsed Microwave Field", *Polymer*, Vol. 26, No. 4, 1985, 506-510.
608. Solar Energy Research Institute, *Feasibility Study of Microwave Application for Solar Cell Fabrication*, SERI/TR-8041-16-T2, S. Chitre, M. C. Keeling, Jan. 1982.
609. "Glass Fibres - The Secret of the Glass Skeins", *Funkschau*, No. 6, 1988, 46, 67-70.
610. D. C. Guidici, "Direct Coupled Microwave Thermal Processing For Photovoltaic Device Fabrication", *Proceedings of Melecon 1981, The First Mediterranean Electrotechnical Conference*, IEEE, New York, NY, 1981.
611. T. T. Chen, J. E. Durtizac, K. E. Haque, W. Wyslouzil, and S. Kashyap, "Relative Transparency of Minerals to Microwave Radiation", *Canadian Metallurgical Quarterly*, Vol. 23, No. 3, 1984, 349-351.
612. Oesterreichisches Forschungszentrum Seibersdorf G.m.b.H., *Production of HTR-Fuel Kernels by Microwave Hardening of Aqueous Metal-salt-resin Droplets*, OEFZS-4080; CH-228/81, K. Knotik, P. Leichter, E. Bonek, G. Magerl, and H. Huschka, April 1981.
- 612a. "Gyratron Microwave Processing", Project Summary, USP Holdings, Ann Arbor, MI, April 1991.

D. MAGNETIC FIELD EFFECTS

613. T. Kozkua, S. Asai, and I. Muchi, "Fracture Resistance Measurement Procedure for Brittle Materials", *Transactions of the Iron and Steel Institute of Japan*, Vol. 28, No. 2, 1987, B. 80.
614. H. Futterer, T. Yohannes, H. Bach, J. Pelzl, and K. Nahm, "Magnetic Field Dependence of the Elastic Constants in Nd_3Se_4 ", *Journal of Applied Physics*, Vol. 63, No. 8, pt. 2B, 1988, 3933.
615. S. Kiss, L. Malkinski, G. Posgay, and L. Pogany, "Influence of Tensile Stresses on Magnetic Field Dependence of Internal Friction and of Shear Modulus of the Fe-Si-B Metallic Glass", *Acta Phys. Pol. A*, Vol. A76, No. 1, Poland, 1989, 157-161.
616. A. I. Tananov, N. N. Beklemishev, B. N. Zhurkin, V. S. Akinshin, and A. E. Gorskii, "Methods of Evaluating the Mechanical Properties of Metallic Materials Subjected to Electric Effects", *Zavodskaiia Laboratoriia*, Vol. 49, 1983, 59-66.

617. J. Jarzynski, J. H. Cole, J. A. Bucaro, and C. M. Davis, Jr., "Magnetic Field Sensitivity of an Optical Fiber with Magnetostrictive Jacket", *Applied Optics*, Vol. 19, No. 22, 1980, 3746-3748.
618. V. E. Gul, N. N. Turkova, and M. G. Golubeva, "On the Increase in Strength of Electrically Conductive Polymer Film with Metallic Filler Under the Influence of a Static Magnetic Field", *Dokl. Akad. Nauk.*, Vol. 199, No. 1, SSSR, 1971, 135-137.
619. Z. Rigbi, and J. E. Mark, "Effects of a Magnetic Field Applied During the Curing of a Polymer Loaded with Magnetic Filler", *Journal of Polymer Science, Polymer Physics Edition*, Vol. 23, No. 6, 1985, 1267-1269.
620. Y. P. Rodin, Y. M. Molchanov, and N. V. Kharitonova, "Anisotropy of Strength Properties of Plastics and Their Components Treated in a Magnetic Field", *Mechanics of Composite Materials*, Vol. 20, No. 3, 1984, 367-372.
621. Y. V. Efimov, T. M. Shkatova, and V. N. Dmitriev, "Ultrafast Hardening in Magnetic Fields", *Metallofizika*, Vol. 9, No. 1, USSR, 1987, 33-36.
622. V. N. Chachin, A. L. Skripnichenko, V. V. Kunitsky, and B. I. Gorbachev, "Some Characteristics of the Behavior of Metal in Magnetic-Pulse Expansion", *Izv. Akad. Nauk. Beloruss SSR Fiz. Tekhn.*, (4), 1971, 28-31.
623. Lawrence Livermore Laboratory, *Evaluation of Metal-Foil Strain Gauges for Cryogenic Application in Magnetic Fields*, CONF-770801-13, H. S. Freynik, Jr., D. R. Roach, D. W. Deis, and D. G. Hirzel, July 8, 1977.
624. A. I. Taub, and P. G. Frishmann, "Effect of a Magnetic Field on Flow of Amorphous Alloys", *Scr. Metall.*, 16, (11), 1982, 1267-1268.
625. R. Indrukhya, M. K. Muju, and K. S. Ram, "A Study of Material Transfer Under the Influence of a Magnetic Field By the PIXE Technique", *Transactions of the American Nuclear Society*, Vol. 56, 1988, 252-253.
626. L. T. Baczewski, Z. Kaczkowski, and E. Lipinski, "Delta E-Effect and Internal Friction in Co-Si-B Metallic Glasses", *Journal of Magnetism and Magnetic Materials*, Vol. 41, No. 1-3, 1984, 346-348.
627. N. Kasai, A. Nakamura, H. Sasaki, and H. Nakamura, "Magnetic Effects of Building Materials for a Non-Magnetic Building and Distribution of Earth-Magnetic Field", *Bulletin of the Electrotechnical Laboratory*, Vol. 47, No. 1, 1983, 40-55.
628. Y. P. Rodin, Y. Molchanov, and N. V. Kharitonova, "Anisotropy of Strength Properties of Plastics and Their Components Treated in a Magnetic Field", *Mech. Comp. Mater.*, Vol. 20, No. 3, 1984, 367-372.
629. T. A. Manko, A. N. Kvasha, A. V. Solovev, and I. M. Ermolaev, "Change in Structure and Physio-Mechanical Properties of Polymer Materials Under the Action of a Constant Magnetic Field", *Elektron. Obrab. Mater.*, No. 5, 1982, 41-42.
630. A. D. Stadnik, and F. D. Miroshnichenko, "Effect of a Constant Magnetic Field on Certain Properties of Polymers", *Polym. Mech.*, Vol. 14, No. 2, 1978, 280-281.

631. V. F. Belostotskii, V. A. Demkin, and I. G. Polotskii, "Reduction of Fatigue Life of Nickel in Constant Magnetic Field at Low Temperatures", *Metallofizika*, Vol. 7, No. 3, Kiev, USSR, 1985, 113-114.
632. V. I. Kononenko, and V. V. Pustovalov, "Effect of a Constant Magnetic Field on the Yield Stress of Nickel at 4.2 Degrees K", *Soviet Journal of Low Temperature Physics*, Vol. 2, No. 2, 1976, 132-135.
633. E. S. Makarov, and L. A. Tolokonnikov, "Equations of the Theory of a Magnetoplastic Isotropic Dilatant Medium", *Mechanics of Solids*, Vol. 18, No. 5, 1983, 188-190.
634. F. M. Wagner, and H. Markert, "Reactivation of the Magnetic Aftereffect of Nickel Single Crystals by Means of Plastic Deformation", *ACTA Metall.*, Vol. 27, No. 6, 1979, 951-957.
635. D. N. Bolshutkin, V. A. Desnenko, and V. Y. Ilychev, "Magnetoplastic Effect and Eddy Current Heating", *Soviet Journal of Low Temperature Physics*, Vol. 2, No. 12, 1976, 1544-1550.
636. I. A. Gindin, I. S. Lavrinenko, and I. M. Neklyudov, "Influence of a Magnetic Field on the Creep of Nickel", *Soviet Physics - Solid State*, Vol. 18, No. 4, 1976, 682-683.
637. H. H. Liebermann, and C. D. Graham, Jr., "Magnetoplastic Deformation of Dy Crystals", *American Institute of Physics Conference Proceedings*, No. 29, 1976, 598-599.
638. Y. G. Gagen, and T. A. Martynyuk, "The Effects of the Parameters of Longitudinal Magnetic Fields on the Structure and Mechanical Properties of Welded Joints in Gas and Oil Main", *Avtom. Svarka*, No. 9, 1978, 37-38.
639. D. Y. Tzou, "Intensification of Externally Applied Magnetic Field Around a Crack in Layered Composite", *Theoretical and Applied Fracture Mechanics*, Vol. 4, No. 3, 1985, 191-199.
640. I. A. Gidin, I. S. Lavrinenko, and I. M. Neklyudov, "Magnetoplastic Effect in Dysprosium", *Soviet Physics, Solid State*, Vol. 16, No. 6, 1974, 1084-1086.
641. A. I. Akhiezer, V. P. Demutskii, and R. V. Polovin, "Theory of Magnetoplasticity", *Physics of Metals and Metallography*, Vol. 23, No. 5, 1967, 71-74.
642. A. I. Akhiezer, V. P. Demutskii, and R. V. Polovin, "Stresses and Waves in a Magnetoplastic Medium, High-Frequency Properties of Plasma", *Izdatelstvo Naukova Dumka*, 1968, 197-202.
643. I. A. Gindin, I. S. Lavrinenko, and I. M. Neklyudov, "Magnetoplastic Effect in Polycrystalline Ni", *Soviet Physics - Solid State*, Vol. 15, No. 2, 1973, 451.
644. A. L. Skripnichenko, A. G. Yaskovich, and B. A. Meleshchenko, "Strength of Metals Under Exposure to a Pulsed Magnetic Field", *Vestsi Akad. Navuk BSSSR, Fiz.-Tekh.*, (4), 1985, 12-16.

645. V. P. Lebedev, and V. S. Krylovskii, "Flow Stress of Aluminum, Lead and Indium in a Strong Magnetic Field", *Phys. Met. Metallogr.*, Vol. 58, No. 4, 1984, 186-189.
646. B. Fultz, and J. W. Morris, Jr., "Effects of High Magnetic Fields on the Flow Stress of 18-8 Stainless Steels", *Acta Metall.*, Vol. 34, No. 3, 1986, 379-384.
647. V. N. Pustovoi, and A. I. Smolyaninov, "Influence of Heat Treatment in a Magnetic Field on the Mechanical Properties of Steel 7Kh3", *Izv. V.U.Z. Chernaya Metall.*, (11), 1983, 104-107.
648. Y. I. Golovin, V. M. Ivanov, and V. A. Kiperman, "Mechanisms of Failure in Pre-cracked Metal (Sheet) Specimens Placed in Electromagnetic Fields", *Fizika i Khim. Obrab. Mater.*, (6), 1983, 64-69.
649. V. P. Lebedev, and K. K. Le, "Softening of Lead in a Dynamic Intermediate State", *Soviet Physics, Solid State*, Vol. 25, No. 1, 1983, 125-127.
650. R. P. Reed, J. M. Arvidson, J. W. Ekin, and R. H. Schoon, "Magnetic Field Effects on Tensile Behavior of Alloys 304 and 310 at 4K", *Materials Studies for Magnetic Fusion Energy Application at Low Temperatures*, Vol. 71-83, National Bureau of Standards, Fracture and Deformation Division, Boulder, CO, 1982.
651. A. P. Yakovlev, "An Apparatus for Studying the Effect of a Magnetic Field on the Mechanical Characteristics of Materials", *Mechanical Testing of Structural Alloys at Cryogenic Temperatures*, *Naukova Dumka*, 1982, 31-42.
652. K. I. Arai, and N. Tsuya, "Magnetomechanical Coupling Factor in Amorphous Fe₈₁(Si,B,C)₁₉ Ribbons", *Structure and Properties of Amorphous Metals II*, Research Institutes, Tohoku University, Sendai, Japan, 1980, 247-250.
653. V. I. Gostishchev, R. A. Glinik, M. D. Petrovskii, and V. N. Khazov, "Effect of Magnetic Field on the Plastic Deformation of Aluminum at 4.2 degree K", *JETP Letters*, Vol. 30, No. 2, 1979, 92-96.
654. S. T. Alhassani, "Electrodynamics of a Thick Walled Tube Containing a High Intensity Sinusoidally Varying Magnetic Field", *Proceedings of the 6th International Conference on High Energy Rate Fabrication*, 1977, 4.2.1-4.2.14.
655. D. N. Bolshutskin, V. A. Desnenko, and V. Y. Ilichev, "Low Temperature Plastic Deformation of Fe-Cr-Ni Steels in Magnetic Fields to 2.71×10^3 A.m exp-1", *Cryogenics*, Vol. 19, No. 4, 1979, 231-234.
656. D. N. Bolshutskin, V. A. Desnenko, and V. Y. Ilichev, "Low Temperature Plastic Deformation of Nickel in Magnetic Fields up to 34 kOe", *Soviet Journal of Low Temperature Physics*, Vol. 2, No. 2, 1976, 129-131.
657. V. Ramakrishnan, and A. Ghosh, "Effect of an External Magnetic Field on Some Mechanical Properties of Metglas 2826 MB", *Wear*, Vol. 69, No. 1, 1981, 71-80.
658. K. Kumagai, "Effects of Magnetic Fields on Wear of Ferromagnetic Materials", *Bulletin of Japanese Society of Precision Engineering*, Vol. 19, No. 1, 1985, 43-48.

659. K. Hiratsuka, T. Sasada, and S. Norose, "Magnetic Effect on Wear of Metals", *Proceedings of the JSLE International Tribology Conference*, Elsevier Science Publishing Co., New York, NY, 1985, 159-164.
660. K. Hiratsuka, T. Sasada, and S. Norose, "The Magnetic Effect on the Wear of Metals", *Wear*, Vol. 110, No. 3-4, 1986, 251-261.
661. D. N. Garkunov, G. I. Suranov, and G. B. Koptyaeva, "The Nature of the Increase in the Wear Resistance of Components and Tools by Magnetic Treatment", *Trenie Iznos*, Vol. 3, No. 2, 1982, 327-330.
662. M. K. Muju, and A. Ghosh, "A Model for Cross Diffusion Across a Sliding Contact in the Presence of a Magnetic Field", *Wear*, Vol. 53, No. 1, 1979, 35-42.
663. Y. S. Yang., and Z. H. Li, "Effect of Composite Magnetic Annealing in Amorphous Alloys", *IEEE Transactions on Magnetics*, Vol. MAG-18, No. 6, 1982, 1397-1399.
664. E. P. Wohlfarth, "High Magnetic Field Effects in Some Metallic Magnetic Materials", *Journal of Magnetism and Magnetic Materials*, Vol. 20, No. 1, 1980, 77-83.
665. S. Roth, "Stability of Magnetic Field Induced Anisotropy in Amorphous Fe-B-Si Alloys with Different Additions", *Key Engineering Materials*, Trans. Tech. Publications, Aedermannsdorf, Switz., 1990, 363-367.
666. I. A. Manko, A. N. Kvasha, A. V. Solovev, and I. M. Ermolaev, "Variation of the Structure and Physiomechanical Properties of Polymeric Materials Under the Action of a Constant Magnetic Field", *Elektronnaya Obrabotka Materialov*, Vol. 107, No. 5, 1982, 41-42.
667. P. R. Sahm, and H. R. Fillias, "Directional Solidification of Eutectic and Off-Eutectic Au-Co Composites With and Without Magnetic Field", *Journal of Material Science*, Vol. 5, No. 12, 1970, 1027-1036.
668. S. K. Yaremkevich, "Investigation of the Effect of Thermomagnetic Treatment on Structure Changes and Properties of Alnico Alloys", *IEEE Transactions on Magnetics*, Vol. MAG-6, No. 2, IEEE, New York, New York, 1970, 304.
669. K. I. Arai, N. Tsuya, M. Yamada, and T. Masumoto, "Giant Delta E Effect and Magnetomechanical Coupling Factor in Amorphous Fe₉₀P₁₃C₇ Ribbons", *IEEE Transaction Magnetic*, Vol. MAG-12, No. 6, IEEE, New York, NY, 1976, 936-938.
670. W. P. Wolf, "Field Induced Magnetic Phase Transitions in DAG", ARO-9960.6-P, 1975.
671. A. N. Gerasimovich, and Y. G. Rumyantsev, "On the Increased Value of the Magnetic Flux, Temperature and Losses in the Metallic Bar Sections Situated above Phase C of a Current Conductor", *Izv Vyssh Uchebn Zaved, Energ*, No. 12, 1972, 33-39.

672. V. V. Eremenko, K. L. Dudko, Yu. G. Litvinenko, and N. F. Kharchenko, "Magnetic and Magneto-optical Effects Under Phase Transition in Antiferromagnets", *IEEE Transactions on Magnetics*, Vol. MAG-8, No. 3, 1972, 645-646.
673. T. Kakeshita, K. Shimizu, T. Sakakibara, S. Funada, and M. Date, "Magnetic Field-Induced Martensitic Transformation in an Fe-31.7 at Percent Ni Alloy", *Trans. Japanese Institute of Met.*, Vol. 24, No. 11, 1983, 748-753.
674. V. P. Naberezhnykh, S. K. Krysova, V. I. Krysov, and I. N. Moshenskaya, "Structure of Amorphous Alloys Ni₈₀P₂₀ and Co₈₃P₁₇ Electrodeposited in a Magnetic Field", *Izv. Akad. Nauk. SSSR Met.*, No. 3, 1986, 184-188.
675. M. Naoe, N. Kitamura, and H. Ito, "Improvement of the C/N Ratio and Corrosivity of TbFeCo Amorphous Films by Controlling Their Microstructure", *Journal of Applied Physics*, Vol. 63, No. 8, pt. 2B, 1988, 3850-3852.
676. K. Zdunek, "Properties of Alnico Magnet Layers Produced by Pulse Plasma Method", *5th International Congress on Heat Treatment of Material*, Vol. 1, International Federation for the Heat Treatment of Materials, 1986, 670-675.
677. E. M. Savitsky, J. V. Jefimov, B. P. Michailov, M. I. Bychkova, and R. S. Torchinova, "Influence of Extreme External Conditions on Microstructure and Properties of Alloys Having Special Physical Properties", *Zeitschrift für Metallkunde*, Vol. 74, No. 7, 1983, 411-418.
678. Y. Iye, L. E. McNeil, G. Dresselhaus, G. S. Boebinger, and P. Berglund, "Electronic Phase Transition in Graphite under Strong Magnetic Field", *Proceedings of the 17th International Conference on the Physics of Semiconductors*, Springer-Verlag, New York, NY, 1985, 981-984.
679. Y. M. Molchanov, E. R. Kisis, and Y. P. Rodin, "Changes in the Structure of Polymeric Materials in a Magnetic Field", *Polym. Mech.*, Vol. 9, No. 4, 1973, 646-649.
680. M. G. Martl, and K. Hummel, "Polymeric Materials in Magnetic Fields", *Kautschuk und Gummi Kunststoffe*, Vol. 39, No. 12, 1986, 1182-1185.
681. T. A. Manko, A. N. Kvasha, A. V. Solovev, and I. M. Ermolaev, "Change in Structure and Physico-Mechanical Properties of Polymer Materials Under the Action of a Constant Magnetic Field", *Elektron. Orab. Mater.*, No. 5, 1982, 41-42.
682. Y. P. Rodin, and Y. M. Molchanov, "Orientation of Molecules of Epoxide Oligomers in a Uniform Stationary Magnetic Field", *Mekh. Kompozitnykh Materials*, Vol. 18, no. 6, 1982, 1056-1059.
683. F. S. Roig, and J. E. Schoutens, "Longitudinal Electrical Conductivity of Metal-Matrix Composites At Cryogenic Temperatures in the Presence of a Longitudinal Magnetic Field", *Journal of Materials Science*, Vol. 22, No. 10, 1987, 3749-3754.
684. V. M. Polyanovskii, "Longitudinal Magnetoresistance in Superlattice Semiconductors", *Soviet Physics, Semiconductors*, Vol. 18, No. 10, 1985, 1142-1144.

685. A. Sternberg, L. Shebanov, and A. Kepeniaks, "Influence of Irradiation and Permanent Magnetic Field on Physical Properties of PLZT and PSN Transparent Ferroelectric Ceramics", *Ferroelectrics, Letters Section*, Vol. 2, No. 2, 1984, 5-8.
686. V. F. Belostotskii, "Effect of DC Magnetic Field on the Electrical Resistivity with Low-temperature Ultrasound Deformation", *Soviet Journal of Low Temperature Physics*, Vol. 6, No. 2, 1980, 248-251.
687. E. M. Savitskii, R. S. Torchinova, and S. A. Turanov, "Effect of Magnetic Field on the Crystallization Process and Magnetic Properties of Manganese - Bismuth Alloys", *Dokl. Akad. Nauk. SSSR*, Vol. 253, No. 3, 1980, 594-597.
688. W. Wolf., "Magnetic Properties of Amorphous $(\text{Fe,Ni})_{80}\text{P}_{14}\text{B}_6$ and $(\text{Fe,Ni})_{83}\text{B}_{15}\text{C}_2$ Alloys", *Journal of Magnetism and Magnetic Materials*, 9, (1/3), 1978, 200-202.
689. R. Barrue, J. C. Perron, and J. Robert, "Influence of Magneto-Thermal Treatment on the Magnetic Performance of Cobalt Basis Amorphous Alloys. Applications of Magnetic Fields", *Review of Physics Applications*, Vol. 22, No. 6, 1987, 399-405.
690. R. Barrue, J. Bigot, J. C. Faugieres, J. C. Perron, J. F. Rialland, J. Robert, and F. Schwartz, "Influence of Substitutional Elements on Magnetic and Thermal Properties of Amorphous $\text{Fe}_{79}\text{B}_{16}\text{Si}_5$ Ribbons", *Physics Scr.*, Vol. 37, No. 3, 1988, 356-358.
691. J. Park, and H. Kim, "Effects of Nb Addition and Annealing on the Magnetic Properties of Fe-Ni-Nb-Si-B Amorphous Alloys", *Journal of the Korean Institute of Met.*, Vol. 27, No. 7, 1989, 619-624.
692. L. T. Kabacoff, and M. Wun-Fogle, "Magnetomechanical Properties of Flash Annealed Metglas 2605 SC", *Journal of Applied Physics*, Vol. 57, No. 8, pt. 2A, 1985, 3499-3501.
693. Z. Kaczkowski, "Heat Treatment, Thickness, and Magnetomechanical Coupling Coefficient of the $\text{Fe}_{79}\text{Si}_{12}\text{B}_9$ Metallic Glasses", *Key Engineering Materials*, Vol. 40-41, 1990, 345-349.
694. Z. Kaczkowski, and L. Malkinski, "Annealing Effect on Elasticity of the $\text{Fe}_{78}\text{Si}_8\text{B}_{14}$ Metallic Glass", *Journal of Magnetism and Magnetic Materials*, 1990, 365-366.
695. H. Kronmuller, and N. Moser, "Magnetic After-Effects and the Hysteresis Loop", *Amorphous Metallic Alloys*, Butterworths, London, 1983, 341-359.
696. R. Hasegawa, *High Frequency Magnetic Properties and Magnetic Stability of Metallic Glasses*, Pergamon Press, Headington Hill Hall, Oxford, 1986, 196-203.
697. K. Makela, T. Tiainen, and P. Kettunen, *The Optimization of Amorphous Materials for Toroidal Transformer Cores*, Martinus Nijhoff Publishers, Dordrecht, The Netherlands, 1986, 276-279.

698. V. I. Borisova, T. V. Efimova, S. V. Zolkina, L. A. Olikhovskaya, V. V. Polotnyuk, K. V. Chuistov, and A. M. Shalayev, "The Change in Magnetic Properties of Metallic Glasses During Crystallization", *Phys. Met.*, Vol. 5, No. 4, 1985, 680-685.
699. J. Fink-Finowicki, B. Lisowski, S. M. Zakharov, and L. Zaluski, "Field Induced Magnetic Anisotropy in Co-based Amorphous Alloy", *Acta Phys. Pol. A*, Vol. A76, No. 1, 1989, 167-170.
700. A. Hernando, C. Aroca, and V. Madurga, "Transverse Susceptibility and Magnetization of Transverse Field Annealed Metglas 2605CO", *Journal of Applied Physics*, 1982, 2297.
701. W. Grimm, B. Metzner, and A. Hubert, "Optimized Domain Pattern in Metallic Glasses Prepared by Magnetic Field Heat Treatment and/or Surface Crystallization", *Journal of Magnetism and Magnetic Materials*, Vol. 41, No. 1-3, 1984, 171-174.
702. Y. Makino, K. Aso, S. Uedaira, M. Hayakawa, Y. Ochiai, and H. Hotai, "Induced Magnetic Anisotropy of Co-Based Amorphous Alloys", *Journal of Applied Physics*, Vol. 52, No. 3, Pt.2, 1981, 2477-2479.
703. V. Druzhinin, A. I. Pavlovskii, and O. M. Tatsenko, "Possible Effects in Solids in Ultrastrong Magnetic Fields", *Journal of Applied Mechanics and Technical Physics*, Vol. 25, No. 6, 1985, 825-828.
704. A. Maziewski, and A. Stankiewicz, "Magnetic Field Induced Changes of Domain Structure Grating", *Proc. SPIE - International Society of Optical Engineering*, Vol. 859, 1988, 206-215.
705. V. S. Bobrov, and M. A. Lebedkin, "The Weakening of Nickel Single Crystals During the Rearrangement of the Domain Structure in a Magnetic Field", *Fizika Tverdogo Tela*, Vol. 27, No. 3, 1985, 820-824.
706. S. A. Flerova, O. E. Bochkov, and I. L. Tsinman, "Influence of Magnetic Field on the Ferroelectric Phase Transition in Barium Titanate", *Fiz. Tverdogo Tela*, Vol. 24, No. 8, 1982, 2505-2507.
707. L. C. Brunel, G. Landwehr, A. Bussmann-Holder, H. Bilz, and M. Balanski, "Influence of Strong Magnetic Fields on Ferroelectric Phase Transitions", *Journal of Physics Colloquium*, Vol. 42, No. C-6, 1981, 412-414.
708. T. Kakeshita, H. Shirai, K. Shimizu, and K. Sugiyama, "Effect of Magnetic Fields on Martensitic Transformations in Alloys with a Paramagnetic to Antiferromagnetic Transition in the Austenitic State", *Transactions of the Japan Institute of Metals*, Vol. 29, No. 7, 1988, 553-560.
709. A. Kawashima, K. Asami, T. Sato, and K. Hashimoto, "Electromagnetic Filtration Characteristics of Amorphous Alloys For Purification of Water Contaminated With Iron Rusts", *Rapidly Quenched Metals, Proceedings of the Fifth International Conference*, North-Holland, Amsterdam, Netherlands, 1985, 1671-1674.

710. D. Karpinos, G. I. Yaglo, L. M. Apiniskaya, N. F. Efremova, and Y. A. Maksimenko, "Magnetic Orientation of Fine Particles in Composite Materials", *Soviet Powder Metallurgy and Metal Ceramics*, Vol. 21, No. 6, 1982, 490-493.
711. Z. Heni, S. Eliezer, and A. Zigler, "Increase of Energy Storage in Metals Without a Significant Decrease in Electrical Conductivity", *Journal of Physics D: Applied Physics*, Vol. 22, No. 7, 1989, 997-1000.
712. B. Fitzke, "Determining the Admissible Effect of Magnetic Force on Electric Heating Elements", *Elektrowaerme International, Edition B: Industrielle Electrowaerme*, Vol. 47, No. 2, 1989, 100-106.
713. W. Dawihl, and W. Eicke, "Fabrication and Properties of Carbon-Containing Iron Fibers and Fiber Sinter Bodies", *Deutsche Gesellschaft fuer Metallkunde*, 1971, 61-68, 71-86.
714. L. Dobrescu, N. Muresan, and A. Bogdan, "Effect of the Dispersing Reagents in Magnetic Cleaning Processes of Some Clay Raw Materials by High Gradient Magnetic Separators (H.G.M.S.)", *Editions GEDIM*, St. Etienne, France, 1985, 343-353.
715. L. N. Hjellming, and J. S. Walker, "Isothermal Motion in a Liquid-Encapsulated Czochralski Crystal Puller with an Axial Magnetic Field", *PhysicoChemical Hydrodynamics*, Vol. 10, No. 1, 1988, 107-131.
716. "Vacuum Metallizing With Closed Field Sputtering (CFS) Equipment", *Prod. Finish*, 36, (9), 1983, 25-26.
717. Foreign Technology Division, *Method of Obtaining Polymeric Materials*, FTD-ID(RD)R-1125-87, V. A. Berestnew, Nov. 4, 1987.
718. S. H. Chan, "Investigation of Silica Fouling and Its Prevention by Magnetic Devices", Ongoing Research by University of Wisconsin, Milwaukee, for National Science Foundation, Div. of Chemical and Thermal Systems.
719. W. N. Kestelmann, S. S. Negmatow, and C. U. Sadykow, "Investigation of the Properties of Plastic Coatings Modified by a Magnetic Field", *Plaste und Kautsch*, Vol. 27, No. 8, 1980, 448-451.
720. K. Kondo, Y. Sata, K. Miyasato, H. Takezoe, A. Fukuda, E. Kuze, K. Flatischler, and K. Sharp, "Magnetic Field Effects on Preparing Thin Homogeneous Ferroelectric Smectic Cells for Electro-Optical Microsecond Switches", *Japan Journal of Applied Physics, Part 2*, Vol. 22, No. 1, 1983, L13-L15.
721. M. E. Gray, and I. R. Harrison, "Influence of Low Magnetic Fields on Semiconductors", *Journal of Applied Polymer Science*, Vol. 28, No. 11, 1983, 3603-3606.
722. B. S. Monozon, "Effects of Modulation of a Magnetic Field on the Absorption of Light in Optically Anisotropic Semiconductors", *Soviet Physics, Semiconductors*, Vol. 13, No. 7, 1979, 808-810.

723. S. K. Aorara, G. S. Trivikrama Rao, and E. M. Uyukin, "Influence of Magnetic Field on the Photorefractive Effect in LiNb₃ Crystals", *Pramana*, Vol. 24, No. 3, 1985, 521-525.
724. N. Geacintov, M. Pope, and F. Vogel, "Effect of Magnetic Field on the Fluorescence of Tetracene Crystals. Exciton Fission.", *Physics Review Letters*, Vol. 22, No. 12, 1969, 593-6.
725. V. V. Eremenko, E. V. Matyushkin, V. V. Shapiro, and R. Y. Bron, "Mechanism of Magnetic Field Induced Enhancement of Luminescence in Antiferromagnets", *Soviet Journal of Low Temperature Physics*, Vol. 3, No. 1, 1977, 61-63.
726. O. S. Eritsyian, "Optical Properties of Magnetic Crystals with a Natural Optical Activity", *Soviet Physics, Solid State*, Vol. 19, No. 9, 1977, 1491-1494.
727. L. E. Schmutz, G. Dresselhaus, and M. S. Dresselhaus, "Optical Absorption of EuTe in High Magnetic Fields", *Solid State Community*, 28, (8), 1978, 597-600.
728. F. Canal, "Influence of a Magnetic Field on the Optical Properties of BaTiO₃", *Conference on Electrical Insulation and Dielectric Phenomena*, IEEE, New York, 1984, pp. 523-527.
729. E. Iacopini, G. Stefanini, and E. Zavattini, "Effects of a Magnetic Field on the Optical Properties of Dielectric Mirrors", *Applied Physics A: Solids and Surfaces*, Vol. A32, No. 2, 1983, 63-67.
730. D. Halliday, and R. Resnick, *Physics, Part 1-2*, John Wiley & Sons, Inc., New York, NY, 1978, 14-15.
731. F. J. Williams, Thesis, Department of Mechanical Engineering, M.I.T., 1979.